



US 20190044072A1

(19) **United States**

(12) **Patent Application Publication**
Sim et al.

(10) **Pub. No.: US 2019/0044072 A1**

(43) **Pub. Date: Feb. 7, 2019**

(54) **CONDENSED-CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

(71) Applicant: **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si (KR)

(72) Inventors: **Munki Sim**, Yongin-si (KR); **Junha Park**, Yongin-si (KR); **Hyoyoung Lee**, Yongin-si (KR); **Youngkook Kim**, Yongin-si (KR); **Seokhwan Hwang**, Yongin-si (KR)

(21) Appl. No.: **15/866,885**

(22) Filed: **Jan. 10, 2018**

(30) **Foreign Application Priority Data**

Aug. 4, 2017 (KR) 10-2017-0099082


Publication Classification

(51) **Int. Cl.**
H01L 51/00 (2006.01)
H01L 51/50 (2006.01)
H01L 51/52 (2006.01)
C07D 471/04 (2006.01)
C07F 9/53 (2006.01)

(52) **U.S. Cl.**
 CPC *H01L 51/0072* (2013.01); *H01L 51/506* (2013.01); *H01L 51/5262* (2013.01); *H01L 51/5064* (2013.01); *C07D 471/04* (2013.01); *H01L 51/0067* (2013.01); *H01L 51/5088* (2013.01); *H01L 51/5012* (2013.01); *H01L 51/5016* (2013.01); *H01L 51/5072* (2013.01); *H01L 51/5092* (2013.01); *H01L 2251/552* (2013.01); *H01L 51/5056* (2013.01); *C07F 9/5325* (2013.01)

(57) **ABSTRACT**
 A condensed cyclic compound and an organic light-emitting device, the compound being represented by Formula 1:

<Formula 1>



10

190
150
110

FIG. 1

10

190
150
110

FIG. 2

20

190
150
110
210

FIG. 3

30

220
190
150
110

FIG. 4

40

220
190
150
110
210

**CONDENSED-CYCLIC COMPOUND AND
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME**

CROSS-REFERENCE TO RELATED
APPLICATION

[0001] Korean Patent Application No. 10-2017-0099082, filed on Aug. 4, 2017, in the Korean Intellectual Property Office, and entitled: “Condensed-Cyclic Compound and Organic Light-Emitting Device Including the Same,” is incorporated by reference herein in its entirety.

BACKGROUND

1. Field

[0002] Embodiments relate to a condensed cyclic compound and an organic light-emitting device.

2. Description of the Related Art


[0003] Organic light-emitting devices are self-emission devices that produce full-color images, and also have wide viewing angles, high contrast ratios, short response times, and excellent characteristics in terms of luminance, driving voltage, and response speed, compared to other devices.

[0004] An example of such organic light-emitting devices may include a first electrode located on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode, which are sequentially located on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, recombine in the emission layer to produce excitons. These excitons transit from an excited state to a ground state, thereby generating light.

SUMMARY

[0005] Embodiments are directed to a condensed cyclic compound and an organic light-emitting device.


[0006] The embodiments may be realized by providing a condensed cyclic compound represented by Formula 1:



<Formula 1>

[0007] wherein, in Formula 1, A_1 is a benzene ring or a naphthalene ring, R_1 to R_7 are each independently selected from a group represented by Formula 2, hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group,

a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_1)(Q_2)(Q_3)$, $-B(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-N(Q_1)(Q_2)$, $-P(=O)(Q_1)(Q_2)$, $-P(=S)(Q_1)(Q_2)$, $-S(=O)(Q_1)(Q_2)$, and $-S(=O)_2(Q_1)(Q_2)$, provided that at least one of R_1 to R_7 is a group represented by Formula 2,



<Formula 2>

[0008] wherein, in Formulae 1 and 2, $b7$ is an integer of 1 to 6, and when $b7$ is 2, 3, 4, 5, or 6, the $R_7(s)$ are identical to or different from each other, L_{21} is a single bond, a substituted or unsubstituted C_5 - C_{60} carbocyclic group, or a substituted or unsubstituted C_1 - C_{60} heterocyclic group, $a21$ is an integer of 1 to 5, and when $a21$ is 2, 3, 4, or 5, the $L_{21}(s)$ are identical to or different from each other, Ar_{21} is selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_1)(Q_2)(Q_3)$, $-B(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-N(Q_1)(Q_2)$, $-P(=O)(Q_1)(Q_2)$, $-P(=S)(Q_1)(Q_2)$, $-S(=O)(Q_1)(Q_2)$, and $-S(=O)_2(Q_1)(Q_2)$, $b21$ is an integer of 1 to 8, and when $b21$ is 2, 3, 4, 5, 6, 7, or 8, the $Ar_{21}(s)$ are identical to or different from each other, two selected from L_{21} and Q_1 to Q_3 are separate or are linked to form a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group, at least one substituent of the substituted C_5 - C_{60} carbocyclic group, substituted C_1 - C_{60} heterocyclic group, substituted C_1 - C_{60} alkyl group, substituted C_2 - C_{60} alkenyl group, substituted C_2 - C_{60} alkynyl group, substituted C_1 - C_{60} alkoxy group, substituted C_3 - C_{10} cycloalkyl group, substituted C_1 - C_{10} heterocycloalkyl group, substituted C_3 - C_{10} cycloalkenyl group, substituted C_1 - C_{10} heterocycloalkenyl group, substituted C_6 - C_{60} aryl group, substituted C_6 - C_{60} aryloxy group, substituted C_6 - C_{60} arylthio group, substituted C_1 - C_{60} heteroaryl group, substituted C_1 - C_{60} hetero aryloxy group, substituted monovalent non-aromatic condensed polycyclic group, or substituted monovalent non-aromatic condensed heteropolycyclic group is selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group; a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one

selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂); a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group; a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂); Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and * indicates a binding site to a neighboring atom.

[0009] The embodiments may be realized by providing an organic light-emitting device including a first electrode; a second electrode facing the first electrode; and an organic layer including an emission layer between the first electrode and the second electrode, wherein the organic layer includes the condensed cyclic compound according to an embodiment.

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] Features will be apparent to those of skill in the art by describing in detail exemplary embodiments with reference to the attached drawings in which:

[0011] FIG. 1 illustrates a schematic view of an organic light-emitting device according to an embodiment;

[0012] FIG. 2 illustrates a schematic view of an organic light-emitting device according to an embodiment;

[0013] FIG. 3 illustrates a schematic view of an organic light-emitting device according to an embodiment; and

[0014] FIG. 4 illustrates a schematic view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

[0015] Example embodiments will now be described more fully hereinafter with reference to the accompanying drawings; however, they may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey exemplary implementations to those skilled in the art.

[0016] In the drawing figures, the dimensions of layers and regions may be exaggerated for clarity of illustration. In addition, it will also be understood that when a layer is referred to as being “between” two layers, it can be the only layer between the two layers, or one or more intervening layers may also be present. Like reference numerals refer to like elements throughout.

[0017] As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list. The term “or” is not an exclusive term, e.g., “A or B” would include A, B, or A and B.


[0018] As used herein, the singular forms “a,” “an” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

[0019] It will be further understood that the terms “includes,” “including,” “comprises,” and/or “comprising” used herein specify the presence of stated features or components, but do not preclude the presence or addition of one or more other features or components.

[0020] It will be understood that when a layer, region, or component is referred to as being “on” or “onto” another layer, region, or component, it may be directly or indirectly formed on the other layer, region, or component. That is, for example, intervening layers, regions, or components may be present.

[0021] A condensed cyclic compound according to an embodiment may be represented by Formula 1 below.

<Formula 1>



[0022] A₁ in Formula 1 may be, e.g., a benzene ring or a naphthalene ring.

[0023] R₁ to R₇ in Formula 1 may each independently be selected from or include, e.g., a group represented by

Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —B(Q₁)(Q₂), —C(=O)(Q₁), —N(Q₁)(Q₂), —P(=O)(Q₁)(Q₂), —P(=S)(Q₁)(Q₂), —S(=O)(Q₁)(Q₂), and —S(=O)₂(Q₁)(Q₂).

[0024] In an implementation, at least one selected from R₁ to R₇ may be a group represented by Formula 2.



[0025] In an implementation, R₁ to R₇ may each independently be selected from or include, e.g., a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group.

[0026] In an implementation, R₁ to R₇ may each independently be selected from or include, e.g., a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a methyl group, an ethyl group, a propyl group, an iso-propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, ter-butyl group, pentyl group, an iso-amyl group, a hexyl group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group.

[0027] b₇ in Formula 1 indicates the number of R₇(s). b₇ may be, e.g., an integer of 1 to 6. When b₇ is 2, 3, 4, 5, or 6, the R₇(s) may be identical to or different from each other.

[0028] L₂₁ in Formula 2 may be selected from or include, e.g., a single bond, a substituted or unsubstituted C₅-C₆₀ carbocyclic group, and a substituted or unsubstituted C₁-C₆₀ heterocyclic group.


[0029] In an implementation, L₂₁ may be selected from or include, e.g., a single bond, a phenylene group, a pental-

enylene group, an indenylene group, a naphthylene group, an azulenylenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylenylene group, a coronenylenylene group, an ovalenylenylene group, a pyrrolylene group, a thiophenylenylene group, a furanylene group, an imidazolylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylene group, an isoxazolylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylene group, an isoindolylenylene group, an indolylenylene group, an indazolylene group, a purinylenylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, benzophenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a benzoxazolylene group, a triazolylene group, a tetrazolylenylene group, an oxadiazolylenylene group, a triazinylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylene group, and a dibenzocarbazolylene group; and


[0030] a phenylene group, a pentalenylenylene group, an indenylene group, a naphthylene group, an azulenylenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylenylene group, a coronenylenylene group, an ovalenylenylene group, a pyrrolylene group, a thiophenylenylene group, a furanylene group, an imidazolylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylene group, an isoxazolylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylene group, an isoindolylenylene group, an indolylenylene group, an indazolylene group, a purinylenylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a benzophenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a benzoxazolylene group, a triazolylene group, a tetrazolylenylene group, an oxadiazolylenylene group, a triazinylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylene group, and a dibenzocarbazolylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a

cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a benzophenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group.


[0031] In an implementation, L_{21} may be selected from, e.g., single bond or a group represented by one of Formulae 3-1 to 3-35.




3-1




3-2



3-3




3-4




3-5


-continued




3-6




3-7




3-8




3-9




3-10




3-11



3-12














3-13




3-14

-continued




-continued

3-15




3-16

3-17




3-18

3-19




3-20

3-21




3-22

3-23




3-24

3-25



-continued



3-32

phenazinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

[0035] d2 may be, e.g., an integer of 0 to 2, and when d2 is 2, the Z₁(s) may be identical to or different from each other,

[0036] d3 may be, e.g., an integer of 0 to 3, and when d3 is 2 or 3, the Z₁(s) may be identical to or different from each other and the Z₂(s) may be identical to or different from each other,

[0037] d4 may be, e.g., an integer of 0 to 4, and when d4 is 2, 3, or 4, the Z₁(s) may be identical to or different from each other and the Z₂(s) may be identical to or different from each other,


[0038] d5 may be, e.g., an integer of 0 to 5, and when d5 is 2, 3, 4, or 5, the Z₁(s) may be identical to or different from each other and the Z₂(s) may be identical to or different from each other,

[0039] d6 may be, e.g., an integer of 0 to 6, and when d6 is 2, 3, 4, 5, or 6, the Z₁(s) may be identical to or different from each other and the Z₂(s) may be identical to or different from each other,


[0040] d8 may be, e.g., an integer of 0 to 8, and when d8 is 2, 3, 4, 5, 6, 7, or 8, the Z₁(s) may be identical to or different from each other, and

[0041] * and *' each indicate a binding site to a neighboring atom.


[0042] In an implementation, L₂₁ may be selected from, e.g., a single bond or a group represented by one of Formulae 4-1 to 4-8.



3-33



3-34




3-35


[0032] In Formula 3-1 to 3-35,

[0033] Y₁ may be O, S, C(Z₃)(Z₄), N(Z₅), or Si(Z₆)(Z₇),


[0034] Z₁ to Z₇ may each independently be selected from or include, e.g., hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a




4-1




4-2



4-3




4-4




4-5


-continued



4-6



4-7



4-8

[0043] In Formulae 4-1 to 4-8,

[0044] Y_1 may be O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, or $Si(Z_6)(Z_7)$,

[0045] Z_1 and Z_3 to Z_7 may each independently be selected from or include, e.g., hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, and a naphthyl group,

[0046] * and *' each indicate a binding site to a neighboring atom.

[0047] a_{21} in Formula 2 indicates the number of $L_{21}(s)$. a_{21} may be, e.g., an integer of 1 to 5.

[0048] When a_{21} is 2, 3, 4, or 5, the $L_{21}(s)$ may be identical to or different from each other.

[0049] In an implementation, a_{21} may be, e.g., 1, 2, 3, or 4.

[0050] Ar_{21} in Formula 2 may be selected from or include, e.g., a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_1)(Q_2)(Q_3), —B(Q_1)(Q_2), —C(=O)(Q_1), —N(Q_1)(Q_2), —P(=O)(Q_1)(Q_2), —P(=S)(Q_1)(Q_2), —S(=O)(Q)(Q_2), and —S(=O)₂(Q_1)(Q_2).

[0051] In an implementation, Ar_{21} may be selected from or include, e.g., a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or

unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —P(=O)(Q_1)(Q_2).


[0052] In an implementation, Ar_{21} may be selected from or include, e.g., a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a benzophenanthrolinyl group, a phenazinyl group, a benzoxazolyl group, a benzimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzoxazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and a benzocarbazolyl group;

[0053] a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a benzophenanthrolinyl group, a phenazinyl group, a benzoxazolyl group, a benzimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzoxazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and a benzocarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a C_6 - C_{20} aryl group, and a C_2 - C_{20} heteroaryl group, and

[0054] —Si(Q_1)(Q_2)(Q_3), —B(Q_1)(Q_2), —C(=O)(Q_1), —N(Q_1)(Q_2), —P(=O)(Q_1)(Q_2), —P(=S)(Q_1)(Q_2), —S(=O)(Q_1)(Q_2), and —S(=O)₂(Q_1)(Q_2).


[0055] In an implementation, Ar_{21} may be selected from, e.g., a group represented by one of Formulae 5-1 to 5-53 or —P(=O)(Q_1)(Q_2).

-continued




5-1

5-9




5-2

5-10




5-3

5-11




5-4

5-12




5-5

5-13




5-6

5-14












5-7

5-15













5-8












5-17



-continued



-continued



5-28

5-29

5-30

5-31

5-32

5-33

5-34


5-35

5-36


5-37

5-38


-continued




5-39




5-40




5-41




5-42




5-43



5-44




5-45




5-46


-continued




5-47




5-48




5-49




5-50



5-51



5-52



5-53

[0056] In Formulae 5-1 to 5-53,

[0057] Y_{31} may be O, S, $C(Z_{33})(Z_{34})$, $N(Z_{35})$, $Si(Z_{36})(Z_{37})$, or $P(=O)(Z_{38})$.[0058] Z_{31} to Z_{38} , Q_1 , and Q_2 may each independently be selected from or include, e.g., hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono

group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a spiro-fluorene-benzofluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a benzophenanthrolinyl group, a phenazinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

[0059] e₂ may be an integer of 0 to 2, when e₂ is 2, the Z₃₁(s) may be identical to or different from each other and Z₃₂(s) may be identical to or different from each other,

[0060] e₃ may be an integer of 0 to 3, and when e₃ is 2 or 3, the Z₃₁(s) may be identical to or different from each other and Z₃₂(s) may be identical to or different from each other,

[0061] e₄ may be an integer of 0 to 4, and when e₄ is 2, 3, or 4, the Z₃₁(s) may be identical to or different from each other and Z₃₂(s) may be identical to or different from each other,

[0062] e₅ may be an integer of 0 to 5, and when e₅ is 2, 3, 4, or 5, the Z₃₁(s) may be identical to or different from each other,

[0063] e₆ may be an integer of 0 to 6, and when e₆ is 2, 3, 4, 5, or 6, the Z₃₁(s) may be identical to or different from each other,

[0064] e₇ may be an integer of 0 to 7, and when e₇ is 2, 3, 4, 5, 6, or 7, the Z₃₁(s) may be identical to or different from each other,












[0065] e₉ may be an integer of 0 to 9, and when e₉ is 2, 3, 4, 5, 6, 7, 8, or 9, the Z₃₁(s) may be identical to or different from each other, and

[0066] * indicates a binding site to a neighboring atom.


[0067] In an implementation, Ar₂₁ may be selected from, e.g., a group represented by one of Formulae 5-1, 5-3, 5-11, 5-12, 5-22, and 5-40 to 5-53 or P(=O)(Q₁)(Q₂).

[0068] In an implementation, Ar₂₁ may be, e.g., a group represented by one of Formulae 6-1 to 6-16.


-continued




-continued




6-12




6-13



6-14



6-15



6-16

[0069] In Formulae 6-1 to 6-16, Ph indicates a phenyl group, and * indicates a binding site to a neighboring atom.

[0070] b21 in Formula 2 indicates the number of Ar₂₁(s). b21 may be, e.g., an integer of 1 to 8.


[0071] When b21 is 2, 3, 4, 5, 6, 7, or 8, the Ar₂₁(s) may be identical to or different from each other.

[0072] In an implementation, two (e.g., adjacent ones) of L₂₁ and Q₁ to Q₃ in Formulae 1 and 2 may be separate or may optionally be linked to form a substituted or unsubstituted C₅-C₆₀ carbocyclic group or a substituted or unsubstituted C₁-C₆₀ heterocyclic group.


[0073] In an implementation, L₂₁ in Formula 2 may be selected from, e.g., a single bond and a group represented by one of Formulae 4-1 to 4-8, and Ar₂₁ in Formula 2 may be, e.g., a group represented by one of Formulae 6-1 to 6-16.

[0074] In an implementation, the condensed cyclic compound represented by Formula 1 may be represented by, e.g., one of Formulae 1-1 to 1-4.


<Formula 1-1>




<Formula 1-2>



<Formula 1-3>



<Formula 1-4>



[0075] In Formulae 1-1 to 1-4,

[0076] R₁ to R₇, L₂₁, Ar₂₁, a21, and b21 may be defined the same as those of Formulae 1 and 2,

[0077] R₈ to R₁₂ may be defined the same as R₁ of Formula 1,

[0078] at least one of R₁ to R₁₀ in Formula 1-1 may be a group represented by Formula 2,

[0079] at least one of R₁ to R₁₂ in Formulae 1-2 to 1-4 may be a group represented by Formula 2, and

[0080] * indicates a binding site to a neighboring atom.

[0081] In an implementation, at least one of R₁, R₂, R₄, and R₈ in Formulae 1-1 and 1-2 may be a group represented by Formula 2.

[0082] In an implementation, R_1 , R_2 , R_4 , or R_8 (e.g., only one of R_1 , R_2 , R_4 , or R_8) in Formulae 1-1 and 1-2 may be a group represented by Formula 2.

[0083] In an implementation, at least one of R_1 , R_2 , R_4 , and R_5 in Formulae 1-1 to 1-4 may be a group represented by Formula 2.

[0084] In an implementation, R_1 , R_2 , R_4 , or R_5 in Formulae 1-1 to 1-4 may be a group represented by Formula 2.

[0085] In an implementation, at least one of R_1 , R_2 , R_4 , R_5 , and R_7 in Formula 1 may be a group represented by Formula 2.

[0086] In an implementation, R_1 , R_2 , R_4 , R_5 , or R_7 in Formula 1 may be a group represented by Formula 2.

[0087] In an implementation, R_1 , R_2 , R_4 , R_5 , or R_7 in Formula 1 may be a group represented by Formula 2, and

[0088] the remaining ones of R_1 to R_7 may each independently be selected from or include hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a phenanthrolinyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group.

[0089] In an implementation, in Formula 1,

[0090] R_1 may be a group represented by Formula 2, and R_2 to R_7 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group; or

[0091] R_2 may be a group represented by Formula 2, and R_1 and R_3 to R_7 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group; or


[0092] R_4 may be a group represented by Formula 2, and R_1 to R_3 and R_5 to R_7 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group; or

[0093] R_5 may be a group represented by Formula 2, and R_1 to R_4 , R_6 , and R_7 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group; or


[0094] R_7 may be a group represented by Formula 2, and R_1 to R_6 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group.

[0095] In an implementation, R_1 , R_2 , R_4 , R_5 , or R_7 in Formula 1 may be a group represented by Formula 2, L_{21} in Formula 2 may be selected from a single bond and a group represented by one of Formulae 4-1 to 4-8, and Ar_{21} in Formula 2 may be a group represented by one of Formulae 6-1 to 6-16.


[0096] In an implementation, the condensed cyclic compound represented by Formula 1 may be, e.g., one of the following Compounds 1 to 118.



1




2




3


-continued




4




5




6




7



8




9




10

-continued


11




12




13




14




-continued




15




16




17



18




19




20


-continued




21




22




23




24




25



26










27




28

-continued




-continued


36




38




37




39




41



40





42




-continued

43


44




45




46




47




48




-continued




49




50




51



52



53




54


-continued

55


56




57




58




59




60




-continued




62




63




64




65




66








67










68




-continued




-continued




-continued




81




82



83










84









85

-continued




-continued




-continued


99




100




101




102




103




104








105



106




-continued




-continued


112




113




114





115



116



-continued
117

118

[0097] The condensed cyclic compound represented by Formula 1 may include a pi-conjugated system and may have a small intramolecular steric hindrance. Accordingly, the condensed cyclic compound may have enhanced intermolecular packing and high charge transport ability. Due to the intermolecular packing, the condensed cyclic compound may have high glass transition temperature (T_g) and melting point. In addition, in the condensed cyclic compound, two N atoms of the core represented by Formula 1 may be located in such positions favorable for coordinate bonding with an n-type dopant. Therefore, an organic light-emitting device including the condensed cyclic compound may have high durability during driving, low driving voltage, and high efficiency.

[0098] The structure represented by Formula 1 may have a long conjugate system length and hence a large pi-orbital overlap. The large pi-orbital overlap may result in an increase in the transfer integral and hence high hopping rate, which is suitable for charge-transport. A molecule having a linear rod shape may have a high mobility obtained by enhanced packing when forming a bulk film. Regarding the condensed cyclic compound represented by Formula 1, the core may have the rod shape. For example, the group represented by Formula 2 may be introduced into end parts of the core in a longitudinal direction of the core (e.g., R_1 , R_2 , R_4 , and R_7 in Formula 1), and the steric hindrance between the core represented by Formula 1 and the group represented by Formula 2 may be reduced and the angle between the core represented by Formula 1 and the group represented by Formula 2 may be reduced to further expand the pi-conjugated system. Also, the entire molecule may have a rod shape in addition to the core structure represented by Formula 1, and the electron mobility may be increased.

[0099] Synthesis methods for the condensed cyclic compound represented by Formula 1 may be understood in view of the following examples.

[0100] At least one of the condensed cyclic compounds of Formula 1 may be used or included between a pair of electrodes of an organic light-emitting device. For example, the condensed cyclic compound may be included in at least one layer selected from a hole transport region, an electron transport region, and an emission layer. In an implementation, the condensed cyclic compound of Formula 1 may be used as a material for a capping layer located outside a pair of electrodes of an organic light-emitting device.

[0101] Another aspect provides an organic light-emitting device that includes: a first electrode; a second electrode facing the first electrode; and an organic layer that is located between the first electrode and the second electrode and

includes an emission layer, wherein the organic layer includes at least one condensed cyclic compound represented by Formula 1.

[0102] The expression “(an organic layer) includes at least one condensed cyclic compound” used herein may include a case in which “(an organic layer) includes identical compounds represented by Formula 1” and a case in which “(an organic layer) includes two or more different condensed cyclic compounds.”

[0103] In an implementation, the first electrode may be an anode, the second electrode may be a cathode, and the organic layer may further include a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode, and the hole transport region includes a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or any combination thereof, and the electron transport region includes a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, an electron injection layer, or any combination thereof.

[0104] In an implementation, the electron transport region may include the condensed cyclic compound represented by Formula 1.

[0105] In an implementation, the electron transport region may include at least one of an electron transport layer and an electron injection layer, and the at least one of the electron transport layer and the electron injection layer may include the condensed cyclic compound represented by Formula 1.

[0106] In an implementation, the emission layer may include the condensed cyclic compound represented by Formula 1.

[0107] In an implementation, the emission layer may consist of the condensed cyclic compound represented by Formula 1. In an implementation, the emission layer may further include a dopant. An amount of the dopant may be in a range of, e.g., about 0.1 parts by weight to about 50 parts by weight, based on 100 parts by weight of the the emission layer.

[0108] The dopant may be a phosphorescent dopant or a fluorescent dopant.

[0109] In an implementation, the hole transport region of the organic light-emitting device may include a p-dopant having a lowest unoccupied molecular orbital (LUMO) energy level of, e.g., less than -3.5 eV.

[0110] The emission layer of the organic light-emitting device may be a first color light emission layer,

[0111] the organic light-emitting device may further include i) at least one second color light emission layer or ii)

at least one second color light emission layer and at least one third color light emission layer, between the first electrode and the second electrode,

[0112] a maximum emission wavelength of the first color light-emitting emission layer, a maximum emission wavelength of the second color light-emitting emission layer, and a maximum emission wavelength of the third color light-emitting emission layer are identical to or different from each other, and

[0113] the first color light and the second color light may be emitted in the form of mixed light, or the first color light, the second color light, and the third color light may be emitted in the form of mixed light.

[0114] The organic light-emitting device may further include at least one selected from a first capping layer located in a pathway along which light generated in an emission layer proceeds toward the outside through the first electrode and a second capping layer located in a pathway along which light generated in an emission layer proceeds toward the outside through the second electrode, and the at least one selected from the first capping layer and the second capping layer may include the condensed cyclic compound represented by Formula 1.

[0115] For example, the organic light-emitting device may have i) a stacked structure including a first electrode, an organic layer, a second electrode, and a second capping layer which are sequentially stacked in this stated order, ii) a stacked structure including a first capping layer, a first electrode, an organic layer, and a second electrode which are sequentially stacked in this stated order, or iii) a stacked structure including a first capping layer, a first electrode, an organic layer, a second electrode, and a second capping layer which are sequentially stacked in this stated order, and at least one selected from the first capping layer and the second capping layer may include the condensed cyclic compound.

[0116] The term “organic layer” used herein refers to a single layer and/or a plurality of layers located between the first electrode and the second electrode of an organic light-emitting device. A material included in the “organic layer” is not limited to an organic material.

[0117] FIG. 1 illustrates a schematic view of an organic light-emitting device 10 according to an embodiment. The organic light-emitting device 10 may include a first electrode 110, an organic layer 150, and a second electrode 190.

[0118] Hereinafter, the structure of the organic light-emitting device 10 according to an embodiment and a method of manufacturing the organic light-emitting device 10 will be described in connection with FIG. 1.

[0119] In an implementation, a substrate may be additionally located under the first electrode 110 or above the second electrode 190. The substrate may be a glass substrate or a plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

[0120] The first electrode 110 may be formed by depositing or sputtering a material for forming the first electrode

110 on the substrate. When the first electrode 110 is an anode, the material for a first electrode may be selected from materials with a high work function to facilitate hole injection.

[0121] The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. When the first electrode 110 is a transmissive electrode, a material for forming a first electrode may be selected from indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), zinc oxide (ZnO), and any combinations thereof. When the first electrode 110 is a semi-transmissive electrode or a reflective electrode, as a material for forming the first electrode 110, magnesium (Mg), silver (Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), or any combination thereof may be used.

[0122] The first electrode 110 may have a single-layered structure, or a multi-layered structure including two or more layers. For example, the first electrode 110 may have a three-layered structure of ITO/Ag/ITO.

[0123] The organic layer 150 is located on the first electrode 110. The organic layer 150 may include an emission layer.


[0124] The organic layer 150 may further include a hole transport region between the first electrode 110 and the emission layer, and an electron transport region between the emission layer and the second electrode 190.

[0125] The hole transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.


[0126] The hole transport region may include at least one layer selected from a hole injection layer (HIL), a hole transport layer (HTL), an emission auxiliary layer, and an electron blocking layer (EBL).

[0127] For example, the hole transport region may have a single-layered structure including a single layer including a plurality of different materials, or a multi-layered structure having a hole injection layer/hole transport layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/electron blocking layer structure, wherein for each structure, constituting layers are sequentially stacked from the first electrode 110 in this stated order.


[0128] The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB (NPD), β-NPB, TPD, Spiro-TPD, Spiro-NPB, methylated-NPB, TAPC, HMTDP, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:



m-MTDATA




TDATA




2-TNATA


-continued




NPB




β -NPB



TPD



Spiro-TPD



Spiro-NPB

indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, and a pyridinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacacenyl group, a pentacacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃) and —N(Q₃₁)(Q₃₂);

[0140] wherein Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0141] In one or more embodiments, xa1 to xa4 may each independently be 0, 1, or 2.

[0142] In one or more embodiments, xa5 may be 1, 2, 3, or 4.

[0143] In one or more embodiments, R₂₀₁ to R₂₀₄ and Q₂₀₁ may each independently be selected from a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacacenyl group, a pentacacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group; and

[0144] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl

group, a hexacacenyl group, a pentacacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacacenyl group, a pentacacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —N(Q₃₁)(Q₃₂),

[0145] wherein Q₃₁ to Q₃₃ are the same as described above.

[0146] In one or more embodiments, at least one selected from R₂₀₁ to R₂₀₃ in Formula 201 may each independently be selected from:

[0147] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0148] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group

[0149] In one or more embodiments, in Formula 202, i) R₂₀₁ and R₂₀₂ may be linked via a single bond, and/or ii) R₂₀₃ and R₂₀₄ may be linked via a single bond.


[0150] In one or more embodiments, at least one selected from R₂₀₁ to R₂₀₄ in Formula 202 may be selected from:

[0151] a carbazolyl group; and


[0152] a carbazolyl group substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl

group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothio-phenyl group.


[0153] The compound represented by Formula 201 may be represented by Formula 201A:




[0154] In one embodiment, the compound represented by Formula 201 may be represented by Formula 201A(1) below:




[0155] In one embodiment, the compound represented by Formula 201 may be represented by Formula 201A-1 below:



[0156] In one embodiment, the compound represented by Formula 202 may be represented by Formula 202A:



[0157] In one embodiment, the compound represented by Formula 202 may be represented by Formula 202A-1:



[0158] In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1,

[0159] L₂₀₁ to L₂₀₃, xa1 to xa3, xa5, and R₂₀₂ to R₂₀₄ may be the same as described above,





[0160] R₂₁₁ and R₂₁₂ are the same as described in connection with R₂₀₃,

[0161] R₂₁₃ to R₂₁₇ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl


group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a

pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.


[0162] The hole transport region may include at least one compound selected from Compounds HT1 to HT39:




-continued
HT5




HT6




HT7




HT8




HT9




HT10




-continued
HT11




HT12




HT13




HT14




HT15




HT16




-continued




HT17




HT18



HT19




HT20




HT21

-continued


HT22




HT23




HT24




-continued
HT25




HT26



HT27




HT28




-continued


HT29



HT30




HT31




-continued


HT32




HT33




HT34




HT35




-continued
HT36


HT37



HT38



HT39



[0163] A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes at least one of a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of about 100 Å to about 9,000 Å, for example, about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, for example about 100 Å to about 1,500 Å.

[0164] When the thicknesses of the hole transport region, the hole injection layer and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

[0165] The emission auxiliary layer may increase light-emission efficiency by compensating for an optical resonance distance according to the wavelength of light emitted by an emission layer, and the electron blocking layer may block the flow of electrons from an electron transport region. The emission auxiliary layer and the electron blocking layer may include the materials as described above.

[0166] The hole transport region may further include, in addition to these materials, a charge-generation material for

the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

[0167] The charge-generation material may be, for example, a p-dopant.

[0168] In one embodiment, a lowest unoccupied molecular orbital (LUMO) energy level of the p-dopant may be -3.5 eV or less.

[0169] The p-dopant may include at least one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound.


[0170] For example, the p-dopant may include at least one selected from

[0171] a quinone derivative, such as tetracyanoquinodimethane (TCNQ) or 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4-TCNQ);

[0172] a metal oxide, such as tungsten oxide or molybdenum oxide;

[0173] 1,4,5,8,9,11-hexaazatriphenylene-hexacarbonitrile (HAT-CN); and

[0174] a compound represented by Formula 221 below:



[0175] In Formula 221,

[0176] R_{221} to R_{223} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and at least one selected from R_{221} to R_{223} may include at least one substituent selected from a cyano group, $-F$, $-Cl$, $-Br$, $-I$, a C_1 - C_{20} alkyl group substituted with $-F$, a C_1 - C_{20} alkyl group substituted with $-Cl$, a C_1 - C_{20} alkyl group substituted with $-Br$, and a C_1 - C_{20} alkyl group substituted with $-I$.

[0177] When the organic light-emitting device **10** is a full-color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub-pixel. In one or more embodiments, the emission layer may have a stacked structure of two or more layers selected from a red emission layer, a green emission layer, and a blue emission layer, in which the two or more layers contact each other or are separated from each other. In one or more embodiments, the emission layer may include two or more materials selected from a red light-emitting material, a green light-emitting material, and a blue light-emitting material, in which the two or more materials are mixed with each other in a single layer to emit white light.

[0178] The emission layer may include a host and a dopant. The dopant may include at least one selected from a phosphorescent dopant and a fluorescent dopant.

[0179] An amount of the dopant in the emission layer may be, in general, in a range of about 0.01 parts by weight to about 15 parts by weight based on 100 parts by weight of the host.

[0180] A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.

[0181] The host may include the condensed cyclic compound represented by Formula 1.

[0182] In one or more embodiments, the host may include a compound represented by Formula 301 below.



[0183] In Formula 301,

[0184] Ar_{301} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group, or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

[0185] $xb11$ may be 1, 2, or 3; and

[0186] L_{301} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0187] $xb1$ may be an integer of 0 to 5,

[0188] R_{301} may be selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(Q_{301})(Q_{302})(Q_{303})$, $-\text{N}(Q_{301})(Q_{302})$, $-\text{B}(Q_{301})(Q_{302})$, $-\text{C}(=\text{O})(Q_{301})$, $-\text{S}(=\text{O})_2(Q_{301})$, and $-\text{P}(=\text{O})(Q_{301})(Q_{302})$,

[0189] $xb21$ may be an integer of 1 to 5,

[0190] Q_{301} to Q_{303} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0191] In one embodiment, Ar_{301} in Formula 301 may be selected from:

[0192] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene


group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group; and

[0193] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂);


[0194] Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0195] When xb11 in Formula 301 is two or more, two or more Ar₃₀₁(s) may be linked via a single bond.

[0196] In one or more embodiments, the compound represented by Formula 301 may be represented by Formula 301-1 or 301-2:



<Formula 301-1>



<Formula 301-2>

[0197] In Formulae 301-1 to 301-2,

[0198] A₃₀₁ to A₃₀₄ may each independently be selected from a benzene group, a naphthalene group, a phenanthrene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a pyridine group, a pyrimidine group, an indene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, an indole group, a carbazole group, a benzocarbazole group, a dibenzocarbazole group, a furan group, a benzofuran group, a dibenzofuran group, a naphthofuran group, a benzonaphthofuran group, a dinaphthofuran group, a thiophene group,

a benzothiophene group, a dibenzothiophene group, a naphthothiophene group, a benzonaphthothiophene group, and a dinaphthothiophene group,

[0199] X₃₀₁ may be O, S, or N-[(L₃₀₄)_{xb4}-R₃₀₄],

[0200] R₃₁₁ to R₃₁₄ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

[0201] xb22 and xb23 may each independently be 0, 1, or 2,

[0202] L₃₀₁, xb1, R₃₀₁, and Q₃₁ to Q₃₃ are the same as described above,

[0203] L₃₀₂ to L₃₀₄ may each independently be the same as described in connection with L₃₀₁,

[0204] Xb2 to xb4 may each independently be the same as described in connection with xb1,

[0205] R₃₀₂ to R₃₀₄ may each independently be the same as described in connection with R₃₀₁.

[0206] For example, L₃₀₁ to L₃₀₄ in Formulae 301, 301-1 and 301-2 may each independently be selected from:

[0207] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylene

group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, a pyridinylylene group, an imidazolylylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazolylylene group, an isoxazolylylene group, a thiadiazolylylene group, an oxadiazolylylene group, a pyrazinylylene group, a pyrimidinylylene group, a pyridazinylylene group, a triazinylylene group, a quinolylylene

group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group; and

[0208] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylene group, a dibenzofuranylenylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl

zoyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

[0209] wherein Q₃₁ to Q₃₃ may be the same as described above.

[0210] In one embodiment, R₃₀₁ to R₃₀₄ in Formulae 301, 301-1 and 301-2 may each independently be selected from:

[0211] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and


[0212] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl

group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenaziny group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$;


[0213] Q_{31} to Q_{33} may be the same as described above.

[0214] In one or more embodiments, the host may include an alkaline earth metal complex. For example, the host may be selected from a Be complex (for example, Compound H55), a Mg complex, and a Zn complex.

[0215] The host may include at least one selected from 9,10-di(2-naphthyl)anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl)anthracene (MADN), 9,10-di(2-naphthyl)-2-t-butyl-anthracene (TBADN), 4,4'-bis(N-carbazolyl)-1,1'-biphenyl (CBP), 1,3-di-9-carbazolylbenzene (mCP), 1,3,5-tri(carbazol-9-yl)benzene (TCP), and Compounds H1 to H55:




H1




H2


-continued




H3




H4




H5



H6




H7




H8

-continued


H9




H10




H11



H12




H13




-continued


H14




H15




H16



H17




H18




-continued

H19




-continued


H23




H20




H24




H21




H25



H22




-continued




H26


-continued




H29




H27




H30



H28




H31




H32

-continued


H33




H34



H35




H36




-continued


H37






H38







H39




-continued




-continued




-continued




H47




H48




H49



H50




H51




H52


-continued



H53




H54




H55

[0216] The phosphorescent dopant may include an organometallic complex represented by Formula 401 below:



<Formula 401>

<Formula 402>



[0217] In Formulae 401 and 402,

[0218] M may be selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), and thulium (Tm),

[0219] L_{401} may be selected from ligands represented by Formula 402, and xc1 may be 1, 2, or 3, wherein, when xc1 is two or more, two or more $L_{401}(s)$ may be identical to or different from each other,

[0220] L_{402} may be an organic ligand, and xc2 may be an integer of 0 to 4, wherein, when xc2 is two or more, two or more $L_{402}(s)$ may be identical to or different from each other,

[0221] X_{401} to X_{404} may each independently be nitrogen or carbon,

[0222] X_{401} and X_{403} may be linked via a single bond or a double bond, and X_{402} and X_{404} may be linked via a single bond or a double bond,

[0223] A_{401} and A_{402} may each independently be selected from a C_5 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group,

[0224] X_{405} may be a single bond, $*-O-*$, $*-S-*$, $*-C(=O)-*$, $*-N(Q_{411})-*$, $*-C(Q_{41})(Q_{412})-*$, $*-C(Q_{411})=C(Q_{412})-*$, $*-C(Q_{41})=*$, or $*=C(Q_{41})=*$, Q_{411} and Q_{412} may be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group,

[0225] X_{406} may be a single bond, O, or S,

[0226] R_{401} and R_{402} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_{401})(Q_{402})(Q_{403})$, $-N(Q_{401})(Q_{402})$, $-B(Q_{401})(Q_{402})$, $-C(=O)(Q_{401})$, $-S(=O)_2(Q_{401})$, and $-P(=O)(Q_{401})(Q_{402})$, wherein Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a C_6 - C_{20} aryl group, and a C_1 - C_{20} heteroaryl group,

[0227] xc11 and xc12 may each independently be an integer of 0 to 10, and

[0228] * and *ⁿ in Formula 402 each indicate a binding site to M in Formula 401.

[0229] In one embodiment, A_{401} and A_{402} in Formula 402 may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a benzimi-

dazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, and a dibenzothiophene group.

[0230] In one or more embodiments, in Formula 402, i) X_{401} is nitrogen and X_{402} is carbon, or ii) each of X_{401} and X_{402} may be nitrogen.

[0231] In one or more embodiments, R_{401} and R_{402} in Formula 402 may each independently be selected from:

[0232] hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0233] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, and a norbornenyl group;

[0234] a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

[0235] a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0236] $-Si(Q_{401})(Q_{402})(Q_{403})$, $-N(Q_{401})(Q_{402})$, $-B(Q_{401})(Q_{402})$, $-C(=O)(Q_{401})$, $-S(=O)_2(Q_{401})$, and $-P(=O)(Q_{401})(Q_{402})$,


[0237] wherein Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group.

[0238] In one or more embodiments, when xc1 in Formula 401 is two or more, two $A_{401}(s)$ in two or more $L_{401}(s)$ may optionally be linked via X_{407} , which is a linking group, or two $A_{402}(s)$ in two or more $L_{401}(s)$ may optionally be linked


via X_{408} , which is a linking group (see Compounds PD1 to PD4 and PD7). X_{407} and X_{408} may each independently be a single bond, $*-O-*$, $*-S-*$, $*-C(=O)-*$, $*-N(Q_{413})-*$, $*-C(Q_{413})(Q_{414})-*$, or $*-C(Q_{413})=C(Q_{414})-*$ (wherein Q_{413} and Q_{414} may each independently be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group).

[0239] L_{402} in Formula 401 may be a monovalent, divalent, or trivalent organic ligand. For example, L_{402} may be selected from halogen, diketone (for example, acetylacetonate), carboxylic acid (for example, picolinate), $-C(=O)$, isonitrile, $-CN$, and phosphorus (for example, phosphine, or phosphite).


[0240] In one or more embodiments, the phosphorescent dopant may be selected from, for example, Compounds PD1 to PD25:




PD1




PD2




PD3




PD4




PD5




PD6



PD7








PD8




PD9

-continued




-continued

PD10




PD15

PD11




PD16

PD12




PD17

PD13




PD18

PD14




PD19

-continued




PD20


-continued



PD24



PD21




PD25


[0241] The fluorescent dopant may include an arylamine compound or a styrylamine compound.

[0242] The fluorescent dopant may include a compound represented by Formula 501 below.

PD22



<Formula 501>



[0243] In Formula 501,


[0244] Ar₅₀₁ may be a substituted or unsubstituted C₅-C₆₀ carbocyclic group or a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

[0245] L₅₀₁ to L₅₀₃ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

PD23

[0246] x_{d1} to x_{d3} may each independently be an integer of 0 to 3;

[0247] R₅₀₁ and R₅₀₂ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalk-



enyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

[0248] xd4 may be an integer of 1 to 6.

[0249] In one embodiment, Ar₅₀₁ in Formula 501 may be selected from:

[0250] a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group; and

[0251] a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0252] In one or more embodiments, L₅₀₁ to L₅₀₃ in Formula 501 may each independently be selected from:

[0253] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, a pyridinylylene group; and

[0254] a phenylene group, a naphthylene group, a fluorenylylene group, a spiro-bifluorenylylene group, a benzofluorenylylene group, a dibenzofluorenylylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, and a pyridinylylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl

thyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolylyl group, an indolylyl group, an isoindolylyl group, a benzofuranylyl group, a benzothiophenyl group, a dibenzofuranylyl group, a dibenzothiophenyl group, a benzocarbazolylyl group, a dibenzocarbazolylyl group, a dibenzosilolylyl group, and a pyridinylyl group.

[0255] In one or more embodiments, R₅₀₁ and R₅₀₂ in Formula 501 may each independently be selected from:


[0256] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolylyl group, an indolylyl group, an isoindolylyl group, a benzofuranylyl group, a benzothiophenyl group, a dibenzofuranylyl group, a dibenzothiophenyl group, a benzocarbazolylyl group, a dibenzocarbazolylyl group, a dibenzosilolylyl group, and a pyridinylyl group; and

[0257] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolylyl group, an indolylyl group, an isoindolylyl group, a benzofuranylyl group, a benzothiophenyl group, a dibenzofuranylyl group, a dibenzothiophenyl group, a benzocarbazolylyl group, a dibenzocarbazolylyl group, a dibenzosilolylyl group, and a pyridinylyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolylyl group, an indolylyl group, an isoindolylyl group, a benzofuranylyl group, a benzothiophenyl group, a dibenzofuranylyl group, a dibenzothiophenyl group, a benzocarbazolylyl group, a dibenzocarbazolylyl group, a dibenzosilolylyl group, a pyridinylyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃);


[0258] wherein Q₃₁ to Q₃₃ may each be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0259] In one or more embodiments, xd4 in Formula 501 may be 2.


[0260] For example, the fluorescent dopant may be selected from Compounds FD1 to FD22:




FD1




FD2




FD3



FD4




FD5



FD6


-continued

FD7




-continued


FD10




FD11




FD8





FD12







FD13



FD14




-continued




-continued

FD19


FD15




FD16



FD20




FD17




FD21

FD22


FD18




[0261] In one or more embodiments, the fluorescent dopant may be selected from the following compounds.




DPVBi




DPAVBi




TBPe




DCM



DCJTb



Coumarin 6



[0262] The electron transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0263] The electron transport region may include at least one selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, and an electron injection layer.

[0264] For example, the electron transport region may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron transport layer/electron injection layer structure, or a buffer layer/electron transport layer/electron injection layer structure, wherein for each structure, constituting layers are sequentially stacked from an emission layer.

[0265] The electron transport region may include the condensed cyclic compound represented by Formula 1.

[0266] In one or more embodiments, the electron transport region (for example, a buffer layer, a hole blocking layer, an electron control layer, or an electron transport layer in the electron transport region) may further include a metal-free compound containing at least one π electron-depleted nitrogen-containing ring.

[0267] The “ n electron-depleted nitrogen-containing ring” indicates a C_1 - C_{60} heterocyclic group having at least one $*-N=*^*$ moiety as a ring-forming moiety.

[0268] For example, the “ n electron-depleted nitrogen-containing ring” may be i) a 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*^*$ moiety, ii) a heteropolycyclic group in which two or more 5-membered to 7-membered heteromonocyclic groups each having at least one $*-N=*^*$ moiety are condensed with each other, or iii) a heteropolycyclic group in which at least one of 5-membered to 7-membered heteromonocyclic groups, each having at least one $*-N=*^*$ moiety, is condensed with at least one C_5 - C_{60} carbocyclic group.

[0269] Examples of the n electron-depleted nitrogen-containing ring include an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isoxazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, an indazole, a purine, a quinoline, an isoquinoline, a benzoquinoline, a phthalazine, a naphthyridine, a quinoxaline, a quinazoline, a cinnoline, a phenanthridine, an acridine, a phenanthroline, a phenazine, a benzimidazole, an isobenzothiazole, a benzoxazole, an isobenzoxazole, a triazole, a tetrazole, an oxadiazole, a triazine, thiadiazol, an imidazopyridine, an imidazopyrimidine, and an azacarbazole.

[0270] For example, the electron transport region may include a compound represented by Formula 601:



[0271] In Formula 601,

[0272] Ar_{601} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

[0273] $xe11$ may be 1, 2, or 3,

[0274] L_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0275] $xe1$ may be an integer of 0 to 5,

[0276] R_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(Q_{601})(Q_{602})(Q_{603})$, $-\text{C}(=\text{O})(Q_{601})$, $-\text{S}(=\text{O})_2(Q_{601})$, and $-\text{P}(=\text{O})(Q_{601})(Q_{602})$,

[0277] Q_{601} to Q_{603} may each independently be a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group, and

[0278] $xe21$ may be an integer of 1 to 5.

[0279] In one embodiment, at least one of $Ar_{601}(s)$ in the number of $xe11$ and $R_{601}(s)$ in the number of $xe21$ may include the π electron-depleted nitrogen-containing ring.

[0280] In one embodiment, ring Ar_{601} in Formula 601 may be selected from:

[0281] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran

group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group; and

[0282] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, phenanthroline group, phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂);


[0283] wherein Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0284] When xe11 in Formula 601 is two or more, two or more Ar₆₀₁(s) may be linked via a single bond.

[0285] In one or more embodiments, Ar₆₀₁ in Formula 601 may be an anthracene group.

[0286] In one or more embodiments, a compound represented by Formula 601 may be represented by Formula 601-1:

<Formula 601-1>



[0287] In Formula 601-1,

[0288] X₆₁₄ may be N or C(R₆₁₄), X₆₁₅ may be N or C(R₆₁₅), X₆₁₆ may be N or C(R₆₁₆), at least one selected from X₆₁₄ to X₆₁₆ may be N,

[0289] L₆₁₁ to L₆₁₃ are the same as described in connection with L₆₀₁,

[0290] xe611 to xe613 are the same as described in connection with xe1,

[0291] R₆₁₁ to R₆₁₃ are the same as described in connection with R₆₀₁,

[0292] R₆₁₄ to R₆₁₆ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0293] In one embodiment, L₆₀₁ and L₆₁₁ to L₆₁₃ in Formulae 601 and 601-1 may each independently be selected from:

[0294] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, a pyridinylylene group, an imidazololylylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazololylylene group, an isoxazololylylene group, a thiadiazolylylene group, an oxadiazolylylene group, a pyrazinylylene group, a pyrimidinylylene group, a pyridazinylylene group, a triazinylylene group, a quinolinilylylene group, an isoquinolinilylylene group, a benzoquinolinilylylene group, a phthalazinilylylene group, a naphthyridinilylylene group, a quinoxalinilylylene group, a quinazolinilylylene group, a cinnolinilylylene group, a phenanthridinilylylene group, an acridinilylylene group, a phenanthrolinilylylene group, a phenazinilylylene group, a benzimidazololylylene group, an isobenzothiazolylylene group, a benzoxazololylylene group, an isobenzoxazololylylene group, a triazololylylene group, a tetrazolylylene group, an imidazopyridinilylylene group, an imidazopyrimidinilylylene group, and an azacarbazolylylene group; and

[0295] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylylene group, a dibenzofluorenylylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, a pyridinylylene group, an imidazololylylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazololylylene group, an isoxazololylylene group, a thiadiazolylylene group, an oxadiazolylylene group, a pyrazinylylene group, a pyrimidinylylene group, a

pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group.

[0296] In one or more embodiments, xe1 and xe611 to xe613 in Formulae 601 and 601-1 may each independently be 0, 1, or 2.

[0297] In one or more embodiments, R₆₀₁ and R₆₁₁ to R₆₁₃ in Formulae 601 and 601-1 may each independently be selected from:

[0298] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl


group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

[0299] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and


[0300] —S(=O)₂(Q₆₀₁) and —P(=O)(Q₆₀₁)(Q₆₀₂),

[0301] wherein Q₆₀₁ and Q₆₀₂ are the same as described above.


[0302] The electron transport region may include at least one compound selected from Compounds ET1 to ET36:
ET1




ET2




ET3




-continued



ET4




ET5




ET6

-continued


ET7



ET8




ET9




-continued


ET10



ET11




ET12




-continued

ET13





-continued

ET16





ET17

ET14






ET18

ET15




-continued



-continued


ET19

ET22




ET20

ET23




ET21


ET24




-continued




-continued




ET26




ET29




ET27



ET30




-continued




ET31

-continued




ET34


ET32




ET35




ET33



ET36



[0303] In one or more embodiments, the electron transport region may include at least one selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq3, BALq, 3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (TAZ), and NTAZ.




[0304] A thickness of the buffer layer, the hole blocking layer, or the electron control layer may be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer, and the electron control layer are within these ranges, the electron blocking layer may have excellent electron blocking characteristics or electron control characteristics without a substantial increase in driving voltage.

[0305] A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.


[0306] The electron transport region (for example, the electron transport layer in the electron transport region) may further include, in addition to the materials described above, a metal-containing material.

[0307] The metal-containing material may include at least one selected from alkali metal complex and alkaline earth-metal complex. The alkali metal complex may include a metal ion selected from a Li ion, a Na ion, a K ion, a Rb ion, and a Cs ion, and the alkaline earth-metal complex may include a metal ion selected from a Be ion, a Mg ion, a Ca ion, a Sr ion, and a Ba ion. A ligand coordinated with the metal ion of the alkali metal complex or the alkaline earth-metal complex may be selected from a hydroxy quinoline, a hydroxy isoquinoline, a hydroxy benzoquinoline, a hydroxy acridine, a hydroxy phenanthridine, a hydroxy phenyloxazole, a hydroxy phenylthiazole, a hydroxy diphenyloxadiazaole, a hydroxy diphenylthiadiazol, a hydroxy phenylpyridine, a hydroxy phenylbenzimidazole, a hydroxy phenylbenzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene.

[0308] For example, the metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2.



ET-D1



ET-D2

[0309] The electron transport region may include an electron injection layer that facilitates the injection of electrons from the second electrode 190. The electron injection layer may directly contact the second electrode 190.

[0310] The electron injection layer may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0311] The electron injection layer may include an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof.

[0312] The alkali metal may be selected from Li, Na, K, Rb, and Cs. In one embodiment, the alkali metal may be Li, Na, or Cs. In one or more embodiments, the alkali metal may be Li or Cs.

[0313] The alkaline earth metal may be selected from Mg, Ca, Sr, and Ba.

[0314] The rare earth metal may be selected from Sc, Y, Ce, Tb, Yb, and Gd.

[0315] The alkali metal compound, the alkaline earth-metal compound, and the rare earth metal compound may be selected from oxides and halides (for example, fluorides, chlorides, bromides, or iodides) of the alkali metal, the alkaline earth-metal, and the rare earth metal.

[0316] The alkali metal compound may be selected from alkali metal oxides, such as Li_2O , Cs_2O , or K_2O , and alkali metal halides, such as LiF, NaF, CsF, KF, LiI, NaI, CsI, or KI. In one embodiment, the alkali metal compound may be selected from LiF, Li_2O , NaF, Li, NaI, CsI, and KI.

[0317] The alkaline earth-metal compound may be selected from alkaline earth-metal oxides, such as BaO, SrO, CaO, $\text{Ba}_x\text{Sr}_{1-x}\text{O}$ ($0 < x < 1$), $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ ($0 < x < 1$). In one embodiment, the alkaline earth-metal compound may be selected from BaO, SrO, and CaO.

[0318] The rare earth metal compound may be selected from YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , and TbF_3 . In one embodiment, the rare earth metal compound may be selected from YbF_3 , ScF_3 , TbF_3 , YbI_3 , ScI_3 , and TbI_3 .

[0319] The alkali metal complex, the alkaline earth-metal complex, and the rare earth metal complex may include an ion of alkali metal, alkaline earth-metal, and rare earth metal as described above, and a ligand coordinated with a metal ion of the alkali metal complex, the alkaline earth-metal complex, or the rare earth metal complex may be selected from hydroxy quinoline, hydroxy isoquinoline, hydroxy benzoquinoline, hydroxy acridine, hydroxy phenanthridine, hydroxy phenyloxazole, hydroxy phenylthiazole, hydroxy diphenyloxadiazole, hydroxy diphenylthiadiazol, hydroxy phenylpyridine, hydroxy phenylbenzimidazole, hydroxy phenylbenzothiazole, bipyridine, phenanthroline, and cyclopentadiene.

[0320] The electron injection layer may consist of an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof, as described above. In one or more embodiments, the electron injection layer may further include an organic material. When the electron injection layer further includes an organic material, an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof may be homogeneously or non-homogeneously dispersed in a matrix including the organic material.

[0321] A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

[0322] The second electrode 190 may be located on the organic layer 150 having such a structure. The second electrode 190 may be a cathode which is an electron injection electrode, and in this regard, a material for forming the second electrode 190 may be selected from metal, an alloy, an electrically conductive compound, and a combination thereof, which have a relatively low work function.

[0323] The second electrode 190 may include at least one selected from lithium (Li), silver (Si), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), ITO, and IZO. The second electrode 190 may be a transmissive electrode, a semi-transmissive electrode, or a reflective electrode.

[0324] The second electrode 190 may have a single-layered structure, or a multi-layered structure including two or more layers.

[0325] An organic light-emitting device 20 of FIG. 2 includes a first capping layer 210, a first electrode 110, an organic layer 150, and a second electrode 190, sequentially stacked in this stated order, an organic light-emitting device 30 of FIG. 3 includes a first electrode 110, an organic layer 150, a second electrode 190, and a second capping layer 220, sequentially stacked in this stated order, and an organic light-emitting device 40 of FIG. 4 includes a first capping layer 210, a first electrode 110, an organic layer 150, a second electrode 190, and a second capping layer 220, sequentially stacked in this stated order.

[0326] Regarding FIGS. 2 to 4, the first electrode 110, the organic layer 150, and the second electrode 190 may be understood by referring to the description presented in connection with FIG. 1.

[0327] In the organic layer 150 of each of the organic light-emitting devices 20 and 40, light generated in an emission layer may pass through the first electrode 110 and the first capping layer 210 toward the outside, wherein the first electrode 110 may be a semi-transmissive electrode or a transmissive electrode. In the organic layer 150 of each of the organic light-emitting devices 30 and 40, light generated in an emission layer may pass through the second electrode 190 and the second capping layer 220 toward the outside, wherein the second electrode 190 may be a semi-transmissive electrode or a transmissive electrode.


[0328] The first capping layer 210 and the second capping layer 220 may increase external luminescent efficiency according to the principle of constructive interference.

[0329] The first capping layer 210 and the second capping layer 220 may each independently be an organic capping layer including an organic material, an inorganic capping layer including an inorganic material, or a composite capping layer including an organic material and an inorganic material.

[0330] At least one selected from the first capping layer 210 and the second capping layer 220 may each independently include at least one material selected from carbocyclic compounds, heterocyclic compounds, amine-based compounds, porphyrine derivatives, phthalocyanine derivatives, a naphthalocyanine derivatives, alkali metal complexes, and alkaline earth-based complexes. The carbocyclic compound, the heterocyclic compound, and the amine-based compound may be optionally substituted with a substituent containing at least one element selected from O, N, S, Se, Si, F, Cl, Br, and I. In one embodiment, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include an amine-based compound.


[0331] In one embodiment, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include the compound represented by Formula 201 or the compound represented by Formula 202.

[0332] In one or more embodiments, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include a compound selected from Compounds HT28 to HT33 and Compounds CP1 to CP5.



-continued

CP5



[0333] Hereinbefore, the organic light-emitting device according to an embodiment has been described in connection with FIGS. 1-4.

[0334] Layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region may be formed in a certain region by using one or more suitable methods selected from vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, ink-jet printing, laser-printing, and laser-induced thermal imaging.

[0335] When layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region are formed by vacuum deposition, for example, the vacuum deposition may be performed at a deposition temperature of about 100 to about 500° C., at a vacuum degree of about 10⁻⁸ to about 10⁻³ torr, and at a deposition rate of about 0.01 to about 100 Å/sec by taking into account a material to be included in a layer to be formed, and the structure of a layer to be formed.

[0336] When layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region are formed by spin coating, the spin coating may be performed at a coating speed of about 2000 rpm to about 5000 rpm and at a heat treatment temperature of about 80° C. to 200° C. by taking into account a material to be included in a layer to be formed, and the structure of a layer to be formed.

[0337] The term “C₁-C₆₀ alkyl group” as used herein refers to a linear or branched saturated aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms, and examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. A C₁-C₆₀ alkylene group used herein refers to a divalent group having the same structure as that of the C₁-C₆₀ alkyl group.

[0338] The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group having the same structure as that of the C₂-C₆₀ alkyl group, except for at least one carbon-carbon double bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethenyl group, a propenyl group, and a butenyl group. A C₂-C₆₀ alkenylene group used herein refers to a divalent group having the same structure as that of the C₂-C₆₀ alkenyl group.

[0339] The term “C₂-C₆₀ alkynyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon triple bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethynyl

group, and a propynyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having the same structure as that of the C₂-C₆₀ alkynyl group.

[0340] The term “C₁-C₆₀ alkoxy group” as used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group), and examples thereof include a methoxy group, an ethoxy group, and an isopropoxy group.

[0341] The term “C₃-C₁₀ cycloalkyl group” as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. A C₃-C₁₀ cycloalkylene group used herein refers to a divalent group having the same structure as that of the C₃-C₁₀ cycloalkyl group.

[0342] The term “C₁-C₁₀ heterocycloalkyl group” as used herein refers to a monovalent monocyclic group having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 10 carbon atoms, and examples thereof include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuranlyl group, and a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkyl group.

[0343] The term “C₃-C₁₀ cycloalkenyl group” as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof and no aromaticity, and examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. The term “C₃-C₁₀ cycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

[0344] The term “C₁-C₁₀ heterocycloalkenyl group” as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one carbon-carbon double bond in its ring. Examples of the C₁-C₁₀ heterocycloalkenyl group may include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuranlyl group, and a 2,3-dihydrothiophenyl group.

[0345] The term “C₁-C₁₀ heterocycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkenyl group.

[0346] The term “C₆-C₆₀ aryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C₆-C₆₀ arylene group used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Examples of the C₆-C₆₀ aryl group are a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

[0347] The term “C₁-C₆₀ heteroaryl group” as used herein refers to a monovalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. The term “C₁-C₆₀ heteroarylene group” as used herein refers to a divalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. Examples of the C₆-C₆₀ heteroaryl

group are a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinylnyl group, and an isoquinolinyl group. When the C₆-C₆₀ heteroaryl group and the C₆-C₆₀ heteroarylene group each include two or more rings, the rings may be fused to each other.

[0348] The term “C₆-C₆₀ aryloxy group” as used herein indicates —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and the term “C₆-C₆₀ arylthio group” as used herein indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

[0349] The term “monovalent non-aromatic condensed polycyclic group” as used herein refers to a monovalent group (for example, having 8 to 60 carbon atoms) having two or more rings condensed with each other, only carbon atoms as ring-forming atoms, and no aromaticity in its entire molecular structure. A detailed example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

[0350] The term “monovalent non-aromatic condensed heteropolycyclic group” as used herein refers to a monovalent group (for example, having 1 to 60 carbon atoms) having two or more rings condensed to each other, at least one heteroatom selected from N, O, Si, P, and S, other than carbon atoms, as a ring-forming atom, and no aromaticity in its entire molecular structure. An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. The term “divalent non-aromatic condensed heteropolycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0351] The term “C₅-C₆₀ carbocyclic group” as used herein refers to a monocyclic or polycyclic group having 5 to 60 carbon atoms in which a ring-forming atom is a carbon atom only. The C₅-C₆₀ carbocyclic group may be an aromatic carbocyclic group or a non-aromatic carbocyclic group. The C₅-C₆₀ carbocyclic group may be a ring, such as benzene, a monovalent group, such as a phenyl group, or a divalent group, such as a phenylene group. In one or more embodiments, depending on the number of substituents connected to the C₅-C₆₀ carbocyclic group, the C₅-C₆₀ carbocyclic group may be a trivalent group or a quadrivalent group.

[0352] The term “C₁-C₆₀ heterocyclic group” as used herein refers to a group having the same structure as the C₁-C₆₀ carbocyclic group, except that as a ring-forming atom, at least one heteroatom selected from N, O, Si, P, and S is used in addition to carbon (the number of carbon atoms may be in a range of 1 to 60).

[0353] At least one substituent of the substituted C₅-C₆₀ carbocyclic group, substituted C₁-C₆₀ heterocyclic group, substituted C₃-C₁₀ cycloalkylene group, substituted C₁-C₁₀ heterocycloalkylene group, substituted C₃-C₁₀ cycloalkenylene group, substituted C₁-C₁₀ heterocycloalkenylene group, substituted C₆-C₆₀ arylene group, substituted C₁-C₆₀ heteroarylene group, substituted divalent non-aromatic condensed polycyclic group, substituted divalent non-aromatic condensed heteropolycyclic group, substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, sub-

stituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0354] deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0355] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

[0356] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0357] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂);

[0358] wherein Q₁₁ to Q₁₃, Q₂₁ to Q₂₃ and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0359] The term “Ph”, as used herein, may refer to a phenyl group; the term “Me”, as used herein, may refer to a methyl group; the term “Et”, as used herein, may refer to an ethyl group; the terms “ter-Bu” or “But”, as used herein, may refer to a tert-butyl group; and the term “OMe” as used herein may refer to a methoxy group.

[0360] The term “biphenyl group” as used herein refers to “a phenyl group substituted with a phenyl group.” In other words, the “biphenyl group” is a substituted phenyl group having a C₆-C₆₀ aryl group as a substituent.

[0361] The “terphenyl group” used herein refers to “a phenyl group substituted with a biphenyl group.” In other words, the “terphenyl group” is a phenyl group having, as a substituent, a C₆-C₆₀ aryl group substituted with a C₆-C₆₀ aryl group.

[0362] * and *¹ used herein, unless defined otherwise, each refer to a binding site to a neighboring atom in a corresponding formula.


[0363] Hereinafter, a compound according to embodiments and an organic light-emitting device according to embodiments will be described in detail with reference to Synthesis Examples and Examples. The wording “B was used instead of A” used in describing Synthesis Examples refers to that an identical molar equivalent of B was used in place of A.


[0364] The following Examples and Comparative Examples are provided in order to highlight characteristics of one or more embodiments, but it will be understood that the Examples and Comparative Examples are not to be construed as limiting the scope of the embodiments, nor are the Comparative Examples to be construed as being outside the scope of the embodiments. Further, it will be understood that the embodiments are not limited to the particular details described in the Examples and Comparative Examples.

Synthesis Example

Synthesis Example 1: Synthesis of Compound 3

[0365]





Synthesis of Intermediate 3-1

[0366] 3.11 g (10 mmol) of 5-bromo-2-iodobenzaldehyde, 1.44 g (10 mmol) of 8-aminoquinoline, 0.23 g (0.25 mmol) of $\text{Pd}_2(\text{dba})_3$, 0.28 g (0.5 mmol) of dppf, and 2.76 g (20 mmol) of K_2CO_3 were dissolved in 250 mL of toluene, and then, the mixture was stirred at a temperature of 80° C. for 24 hours. The reaction solution was cooled to ambient temperature, immediately filtered through silica, and the filtrate was dried under reduced pressure. Then, 2.66 g (20 mmol) of AlCl_3 was added thereto and dissolved in 300 mL of toluene, followed by stirring at 80° C. for 24 hours. The reaction solution was cooled to ambient temperature, and then subjected to an extraction process three times by using 60 mL of water and 60 mL of diethyl ether. An organic layer obtained therefrom was dried by using magnesium sulfate and the residual obtained by evaporating a solvent therefrom was separation-purified by silica gel column chromatography to obtain 1.23 g (yield: 40%) of Intermediate 3-1. The obtained compound was identified by LC-MS.

[0367] $\text{C}_{16}\text{H}_{9}\text{BrN}_2$: M+1 309.16


Synthesis of Compound 3


[0368] 3.09 g (10 mmol) of Intermediate 3-1, 5.07 g (10 mmol) of 4'-((4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)naphthalen-1-yl)-[1,1'-biphenyl]-4-carbonitrile, 0.58 g (0.5 mmol) of $\text{Pd}(\text{PPh}_3)_4$, and 4.15 g (30.0 mmol) of K_2CO_3 were dissolved in a mixed solution including 180 mL of THF/ H_2O (2/1), and then, the mixture was stirred at a temperature of 80° C. for 16 hours. The reaction solution was cooled to ambient temperature, and then, subjected to an extraction process three times by using 60 mL of water and 60 mL of diethyl ether. An organic layer obtained therefrom was dried by using magnesium sulfate and the residual obtained by evaporating a solvent therefrom was separation-purified by silica gel column chromatography to obtain 3.65 g (yield 60%) of Compound 3. The obtained compound was confirmed by LC-MS and ^1H NMR.

[0369] $\text{C}_{45}\text{H}_{27}\text{N}_3$: M+1 609.72

Synthesis Example 2: Synthesis of Compound 11

[0370]





11

Synthesis of Compound 11

[0371] 3.49 g (yield 65%) of Compound 11 was obtained in the same manner as used to synthesize Compound 3, except that 2,4-diphenyl-6-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-1,3,5-triazine was used instead of 4'-(4-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)naphthalen-1-yl)-[1,1'-biphenyl]-4-carbonitrile. The obtained compound was confirmed by LC-MS and ^1H NMR.

[0372] $\text{C}_{37}\text{H}_{23}\text{N}_5$; $\text{M}+1$ 537.61


Synthesis Example 3: Synthesis of Compound 13

[0373]

Synthesis of Compound 13

[0374] 5.3 g (yield 80%) of Compound 13 was obtained in the same manner as used to synthesize Compound 3, except that 2,4-diphenyl-6-(4-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)naphthalen-1-yl)phenyl)-1,3,5-triazine was used instead of 4'-(4-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)naphthalen-1-yl)-[1,1'-biphenyl]-4-carbonitrile. The obtained compound was confirmed by LC-MS and ^1H NMR.

[0375] $\text{C}_{47}\text{H}_{29}\text{N}_5$; $\text{M}+1$ 663.76




3-1

13

Synthesis Example 4: Synthesis of Compound 21

[0376]



Synthesis of Intermediate 21-1

[0377] 1.39 g (yield 45%) of Intermediate 21-1 was obtained in the same manner as used to synthesize Intermediate 3-1, except that 2-bromobenzaldehyde was used instead of 5-bromo-2-iodobenzaldehyde and 5-bromo-8-aminoquinoline was used instead of 8-aminoquinoline. The obtained compound was identified by LC-MS.

[0378] C₁₆H₉BrN₂: M+1 309.15

Synthesis of Compound 21


[0379] 4.58 g (yield 75%) of Compound 21 was obtained in the same manner as used to synthesize Compound 3, except that Intermediate 21-1 was used instead of Intermediate 3-1.

[0380] The obtained compound was confirmed by LC-MS and ¹H NMR.


[0381] C₄₅H₂₇N₃: M+1 609.71

Synthesis Example 5: Synthesis of Compound 33

[0382]



-continued



33

Synthesis of Compound 33

[0383] 5.0 g (yield 70%) of Compound 33 was obtained in the same manner as used to synthesize Compound 3, except that Intermediate 21-1 was used instead of Intermediate 3-1 and 2,4-diphenyl-6-(4'-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)-[1,1'-binaphthalen]-4-yl)-1,3,5-triazine was used instead of 4'-(4-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)naphthalen-1-yl)-[1,1'-biphenyl]-4-carbonitrile. The obtained compound was confirmed by LC-MS and ^1H NMR.

[0384] $\text{C}_{51}\text{H}_{31}\text{N}_5$: M+1 713.8

Synthesis Example 6: Synthesis of Compound 34


[0385]

Synthesis of Compound 34


[0386] 2.42 g (yield 50%) of Compound 34 was obtained in the same manner as used to synthesize Compound 3, except that Intermediate 21-1 was used instead of Intermediate 3-1, and 2-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-1,10-phenanthroline was used instead of 4'-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)naphthalen-1-yl)-[1,1'-biphenyl]-4-carbonitrile. The

obtained compound was confirmed by LC-MS and ^1H NMR.

[0387] $\text{C}_{34}\text{H}_{20}\text{N}_4$: M+1 484.57




21-1



34

Synthesis Example 7: Synthesis of Compound 66

[0388]



Synthesis of Intermediate 66-1

[0389] 0.93 g (yield 30%) of Intermediate 66-1 was obtained in the same manner as used to synthesize Intermediate 3-1, except that 4-bromo-3-formylbenzonitrile was used instead of 5-bromo-2-iodobenzaldehyde, and 5-bromo-8-aminoquinoline was used instead of 8-aminoquinoline. The obtained compound was identified by LC-MS.

[0390] C₁₆H₉BrN₂: M+1 309.16

Synthesis of Compound 66


[0391] 4.48 g (yield 65%) of Compound 66 was obtained in the same manner as used to synthesize Compound 3,


except that Intermediate 66-1 was used instead of Intermediate 3-1, and 2,4-diphenyl-6-(4-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)naphthalen-1-yl)phenyl)-1,3,5-triazine was used instead of 4'-(4-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)naphthalen-1-yl)-[1,1'-biphenyl]-4-carbonitrile. The obtained compound was confirmed by LC-MS and ¹H NMR.

[0392] C₄₈H₂₈N₆: M+1 688.76

Synthesis Example 8: Synthesis of Compound 99

[0393]





Synthesis of Intermediate 99-1

[0394] 1.43 g (yield 40%) of Intermediate 99-1 was obtained in the same manner as used to synthesize Intermediate 3-1, except that 1-bromo-2-naphthaldehyde was used instead of 5-bromo-2-iodobenzaldehyde and 5-bromo-8-aminoquinoline was used instead of 8-aminoquinoline. The obtained compound was identified by LC-MS.

[0395] C₂₀H₁₁BrN₂: M+1 359.21

Synthesis of Compound 99


[0396] 4.28 g (yield 77%) of Compound 99 was obtained in the same manner as used to synthesize Compound 3,

except that Intermediate 99-1 was used instead of Intermediate 3-1, and diphenyl(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)phosphine oxide was used instead of 4'-(4-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)naphthalen-1-yl)-[1,1'-biphenyl]-4-carbonitrile. The obtained compound was confirmed by LC-MS and ¹H NMR.


[0397] C₃₈H₂₅N₂O₂P: M+1 556.58

Synthesis Example 9: Synthesis of Compound 105

[0398]



-continued



105

Synthesis of Intermediate 105-1

[0399] 1.23 g (yield 40%) of Intermediate 105-1 was obtained in the same manner as used to synthesize Intermediate 3-1, except that 2-bromobenzaldehyde was used instead of 5-bromo-2-iodobenzaldehyde, and 3-bromoquinolin-8-amine was used instead of 8-aminoquinoline. The obtained compound was identified by LC-MS.

[0400] C₁₆H₉BrN₂: M+1 309.15

Synthesis of Compound 105

[0401] 2.95 g (yield 55%) of Compound 105 was obtained in the same manner as used to synthesize Compound 3, except that Intermediate 105-1 was used instead of Intermediate 3-1, and 2,4-diphenyl-6-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-1,3,5-triazine was used

instead of 4'-(4-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)naphthalen-1-yl)-[1,1'-biphenyl]-4-carbonitrile. The obtained compound was confirmed by LC-MS and ¹H NMR.

[0402] C₃₇H₂₃N₅: M+1 537.64

[0403] ¹H NMR and LC-MS of the compounds synthesized according to Synthesis Examples 1 to 9 are shown in Table 1. Methods of synthesizing compounds other than the compound shown in Table 1 may be understandable by referring to the synthesis paths and source materials described above.

EXAMPLES

Example 1

[0404]

TABLE 1

Compound	¹ H NMR (CDCl ₃ , 400 MHz)	MS/FAB	
		found	calc.
3	9.22-9.20 (m, 1H), 9.01-8.99 (m, 1H), 8.86-8.84 (m, 1H) 8.70-8.68 (m, 2H), 8.55-8.78 (m, 9H), 8.45-8.43 (m, 2H) 8.28-8.34 (m, 3H), 8.20-8.18 (m, 1H), 7.97-8.07 (m, 3H) 7.76-7.90 (m, 2H), 7.46-7.44 (m, 2H)	609.72	609.73
11	9.23-9.20 (m, 1H), 8.79-8.75 (m, 1H), 8.65-8.72 (m, 2H) 8.59-8.55 (m, 1H), 8.51-8.57 (m, 2H), 8.35-8.32 (m, 1H) 8.18-8.33 (m, 8H), 7.85-8.05 (m, 7H)	537.61	537.63
13	9.21-9.18 (m, 1H), 8.80-8.85 (m, 3H), 8.71-8.67 (m, 1H) 8.57-8.69 (m, 4H), 8.42-8.51 (m, 5H), 8.40-8.38 (m, 1H) 8.19-8.27 (m, 4H), 8.04-8.14 (m, 3H), 7.89-8.03 (m, 3H) 7.74-7.70 (m, 4H)	663.76	663.78
21	9.30-9.28 (m, 1H), 9.22-9.20 (m, 1H), 8.98-8.95 (m, 1H) 8.84-8.81 (m, 1H), 8.62-8.73 (m, 4H), 8.60-8.58 (m, 2H) 8.49-8.60 (m, 4H), 8.45-8.41 (m, 2H), 8.18-8.34 (m, 3H) 8.00-8.08 (m, 3H), 7.76-7.91 (m, 3H), 7.46-7.43 (m, 2H)	609.71	609.73
33	7.75-7.87 (m, 5H), 7.95-8.06 (m, 3H), 8.08-8.18 (m, 3H) 8.26-8.24 (m, 1H), 8.32-8.43 (m, 6H), 8.45-8.53 (m, 2H) 8.56-8.54 (m, 1H), 8.64-8.71 (m, 2H), 8.74-8.72 (m, 1H) 8.80-8.87 (m, 2H), 8.90-8.88 (m, 1H), 9.05-9.03 (m, 1H) 9.16-9.14 (m, 1H), 9.22-9.20 (m, 1H), 9.29-9.27 (m, 1H)	713.8	713.84
34	7.97-7.97 (m, 1H), 8.03-8.24 (m, 4H), 8.26-8.33 (m, 3H) 8.37-8.35 (m, 1H), 8.45-8.41 (m, 1H), 8.52-8.48 (m, 1H) 8.62-8.72 (m, 5H), 8.76-8.74 (m, 1H), 8.73-8.81 (m, 2H) 9.22-9.20 (m, 1H)	484.57	484.56
66	7.69-7.65 (m, 4H), 7.94-8.04 (m, 2H), 8.05-8.27 (m, 7H) 8.34-8.30 (m, 1H), 8.46-8.44 (m, 4H), 8.62-8.68 (m, 2H) 8.71-8.68 (m, 1H), 8.80-8.87 (m, 5H), 9.23-9.20 (m, 1H) 9.36-9.33 (m, 1H)	688.76	688.79

TABLE 1-continued

Compound	¹ H NMR (CDCl ₃ , 400 MHz)	MS/FAB	
		found	calc.
99	7.26-7.37 (m, 8H), 7.45-7.42 (m, 2H), 7.95-8.05 (m, 4H) 8.09-8.23 (m, 4H), 8.43-8.55 (m, 2H), 8.64-8.62 (m, 1H) 8.68-8.78 (m, 2H), 8.89-8.85 (m, 1H), 9.52-9.50 (m, 1H)	556.58	556.6
105	7.68-7.64 (m, 4H), 7.95-8.16 (m, 4H), 8.26-8.22 (m, 1H) 8.21-8.19 (m, 1H), 8.32-8.42 (m, 7H), 8.63-8.60 (m, 1H) 8.70-8.65 (m, 1H), 8.75-8.87 (m, 3H), 9.49-9.44 (m, 1H)	537.64	537.63

[0405] A substrate with an anode including the structure of ITO/Ag/ITO (70/1000/70A) deposited thereon was cut to a size of 50 mm×50 mm×0.5 mm, and then, the result was sonicated with isopropyl alcohol and pure water, each for 5 minutes. Then, the result was cleaned by exposure to ultraviolet rays and ozone for 30 minutes. The resultant substrate was provided on a vacuum deposition apparatus.


[0406] Compound 301 (N-([1,1'-biphenyl]-4-yl)-9,9-dimethyl-N-(4-(9-phenyl-9H-carbazol-3-yl)phenyl)-9H-fluoren-2-amine) and F4-TCNQ were vacuum-codeposited on the resultant substrate at a weight ratio of 98:2 to form a hole injection layer having a thickness of 100 Å, and then, Compound 301 was vacuum-deposited on the hole injection layer to form a first hole transport layer having a thickness of 1,200 Å, and N,N-di([1,1'-biphenyl]-4-yl)-4'-(9H-carbazol-9-yl)-[1,1'-biphenyl]-4-amine (Compound HA) was vacuum-deposited on the first hole transport layer to form a second hole transport layer having a thickness of 100 Å. 9,10-di-naphthalene-2-yl-anthracene (ADN), which is a blue fluorescent host, and N,N,N',N'-tetraphenyl-pyrene-1,6-diamine (TPD), which is a blue fluorescent dopant, were co-deposited at a weight ratio 98:2 on the second hole transport layer to form an emission layer having a thickness of 300 Å. Subsequently, Compound 3 and LiQ were codeposited at a weight ratio of 5:5 on the emission layer to form an electron transport layer having a thickness of 300 Å. LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and then, Mg and Ag were vacuum-deposited thereon at a weight ratio of 90:10 to form a cathode having a thickness of 120 Å, thereby completing the manufacture of an organic light-emitting device.

Examples 2 to 9

[0407] Organic light-emitting devices were manufactured in the same manner as in Example 1, except that, in forming the electron transport layer, Compounds shown in Table 2 were used instead of Compound 3.


Comparative Example 1

[0408] An organic light-emitting device was manufactured in the same manner as in Example 1, except that, in forming the electron transport layer, 2-(4-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)-1-phenyl-1H-benzodimidazole (Compound A) was used instead of Compound 3.




Comparative Example 2

[0409] An organic light-emitting device was manufactured in the same manner as in Example 1, except that, in forming the electron transport layer, Compound B was used instead of Compound 3.



Comparative Example 3

[0410] An organic light-emitting device was manufactured in the same manner as in Example 1, except that, in forming the electron transport layer, Compound C was used instead of Compound 3.



[0411] Regarding the organic light-emitting devices, performance (driving voltage, luminance, efficiency, and color coordinates) at a current density of 10 mA/cm² and a time (T97) that passed until the initial luminance decreased by 97% at a current density of 1.0 mA/cm² was measured, and results thereof are shown in Table 2.

[0412] Color coordinates: Power was supplied by using a current-voltmeter (Kethley SMU 236) and measured by using a luminance meter PR650.

[0413] Efficiency: Power was supplied by using a current-voltmeter (Kethley SMU 236) and measured by using a luminance meter PR650.

TABLE 2

Material	Driving voltage (V)	Current density (mA/cm ²)	Efficiency (cd/A)	Color coordinate CIE(x, y)	T97 lifespan (@1.0 mA/cm ²)	
Example 1	Compound 3	3.84	10	5.3	0.140, 0.055	155
Example 2	Compound 11	3.65	10	5.72	0.141, 0.056	121
Example 3	Compound 13	3.73	10	5.44	0.141, 0.055	162
Example 4	Compound 21	3.80	10	5.28	0.140, 0.057	128
Example 5	Compound 33	3.91	10	5.60	0.142, 0.058	148
Example 6	Compound 34	3.82	10	5.34	0.141, 0.054	139
Example 7	Compound 66	3.77	10	5.22	0.141, 0.056	145
Example 8	Compound 99	4.1	10	5.28	0.141, 0.056	142
Example 9	Compound 105	3.78	10	5.33	0.141, 0.055	131
Comparative Example 1	Compound A	4.8	10	4.48	0.141, 0.054	77
Comparative Example 2	Compound B	4.2	10	4.85	0.141, 0.054	105
Comparative Example 3	Compound C	4.5	10	4.60	0.141, 0.056	98

[0414] Referring to Table 2, it may be seen that the organic light-emitting devices of Examples 1 to 9 had lower driving voltage, higher efficiency, and a longer T97 lifespan than the organic light-emitting devices of Comparative Examples 1 to 3.


[0415] An organic light-emitting device including the condensed cyclic compound according to an embodiment may have a low driving voltage, high efficiency, long lifespan, and high maximum quantum efficiency.

[0416] Example embodiments have been disclosed herein, and although specific terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. In some instances, as would be apparent to one of ordinary skill in the art as of the filing of the present application, features, characteristics,

and/or elements described in connection with a particular embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise specifically indicated. Accordingly, it will be understood by those of skill in the art that various changes in form and details may be made without departing from the spirit and scope of the present invention as set forth in the following claims.

What is claimed is:

1. A condensed cyclic compound represented by Formula 1:



wherein, in Formula 1,

A₁ is a benzene ring or a naphthalene ring,

R₁ to R₇ are each independently selected from a group represented by Formula 2, hydrogen, deuterium, —F,

—Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or

unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, $-\text{P}(=\text{S})(\text{Q}_1)(\text{Q}_2)$, $-\text{S}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, and $-\text{S}(=\text{O})_2(\text{Q}_1)(\text{Q}_2)$, provided that at least one of R_1 to R_7 is a group represented by Formula 2,



wherein, in Formulae 1 and 2,

$b7$ is an integer of 1 to 6, and when $b7$ is 2, 3, 4, 5, or 6, the $\text{R}_7(\text{s})$ are identical to or different from each other, L_{21} is a single bond, a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group, or a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,

$a21$ is an integer of 1 to 5, and when $a21$ is 2, 3, 4, or 5, the $\text{L}_{21}(\text{s})$ are identical to or different from each other,

Ar_{21} is selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryloxy group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylthio group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, $-\text{P}(=\text{S})(\text{Q}_1)(\text{Q}_2)$, $-\text{S}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, and $-\text{S}(=\text{O})_2(\text{Q}_1)(\text{Q}_2)$,

$b21$ is an integer of 1 to 8, and when $b21$ is 2, 3, 4, 5, 6, 7, or 8, the $\text{Ar}_{21}(\text{s})$ are identical to or different from each other,

two selected from L_{21} and Q_1 to Q_3 are separate or are linked to form a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,

at least one substituent of the substituted $\text{C}_5\text{-C}_{60}$ carbocyclic group, substituted $\text{C}_1\text{-C}_{60}$ heterocyclic group, substituted $\text{C}_1\text{-C}_{60}$ alkyl group, substituted $\text{C}_2\text{-C}_{60}$ alkenyl group, substituted $\text{C}_2\text{-C}_{60}$ alkynyl group, substituted $\text{C}_1\text{-C}_{60}$ alkoxy group, substituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, substituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, substituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, substituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, substituted $\text{C}_6\text{-C}_{60}$ aryl group, substituted $\text{C}_6\text{-C}_{60}$ aryloxy group, substituted $\text{C}_6\text{-C}_{60}$ arylthio group, substituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, substituted $\text{C}_1\text{-C}_{60}$ hetero aryloxy group, substituted monovalent non-aromatic condensed polycyclic group, or substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, and a $\text{C}_1\text{-C}_{60}$ alkoxy group;

a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, and a $\text{C}_1\text{-C}_{60}$ alkoxy group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a

nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{11})(\text{Q}_{12})(\text{Q}_{13})$, $-\text{N}(\text{Q}_1)(\text{Q}_{12})$, $-\text{B}(\text{Q}_{11})(\text{Q}_{12})$, $-\text{C}(=\text{O})(\text{Q}_{11})$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, and $-\text{P}(=\text{O})(\text{Q}_{11})(\text{Q}_{12})$;

a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{21})(\text{Q}_{22})(\text{Q}_{23})$, $-\text{N}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{B}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{C}(=\text{O})(\text{Q}_{21})$, $-\text{S}(=\text{O})_2(\text{Q}_{21})$, and $-\text{P}(=\text{O})(\text{Q}_{21})(\text{Q}_{22})$; and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$,

Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and

* indicates a binding site to a neighboring atom.

2. The condensed cyclic compound as claimed in claim 1, wherein L_{21} in Formula 2 is selected from:


a single bond, a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a

pyrenylene group, a chrysenylene group, a naphthacenylylene group, a picenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a rubicenylylene group, a coronenylylene group, an ovalenylylene group, a pyrrolylylene group, a thiophenylylene group, a furanylylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylylene group, a pyrazinylylene group, a pyrimidinylylene group, a pyridazinylylene group, an isoindolylylene group, an indolylylene group, an indazolylene group, a purinylylene group, a quinolinylylene group, an isoquinolinylylene group, a benzoquinolinylylene group, a phthalazinylylene group, a naphthyridinylylene group, a quinoxalinylylene group, a quinazolinylylene group, a cinolinolylylene group, a carbazolylene group, a phenanthridinylylene group, an acridinylylene group, a phenanthrolinylylene group, a benzophenanthrolinylylene group, a phenazinylylene group, a benzimidazolylene group, a benzofuranylylene group, a benzothiophenylylene group, a benzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylene group, and a dibenzocarbazolylene group; and










a phenylene group, a pentalenylylene group, an indenylene group, a naphthylene group, an azulenylylene group, a heptalenylylene group, an indacenylylene group, an acenaphthylene group, a fluorenylylene group, a spiro-bifluorenylylene group, a phenalenylylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylylylene group, a pyrenylene group, a chrysenylene group, a naphthacenylylene group, a picenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a rubicenylylene group, a coronenylylene group, an ovalenylylene group, a pyrrolylylene group, a thiophenylylene group, a furanylylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylylene group, a pyrazinylylene group, a pyrimidinylylene group, a pyridazinylylene group, an isoindolylylene group, an indolylylene group, an indazolylene group, a purinylylene group, a quinolinylylene group, an isoquinolinylylene group, a benzoquinolinylylene group, a phthalazinylylene group, a naphthyridinylylene group, a quinoxalinylylene group, a quinazolinylylene group, a cinolinolylylene group, a carbazolylene group, a phenanthridinylylene group, an acridinylylene group, a phenanthrolinylylene group, a benzophenanthrolinylylene group, a phenazinylylene group, a benzimidazolylene group, a benzofuranylylene group, a benzothiophenylylene group, a benzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylene group, and a dibenzocarbazolylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group,

a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenylylene group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylylylene group, a pyrenyl group, a chrysenyl group, a naphthacenylylene group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenylylene group, a pentacenylylene group, a rubicenylylene group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinylylene group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a benzophenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group.

3. The condensed cyclic compound as claimed in claim 1, wherein L₂₁ in Formula 2 is a single bond or a group represented by one of Formulae 3-1 to 3-5:




-continued




-continued

3-6




3-15

3-7




3-16

3-8




3-17

3-9




3-18

3-10




3-19

3-11




3-20

3-12




3-21

3-13




3-22


3-14



3-23




3-24




3-25


-continued




3-26




3-27




3-28



3-29




3-30




3-31


-continued




3-32



3-33



3-34



3-35

wherein, in Formulae 3-1 to 3-35,

Y_1 is O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, or $Si(Z_6)(Z_7)$,

Z_1 to Z_7 are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group,

a phenazinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

d2 is an integer of 0 to 2, and when d2 is 2, the $Z_1(s)$ are identical to or different from each other,

d3 is an integer of 0 to 3, and when d3 is 2 or 3, the $Z_1(s)$ are identical to or different from each other and the $Z_2(s)$ are identical to or different from each other,

d4 is an integer of 0 to 4, and when d4 is 2, 3, or 4, the $Z_1(s)$ are identical to or different from each other and the $Z_2(s)$ are identical to or different from each other,


d5 is an integer of 0 to 5, and when d5 is 2, 3, 4, or 5, the $Z_1(s)$ are identical to or different from each other and the $Z_2(s)$ are identical to or different from each other,

d6 is an integer of 0 to 6, and when d6 is 2, 3, 4, 5, or 6, the $Z_1(s)$ are identical to or different from each other and the $Z_2(s)$ are identical to or different from each other,


d8 is an integer of 0 to 8, and when d8 is 2, 3, 4, 5, 6, 7, or 8, the $Z_1(s)$ are identical to or different from each other, and

* and *' each indicate a binding site to a neighboring atom.


4. The condensed cyclic compound as claimed in claim 1, wherein L_{21} in Formula 2 is a single bond or a group represented by one of Formulae 4-1 to 4-8:




4-1




4-2




4-3



4-4




4-5




4-6

-continued

4-7



4-8



wherein, in Formulae 4-1 to 4-8,

Y_1 is O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, or $Si(Z_6)(Z_7)$,

Z_1 and Z_3 to Z_7 are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, and a naphthyl group, and

* and *' each indicates a binding site to a neighboring atom.

5. The condensed cyclic compound as claimed in claim 1, wherein Ar_{21} in Formula 2 is selected from:


a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluo-ranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinoliny group, a benzoquinoliny group, a phthalazinyl group, a naphthyridinyl group, a quinoxaliny group, a quinazoliny group, a cinnoliny group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a benzo-phenanthrolinyl group, a phenazinyl group, a benzoxazolyl group, a benzimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzoxazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and a benzocarbazolyl group;

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluo-ranthenyl group, a triphenylenyl group, a pyrenyl


group, a chrysenyl group, a naphthacenylyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a benzophenanthrolinyl group, a phenazinyl group, a benzoxazolyl group, a benzimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzoxazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and a benzocarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a C₆-C₂₀ aryl group, and a C₂-C₂₀ heteroaryl group; and

—Si(Q₁)(Q₂)(Q₃), —B(Q₁)(Q₂), —C(=O)(Q₁), —N(Q₁)(Q₂), —P(=O)(Q₁)(Q₂), —P(=S)(Q₁)(Q₂), —S(=O)(Q₁)(Q₂) and —S(=O)₂(Q₁)(Q₂), in which Q₁ to Q₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group


6. The condensed cyclic compound as claimed in claim 1, wherein Ar₂₁ in Formula 2 is —P(=O)(Q₁)(Q₂) or a group represented by one of Formulae 5-1 to 5-53:




5-1




5-2




5-3




5-4




5-5




5-6




5-7




5-8



5-9













5-10




5-11

-continued




-continued

5-12




5-22

5-13




5-23

5-14




5-24

5-15




5-25

5-16




5-26

5-17




5-27

5-18




5-28

5-19




5-29

5-20




5-30

5-21













5-31










5-32


-continued




-continued




-continued




5-50



5-51



5-52



5-53

wherein, in Formulae 5-1 to 5-53,

Y_{31} is O, S, C(Z_{33})(Z_{34}), N(Z_{35}), Si(Z_{36})(Z_{37}), or P(=O)(Z_{38}),

Z_{31} to Z_{38} , Q_1 , and Q_2 are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a spiro-fluorene-benzofluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a benzo-phenanthrolinyl group, a phenazinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

e_2 is an integer of 0 to 2, and when e_2 is 2, the $Z_{31}(s)$ are identical to or different from each other and $Z_{32}(s)$ are identical to or different from each other,


e_3 is an integer of 0 to 3, and when e_3 is 2 or 3, the $Z_{31}(s)$ are identical to or different from each other and the $Z_{32}(s)$ are identical to or different from each other,

e_4 is an integer of 0 to 4, and when e_4 is 2, 3, or 4, the $Z_{31}(s)$ are identical to or different from each other and the $Z_{32}(s)$ are identical to or different from each other, e_5 is an integer of 0 to 5, and when e_5 is 2, 3, 4, or 5, the $Z_{31}(s)$ are identical to or different from each other, e_6 is an integer of 0 to 6, and when e_6 is 2, 3, 4, 5, or 6, the $Z_{31}(s)$ are identical to or different from each other, e_7 is an integer of 0 to 7, and when e_7 is 2, 3, 4, 5, 6, or 7, the $Z_{31}(s)$ are identical to or different from each other,


e_9 is an integer of 0 to 9, and when e_9 is 2, 3, 4, 5, 6, 7, 8, or 9, the $Z_{31}(s)$ are identical to or different from each other, and

* indicates a binding site to a neighboring atom.


7. The condensed cyclic compound as claimed in claim 1, wherein Ar_{21} in Formula 2 is a group represented by one of Formulae 6-1 to 6-16:




6-1




6-2




6-3




6-4



6-5











6-6




6-7

-continued



-continued

6-8



6-16

6-9

wherein, in Formulae 6-1 to 6-16,

Ph indicates a phenyl group, and


* indicates a binding site to a neighboring atom.

6-10

8. The condensed cyclic compound as claimed in claim 1, wherein the compound represented by Formula 1 is represented by one of Formula 1-1 to Formula 1-4:

<Formula 1-1>


6-11



6-12

<Formula 1-2>


6-13



6-14

<Formula 1-3>



6-15



-continued



4

5





6

7





8

9





10

11




12

13





-continued

14




15


16



17





18




19

20





21



-continued



22

23





24

25





26

27




28

29




-continued


30




31




32




33




34



35





36




-continued

37

38





39





40

41




42

43




-continued


44




45



46





47










48







49







-continued









-continued








-continued








-continued



-continued





-continued



-continued



88

89





90

91





92

93









94


95



-continued




-continued




-continued

109





110





111

112





113

114




115

116




-continued

117



118



13. An organic light-emitting device, comprising:
 a first electrode;
 a second electrode facing the first electrode; and
 an organic layer between the first electrode and the second electrode, the organic layer including an emission layer, wherein the organic layer includes the condensed cyclic compound as claimed in claim 1.

14. The organic light-emitting device as claimed in claim 13, wherein:

the first electrode is an anode,
 the second electrode is a cathode, and
 the organic layer further includes a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode,

the hole transport region includes a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or any combination thereof, and

the electron transport region includes a hole blocking layer, an electron transport layer, an electron injection layer, or any combination thereof.

15. The organic light-emitting device as claimed in claim 14, wherein the electron transport region includes the condensed cyclic compound.

16. The organic light-emitting device as claimed in claim 14, wherein:

the electron transport region includes at least one of an electron transport layer and an electron injection layer, and

the at least one of the electron transport layer and the electron injection layer includes the condensed cyclic compound.

17. The organic light-emitting device as claimed in claim 13, wherein the emission layer includes the condensed cyclic compound.

18. The organic light-emitting device as claimed in claim 17, wherein:

the emission layer consists of the condensed cyclic compound; or

the emission layer further includes a dopant, and the dopant is included in an amount of about 0.1 parts by weight to about 50 parts by weight, based on 100 parts by weight of the emission layer.

19. The organic light-emitting device as claimed in claim 18, wherein the dopant is a phosphorescent dopant or a fluorescent dopant.

20. The organic light-emitting device as claimed in claim 14, wherein the hole transport region includes a p-dopant that has a lowest unoccupied molecular orbital (LUMO) energy level of less than -3.5 eV.

* * * * *

专利名称(译)	缩合环状化合物和包括其的有机发光器件		
公开(公告)号	US20190044072A1	公开(公告)日	2019-02-07
申请号	US15/866885	申请日	2018-01-10
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	SIM MUNKI PARK JUNHA LEE HYOYOUNG KIM YOUNGKOOK HWANG SEOKHWAN		
发明人	SIM, MUNKI PARK, JUNHA LEE, HYOYOUNG KIM, YOUNGKOOK HWANG, SEOKHWAN		
IPC分类号	H01L51/00 H01L51/50 H01L51/52 C07D471/04 C07F9/53		
CPC分类号	H01L51/0072 H01L51/506 H01L51/5262 H01L51/5064 C07D471/04 H01L51/0067 C07F9/5325 H01L51/5012 H01L51/5016 H01L51/5072 H01L51/5092 H01L2251/552 H01L51/5056 H01L51/5088 C07D519/00 C07F9/6561 C07F9/65685		
优先权	1020170099082 2017-08-04 KR		
外部链接	Espacenet USPTO		

摘要(译)

缩合环状化合物和有机发光器件，该化合物由式1表示：## STR00001
##

10

190
150
110