



(19) **United States**

(12) **Patent Application Publication** (10) **Pub. No.: US 2019/0280222 A1**
KIM et al. (43) **Pub. Date: Sep. 12, 2019**

(54) **ORGANOMETALLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

C07F 1/10 (2013.01); *C07F 1/12* (2013.01); *C07F 15/006* (2013.01)

(57) **ABSTRACT**

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin-si (KR)

An organometallic compound represented by Formula 1 or 2 and an organic light-emitting device including the same.

(72) Inventors: **Sungbum KIM**, Yongin-si (KR); **Soobyung KO**, Yongin-si (KR); **Junha PARK**, Yongin-si (KR); **Munki SIM**, Yongin-si (KR); **Heechoon AHN**, Yongin-si (KR); **Hyoyoung LEE**, Yongin-si (KR); **Mina JEON**, Yongin-si (KR); **Mieun JUN**, Yongin-si (KR); **Junghoon HAN**, Yongin-si (KR); **Youngkook KIM**, Yongin-si (KR); **Seokhwan HWANG**, Yongin-si (KR)

(21) Appl. No.: **16/203,554**

(22) Filed: **Nov. 28, 2018**



(30) **Foreign Application Priority Data**

Mar. 9, 2018 (KR) 10-2018-0028303

Publication Classification

(51) **Int. Cl.**
H01L 51/00 (2006.01)
C07F 15/00 (2006.01)
C07F 1/08 (2006.01)
C07F 1/10 (2006.01)
C07F 1/12 (2006.01)

(52) **U.S. Cl.**
CPC *H01L 51/0087* (2013.01); *H01L 51/0091* (2013.01); *C07F 15/0086* (2013.01); *H01L 51/5012* (2013.01); *C07F 1/08* (2013.01);



10

190
150
110

FIG. 1

10

190
150
110

FIG. 2

20

190
150
110
210

FIG. 3

30

220
190
150
110

FIG. 4

40

220
190
150
110
210

**ORGANOMETALLIC COMPOUND AND
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME**

CROSS-REFERENCE TO RELATED
APPLICATION

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2018-0028303, filed on Mar. 9, 2018, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

[0002] One or more embodiments relate to an organometallic compound and an organic light-emitting device including the same.

2. Description of the Related Art

[0003] Organic light-emitting devices are self-emission devices that produce full-color images, and also have wide viewing angles, high contrast ratios, short response times, and excellent characteristics in terms of brightness, driving voltage, and response speed, compared to devices in the art.


[0004] An example of such organic light-emitting devices may include a first electrode disposed on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode, which are sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, recombine in the emission layer to produce excitons. These excitons transit from an excited state to a ground state, thereby generating light.

SUMMARY

[0005] Aspects of the present disclosure are directed toward a novel organometallic compound and an organic light-emitting device including the same.


[0006] Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

[0007] According to an embodiment, an organometallic compound is represented by Formula 1 or 2:



-continued


Formula 2



[0008] In Formulae 1 and 2,

[0009] M_{11} may be selected from platinum (Pt), palladium (Pd), copper (Cu), zinc (Zn), silver (Ag), gold (Au), rhodium (Rh), iridium (Ir), ruthenium (Ru), rhenium (Re), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm),

[0010] A_{11} to A_{13} may each independently be selected from a C_5 - C_{60} carbocyclic group and a C_1 - C_{60} heterocyclic group, wherein A_{11} in Formula 1 is not represented by a



moiety,

[0011] Y_{11} to Y_{13} may each independently be selected from a carbon atom (C) and a nitrogen atom (N),

[0012] B_{11} to B_{14} may each independently be selected from a single bond, O, and S,

[0013] L_{11} to L_{14} may each independently be selected from a single bond, $*-O-*$, $*-S-*$, $*-C(R_{15})(R_{16})-*$, $*-C(R_{15})=*$, $*=C(R_{15})-*$, $*-C(R_{15})=C(R_{16})-*$, $*-C(=O)-*$, $*-C(=S)-*$, $*-C\equiv C-*$, $-B(R_{15})-*$, $*-N(R_{15})-*$, $*-P(R_{15})-*$, $*-Si(R_{15})(R_{16})-*$, $*-P(R_{15})(R_{16})-*$, and $*-Ge(R_{15})(R_{16})-*$,

[0014] a_{11} , a_{12} , and a_{14} may each independently be an integer from 0 to 3, and a_{13} may be an integer from 1 to 3, wherein at least two of a_{11} , a_{12} , and a_{14} may each independently be an integer from 1 to 3,

[0015] when a_{11} is 0, A_{11} and A_{12} may not be linked to each other, when a_{12} is 0, A_{12} and A_{13} may not be linked to each other, when a_{13} is 0, A_{13} and a nitrogen atom (N) may not be linked to each other, and when a_{14} is 0, A_{11} and X_{15} in Formula 1 and A_{11} and X_{19} in Formula 2 may not be linked to each other,

[0016] X_{11} may be N or $C(R_{14})$, X_{12} may be N or $C(R_{17})$, X_{13} may be N or $C(R_{18})$, and X_{14} may be N or $C(R_{19})$;

[0017] X_{15} may be N or $C(R_{20})$ when a_{14} is 0, and X_{15} may be C when a_{14} is not 0,

[0018] X_{16} may be $C(R_{21})(R_{22})$, X_{17} may be $C(R_{23})(R_{24})$, and X_{18} may be $C(R_{25})(R_{26})$,

[0019] X_{19} may be $C(R_{27})(R_{28})$ when a14 is 0, and X_{19} may be $C(R_{27})$ when a14 is not 0,

[0020] R_{11} to R_{28} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{10} cycloalkyl group, a substituted or unsubstituted C_1-C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3-C_{10} cycloalkenyl group, a substituted or unsubstituted C_1-C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, a substituted or unsubstituted C_1-C_{60} heteroaryl group, a substituted or unsubstituted C_1-C_{60} heteroaryloxy group, a substituted or unsubstituted C_1-C_{60} heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_1)(Q_2)(Q_3)$, $-B(Q_1)(Q_2)$, $-N(Q_1)(Q_2)$, $-P(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)(Q_1)$, $-S(=O)_2(Q_1)$, $-P(=O)(Q_1)(Q_2)$, and $-P(=S)(Q_1)(Q_2)$,

[0021] R_{15} and R_{11} , R_{15} and R_{12} , and/or R_{15} and R_{13} may optionally be linked to form a substituted or unsubstituted C_5-C_{60} carbocyclic group or a substituted or unsubstituted C_1-C_{60} heterocyclic group,

[0022] b11 to b13 may each independently be an integer from 1 to 8,

[0023] at least one substituent of the substituted C_5-C_{60} carbocyclic group, the substituted C_1-C_{60} heterocyclic group, the substituted C_1-C_{60} alkyl group, the substituted C_2-C_{60} alkenyl group, the substituted C_2-C_{60} alkynyl group, the substituted C_1-C_{60} alkoxy group, the substituted C_3-C_{10} cycloalkyl group, the substituted C_1-C_{10} heterocycloalkyl group, the substituted C_3-C_{10} cycloalkenyl group, the substituted C_1-C_{10} heterocycloalkenyl group, the substituted C_6-C_{60} aryl group, the substituted C_6-C_{60} aryloxy group, the substituted C_6-C_{60} arylthio group, the substituted C_1-C_{60} heteroaryl group, the substituted C_1-C_{60} heteroaryloxy group, the substituted C_1-C_{60} heteroarylthio group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0024] deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, and a C_1-C_{60} alkoxy group;

[0025] a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, and a C_1-C_{60} alkoxy group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_1-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic

group, $-Si(Q_{11})(Q_{12})(Q_{13})$, $-N(Q_{11})(Q_{12})$, $-B(Q_{11})(Q_{12})$, $-C(=O)(Q_{11})$, $-S(=O)_2(Q_{11})$, and $-P(=O)(Q_{11})(Q_{12})$;

[0026] a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_1-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0027] a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_1-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, a C_1-C_{60} alkoxy group, a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_1-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_{21})(Q_{22})(Q_{23})$, $-N(Q_{21})(Q_{22})$, $-B(Q_{21})(Q_{22})$, $-C(=O)(Q_{21})$, $-S(=O)_2(Q_{21})$, and $-P(=O)(Q_{21})(Q_{22})$; and

[0028] $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, $-B(Q_{31})(Q_{32})$, $-C(=O)(Q_{31})$, $-S(=O)_2(Q_{31})$, and $-P(=O)(Q_{31})(Q_{32})$,

[0029] Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, a C_1-C_{60} alkoxy group, a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_1-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C_1-C_{60} alkyl group substituted with at least one selected from deuterium, $-F$, and a cyano group, a C_6-C_{60} aryl group substituted with at least one selected from deuterium, $-F$, and a cyano group, a biphenyl group, and a terphenyl group, and

[0030] *, **, and *** each indicate a binding site to a neighboring atom.

[0031] According to another embodiment, an organic light-emitting device includes: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode and including an emission layer, wherein the organic layer further includes at least one of the organometallic compound represented by Formula 1 or 2.

BRIEF DESCRIPTION OF THE DRAWINGS

[0032] These and/or other aspects will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with the accompanying drawings in which:

[0033] FIG. 1 is a schematic diagram illustrating a structure of an organic light-emitting device according to an embodiment;

[0034] FIG. 2 is a schematic diagram illustrating a structure of an organic light-emitting device according to an embodiment;

[0035] FIG. 3 is a schematic diagram illustrating a structure of an organic light-emitting device according to an embodiment; and

[0036] FIG. 4 is a schematic diagram illustrating a structure of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

[0037] The present disclosure will now be described more fully with reference to exemplary embodiments. The disclosure may, however, be embodied in many different forms and should not be construed as being limited to the embodiments set forth herein; rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the concept of the disclosure to those skilled in the art. Enhancements, features, and how to achieve them of the present invention will become apparent by reference to the embodiment that will be described later in more detail, together with the accompanying drawings. This invention may, however, be embodied in many different forms and should not be limited to the exemplary embodiments.

[0038] Hereinafter, embodiments are described in more detail by referring to the attached drawings, and in the drawings, like reference numerals denote like elements, and a redundant explanation thereof will not be provided herein.

[0039] As used herein, the singular forms “a,” “an” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

[0040] It will be further understood that the terms “comprises” and/or “comprising” as used herein specify the presence of stated features or components, but do not preclude the presence or addition of one or more other features or components.


[0041] It will be understood that when a layer, region, or component is referred to as being “on” or “onto” another layer, region, or component, it may be directly or indirectly formed on the other layer, region, or component. That is, for example, intervening layers, regions, or components may be present.

[0042] Sizes of components in the drawings may be exaggerated for convenience of explanation. In other words, because sizes and thicknesses of components in the drawings are arbitrarily illustrated for convenience of explanation, the following embodiments of the present disclosure are not limited thereto. Also, any numerical range recited herein is intended to include all sub-ranges of the same numerical precision subsumed within the recited range. For example, a range of “1.0 to 10.0” is intended to include all subranges between (and including) the recited minimum value of 1.0 and the recited maximum value of 10.0, that is, having a minimum value equal to or greater than 1.0 and a maximum value equal to or less than 10.0, such as, for example, 2.4 to 7.6. Any maximum numerical limitation recited herein is intended to include all lower numerical limitations subsumed therein and any minimum numerical


limitation recited in this specification is intended to include all higher numerical limitations subsumed therein. Accordingly, Applicant reserves the right to amend this specification, including the claims, to expressly recite any sub-range subsumed within the ranges expressly recited herein.

[0043] According to an embodiment of the present disclosure, an organometallic compound is represented by Formula 1 or 2:

Formula 1



Formula 2




[0044] In Formulae 1 and 2, M_{11} may be selected from platinum (Pt), palladium (Pd), copper (Cu), zinc (Zn), silver (Ag), gold (Au), rhodium (Rh), iridium (Ir), ruthenium (Ru), rhenium (Re), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm).

[0045] In one embodiment, M_{11} may be selected from Pt, Pd, Cu, Ag, and Au.

[0046] For example, M_{11} may be Pt, Pd, or Au, but embodiments of the present disclosure are not limited thereto.


[0047] In Formulae 1 and 2, A_1 to A_{13} may each independently be selected from a C_5 - C_{60} carbocyclic group and a C_1 - C_{60} heterocyclic group, wherein A_{11} in Formula 1 is not represented by




moiety.

[0048] In one embodiment, A₁₁ to A₁₃ may each independently be selected from a benzene group, a naphthalene group, an anthracene group, a phenanthrene group, an azulene group, a triphenylene group, a pyrene group, a chrysene group, a cyclopentadiene group, a 1,2,3,4-tetrahydronaphthalene group, a furan group, a thiophene group, a silole group, an indene group, a fluorene group, an indole group, a carbazole group, a benzofuran group, a dibenzofuran group, a benzothiophene group, a dibenzothiophene group, a benzosilole group, a dibenzosilole group, an indenopyridine group, an indolopyridine group, a benzofuopyridine group, a benzothienopyridine group, a benzosilolopyridine group, an indenopyrimidine group, an indolopyrimidine group, a benzofuopyrimidine group, a benzothienopyrimidine group, a benzosilolopyrimidine group, a dihydropyridine group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a phenanthroline group, a pyrrole group, a pyrazole group, an imidazole group, a 2,3-dihydroimidazole group, a triazole group, a 2,3-dihydrotriazole group, an oxazole group, an isoxazole group, a thiazole group, an isothiazole group, an oxadiazole group, a thiadiazole group, a benzopyrazole group, a benzimidazole group, a 2,3-dihydrobenzimidazole group, an imidazopyridine group, a 2,3-dihydroimidazopyridine group, an imidazopyrimidine group, a 2,3-dihydroimidazopyrimidine group, an imidazopyrazine group, a 2,3-dihydroimidazopyrazine group, a benzoxazole group, a benzothiazole group, a benzoaxadiazole group, a benzothiadiazole group, a 5,6,7,8-tetrahydroisoquinoline group, and a 5,6,7,8-tetrahydroquinoline group.


[0049] In one or more embodiments, A₁₁ to A₁₃ may each independently be selected from groups represented by Formulae 3-1(1) to 3-1(31) and 3-2(1) to 3-2(19):




3-1(1)




3-1(2)




3-1(3)




3-1(4)




3-1(5)




3-1(6)




3-1(7)



3-1(8)










3-1(9)



3-1(10)


-continued

-continued




-continued

3-1(11)




3-1(18)

3-1(12)




3-1(19)

3-1(13)




3-1(19)

3-1(14)




3-1(20)

3-1(15)




3-1(21)

3-1(16)




3-1(22)


3-1(17)



3-1(23)












3-1(24)




3-1(25)

-continued




-continued

3-1(26)




3-2(4)

3-1(27)




3-2(5)

3-1(28)




3-2(6)

3-1(29)




3-2(7)

3-1(30)




3-2(8)

3-1(31)




3-2(9)

3-2(1)




3-2(10)

3-2(2)




3-2(11)


-continued




3-2(12)




3-2(13)




3-2(14)




3-2(15)



3-2(16)




3-2(17)



3-2(18)

-continued



3-2(19)

[0050] In Formulae 3-1(1) to 3-1(31) and 3-2(1) to 3-2(19),

[0051] Y_{15} may be Y_{11} , Y_{12} , or Y_{13} ,

[0052] R_{31} and R_{32} may each independently be defined the same as R_{11} in Formulae 1 and 2,

[0053] b_{32} may be 1 or 2,

[0054] b_{33} may be 1, 2, or 3,

[0055] b_{34} may be 1, 2, 3, or 4,

[0056] b_{35} may be 1, 2, 3, 4, or 5,

[0057] * indicates a binding site to M_{11} , and

[0058] *' and *'' each indicate a binding site to a neighboring atom.

[0059] For example, A_{11} to A_{13} may each independently be selected from groups represented by Formulae 3-1(1) to 3-1(5) and 3-2(1) to 3-2(4), but embodiments of the present disclosure are not limited thereto.

[0060] In one embodiment, A_{11} to A_{13} may each independently be selected from groups represented by Formulae 3-1(1), 3-1(4), 3-2(1), and 3-2(3), but embodiments of the present disclosure are not limited thereto.

[0061] In one embodiment, A_{11} may be a group represented by Formula 3-1(1) or 3-2(1), and A_{12} and A_{13} may each independently be a group represented by Formula 3-1(1), 3-2(1), or 3-2(3), but embodiments of the present disclosure are not limited thereto.

[0062] In one embodiment, R_{31} and R_{32} may each independently be selected from:

[0063] hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0064] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a phenyl group, and a biphenyl group;

[0065] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a

quinoxaliny group, a benzoquinoxaliny group, a quinazoliny group, a benzoquinazoliny group, a cinnoliny group, a phenanthridiny group, an acridiny group, a phenanthroliny group, a phenaziny group, a benzimidazoliny group, a benzofurany group, a benzothiopheny group, a benzosiloly group, a benzothiazoliny group, a benzoisothiazoliny group, a benzoxazoliny group, a benzoisoxazoliny group, a triazoliny group, a tetrazoliny group, a thiadiazoliny group, an oxadiazoliny group, a triazininy group, a carbazoliny group, a dibenzofurany group, a dibenzothiopheny group, a dibenzosiloly group, a benzocarbazoliny group, a naphtho benzofurany group, a naphtho benzothiopheny group, a naphthobenzosiloly group, a dibenzocarbazoliny group, a dinaphthofurany group, a dinaphtho thiopheny group, a dinaphtho siloly group, an imidazopyridiny group, an imidazopyrimidiny group, an oxazolopyridiny group, a thiazolopyridiny group, a benzonaphthyridiny group, an azafluoreny group, an azaspiro-bifluoreny group, an azacarbazoliny group, an azadibenzofurany group, an azadibenzothiopheny group, an azadibenzosiloly group, an indenopyrroly group, an indolopyrroly group, an indenocarbazoliny group, and an indolocarbazoliny group;

[0066] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indaceny group, an acenaphthyl group, a fluoreny group, a spiro-bifluoreny group, a benzofluoreny group, a dibenzofluoreny group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a siloly group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, an isoquinoliny group, a phthalazinyl group, a naphthyridinyl group, a quinoxaliny group, a benzoquinoxaliny group, a quinazoliny group, a benzoquinazoliny group, a cinnoliny group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenaziny group, a benzimidazolyl group, a benzofurany group, a benzothiophenyl group, a benzosiloly group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofurany group, a dibenzothiophenyl group, a dibenzosiloly group, a benzocarbazolyl group, a naphtho benzofurany group, a naphtho benzothiophenyl group, a naphthobenzosiloly group, a dibenzocarbazolyl group, a dinaphthofurany group, a dinaphtho thiophenyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluoreny group, an azaspiro-bifluoreny group, an azacarbazolyl group, an azadibenzofurany group, an azadibenzothiophenyl group, an azadibenzosiloly group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a C₁-C₂₀ alkyl group,

a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indaceny group, an acenaphthyl group, a fluoreny group, a spiro-bifluoreny group, a benzofluoreny group, a dibenzofluoreny group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a siloly group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, an isoquinoliny group, a phthalazinyl group, a naphthyridinyl group, a quinoxaliny group, a benzoquinoxaliny group, a quinazoliny group, a benzoquinazoliny group, a cinnoliny group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenaziny group, a benzimidazolyl group, a benzofurany group, a benzothiophenyl group, a benzosiloly group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofurany group, a dibenzothiophenyl group, a dibenzosiloly group, a benzocarbazolyl group, a naphtho benzofurany group, a naphtho benzothiophenyl group, a naphthobenzosiloly group, a dibenzocarbazolyl group, a dinaphthofurany group, a dinaphtho thiophenyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluoreny group, an azaspiro-bifluoreny group, an azacarbazolyl group, an azadibenzofurany group, an azadibenzothiophenyl group, an azadibenzosiloly group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)(Q₃₁), —S(=O)₂(Q₃₁), —P(=O)(Q₃₁)(Q₃₂), and —P(=S)(Q₃₁)(Q₃₂); and

[0067] —Si(Q₁)(Q₂)(Q₃), —B(Q₁)(Q₂), —N(Q₁)(Q₂), —P(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂), and

[0068] Q₁ to Q₃ and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C₁-C₆₀ alkyl group substituted with at least one selected from deuterium, —F, and a cyano group, a C₆-C₆₀ aryl group substituted with at least one selected from deuterium, —F, and a cyano group, a biphenyl group, and a terphenyl group.

[0069] In one or more embodiments, R_{31} and R_{32} may each independently be selected from:

[0070] hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, and a triazinyl group;

[0071] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a triazinyl group, —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), and —B(Q_{31})(Q_{32}); and

[0072] —Si(Q_1)(Q_2)(Q_3), —B(Q_1)(Q_2), and —N(Q_1)(Q_2), and

[0073] Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a C_1 - C_{20} alkyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a naphthyl group, a biphenyl group, and a terphenyl group.

[0074] In Formulae 1 and 2, Y_{11} to Y_{13} may each independently be selected from carbon atom (C) and nitrogen atom (N).

[0075] In one embodiment, Y_{11} and Y_{12} may each be C, and Y_{13} may be N;

[0076] Y_{11} and Y_{12} may each be N, and Y_{13} may be C;

[0077] Y_{11} and Y_{13} may each be C, and Y_{12} may be N;

[0078] Y_{11} and Y_{13} may each be N, and Y_{12} may be C;

[0079] Y_{12} and Y_{13} may each be C, and Y_{11} may be N; or

[0080] Y_{12} and Y_{13} may each be N, and Y_{11} may be C.

[0081] For example, Y_{12} and Y_{13} may each be C, and Y_{11} may be N, but embodiments of the present disclosure are not limited thereto.

[0082] In Formulae 1 and 2, B_{11} to B_{14} may each independently be selected from a single bond, O, and S.

[0083] In one embodiment, B_{11} to B_{14} may each be a single bond.

[0084] In one or more embodiments, B_{11} to B_{14} may each be a single bond,

[0085] a bond between M_{11} and Y_{11} and a bond between M_{11} and Y_{12} may each be a covalent bond, and a bond between M_{11} and Y_{13} may be a coordinate bond;

[0086] a bond between M_{11} and Y_{11} and a bond between M_{11} and Y_{13} may each be a covalent bond, and a bond between M_{11} and Y_{12} may be a coordinate bond; or

[0087] a bond between M_{11} and Y_{12} and a bond between M_{11} and Y_{13} may each be a covalent bond, and a bond between M_{11} and Y_{11} may be a coordinate bond.

[0088] For example, B_{11} to B_{14} may each be a single bond, the bond between M_{11} and Y_{12} and the bond between M_{11} and Y_{13} may each be a covalent bond, and a bond between M_{11} and Y_{11} may be a coordinate bond, but embodiments of the present disclosure are not limited thereto.

[0089] In Formulae 1 and 2, L_{11} to L_{14} may each independently be selected from a single bond, $*-O-*$, $*-S-*$, $*-C(R_{15})(R_{16})-*$, $*-C(R_{15})=*$, $*=C(R_{15})-*$, $*-C(R_{15})=C(R_{16})-*$, $*-C(=O)-*$, $*-C(=S)-*$, $*-C\equiv C-*$, $*-B(R_{15})-*$, $*-N(R_{15})-*$, $*-P(R_{15})-*$, $*-Si(R_{15})(R_{16})-*$, $*P(R_{15})(R_{16})-*$, and $*-Ge(R_{15})(R_{16})-*$.

[0090] In one embodiment, L_{11} to L_{14} may each independently be selected from a single bond, $*-O-*$, $*-S-*$, $*-C(R_{15})(R_{16})-*$, $*-C(R_{15})=*$, $*=C(R_{15})-*$, $*-B(R_{15})-*$, $*-N(R_{15})-*$, $*-Si(R_{15})(R_{16})-*$, and $*-P(R_{15})(R_{16})-*$.

[0091] In one or more embodiments, L_{11} to L_{14} may each independently be selected from a single bond, $*-O-*$, and $*-N(R_{15})-*$.

[0092] In one or more embodiments, L_{11} and L_{12} may each independently be selected from $*-O-*$ and $*-N(R_{15})-*$, and L_{13} and L_{14} may each independently be selected from a single bond, $*-O-*$, and $*-N(R_{15})-*$.

[0093] In Formulae 1 and 2, a_{11} , a_{12} , and a_{14} may each independently be an integer from 0 to 3, and a_{13} may be an integer from 1 to 3. At least two of a_{11} , a_{12} , and a_{14} may each independently be an integer from 1 to 3.

[0094] When a_{11} is 0, A_{11} and A_{12} may not be linked to each other, when a_{12} is 0, A_{12} and A_{13} may not be linked to each other, when a_{13} is 0, A_{13} and a nitrogen atom (N) may not be linked to each other, and when a_{14} is 0, A_{11} and X_{15} in Formula 1 and A_{11} and X_{19} in Formula 2 may not be linked to each other.

[0095] a_{11} indicates the number of $L_{11}(s)$, wherein, when a_{11} is two or more, two or more $L_{11}(s)$ may be identical to or different from each other. a_{12} indicates the number of $L_{12}(s)$, wherein, when a_{12} is two or more, two or more $L_{12}(s)$ may be identical to or different from each other. a_{13} indicates the number of $L_{13}(s)$, wherein, when a_{13} is two or more, two or more $L_{13}(s)$ may be identical to or different from each other. a_{14} indicates the number of $L_{14}(s)$, wherein, when a_{14} is two or more, two or more $L_{14}(s)$ may be identical to or different from each other.

[0096] In one embodiment, a_{11} to a_{13} may each be 1, and a_{14} may be 0;

[0097] a_{12} to a_{14} may each be 1, and a_{11} may be 0; or

[0098] a_{11} , a_{13} , and a_{14} may each be 1, and a_{12} may be 0.

[0099] In one or more embodiments, a_{11} to a_{13} may each be 1, and a_{14} may be 0.

[0100] In one or more embodiments, a_{11} to a_{13} may each be 1, a_{14} may be 0, L_{11} and L_{12} may each independently be selected from $*-O-*$ and $*-N(R_{15})-*$, and L_{13} may be a single bond.

[0101] In Formulae 1 and 2, X_{11} may be N or C(R_{14}), X_{12} may be N or C(R_{17}), X_{13} may be N or C(R_{18}), and X_{14} may be N or C(R_{19}),

[0102] X_{15} may be N or $C(R_{20})$ when a14 is 0, and X_{15} may be C when a14 is not 0,

[0103] X_{16} may be $C(R_{21})(R_{22})$, X_{17} may be $C(R_{23})(R_{24})$, and X_{18} may be $C(R_{25})(R_{26})$, and

[0104] X_{19} may be $C(R_{27})(R_{28})$ when a14 is 0, and X_{19} may be $C(R_{27})$ when a14 is not 0.

[0105] In one embodiment, in Formula 1, X_{12} may be $C(R_{17})$, X_{13} may be $C(R_{18})$, and X_{14} may be $C(R_{19})$, and

[0106] X_{15} may be $C(R_{20})$ when a14 is 0, and X_{15} may be C when a14 is not 0.

[0107] In Formulae 1 and 2, R_{11} to R_{28} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_1)(Q_2)(Q_3), —B(Q_1)(Q_2), —N(Q_1)(Q_2), —P(Q_1)(Q_2), —C(=O)(Q_1), —S(=O)(Q_1), —S(=O)₂(Q_1), —P(=O)(Q_1)(Q_2), and —P(=S)(Q_1)(Q_2), and

[0108] Q_1 to Q_3 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C_1 - C_{60} alkyl group substituted with at least one selected from deuterium, —F, and a cyano group, a C_6 - C_{60} aryl group substituted with at least one selected from deuterium, —F, and a cyano group, a biphenyl group, and a terphenyl group.

[0109] Here, R_{15} and R_{11} ; R_{15} and R_{12} ; and/or R_{15} and R_{13} may optionally be linked to form a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group. For example, when L_{11} is *—N(R_{15})—*, R_{15} may optionally be linked with R_{11} to form a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group.

[0110] In one embodiment, R_{11} to R_{28} may each independently be selected from:

[0111] hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0112] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a phenyl group, and a biphenyl group;

[0113] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphtho benzofuranyl group, a naphtho benzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphtho thiophenyl group, a dinaphtho silolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group;

[0114] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a

phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzisothiazolyl group, a benzoxazolyl group, a benzisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphtho benzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphtho thiophenyl group, a dinaphtho silolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzisothiazolyl group, a benzoxazolyl group, a benzisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphtho benzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphtho thiophenyl group, a dinaphtho silolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, an indolocarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂),

—B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)(Q₃₁), —S(=O)₂(Q₃₁), —P(=O)(Q₃₁)(Q₃₂), and —P(=S)(Q₃₁)(Q₃₂); and [0115] —Si(Q₁)(Q₂)(Q₃), —B(Q₁)(Q₂), —N(Q₁)(Q₂), —P(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂), and

[0116] Q₁ to Q₃ and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C₁-C₆₀ alkyl group substituted with at least one selected from deuterium, —F, and a cyano group, a C₆-C₆₀ aryl group substituted with at least one selected from deuterium, —F, and a cyano group, a biphenyl group, and a terphenyl group.

[0117] In one or more embodiments, R₁₁ to R₂₈ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0118] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂) and —B(Q₃₁)(Q₃₂); and

[0119] —Si(Q₁)(Q₂)(Q₃), —B(Q₁)(Q₂), and —N(Q₁)(Q₂), and

[0120] Q₁ to Q₃ and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a C₁-C₂₀ alkyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a naphthyl group, a biphenyl group, and a terphenyl group.

[0121] In one or more embodiments, R₁₁ to R₂₈ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a methyl group, an ethyl group, a propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a

sec-butyl group, ter-butyl group, pentyl group, an isoamyl group, a hexyl group, a phenyl group, a biphenyl group, a naphthyl group, and a pyridinyl group.

[0122] In Formulae 1 and 2, b11 to b13 may each independently be an integer from 1 to 8.

[0123] b11 indicates the number of $R_{11}(s)$, wherein, when b11 is two or more, two or more $R_{11}(s)$ may be identical to or different from each other. b12 indicates the number of $R_{12}(s)$, wherein, when b12 is two or more, two or more $R_{12}(s)$ may be identical to or different from each other. b13 indicates the number of $R_{13}(s)$, wherein, when b13 is two or more, two or more $R_{13}(s)$ may be identical to or different from each other.

[0124] In one embodiment, L_{11} may be $^*C(R_{15})(R_{16})-^*$, $^*N(R_{15})-^*$, or $^*Si(R_{15})(R_{16})-^*$, and

[0125] R_{15} and R_{11} may be linked to form a substituted or unsubstituted C_5-C_{60} carbocyclic group or a substituted or unsubstituted C_1-C_{60} heterocyclic group, or R_{15} and R_{12} may be linked to form a substituted or unsubstituted C_5-C_{60} carbocyclic group or a substituted or unsubstituted C_1-C_{60} heterocyclic group.

[0126] In one or more embodiments, L_{11} may be $^*N(R_{15})-^*$,






[0127] R_{15} and R_{11} may be linked to form a substituted or unsubstituted C_1-C_{60} heterocyclic group, or R_{15} and R_{12} may be linked to form a substituted or unsubstituted C_1-C_{60} heterocyclic group.

[0128] In one embodiment, the organometallic compound may be represented by Formula 1-1 or 1-2:


[0129] In Formulae 1-1 and 1-2,

[0130] M_{11} , A_{11} to A_{13} , Y_{11} to Y_{13} , B_{11} to B_{14} , L_{11} to L_{13} , a11 to a13, R_{11} to R_{28} , and b11 to b13 are the same as described in Formulae 1 and 2.

[0131] In one embodiment, the organometallic compound may be selected from Compounds 1 to 15, but embodiments of the present disclosure are not limited thereto:




-continued




5


-continued




10




6




11




7




12




8



13




9



14

-continued



[0132] The organometallic compound represented by Formula 1 or 2 may include at least one imidazopyridine ring or tetrahydroimidazopyridine ring in a tetradentate ligand. A binding site of the imidazopyridine ring or the tetrahydroimidazopyridine ring and the core metal may be a carbene. Therefore, lowest unoccupied molecular orbital (LUMO) energy of the organometallic compound may increase, and an emission wavelength may be shifted to a short wavelength, thereby emitting blue light having high color purity.

[0133] In addition, N—C bond between a nitrogen atom of a carbene and a substituent linked to the nitrogen atom is low in chemical and electrical stability and thus may be easily decomposed. Therefore, when a compound having the carbene structure is utilized in the organic light-emitting device, the lifespan of the organic light-emitting device may be shortened. The organometallic compound represented by Formula 1 or 2 may include a structure in which the substituent linked to the nitrogen atom of the carbene is linked to another adjacent substituent to form a condensed ring, for example, an imidazopyridine ring or a tetrahydroimidazopyridine ring. In addition, the nitrogen atom of the carbene may be linked to an adjacent ring linked to the core metal, for example, ring A₁₃. That is, the organometallic compound represented by Formula 1 or 2 may suppress the decomposition of the N—C bond between the nitrogen atom of the carbene and the substituent linked to the nitrogen atom. Therefore, an electronic device, for example, an organic light-emitting device, which includes the organometallic compound, may have a low driving voltage, high efficiency, high luminance, and a long lifespan.

[0134] The organometallic compound represented by Formula 1 or 2 may be synthesized utilizing suitable (e.g., known) organic synthesis methods.

[0135] The organometallic compound represented by Formulae 1 or 2 may be utilized between a pair of electrodes of an organic light-emitting device. For example, the organometallic compound may be included in the emission layer. The organometallic compound included in the emission layer may act as a dopant.

[0136] According to another embodiment, an organic light-emitting device includes: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode and including an emission layer, wherein the organic layer includes at least one of the organometallic compound represented by Formula 1 or 2.

[0137] The expression “(an organic layer) includes at least one of organometallic compounds” as used herein may include a case in which “(an organic layer) includes the same

(e.g., identical) organometallic compounds represented by Formula 1 or 2” and a case in which “(an organic layer) includes two or more different organometallic compounds represented by Formula 1 or 2.”

[0138] For example, the organic layer may include, as the organometallic compound, only Compound 1. In this regard, Compound 1 may exist in an emission layer of the organic light-emitting device. In one or more embodiments, the organic layer may include, as the organometallic compound, Compound 1 and Compound 2. In this case, Compound 1 and Compound 2 may be present in the same layer (for example, both Compound 1 and Compound 2 may be present in the emission layer), or may be on different layers (for example, Compound 1 may be present in the emission layer and Compound 2 may be present in the electron transport layer).

[0139] In one embodiment, the emission layer may include the organometallic compound.

[0140] In one or more embodiments, the emission layer may include (e.g., consist of) the organometallic compound or may include the organometallic compound and a host, and an amount of the organometallic compound in the emission layer may be in a range of about 0.01 parts by weight to about 50 parts by weight based on 100 parts by weight of the emission layer.

[0141] In one embodiment, the host may include two different hosts.

[0142] A weight ratio of the two different hosts may be in a range of 90:10 to 10:90. For example, the weight ratio of the two different hosts may be in a range of 80:20, 70:30, 60:40, 50:50, 40:60, 30:70, or 20:80. For example, a weight ratio of the first compound to the second compound may be 50:50, but embodiments of the present disclosure are not limited thereto.

[0143] In one embodiment, the host may include a first host and a second host, the first host may include a carbazole-containing host or a silyl-containing host, and the second host may include a phosphine oxide-containing host.

[0144] In one embodiment, the emission layer may include the organometallic compound, and the emission layer may emit blue light. For example, the emission layer may emit blue light having a maximum emission wavelength of about 430 nm to about 490 nm, but embodiments of the present disclosure are not limited thereto.

[0145] In one embodiment, the first electrode may be an anode, the second electrode may be a cathode, the organic layer may further include a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode. The hole transport region may include at least one selected from a hole injection layer, a hole transport layer, a buffer layer, an emission auxiliary layer, and an electron blocking layer, and the electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

[0146] In one embodiment, at least one of the emission layer, the hole blocking layer, the electron transport layer, and the electron injection layer may include a phosphine oxide-containing compound.

[0147] In one or more embodiments, at least one of the emission layer, the hole blocking layer, the electron transport layer, and the electron injection layer may include a silyl-containing compound.

[0148] In one embodiment, the electron transport region may include a hole blocking layer, and the hole blocking layer may include a phosphine oxide-containing compound.

[0149] The term “organic layer” as used herein refers to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of the organic light-emitting device. A material included in the “organic layer” is not limited to an organic material.

Description of FIG. 1

[0150] FIG. 1 is a schematic view of an organic light-emitting device 10 according to an embodiment. The organic light-emitting device 10 includes a first electrode 110, an organic layer 150, and a second electrode 190.

[0151] Hereinafter, the structure of the organic light-emitting device 10 according to an embodiment and a method of manufacturing the organic light-emitting device 10 will be described in connection with FIG. 1.

First Electrode 110

[0152] In FIG. 1, a substrate may be additionally disposed under the first electrode 110 or above the second electrode 190. The substrate may be a glass substrate or a plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

[0153] The first electrode 110 may be formed by depositing or sputtering a material for forming the first electrode 110 on the substrate. When the first electrode 110 is an anode, the material for forming a first electrode may be selected from materials with a high work function to facilitate hole injection.

[0154] The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. When the first electrode 110 is a transmissive electrode, a material for forming the first electrode may be selected from indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), zinc oxide (ZnO), and any combinations thereof, but embodiments of the present disclosure are not limited thereto. When the first electrode 110 is a semi-transmissive electrode or a reflective electrode, as a material for forming the first electrode 110, magnesium (Mg), silver (Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), or any combination thereof may be utilized. However, the material for forming the first electrode 110 is not limited thereto.

[0155] The first electrode 110 may have a single-layered structure, or a multi-layered structure including two or more layers. For example, the first electrode 110 may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode 110 is not limited thereto.

Organic Layer 150

[0156] The organic layer 150 is disposed on the first electrode 110. The organic layer 150 may include an emission layer.

[0157] The organic layer 150 may further include a hole transport region between the first electrode 110 and the emission layer, and an electron transport region between the emission layer and the second electrode 190.


Hole Transport Region in Organic Layer 150

[0158] The hole transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.


[0159] The hole transport region may include at least one layer selected from a hole injection layer, a hole transport layer, an emission auxiliary layer, and an electron blocking layer.

[0160] For example, the hole transport region may have a single-layered structure including a single layer including a plurality of different materials, or a multi-layered structure having a hole injection layer/hole transport layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/electron blocking layer structure, wherein for each structure, constituting layers are sequentially stacked from the first electrode 110 in this stated order, but the structure of the hole transport region is not limited thereto.


[0161] The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB (NPB), 1-NPB, TPD, Spiro-TPD, Spiro-NPB, methylated-NPB, TAPC, HMTPD, 4,4',4"-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), PEDOT/PSS (poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate)), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:




-continued



TDATA




2-TNATA




NPB


-continued




β -NPB




TPD




Spiro-TPD




Spiro-NPB




methylated NPB



Formula 201



Formula 202



[0162] In Formulae 201 and 202,

[0163] L_{201} to L_{204} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0164] L_{205} may be selected from $*-O-*$, $*-S-*$, $*-N(Q_{201})-*$, a substituted or unsubstituted C_1 - C_{20} alkylene group, a substituted or unsubstituted C_2 - C_{20} alkenylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0165] $xa1$ to $xa4$ may each independently be an integer of 0 to 3,

[0166] $xa5$ may be an integer of 1 to 10,

[0167] R_{201} to R_{204} and Q_{201} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

[0168] For example, in Formula 202, R_{201} and R_{202} may optionally be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group, and R_{203} and R_{204} may optionally be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group.

[0169] In one or more embodiments, in Formulae 201 and 202,

[0170] L_{201} to L_{205} may each independently be selected from:

[0171] a phenylene group, a pentalenylene group, an indenylene group, a naphthalenylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylene group; and

[0172] a phenylene group, a pentalenylene group, an indenylene group, a naphthalenylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylene group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono

group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacacenyl group, a pentacacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —N(Q₃₁)(Q₃₂),

[0173] Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0174] In one or more embodiments, xa1 to xa4 may each independently be 0, 1, or 2.

[0175] In one or more embodiments, xa5 may be 1, 2, 3, or 4.

[0176] In one or more embodiments, R₂₀₁ to R₂₀₄ and Q₂₀₁ may each independently be selected from:

[0177] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacacenyl group, a pentacacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group; and

[0178] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacacenyl group, a pentacacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl,

—Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacacenyl group, a pentacacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —N(Q₃₁)(Q₃₂), and

[0179] Q₃₁ to Q₃₃ may respectively be defined the same as those described above in connection with L₂₀₁ to L₂₀₅.

[0180] In one or more embodiments, in Formula 201, at least one selected from R₂₀₁ to R₂₀₃ may each independently be selected from:

[0181] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0182] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

[0183] but embodiments of the present disclosure are not limited thereto.

[0184] In one or more embodiments, in Formula 202, i) R₂₀₁ and R₂₀₂ may be linked via a single bond, and/or ii) R₂₀₃ and R₂₀₄ may be linked via a single bond.

[0185] In one or more embodiments, in Formula 202, at least one selected from R₂₀₁ to R₂₀₄ may be selected from:



[0186] a carbazolyl group; and

[0187] a carbazolyl group substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl


group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothio-phenyl group,

[0188] but embodiments of the present disclosure are not limited thereto.

[0189] The compound represented by Formula 201 may be represented by Formula 201A:





[0192] In one embodiment, the compound represented by Formula 202 may be represented by Formula 202A:



[0190] In one embodiment, the compound represented by Formula 201 may be represented by Formula 201A(1), but embodiments of the present disclosure are not limited thereto:

[0193] In one embodiment, the compound represented by Formula 202 may be represented by Formula 202A-1:



[0191] In one embodiment, the compound represented by Formula 201 may be represented by Formula 201A-1 below, but embodiments of the present disclosure are not limited thereto:

[0194] In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1,

[0195] L_{201} to L_{203} , $xa1$ to $xa3$, $xa5$, and R_{202} to R_{204} may respectively be defined the same as those described above in connection with Formulae 201 and 202,

[0196] R_{211} and R_{212} may respectively be defined the same as described in connection with R_{203} in Formulae 201 and 202.


[0197] R_{213} to R_{217} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl

group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an


ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

[0198] The hole transport region may include at least one compound selected from Compounds HT1 to HT39, but embodiments of the present disclosure are not limited thereto:


HT1




HT2



HT3




HT4




-continued


HT5




HT6



HT7




HT8




-continued


HT9




HT10



HT11





HT12





-continued
HT13

HT14





HT15

HT16




HT17

HT18




-continued
HT19

HT20




HT21

HT22




HT23




-continued


HT24




HT25




HT26




HT27



HT28




HT29




-continued


HT30




HT31




HT32




HT33



HT34





HT35





-continued
HT36

HT37



HT38

HT39



[0199] A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes at least one of a hole injection layer and a hole transport layer, the thickness of the hole injection layer may be in a range of about 100 Å to about 9,000 Å, and for example, about 100 Å to about 1,000 Å, and the thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, and for example, about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

[0200] The emission auxiliary layer may increase light-emission efficiency by compensating for an optical resonance distance according to the wavelength of light emitted by an emission layer, and the electron blocking layer may block the flow of electrons from an electron transport region. The emission auxiliary layer and the electron blocking layer may include the materials as described above. p-dopant

[0201] The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

[0202] The charge-generation material may be, for example, a p-dopant.

[0203] In one embodiment, the p-dopant may have a lowest unoccupied molecular orbital (LUMO) level of -3.5 eV or less.

[0204] The p-dopant may include at least one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments of the present disclosure are not limited thereto.

[0205] For example, the p-dopant may include at least one selected from:


[0206] a quinone derivative, such as tetracyanoquinodimethane (TCNQ) or 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4-TCNQ);

[0207] a metal oxide, such as tungsten oxide or molybdenum oxide;


[0208] 1,4,5,8,9,11-hexaazatriphenylene-hexacarbonitrile (HAT-CN); and

[0209] a compound represented by Formula 221,


[0210] but embodiments of the present disclosure are not limited thereto:



HAT-CN



F4-TCNQ



Formula 221

[0211] In Formula 221,

[0212] R_{221} to R_{223} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, wherein at least one selected from R_{221} to R_{223} may have at least one substituent selected from a cyano group, —F, —Cl, —Br, —I, a C_1 - C_{20} alkyl group substituted with —F, a C_1 - C_{20} alkyl group substituted with —Cl, a C_1 - C_{20} alkyl group substituted with —Br and a C_1 - C_{20} alkyl group substituted with —I.

Emission Layer in Organic Layer 150

[0213] When the organic light-emitting device 10 is a full-color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub-pixel. In one or more embodiments, the emission layer may have a stacked structure of two or more layers selected from a red emission layer, a green emission layer, and a blue emission layer, in which the two or more layers contact each other or

are separated from each other. In one or more embodiments, the emission layer may include two or more materials selected from a red light-emitting material, a green light-emitting material, and a blue light-emitting material, in which the two or more materials are mixed with each other in a single layer to emit white light.

[0214] The emission layer may include a host and a dopant. The dopant may include at least one selected from a phosphorescent dopant and a fluorescent dopant.

[0215] In the emission layer, an amount of a dopant may be in a range of about 0.01 parts to about 15 parts by weight based on 100 parts by weight of the host, but embodiments of the present disclosure are not limited thereto.

[0216] A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.

Host in Emission Layer

[0217] In one or more embodiments, the host may include a compound represented by Formula 301 below.



[0218] In Formula 301,

[0219] Ar_{301} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

[0220] $xb11$ may be 1, 2, or 3,

[0221] L_{301} may each independently (i.e., when two or more L_{301} s are included) be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

[0222] $xb1$ may be an integer from 0 to 5,

[0223] R_{301} may be selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{301})(Q_{302})(Q_{303}), —N(Q_{301})(Q_{302}), —B(Q_{301})(Q_{302}), —C(=O)(Q_{301}), —S(=O)₂(Q_{301}), and —P(=O)(Q_{301})(Q_{302}),

[0224] xb_{21} may be an integer from 1 to 5, and

[0225] Q_{301} to Q_{303} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto.

[0226] In one embodiment, Ar_{301} in Formula 301 may be selected from:

[0227] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group; and

[0228] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, $-B(Q_{31})(Q_{32})$, $-C(=O)(Q_{31})$, $-S(=O)_2(Q_{31})$, and $-P(=O)(Q_{31})(Q_{32})$, and

[0229] Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group. However, embodiments of the present disclosure are not limited thereto.

[0230] When xb_{111} in Formula 301 is two or more, two or more $Ar_{301}(s)$ may be linked via a single bond.

[0231] In one or more embodiments, the compound represented by Formula 301 may be represented by Formula 301-1 or 301-2:

[0232] In Formulae 301-1 and 301-2,

[0233] A_{301} to A_{304} may each independently be selected from a benzene, a naphthalene, a phenanthrene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a pyridine, a pyrimidine, an indene, a fluorene, a spiro-bifluorene, a benzofluorene, a dibenzofluorene, an indole, a carbazole, benzocarbazole, dibenzocarbazole, a furan, a benzofuran, a dibenzofuran, a naphthofuran, a benzonaphthofuran, dinaphthofuran, a thiophene, a benzothiophene, a dibenzothiophene, a naphthothiophene, a benzonaphthothiophene, and a dinaphthothiophene,

[0234] X_{301} may be O, S, or $N-[(L_{304})_{xb4}-R_{304}]$,

[0235] R_{311} to R_{314} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, $-B(Q_{31})(Q_{32})$, $-C(=O)(Q_{31})$, $-S(=O)_2(Q_{31})$, and $-P(=O)(Q_{31})(Q_{32})$,

[0236] xb_{22} and xb_{23} may each independently be 0, 1, or 2,

[0237] L_{301} , xb_1 , R_{301} , and Q_{31} to Q_{33} may respectively be defined the same as those described above in connection with Formula 301,


[0238] L_{302} to L_{304} may respectively be defined the same connection with L_{301} in Formula 301,

[0239] xb_2 to xb_4 may respectively be defined the same as described in connection with xb_1 in Formula 301, and


[0240] R_{302} to R_{304} may respectively be defined the same as described in connection with R_{301} in Formula 301,

[0241] For example, in Formulae 301, 301-1, and 301-2, L_{301} to L_{304} may each independently be selected from:

[0242] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene



Formula 301-1



Formula 301-2

group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group; and

[0243] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazoly group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group,

a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂), and

[0244] Q₃₁ to Q₃₃ may respectively be defined the same as those described above in connection with Ar₃₀₁ in Formula 301.

[0245] In one embodiment, in Formulae 301, 301-1, and 301-2, R₃₀₁ to R₃₀₄ may each independently be selected from:

[0246] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and

[0247] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a


phenanthrolyl group, a phenaziny group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexaceny group, a pentaceny group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenaziny group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂), and

[0248] Q₃₁ and Q₃₃ may respectively be defined the same as those described above.


[0249] In one or more embodiments, the host may include an alkaline earth metal complex. For example, the host may be selected from a Be complex (for example, Compound H55), a Mg complex, and a Zn complex.

[0250] The host may include at least one selected from 9,10-di(2-naphthyl)anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl)anthracene (MADN), 9,10-di-(2-naphthyl)-2-t-butyl-anthracene (TBADN), a 4,4'-bis(N-carbazolyl)-1,1'-biphenyl (CBP), 1,3-di-9-carbazolylbenzene (mCP), 1,3,5-tri(carbazol-9-yl)benzene (TCP), and Compounds H1 to H55, but embodiments of the present disclosure are not limited thereto:


-continued




H2




H3




H4




H5



H6




H7




H1

-continued


H8




H9




H10




H11



H12




H13




-continued


H14




H15




H16







H17






H18





-continued



-continued




-continued




-continued

H26




H28

H29




H30


H27




H31




-continued




H32



H33




H34




H35


-continued




H36



H37




H38




H39



-continued




-continued





H41



H45












H46



-continued



-continued



Phosphorescent Dopant Included in Emission Layer in Organic Layer **150**

[0251] The phosphorescent dopant may include an organometallic compound represented by Formula 1 or 2.

[0252] In addition, the phosphorescent dopant may further include an organometallic complex represented by Formula 401:



Formula 401

Formula 402

[0253] In Formulae 401 and 402,

[0254] M may be selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), and thulium (Tm),

[0255] L_{401} may be selected from ligands represented by Formula 402, and xc1 may be 1, 2, or 3, wherein, when xc1 is two or more, two or more $L_{401}(s)$ may be identical to or different from each other,

[0256] L_{402} may be an organic ligand, and xc2 may be an integer from 0 to 4, wherein, when xc2 is two or more, two or more $L_{402}(s)$ may be identical to or different from each other,

[0257] X_{401} to X_{404} may each independently be nitrogen or carbon,

[0258] X_{401} and X_{403} may be linked via a single bond or a double bond, and X_{402} and X_{404} may be linked via a single bond or a double bond,

[0259] A_{401} and A_{402} may each independently be selected from a C_5 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group,

[0260] X_{405} may be a single bond, $*-O-*$, $*-S-*$, $*-C(=O)-*$, $*-N(Q_{411})-*$, $*-C(Q_{411})(Q_{412})-*$, $*-C(Q_{411})=C(Q_{412})-*$, $*-C(Q_{411})=*$, or $*=C(Q_{411})-*$, wherein Q_{411} and Q_{412} may be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group,

[0261] X_{406} may be a single bond, O, or S,

[0262] R_{401} and R_{402} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_{401})(Q_{402})(Q_{403})$, $-N(Q_{401})(Q_{402})$, $-B(Q_{401})(Q_{402})$, $-C(=O)(Q_{401})$, $-S(=O)_2$

(Q_{401}), and $-P(=O)(Q_{401})(Q_{402})$, wherein Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a C_6 - C_{20} aryl group, and a C_1 - C_{20} heteroaryl group,

[0263] xc11 and xc12 may each independently be an integer of 0 to 10, and

[0264] * and *' in Formula 402 each indicate a binding site to M of Formula 401.

[0265] In one embodiment, A_{401} and A_{402} in Formula 402 may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, and a dibenzothiophene group.

[0266] In one or more embodiments, in Formula 402, i) X_{401} may be nitrogen, and X_{402} may be carbon, or ii) X_{401} and X_{402} may each be nitrogen at the same time.

[0267] In one or more embodiments, in Formula 402, R_{401} and R_{402} may each independently be selected from:

[0268] hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0269] a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, and a norbornenyl group;

[0270] a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuran group, and a dibenzothiophenyl group;

[0271] a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuran group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl









group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and [0272] $-\text{Si}(\text{Q}_{401})(\text{Q}_{402})(\text{Q}_{403})$, $-\text{N}(\text{Q}_{401})(\text{Q}_{402})$, $-\text{B}(\text{Q}_{401})(\text{Q}_{402})$, $-\text{C}(=\text{O})(\text{Q}_{401})$, $-\text{S}(=\text{O})_2(\text{Q}_{401})$, and $-\text{P}(=\text{O})(\text{Q}_{401})(\text{Q}_{402})$, and

[0273] Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto.


[0274] In one or more embodiments, when xc1 in Formula 401 is two or more, two $\text{A}_{401}(\text{s})$ in two or more $\text{L}_{401}(\text{s})$ may optionally be linked via X_{407} , which is a linking group, or two $\text{A}_{402}(\text{s})$ in two or more $\text{L}_{401}(\text{s})$ may optionally be linked via X_{408} , which is a linking group (see Compounds PD1 to PD4 and PD7). X_{407} and X_{408} may each independently be a single bond, $^*-\text{O}-^*$, $^*-\text{S}-^*$, $^*-\text{C}(=\text{O})-^*$, $^*-\text{N}(\text{Q}_{413})-^*$, $^*-\text{C}(\text{Q}_{413})(\text{Q}_{414})-^*$, or $^*-\text{C}(\text{Q}_{413})=\text{C}(\text{Q}_{414})-^*$, wherein Q_{413} and Q_{414} may each independently be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group, but embodiments of the present disclosure are not limited thereto.

[0275] L_{402} in Formula 401 may be a monovalent, divalent, or trivalent organic ligand. For example, L_{402} may be selected from halogen, diketone (for example, acetylacetonate), carboxylic acid (for example, picolinate), $-\text{C}(=\text{O})$, isonitrile, $-\text{CN}$, and phosphorus (for example, phosphine, or phosphite), but embodiments of the present disclosure are not limited thereto.

[0276] In one or more embodiments, the phosphorescent dopant may be selected from, for example, Compounds PD1 to PD25, but embodiments of the present disclosure are not limited thereto:




-continued




PD9


-continued




PD14




PD10




PD15




PD11




PD16




PD12



PD17




PD13




PD18

-continued




PD19

-continued




PD20


PD23




PD24




PD25



PD21



PD22




Fluorescent Dopant in Emission Layer

[0277] The fluorescent dopant may include an arylamine compound or a styrylamine compound.

[0278] The fluorescent dopant may include a compound represented by Formula 501 below.

Formula 501



[0279] In Formula 501,

[0280] Ar₅₀₁ may be a substituted or unsubstituted C₅-C₆₀ carbocyclic group or a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

[0281] L₅₀₁ to L₅₀₃ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene

group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

[0282] xd1 to xd3 may each independently be an integer of 0 to 3;

[0283] R₅₀₁ and R₅₀₂ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and

[0284] xd4 may be an integer of 1 to 6.

[0285] In one embodiment, Ar₅₀₁ in Formula 501 may be selected from:

[0286] a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group; and

[0287] a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0288] In one or more embodiments, L₅₀₁ to L₅₀₃ in Formula 501 may each independently be selected from:

[0289] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group; and

[0290] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

[0291] In one or more embodiments, in Formula 501, R₅₀₁ and R₅₀₂ may each independently be selected from:

[0292] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group; and


[0293] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group,

a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and


[0294] Q_{31} to Q_{33} may each be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0295] In one or more embodiments, xd4 in Formula 501 may be 2, but embodiments of the present disclosure are not limited thereto.


[0296] For example, the fluorescent dopant may be selected from Compounds FD1 to FD22:




FD1



FD2



FD3




FD4

-continued


-continued

FD5




-continued


FD8




FD6




FD9




FD7




FD10




-continued




-continued




FD12




FD17




FD13



FD18





FD14




FD19

FD15




-continued

FD20




FD21




-continued


FD22




[0297] In one or more embodiments, the fluorescent dopant may be selected from the following compounds, but embodiments of the present disclosure are not limited thereto.



DPVBi



DPAVBi



Electron Transport Region in Organic Layer 150

[0298] The electron transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0299] The electron transport region may include at least one selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, and an electron injection layer, but embodiments of the present disclosure are not limited thereto.

[0300] For example, the electron transport region may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron transport layer/electron injection layer structure, or a buffer layer/electron transport layer/electron injection layer structure, wherein for each structure, constituting layers are sequentially stacked from an emission layer. However, embodiments of the structure of the electron transport region are not limited thereto.

[0301] The electron transport region (for example, a buffer layer, a hole blocking layer, an electron control layer, or an electron transport layer in the electron transport region) may include a metal-free compound containing at least one π electron-depleted nitrogen-containing ring.


[0302] The term “ π electron-depleted nitrogen-containing ring” as used herein indicates a C_1 - C_{60} heterocyclic group having at least one $*-N=*$ moiety as a ring-forming moiety.

[0303] For example, the “ π electron-depleted nitrogen-containing ring” may be i) a 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety, ii) a heteropolycyclic group in which two or more 5-membered to 7-membered heteromonocyclic groups each

having at least one $*-N=*$ moiety are condensed with each other, or iii) a heteropolycyclic group in which at least one of 5-membered to 7-membered heteromonocyclic groups, each having at least one $*-N=*$ moiety, is condensed with at least one C_5 - C_{60} carbocyclic group.

[0304] Examples of the π electron-depleted nitrogen-containing ring include an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isoxazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, an indazole, a purine, a quinoline, an isoquinoline, a benzoquinoline, a phthalazine, a naphthyridine, a quinoxaline, a quinazoline, a cinnoline, a phenanthridine, an acridine, a phenanthroline, a phenazine, a benzimidazole, an isobenzothiazole, a benzoxazole, an isobenzoxazole, a triazole, a tetrazole, an oxadiazole, a triazine, a thiadiazole, an imidazopyridine, an imidazopyrimidine, and an azacarbazole, but embodiments of the present disclosure are not limited thereto.

[0305] For example, the electron transport region may include a compound represented by Formula 601:



[0306] In Formula 601,

[0307] Ar_{601} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

[0308] $xe11$ may be 1, 2, or 3,

[0309] L_{601} may each independently (i.e., when two or more L_{601} s are included) be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0310] xe1 may be an integer from 0 to 5,

[0311] R_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{601})(\text{Q}_{602})(\text{Q}_{603})$, $-\text{C}(=\text{O})(\text{Q}_{601})$, $-\text{S}(=\text{O})_2(\text{Q}_{601})$, and $-\text{P}(=\text{O})(\text{Q}_{601})(\text{Q}_{602})$,

[0312] Q_{601} to Q_{603} may each independently be a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group, and

[0313] xe21 may be an integer from 1 to 5.

[0314] In one embodiment, at least one of $\text{Ar}_{601}(\text{s})$ in the number of xe11 and/or at least one of $\text{R}_{601}(\text{s})$ in the number of xe21 may include the π electron-depleted nitrogen-containing ring.

[0315] In one embodiment, ring Ar_{601} in Formula 601 may be selected from:

[0316] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group; and

[0317] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group; and

azazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, and


[0318] Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0319] When xe11 in Formula 601 is two or more, two or more $\text{Ar}_{601}(\text{s})$ may be linked via a single bond.

[0320] In one or more embodiments, Ar_{601} in Formula 601 may be an anthracene group.

[0321] In one or more embodiments, a compound represented by Formula 601 may be represented by Formula 601-1:

Formula 601-1



[0322] In Formula 601-1,

[0323] X_{614} may be N or C(R_{614}), X_{615} may be N or C(R_{615}), X_{616} may be N or C(R_{616}), and at least one selected from X_{614} to X_{616} may be N,

[0324] L_{611} to L_{613} may each independently be the same as described in connection with L_{601} in Formula 601,

[0325] xe611 to xe613 may each independently be defined the same as described in connection with xe1 in Formula 601,

[0326] R_{611} to R_{613} may each independently be the same as described in connection with R_{601} in Formula 601, and

[0327] R_{614} to R_{616} may each independently be selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0328] In one embodiment, L_{601} and L_{611} to L_{613} in Formulae 601 and 601-1 may each independently be selected from:

[0329] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a

dibenzosilolylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group; and

[0330] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a benzofuranyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

quinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, but embodiments of the present disclosure are not limited thereto,

[0331] but embodiments of the present disclosure are not limited thereto.

[0332] In one or more embodiments, xe1 and xe611 to xe613 in Formulae 601 and 601-1 may each independently be 0, 1, or 2.

[0333] In one or more embodiments, R₆₀₁ and R₆₁₁ to R₆₁₃ in Formula 601 and 601-1 may each independently be selected from:

[0334] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

[0335] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl


group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, and an azacarbazolyl group; and

[0336] —S(=O)₂(Q₆₀₁) and —P(=O)(Q₆₀₁)(Q₆₀₂), and

[0337] Q₆₀₁ and Q₆₀₂ may respectively be defined the same as those described above in connection with R₆₀₁ in Formula 601.


[0338] The electron transport region may include at least one compound selected from Compounds ET1 to ET36, but embodiments of the present disclosure are not limited thereto:

ET1




-continued


ET2



ET3




ET4




-continued

-continued


ET5



ET8





ET6




ET9

ET7




-continued

ET10




-continued


ET13




ET11




ET14




ET12



ET15




-continued




ET16


-continued




ET19




ET17



ET20



ET18





ET21

-continued

-continued



ET22

ET25





ET23

ET26




ET24

ET27




-continued




ET28

-continued




ET31


ET29




ET32






ET30




ET33




-continued




ET34

Alq₃

ET35




BAIq



TAZ

ET36



NTAZ

[0339] In one or more embodiments, the electron transport region may include at least one compound selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq₃, BAIq, 3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (TAZ), and NTAZ:


[0340] The thickness of the buffer layer, the hole blocking layer, or the electron controlling layer may each independently be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer, and the electron control layer are within these ranges, the electron blocking layer may have excellent electron blocking characteristics or electron control characteristics without a substantial increase in driving voltage.

[0341] A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the ranges described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.


[0342] The electron transport region (for example, the electron transport layer in the electron transport region) may further include, in addition to the materials described above, a metal-containing material.

[0343] The metal-containing material may include at least one selected from alkali metal complex and alkaline earth-metal complex. The alkali metal complex may include a metal ion selected from a Li ion, a Na ion, a K ion, a Rb ion, and a Cs ion, and the alkaline earth-metal complex may include a metal ion selected from a Be ion, a Mg ion, a Ca ion, a Sr ion, and a Ba ion. A ligand coordinated with the metal ion of the alkali metal complex or the alkaline earth-metal complex may be selected from a hydroxy quinoline, a hydroxy isoquinoline, a hydroxy benzoquinoline, a hydroxy acridine, a hydroxy phenanthridine, a hydroxy phenyloxazole, a hydroxy phenylthiazole, a hydroxy diphenyloxadiazole, a hydroxy diphenylthiadiazol, a hydroxy phenylpyridine, a hydroxy phenylbenzimidazole, a hydroxy phenylbenzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene, but embodiments of the present disclosure are not limited thereto.

[0344] For example, the metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2:



ET-D1



ET-D2

[0345] The electron transport region may include an electron injection layer that facilitates injection of electrons from the second electrode **190**. The electron injection layer may directly contact the second electrode **190**.

[0346] The electron injection layer may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0347] The electron injection layer may include an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof.

[0348] The alkali metal may be selected from Li, Na, K, Rb, and Cs. In one embodiment, the alkali metal may be Li,

Na, or Cs. In one or more embodiments, the alkali metal may be Li or Cs, but embodiments of the present disclosure are not limited thereto.

[0349] The alkaline earth metal may be selected from Mg, Ca, Sr, and Ba.

[0350] The rare earth metal may be selected from Sc, Y, Ce, Tb, Yb, and Gd.

[0351] The alkali metal compound, the alkaline earth-metal compound, and the rare earth metal compound may be selected from oxides and halides (for example, fluorides, chlorides, bromides, or iodides) of the alkali metal, the alkaline earth-metal, and the rare earth metal.

[0352] The alkali metal compound may be selected from alkali metal oxides, such as Li_2O , Cs_2O , or K_2O , and alkali metal halides, such as LiF, NaF, CsF, KF, LiI, NaI, CsI, or KI. In one embodiment, the alkali metal compound may be selected from LiF, Li_2O , NaF, LiI, NaI, CsI, and KI, but embodiments of the present disclosure are not limited thereto.

[0353] The alkaline earth-metal compound may be selected from alkaline earth-metal oxides, such as BaO, SrO, CaO, $\text{Ba}_x\text{Sr}_{1-x}\text{O}$ ($0 < x < 1$), or $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ ($0 < x < 1$). In one embodiment, the alkaline earth-metal compound may be selected from BaO, SrO, and CaO, but embodiments of the present disclosure are not limited thereto.

[0354] The rare earth metal compound may be selected from YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , and TbF_3 . In one embodiment, the rare earth metal compound may be selected from YbF_3 , ScF_3 , TbF_3 , YbI_3 , ScI_3 , and TbI_3 , but embodiments of the present disclosure are not limited thereto.

[0355] The alkali metal complex, the alkaline earth-metal complex, and the rare earth metal complex may include an ion of alkali metal, alkaline earth-metal, and rare earth metal as described above, and a ligand coordinated with a metal ion of the alkali metal complex, the alkaline earth-metal complex, or the rare earth metal complex may be selected from hydroxy quinoline, hydroxy isoquinoline, hydroxy benzoquinoline, hydroxy acridine, hydroxy phenanthridine, hydroxy phenyloxazole, hydroxy phenylthiazole, hydroxy diphenyloxadiazole, hydroxy diphenylthiadiazol, hydroxy phenylpyridine, hydroxy phenylbenzimidazole, hydroxy phenylbenzothiazole, bipyridine, phenanthroline, and cyclopentadiene, but embodiments of the present disclosure are not limited thereto.

[0356] The electron injection layer may include (e.g., consist of) an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof, as described above. In one or more embodiments, the electron injection layer may further include an organic material. When the electron injection layer further includes an organic material, an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof may be homogeneously or non-homogeneously dispersed in a matrix including the organic material.

[0357] A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron

injection layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

Second Electrode 190

[0358] The second electrode 190 may be disposed on the organic layer 150 having such a structure. The second electrode 190 may be a cathode that is an electron injection electrode, and in this regard, a material for forming the second electrode 190 may be a material having a low work function, and such a material may be metal, alloy, an electrically conductive compound, or a combination thereof.

[0359] The second electrode 190 may include at least one selected from lithium (Li), silver (Si), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), ITO, and IZO, but embodiments of the present disclosure are not limited thereto. The second electrode 190 may be a transmissive electrode, a semi-transmissive electrode, or a reflective electrode.

[0360] The second electrode 190 may have a single-layered structure, or a multi-layered structure including two or more layers.

[0361] [Description of FIGS. 2 to 4]

[0362] An organic light-emitting device 20 of FIG. 2 includes a first capping layer 210, a first electrode 110, an organic layer 150, and a second electrode 190, which are sequentially stacked in this stated order; an organic light-emitting device 30 of FIG. 3 includes a first electrode 110, an organic layer 150, a second electrode 190, and a second capping layer 220, which are sequentially stacked in this stated order; and an organic light-emitting device 40 of FIG. 4 includes a first capping layer 210, a first electrode 110, an organic layer 150, a second electrode 190, and a second capping layer 220.

[0363] Regarding FIGS. 2 to 4, the first electrode 110, the organic layer 150, and the second electrode 190 may be understood by referring to the description presented in connection with FIG. 1.

[0364] In the organic layer 150 of each of the organic light-emitting devices 20 and 40, light generated in an emission layer may pass through the first electrode 110, which is a semi-transmissive electrode or a transmissive electrode, and the first capping layer 210 toward the outside, and in the organic layer 150 of each of the organic light-emitting devices 30 and 40, light generated in an emission layer may pass through the second electrode 190, which is a semi-transmissive electrode or a transmissive electrode, and the second capping layer 220 toward the outside.

[0365] The first capping layer 210 and the second capping layer 220 may increase external luminescent efficiency according to the principle of constructive interference.


[0366] The first capping layer 210 and the second capping layer 220 may each independently be an organic capping layer including an organic material, an inorganic capping layer including an inorganic material, or a composite capping layer including an organic material and an inorganic material.

[0367] At least one selected from the first capping layer 210 and the second capping layer 220 may each independently include at least one material selected from carbocyclic compounds, heterocyclic compounds, amine-based compounds, porphyrine derivatives, phthalocyanine deriva-


tives, a naphthalocyanine derivatives, alkali metal complexes, and alkaline earth-based complexes. The carbocyclic compound, the heterocyclic compound, and the amine-based compound may be optionally substituted with a substituent containing at least one element selected from O, N, S, Se, Si, F, Cl, Br, and I. In one embodiment, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include an amine-based compound.

[0368] In one embodiment, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include the compound represented by Formula 201 and/or the compound represented by Formula 202.

[0369] In one or more embodiments, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include a compound selected from Compounds HT28 to HT33 and Compounds CP1 to CP5, but embodiments of the present disclosure are not limited thereto:



-continued



[0370] Hereinbefore, the organic light-emitting device according to an embodiment has been described in connection with FIGS. 1-4. However, embodiments of the present disclosure are not limited thereto.

[0371] Layers constituting the hole transport region, the emission layer, and layers constituting the electron transport region may be formed in a certain region utilizing one or more suitable methods selected from vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, ink-jet printing, laser-printing, and laser-induced thermal imaging.

[0372] When layers constituting the hole transport region, the emission layer, and layers constituting the electron transport region are formed by vacuum deposition, the deposition may be performed at a deposition temperature of about 100° C. to about 500° C., a vacuum degree of about 1008 torr to about 10⁻³ torr, and a deposition rate of about 0.01 Å/sec to about 100 Å/sec by taking into account a material to be included in a layer to be formed, and the structure of a layer to be formed.

[0373] When layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region are formed by spin coating, the spin coating may be performed at a coating speed of about 2,000 rpm to about 5,000 rpm and at a heat treatment temperature of about 80° C. to about 200° C., depending on a material to be included in a layer and the structure of each layer to be formed.

General Definition of Substituents

[0374] The term “C₁-C₆₀ alkyl group” as used herein refers to a linear or branched saturated aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms, and non-limiting examples thereof may include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl

group, a tert-butyl group, a pentyl group, an isoamyl group, and a hexyl group. The term “C₁-C₆₀ alkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

[0375] The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group formed by substituting at least one carbon-carbon double bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and non-limiting examples thereof may include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkenylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

[0376] The term “C₂-C₆₀ alkynyl group” as used herein refers to a hydrocarbon group formed by substituting at least one carbon-carbon triple bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and non-limiting examples thereof may include an ethynyl group, and a propynyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

[0377] The term “C₁-C₆₀ alkoxy group” as used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ represents the C₁-C₆₀ alkyl group), and non-limiting examples thereof may include a methoxy group, an ethoxy group, and an isopropoxy group.

[0378] The term “C₃-C₁₀ cycloalkyl group” as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and non-limiting examples thereof may include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The term “C₃-C₁₀ cycloalkylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

[0379] The term “C₁-C₁₀ heterocycloalkyl group” as used herein refers to a monovalent saturated monocyclic group having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom in addition to 1 to 10 carbon atoms, and non-limiting examples thereof may include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuranlyl group, a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkyl group.

[0380] The term “C₃-C₁₀ cycloalkenyl group” as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof, wherein the molecular structure as a whole is non-aromatic, and non-limiting examples thereof may include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. The term “C₃-C₁₀ cycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

[0381] The term “C₁-C₁₀ heterocycloalkenyl group” as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom in addition to 1 to 10 carbon atoms, and at least one carbon-carbon double bond in its ring. Non-limiting examples of the C₁-C₁₀ heterocycloalkenyl group may include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuranlyl group, and a 2,3-dihydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkenyl group.

[0382] The term “C₆-C₆₀ aryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system

having 6 to 60 carbon atoms, and the term “C₆-C₆₀ arylene group” as used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Non-limiting examples of the C₆-C₆₀ aryl group may include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

[0383] The term “C₁-C₆₀ heteroaryl group” as used herein refers to a monovalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. The term “C₁-C₆₀ heteroarylene group” as used herein refers to a divalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. Non-limiting examples of the C₁-C₆₀ heteroaryl group may include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the rings may be fused to each other.

[0384] The term “C₆-C₆₀ aryloxy group” as used herein refers to a group represented by —OA₁₀₂ (wherein A₁₀₂ represents the C₆-C₆₀ aryl group), and the term “C₆-C₆₀ arylthio group” as used herein refers to a group represented by —SA₁₀₃ (wherein A₁₀₃ represents the C₆-C₆₀ aryl group).

[0385] The term “monovalent non-aromatic condensed polycyclic group” as used herein refers to a monovalent group (for example, having 8 to 60 carbon atoms) having two or more rings condensed with each other, only carbon atoms as ring-forming atoms, and no aromaticity in its entire molecular structure. An example of the monovalent non-aromatic condensed polycyclic group may be a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

[0386] The term “monovalent non-aromatic condensed heteropolycyclic group” as used herein refers to a monovalent group (for example, having 1 to 60 carbon atoms) having two or more rings condensed to each other, at least one heteroatom selected from N, O, Si, P, and S, other than carbon atoms, as a ring-forming atom, and no aromaticity in its entire molecular structure. An example of the monovalent non-aromatic condensed heteropolycyclic group may be a carbazolyl group. The term “divalent non-aromatic condensed heteropolycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0387] The term “C₅-C₆₀ carbocyclic group” as used herein refers to a monocyclic or polycyclic group having 5 to 60 carbon atoms in which a ring-forming atom includes carbon atom only. The C₅-C₆₀ carbocyclic group may be an aromatic carbocyclic group or a non-aromatic carbocyclic group. The C₅-C₆₀ carbocyclic group may be a ring (e.g., a neutral ring), such as benzene, a monovalent group, such as a phenyl group, or a divalent group, such as a phenylene group. In one or more embodiments, depending on the number of substituents connected to the C₅-C₆₀ carbocyclic group, the C₅-C₆₀ carbocyclic group may be a trivalent group or a quadrivalent group.

[0388] The term “C₁-C₆₀ heterocyclic group” as used herein refers to a group having the same structure as the C₁-C₆₀ carbocyclic group, except that as a ring-forming atom, at least one heteroatom selected from N, O, Si, P, and S is used in addition to carbon (the number of carbon atoms may be in a range of 1 to 60).

[0389] At least one substituent selected from the substituted C₅-C₆₀ carbocyclic group, substituted C₁-C₆₀ heterocyclic group, substituted C₃-C₁₀ cycloalkylene group, substituted C₁-C₁₀ heterocycloalkylene group, substituted C₃-C₁₀ cycloalkenylene group, substituted C₁-C₁₀ heterocycloalkenylene group, substituted C₆-C₆₀ arylene group, substituted C₁-C₆₀ heteroarylene group, substituted divalent non-aromatic condensed polycyclic group, substituted divalent non-aromatic condensed heteropolycyclic group, substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0390] deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0391] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

[0392] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0393] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a

monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{21})(\text{Q}_{22})(\text{Q}_{23})$, $-\text{N}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{B}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{C}(=\text{O})(\text{Q}_{21})$, $-\text{S}(=\text{O})_2(\text{Q}_{21})$, and $-\text{P}(=\text{O})(\text{Q}_{21})(\text{Q}_{22})$; and

[0394] $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$; and

[0395] Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0396] The term "Ph" as used herein may refer to a phenyl group; the term "Me", as used herein, may refer to a methyl group; the term "Et", as used herein, may refer to an ethyl group; the term "ter-Bu" or "But", as used herein, may refer to a tert-butyl group; and the term "OMe" as used herein may refer to a methoxy group.

[0397] The term "a biphenyl group" as used herein may refer to "a phenyl group substituted with a phenyl group". In other words, the "biphenyl group" is a substituted phenyl group having a C_6 - C_{60} aryl group as a substituent.

[0398] The term "a terphenyl group" as used herein may refer to "a phenyl group substituted with a biphenyl group". The term "a terphenyl group" as used herein may refer to "a C_6 - C_{60} aryl group substituted with a C_6 - C_{60} aryl group" belonging to "the substituted phenyl group".


[0399] *, **, and *** used herein, unless defined otherwise, each indicate a binding site to a neighboring atom in the corresponding formulae.


[0400] Hereinafter, a compound according to embodiments and an organic light-emitting device according to embodiments will be described in more detail with reference to Synthesis Examples and Examples. The wording "B was utilized instead of A" utilized in describing Synthesis Examples refers to that an identical molar equivalent of B was utilized in place of A.

EXAMPLES

Synthesis Example 1: Synthesis of Compound 1

[0401]





(1) Synthesis of Intermediate [1-A]

[0402] 5.00 g (27.30 mmol) of 2-hydroxycarbazole, 3.25 ml (27.30 mmol) of benzyl bromide, and 3.77 g (27.30 mmol) of potassium carbonate were dissolved in dimethylformamide and stirred at room temperature for 2 days. Distilled water was added to the reaction mixture and stirred for 10 minutes. The resulting precipitate was filtered and washed with distilled water (3 times) and ethyl acetate (1 time). The precipitate was dried under reduced pressure to obtain 6.00 g of Intermediate [1-A].

(2) Synthesis of Intermediate [1-B]

[0403] 4.00 g (15.00 mmol) of the synthesized Intermediate [1-A], 0.28 g (0.30 mmol) of $\text{Pd}_2(\text{dba})_3$, 0.18 g (0.60 mmol) of JohnPhos ((2-biphenyl)di-tert-butylphosphine), 2.31 g (24.00 mmol) of sodium tert-butoxide, and 1.72 g (18.00 mmol) of 2-bromopyridine were suspended in 45 ml of toluene, heated to a temperature of 100°C ., and stirred for 3 days. The reaction mixture was cooled to room temperature and concentrated under reduced pressure. The concentrate obtained therefrom was purified by column chromatography (ethyl acetate:n-hexane=10:1 to 5:1) to obtain 4.55 g of Intermediate [1-B].

(3) Synthesis of Intermediate [1-C]

[0404] 4.55 g (13.00 mmol) of the synthesized Intermediate [1-B] and 5.78 g (39.0 mmol) of pentamethylbenzene were dissolved in 100 ml of methylene chloride, cooled to a temperature of 0°C ., and 32.5 ml of BCl_3 (1 M methylene chloride solution, 32.5 mmol) was slowly added dropwise thereto. The reaction mixture was stirred for 1.5 hours. The reaction was terminated by adding distilled water, and the reaction product was diluted with methylene chloride. The diluted solution was neutralized by adding saturated sodium bicarbonate solution, and an organic layer was extracted therefrom. The organic layer was dried utilizing sodium sulfate, filtered, and dried under reduced pressure. The concentrate obtained therefrom was purified by column chromatography (ethyl acetate:n-hexane=10:1 to 3:1) to obtain 2.79 g of Intermediate [1-C].

(4) Synthesis of Intermediate [1-D]

[0405] 2.50 g of the synthesized Intermediate [1-C], 5.0 g of tert-butyl(3-bromophenyl)carbamate, and 0.10 g of iodine copper were suspended in 150 ml of dimethylformamide solvent, heated to a temperature of 160°C ., and stirred for 12 hours. The reaction mixture was concentrated under

reduced pressure, and an organic layer was extracted therefrom utilizing methylene chloride and distilled water. The organic layer was dried utilizing magnesium sulfate, filtered, and concentrated under reduced pressure. The concentrate obtained therefrom was purified by column chromatography to obtain 2.00 g of Intermediate [1-D].

(5) Synthesis of Intermediate [1-E]

[0406] 2.00 g of the synthesized Intermediate [1-D] was dissolved in 150 ml of methylene chloride, and 1.5 ml of trifluoroacetic acid was added thereto at a temperature of 0°C and stirred at room temperature for 5 hours. After the reaction was completed, distilled water was added to the reaction product, and an organic layer was extracted therefrom. The organic layer was dried utilizing magnesium sulfate, filtered, and concentrated under reduced pressure to obtain 1.50 g of Intermediate [1-E].

(6) Synthesis of Intermediate [1-F]

[0407] 24.5 g (50.0 mmol) of the synthesized Intermediate [1-E] was dissolved in 50 ml of methylene chloride, concentrated hydrochloric acid was added dropwise thereto, and the reaction mixture was solidified. The resulting solid was filtered, washed with diethylether, and dried. The solid was dissolved in 100 ml of ethanol, and 2.1 ml of 37% formaldehyde aqueous solution and 4.8 ml of 2-pyridine carboxaldehyde were added thereto. The precipitate obtained after stirring at room temperature for 24 hours was filtered, washed with diethylether, and dried. The dried solid was dissolved in a mixed solution of methanol/distilled water and 50% aqueous solution of tetrafluoroboric acid, and the produced solid was filtered and washed with diethylether to obtain 22.0 g of Intermediate [1-F].

(7) Synthesis of Compound 1

[0408] The synthesized Intermediate [1-F] (1.0 eq) and potassium tetrachloroplatinate (K_2PtCl_4) (1.1 eq), and tetrabutylammonium bromide (0.1 eq) were dissolved in acetic acid (0.1M) and stirred at a temperature of 120°C for 72 hours. The reaction mixture was cooled to room temperature, and an organic layer was extracted therefrom three times utilizing dichloromethane and water. The extracted organic layer was dried utilizing magnesium sulfate and concentrated, and column chromatography was utilized to obtain Compound 1 (yield: 20%).

Synthesis Example 2: Synthesis of Compound 2

[0409] Compound 2 was obtained in the same manner as in Synthesis Example 1, except that 2-chloro-4-tert-butylpyridine was utilized instead of 2-bromopyridine.

Synthesis Example 3: Synthesis of Compound 3

[0410] Compound 3 was synthesized in the same manner as in Synthesis Example 1, except that 2-bromo-4-methylpyridine was utilized instead of 2-bromopyridine.

Synthesis Example 4: Synthesis of Compound 4

[0411] Compound 4 was synthesized in the same manner as in Synthesis Example 1, except that tert-butyl(5-bromopyridin-3-yl)carbamate was utilized instead of tert-butyl(3-bromophenyl)carbamate

Synthesis Example 5: Synthesis of Compound 5

[0412] Compound 4 was synthesized in the same manner as in Synthesis Example 1, except that 2-chloro-4-fluorobutylpyridine was utilized instead of 2-bromopyridine, and tert-butyl (5-bromopyridin-3-yl)carbamate was utilized instead of tert-butyl(3-bromophenyl)carbamate.

Synthesis Example 6: Synthesis of Compound 6

[0413] Compound 6 was obtained in the same manner as in Synthesis Example 1, except that 3-(pyridin-2-yloxy)phenol was utilized instead of Intermediate [1-C]

Synthesis Example 7: Synthesis of Compound 7

[0414] Compound 7 was obtained in the same manner as in Synthesis Example 1, except that 3-((4-(tert-butyl)pyridin-2-yl)oxy)phenol was utilized instead of Intermediate [1-C].

Synthesis Example 8: Synthesis of Compound 8

[0415] Compound 8 was obtained in the same manner as in Synthesis Example 1, except that 3-((4-methylpyridin-2-yl)oxy)phenol was utilized instead of Intermediate [1-C].

Synthesis Example 9: Synthesis of Compound 9

[0416] Compound 9 was obtained in the same manner as in Synthesis Example 1, except that tert-butyl(5-bromopyridin-3-yl)carbamate was utilized instead of Tert-butyl(3-bromophenyl)carbamate, and 3-(pyridin-2-yloxy)phenol was utilized instead of Intermediate [1-C].

Synthesis Example 10: Synthesis of Compound 10

[0417] Compound 10 was obtained in the same manner as in Synthesis Example 1, except that tert-butyl(5-bromopyridin-3-yl)carbamate was utilized instead of tert-butyl(3-bromophenyl)carbamate, and 3-((4-fluoropyridin-2-yl)oxy)phenol was utilized instead of Intermediate [1-C].

[0418] ¹H NMR and HR-EIMS of Compounds synthesized in Synthesis Examples 1 to 10 are shown in Table 1.

TABLE 1

Compound	¹ H NMR (CDCl ₃ , 500 MHz)	HR-EIMS	
		found	calc.
1	δ 8.42 (d, 1H), 8.24 (m, 1H), 7.72~7.82 (m, 2H), 7.43 (d, 1H), 7.25~7.29 (m, 2H), 7.16 (m, 1H), 7.12 (d, 1H), 6.78~6.88 (m, 1H), 6.62~6.64 (m, 1H), 6.57~6.59 (m, 2H), 6.50~6.52 (m, 1H), 6.45~6.48 (m, 1H), 6.38 (m, 1H), 5.84 (m, 1H)	645.5828	645.5850
2	δ 8.37~8.42 (d, 1H), 8.19~8.29 (m, 1H), 7.80~7.82 (m, 1H), 7.60~7.63 (m, 1H), 7.25~7.29 (m, 3H), 7.17~7.20 (m, 1H), 6.88~6.90 (m, 2H), 6.62~6.65 (m, 1H), 6.59 (d, 1H), 6.48~6.50 (m, 2H), 6.43 (m, 1H), 6.38 (d, 1H), 5.84 (m, 1H), 1.36 (s, 9H)	701.6981	701.6930
3	δ 8.27~8.29 (m, 2H), 7.80~7.82 (m, 2H), 7.60~7.63 (m, 1H), 7.29 (m, 1H), 7.24 (m, 1H), 7.16 (m, 1H), 7.06 (m, 1H), 6.84~7.89 (m, 1H), 6.59~6.65 (m, 3H), 6.48~6.50 (m, 2H), 6.38~6.43 (m, 2H), 5.84 (m, 1H), 2.21 (s, 3H)	659.6145	659.6120
4	δ 8.45 (m, 1H), 8.25 (m, 1H), 7.89~7.91 (m, 2H), 7.80~7.82 (m, 2H), 7.74 (m, 1H), 7.60~7.62 (m, 1H), 7.35~7.43 (m, 2H), 7.29 (m, 1H), 7.11~7.20 (m, 2H), 6.70~6.72 (m, 2H), 6.65 (m, 1H), 6.55 (m, 1H), 6.48 (m, 1H), 5.94~5.96 (m, 1H)	646.5788	646.5730
5	δ 8.39 (m, 1H), 8.24~8.29 (m, 1H), 7.87~7.91 (m, 2H), 7.70 (m, 1H), 7.62 (d, 1H), 7.40~7.41 (m, 1H), 7.20~7.30 (m, 2H), 6.99 (m, 1H), 6.70~6.73 (d, 2H), 6.65 (m, 1H), 6.44~6.48 (m, 1H), 6.36 (m, 1H), 5.84~5.88 (m, 1H)	664.5615	664.5634
6	δ 8.34 (m, 1H), 7.20~7.24 (m, 2H), 7.06 (m, 1H), 6.93 (m, 1H), 6.82~6.88 (m, 2H), 6.48~6.53 (m, 4H), 6.42 (m, 1H), 6.33~6.38 (m, 3H), 5.84 (m, 1H)	572.4838	572.4870
7	δ 8.24~8.27 (m, 1H), 7.14~7.24 (m, 3H), 6.67~6.97 (m, 4H), 6.50~6.53 (m, 2H), 6.48 (d, 1H), 6.42~6.44 (m, 1H), 6.34~6.38 (m, 2H), 5.84 (m, 1H), 1.34 (s, 9H)	628.5962	628.5950
8	δ 8.19 (m, 1H), 7.20~7.24 (m, 2H), 6.90~6.93 (m, 1H), 6.86~6.88 (m, 1H), 6.69 (m, 1H), 6.50~6.57 (m, 3H), 6.48 (m, 1H), 6.34~6.45 (m, 4H), 5.84 (m, 1H), 2.37 (s, 3H)	586.5132	586.5140
9	δ 8.38 (m, 1H), 7.82~7.84 (m, 2H), 7.68 (m, 1H), 7.25~7.32 (m, 2H), 7.06~7.15 (m, 2H), 6.83 (d, 1H), 6.71~6.75 (m, 2H), 6.48~6.53 (m, 3H), 6.33 (d, 1H), 5.84 (d, 1H)	573.4782	573.4750
10	δ 8.45~8.49 (m, 1H), 7.84 (d, 1H), 7.68 (d, 1H), 7.23~7.35 (m, 2H), 7.16 (d, 1H), 6.45~6.75 (m, 6H), 6.16 (d, 1H), 5.84 (d, 1H)	591.4615	591.4654

[0419] Synthesis methods of compounds other than Compounds synthesized according to Synthesis Examples 1 to 10 may also be easily recognized by those of ordinary skill in the art by referring to the synthesis mechanisms and source materials described above.


Example 1

[0420] As a substrate and an ITO anode, a Corning glass substrate, on which $15 \Omega/\text{cm}^2$ (1,200 Å) ITO was formed, was cut into a size of 50 mm×50 mm×0.7 mm, sonicated with isopropyl alcohol and pure water each for 5 minutes, and then cleaned by exposure to ultraviolet rays and ozone for 30 minutes. Then, the glass substrate was provided to a vacuum deposition apparatus.

[0421] 2-TNATA was vacuum-deposited on the ITO anode formed on the glass substrate to form a hole injection layer having a thickness of 600 Å, and NPB was vacuum-deposited on the hole injection layer to form a hole transport layer having a thickness of 300 Å.


[0422] BCPDS and POPCPA as a co-host (a weight ratio of BCPDS to POPCPA was 1:1) and Compound 1 (dopant) were co-deposited on the hole transport layer at a co-host to dopant weight ratio of 90:10 to form an emission layer having a thickness of 300 Å.

[0423] TSP01 was deposited on the emission layer to form a hole blocking layer having a thickness of 50 Å, Alq_3 was deposited on the hole blocking layer to form an electron transport layer having a thickness of 300 Å, LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Al was vacuum-deposited on the electron injection layer to form a cathode having a thickness of 3,000 Å, thereby completing the manufacture of an organic light-emitting device.




2-TNATA


-continued




NPB



BCPDS




POPCPA



TSP01

-continued



Examples 2 to 10 and Comparative Examples A to E

[0424] Organic light-emitting devices were manufactured substantially in the same manner as in Example 1, except that Compounds shown in Table 2 were each utilized instead of Compound 1 as a dopant in forming an emission layer.

Evaluation Example

[0425] The driving voltage, current density, luminance, luminescent efficiency, and maximum emission wavelength of the organic light-emitting devices manufactured according to Examples 1 to 10 and Comparative Examples A to E were measured by using Keithley SMU 236 and a luminance meter PR650, and results thereof are shown in Table 2. The half lifespan (T50) indicates an amount of time that lapsed when luminance was 50% of the initial luminance (100%) after driving an organic light-emitting device for the lapsed time.


TABLE 2

	Dopant compound	Driving voltage (V)	Luminescent Luminance (cd/m ²)	Luminescent efficiency (cd/A)	Emission color	Maximum emission wavelength (nm)	Half lifespan (T50) (h)
Example 1	1	3.4	15	19.6	Blue	450	55
Example 2	2	3.4	15	17.2	Blue	455	52
Example 3	3	3.3	15	15.1	Blue	452	45
Example 4	4	3.3	15	16.2	Blue	456	43
Example 5	5	3.3	15	16.7	Blue	450	40
Example 6	6	3.3	15	15.3	Blue	451	45
Example 7	7	3.4	15	19.2	Blue	449	47
Example 8	8	3.4	15	18.4	Blue	452	35
Example 9	9	3.3	15	16.9	Blue	449	32
Example 10	10	3.4	15	16.2	Blue	453	34
Comparative Example A	A	4.3	15	20.1	Blue	481	1<
Comparative Example B	B	4.2	15	6.5	Sky-blue	478	20
Comparative Example C	C	3.2	15	9.5	Blue	450	2
Comparative Example D	D	3.8	15	10.5	Sky-blue	475	1

TABLE 2-continued


	Dopant compound	Driving voltage (V)	Luminance (cd/m ²)	Luminescent efficiency (cd/A)	Emission color	Maximum emission wavelength (nm)	Half lifespan (T50) (h)
Comparative Example E	E	4.5	15	15.5	Sky-blue	473	<1

Compound A




Flpic

Compound B




PtNON


Compound C



Compound D



Compound E



[0426] Referring to Table 2, it is confirmed that the organic light-emitting devices of Examples 1 to 10 have a low driving voltage, high efficiency, and high color purity, as compared with those of the organic light-emitting devices of Comparative Examples A to E.

[0427] The organic light-emitting device including the organometallic compound may have a low driving voltage and high efficiency and may exhibit high color purity, thereby implementing high-quality organic light-emitting devices.


[0428] It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

[0429] While one or more embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope as defined by the following claims, and equivalents thereof.


What is claimed is:

1. An organic light-emitting device comprising: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode and comprising an emission layer, wherein the organic layer further comprises at least one of an organometallic compound represented by Formula 1 or 2:

Formula 1



Formula 2




wherein, in Formulae 1 and 2,

M_{11} is selected from platinum (Pt), palladium (Pd), copper (Cu), zinc (Zn), silver (Ag), gold (Au), rhodium

(Rh), iridium (Ir), ruthenium (Ru), rhenium (Re), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm),

A_{11} to A_{13} are each independently selected from a C_5 - C_{60} carbocyclic group and a C_1 - C_{60} heterocyclic group, wherein A_{11} in Formula 1 is not represented by a



moiety,

Y_{11} to Y_{13} are each independently selected from a carbon atom (C) and a nitrogen atom (N),

B_{11} to B_{14} are each independently selected from a single bond, O, and S,

L_{11} to L_{14} are each independently selected from a single bond, $*-O-*$, $*-S-*$, $*-C(R_{15})(R_{16})-*$, $*-C(R_{15})=*$, $*-C(R_{15})-*$, $*-C(R_{15})=C(R_{16})-*$, $*-C(=O)-*$, $*-C(=S)-*$, $*-C\equiv C-*$, $*-B(R_{15})-*$, $*-N(R_{15})-*$, $*-P(R_{15})-*$, $*-Si(R_{15})(R_{16})-*$, $*-P(R_{15})(R_{16})-*$, and $*-Ge(R_{15})(R_{16})-*$,

a_{11} , a_{12} , and a_{14} are each independently an integer from 0 to 3, and a_{13} is an integer from 1 to 3, wherein at least two of a_{11} , a_{12} , and a_{14} are each independently an integer from 1 to 3,

when a_{11} is 0, A_{11} and A_{12} are not linked to each other, when a_{12} is 0, A_{12} and A_{13} are not linked to each other, when a_{13} is 0, A_{13} and a nitrogen atom (N) are not linked to each other, when a_{14} is 0, A_{11} and X_{15} in Formula 1 and A_{11} and X_{19} in Formula 2 are not linked to each other,

X_{11} is N or C(R_{14}), X_{12} is N or C(R_{17}), X_{13} is N or C(R_{18}), and X_{14} is N or C(R_{19}),

X_{15} is N or C(R_{20}) when a_{14} is 0, and X_{15} is C when a_{14} is not 0,

X_{16} is C(R_{21})(R_{22}), X_{17} is C(R_{23})(R_{24}), and X_{18} is C(R_{25})(R_{26}),

X_{19} is C(R_{27})(R_{28}) when a_{14} is 0, and X_{19} is C(R_{27}) when a_{14} is not 0,

R_{11} to R_{28} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a

substituted or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —B(Q₁)(Q₂), —N(Q₁)(Q₂), —P(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂),

R_{1,5} and R₁₁, R₁₅ and R₁₂, and/or R₁₅ and R₁₃ are optionally linked to form a substituted or unsubstituted C₅-C₆₀ carbocyclic group or a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

b11 to b13 are each independently an integer from 1 to 8, at least one substituent of the substituted C₅-C₆₀ carbocyclic group, the substituted C₁-C₆₀ heterocyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted C₁-C₆₀ heteroaryloxy group, the substituted C₁-C₆₀ heteroarylthio group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at

least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and

—Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C₁-C₆₀ alkyl group substituted with at least one selected from deuterium, —F, and a cyano group, a C₆-C₆₀ aryl group substituted with at least one selected from deuterium, —F, and a cyano group, a biphenyl group, and a terphenyl group, and

*, **, and *** each indicate a binding site to a neighboring atom.

2. The organic light-emitting device of claim 1, wherein the emission layer comprises the organometallic compound.

3. The organic light-emitting device of claim 1, wherein the emission layer consists of the organometallic compound; or

the emission layer comprises the organometallic compound and a host, and an amount of the organometallic compound in the emission layer is in a range of about 0.01 parts by weight to about 50 parts by weight based on 100 parts by weight of the emission layer.

4. The organic light-emitting device of claim 3, wherein the host comprises two different hosts.

5. The organic light-emitting device of claim 1, wherein the emission layer comprises the organometallic compound, and

the emission layer emits blue light having a maximum emission wavelength of about 430 nm to about 490 nm.

6. The organic light-emitting device of claim 1, wherein the first electrode is an anode,

the second electrode is a cathode,

the organic layer further comprises a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode,

the hole transport region comprises at least one selected from a hole injection layer, a hole transport layer, a buffer layer, an emission auxiliary layer, and an electron blocking layer, and


the electron transport region comprises at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

7. The organic light-emitting device of claim 6, wherein the electron transport region comprises a hole blocking layer, and


the hole blocking layer comprises a phosphine oxide-containing compound or a silyl-containing compound.

8. An organometallic compound represented by Formula 1 or 2:

Formula 1




Formula 2



wherein, in Formulae 1 and 2,

M_{11} is platinum (Pt), palladium (Pd), copper (Cu), zinc (Zn), silver (Ag), gold (Au), rhodium (Rh), iridium (Ir), ruthenium (Ru), rhenium (Re), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm),

A_{11} to A_{13} are each independently selected from a C_5 - C_{60} carbocyclic group and a C_1 - C_{60} heterocyclic group, wherein A_{11} in Formula 1 is not represented by a



moiety,

Y_{11} to Y_{13} are each independently selected from a carbon atom (C) and a nitrogen atom (N),

B_{11} to B_{14} are each independently selected from a single bond, O, and S,

L_{11} to L_{14} are each independently selected from a single bond, $*-O-*$, $*-S-*$, $*C(R_{15})(R_{16})-*$, $*C(R_{15})-*$, $*=C(R_{15})-*$, $*-C(R_{15})=C(R_{16})-*$, $*-C(=O)-*$, $*-C(=S)-*$, $*-C\equiv C-*$, $*-B(R_{15})-*$, $*-N(R_{15})-*$, $*-P(R_{15})-*$, $*-Si(R_{15})(R_{16})-*$, $*-P(R_{15})(R_{16})-*$, and $*-Ge(R_{15})(R_{16})-*$,

a_{11} , a_{12} , and a_{14} are each independently an integer from 0 to 3, and a_{13} is an integer from 1 to 3, wherein at least two of a_{11} , a_{12} , and a_{14} are each independently an integer from 1 to 3,

when a_{11} is 0, A_{11} and A_{12} are not linked to each other, when a_{12} is 0, A_{12} and A_{13} are not linked to each other, when a_{13} is 0, A_{13} and a nitrogen atom (N) are not linked to each other, when a_{14} is 0, A_{11} and X_{15} in Formula 1 and A_{11} and X_{19} in Formula 2 are not linked to each other,

X_{11} is N or C(R_{14}), X_{12} is N or C(R_{17}), X_{13} is N or C(R_{18}), and X_{14} is N or C(R_{19}),

X_{15} is N or C(R_{20}) when a_{14} is 0, and X_{15} is C when a_{14} is not 0,

X_{16} is C(R_{21})(R_{22}), X_{17} is C(R_{23})(R_{24}), and X_{18} is C(R_{25})(R_{26}),

X_{19} is C(R_{27})(R_{28}) when a_{14} is 0, and X_{19} is C(R_{27}) when a_{14} is not 0,

R_{11} to R_{28} are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_1)(Q_2)(Q_3)$, $-B(Q_1)(Q_2)$, $-N(Q_1)(Q_2)$, $-P(Q_1)(Q_2)$, $-C(=O)$

(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂),

R₁₅ and R₁₁, R₁₅ and R₁₂, and/or R₁₅ and R₁₃ are optionally linked to form a substituted or unsubstituted C₅-C₆₀ carbocyclic group or a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

b1 to b13 are each independently an integer from 1 to 8, at least one substituent of the substituted C₅-C₆₀ carbocyclic group, the substituted C₁-C₆₀ heterocyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted C₁-C₆₀ heteroaryloxy group, the substituted C₁-C₆₀ heteroarylthio group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkyl

enyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and

—Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C₁-C₆₀ alkyl group substituted with at least one selected from deuterium, —F, and a cyano group, a C₆-C₆₀ aryl group substituted with at least one selected from deuterium, —F, and a cyano group, a biphenyl group, and a terphenyl group, and

*, **, and *** each indicate a binding site to a neighboring atom.

9. The organometallic compound of claim 8, wherein

M₁₁ is selected from Pt, Pd, Cu, Ag, and Au.

10. The organometallic compound of claim 8, wherein


A₁₁ to A₁₃ are each independently selected from a benzene group, a naphthalene group, an anthracene group, a phenanthrene group, an azulene group, a triphenylene group, a pyrene group, a chrysene group, a cyclopentadiene group, a 1,2,3,4-tetrahydronaphthalene group, a furan group, a thiophene group, a silole group, an indene group, a fluorene group, an indole group, a carbazole group, a benzofuran group, a dibenzofuran group, a benzothiophene group, a dibenzothiophene group, a benzosilole group, a dibenzosilole group, an indenopyridine group, an indolopyridine group, a benzofuro-pyridine group, a benzothienopyridine group, a benzosilolopyridine group, an indenopyrimidine group, an indolopyrimidine group, a benzofuro-pyrimidine group, a benzothienopyrimidine group, a benzosilolopyrimidine group, a dihydro-pyridine group, a pyridine group, a pyrimidine group, a pyrazine group, a pyridazine group, a triazine group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a phenanthroline group, a pyrrole group, a pyrazole group, an imidazole group, a 2,3-dihydroimidazole group, a triazole group, a 2,3-dihydrotriazole group, an oxazole group, an isoxazole group, a thiazole group, an isothiazole group, an oxadiazole group, a thiadiazole group, a benzopyrazole group, a benzimidazole group, a 2,3-dihydrobenzimidazole group, an imidazopyridine group, a 2,3-dihydroimidazopyridine group, an imidazopyrimidine group, a 2,3-dihydroimidazopyrimidine group, an imidazopyrazine group, a 2,3-dihydroimidazopyrazine group, a benzoxazole group, a benzothiazole group, a benzooxadiazole

group, a benzothiadiazole group, a 5,6,7,8-tetrahydroisoquinoline group, and a 5,6,7,8-tetrahydroquinoline group.


11. The organometallic compound of claim 8, wherein

A₁₁ to A₁₃ are each independently selected from groups represented by Formulae 3-1(1) to 3-1(31) and 3-2(1) to 3-2(19):


-continued




3-1(1)




3-1(2)




3-1(3)




3-1(4)




3-1(5)




3-1(6)




3-1(7)




3-1(8)




3-1(9)




3-1(10)



3-1(11)




3-1(12)




3-1(13)


-continued




3-1(14)




3-1(15)




3-1(16)




3-1(17)




3-1(18)




3-1(19)



3-1(19)



3-1(20)



-continued

-continued

3-1(21)

3-1(22)

3-1(23)

3-1(24)

3-1(25)


3-1(26)

3-1(27)


3-1(28)

3-1(29)


-continued




3-1(30)




3-1(31)




3-2(1)




3-2(2)




3-2(3)



3-2(4)




3-2(5)




3-2(6)


-continued




3-2(7)




3-2(8)




3-2(9)




3-2(10)



3-2(11)




3-2(12)




3-2(13)


-continued




3-2(14)




3-2(15)




3-2(16)



3-2(17)



3-2(18)



3-2(19)

wherein, in Formulae 3-1(1) to 3-1(31) and 3-2(1) to 3-2(19),

Y_{15} is Y_{11} , Y_{12} , or Y_{13} ,

R_{31} and R_{32} are each independently the same as described in connection with R_{11} in Formulae 1 and 2,

b32 is 1 or 2,

b33 is 1, 2, or 3,

b34 is 1, 2, 3, or 4,

b35 is 1, 2, 3, 4, or 5,

* indicates a binding site to M_{11} , and

*' and *'' each indicate a binding site to a neighboring atom.

12. The organometallic compound of claim 8, wherein

Y_{11} and Y_{12} are each C, and Y_{13} is N;

Y_{11} and Y_{12} are each N, and Y_{13} is C;

Y_{11} and Y_{13} are each C, and Y_{12} is N;

Y_{11} and Y_{13} are each N, and Y_{12} is C;

Y_{12} and Y_{13} are each C, and Y_{11} is N; or

Y_{12} and Y_{13} are each N, and Y_{11} is C.

13. The organometallic compound of claim 8, wherein

B_{11} to B_{14} are each a single bond,

a bond between M_{11} and Y_{11} and a bond between M_{11} and

Y_{12} are each a covalent bond, and a bond between M_{11} and Y_{13} is a coordinate bond;

a bond between M_{11} and Y_{11} and a bond between M_{11} and

Y_{13} are each a covalent bond, and a bond between M_{11} and

Y_{12} is a coordinate bond; or

a bond between M_{11} and Y_{12} and a bond between M_{11} and

Y_{13} are each a covalent bond, and a bond between M_{11} and

Y_{11} is a coordinate bond.

14. The organometallic compound of claim 8, wherein

B_{11} to B_{14} are each a single bond;

B_{11} is selected from O and S, and B_{12} to B_{14} are each a single bond;

B_{12} is selected from O and S, and B_{11} , B_{13} , and B_{14} are each a single bond;

B_{13} is selected from O and S, and B_{11} , B_{12} , and B_{14} are each a single bond; or

B_{14} is selected from O and S, and B_{11} , B_{12} , and B_{13} are each a single bond.

15. The organometallic compound of claim 8, wherein

a11 to a13 are each 1, and a14 is 0;

a12 to a14 are each 1, and a11 is 0; or

a11, a13, and a14 are each 1, and a12 is 0.

16. The organometallic compound of claim 8, wherein

a11 to a13 are each 1, and a14 is 0.

17. The organometallic compound of claim 8, wherein

L_{11} is $*-C(R_{15})(R_{16})-*'$, $*-N(R_{15})-*'$, or $*-Si(R_{15})(R_{16})-*'$, and

R_{15} and R_{11} are linked to form a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group, or R_{15} and R_{12} are linked to form a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group.

18. The organometallic compound of claim 8, wherein

R_{11} to R_{28} are each independently selected from:

hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a cyano group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;


a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a cyano group, a phenyl group, and a biphenyl group;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phe-


nalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazoliny group, a benzoquinazoliny group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphtho benzofuranyl group, a naphtho benzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphtho thiophenyl group, a dinaphtho silolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazoliny group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphtho benzofuranyl group, a naphtho benzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphtho thiophenyl group, a dinaphtho silolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, an indolocarbazolyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, and $-\text{P}(=\text{S})(\text{Q}_{31})(\text{Q}_{32})$; and


-continued




6




7



8




9




10


-continued




11




12



13



14



15

* * * * *

专利名称(译)	有机金属化合物和包括其的有机发光器件		
公开(公告)号	US20190280222A1	公开(公告)日	2019-09-12
申请号	US16/203554	申请日	2018-11-28
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KIM SUNGBUM KO SOOBYUNG PARK JUNHA SIM MUNKI AHN HEECHOON LEE HYOYOUNG JEON MINA JUN MIEUN HAN JUNGHOON KIM YOUNGKOOK HWANG SEOKHWAN		
发明人	KIM, SUNGBUM KO, SOOBYUNG PARK, JUNHA SIM, MUNKI AHN, HEECHOON LEE, HYOYOUNG JEON, MINA JUN, MIEUN HAN, JUNGHOON KIM, YOUNGKOOK HWANG, SEOKHWAN		
IPC分类号	H01L51/00 C07F15/00 C07F1/08 C07F1/10 C07F1/12		
CPC分类号	H01L51/0091 C07F1/12 H01L51/0087 C07F15/006 C07F1/10 C07F15/0086 H01L51/5012 C07F1/08 H01L51/0094 H01L51/5016 H01L2251/308 H01L2251/5384		
优先权	1020180028303 2018-03-09 KR		
外部链接	Espacenet USPTO		

摘要(译)

由式1或2表示的有机金属化合物和包含其的有机发光装置。

10

190
150
110