



US 2020006671A1

(19) **United States**

(12) **Patent Application Publication**
SIM et al.

(10) **Pub. No.: US 2020/0006671 A1**
(43) **Pub. Date: Jan. 2, 2020**

(54) **CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

(71) Applicant: **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si (KR)

(72) Inventors: **Munki SIM**, Yongin-si (KR); **Junha PARK**, Yongin-si (KR); **Jangyeol BAEK**, Yongin-si (KR); **Hyoyoung LEE**, Yongin-si (KR); **Soobyung KO**, Yongin-si (KR); **Youngkook KIM**, Yongin-si (KR)

(52) **U.S. Cl.**
CPC **H01L 51/0072** (2013.01); **H01L 51/5012** (2013.01); **H01L 51/5092** (2013.01); **H01L 51/5096** (2013.01); **H01L 51/0073** (2013.01); **H01L 51/5072** (2013.01); **H01L 51/0061** (2013.01); **H01L 51/0058** (2013.01); **C07F 5/02** (2013.01); **H01L 51/5056** (2013.01); **H01L 51/0074** (2013.01)

(57) **ABSTRACT**
A condensed cyclic compound and an organic light-emitting device including the same, the condensed cyclic compound being represented by Formula 1:

(21) Appl. No.: **16/293,753**

(22) Filed: **Mar. 6, 2019**



(30) **Foreign Application Priority Data**

Jun. 27, 2018 (KR) 10-2018-0074184

Publication Classification

(51) **Int. Cl.**
H01L 51/00 (2006.01)
H01L 51/50 (2006.01)
C07F 5/02 (2006.01)

<Formula 1>



190
150
110

FIG. 1




FIG. 2




FIG. 3





FIG. 4



**CONDENSED CYCLIC COMPOUND AND
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME**

CROSS-REFERENCE TO RELATED
APPLICATION

[0001] Korean Patent Application No. 10-2018-0074184, filed on Jun. 27, 2018, in the Korean Intellectual Property Office, and entitled: "Condensed Cyclic Compound and Organic Light-Emitting Device Including the Same," is incorporated by reference herein in its entirety.

BACKGROUND

1. Field

[0002] Embodiments relate to a condensed cyclic compound and an organic light-emitting device including the same.

2. Description of the Related Art


[0003] Organic light-emitting devices are self-emission devices that produce full-color images, and also have wide viewing angles, high contrast ratios, short response times, and excellent characteristics in terms of brightness, driving voltage, and response speed, compared to devices in the art.

[0004] An example of such organic light-emitting devices may include a first electrode disposed on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode, which are sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, recombine in the emission layer to produce excitons. These excitons transit from an excited state to a ground state, thereby generating light.

SUMMARY

[0005] The embodiments may be realized by providing a condensed cyclic compound represented by Formula 1:


<Formula 1>



[0006] wherein, in Formula 1, R_{11} to R_{14} are each independently selected from a group represented by Formula 2, hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{10} alkoxy

group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_1)(Q_2)(Q_3)$, $-B(Q_1)(Q_2)$, $-N(Q_1)(Q_2)$, $-P(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)(Q_1)$, $-S(=O)_2(Q_1)$, $-P(=O)(Q_1)(Q_2)$, and $-P(=S)(Q_1)(Q_2)$,

<Formula 2>



[0007] wherein, in Formulae 1 and 2, A_{11} to A_{14} and A_{21} to A_{24} are each independently selected from a C_5 - C_{60} carbocyclic group and a C_1 - C_{60} heterocyclic group, in which A_{11} to A_{14} are separate or are linked via a first linking group and A_{21} to A_{24} are separate or are linked via a second linking group, n_{11} and n_{21} are each independently 0 or 1. L_{11} to L_{14} and L_{21} to L_{24} are each independently selected from a single bond, $*-N(R_a)-*$, a substituted or unsubstituted C_5 - C_{60} carbocyclic group, and a substituted or unsubstituted C_1 - C_{60} heterocyclic group, in which $*$ and * indicate a binding site to a neighboring atom, a_{11} to a_{14} and a_{21} to a_{24} are each independently selected from 0, 1, 2, and 3, R_a and R_{21} to R_{24} are each independently selected from a binding site, hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_1)(Q_2)(Q_3)$, $-B(Q_1)(Q_2)$, $-N(Q_1)(Q_2)$, $-P(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)(Q_1)$, $-S(=O)_2(Q_1)$, $-P(=O)(Q_1)(Q_2)$, and $-P(=S)(Q_1)(Q_2)$,

and $-P(=S)(Q_1)(Q_2)$, provided that one of R_{21} to R_{24} is the binding site, b11 to b14 and b21 to b24 are each independently selected from 1, 2, 3, 4, 5, and 6, c11 to c14 and c21 to c24 are each independently selected from 1, 2, 3, 4, 5, and 6, and Q_1 to Q_3 are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C_1 - C_{60} alkyl group substituted with at least one selected from deuterium, $-F$, and a cyano group, a C_6 - C_{60} aryl group substituted with at least one selected from deuterium, $-F$, and a cyano group, a biphenyl group, and a terphenyl group.

[0008] The embodiments may be realized by providing an organic light-emitting device including a first electrode; a second electrode; and an organic layer between the first electrode and the second electrode and including an emission layer, wherein the organic layer includes the condensed cyclic compound according to an embodiment.

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] Features will be apparent to those of skill in the art by describing in detail exemplary embodiments with reference to the attached drawings in which:

[0010] FIG. 1 illustrates a schematic cross-sectional view of an organic light-emitting device according to an embodiment;

[0011] FIG. 2 illustrates a schematic cross-sectional view of an organic light-emitting device according to an embodiment;

[0012] FIG. 3 illustrates a schematic cross-sectional view of an organic light-emitting device according to an embodiment; and

[0013] FIG. 4 illustrates a schematic cross-sectional view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

[0014] Example embodiments will now be described more fully hereinafter with reference to the accompanying drawings; however, they may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey exemplary implementations to those skilled in the art.

[0015] In the drawing figures, the dimensions of layers and regions may be exaggerated for clarity of illustration.

[0016] Hereinafter, embodiments are described in detail by referring to the attached drawings, and in the drawings, like reference numerals denote like elements, and a redundant explanation thereof will not be provided herein.


[0017] As used herein, the singular forms “a,” “an” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. As used herein, the terms “or” and “and/or” are not exclusive terms.

[0018] It will be further understood that the terms “includes,” “including,” “comprises,” and/or “comprising” used herein specify the presence of stated features or components, but do not preclude the presence or addition of one or more other features or components.


[0019] It will be understood that when a layer, region, or component is referred to as being “on” or “onto” another layer, region, or component, it may be directly or indirectly formed on the other layer, region, or component. For example, intervening layers, regions, or components may be present.

[0020] An aspect provides a condensed cyclic compound represented by Formula 1:

<Formula 1>



<Formula 2>



[0021] In Formulae 1 and 2, A_{11} to A_{14} and A_{21} to A_{24} (e.g., ring A_{11} to ring A_{14} and ring A_{21} to ring A_{24}) may each independently be selected from a C_5 - C_{60} carbocyclic group and a C_1 - C_{60} heterocyclic group. In an implementation, in Formulae 1 and 2, A_{11} to A_{14} may be separate or may be linked via a first linking group, and A_{21} to A_{24} may be separate or may be linked via a second linking group.

[0022] In an implementation, in Formulae 1 and 2, A_{11} to A_{14} and A_{21} to A_{24} may each independently be selected from, e.g., a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a perylene group, a thiophene group, a furan group, a silole group, a carbazole group, an indole group, an isoindole group, a benzofuran group, a benzothiophene group, a benzosilole group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, a dibenzocarbazole group, and a dibenzosilole group.

[0023] In an implementation, in Formulae 1 and 2, A_{11} to A_{14} and A_{21} to A_{24} may each independently be selected from, e.g., a benzene group, a naphthalene group, a fluorene group, a phenanthrene group, an anthracene group, a triphenylene group, a pyrene group, a chrysene group, a perylene group, a carbazole group, a dibenzofuran group, and a dibenzothiophene group.

[0024] In an implementation, in Formulae 1 and 2, A_{11} to A_{14} and A_{21} to A_{24} may each independently be selected from, e.g., a benzene group, a naphthalene group, and a carbazole group.

[0025] In an implementation, in Formulae 1 and 2, A_{11} to A_{14} and A_{21} to A_{24} may each be, e.g., a benzene group.

[0026] In an implementation, in Formula 1, A_{13} and A_{14} and/or A_{11} and A_{14} may optionally be linked via a first linking group.

[0027] In an implementation, in Formula 2, A_{23} and A_{24} and/or A_{21} and A_{24} may optionally be linked via a second linking group.

[0028] The first linking group may be selected from, e.g., a single bond, $*-O-*$, $*-S-*$, $*-B(R_{15})-*$, $*-N(R_{15})-*$, $*-C(R_{15})(R_{16})-*$, and $-C(R_{15})=C(R_{16})-*$,

[0029] R_{15} and R_{16} may each independently be selected from:

[0030] hydrogen, a C_1 - C_{20} alkyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0031] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, a C_1 - C_{20} alkyl group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, and

[0032] $*$ and $*'$ each indicate a binding site to a neighboring atom.

[0033] The second linking group may be selected from a single bond, $*-O-*$, $*-S-*$, $*-B(R_{25})-*$, $*-N(R_{25})-*$, $*-C(R_{25})(R_{26})-*$, and $-C(R_{25})=C(R_{26})-*$,

[0034] R_{25} and R_{26} may each independently be selected from:

[0035] hydrogen, a C_1 - C_{20} alkyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0036] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, a C_1 - C_{20} alkyl group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, and

[0037] $*$ and $*'$ each indicate a binding site to a neighboring atom.

[0038] In an implementation, the first linking group and the second linking group may each independently be selected from, e.g., a single bond, $*-O-*$, and $*-S-*$.

[0039] In Formula 1, n_{11} indicates the number of $A_{14}(s)$ and may be selected from 0 and 1.

[0040] In Formula 2, n_{21} indicates the number of $A_{24}(s)$ and may be selected from 0 and 1.

[0041] In an implementation, in Formulae 1 and 2, L_{11} to L_{14} and L_{21} to L_{24} may each independently be selected from, e.g., a single bond, $*-N(R_a)-*$, a substituted or unsubstituted C_5 - C_{60} carbocyclic group, and a substituted or unsubstituted C_1 - C_{60} heterocyclic group.

[0042] For example, in Formulae 1 and 2, L_{11} to L_{14} and L_{21} to L_{24} may each independently be selected from:


[0043] a single bond, $*-N(R_a)-*$, a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoranthene

group, a triphenylene group, a pyrene group, a chrysene group, a perylene group, a thiophene group, a furan group, a silole group, a carbazole group, an indole group, an isoindole group, a benzofuran group, a benzothiophene group, a benzosilole group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, a dibenzocarbazole group, and a dibenzosilole group; and


[0044] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a perylene group, a thiophene group, a furan group, a silole group, a carbazole group, an indole group, an isoindole group, a benzofuran group, a benzothiophene group, a benzosilole group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, a dibenzocarbazole group, and a dibenzosilole group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a thiophenyl group, a furanyl group, a silolyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, and $-B(Q_{31})(Q_{32})$, and

[0045] Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{60} alkyl group, a phenyl group, a biphenyl group, and a terphenyl group.


[0046] In an implementation, in Formulae 1 and 2, L_{11} to L_{14} and L_{21} to L_{24} may each independently be selected from, e.g., a single bond, $*-N(R_a)-*$, and a group represented by one of Formulae 3-1 to 3-41:




3-1



3-2













3-3




3-4

-continued




-continued

3-5




3-15

3-6




3-16

3-7




3-17

3-8




3-18

3-9




3-19

3-10




3-20

3-11




3-21

3-12










3-22

3-13




3-14

-continued




-continued

3-23




3-30

3-24




3-31

3-25




3-32

3-26




3-33

3-27




3-34

3-28




3-35

3-29




3-36


-continued




3-37




3-38



3-39



3-40



3-41

[0047] In Formulae 3-1 to 3-41,**[0048]** X_{31} may be selected from O and S.**[0049]** X_{32} may be selected from O, S, $N(R_{33})$, and $C(R_{33})(R_{34})$.**[0050]** R_{31} to R_{34} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1-C_{20} alkyl group,a C_1-C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a thiophenyl group, a furanyl group, a silolyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranlyl group, a benzothiophenyl group, a benzosilolyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzo-carbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, and $-B(Q_{31})(Q_{32})$.**[0051]** Q_{31} to Q_{33} each independently be selected from a C_1-C_{60} alkyl group, a phenyl group, a biphenyl group, and a terphenyl group.**[0052]** b_{31} may be selected from 1, 2, 3, and 4,**[0053]** b_{32} may be selected from 1, 2, 3, 4, 5, and 6,**[0054]** b_{33} may be selected from 1, 2, 3, 4, 5, 6, 7, and 8,**[0055]** b_{34} may be selected from 1, 2, 3, 4, and 5,**[0056]** b_{35} may be selected from 1, 2, and 3,**[0057]** b_{36} may be selected from 1 and 2, and**[0058]** * and *' each indicate a binding site to a neighboring atom.**[0059]** In an implementation, in Formulae 1 and 2, a_{11} to a_{14} and a_{21} to a_{24} indicate the number of L_{11} to L_{14} and L_{21} to L_{24} , respectively, and may each independently be selected from 0, 1, 2, and 3.**[0060]** In an implementation, in Formulae 1 and 2, a_{11} to a_{14} and a_{21} to a_{24} may each independently be selected from 0 and 1.**[0061]** In Formula 1, R_{11} to R_{14} may each independently be selected from a group represented by Formula 2, hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{10} cycloalkyl group, a substituted or unsubstituted C_1-C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3-C_{10} cycloalkenyl group, a substituted or unsubstituted C_1-C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, a substituted or unsubstituted C_1-C_{60} heteroaryl group, a substituted or unsubstituted C_1-C_{60} heteroaryloxy group, a substituted or unsubstituted C_1-C_{60} heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_1)(Q_2)(Q_3)$, $-B(Q_1)(Q_2)$, $-N(Q_1)(Q_2)$, $-P(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)(Q_1)$, $-S(=O)_2(Q_1)$, $-P(=O)(Q_1)(Q_2)$, and $-P(=S)(Q_1)(Q_2)$, and**[0062]** Q_1 to Q_3 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, a C_1-C_{60} alkoxy group, a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_1-C_{60} heteroaryl group, a C_1-C_{60} heteroaryloxy group, a C_1-C_{60}

heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C₁-C₆₀ alkyl group substituted with at least one selected from deuterium, —F, and a cyano group, a C₆-C₆₀ aryl group substituted with at least one selected from deuterium, —F, and a cyano group, a biphenyl group, and a terphenyl group.

[0063] For example, in Formula 1, R₁₁ to R₁₄ may each independently be selected from:

[0064] a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

[0065] a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a phenyl group, and a biphenyl group;

[0066] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiophenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group;

[0067] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl

group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiophenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiophenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group,

phenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothio-phenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, an indolocarbazolyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_3)$, $-\text{S}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, and $-\text{P}(=\text{S})(\text{Q}_{31})(\text{Q}_{32})$; and

[0068] $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, and $-\text{P}(=\text{S})(\text{Q}_1)(\text{Q}_2)$, and

[0069] Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0070] In an implementation, in Formula 1, R_{11} to R_{14} may each independently be selected from:



[0071] a group represented by Formula 2, hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a cyano group, a C_1 - C_{20} alkyl group;

[0072] a C_1 - C_{20} alkyl group substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, and a cyano group;











[0073] groups represented by Formulae 5-1 to 5-142; and

[0074] $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, and $-\text{P}(=\text{S})(\text{Q}_1)(\text{Q}_2)$:

-continued




-continued




-continued

5-13




5-23

5-14




5-24

5-15




5-25

5-16




5-26

5-17




5-27

5-18




5-28

5-19




5-29

5-20




5-30

5-21




5-31

5-22
















5-32




5-33

-continued




-continued

5-34




5-47

5-35




5-48

5-36




5-49

5-37




5-50

5-38




5-51

5-39




5-52

5-40




5-53

5-41




5-54

5-42




5-55

5-43




5-56

5-44




5-57











5-45



5-46




-continued




-continued

5-58




5-68

5-59




5-69

5-60




5-70

5-61




5-71

5-62




5-72

5-63




5-73

5-64




5-74

5-65




5-75

5-66




5-76

5-67




5-77




5-78


-continued




5-79




5-80




5-81




5-82




5-83




5-84




5-85




5-86



5-87




5-88




5-89


-continued




5-90




5-91




5-92




5-93




5-94




5-95




5-96




5-97



5-98











5-99




5-100

-continued




-continued

5-101




5-109

5-102




5-110

5-103




5-111

5-104




5-112

5-105




5-113

5-106




5-114

5-107




5-115

5-108




5-116


-continued




5-117




5-118




5-119




5-120




5-121



5-122




5-123




5-124


-continued




5-125




5-126




5-127




5-128




5-129



5-130




5-131




5-132


-continued




5-133




5-134




5-135




5-136



5-137




5-138




5-139


-continued



5-140



5-141



5-142

[0075] In Formulae 5-1 to 5-142,

[0076] X_{51} may be selected from O, S, $N(R_{51})$, and $C(R_{51})(R_{60})$;

[0077] X_{52} may be N or $C(R_{52})$, X_{53} may be N or $C(R_{53})$, X_{54} may be N or $C(R_{54})$, X_{55} may be N or $C(R_{55})$, X_{56} may be N or $C(R_{56})$, X_{57} may be N or $C(R_{57})$, X_{58} may be N or $C(R_{58})$, and X_{59} may be N or $C(R_{59})$,

[0078] R_{51} to R_{60} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a thiophenyl group, a furanyl group, a silolyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, $-Si(Q_{31})(Q_{32})(Q_{33})$, $-N(Q_{31})(Q_{32})$, $-B(Q_{31})(Q_{32})$, $-C(=O)(Q_{31})$, $-S(=O)(Q_{31})$, $-S(=O)_2(Q_{31})$, $-P(=O)(Q_{31})(Q_{32})$, and $-P(=S)(Q_{31})(Q_{32})$,

[0079] Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{60} alkyl group, a phenyl group, a biphenyl group, and a terphenyl group,

[0080] b51 may be selected from 1, 2, 3, 4, and 5,

[0081] b52 may be selected from 1, 2, 3, 4, 5, 6, and 7,

[0082] b53 may be selected from 1, 2, 3, 4, 5, 6, 7, 8, and 9,

[0083] b54 may be selected from 1, 2, 3, and 4,

[0084] b55 may be selected from 1, 2, and 3,

[0085] b56 may be selected from 1 and 2,

[0086] b57 may be selected from 1, 2, 3, 4, 5, and 6, and

[0087] * indicates a binding site to a neighboring atom.


[0088] In one embodiment, in Formula 1, R_{11} to R_{14} may each independently be selected from:

[0089] a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group;


[0090] a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, and a cyano group; and

[0091] groups represented by Formulae 6-1 to 6-161:


-continued




6-1




6-2




6-3




6-4




6-5




6-6




6-7




6-8




6-9




6-10




6-11




6-12




6-13



6-14












6-15




6-16

-continued




-continued

6-17




6-26

6-18




6-27

6-19




6-28

6-20



6-29


6-21



6-30


6-22

6-23




6-31

6-24












6-32

6-25




6-33

-continued




-continued

6-34




6-43

6-35




6-44

6-36




6-45

6-37




6-46




6-47

6-38




6-48

6-39




6-49

6-40




6-50

6-41













6-51

6-42




-continued




-continued

6-52




6-62

6-53




6-63

6-54




6-64

6-55




6-65

6-56




6-66

6-57




6-67

6-58




6-68

6-59




6-69

6-60













6-70

6-61




6-71

-continued




-continued


6-72




6-73




6-74




6-75




6-76




6-77




6-78




6-79



6-80



6-81



6-82

6-83

6-84

6-85

6-86

6-87


6-88

6-89


6-90

6-91


-continued




6-92




6-93




6-94




6-95




6-96




6-97



6-98




6-99




6-100


-continued




6-101




6-102




6-103




6-104




6-105



6-106




6-107




6-108


-continued




6-109




6-110




6-111




6-112




6-113



6-114




6-115




6-116


-continued




6-117




6-118




6-119




6-120




6-121



6-122











6-123




6-124

-continued




-continued

6-125




6-133

6-126




6-134

6-127




6-135

6-128




6-136

6-129




6-137

6-130




6-138

6-131




6-139

6-132




6-140


-continued




6-141




6-142




6-143




6-144




6-145



6-146




6-147




6-148


-continued




6-149




6-150




6-151




6-152




6-153




6-154



6-155




6-156




6-157


-continued




6-158



6-159



6-160



6-161

- [0092] In Formulae 6-1 to 6-161,
 [0093] i-Pr indicates an isopropyl group,
 [0094] t-Bu indicates a tert-butyl group,
 [0095] Ph indicates a phenyl group,
 [0096] 1-Naph indicates a 1-naphthyl group,
 [0097] 2-Naph indicates a 2-naphthyl group, and
 [0098] * indicates a binding site to a neighboring atom.
 [0099] In Formulae 1 and 2, R_α and R_{21} to R_{24} may each independently be selected from a binding site (e.g., between Formula 1 and Formula 2), hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60}

heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_1)(Q_2)(Q_3), —B(Q_1)(Q_2), —N(Q_1)(Q_2), —P(Q_1)(Q_2), —C(=O)(Q_1), —S(=O)(Q_1), —S(=O)₂(Q_1), —P(=O)(Q_1)(Q_2), and —P(=S)(Q)(Q_2), wherein at least one selected from R_{21} to R_{24} may be a binding site, and

[0100] Q_1 to Q_3 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C_1 - C_{60} alkyl group substituted with at least one selected from deuterium, —F, and a cyano group, a C_6 - C_{60} aryl group substituted with at least one selected from deuterium, —F, and a cyano group, a biphenyl group, and a terphenyl group.

[0101] For example, in Formulae 1 and 2, R_α and R_{21} to R_{24} may each independently be selected from:

[0102] a binding site, hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0103] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a phenyl group, and a biphenyl group;

[0104] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinylnyl group, a benzoquinazolinylnyl group, a cinnolinylnyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl

group, a dinaphthofuranyl group, a dinaphthothiophenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group;

[0105] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoxazolyl group, a benzisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiophenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, an indolocarbazolyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, and $-\text{P}(=\text{S})(\text{Q}_{31})(\text{Q}_{32})$; and

[0106] $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, and $-\text{P}(=\text{S})(\text{Q}_1)(\text{Q}_2)$, and

[0107] Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0108] In an implementation, in Formulae 1 and 2, R_a and R_{21} to R_{24} may each independently be selected from:

[0109] a binding site, hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a cyano group, a C_1 - C_{20} alkyl group;

[0110] a C_1 - C_{20} alkyl group substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$ and a cyano group;

[0111] groups represented by Formulae 5-1 to 5-142; and

[0112] $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, and $-\text{P}(=\text{S})(\text{Q}_1)(\text{Q}_2)$, and

[0113] Q_1 to Q_3 may each independently be selected from a C_1 - C_{60} alkyl group, a phenyl group, a biphenyl group, and a terphenyl group.

[0114] In an implementation, in Formulae 1 and 2, R_a and R_{21} to R_{24} may each independently be selected from:

[0115] a binding site, hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a cyano group, a methyl group, an ethyl group, an

azolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiophenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, an indolocarbazolyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, and $-\text{P}(=\text{S})(\text{Q}_{31})(\text{Q}_{32})$; and

[0106] $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, and $-\text{P}(=\text{S})(\text{Q}_1)(\text{Q}_2)$, and

[0107] Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0108] In an implementation, in Formulae 1 and 2, R_a and R_{21} to R_{24} may each independently be selected from:

[0109] a binding site, hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a cyano group, a C_1 - C_{20} alkyl group;

[0110] a C_1 - C_{20} alkyl group substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$ and a cyano group;

[0111] groups represented by Formulae 5-1 to 5-142; and

[0112] $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, and $-\text{P}(=\text{S})(\text{Q}_1)(\text{Q}_2)$, and

[0113] Q_1 to Q_3 may each independently be selected from a C_1 - C_{60} alkyl group, a phenyl group, a biphenyl group, and a terphenyl group.

[0114] In an implementation, in Formulae 1 and 2, R_a and R_{21} to R_{24} may each independently be selected from:

[0115] a binding site, hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a cyano group, a methyl group, an ethyl group, an

n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group;




[0116] a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I and a cyano group; and

[0117] groups represented by Formulae 6-1 to 6-161.

[0118] In Formulae 1 and 2, b11 to b14 and b21 to b24 indicate the number of substitutions of R₁₁ to R₁₄ and R₂₁ to R₂₄, respectively, and may each independently be selected from 1, 2, 3, 4, 5, and 6.

[0119] In Formulae 1 and 2, c11 to c14 and c21 to c24 may each independently be selected from 1, 3, 4, 5, and 6.

[0120] In an implementation, the condensed cyclic compound represented by Formula 1 may be represented by one selected from Formulae 1-1 to 1-3.



[0121] In Formulae 1-1 to 1-3,


[0122] A₁₁ to A₁₄, L₁₁ to L₁₄, a11 to a14, and b11 to b14 may each independently be the same as those described in Formula 1,

[0123] X₁₁ may be selected from a single bond, *—O—*, and *—S—*;




[0124] R₁₁ to R₁₄ may each independently be selected from a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —B(Q₁)(Q₂), —N(Q₁)(Q₂), —P(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂), and

[0125] Q₁ to Q₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C₁-C₆₀ alkyl group substituted with at least one selected from deuterium, —F, and a cyano group, a C₆-C₆₀ aryl group substituted with at least one selected from deuterium, —F, and a cyano group, a biphenyl group, and a terphenyl group.

[0126] In an implementation, the group represented by Formula 2 may be represented by one selected from Formulae 2-1 to 2-4.



-continued



[0127] In Formulae 2-1 to 2-4,

[0128] * indicates a binding site,




[0129] A₂₁ to A₂₄, L₂₁ to L₂₄, a₂₁ to a₂₄, and b₂₁ to b₂₄ may each independently be the same as those described in Formula 2,



[0130] R₂₁ to R₂₄ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio

group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —B(Q₁)(Q₂), —N(Q₁)(Q₂), —P(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂), and

[0131] Q₁ to Q₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C₁-C₆₀ alkyl group substituted with at least one selected from deuterium, —F, and a cyano group, a C₆-C₆₀ aryl group substituted with at least one selected from deuterium, —F, and a cyano group, a biphenyl group, and a terphenyl group.

[0132] In an implementation, the group represented by Formula 2 may be represented by one selected from Formulae 2-11 to 2-22.





[0133] In Formulae 2-11 to 2-22,

[0134] * indicates a binding site,

[0135] A₂₁ to A₂₄, L₂₁ to L₂₄, a₂₁ to a₂₄, and b₂₁ to b₂₄ may each independently be the same as those described in Formula 2,



[0136] X₂₁ may be selected from a single bond, *—O—*, and *—S—*,

[0137] R₂₁ to R₂₄ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted





C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_0 heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{P}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$, and $-\text{P}(=\text{S})(\text{Q}_1)(\text{Q}_2)$, and

[0138] Q_1 to Q_3 may each independently be selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C_1 - C_{60} alkyl group substituted with at least one selected from deuterium, $-\text{F}$, and a cyano group, a C_6 - C_{60} aryl group substituted with at least one selected from deuterium, $-\text{F}$, and a cyano group, a biphenyl group, and a terphenyl group.

[0139] In an implementation, the condensed cyclic compound represented by Formula 1 may be one of Compounds 1 to 86.



-continued



1

2

3







4

5

6


-continued

-continued




-continued

-continued





13

16





14

17




15

18




-continued


19




20



21




22




-continued


23



24




25




-continued


26



27




28




-continued




29





30




-continued



-continued




-continued




36

-continued




38

37




39




-continued

40




-continued


43




41




44




42



45




-continued




46


-continued




49




47



50




48




51

-continued




52


-continued




55




53




56




57



54




58




59


-continued




60



61




62




63


-continued




64




65



66




67




68

-continued


69




70




71



72




73




-continued


74




75




76



77




78




-continued

-continued


79




80




81




82




83




84



85




-continued



86

<Formula 1A>



[0140] The condensed cyclic compound represented by Formula 1 may variously emit light such as red light, green light, and blue light. For example, the condensed cyclic compound represented by Formula 1 may emit blue light. In an implementation, the condensed cyclic compound represented by Formula 1 may emit blue light having a maximum (intensity) emission wavelength of, e.g., about 440 nm to about 480 nm.

[0141] In order to effectively achieve a thermally activated delayed fluorescence process, satisfying a small difference value (ΔE_{ST}) between a lowest excitation singlet energy level and a lowest excitation triplet energy level and a large oscillator strength (f) may be desirable. The small ΔE_{ST} and the large f may have a trade-off relation, and it may be difficult to satisfy the small ΔE_{ST} and the large f at the same time. Due to the structural characteristics described below, the condensed cyclic compound represented by Formula 1 may satisfy the small ΔE_{ST} and the large f at the same time, thereby effectively achieving the thermally activated delayed fluorescence process.


[0142] The condensed cyclic compound may include boron (B) in a core as represented by Formula 1A. For example, nitrogen (N) may have energy corresponding to highest occupied molecular orbital (HOMO), B may have energy corresponding to lowest unoccupied molecular orbital (LUMO), and carbon (C) adjacent to N and B alternately may have energy corresponding to HOMO/LUMO due to a resonance effect. As such, in the condensed cyclic compound, HOMO and LUMO may be separated at an atom level, and TADF characteristics may be exhibited. For example, the condensed cyclic compound may exhibit characteristics different from a compound including a carbazole structure that does not include B (e.g., a compound including only a carbazole structure may not exhibit TADF characteristics). Due to such TADF characteristics, the organic light-emitting device including the condensed cyclic compound may have high efficiency:

[0143] In addition, the condensed cyclic compound may form the overlap of HOMO and LUMO due to a multiple resonance effect, and the condensed cyclic compound may be advantageous to emission transition.

[0144] The condensed cyclic compound may include a carbazole ring in a core as represented by Formula 1B, and the condensed cyclic compound may have a relatively rigid structure. In general, when a compound absorbs energy and emits light while the energy transitions, the change in the structure of the compound may result. The condensed cyclic compound may include a carbazole ring, and such a structural change may be minimized. For example, full width at half maximum (FWHM) may be narrowed and vibration may be suppressed, thereby contributing to improving quantum efficiency. Consequently, the efficiency of the organic light-emitting device including the condensed cyclic compound may be improved and high color purity may be provided.

[0145] Relatively high S1 and T1 may be required for emitting blue light. The condensed cyclic compound may include a carbazole ring, and it is possible to provide a compound having relatively high bond dissociation energy. For example, the condensed cyclic compound may include a carbazole ring, the condensed cyclic compound may have high bond dissociation energy, and the efficiency of the organic light-emitting device including the condensed cyclic compound may be improved.

<Formula 1B>



[0146] Furthermore, the condensed cyclic compound may have relatively high charge (hole or electron) transport capability, the exciton formation ratio in the emission layer of the organic light-emitting device including the condensed cyclic compound represented by Formula 1 may be improved, and the organic light-emitting device may have a low driving voltage, high efficiency, a long lifespan, and high maximum quantum efficiency.

[0147] In addition, the condensed cyclic compound may have a relatively small ΔE_{ST} , the condensed cyclic com-

compound may maintain a relatively low T1 ratio, and TTA or TPQ caused at a high T1 ratio may occur to a relatively lesser degree. For example, roll-off characteristics of the organic light-emitting device including the condensed cyclic compound may be improved.

[0148] A synthesis method for the condensed cyclic compound represented by Formula 1 may be understood art by referring to the following examples.

[0149] At least one condensed cyclic compound represented by Formula 1 may be included between a pair of electrodes constituting an organic light-emitting device. In an implementation, the condensed cyclic compound may be included in at least one layer selected from a hole transport region, an electron transport region, and an emission layer. In an implementation, the condensed cyclic compound of Formula 1 may be used as a material for a capping layer located outside a pair of electrodes of an organic light-emitting device.

[0150] Another aspect provides an organic light-emitting device including: a first electrode, a second electrode facing the first electrode, and an organic layer between the first electrode and the second electrode, the organic layer including an emission layer and at least one condensed cyclic compound represented by Formula 1 described above.

[0151] The term “organic layer” as used herein refers to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of the organic light-emitting device. A material included in the “organic layer” is not limited to an organic material.

[0152] The expression “(an organic layer) includes at least one condensed cyclic compound” used herein may include a case in which “(an organic layer) includes identical compounds represented by Formula 1” and a case in which “(an organic layer) includes two or more different condensed cyclic compounds represented by Formula 1.”

[0153] For example, the organic layer may include, as the condensed cyclic compound, only Compound 1. In this regard, Compound 1 may exist in an emission layer of the organic light-emitting device. In one or more embodiments, the organic layer may include, as the condensed cyclic compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may exist in an identical layer (for example, Compound 1 and Compound 2 may all exist in an emission layer), or different layers (for example, Compound 1 may exist in an emission layer and Compound 2 may exist in an electron transport region).

[0154] In an implementation, the first electrode of the organic light-emitting device may be an anode, and the second electrode of the organic light-emitting device may be a cathode, and the organic layer may further include a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode, and the hole transport region may include a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or any combination thereof, and the electron transport region may include a hole blocking layer, an electron control layer, an electron transport layer, an electron injection layer, or a combination thereof.

[0155] In an implementation, the emission layer may include the condensed cyclic compound represented by Formula 1. The emission layer may further include a host in addition to the condensed cyclic compound, and an amount of the condensed cyclic compound in the emission layer may

be smaller than an amount of the host. In an implementation, the condensed cyclic compound may act as a thermally activated delayed fluorescence (TADF) emitter:

[0156] In an implementation, the emission layer may not include a phosphorescent compound (e.g., a transition metal compound). For example, the emission layer may consist of the condensed cyclic compound represented by Formula 1 and the host.

[0157] In an implementation, at least one selected from the hole transport region and the emission layer may include at least one selected from an arylamine-containing compound, an acridine-containing compound, and a carbazole-containing compound.

[0158] In an implementation, at least one selected from the emission layer and the electron transport region may include at least one selected from a silicon-containing compound, a phosphine-containing compound, a sulfur oxide-containing compound, a phosphorus oxide-containing compound, a triazine-containing compound, a pyrimidine-containing compound, a pyridine-containing compound, a dibenzofuran-containing compound, and a dibenzothiophene-containing compound.

[0159] [Description of FIG. 1]

[0160] FIG. 1 illustrates a schematic view of an organic light-emitting device 10 according to an embodiment. The organic light-emitting device 10 may include a first electrode 110, an organic layer 150, and a second electrode 190.

[0161] Hereinafter, the structure of the organic light-emitting device 10 according to an embodiment and a method of manufacturing the organic light-emitting device 10 will be described in connection with FIG. 1.

[0162] [First Electrode 110]

[0163] In an implementation, a substrate may be additionally disposed under the first electrode 110 or above the second electrode 190. The substrate may be a glass substrate or a plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

[0164] The first electrode 110 may be formed by depositing or sputtering a material for forming the first electrode 110 on the substrate. When the first electrode 110 is an anode, the material for a first electrode may be selected from materials with a high work function to facilitate hole injection.

[0165] The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. In an implementation, when the first electrode 110 is a transmissive electrode, a material for forming a first electrode may be selected from, e.g., indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), zinc oxide (ZnO), and a combinations thereof. In an implementation, when the first electrode 110 is a semi-transmissive electrode or a reflectable electrode, a material for forming a first electrode may be selected from, e.g., magnesium (Mg), silver (Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), and a combinations thereof.

[0166] The first electrode 110 may have a single-layered structure, or a multi-layered structure including two or more layers. In an implementation, the first electrode 110 may have a three-layered structure of, e.g., ITO/Ag/ITO.

[0167] [Organic Layer 150]

[0168] The organic layer 150 is disposed on the first electrode 110. The organic layer 150 may include an emission layer.

[0169] The organic layer 150 may further include a hole transport region between the first electrode 110 and the emission layer, and an electron transport region between the emission layer and the second electrode 190.


[0170] [Hole Transport Region in Organic Layer 150]

[0171] The hole transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0172] The hole transport region may include at least one layer selected from a hole injection layer, a hole transport layer, an emission auxiliary layer, and an electron blocking layer.


[0173] In an implementation, the hole transport region may have a single-layered structure including a single layer including a plurality of different materials, or a multi-layered structure having a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/emission auxiliary layer structure, wherein for each structure, constituting layers are sequentially stacked from the first electrode 110 in this stated order.

[0174] The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB (NPB), β -NPB, TPD, Spiro-TPD, Spiro-NPB, methylated-NPB, TAPC, HMTPD, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), TCTA, CzSi, a compound represented by Formula 201, and a compound represented by Formula 202:




m-MTDATA


-continued



TDATA





2-TNATA




NPB


-continued

 β -NPB


TPD



Spiro-TPD




Spiro-NPB




methylated NPB


-continued




TAPC




HMTPD




TCTA



<Formula 201>



<Formula 202>

**[0175]** In Formulae 201 and 202,**[0176]** L_{201} to L_{204} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,**[0177]** L_{205} may be selected from $^* \text{---} \text{O} \text{---} ^*$, $^* \text{---} \text{S} \text{---} ^*$, $^* \text{---} \text{N} (\text{Q}_{201}) \text{---} ^*$, a substituted or unsubstituted C_1 - C_{20} alkylene group, a substituted or unsubstituted C_2 - C_{20} alkenylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,**[0178]** x_{a1} to x_{a4} may each independently be an integer from 0 to 3,**[0179]** x_{a5} may be an integer from 1 to 10, and**[0180]** R_{201} to R_{204} and Q_{201} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstitutedsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.**[0181]** In one embodiment, in Formula 202, R_{201} and R_{202} may optionally be linked each other via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group, and R_{203} and R_{204} may optionally be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group.**[0182]** In one embodiment, in Formulae 201 and 202,**[0183]** L_{201} to L_{205} may each independently be selected from:**[0184]** a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, and a pyridinylene group; and**[0185]** a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, and a pyridinylene group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with $-\text{F}$, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzo-

fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, and

[0186] Q_{31} to Q_{33} may each independently be selected from a $\text{C}_1\text{-C}_{10}$ alkyl group, a $\text{C}_1\text{-C}_{10}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0187] In one or more embodiments, xa1 to xa4 may each independently be 0, 1, or 2.

[0188] In one or more embodiments, xa5 may be 1, 2, 3, or 4.

[0189] In one or more embodiments, R_{201} to R_{204} and Q_{201} may each independently be selected from:

[0190] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group; and

[0191] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a

$\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a $\text{C}_1\text{-C}_{10}$ alkyl group, a phenyl group substituted with $-\text{F}$, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, and

[0192] Q_{31} to Q_{33} may each independently be the same as described above.

[0193] In an implementation, in Formula 201, at least one selected from R_{201} to R_{203} may each independently be selected from:

[0194] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a benzothiophenyl group; and

[0195] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a benzothiophenyl group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a $\text{C}_1\text{-C}_{10}$ alkyl group, a phenyl group substituted with $-\text{F}$, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a benzothiophenyl group.

[0196] In one or more embodiments, in Formula 202, i) R_{201} and R_{202} may be linked each other via a single bond, and/or ii) R_{203} and R_{204} may be linked each other via a single bond.

[0197] In an implementation, in Formula 202, at least one selected from R_{201} to R_{204} may be selected from:


[0198] a carbazolyl group; and

[0199] a carbazolyl group substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclo-

hexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothio-phenyl group.


[0200] The compound represented by Formula 201 may be represented by Formula 201A:

<Formula 201A>




[0201] In an implementation, the compound represented by Formula 201 may be represented by Formula 201A(1).

<Formula 201A(1)>




[0202] In an implementation, the compound represented by Formula 201 may be represented by Formula 201A-1.

<Formula 201A-1>




[0203] In an implementation, the compound represented by Formula 202 may be represented by Formula 202A:

<Formula 202A>



[0204] In an implementation, the compound represented by Formula 202 may be represented by Formula 202A-1:

<Formula 202A-1>



[0205] In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1,


[0206] L₂₀₁ to L₂₀₃, xa1 to xa3, xa5, and R₂₀₂ to R₂₀₄ may each independently be the same as described above,

[0207] R₂₁₁ and R₂₁₂ are same as R₂₀₃, and


[0208] R₂₁₃ to R₂₁₇ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

[0209] In an implementation, the hole transport region may include at least one compound selected from Compounds HT1 to HT39:


HT1




HT2



HT3




HT4




-continued


H9




H10



H11





H12



-continued



H13

H14





H15

H16




H17


H18




-continued
H19




H20




H21



H22




H23




-continued


H24




H25




H26




H27




H28



H29




-continued




-continued
H36



H37



H38



H39



[0210] A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes at least one of a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of about 100 Å to about 9,000 Å, for example, about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, for example about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

[0211] The emission auxiliary layer may help increase light-emission efficiency by compensating for an optical resonance distance according to the wavelength of light emitted by an emission layer, and the electron blocking layer may block the flow of electrons from an electron transport region. The emission auxiliary layer and the electron blocking layer may include the materials as described above.

[0212] [p-Dopant]

[0213] The hole transport region may further include, in addition to these materials, a charge-generation material for

the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

[0214] The charge-generation material may be, for example, a p-dopant.

[0215] In one embodiment, the p-dopant may have a lowest unoccupied molecular orbital (LUMO) level of -3.5 eV or less.

[0216] In an implementation, the p-dopant may include at least one selected from, e.g., a quinone derivative, a metal oxide, and a cyano group-containing compound.


[0217] In an implementation, the p-dopant may include at least one selected from, e.g.,

[0218] a quinone derivative, such as tetracyanoquinodimethane (TCNQ) or 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4-TCNQ);


[0219] a metal oxide, such as tungsten oxide or molybdenum oxide;

[0220] 1,4,5,8,9,12-hexaazatriphenylene-hexacarbonitrile (HAT-CN); and


[0221] a compound represented by Formula 221.



<HAT-CN>



<F4-TCNQ>



<Formula 221>

[0222] In Formula 221,

[0223] R₂₂₁ to R₂₂₃ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and at least one selected from R₂₂₁ to R₂₂₃ may have at least one substituent selected from a cyano group, —F, —Cl, —Br, —I, a C₁-C₂₀ alkyl group substituted with —F, a C₁-C₂₀ alkyl group substituted with —Cl, a C₁-C₂₀ alkyl group substituted with —Br and a C₁-C₂₀ alkyl group substituted with —I.

[0224] [Emission Layer in Organic Layer 150]

[0225] When the organic light-emitting device 10 is a full-color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub-pixel. In an implementation, the emission layer may have a stacked structure of two or more layers selected from a red emission layer, a green emission layer, and a blue emission layer, in which the two or more layers contact each other or are separated from each other. In an implementation, the emission layer may include two or more materials selected from a red light-emitting material, a green light-emitting material, and a blue light-emitting material, in which the two or more materials are mixed with each other in a single layer to emit white light.

[0226] The emission layer may include a host and a dopant. The dopant may include the condensed cyclic compound represented by Formula 1.

[0227] In an implementation, in the emission layer, an amount of the dopant may be in a range of, e.g., about 0.01 parts by weight to about 30 parts by weight, based on 100 parts by weight of the host.

[0228] A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is satisfied within the range above, excellent emission characteristics may be exhibited without substantial increase in driving voltage.

[0229] [Host in Emission Layer]

[0230] In an implementation, the host may include a compound represented by Formula 301 below.



[0231] In Formula 301,

[0232] Ar₃₀₁ may be a substituted or unsubstituted C₅-C₆₀ carbocyclic group or a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

[0233] xb11 may be 1, 2, or 3,

[0234] L₃₀₁ may be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0235] xb1 may be an integer from 0 to 5,

[0236] R₃₀₁ may be selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₃₀₁)(Q₃₀₂)(Q₃₀₃), —N(Q₃₀₁)(Q₃₀₂), —B(Q₃₀₁)(Q₃₀₂), —C(=O)(Q₃₀₁), —S(=O)₂(Q₃₀₁), and —P(=O)(Q₃₀₁)(Q₃₀₂),

[0237] xb21 may be an integer from 1 to 5, and

[0238] Q₃₀₁ to Q₃₀₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0239] In an implementation, Ar₃₀₁ in Formula 301 may be selected from:

[0240] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthra-


cene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a plicene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group; and

[0241] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a plicene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂), and


[0242] Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0243] When xb11 in Formula 301 is two or more, two or more Ar₃₀₁(s) may be linked via a single bond.

[0244] In an implementation, the compound represented by Formula 301 may be represented by Formula 301-1 or 301-2:



<Formula 301-1>



<Formula 301-2>

[0245] In Formulae 301-1 and 301-2,

[0246] A₃₀₁ to A₃₀₄ may each independently be selected from a benzene group, a naphthalene group, a phenanthrene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a pyridine group, a pyrimidine group, an indene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, an indole group, a carbazole group, a benzocarbazole group, a dibenzocarbazole group, a furan group, a benzofuran group, a dibenzofuran group, a naphthofuran group, a benzonaphthofuran group, a dinaphthofuran group, a thiophene group,

a benzothiophene group, a dibenzothiophene group, a naphthothiophene group, a benzonaphthothiophene group, and a dinaphthothiophene group,

[0247] X₃₀₁ may be O, S, or N-[(L₃₀₄)_{xb4}-R₃₀₄],

[0248] R₃₁₁ to R₃₁₄ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

[0249] xb22 and xb23 may each independently be 0, 1, or 2,

[0250] L₃₀₁, xb1, R₃₀₁, and Q₃₁ to Q₃₃ may each independently be the same as described above,

[0251] L₃₀₂ to L₃₀₄ may each independently be the same as L₃₀₁,

[0252] xb2 to xb4 may each independently be the same as xb1, and

[0253] R₃₀₂ to R₃₀₄ may each independently be the same as R₃₀₁.

[0254] In an implementation, in Formulae 301, 301-1, and 301-2, L₃₀₁ to L₃₀₄ may each independently be selected from:

[0255] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene

group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilylylylene group, a pyridinylylene group, an imidazolylylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazolylylene group, an isoxazolylylene group, a thiadiazolylylene group, an oxadiazolylylene

group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group; and

[0256] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, a fluoranthrenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylenylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and

azolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂), and

[0257] Q₃₁ to Q₃₃ may each independently be the same as described above.

[0258] In one embodiment, in Formulae 301, 301-1, and 301-2, R₃₀₁ to R₃₀₄ may each independently be selected from:

[0259] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and


[0260] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a

C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂), and


[0261] Q₃₁ to Q₃₃ may each independently be the same as described above.

[0262] In an implementation, the host may include an alkaline earth metal complex. For example, the host may be selected from a Be complex (for example, Compound H55), a Mg complex, and a Zn complex.


[0263] In an implementation, the host may include at least one selected from 9,10-di(2-naphthyl)anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl)anthracene (MADN), 9,10-di-(2-naphthyl)-2-t-butyl-anthracene (TBADN), 4,4'-bis(N-carbazolyl)-1,1'-biphenyl (CBP), 1,3-di-9-carbazolyl-benzene (mCP), 1,3,5-tri(carbazol-9-yl)benzene (TCP), bis(4-(9H-carbazol-9-yl)phenyl)diphenylsilane (BCPDS), 4-(1-(4-(diphenylamino)phenyl)cyclohexyl)phenyl)diphenyl-phosphine oxide (POPCPA), DPEPO, and Compounds H1 to H55:




-continued




H1




H2




H3




H4




H5




-continued




H6




H7




H8



H9




H10




H11


-continued




H12




H13



H14




H15




H16

-continued


H17




H18




H19



H20




H21




-continued


H22




H23



H24




-continued




H30


-continued




H35




H31




H36




H32




H37



H33




H34




H38

-continued




H39

-continued





H41

H42




H40


H43




-continued




H44



H45




H46




H47


-continued




H48




H49




H50



H51




H52




H53

-continued



H54



H55

[0264] The host may only include at least one compound, or at least two different compounds, in various manners.

[0265] [Dopant Included in Emission Layer in Organic Layer 150]

[0266] The dopant may include a compound represented by Formula 1: The emission layer is the same as described above.

[0267] [Electron Transport Region in Organic Layer 150]

[0268] The electron transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0269] In an implementation, the electron transport region may include at least one selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, and an electron injection layer.

[0270] In an implementation, the electron transport region may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron transport layer/electron injection layer structure, or a buffer layer/electron transport layer/electron injection layer structure, wherein for each structure, constituting layers are sequentially stacked from an emission layer.

[0271] The electron transport region (for example, a buffer layer, a hole blocking layer, an electron control layer, or an electron transport layer in the electron transport region) may include a metal-free compound containing at least one π electron-depleted nitrogen-containing ring.

[0272] The “ π electron-depleted nitrogen-containing ring” indicates a C_1 - C_{60} heterocyclic group having at least one $*-N=*$ moiety as a ring-forming moiety.

[0273] For example, the “it electron-depleted nitrogen-containing ring” may be i) a 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety, ii) a heteropolycyclic group in which two or more 5-membered to 7-membered heteromonocyclic groups each having at least one $*-N=*$ moiety are condensed with each other, or iii) a heteropolycyclic group in which at least one of 5-membered to 7-membered heteromonocyclic groups, each having at least one $*-N=*$ moiety, is condensed with at least one C_5 - C_{60} carbocyclic group.

[0274] Examples of the π electron-depleted nitrogen-containing ring include an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isoxazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, an indazole, a purine, a quino- line, an isoquinoline, a benzoquinoline, a phthalazine, a naphthyridine, a quinoxaline, a quinazoline, a cinnoline, a phenanthridine, an acridine, a phenanthroline, a phenazine, a benzimidazole, an isobenzothiazole, a benzoxazole, an isobenzoxazole, a triazole, a tetrazole, an oxadiazole, a triazine, thiadiazol, an imidazopyridine, an imidazopyrimi- dine, and an azacarbazole.

[0275] For example, the electron transport region may include a compound represented by Formula 601:



[0276] In Formula 601,

[0277] Ar_{601} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

[0278] $xe11$ may be 1, 2, or 3,

[0279] L_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0280] $xe1$ may be an integer from 0 to 5,

[0281] R_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted mono- valent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(Q_{601})(Q_{602})(Q_{603})$, $-\text{C}(=\text{O})(Q_{601})$, $-\text{S}(=\text{O})_2(Q_{601})$, and $-\text{P}(=\text{O})(Q_{601})(Q_{602})$,

[0282] Q_{601} to Q_{603} may each independently be a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group, and

[0283] $xe21$ may be an integer from 1 to 5.

[0284] In one embodiment, at least one of $Ar_{601}(s)$ in the number of $xe11$ and/or at least one of $R_{601}(s)$ in the number of $xe21$ may include the t electron-depleted nitrogen-containing ring.

[0285] In one embodiment, ring Ar_{601} in Formula 601 may be selected from:

[0286] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group; and

[0287] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, $-Si(Q_{31})(Q_{32})(Q_{33})$, $-S(=O)_2(Q_{31})$, and $-P(=O)(Q_{31})(Q_{32})$, and


[0288] Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0289] When $xe11$ in Formula 601 is two or more, two or more $Ar_{601}(s)$ may be linked via a single bond.

[0290] In one or more embodiments, Ar_{601} in Formula 601 may be an anthracene group.

[0291] In one or more embodiments, a compound represented by Formula 601 may be represented by Formula 601-1:

<Formula 601-1>



[0292] In Formula 601-1,

[0293] X_{614} may be N or C(R_{614}), X_{615} may be N or C(R_{615}), X_{616} may be N or C(R_{616}), and at least one selected from X_{614} to X_{616} may be N,

[0294] L_{611} to L_{613} may each independently be the same as L_{601} ,

[0295] $xe611$ to $xe613$ may each independently be the same as $xe1$,

[0296] R_{611} to R_{613} may each independently be the same as R_{601} , and

[0297] R_{614} to R_{616} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0298] In an implementation, L_{601} and L_{611} to L_{613} in Formulae 601 and 601-1 may each independently be selected from:

[0299] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, a pyridinylylene group, an imidazolylylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazolylylene group, an isoxazolylylene group, a thiadiazolylylene group, an oxadiazolylylene group, a pyrazinylylene group, a pyrimidinylylene group, a pyridazinylylene group, a triazinyllylene group, a quinolinyllylene group, an isoquinolinyllylene group, a benzoquinolinyllylene group, a phthalazinyllylene group, a naphthyridinyllylene group, a quinoxalinyllylene group, a quinazolinyllylene group, a cinnolinyllylene group, a phenanthridinyllylene group, an acridinyllylene group, a phenanthrolinyllylene group, a phenazinyllylene group, a benzimidazolylylene group, an isobenzothiazolylylene group, a benzoxazolylylene group, an isobenzoxazolylylene group, a triazolylylene group, a tetrazolylylene group, an imidazopyridinyllylene group, an imidazopyrimidinyllylene group, and an azacarbazolylylene group; and

[0300] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylylene group, a benzofluorenylylene group, a dibenzofluorenylylene group, a phenanthre-

nylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylynylene group, a pyrenylylene group, a chrysenylylene group, a perylenylylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, a pyridinylylene group, an imidazolylylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazolylylene group, an isoxazolylylene group, a thiadiazolylylene group, an oxadiazolylylene group, a pyrazinylylene group, a pyrimidinylylene group, a pyridazinylylene group, a triazinylylene group, a quinolinylylene group, an isoquinolinylylene group, a benzoquinolinylylene group, a phthalazinylylene group, a naphthyridinylylene group, a quinoxalinylylene group, a quinazolinylylene group, a cinnolinylylene group, a phenanthridinylylene group, an acridinylylene group, a phenanthrolinylylene group, a phenazinylylene group, a benzimidazolylylene group, an isobenzothiazolylylene group, a benzoxazolylylene group, an isobenzoxazolylylene group, a triazolylylene group, a tetrazolylylene group, an imidazopyridinylylene group, an imidazopyrimidinylylene group, and an azacarbazolylylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalyl group, a quinazolyl group, a cinnolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group.

[0301] In one or more embodiments, in Formulae 601 and 601-1, xe1 and xe611 to xe613 may each independently be 0, 1, or 2.

[0302] In one or more embodiments, in Formulae 601 and 601-1, R₆₀₁ and R₆₁₁ to R₆₁₃ may each independently be selected from:

[0303] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group,

a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalyl group, a quinazolyl group, a cinnolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;




[0304] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalyl group, a quinazolyl group, a cinnolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group,

a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenaziny group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and

[0305] $-S(=O)_2(Q_{601})$ and $-P(=O)(Q_{601})(Q_{602})$, and


[0306] Q_{601} and Q_{602} may be the same as described above.

[0307] In an implementation, the electron transport region may include, e.g., at least one compound selected from Compounds ET1 to ET36:




-continued

ET6




-continued

ET9





ET7




ET10

ET8




-continued

ET11





-continued

ET14





ET12

ET15




ET13

ET16




-continued



ET17



-continued

ET20





ET18

ET21



ET19

ET22





-continued

-continued



ET23

ET26





ET24

ET27




ET25

ET28




-continued

ET29





-continued

ET32





ET30

ET33




ET31

ET34




-continued





ET35

-continued




BAlq

ET36




TAZ




NTAZ


[0308] In an implementation, the electron transport region may include at least one selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq₃, BAlq, 3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (), NTAZ, diphenyl(4-(triphenylsilyl)phenyl)-phosphine oxide (TSPO1), TPBI, and DPEPO:




TSPO1



Alq₃



TPBI




[0309] A thickness of the buffer layer, the hole blocking layer, or the electron control layer may be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer, and the electron control layer are within these ranges, the electron blocking layer may have excellent electron blocking characteristics or electron control characteristics without a substantial increase in driving voltage.

[0310] A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.

[0311] The electron transport region (for example, the electron transport layer in the electron transport region) may further include, in addition to the materials described above, a metal-containing material.

[0312] The metal-containing material may include at least one selected from an alkali metal complex and an alkaline earth metal complex. The alkali metal complex may include a metal ion selected from a Li ion, a Na ion, a K ion, a Rb ion, and a Cs ion, and the alkaline earth-metal complex may include a metal ion selected from a Be ion, a Mg ion, a Ca ion, a Sr ion, and a Ba ion. A ligand coordinated with the metal ion of the alkali metal complex or the alkaline earth-metal complex may be selected from a hydroxy quinoline, a hydroxy isoquinoline, a hydroxy benzoquinoline, a hydroxy acridine, a hydroxy phenanthridine, a hydroxy phenyloxazole, a hydroxy phenylthiazole, a hydroxy diphenyloxadiazole, a hydroxy diphenylthiadiazol, a hydroxy phenylpyridine, a hydroxy phenylbenzimidazole, a hydroxy phenylbenzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene.


[0313] For example, the metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2.



ET-D1

-continued

ET-D2



[0314] The electron transport region may include an electron injection layer that facilitates injection of electrons from the second electrode **190**. The electron injection layer may directly contact the second electrode **190**.

[0315] The electron injection layer may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0316] The electron injection layer may include an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or a combinations thereof.

[0317] The alkali metal may be selected from Li, Na, K, Rb, and Cs. In one embodiment, the alkali metal may be Li, Na, or Cs. In an implementation, the alkali metal may be Li or Cs.

[0318] The alkaline earth metal may be selected from Mg, Ca, Sr, and Ba.

[0319] The rare earth metal may be selected from Sc, Y, Ce, Tb, Yb, and Gd.

[0320] The alkali metal compound, the alkaline earth-metal compound, and the rare earth metal compound may be selected from oxides and halides (for example, fluorides, chlorides, bromides, or iodides) of the alkali metal, the alkaline earth-metal, and the rare earth metal.

[0321] The alkali metal compound may be selected from alkali metal oxides, such as Li₂O, Cs₂O, and K₂O, and alkali metal halides, such as LiF, NaF, CsF, KF, LiI, NaI, CsI, KI, and RbI. In an implementation, the alkali metal compound may be selected from LiF, Li₂O, NaF, LiI, NaI, CsI, and KI.

[0322] The alkaline earth-metal compound may be selected from alkaline earth-metal oxides, such as BaO, SrO, CaO, Ba_xSr_{1-x}O (0<x<1), Ba_xCa_{1-x}O (0<x<1). In an implementation, the alkaline earth-metal compound may be selected from BaO, SrO, and CaO.

[0323] The rare earth metal compound may be selected from YbF₃, ScF₃, ScO₃, Y₂O₃, Ce₂O₃, GdF₃, and TbF₃. In an implementation, the rare earth metal compound may be selected from YbF₃, ScF₃, TbF₃, YbI₃, ScI₃, and TbI₃.

[0324] In an implementation, the alkali metal complex, the alkaline earth-metal complex, and the rare earth metal complex may include an ion of alkali metal, alkaline earth-metal, and rare earth metal as described above, and a ligand coordinated with a metal ion of the alkali metal complex, the alkaline earth-metal complex, or the rare earth metal complex may be selected from hydroxy quinoline, hydroxy

isoquinoline, hydroxy benzoquinoline, hydroxy acridine, hydroxy phenanthridine, hydroxy phenyloxazole, hydroxy phenylthiazole, hydroxy diphenyloxadiazole, hydroxy diphenylthiadiazol, hydroxy phenylpyridine, hydroxy phenylbenzimidazole, hydroxy phenylbenzothiazole, bipyridine, phenanthroline, and cyclopentadiene.

[0325] In an implementation, the electron injection layer may consist of or include an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof, as described above. In one or more embodiments, the electron injection layer may further include an organic material. When the electron injection layer further includes an organic material, an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof may be homogeneously or non-homogeneously dispersed in a matrix including the organic material.

[0326] A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

[0327] [Second Electrode 190]

[0328] The second electrode 190 may be disposed on the organic layer 150 having such a structure. The second electrode 190 may be a cathode which is an electron injection electrode, and in this regard, a material for forming the second electrode 190 may be selected from metal, an alloy, an electrically conductive compound, and a combination thereof, which have a relatively low work function.

[0329] In an implementation, the second electrode 190 may include at least one selected from, e.g., lithium (Li), silver (Ag), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), ITO, and IZO. The second electrode 190 may be a transmissive electrode, a semi-transmissive electrode, or a reflective electrode.

[0330] The second electrode 190 may have a single-layered structure, or a multi-layered structure including two or more layers.

[0331] [Description of FIGS. 2 to 4]

[0332] An organic light-emitting device 20 of FIG. 2 includes a first capping layer 210, a first electrode 110, an organic layer 150, and a second electrode 190 which are sequentially stacked in this stated order, an organic light-emitting device 30 of FIG. 3 includes a first electrode 110, an organic layer 150, a second electrode 190, and a second capping layer 220 which are sequentially stacked in this stated order, and an organic light-emitting device 40 of FIG. 4 includes a first capping layer 210, a first electrode 110, an organic layer 150, a second electrode 190, and a second capping layer 220.

[0333] Regarding FIGS. 2 to 4, the first electrode 110, the organic layer 150, and the second electrode 190 may be understood by referring to the description presented in connection with FIG. 1.

[0334] In the organic layer 150 of each of the organic light-emitting devices 20 and 40, light generated in an emission layer may pass through the first electrode 110, which is a semi-transmissive electrode or a transmissive electrode, and the first capping layer 210 toward the outside, and in the organic layer 150 of each of the organic light-emitting devices 30 and 40, light generated in an emission layer may pass through the second electrode 190, which is a semi-transmissive electrode or a transmissive electrode, and the second capping layer 220 toward the outside.


[0335] The first capping layer 210 and the second capping layer 220 may increase external luminescent efficiency according to the principle of constructive interference.

[0336] The first capping layer 210 and the second capping layer 220 may each independently be an organic capping layer including an organic material, an inorganic capping layer including an inorganic material, or a composite capping layer including an organic material and an inorganic material.


[0337] At least one selected from the first capping layer 210 and the second capping layer 220 may each independently include at least one material selected from carbocyclic compounds, heterocyclic compounds, amine-based compounds, porphyrine derivatives, phthalocyanine derivatives, a naphthalocyanine derivatives, alkali metal complexes, and alkaline earth-based complexes. The carbocyclic compound, the heterocyclic compound, and the amine-based compound may be optionally substituted with a substituent containing at least one element selected from O, N, S, Se, Si, F, Cl, Br, and I. In one embodiment, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include an amine-based compound.

[0338] In an implementation, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include the compound represented by Formula 201 or the compound represented by Formula 202.

[0339] In an implementation, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include a compound selected from Compounds HT28 to HT33 and Compounds CP1 to CP5.



-continued



[0340] Hereinbefore, the organic light-emitting device according to an embodiment has been described in connection with FIGS. 1 to 4.

[0341] Layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region may be formed in a certain region by using one or more suitable methods selected from vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, ink-jet printing, laser-printing, and laser-induced thermal imaging.

[0342] When layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region are formed by vacuum deposition, the deposition may be performed at a deposition temperature of about 100° C. to about 500° C., a vacuum degree of about 10⁻⁸ torr to about 10⁻³ torr, and a deposition speed of about 0.01 Å/sec

to about 100 Å/sec by taking into account a material to be included in a layer to be formed, and the structure of a layer to be formed.

[0343] When layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region are formed by spin coating, the spin coating may be performed at a coating speed of about 2,000 rpm to about 5,000 rpm and at a heat treatment temperature of about 80° C. to about 200° C. by taking into account a material to be included in a layer to be formed, and the structure of a layer to be formed.

[0344] [General Definition of Substituents]

[0345] The term “C₁-C₆₀ alkyl group” as used herein refers to a linear or branched saturated aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms, and examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an isoamyl group, and a hexyl group. The term “C₁-C₆₀ alkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

[0346] The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group having at least one double bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkenylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

[0347] The term “C₂-C₆₀ alkynyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon triple bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethynyl group, and a propynyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

[0348] The term “C₁-C₆₀ alkoxy group” as used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group), and examples thereof include a methoxy group, an ethoxy group, and an isopropoxy group.

[0349] The term “C₃-C₁₀ cycloalkyl group” as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The term “C₃-C₁₀ cycloalkylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

[0350] The term “C₁-C₁₀ heterocycloalkyl group” as used herein refers to a monovalent monocyclic group having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 10 carbon atoms, and examples thereof include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuran group, and a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkyl group.

[0351] A C₃-C₁₀ cycloalkenyl group used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one double bond in the ring thereof and no aromaticity, and examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group.

The term “C₃-C₁₀ cycloalkenylene group,” used herein, refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

[0352] The term “C₁-C₁₀ heterocycloalkenyl group” as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one double bond in its ring. Examples of the C₁-C₁₀ heterocycloalkenyl group include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuranyl group, and a 2,3-dihydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkenylene group,” used herein, refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkenyl group.

[0353] The term “C₆-C₆₀ aryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C₆-C₆₀ arylene group used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Examples of the C₆-C₆₀ aryl group are a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

[0354] The term “C₁-C₆₀ heteroaryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 1 carbon atoms. The term “C₁-C₆₀ heteroarylene group” as used herein refers to a divalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. Examples of the C₁-C₆₀ heteroaryl group are a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the rings may be fused to each other.

[0355] The term “C₆-C₆₀ aryloxy group,” used herein, indicates —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and a C₆-C₆₀ arylthio group indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

[0356] The term “C₁-C₆₀ heteroaryloxy group” as used herein indicates —OA₁₀₄ (wherein A₁₀₄ is the C₁-C₆₀ heteroaryl group), and the term “C₆-C₆₀ heteroarylthio group” as used herein indicates —SA₁₀₅ (wherein A₁₀₅ is the C₁-C₆₀ heteroaryl group).

[0357] The term “monovalent non-aromatic condensed polycyclic group” as used herein refers to a monovalent group (for example, having 8 to 60 carbon atoms) having two or more rings condensed with each other, only carbon atoms as ring-forming atoms, and no aromaticity in its entire molecular structure. A detailed example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

[0358] The term “monovalent non-aromatic condensed heteropolycyclic group” as used herein refers to a monovalent group (for example, having 1 to 60 carbon atoms) having two or more rings condensed to each other, at least one heteroatom selected from N, O, Si, P, and S, other than

carbon atoms, as a ring-forming atom, and no aromaticity in its entire molecular structure. An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. The term “divalent non-aromatic condensed heteropolycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0359] The term “C₅-C₆₀ carbocyclic group” as used herein refers to a monocyclic or polycyclic group having 5 to 60 carbon atoms in which a ring-forming atom is a carbon atom only. The C₅-C₆₀ carbocyclic group may be an aromatic carbocyclic group or a non-aromatic carbocyclic group. The C₅-C₆₀ carbocyclic group may be a ring, such as benzene, a monovalent group, such as a phenyl group, or a divalent group, such as a phenylene group. In one or more embodiments, depending on the number of substituents connected to the C₅-C₆₀ carbocyclic group, the C₅-C₆₀ carbocyclic group may be a trivalent group or a quadrivalent group.

[0360] The term “C₁-C₆₀ heterocyclic group” as used herein refers to a group having the same structure as the C₅-C₆₀ carbocyclic group, except that as a ring-forming atom, at least one heteroatom selected from N, O, Si, P, and S is used in addition to carbon (the number of carbon atoms may be in a range of 1 to 60).

[0361] At least one substituent of the substituted C₅-C₆₀ carbocyclic group, the substituted C₁-C₆₀ heterocyclic group, the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted C₁-C₆₀ heteroaryloxy group, the substituted C₁-C₆₀ heteroarylthio group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0362] deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0363] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic

group, $-\text{Si}(\text{Q}_{11})(\text{Q}_{12})(\text{Q}_{13})$, $-\text{N}(\text{Q}_{11})(\text{Q}_{12})$, $-\text{B}(\text{Q}_{11})(\text{Q}_{12})$, $-\text{C}(=\text{O})(\text{Q}_{11})$, $-\text{S}(=\text{O})_2(\text{Q}_{11})$, and $-\text{P}(=\text{O})(\text{Q}_{11})(\text{Q}_{12})$;

[0364] a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a $\text{C}_1\text{-C}_{60}$ heteroaryloxy group, a $\text{C}_1\text{-C}_{60}$ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0365] a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a $\text{C}_1\text{-C}_{60}$ heteroaryloxy group, a $\text{C}_1\text{-C}_{60}$ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a $\text{C}_1\text{-C}_{60}$ heteroaryloxy group, a $\text{C}_1\text{-C}_{60}$ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{21})(\text{Q}_{22})(\text{Q}_{23})$, $-\text{N}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{B}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{C}(=\text{O})(\text{Q}_{21})$, $-\text{S}(=\text{O})_2(\text{Q}_{21})$, and $-\text{P}(=\text{O})(\text{Q}_{21})(\text{Q}_{22})$; and

[0366] $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_3)$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, and

[0367] Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a $\text{C}_1\text{-C}_{60}$ heteroaryloxy group, a $\text{C}_1\text{-C}_{60}$ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a $\text{C}_1\text{-C}_{60}$ alkyl group substituted with at least one selected from deuterium, $-\text{F}$, and a cyano group, a $\text{C}_6\text{-C}_{60}$ aryl group substituted with at least one selected from deuterium, $-\text{F}$, and a cyano group, a biphenyl group, and a terphenyl group.

[0368] The term “Ph” used herein refers to a phenyl group, the term “Me” used herein refers to a methyl group, the term “Et” used herein refers to an ethyl group, the term “ter-Bu” or “But” used herein refers to a tert-butyl group, and the term “OMe” used herein refers to a methoxy group.

[0369] The term “biphenyl group” as used herein refers to “a phenyl group substituted with a phenyl group.” In other words, the “biphenyl group” is a substituted phenyl group having a $\text{C}_6\text{-C}_{60}$ aryl group as a substituent.

[0370] The term “terphenyl group” as used herein refers to “a phenyl group substituted with a biphenyl group.” In other

words, the “terphenyl group” is a phenyl group having, as a substituent, a $\text{C}_6\text{-C}_{60}$ aryl group substituted with a $\text{C}_6\text{-C}_{60}$ aryl group.

[0371] * and *' used herein, unless defined otherwise, each refer to a binding site to a neighboring atom in a corresponding formula.


[0372] Hereinafter, a compound according to embodiments and an organic light-emitting device according to embodiments will be described in detail with reference to Synthesis Examples and Examples. The wording “B was used instead of A” used in describing Synthesis Examples refers to that an identical molar equivalent of B was used in place of A.

[0373] The following Examples and Comparative Examples are provided in order to highlight characteristics of one or more embodiments, but it will be understood that the Examples and Comparative Examples are not to be construed as limiting the scope of the embodiments, nor are the Comparative Examples to be construed as being outside the scope of the embodiments. Further, it will be understood that the embodiments are not limited to the particular details described in the Examples and Comparative Examples.


EXAMPLES

Synthesis Example 1: Synthesis of Compound 13

[0374]



-continued

**[0375]** (1) Synthesis of Intermediate 13-1

[0376] 1-bromo-4-fluoro-9H-carbazole (1 eq), 1-bromo-2-fluorobenzene (2 eq), and K_3PO_4 (2 eq) were added to dimethylformamide and stirred at a temperature of 160° C. for 12 hours. The reaction mixture was cooled to ambient temperature and poured into NaCl aqueous solution. After the reaction was completed, the reaction product was stirred for 30 minutes. A solid obtained by filtering the generated precipitate was extracted therefrom by using distilled water and dichloromethane. Then, an organic layer obtained therefrom was dried by using $MgSO_4$ and dried under reduced pressure. A crude product obtained therefrom was purified by column chromatography (dichloromethane/hexane) to obtain Intermediate 13-1 (yield: 75%).


[0377] (2) Synthesis of Intermediate 13-2

[0378] Intermediate 13-2 (yield: 70%) was synthesized in the same manner as in Synthesis of Intermediate 13-1, except that Intermediate 13-1 (1 eq) and 2,7-diphenyl-9H-carbazole (1 eq) were used instead of 1-bromo-4-fluoro-9H-carbazole (1 eq) and 1-bromo-2-fluorobenzene (2 eq).

[0379] (3) Synthesis of Compound 13

[0380] Intermediate 13-2 (1 eq) and tetrahydrofuran were added to a reaction container and cooled to a temperature of -76° C., and n-BuLi (2.2 eq) was slowly added thereto. The reaction mixture was stirred at a low temperature for 2 hours, and a solution in which dichloro(p-tolyl)borane (1.3 eq) was diluted in tetrahydrofuran was added to the reaction container. The reaction mixture was stirred at ambient temperature for 24 hours and poured into NaCl aqueous solution. After the reaction was completed, an organic layer was extracted therefrom three times by using distilled water and ethyl acetate. Then, the organic layer collected therefrom was dried by using $MgSO_4$ and dried under reduced pressure. A crude product obtained therefrom was purified by column chromatography (dichloromethane/hexane) to obtain Compound 13 (yield: 55%).

Synthesis Example 2: Synthesis of Compound 18

[0381]**[0382]** (1) Synthesis of Intermediate 18-1

[0383] 3,3'''-dibromo-2,2'''-dinitro-1,1':2',1'':2'',1'''-quar-terphenyl (1 eq) and triphenylphosphine (3 eq) were added to 1,2-dichlorobenzene and stirred at a temperature of 200° C. for 36 hours. The reaction solution was cooled and dried by a rotary evaporator. An organic layer was extracted therefrom by using distilled water and dichloromethane, dried by using $MgSO_4$, and dried under reduced pressure.

The obtained organic layer was washed by using diethyl ether and washed by using acetone to obtain Intermediate 18-1 (yield: 43%).

[0384] (2) Synthesis of Intermediate 18-2


[0385] Intermediate 18-2 (yield: 55%) was synthesized in the same manner as in Synthesis of Intermediate 13-1, except that Intermediate 18-1 (1 eq) and 1-bromo-2-fluorobenzene (5 eq) were used instead of 1-bromo-4-fluoro-9H-carbazole (1 eq) and 1-bromo-2-fluorobenzene (2 eq).

[0386] (3) Synthesis of Compound 18

[0387] Compound 18 (yield: 23%) was synthesized in the same manner as in Synthesis of Compound 13, except that Intermediate 18-2 (1 eq), n-BuLi (5 eq), and dichloro(mesityl)borane (2.5 eq) were used instead of Intermediate 13-2 (1 eq), n-BuLi (2.2 eq), and dichloro(p-tolyl)borane (1.3 eq).

Synthesis Example 3: Synthesis of Compound 20

[0388]



[0389] (1) Synthesis of Intermediate 20-1

[0390] Intermediate 20-1 (yield: 65%) was synthesized in the same manner as in Synthesis of Intermediate 13-1, except that 1-bromo-9H-carbazole (1 eq) and 1-bromo-2-fluorobenzene (2 eq) were used instead of 1-bromo-4-fluoro-9H-carbazole (1 eq) and 1-bromo-2-fluorobenzene (2 eq).


[0391] (2) Synthesis of Compound 20

[0392] Compound 20 (yield: 30%) was synthesized in the same manner as in Synthesis of Compound 13, except that Intermediate 20-1 (1 eq), n-BuLi (2.2 eq), and (2,4,6-trimethyl-1,3-phenylene)bis(dichloroborane) (0.45 eq) were

used instead of Intermediate 13-2 (1 eq), n-BuLi (2.2 eq), and dichloro(p-tolyl)borane (1.3 eq).

Synthesis Example 4: Synthesis of Compound 43

[0393]



[0394] (1) Synthesis of Intermediate 43-1

[0395] Intermediate 43-1 (yield: 70%) was synthesized in the same manner as in Synthesis of Intermediate 13-1,


except that 1-bromo-3,6-di-tert-butyl-9H-carbazole (1 eq) and 9-(2-bromo-3-fluorophenyl)-3,6-di-tert-butyl-9H-carbazole (1 eq) were used instead of 1-bromo-4-fluoro-9H-carbazole (1 eq) and 1-bromo-2-fluorobenzene (2 eq).

[0396] (2) Synthesis of Compound 43

[0397] Compound 43 (yield: 60%) was synthesized in the same manner as in Synthesis of Compound 13, except that Intermediate 43-1 (1 eq) and dichloro(phenyl)borane (1.3 eq) were used instead of Intermediate 13-2 (1 eq) and dichloro(p-tolyl)borane (1.3 eq).

Synthesis Example 5: Synthesis of Compound 67

[0398]



[0399] (1) Synthesis of Intermediate 67-1

[0400] Intermediate 67-1 (yield: 64%) was synthesized in the same manner as in Synthesis of Intermediate 13-1, except that 9-(2-bromo-3-fluorophenyl)-9H-carbazole (1 eq) and 3-(9H-carbazole-9-yl)phenol (1 eq) were used instead of 1-bromo-4-fluoro-9H-carbazole (1 eq) and 1-bromo-2-fluorobenzene (2 eq).


[0401] (2) Synthesis of Compound 67

[0402] Intermediate 67-1 was dissolved in o-xylene, cooled to a temperature of -20°C ., and stirred. n-BuLi (1.2 eq) was added thereto, and the reaction mixture was heated to a temperature of 70°C ., and stirred for 2 hours. The reaction container was cooled again to a temperature of -30°C ., and BBr_3 (1.3 eq) was slowly added thereto and stirred

at ambient temperature for 1 hour. After the reaction container is cooled to a temperature of 0°C ., triethylamine (1.5 eq) was added thereto, heated to a temperature of 120°C ., and stirred for 5 hours. After cooling, the reaction was completed by pouring sodium acetate aqueous solution, and the reaction solution was removed at a rotary evaporator by drying under reduced pressure. The product obtained therefrom was washed by using diethyl ether and washed and filtered by using acetone to obtain Compound 67 (yield: 24%).

Synthesis Example 6: Synthesis of Compound 69

[0403]



[0404] (1) Synthesis of Intermediate 69-1


[0405] Intermediate 69-1 (yield: 50%) was synthesized in the same manner as in Synthesis of Intermediate 13-1, except that 9-(2-bromo-3-fluorophenyl)-9H-carbazole (1 eq) and 3-(dibenzo[b,d]furan-4-yl)phenol (1 eq) were used instead of 1-bromo-4-fluoro-9H-carbazole (1 eq) and 1-bromo-2-fluorobenzene (2 eq).

[0406] (2) Synthesis of Compound 69

[0407] Compound 69 (yield: 18%) was synthesized in the same manner as in Synthesis of Compound 67, except that Intermediate 69-1 was used instead of Intermediate 67-1.

Synthesis Example 7: Synthesis of Compound 81

[0408]



[0409] (1) Synthesis of Intermediate 81-1


[0410] Intermediate 81-1 (yield: 68%) was synthesized in the same manner as in Synthesis of Intermediate 13-1, except that 9-(2-bromo-3-fluorophenyl)-9H-carbazole (1 eq) and 3-(9,9'-spiro[fluorene]-4-yl) (1 eq) were used instead of 1-bromo-4-fluoro-9H-carbazole (1 eq) and 1-bromo-2-fluorobenzene (2 eq).

[0411] (2) Synthesis of Compound 81

[0412] Compound 81 (yield: 14%) was synthesized in the same manner as in Synthesis of Compound 67, except that Intermediate 81-1 was used instead of Intermediate 67-1.

Synthesis Example 8: Synthesis of Compound 85

[0413]



[0414] (1) Synthesis of Intermediate 85-1

[0415] Intermediate 85-1 (yield: 40%) was synthesized in the same manner as in Synthesis of Intermediate 13-1, except that 2-bromo-3-(9H-carbazole-9-yl)-5-iodophenol (1 eq) and fluorobenzene (2 eq) were used instead of 1-bromo-4-fluoro-9H-carbazole (1 eq) and 1-bromo-2-fluorobenzene (2 eq).

[0416] (2) Synthesis of Intermediate 85-2



[0417] Intermediate 85-1 (1 eq), carbazole (1 eq), CuI (0.05 eq), 1,10-phenanthroline (0.05 eq), and K_2CO_3 (3 eq) were added to dimethylformamide and stirred at a temperature of 170° C. for 24 hours. After cooling, the reaction solvent was dried by a rotary evaporator, and an organic layer was extracted therefrom by using dichloromethane and distilled water. The organic layer collected therefrom was dried by using $MgSO_4$, washed by using diethyl ether, and washed and filtered by using acetone to synthesize Intermediate 85-2 (yield: 55%).

[0418] (3) Synthesis of Compound 85


[0419] Compound 85 (yield: 31%) was synthesized in the same manner as in Synthesis of Compound 67, except that Intermediate 85-2 was used instead of Intermediate 67-1.

Synthesis Example 9: Compound 86

[0420]



-continued



[0421] (1) Synthesis of Intermediate 86-1

[0422] Aniline (1 eq), Intermediate 85-1 (2 eq), $Pd_2(dba)_3$ (0.05 eq), tert-butyl phosphine (0.1 eq), and sodium tert-butoxide (3 eq) were added to toluene and stirred at a temperature of 100° C. for 6 hours. After cooling, the reaction solvent was dried by a rotary evaporator, and an organic layer was extracted therefrom by dichloromethane and distilled water. The obtained organic layer was dried by using $MgSO_4$ and washed and filtered by using acetone to synthesize Intermediate 86-1 (yield: 40%).

[0423] (2) Synthesis of Compound 86

[0424] Compound 86 (yield: 20%) was synthesized in the same manner as in Synthesis of Compound 67, except that Intermediate 86-1 was used instead of Intermediate 67-1.

[0425] 1H NMR and MS/FAB of Compounds synthesized according to Synthesis Examples 1 to 9 are shown in Table 1.

[0426] Methods of synthesizing compounds other than Compounds shown in Table 1 are understood by referring to the synthesis paths and source materials described above.

TABLE 1

Compound	1H NMR ($CDCl_3$, 400 MHz)	MS/FAB	
		Calcd.	Found
13	8.63-8.53 (4H, m), 8.39-8.33 (2H, m), 8.25-8.20 (2H, m), 7.99-7.73 (10H, m), 7.69-7.44 (10H, m), 6.88-6.80 (2H, m), 2.33-2.30 (3H, s)	660.61	660.60
18	8.72-8.65 (2H, m), 8.40-8.30 (6H, m), 8.03-7.80 (6H, m), 7.60-7.50 (6H, m), 6.81-6.70 (4H, m), 2.34-2.29 (18H, m), 8.20-8.09 (4H, m), 7.98-7.92 (2H, m), 7.69-7.35 (16H, m), 6.84-6.79 (1H, s), 2.36-2.28 (9H, m)	740.55	740.53
20	7.91-7.80 (7H, m), 7.73-7.69 (1H, m), 7.66-7.55 (4H, m), 7.40-7.19 (7H, m), 1.75-1.40 (36H, m)	622.37	622.35
43	7.91-7.80 (7H, m), 7.73-7.69 (1H, m), 7.66-7.55 (4H, m), 7.40-7.19 (7H, m), 1.75-1.40 (36H, m)	718.82	718.80

TABLE 1-continued

Compound	¹ H NMR (CDCl ₃ , 400 MHz)	MS/FAB	
		Calcd.	Found
67	8.20-8.10 (2H, m), 8.00-7.94 (3H, m), 7.79-7.70 (2H, m) 7.63-7.41 (10H, m), 7.33-7.28 (1H, m), 7.10-7.01 (1H, m) 6.59-6.45 (2H, m)	508.38	508.36
69	8.26-8.00 (7H, m), 7.81-7.75 (1H, m), 7.76-7.30 (10H, m), 7.04-6.99 (1H, m), 6.33-6.27 (1H, m)	509.36	509.34
81	8.16-8.03 (3H, m), 7.94-7.32 (23H, m), 7.18-7.12 (1H, m) 6.32-6.25 (1H, m)	657.56	657.54
85	8.27-7.93 (8H, m) 7.62-7.42 (10H, m) 7.27-7.13 (2H, m) 6.82-6.78 (1H, m)	508.38	508.37
86	8.16-8.05 (2H, m), 8.01-7.91 (4H, m), 7.64-7.30 (13H, m) 7.25-6.95 (10H, m)	775.46	775.44

Example 1

[0427] As an anode electrode, a Corning 15 Ω/cm² (1,200 Å) ITO glass substrate was cut to a size of 50 mm×50 mm×0.7 mm, sonicated with isopropyl alcohol and pure water each for 5 minutes, and then cleaned by exposure to ultraviolet rays and ozone for 30 minutes. Then, the ITO glass substrate was provided to a vacuum deposition apparatus.

[0428] NPD was vacuum-deposited on the ITO glass substrate to form a hole injection layer having a thickness of 300 Å, and TCTA was vacuum-deposited to form a first hole transport layer having a thickness of 200 Å. CzSi was vacuum-deposited on the first hole transport layer to form a second hole transport layer having a thickness of 100 Å. DPEPO (host) and Compound 4 (dopant) were co-deposited on the second hole transport layer at a weight ratio of 90:10 to form an emission layer having a thickness of 200 Å.

[0429] Then, DPEPO was vacuum-deposited on the emission layer to form a first electron transport layer having a thickness of 200 Å, and TPBI was vacuum-deposited on the first electron transport layer to form a second electron

transport layer having a thickness of 300 Å. LiF was vacuum-deposited on the second electron transport layer to form an electron injection layer having a thickness of 10 Å, and Al was vacuum-deposited to form a cathode electrode having a thickness of 3,000 Å, thereby completing the manufacture of an organic light-emitting device.

Examples 2 to 9 and Comparative Examples 1 to 4

[0430] Organic light-emitting devices were manufactured in the same manner as in Example 1, except that Compounds shown in Table 2 were each used as a dopant instead of Compound 4.

Evaluation Example 1


[0431] The driving voltage, current density, maximum external quantum efficiency, and emission color of the organic light-emitting devices manufactured according to Examples 1 to 9 and Comparative Examples 1 to 4 were measured by using Keithley SMU 236 and a luminance meter PR650, and results thereof are shown in Table 2.

TABLE 2


	Dopant	Driving voltage (V)	Current efficiency (cd/A)	Maximum external quantum efficiency (%)	Emission color
Example 1	Compound 13	4.8	22.1	21	Blue
Example 2	Compound 18	4.9	24.1	22.3	Blue
Example 3	Compound 20	4.7	23.5	21.1	Blue
Example 4	Compound 43	4.6	24.4	22.3	Blue
Example 5	Compound 67	4.7	23.5	21.9	Blue
Example 6	Compound 69	4.9	24.4	23	Blue
Example 7	Compound 81	5.0	23.8	22.7	Blue
Example 8	Compound 85	4.9	24.7	21.3	Blue
Example 9	Compound 86	5.1	23.3	22.4	Blue
Comparative Example 1	Compound A	6.7	19.3	18.5	Blue
Comparative Example 2	Compound B	7.1	4.2	3.9	Blue

TABLE 2-continued


	Dopant	Driving voltage (V)	Current efficiency (cd/A)	Maximum external quantum efficiency (%)	Emission color
Comparative Example 3	Compound C	8.5	18.4	14	Deep blue (short wavelength)
Comparative Example 4	Compound D	5.3	20.8	19	Blue



13




18




20

TABLE 2-continued


Dopant	Driving voltage (V)	Current efficiency (cd/A)	Maximum external quantum efficiency (%)	Emission color
--------	---------------------	---------------------------	---	----------------




43



67



69



81

TABLE 2-continued

Dopant	Driving voltage (V)	Current efficiency (cd/A)	Maximum external quantum efficiency (%)	Emission color
--------	---------------------	---------------------------	---	----------------









TABLE 2-continued

Dopant	Driving voltage (V)	Current efficiency (cd/A)	Maximum external quantum efficiency (%)	Emission color
				
				

[0432] Referring to Table 2, it may be seen that the organic light-emitting devices of Examples 1 to 9 emitted blue light having a maximum emission wavelength of e.g., 440 nm to 480 nm and had a low driving voltage, high current efficiency, and high maximum external quantum efficiency, as compared with those of the organic light-emitting devices of Comparative Examples 1 to 4.


[0433] The organic light-emitting device including the condensed cyclic compound according to an embodiment may have high quantum efficiency and may improve roll-off characteristics at a high current density.

[0434] Example embodiments have been disclosed herein, and although specific terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. In some instances, as would be apparent to one of ordinary skill in the art as of the filing of the present application, features, characteristics, and/or elements described in connection with a particular embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise specifically indicated. Accordingly, it will be understood by those of skill in the art that various changes in form and details may be made without departing from the spirit and scope of the present invention as set forth in the following claims.

What is claimed is:


1. A condensed cyclic compound represented by Formula 1:

<Formula 1>



wherein, in Formula 1, R₁₁ to R₁₄ are each independently selected from a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —B(Q₁)(Q₂), —N(Q₁)(Q₂), —P(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂),

<Formula 2>



wherein, in Formulae 1 and 2,

A₁₁ to A₁₄ and A₂₁ to A₂₄ are each independently selected from a C₅-C₆₀ carbocyclic group and a C₁-C₆₀ heterocyclic group, in which A₁₁ to A₁₄ are separate or are linked via a first linking group and A₂₁ to A₂₄ are separate or are linked via a second linking group,

n11 and n21 are each independently 0 or 1,

L₁₁ to L₁₄ and L₂₁ to L₂₄ are each independently selected from a single bond, *—N(R_a)—*, a substituted or unsubstituted C₅-C₆₀ carbocyclic group, and a substituted or unsubstituted C₁-C₆₀ heterocyclic group, in which * and *' indicate a binding site to a neighboring atom,

a11 to a14 and a21 to a24 are each independently selected from 0, 1, 2, and 3,

R_a and R₂₁ to R₂₄ are each independently selected from a binding site, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —B(Q₁)(Q₂), —N(Q₁)(Q₂), —P(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂), provided that one of R₂₁ to R₂₄ is the binding site,

b11 to b14 and b21 to b24 are each independently selected from 1, 2, 3, 4, 5, and 6,

c11 to c14 and c21 to c24 are each independently selected from 1, 2, 3, 4, 5, and 6, and

Q₁ to Q₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C₁-C₆₀ alkyl group substituted with at least one selected from deuterium, —F, and a cyano group, a C₆-C₆₀ aryl group substituted with at least one selected from deuterium, —F, and a cyano group, a biphenyl group, and a terphenyl group.

2. The condensed cyclic compound as claimed in claim 1, wherein A₁₁ to A₁₄ and A₂₁ to A₂₄ are each independently selected from a benzene group, a naphthalene group, a

fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a perylene group, a thiophene group, a furan group, a silole group, a carbazole group, an indole group, an isoindole group, a benzofuran group, a benzothiophene group, a benzosilole group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, a dibenzocarbazole group, and a dibenzosilole group.

3. The condensed cyclic compound as claimed in claim 1, wherein A₁₁ to A₁₄ and A₂₁ to A₂₄ are each independently selected from a benzene group, a naphthalene group, a fluorene group, a phenanthrene group, an anthracene group, a triphenylene group, a pyrene group, a chrysene group, a perylene group, a carbazole group, a dibenzofuran group, and a dibenzothiophene group.

4. The condensed cyclic compound as claimed in claim 1, wherein:

A₁₃ and A₁₄ and/or A₁₁ and A₁₄ are separate or are linked via a first linking group, and

A₂₃ and A₂₄ and/or A₂₁ and A₂₄ are separate or are linked via a second linking group.

5. The condensed cyclic compound as claimed in claim 1, wherein:

two of A₁₁ to A₁₄ are linked via the first linking group or two of A₂₁ to A₂₄ are linked via the second linking group, and

the first linking group and the second linking group are each independently selected from a single bond, *—O—*, and *—S—*.

6. The condensed cyclic compound as claimed in claim 1, wherein:

L₁₁ to L₁₄ and L₂₁ to L₂₄ are each independently selected from:

a single bond, *—N(R_a)—*, a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a perylene group, a thiophene group, a furan group, a silole group, a carbazole group, an indole group, an isoindole group, a benzofuran group, a benzothiophene group, a benzosilole group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, a dibenzocarbazole group, and a dibenzosilole group; and

a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a perylene group, a thiophene group, a furan group, a silole group, a carbazole group, an indole group, an isoindole group, a benzofuran group, a benzothiophene group, a benzosilole group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, a dibenzocarbazole group, and a dibenzosilole group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl

group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a thiophenyl group, a furanyl group, a silolyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, and $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, and Q_{31} to Q_{33} are each independently selected from a C_1 - C_{60} alkyl group, a phenyl group, a biphenyl group, and a terphenyl group.

7. The condensed cyclic compound as claimed in claim 1, wherein a11 to a14 and a21 to a24 are each independently 0 or 1.

8. The condensed cyclic compound as claimed in claim 1, wherein:

R_{11} to R_{14} are each independently selected from:

a group represented by Formula 2, hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a cyano group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a cyano group, a phenyl group, and a biphenyl group;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiophenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafuorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a cyano group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a

idinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafuorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiophenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafuorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a cyano group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a

pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiophenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafuorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, an indolocarbazolyl group, —Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂); and

—Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂), and

Q₁ to Q₃ and Q₃₁ to Q₃₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

9. The condensed cyclic compound as claimed in claim 1, wherein:


R₁₁ to R₁₄ are each independently selected from:

a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, and a C₁-C₂₀ alkyl group;


a C₁-C₂₀ alkyl group substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, and a cyano group;

a group represented by one of Formulae 5-1 to 5-142; and


—Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂),




5-1




5-2




5-3




5-4




5-5



5-6












5-7




5-8

-continued




-continued

5-9




5-18

5-10




5-19

5-11




5-20

5-12




5-21

5-13




5-22

5-14




5-23

5-15




5-24

5-16




5-25

5-17




5-26




5-27


-continued




5-28




5-29




5-30




5-31




5-32




5-33




5-34




5-35




5-36




5-37



5-38




5-39




5-40


-continued




5-41




5-42




5-43




5-44




5-45




5-46




5-47




5-48




5-49



5-50




5-51




5-52


-continued




5-53




5-54




5-55




5-56




5-57




5-58




5-59



5-60




5-61




5-62


-continued




5-63




5-64




5-65




5-66




5-67




5-68




5-69




5-70



5-71




5-72




5-73


-continued




5-74




5-75




5-76




5-77




5-78




5-79




5-80



5-81




5-82




5-83


-continued




5-84




5-85




5-86




5-87




5-88




5-89




5-90




5-91



5-92













5-93




5-94

-continued




-continued

5-95




5-105

5-96




5-106

5-97



5-107


5-98



5-108

5-99


5-100



5-109


5-101

5-102




5-110

5-103




5-111

5-104




5-112


-continued




5-113




5-114




5-115




5-116




5-117



5-118




5-119




5-120


-continued




5-121




5-122




5-123




5-124




5-125



5-126












5-127



5-128

-continued



5-129

5-130

5-131

5-132

5-133






5-134

5-135

5-136

5-137

-continued



5-138

5-139

5-140

5-141

5-142

wherein, in Formulae 5-1 to 5-142,

X_{51} is selected from O, S, $N(R_{51})$, and $C(R_{51})(R_{60})$,
 X_{52} is N or $C(R_{52})$, X_{53} is N or $C(R_{53})$, X_{54} is N or $C(R_{54})$,
 X_{55} is N or $C(R_{55})$, X_{56} is N or $C(R_{56})$, X_{57} is N or
 $C(R_{57})$, X_{58} is N or $C(R_{58})$, and X_{59} is N or $C(R_{59})$,
 R_{51} to R_{60} are each independently selected from hydro-
gen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group,
a cyano group, a nitro group, an amidino group, a

hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a thiophenyl group, a furanyl group, a silolyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiofenyl group, a benzosilolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)(Q₃₁), —S(=O)₂(Q₃₁), —P(=O)(Q₃₁)(Q₃₂), and —P(=S)(Q₃₁)(Q₃₂).

Q₁ to Q₃ and Q₃₁ to Q₃₃ are each independently selected from a C₁-C₆₀ alkyl group, a phenyl group, a biphenyl group, and a terphenyl group,

b51 is selected from 1, 2, 3, 4, and 5,

b52 is selected from 1, 2, 3, 4, 5, 6, and 7,

b53 is selected from 1, 2, 3, 4, 5, 6, 7, 8, and 9,

b54 is selected from 1, 2, 3, and 4,

b55 is selected from 1, 2, and 3,

b56 is selected from 1 and 2,

b57 is selected from 1, 2, 3, 4, 5, and 6, and

indicates a binding site to a neighboring atom.

10. The condensed cyclic compound as claimed in claim 1, wherein:

R_a and R₂₁ to R₂₄ are each independently selected from: a binding site, hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a phenyl group, and a biphenyl group;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiofenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzosilolyl group, a naphthobenzothiofenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiofenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzoxazolopyridinyl group, an azafuorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiofenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclo-

group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzosilolyl group, a naphthobenzothiofenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiofenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzoxazolopyridinyl group, an azafuorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiofenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiofenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzosilolyl group, a naphthobenzothiofenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiofenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzoxazolopyridinyl group, an azafuorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiofenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, and an indolocarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a cyano group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclo-

pentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentacenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, an isoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a benzoquinoxalinyl group, a quinazolinyl group, a benzoquinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a benzothiazolyl group, a benzoisothiazolyl group, a benzoxazolyl group, a benzoisoxazolyl group, a triazolyl group, a tetrazolyl group, a thiadiazolyl group, an oxadiazolyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a naphthobenzofuranyl group, a naphthobenzosilolyl group, a naphthobenzothiophenyl group, a naphthobenzosilolyl group, a dibenzocarbazolyl group, a dinaphthofuranyl group, a dinaphthothiophenyl group, a dinaphthosilolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an oxazolopyridinyl group, a thiazolopyridinyl group, a benzonaphthyridinyl group, an azafluorenyl group, an azaspiro-bifluorenyl group, an azacarbazolyl group, an azadibenzofuranyl group, an azadibenzothiophenyl group, an azadibenzosilolyl group, an indenopyrrolyl group, an indolopyrrolyl group, an indenocarbazolyl group, an indolocarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)(Q₃₁), —S(=O)₂(Q₃₁), —P(=O)(Q₃₁)(Q₃₂), and —P(=S)(Q₃₁)(Q₃₂); and

—Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂), and

Q₁ to Q₃ and Q₃₁ to Q₃₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.


11. The condensed cyclic compound as claimed in claim 1, wherein:

R_a and R₂₁ to R₂₄ are each independently selected from: a binding site, hydrogen, deuterium, —F, —Cl, —Br, —I, a cyano group, and a C₁-C₂₀ alkyl group;


a C₁-C₂₀ alkyl group substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, and a cyano group;

a group represented by one of Formulae 5-1 to 5-142; and


—Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂);




5-1




5-2




5-3




5-4



5-5












5-6




5-7

-continued




-continued

5-8




5-17

5-9




5-18

5-10




5-19

5-11




5-20

5-12




5-21

5-13




5-22

5-14




5-23

5-15




5-24


5-16



5-25




5-26




5-27


-continued




5-28




5-29




5-30




5-31




5-32




5-33




5-34




5-35




5-36




5-37



5-38




5-39




5-40


-continued




5-41




5-42




5-43




5-44




5-45




5-46




5-47




5-48




5-49



5-50




5-51




5-52


-continued




5-53




5-54




5-55




5-56




5-57




5-58




5-59



5-60




5-61




5-62


-continued




5-63




5-64




5-65




5-66




5-67




5-68




5-69




5-70



5-71




5-72




5-73


-continued




5-74




5-75




5-76




5-77




5-78




5-79




5-80



5-81




5-82




5-83


-continued




5-84




5-85




5-86




5-87




5-88




5-89




5-90




5-91



5-92




5-93




5-94


-continued




-continued




-continued




5-113




5-114




5-115




5-116




5-117



5-118




5-119




5-120


-continued




5-121




5-122




5-123



5-124




5-125




5-118

5-126



5-119


5-127




5-120

5-128


-continued




5-129




5-130




5-131




5-132




5-133




5-134



5-135




5-136




5-137


-continued




5-138




5-139



5-140



5-141



5-142

wherein, in Formulae 5-1 to 5-142,

X_{51} is selected from O, S, N(R_{51}), and C(R_{51})(R_{60});
 X_{52} is N or C(R_{52}), X_{53} is N or C(R_{53}), X_{54} is N or C(R_{54}),
 X_{55} is N or C(R_{55}), X_{56} is N or C(R_{56}), X_{57} is N or C(R_{57}), X_{58} is N or C(R_{58}), and X_{59} is N or C(R_{59}),
 R_{51} to R_{60} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group,

a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a thiophenyl group, a furanyl group, a silolyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃), —S(=O)(Q₃₁), —S(=O)₂(Q₃₁), —P(=O)(Q₃₁)(Q₃₂), and —P(=S)(Q₃₁)(Q₃₂),

Q₁ to Q₃ and Q₃₁ to Q₃₃ are each independently selected from a C₁-C₆₀ alkyl group, a phenyl group, a biphenyl group, and a terphenyl group,

b51 is selected from 1, 2, 3, 4, and 5,

b52 is selected from 1, 2, 3, 4, 5, 6, and 7,

b53 is selected from 1, 2, 3, 4, 5, 6, 7, 8, and 9,

b54 is selected from 1, 2, 3, and 4,


b55 is selected from 1, 2, and 3,

b56 is selected from 1 and 2,

b57 is selected from 1, 2, 3, 4, 5, and 6, and


indicates a binding site to a neighboring atom.

12. The condensed cyclic compound as claimed in claim 1, wherein the condensed cyclic compound represented by Formula 1 is represented by one of Formulae 1-1 to 1-3:



-continued

1-3



wherein, in Formulae 1-1 to 1-3,

A₁₁ to A₁₄, L₁₁ to L₁₄, a11 to a14, and b11 to b14 are defined the same as those of Formula 1,





X₁₁ is selected from a single bond, *—O—*, and *—S—*, in which * and *' indicate a binding site to a neighboring atom,

R₁₁ to R₁₄ are each independently selected from a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —B(Q₁)(Q₂), —N(Q₁)(Q₂), —P(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)(Q₁), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), and —P(=S)(Q₁)(Q₂), and

Q₁ to Q₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C₁-C₆₀ alkyl group substituted with at least one selected from deuterium, —F, and a cyano group, a C₆-C₆₀ aryl group substituted with at least one selected from deuterium, —F, and a cyano group, a biphenyl group, and a terphenyl group.

13. The condensed cyclic compound as claimed in claim 1, wherein:

one of R_{11} to R_{14} is a group represented by Formula 2, and the group represented by Formula 2 is a group represented by one of Formulae 2-1 to 2-4:



wherein, in Formulae 2-1 to 2-4,

* indicates a binding site,

A_{21} to A_{24} , L_{21} to L_{24} , a_{21} to a_{24} , and b_{21} to b_{24} are defined the same as those of Formula 2,


R_{21} to R_{24} are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group,

a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_1)(Q_2)(Q_3)$, $-B(Q_1)(Q_2)$, $-N(Q_1)(Q_2)$, $-P(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)(Q_1)$, $-S(=O)_2(Q_1)$, $-P(=O)(Q_1)(Q_2)$, and $-P(=S)(Q_1)(Q_2)$, and


Q_1 to Q_3 are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryloxy group, a C_1 - C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C_1 - C_{60} alkyl group substituted with at least one selected from deuterium, $-F$, and a cyano group, a C_6 - C_{60} aryl group substituted with at least one selected from deuterium, $-F$, and a cyano group, a biphenyl group, and a terphenyl group.

14. The condensed cyclic compound as claimed in claim 1, wherein:

one of R_{11} to R_{14} is a group represented by Formula 2, and the group represented by Formula 2 is represented by one of Formulae 2-11 to 2-22:




-continued



2-12


-continued




2-17

2-13


2-18




2-14




2-19




2-15





2-20



2-16




2-21



-continued

2-22



wherein, in Formulae 2-11 to 2-22,

* indicates a binding site,

A_{21} to A_{24} , L_{21} to L_{24} , a_{21} to a_{24} , and b_{21} to b_{24} are defined the same as those of Formula 2,





X_{21} is selected from a single bond, $*-O-*$, and $*-S-*$, in which * and * indicate a binding site to a neighboring atom,

R_{21} to R_{24} are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{10} cycloalkyl group, a substituted or unsubstituted C_1-C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3-C_{10} cycloalkenyl group, a substituted or unsubstituted C_1-C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, a substituted or unsubstituted C_1-C_{60} heteroaryl group, a substituted or unsubstituted C_1-C_{60} heteroaryloxy group, a substituted or unsubstituted C_1-C_{60} heteroarylthio group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_1)(Q_2)(Q_3)$, $-B(Q_1)(Q_2)$, $-N(Q_1)(Q_2)$, $-P(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)(Q_1)$, $-S(=O)_2(Q^1)$, $-P(=O)(Q_1)(Q_2)$, and $-P(=S)(Q_1)(Q_2)$, and


Q_1 to Q_3 are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, a C_1-C_{60} alkoxy group, a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_1-C_{60} heteroaryl group, a C_1-C_{60} heteroaryloxy group, a C_1-C_{60} heteroarylthio group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a C_1-C_{60} alkyl group substituted with at least one selected from deuterium, $-F$, and a cyano group, a C_6-C_{60} aryl group substituted with at least one selected from deuterium, $-F$, and a cyano group, a biphenyl group, and a terphenyl group.

15. The condensed cyclic compound as claimed in claim 1, wherein the condensed cyclic compound represented by Formula 1 is a compound of the following Compound Group 1:

<Compound Group 1>




-continued




5


-continued




8




6



9




7




10


-continued



11




12




13


-continued




14



15




16




17

-continued




18

-continued




21




22

19





23




24


20




-continued



-continued




28




26


29




27




-continued



-continued




33




31

34







32




-continued

-continued




-continued




39

-continued




41


42




40



43




-continued




44


-continued




47




45



48




46




49

-continued




50


-continued




53




51



54




52




55

-continued




56


-continued




61




57




62




58




63



59




64




60


-continued




65




66



67




68




69


-continued




70



71











72



73


-continued

-continued




-continued


82




83



84




85



-continued

86



16. An organic light-emitting device, comprising:
a first electrode;
a second electrode; and
an organic layer between the first electrode and the second electrode and including an emission layer,
wherein the organic layer includes the condensed cyclic compound as claimed in claim 1.

17. The organic light-emitting device as claimed in claim 16, wherein:

the first electrode is an anode,
the second electrode is a cathode,
the organic layer further includes a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode,

the hole transport region includes a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or any combination thereof, and

the electron transport region includes a hole blocking layer, an electron transport layer, an electron injection layer, or any combination thereof.

18. The organic light-emitting device as claimed in claim 16, wherein the emission layer includes the condensed cyclic compound.

19. The organic light-emitting device as claimed in claim 16, wherein:

the emission layer includes the condensed cyclic compound and a host, and

the condensed cyclic compound is a thermally activated delayed fluorescence (TADF) emitter.

20. The organic light-emitting device as claimed in claim 19, wherein the condensed cyclic compound is included in the emission layer in an amount of about 0.01 parts by weight to about 30 parts by weight, based on 100 parts by weight of the host.

* * * * *

专利名称(译)	稠合环状化合物和包括该稠合环状化合物的有机发光装置		
公开(公告)号	US20200006671A1	公开(公告)日	2020-01-02
申请号	US16/293753	申请日	2019-03-06
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	SIM MUNKI PARK JUNHA BAEK JANGYEOL LEE HYOYOUNG KO SOOBYUNG KIM YOUNGKOOK		
发明人	SIM, MUNKI PARK, JUNHA BAEK, JANGYEOL LEE, HYOYOUNG KO, SOOBYUNG KIM, YOUNGKOOK		
IPC分类号	H01L51/00 H01L51/50 C07F5/02		
CPC分类号	C07F5/02 H01L51/0074 H01L51/0058 H01L51/0072 H01L51/5012 H01L51/0061 H01L51/5092 H01L51/0073 H01L51/5072 H01L51/5056 H01L51/5096 C09K11/06 C09K2211/104 C09K2211/1088 C09K2211/1092 H01L51/0056 H01L51/0071 H01L51/5024 C07F5/027 H01L51/008		
优先权	1020180074184 2018-06-27 KR		
外部链接	Espacenet USPTO		

摘要(译)

稠合环状化合物和包括该稠合环状化合物的有机发光装置，该稠合环状化合物由式1表示：

