

US008569749B2

(12) **United States Patent**
Kim

(10) **Patent No.:** **US 8,569,749 B2**
(45) **Date of Patent:** **Oct. 29, 2013**

(54) **ORGANIC LIGHT EMITTING DIODE DISPLAY HAVING GETTER AND METHOD OF MANUFACTURING THE SAME**

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,049,217	B2*	11/2011	Sung et al.	257/59
2007/0096631	A1*	5/2007	Sung et al.	313/498
2007/0212525	A1*	9/2007	Sung et al.	428/192
2007/0279571	A1*	12/2007	Koo et al.	349/153
2008/0143247	A1*	6/2008	Kim et al.	313/504
2009/0002625	A1*	1/2009	Koo et al.	349/158
2009/0039780	A1*	2/2009	Kim et al.	313/512
2009/0058292	A1*	3/2009	Koo et al.	313/512
2009/0128015	A1*	5/2009	Kim et al.	313/504
2009/0261341	A1*	10/2009	Choi et al.	257/72
2010/0013071	A1*	1/2010	Chol et al.	257/682
2011/0187629	A1*	8/2011	Nam et al.	345/76

(75) Inventor: **Hoon Kim**, Yongin (KR)

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin, Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 66 days.

FOREIGN PATENT DOCUMENTS

JP	10-134959	A	5/1998
KR	10-2007-0067506	A	6/2007
KR	10-2009-0026928	A	3/2009

(21) Appl. No.: **13/083,380**

(22) Filed: **Apr. 8, 2011**

(65) **Prior Publication Data**

US 2012/0112212 A1 May 10, 2012

(30) **Foreign Application Priority Data**

Nov. 8, 2010 (KR) 10-2010-0110572

(51) **Int. Cl.**
H01L 27/32 (2006.01)

(52) **U.S. Cl.**
USPC **257/40**; 349/158

(58) **Field of Classification Search**
USPC 257/88-100, 40; 349/158, 159, 267, 58
See application file for complete search history.

* cited by examiner

Primary Examiner — Nathan Ha

(74) *Attorney, Agent, or Firm* — Knobbe Martens Olson & Bear LLP

(57) **ABSTRACT**

An organic light emitting diode (OLED) display is disclosed. In one embodiment, the OLED display includes first and second substrates, an OLED interposed between the first and second substrates and an external sealant formed between the first and second substrates and configured to i) substantially seal the first and second substrates and ii) substantially surround the OLED. The OLED display may further include a dam formed between the external sealant and the OLED and configured to substantially surround the OLED, and a getter formed between the external sealant and the dam.

6 Claims, 8 Drawing Sheets




FIG. 1

1000




FIG.2




FIG.3




FIG. 4




FIG.5




FIG.6




FIG.7




FIG.8




FIG.9





FIG. 10



ORGANIC LIGHT EMITTING DIODE DISPLAY HAVING GETTER AND METHOD OF MANUFACTURING THE SAME

RELATED APPLICATIONS

This application claims priority to and the benefit of Korean Patent Application No. 10-2010-0110572 filed in the Korean Intellectual Property Office on Nov. 8, 2010, the entire contents of which are incorporated herein by reference.

BACKGROUND

1. Field

The described technology generally relates to an organic light emitting diode (OLED) display and a method of manufacturing the same, for example, an OLED display including a getter having moisture absorption ability.

2. Description of the Related Technology

A display device displays an image, and nowadays, the OLED display is undergoing rapid improvement.

The OLED display has self luminance characteristics and does not require a separate light source, unlike a liquid crystal display (LCD) device. It thus provides a reduced thickness and weight. Further, the OLED display represents high quality characteristics of low power consumption, high luminance, and a high reaction speed.

SUMMARY

One inventive aspect is an OLED display having advantages of suppressing a failure from occurring in an OLED by a getter.

Another aspect is an OLED display including: a first substrate; an OLED that is positioned on the first substrate; a second substrate that is positioned on the first substrate with the OLED interposed therebetween; an external sealant that is positioned between the first substrate and the second substrate and that coheres and seals the first substrate and the second substrate and that encloses the OLED at a predetermined gap; a dam that is positioned between the external sealant and the OLED and that encloses the OLED; and a getter that is positioned between the external sealant and the dam.

The external sealant may include a light curable material.

The dam may include a thermosetting material.

The dam may include a moisture absorption material.

The getter may be cured from liquid to solid.

The OLED display may further include an internal sealant that is positioned between the external sealant and the getter.

The internal sealant may include a thermosetting material.

The second substrate may be an opaque substrate, and the OLED may emit light in a direction of the first substrate.

Another aspect is a method of manufacturing an OLED display, the method including: forming an external sealant that encloses an OLED at a predetermined gap from the OLED on a first substrate at which the OLED is positioned; forming a dam that encloses the OLED between the external sealant and the OLED; forming a liquid getter between the external sealant and the dam; and cohering and sealing the first substrate and the second substrate with the OLED interposed therebetween.

The cohering and sealing of the first substrate and the second substrate with the OLED interposed therebetween may include disposing the second substrate on the first substrate with the external sealant, the liquid getter, and the dam

interposed therebetween; and curing the external sealant by radiating light to the external sealant.

The cohering and sealing of the first substrate and the second substrate may further include curing the dam by applying heat to the dam.

The liquid getter may be cured into a solid getter by the heat.

The method may further include forming an internal sealant between the external sealant and the OLED in order to position the internal sealant between the external sealant and the getter.

The cohering and sealing of the first substrate and the second substrate with the OLED interposed therebetween may include disposing the second substrate on the first substrate with the external sealant, the internal sealant, the liquid getter, and the dam interposed therebetween; and curing the external sealant by radiating light to the external sealant; and curing the internal sealant, the liquid getter, and the dam by applying heat to the internal sealant, the liquid getter, and the dam.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a top plan view illustrating an OLED display according to a first embodiment.

FIG. 2 is a cross-sectional view illustrating the OLED display taken along line II-II of FIG. 1.

FIG. 3 is a layout view illustrating a structure of a pixel of an OLED display according to the first embodiment.

FIG. 4 is a cross-sectional view illustrating the pixel taken along line IV-IV of FIG. 3.

FIG. 5 is a flowchart illustrating a method of manufacturing an OLED display according to a second embodiment.

FIGS. 6 and 7 are cross-sectional views illustrating a method of manufacturing an OLED display according to the second embodiment.

FIG. 8 is a cross-sectional view illustrating an OLED display according to a third embodiment.

FIGS. 9 and 10 are cross-sectional views illustrating a method of manufacturing an OLED display according to a fourth embodiment.

DETAILED DESCRIPTION

In general, an OLED display includes i) a first substrate, ii) an OLED that is positioned on the first substrate, iii) a second substrate that is opposite to the first substrate with the OLED interposed therebetween, iv) a sealant that coheres and seals the first substrate and the second substrate, and v) a getter that is positioned between the sealant and the OLED and that has moisture absorption ability.

However, when cohering and sealing the first substrate and the second substrate by the sealant, the getter may move in a direction of the OLED by an internal pressure that is formed between the first substrate and the second substrate and thus there is a problem that a failure occurs in the OLED.

Embodiments will be described more fully hereinafter with reference to the accompanying drawings. As those skilled in the art would realize, the described embodiments may be modified in various different ways.

The drawings and description are to be regarded as illustrative in nature and not restrictive. Like reference numerals designate like elements throughout the specification.

Further, in the drawings, a size and thickness of each element are randomly represented for better understanding and ease of description, and not considered limiting.

In the drawings, the thickness of layers, films, panels, regions, etc., may be exaggerated for clarity. In the drawings, for better understanding and ease of description, thicknesses of some layers and areas are excessively displayed. When it is said that any part, such as a layer, film, region, or plate, is positioned on another part, it means the part is directly on the other part or above the other part with at least one intermediate part.

In addition, unless explicitly described to the contrary, the word “comprise” and variations such as “comprises” or “comprising”, will be understood to imply the inclusion of stated elements but not the exclusion of any other elements. Further, in the specification, it means that an upper part of a target portion indicates an upper part or a lower part of a target portion, and it does not mean that the target portion is always positioned at the upper side based on a gravity direction.

Further, for the purpose of convenience, in the accompanying drawings, an active matrix (AM) OLED display of a 2Tr-1 Cap structure having two thin film transistors (TFT) and one capacitor in one pixel is illustrated. However, the OLED display may have two or more capacitors and three or more TFTs in one pixel, and a separate wire may be further formed and thus the OLED display may have various structures. Here, a pixel is a minimum unit that displays an image, and the OLED display displays an image through a plurality of pixels.

Hereinafter, an OLED display according to a first embodiment will be described with reference to FIGS. 1 to 4.

FIG. 1 is a top plan view illustrating an OLED display according to a first embodiment. FIG. 2 is a cross-sectional view illustrating the OLED display taken along line II-II of FIG. 1.

As shown in FIGS. 1 and 2, an OLED display 1000 includes a first substrate 100, a second substrate 200, a wire portion 300, an OLED 400, an external sealant 500, a dam 600, and a getter 700.

At least one of the first and second substrates 100 and 200 may be formed at least partially of glass, polymer, or a metal. The first substrate 100 may be made of a light transmitting material, and the second substrate 200 may be made of a light opaque material. In one embodiment, the second substrate is an opaque substrate including aluminum (Al) or copper (Cu). The wire portion 300 and the OLED 400 are positioned on the first substrate 100, and the second substrate 200 is opposite to the first substrate 100 with the wire portion 300 and the OLED 400 interposed therebetween. The first substrate 100 and the second substrate 200 are cohered and sealed by the external sealant 500 with the OLED 400 interposed therebetween, and the first substrate 100 and the second substrate 200 protect the wire portion 300 and the OLED 400 from external impact or the environment.

In the OLED display 1000, the second substrate 200 may be made of a light opaque material, but in an OLED display according to another embodiment, at least one of the first substrate and the second substrate is made of a light transmitting material.

The wire portion 300 includes a first TFT 10 and a second TFT 20 (shown in FIG. 3) and drives the OLED 400 by transferring a signal to the OLED 400. The OLED 400 emits light according to a signal that is received from the wire portion 300.

The OLED 400 is positioned on the wire portion 300.

The OLED 400 is positioned on the first substrate 100, and receives a signal from the wire portion 300 and displays an image by the received signal.

Hereinafter, an internal structure of an OLED display according to a first embodiment will be described in detail with reference to FIGS. 3 and 4.

FIG. 3 is a layout view illustrating a structure of a pixel of an OLED display according to a first embodiment. FIG. 4 is a cross-sectional view illustrating the pixel taken along line IV-IV of FIG. 3.

Hereinafter, a detailed structure of the wire portion 300 and the OLED 400 is illustrated in FIGS. 3 and 4, but the embodiment shown in FIGS. 3 and 4 is not considered limiting. The wire portion 300 and the OLED 400 can be formed in various structures within a range that can be easily modified by a person of ordinary skill in the art. In one embodiment, in the accompanying drawings, an AM OLED display of a 2Tr-1 Cap structure having two TFTs and one capacitor in one pixel is illustrated as an OLED display. In another embodiment, a display device is not limited to the quantity of the TFT, the quantity of the capacitor, and the quantity of the wire. The pixel is a minimum unit that displays an image, and the OLED display displays an image using a plurality of pixels.

As shown in FIGS. 3 and 4, the OLED display 1000 includes a switching TFT 10, a driving TFT 20, a capacitor 80, and an OLED 400 that are each formed in one pixel. Here, a configuration including the switching TFT 10, the driving TFT 20, and the capacitor 80 is referred to as a wire portion 300. The wire portion 300 further includes a gate line 151 that is disposed along one direction of the first substrate 100 and a data line 171 and a common power source line 172 that are insulated from the gate line 151 and that intersects the gate line 151. Here, a pixel is defined using the gate line 151, the data line 171, and the common power source line 172 as a boundary, but a pixel is not limited thereto.

The OLED 400 includes a first electrode 710, an organic emission layer 720 that is formed on the first electrode 710, and a second electrode 730 that is formed on the organic emission layer 720. Here, the first electrode 710 may be an anode, which is a hole injection electrode, and the second electrode 730 may be a cathode, which is an electron injection electrode. However, the first electrode 710 may become a cathode and the second electrode 730 may become an anode according to a driving method of the OLED display 1000. When holes and electrons are injected into the organic emission layer 720 from the first electrode 710 and the second electrode 730, respectively, and excitons in which holes and electrons that are injected into the organic emission layer 720 are coupled drop from an excited state to a ground state, the organic emission layer 720 emits light. Further, the first electrode 710 is formed in a light transmitting structure, and the second electrode 730 is formed in a light reflecting structure. Thereby, the OLED 400 emits light in a direction of the first substrate 100.

In the OLED display according to another embodiment, at least one of the first electrode and the second electrode can be formed in a light transmitting structure, and the OLED can emit light in a direction of at least one of the first substrate and the second substrate. That is, the OLED display may be a front light emitting type, a rear light emitting type, or both surface light emitting type.

The capacitor 80 includes a pair of capacitor plates 158 and 178 that are disposed with the interlayer insulating layer 161 interposed therebetween. Here, the interlayer insulating layer 161 becomes a dielectric material, and a capacitor capacity of the capacitor 80 is determined by charges that are stored in the capacitor 80 and a voltage between both capacitor plates 158 and 178.

The switching TFT 10 includes a switching semiconductor layer 131, a switching gate electrode 152, a switching source

electrode **173**, and a switching drain electrode **174**. The driving TFT **20** includes a driving semiconductor layer **132**, a driving gate electrode **155**, a driving source electrode **176**, and a driving drain electrode **177**.

The switching TFT **10** is used as a switch for selecting a pixel to emit light. The switching gate electrode **152** is connected to the gate line **151**. The switching source electrode **173** is connected to the data line **171**. The switching drain electrode **174** is separated from the switching source electrode **173** and is connected to one capacitor plate **158**.

The driving TFT **20** applies a driving power source for allowing light emission of the organic emission layer **720** of the OLED **400** within the selected pixel to the second electrode **730**. The driving gate electrode **155** is connected to the capacitor plate **158** that is connected to the switching drain electrode **174**. The driving source electrode **176** and the other one capacitor plate **178** are each connected to the common power source line **172**. The driving drain electrode **177** is positioned at the same layer as that of the first electrode **710** and is connected to the first electrode **710**.

By such a structure, the switching TFT **10** operates by a gate voltage that is applied to the gate line **151** to perform a function of transferring a data voltage that is applied to the data line **171** to the driving TFT **20**. A voltage corresponding to a difference between a common voltage that is applied from the common power source line **172** to the driving TFT **20** and a data voltage that is transferred from the switching TFT **10** is stored in the capacitor **80**, and a current corresponding to a voltage that is stored in the capacitor **80** flows to the OLED **400** through the driving TFT **20** and thus the OLED **400** emits light.

Referring again to FIGS. **1** and **2**, the external sealant **500** is positioned between the first substrate **100** and the second substrate **200**, encloses the OLED **400** at a predetermined gap, and is disposed along edges of the first substrate **100** and the second substrate **200** to cohere and seal the first substrate **100** and the second substrate **200**. In one embodiment, the external sealant **500** includes an organic material including epoxy, acryl, and silicon, etc., in which a light curable material is included, or an organic and inorganic material in which talc, calcium oxide (CaO), barium oxide (BaO), zeolite, and silicon oxide (SiO) are included in an organic material, and is cured by light of ultraviolet (UV) rays, etc.

The dam **600** is positioned between the external sealant **500** and the OLED **400** between the first substrate **100** and the second substrate **200**.

The dam **600** encloses the OLED **400** between the external sealant **500** and the OLED **400** and coheres and seals the first substrate **100** and the second substrate **200** together with the external sealant **500**. In one embodiment, the dam **600** includes an organic material including epoxy, acryl, and silicon in which a thermosetting material is included, or an organic and inorganic material in which talc, calcium oxide (CaO), barium oxide (BaO), zeolite, and silicon oxide (SiO) are included in, an organic material, and is cured by heat. Further, the dam **600** may include a moisture absorption material such as a filler that absorbs moisture, and as the dam **600** includes a moisture absorption material, moisture that may be penetrated from the outside to the OLED **400** is intercepted by the dam **600**. This functions as a factor of improving a life-span of the OLED **400**.

The getter **700** is positioned between the dam **600** and the external sealant **500**.

The getter **700** is closed and sealed by the external sealant **500**, the dam **600**, the first substrate **100**, and the second substrate **200** between the external sealant **500** and the dam **600**. The getter **700** has moisture absorption ability and per-

forms a function of intercepting moisture that may be penetrated from the outside to the OLED **400** through the external sealant **500**. That is, moisture that may be penetrated from the outside to the OLED **400** is intercepted by the getter **700**. This functions as a factor of improving a life-span of the OLED **400**. Particularly, the getter **700** is positioned between the external sealant **500** and the dam **600** in a cured state from liquid of a paste form to solid.

As described above, in the OLED display **1000** according to the first embodiment, as the getter **700** is positioned between the external sealant **500** and the dam **600**, a failure is prevented from occurring in the OLED **400** by the getter **700**. For example, the getter **700** is cured from liquid of a paste form to solid, and when manufacturing the OLED display **1000**, even if the getter **700** is in a liquid phase, the getter **700** is intercepted from flowing in a direction of the OLED **400** by the dam **600**, and thus a failure is prevented from occurring in the OLED **400** as the getter **700** flows to the OLED **400**. Further, when the getter **700** is cured from liquid to solid, even if gas is generated in the getter **700**, the gas is intercepted from moving in a direction of the OLED **400** by the dam **600**, and thus a failure is prevented from occurring in the OLED **400** as gas that is generated from the getter **700** moves to the OLED **400**.

Further, as moisture that may be penetrated from the outside to the OLED **400** is sequentially intercepted by the external sealant **500**, the getter **700**, and the dam **600**, it is minimized that moisture penetrates to the OLED **400**, whereby a life-span of the OLED **400** is improved and thus a life-span of the OLED display **1000** is improved.

Moreover, as the first substrate **100** and the second substrate **200** are cohered and sealed by the external sealant **500** and the dam **600**, a bonding force between the first substrate **100** and the second substrate **200** is improved and thus the first substrate **100** and the second substrate **200** are suppressed from being separated from each other by an external impact. That is, mechanical strength of the OLED display **1000** is improved.

Further, as the external sealant **500** includes a light curable material and the dam **600** includes a thermosetting material, even if the second substrate **200** is an opaque substrate, the external sealant **500** is cured using light such as UV rays and the dam **600** is cured using heat. That is, because the second substrate **200** is an opaque substrate, by curing the external sealant **500** using a thermosetting means such as UV rays, the first substrate **100** and the second substrate **200** can be cohered and sealed, and the dam **600** can be cured using heat and thus when manufacturing an OLED display **1000**, a cohesion process and a heat treatment process can be separated.

By forming both the external sealant **500** and the dam **600** to include a thermosetting material, the external sealant **500** and the dam **600** can be cured at one time by a heat treatment process of one time.

Hereinafter, a method of manufacturing an OLED display according to a second embodiment will be described with reference to FIGS. **5** to **7**. The OLED display **1000** according to the first embodiment is manufactured by a method of manufacturing an OLED display according to the second embodiment.

FIG. **5** is a flowchart illustrating a method of manufacturing an OLED display according to a second embodiment. FIGS. **6** and **7** are cross-sectional views illustrating a method of manufacturing an OLED display according to a second embodiment.

First, as shown in FIGS. **5** and **6**, the external sealant **500** is formed on the first substrate **100** at which the OLED **400** is positioned (**S100**).

Specifically, after the wire portion **300** and the OLED **400** are formed on the first substrate **100**, the external sealant **500** is formed on the first substrate **100** so as to enclose the OLED **400** at a predetermined gap from the OLED **400**. In one embodiment, the external sealant **500** is made of an organic material or an organic and inorganic composite material including a light curable material using an application process or a printing process.

Next, the dam **600** is formed (S200).

Specifically, the dam **600** is formed between the external sealant **500** and the OLED on the first substrate **100** in which the external sealant **500** is formed. In one embodiment, the dam **600** is made of a material including a thermosetting material using an application process or a printing process and as the dam **600** is formed, a predetermined separation space SS is formed between the external sealant **500** and the dam **600**.

The external sealant and the dam may be substantially simultaneously formed on the first substrate, or after the dam is formed on the first substrate, the external sealant may be formed on the first substrate.

Next, the liquid getter **700** is formed (S300).

Specifically, the liquid getter **700** of a paste form is formed in the predetermined separation space SS that is formed between the external sealant **500** and the dam **600**. The liquid getter **700** can be formed using an application process, a dropping process, or an ejecting process. The liquid getter **700** has fluidity, but as the external sealant **500** and the dam **600** limit a flow area of the liquid getter **700**, the liquid getter **700** is positioned only at the separation space SS.

In this way, as the liquid getter **700** having fluidity is formed in the predetermined separation space SS that is formed between the external sealant **500** and the dam **600**, when the OLED display **1000** is manufactured, while the liquid getter **700** does not flow to the environment, the liquid getter **700** does not flow to a portion at which the OLED **400** is positioned and thus a failure is prevented from occurring by the getter **700**.

Next, as shown in FIG. 7, the first substrate **100** and the second substrate **200** are cohered and sealed (S400).

Hereinafter, cohering and sealing of the first substrate **100** and the second substrate **200** will be described in detail.

First, the second substrate **200**, which is an opaque substrate is disposed on the first substrate **100** at which the OLED **400** is positioned with the external sealant **500**, the liquid getter **700**, and the dam **600** interposed therebetween. In this case, as the second substrate **200** contacts with the external sealant **500** and the dam **600**, the liquid getter **700** is enclosed and sealed by the first substrate **100**, the second substrate **200**, the external sealant **500**, and the dam **600**.

Next, by radiating light such as UV rays to the external sealant **500** that is exposed to the outside, the external sealant **500** is cured. As the external sealant **500** is cured, the liquid getter **700**, the dam **600**, and the OLED **400** that are positioned at the inside of the external sealant **500** are closed and sealed by the first substrate **100**, the second substrate **200**, and the external sealant **500**.

Next, by applying heat to the dam **600**, the dam **600** is cured.

Specifically, the dam **600** is cured by applying heat in a direction of the dam **600** from the outside of the first substrate **100** and the second substrate **200**.

As fluidity of a material including a thermosetting material that is included in the dam **600** rapidly rises in a predetermined temperature and heating time period, even if a small pressure is applied, a form of the material may be deformed and when a pressure is applied to an internal space IS between

the first substrate **100** and the second substrate **200**, the dam **600** flows in a direction of the OLED **400**, whereby the liquid getter **700** flows in a direction of the OLED **400** and thus a failure may occur in the OLED **400**.

However, in one embodiment, even if a pressure is applied to the internal space IS between the first substrate **100** and the second substrate **200** and fluidity of a material including a thermosetting material that is included in the dam **600** rapidly rises, the external sealant **500** has been already cured by light and thus the dam **600** is in a closed and sealed state by the first substrate **100**, the second substrate **200**, and the external sealant **500**, whereby a form of the dam **600** is not deformed and is cured by heat. In this case, the liquid getter **700** is cured into the solid getter **700** by heat for curing the dam **600**.

In this way, the first substrate **100** and the second substrate **200** are cohered and sealed and thus the OLED display **1000** is manufactured.

As described above, a method of manufacturing the OLED display according to the second embodiment is performed in consideration of characteristics of a material including a thermosetting material in which fluidity rapidly rises in a predetermined temperature and heating time period. Unlike a method of manufacturing the OLED display according to the second embodiment, for convenience of a process, by forming the external sealant **500** and the dam **600** to include a thermosetting material when the external sealant **500** and the dam **600** are cured using heat, as fluidity of the external sealant **500** and the dam **600** rapidly rises in a predetermined temperature and heating time period, a form thereof is deformed and thus the liquid getter **700** that is positioned at the separation space SS between the external sealant **500** and the dam **600** flows in a direction of the OLED **400** and thus a failure may occur in the OLED **400**.

That is, in a method of manufacturing the OLED display according to the second embodiment, when the second substrate **200** is an opaque substrate, in consideration of characteristics of a material including a thermosetting material, the external sealant **500** is formed to include a material including a light curable material to be first cured using light, and the dam **600** is formed to include a material including a thermosetting material to be cured together with the liquid getter **700**. Thereby, when manufacturing the OLED display **1000**, the liquid getter **700** is prevented from flowing to the OLED **400**, and thus a production yield of the OLED display **1000** is improved.

Hereinafter, an OLED display according to a third embodiment will be described with reference to FIG. 8.

Hereinafter, only characteristic portions different from the first embodiment are described and portions in which a description is omitted follow a description of the first embodiment. In the third embodiment, for better comprehension and ease of description, constituent elements identical to or corresponding to those according to the first embodiment are denoted by the same reference numerals.

FIG. 8 is a cross-sectional view illustrating an OLED display according to a third embodiment.

As shown in FIG. 8, an OLED display **1003** according to a third exemplary embodiment includes a first substrate **100**, a second substrate **200**, a wire portion **300**, an OLED **400**, an external sealant **500**, a dam **600**, a getter **700**, and an internal sealant **800**.

The internal sealant **800** is positioned between the external sealant **500** and the getter **700** and encloses the OLED **400**. The internal sealant **800** coheres and seals the first substrate **100** and the second substrate **200** together with the external sealant **500** and the dam **600**. In one embodiment, the internal sealant **800** includes an organic material including epoxy,

acryl, and silicon in which a thermosetting material is included or an organic and inorganic material in which talc, calcium oxide (CaO), barium oxide (BaO), zeolite, and silicon oxide (SiO) are included in an organic material, and is cured by heat.

As described above, in the OLED display **1003** according to the third embodiment, as the getter **700** is positioned between the internal sealant **800** and the dam **600**, a failure is prevented from occurring in the OLED **400** by the getter **700**. For example, the getter **700** is cured from liquid of a paste form to solid, and when the OLED display **1003** is manufactured, even if the getter **700** is in a liquid phase, the getter **700** is intercepted from flowing in a direction of the OLED **400** by the dam **600**, and thus a failure is prevented from occurring in the OLED **400** as the getter **700** flows to the OLED **400**. Further, when the getter **700** is cured from liquid to solid, even if gas is generated from the getter **700**, the gas is intercepted from moving in a direction of the OLED **400** by the dam **600**, and therefore gas that is generated in the getter **700** moves to the OLED **400**, and thus a failure is prevented from occurring in the OLED **400**.

Further, in the OLED display **1003** according to the third embodiment, as moisture that may penetrate from the outside to the OLED **400** is sequentially intercepted by the external sealant **500**, the internal sealant **800**, the getter **700**, and the dam **600**, it is minimized that moisture penetrates to the OLED **400**, whereby a life-span of the OLED **400** is improved and thus a life-span of the OLED display **1003** is improved.

Further, in the OLED display **1003** according to the first embodiment, as the first substrate **100** and the second substrate **200** are cohered and sealed by the external sealant **500**, the internal sealant **800**, and the dam **600**, a bonding force between the first substrate **100** and the second substrate **200** is improved and thus the first substrate **100** and the second substrate **200** are suppressed from separating by an external impact. That is, mechanical strength of the OLED display **1003** is improved.

Further, in the OLED display **1003** according to the first embodiment, as the external sealant **500** includes a light curable material and the internal sealant **800** and the dam **600** include a thermosetting material, even if the second substrate **200** is an opaque substrate, the external sealant **500** can be cured using light such as UV rays, and the internal sealant **800** and the dam **600** can be cured using heat. That is, because the second substrate **200** is an opaque substrate, the first substrate **100** and the second substrate **200** can be cohered and sealed by curing the external sealant **500** using a thermosetting means such as UV rays, and then the internal sealant **800** and the dam **600** can be cured using heat and thus when the OLED display is manufactured, a cohesion process and a heat treatment process can be separated.

Hereinafter, a method of manufacturing an OLED display according to a fourth embodiment will be described with reference to FIGS. **9** and **10**. The OLED display **1003** according to the third embodiment is manufactured by the method of manufacturing an OLED display according to the fourth embodiment.

Hereinafter, only characteristic portions different from the second embodiment will be described and portions in which a description is omitted follow a description of the second embodiment. In the fourth embodiment, for better comprehension and ease of description, constituent elements identical to or corresponding to those of the second embodiment are denoted by the same reference numerals.

FIGS. **9** and **10** are cross-sectional views illustrating a method of manufacturing an OLED display according to a fourth embodiment.

As shown in FIG. **9**, the external sealant **500** is formed on the first substrate **100** at which the OLED **400** is positioned.

Next, the internal sealant **800** is formed between the external sealant **500** and the OLED **400** so as to position between the external sealant **500** and the getter **700** to be formed later.

Specifically, the internal sealant **800** is formed between the external sealant **500** and an OLED on the first substrate **100** in which the external sealant **500** is formed. The internal sealant **800** is made of a material including a thermosetting material using an application process or a printing process. The internal sealant **800** may be formed simultaneously or in a different order with the external sealant **500** and may contact with or be separated from the external sealant **500**.

Next, the dam **600** is formed.

In a method of manufacturing an OLED display according to another exemplary embodiment, an external sealant, an internal sealant, and a dam may be simultaneously formed on the first substrate, or after a dam is formed on the first substrate, an external sealant and an internal sealant may be formed on the first substrate.

Next, the liquid getter **700** is formed.

Next, as shown in FIG. **10**, the first substrate **100** and the second substrate **200** are cohered and sealed.

Hereinafter, cohering and sealing of the first substrate **100** and the second substrate **200** will be described in detail.

First, the second substrate **200**, which is an opaque substrate is disposed on the first substrate **100** at which the OLED **400** is positioned with the external sealant **500**, the internal sealant **800**, the liquid getter **700**, and the dam **600** interposed therebetween. In this case, as the second substrate **200** contacts with the external sealant **500**, the internal sealant **800**, and the dam **600**, the liquid getter **700** is enclosed and sealed by the first substrate **100**, the second substrate **200**, the internal sealant **800**, and the dam **600**.

Next, by radiating light such as UV rays to the external sealant **500** that is exposed to the outside, the external sealant **500** is cured. As the external sealant **500** is cured, the internal sealant **800**, the liquid getter **700**, the dam **600**, and the OLED **400** that are positioned at the inside of the external sealant **500** are closed and sealed by the first substrate **100**, the second substrate **200**, and the external sealant **500**.

Next, by applying heat to the internal sealant **800**, the liquid getter **700**, and the dam **600**, the internal sealant **800**, the liquid getter **700**, and the dam **600** are cured.

Specifically, by applying heat in a direction of the internal sealant **800**, the liquid getter **700**, and the dam **600** from the outside of the first substrate **100** and the second substrate **200**, the internal sealant **800**, the liquid getter **700**, and the dam **600** are cured.

In this case, in a method of manufacturing an OLED display according to a fourth embodiment, even if a pressure is applied to the inner space IS between the first substrate **100** and the second substrate **200** and fluidity of a material including a thermosetting material that is included in the internal sealant **800** and the dam **600** rapidly increases, the external sealant **500** has been already cured by light and thus the internal sealant **800** and the dam **600** are in a closed and sealed state by the first substrate **100**, the second substrate **200**, and the external sealant **500**, whereby a form of the internal sealant **800** and the dam **600** is not deformed and is cured by heat. In this case, the liquid getter **700** is cured into the solid getter **700** by heat for curing the internal sealant **800** and the dam **600**.

11

In this way, the first substrate **100** and the second substrate **200** are cohered and sealed and thus an OLED display **1003** is manufactured.

As described above, in a method of manufacturing an OLED display according to the fourth embodiment, when the second substrate **200** is an opaque substrate, in consideration of characteristics of a material including a thermosetting material, the external sealant **500** is formed to include a material including a light curable material to be first cured using light, and the internal sealant **800** and the dam **600** are formed to include a material including a thermosetting material to be cured together with the liquid getter **700**. Thereby, when manufacturing the OLED display **1003**, the liquid getter **700** is prevented from flowing to the OLED **400**, and thus a production yield of the OLED display **1003** is improved.

At least one of the disclosed embodiments provide an OLED display in which a failure is suppressed from occurring in an OLED by a getter.

While this disclosure has been described in connection with certain embodiments, it is to be understood that these embodiments are not considered limiting. Thus, various modifications and equivalent arrangements are included within the spirit and scope of the appended claims.

What is claimed is:

1. An organic light emitting diode (OLED) display comprising:
first and second substrates;

12

an OLED interposed between the first and second substrates;

an external sealant formed between the first and second substrates and configured to i) substantially seal the first and second substrates and ii) substantially surround the OLED, wherein the external sealant is formed at least partially of a light curable material;

a dam formed between the external sealant and the OLED and configured to substantially surround the OLED, wherein the dam is formed at least partially of a thermosetting material and a moisture absorption material; and a getter formed between the external sealant and the dam, wherein the getter is formed of a material different from at least one of the external sealant and the dam.

2. The OLED display of claim 1, wherein the getter is configured to be cured from liquid to solid.

3. The OLED display of claim 1, further comprising an internal sealant formed between the external sealant and the getter.

4. The OLED display of claim 3, wherein the internal sealant is formed at least partially of a thermosetting material.

5. The OLED display of claim 1, wherein the getter is formed of a moisture absorption material.

6. The OLED display of any one of claims 1, 2-4, and 5, wherein the second substrate is an opaque substrate, and wherein the OLED is configured to emit light in a direction of the first substrate.

* * * * *

专利名称(译)	具有吸气剂的有机发光二极管显示器及其制造方法		
公开(公告)号	US8569749	公开(公告)日	2013-10-29
申请号	US13/083380	申请日	2011-04-08
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星移动显示器有限公司.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KIM HOON		
发明人	KIM, HOON		
IPC分类号	H01L27/32		
CPC分类号	H01L51/5246 H01L51/5259		
优先权	1020100110572 2010-11-08 KR		
其他公开文献	US20120112212A1		
外部链接	Espacenet	USPTO	

摘要(译)

公开了一种有机发光二极管 (OLED) 显示器。在一个实施例中， OLED 显示器包括第一和第二基板，插入在第一和第二基板之间的OLED和形成在第一和第二基板之间的外部密封剂，并配置成i)基本上密封第一和第二基板，以及ii)基本上环绕OLED。OLED显示器还可以包括形成在外部密封剂和OLED之间并构成基本上围绕OLED的挡板，以及形成在外部密封剂和挡板之间的吸气剂。

