



US008906731B2

(12) **United States Patent**
Lee et al.

(10) **Patent No.:** **US 8,906,731 B2**
(45) **Date of Patent:** **Dec. 9, 2014**

(54) **PATTERNING SLIT SHEET ASSEMBLY,
ORGANIC LAYER DEPOSITION
APPARATUS, METHOD OF
MANUFACTURING ORGANIC
LIGHT-EMITTING DISPLAY APPARATUS,
AND THE ORGANIC LIGHT-EMITTING
DISPLAY APPARATUS**

(75) Inventors: **Myung-Ki Lee**, Yongin (KR);
Sung-Bong Lee, Yongin (KR);
Myong-Hwan Choi, Yongin (KR);
Mu-Hyun Kim, Yongin (KR)

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin-si
(KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **13/461,669**

(22) Filed: **May 1, 2012**

(65) **Prior Publication Data**
US 2012/0298970 A1 Nov. 29, 2012

(30) **Foreign Application Priority Data**
May 27, 2011 (KR) 10-2011-0050842

(51) **Int. Cl.**
H01L 21/00 (2006.01)
C23C 14/12 (2006.01)
H01L 51/00 (2006.01)
C23C 14/04 (2006.01)
H01L 51/56 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 51/0011** (2013.01); **C23C 14/12**
(2013.01); **C23C 14/042** (2013.01); **H01L 51/56**
(2013.01)

USPC **438/82; 257/40**
(58) **Field of Classification Search**
USPC **438/82; 257/40**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,416,217 A 11/1983 Nakamura et al.
4,468,648 A 8/1984 Uchikune
(Continued)

FOREIGN PATENT DOCUMENTS

CN 1476279 A 2/2004
CN 1489419 A 4/2004
(Continued)

OTHER PUBLICATIONS

Patent Abstracts of Japan, and English machine translation of Japa-
nese Publication 2001-052862, 20 pages.

(Continued)

Primary Examiner — Charles Garber


Assistant Examiner — Brigitte Paterson

(74) *Attorney, Agent, or Firm* — Christie, Parker & Hale,
LLP

(57) **ABSTRACT**

A patterning slit sheet assembly to perform a deposition pro-
cess to deposit a thin film on a substrate in a fine pattern. A
patterning slit sheet assembly includes a patterning slit sheet
including a slit unit, and a non-slit region that is located along
edges of the slit unit, the patterning slit sheet being smaller
than the substrate in at least one of a first direction or a second
direction perpendicular to the first direction; a frame com-
bined with the patterning slit sheet to support the patterning
slit sheet; and a shielding unit extending on at least one inner
side of the frame and overlapping an area including the edges
of the slit unit.

10 Claims, 12 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

4,687,939 A	8/1987	Miyauchi et al.	2003/0232563 A1	12/2003	Kamiyama et al.
4,792,378 A	12/1988	Rose et al.	2004/0016907 A1	1/2004	Shi
4,901,667 A	2/1990	Suzuki et al.	2004/0029028 A1	2/2004	Shimizu
5,454,847 A	10/1995	Jacoboni et al.	2004/0056244 A1*	3/2004	Marcus et al. 257/40
5,460,654 A	10/1995	Kikkawa et al.	2004/0086639 A1	5/2004	Grantham et al.
5,487,609 A	1/1996	Asada	2004/0096771 A1	5/2004	Kashiwagi et al.
5,742,129 A	4/1998	Nagayama et al.	2004/0115338 A1	6/2004	Yoneda
5,909,995 A	6/1999	Wolf et al.	2004/0115342 A1	6/2004	Shigemura
6,045,671 A	4/2000	Wu et al.	2004/0123804 A1	7/2004	Yamazaki et al.
6,091,195 A	7/2000	Forrest et al.	2004/0127066 A1	7/2004	Jung
6,099,649 A	8/2000	Schmitt et al.	2004/0134428 A1	7/2004	Sasaki et al.
6,274,198 B1	8/2001	Dautartas	2004/0142108 A1	7/2004	Atobe et al.
6,280,821 B1	8/2001	Kadunce et al.	2004/0144321 A1	7/2004	Grace et al.
6,371,451 B1	4/2002	Choi	2004/0157167 A1	8/2004	Morii
6,417,034 B2	7/2002	Kitazume et al.	2004/0183435 A1	9/2004	Oshita
6,443,597 B1	9/2002	Natori	2004/0194702 A1	10/2004	Sasaki et al.
6,483,690 B1	11/2002	Nakajima et al.	2004/0195530 A1	10/2004	Kwak et al.
6,541,130 B2	4/2003	Fukuda	2004/0216673 A1	11/2004	Sakata et al.
6,554,969 B1	4/2003	Chong	2004/0255857 A1	12/2004	Chow et al.
6,579,422 B1	6/2003	Kakinuma	2004/0263547 A1	12/2004	Sugahara
6,589,673 B1	7/2003	Kido et al.	2004/0263771 A1	12/2004	Jeong et al.
6,650,023 B2	11/2003	Kim	2005/0001546 A1	1/2005	Yamaguchi
6,699,324 B1	3/2004	Berdin et al.	2005/0016461 A1	1/2005	Klug et al.
6,749,906 B2	6/2004	Van Slyke	2005/0031836 A1	2/2005	Hirai
6,776,847 B2	8/2004	Yamazaki et al.	2005/0037136 A1	2/2005	Yamamoto
6,837,939 B1	1/2005	Klug et al.	2005/0039684 A1	2/2005	Yi et al.
6,878,209 B2	4/2005	Himeshima et al.	2005/0072359 A1	4/2005	Kim
6,946,783 B2	9/2005	Kim	2005/0072361 A1	4/2005	Yang et al.
6,995,035 B2	2/2006	Cok et al.	2005/0079418 A1	4/2005	Kelley et al.
7,006,202 B2	2/2006	Byun et al.	2005/0110400 A1	5/2005	Nakamura
RE39,024 E	3/2006	Takahashi	2005/0118788 A1	6/2005	Kuwahara et al.
7,078,070 B2	7/2006	Peng	2005/0129489 A1	6/2005	Quan et al.
7,199,520 B2	4/2007	Fujii et al.	2005/0153472 A1	7/2005	Yotsuya
7,282,855 B2	10/2007	Park et al.	2005/0166842 A1	8/2005	Sakamoto
7,322,248 B1	1/2008	Long	2005/0166844 A1	8/2005	Gralenski
7,495,389 B2	2/2009	Noguchi et al.	2005/0183670 A1	8/2005	Grantham et al.
7,601,439 B2	10/2009	Chun et al.	2005/0186330 A1	8/2005	Kim et al.
7,776,457 B2	8/2010	Lee et al.	2005/0213021 A1	9/2005	Myoung
7,872,256 B2	1/2011	Sung et al.	2005/0217584 A1	10/2005	Abiko et al.
7,910,386 B2	3/2011	Shiang et al.	2005/0229848 A1	10/2005	Shinriki et al.
7,964,037 B2	6/2011	Fukuda et al.	2005/0244580 A1	11/2005	Cok et al.
8,022,448 B1	9/2011	Luu et al.	2005/0263074 A1	12/2005	Masuda et al.
8,128,753 B2	3/2012	Bulovic et al.	2006/0011136 A1	1/2006	Yamazaki et al.
8,137,466 B2	3/2012	Kang et al.	2006/0012771 A1	1/2006	Jeong
8,188,476 B2	5/2012	Takagi et al.	2006/0022590 A1	2/2006	Azia et al.
8,193,011 B2	6/2012	Kang et al.	2006/0040132 A1	2/2006	Liao et al.
8,673,077 B2	3/2014	Sonoda et al.	2006/0045958 A1	3/2006	Abiko et al.
2001/0004186 A1	6/2001	Song et al.	2006/0066231 A1	3/2006	Nishikawa et al.
2001/0006827 A1	7/2001	Yamazaki et al.	2006/0090705 A1	5/2006	Kim
2001/0019807 A1	9/2001	Yamada et al.	2006/0102078 A1	5/2006	Fairbairn et al.
2001/0026638 A1	10/2001	Sangu et al.	2006/0110544 A1	5/2006	Kim et al.
2001/0034175 A1	10/2001	Miyazaki et al.	2006/0113907 A1	6/2006	Im et al.
2002/0011785 A1	1/2002	Tang et al.	2006/0115585 A1	6/2006	Bulovic et al.
2002/0017245 A1	2/2002	Tsubaki et al.	2006/0130766 A1	6/2006	Kim et al.
2002/0033136 A1	3/2002	Savage et al.	2006/0144325 A1	7/2006	Jung et al.
2002/0036759 A1	3/2002	Ise et al.	2006/0152641 A1	7/2006	Brody
2002/0050061 A1	5/2002	Komyoji et al.	2006/0164786 A1	7/2006	Kobayashi et al.
2002/0076847 A1	6/2002	Yamada et al.	2006/0169211 A1	8/2006	Kim et al.
2002/0168577 A1	11/2002	Yoon	2006/0174829 A1	8/2006	An et al.
2002/0179013 A1	12/2002	Kido et al.	2006/0205101 A1	9/2006	Lee et al.
2002/0187253 A1	12/2002	Marcus et al.	2006/0244696 A1	11/2006	Jung et al.
2002/0194727 A1	12/2002	Cho et al.	2006/0267294 A1	11/2006	Busse et al.
2002/0197393 A1	12/2002	Kuwabara	2006/0269671 A1	11/2006	Kim et al.
2003/0021886 A1	1/2003	Baele	2006/0272572 A1	12/2006	Uematsu et al.
2003/0101932 A1	6/2003	Kang	2006/0278522 A1	12/2006	Kim et al.
2003/0101937 A1	6/2003	Van Slyke et al.	2006/0278945 A1	12/2006	Sakurai
2003/0117602 A1	6/2003	Kobayashi et al.	2006/0280588 A1	12/2006	Blonigan et al.
2003/0118950 A1	6/2003	Chao et al.	2007/0009552 A1	1/2007	Whitehead et al.
2003/0124764 A1	7/2003	Yamazaki et al.	2007/0009652 A1	1/2007	Manz et al.
2003/0151637 A1	8/2003	Nakamura et al.	2007/0017445 A1	1/2007	Takehara et al.
2003/0164934 A1	9/2003	Nishi et al.	2007/0022955 A1	2/2007	Bender et al.
2003/0168013 A1	9/2003	Freeman et al.	2007/0024185 A1	2/2007	Kitamura et al.
2003/0173896 A1	9/2003	Grushin et al.	2007/0046185 A1	3/2007	Kim
2003/0221614 A1	12/2003	Kang et al.	2007/0046913 A1	3/2007	Shibazaki
2003/0221620 A1	12/2003	Yamazaki	2007/0054044 A1	3/2007	Shimosaki et al.
			2007/0075955 A1	4/2007	Jung et al.
			2007/0077358 A1	4/2007	Jeong et al.
			2007/0148337 A1	6/2007	Nichols et al.
			2007/0148348 A1	6/2007	Huh et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

2007/0157879	A1	7/2007	Yotsuya et al.	
2007/0158471	A1	7/2007	Park et al.	
2007/0163497	A1	7/2007	Grace et al.	
2007/0178708	A1	8/2007	Ukigaya	
2007/0190235	A1	8/2007	Yamazaki et al.	
2007/0195844	A1	8/2007	Ma et al.	
2007/0231460	A1	10/2007	Ukigaya	
2007/0275497	A1	11/2007	Kwack et al.	
2007/0297887	A1	12/2007	Tanaka	
2008/0018236	A1	1/2008	Arai et al.	
2008/0038935	A1	2/2008	Baude et al.	
2008/0057183	A1	3/2008	Spindler et al.	
2008/0100204	A1	5/2008	Kim	
2008/0115729	A1	5/2008	Oda et al.	
2008/0118743	A1	5/2008	Lee et al.	
2008/0129194	A1	6/2008	Abe et al.	
2008/0131587	A1	6/2008	Boroson et al.	
2008/0145521	A1	6/2008	Guo et al.	
2008/0174235	A1	7/2008	Kim et al.	
2008/0202421	A1	8/2008	Allen et al.	
2008/0216741	A1	9/2008	Ling	
2008/0238294	A1	10/2008	Xu et al.	
2008/0251785	A1	10/2008	Noh et al.	
2008/0286461	A1	11/2008	Noguchi et al.	
2008/0290791	A1	11/2008	Lee et al.	
2008/0298947	A1	12/2008	Yeo et al.	
2008/0309718	A1	12/2008	Oya et al.	
2009/0001882	A1	1/2009	Park et al.	
2009/0014412	A1	1/2009	Nozawa et al.	
2009/0017192	A1	1/2009	Matsuura	
2009/0027767	A1	1/2009	Souriau et al.	
2009/0124033	A1	5/2009	Moriyama	
2009/0133629	A1	5/2009	Kamikawa et al.	
2009/0153033	A1	6/2009	Lee et al.	
2009/0165713	A1 *	7/2009	Kim et al.	118/719
2009/0169868	A1	7/2009	Haglund, Jr. et al.	
2009/0170230	A1	7/2009	Kidu et al.	
2009/0181163	A1	7/2009	Uetake	
2009/0208754	A1	8/2009	Chu et al.	
2009/0220691	A1	9/2009	Kim	
2009/0229524	A1	9/2009	Kim et al.	
2009/0232976	A1	9/2009	Yoon et al.	
2009/0269881	A1	10/2009	Furuta et al.	
2009/0277386	A1	11/2009	Takagi et al.	
2009/0279173	A1	11/2009	Chui et al.	
2009/0302750	A1	12/2009	Jun et al.	
2009/0304906	A1	12/2009	Suduo et al.	
2009/0304924	A1	12/2009	Gadgil	
2009/0308317	A1	12/2009	Sone et al.	
2009/0315456	A1	12/2009	Furukawa et al.	
2010/0001301	A1	1/2010	Karg et al.	
2010/0055810	A1 *	3/2010	Sung et al.	438/22
2010/0086672	A1	4/2010	Von Drasek et al.	
2010/0089443	A1	4/2010	Bloomstein et al.	
2010/0090594	A1	4/2010	Choi et al.	
2010/0130020	A1	5/2010	Kim et al.	
2010/0156279	A1	6/2010	Tamura et al.	
2010/0165454	A1	7/2010	Suetsugu et al.	
2010/0170439	A1	7/2010	Negishi	
2010/0192856	A1	8/2010	Sung et al.	
2010/0196607	A1	8/2010	Carlson et al.	
2010/0248416	A1	9/2010	Priddy et al.	
2010/0255198	A1	10/2010	Cleary et al.	
2010/0271602	A1	10/2010	Hanazaki	
2010/0275842	A1	11/2010	Park et al.	
2010/0297348	A1	11/2010	Lee et al.	
2010/0297349	A1	11/2010	Lee et al.	
2010/0310768	A1	12/2010	Lee et al.	
2010/0328197	A1	12/2010	Lee et al.	
2010/0330265	A1	12/2010	Lee et al.	
2010/0330712	A1	12/2010	Lee et al.	
2011/0033619	A1	2/2011	Lee et al.	
2011/0033621	A1	2/2011	Lee et al.	
2011/0042659	A1	2/2011	Kim et al.	
2011/0045617	A1	2/2011	Kang et al.	

2011/0048320	A1	3/2011	Choi et al.	
2011/0052791	A1	3/2011	Lee et al.	
2011/0052795	A1	3/2011	Choi et al.	
2011/0053296	A1	3/2011	Lee et al.	
2011/0053300	A1	3/2011	Ryu et al.	
2011/0068331	A1	3/2011	Koh et al.	
2011/0123707	A1 *	5/2011	Lee et al.	427/66
2011/0139069	A1	6/2011	Ahn et al.	
2011/0165327	A1	7/2011	Park et al.	
2011/0168986	A1	7/2011	Lee et al.	
2011/0220019	A1	9/2011	Lee et al.	
2011/0220022	A1	9/2011	Hong et al.	
2011/0241438	A1	10/2011	Kim et al.	
2011/0262625	A1	10/2011	Park et al.	
2011/0266944	A1	11/2011	Song et al.	
2012/0006259	A1	1/2012	Sung et al.	
2012/0009328	A1	1/2012	Ryu et al.	
2012/0009332	A1	1/2012	Kim et al.	
2012/0009706	A1	1/2012	Choi et al.	
2012/0028390	A1	2/2012	Lee et al.	
2012/0068199	A1	3/2012	Sung et al.	
2012/0068201	A1	3/2012	Sung et al.	
2012/0070928	A1	3/2012	Kim et al.	
2012/0083061	A1	4/2012	Kang et al.	
2012/0097992	A1	4/2012	Jeong	
2012/0100282	A1	4/2012	Lee et al.	
2012/0103253	A1	5/2012	Park et al.	
2012/0132137	A1	5/2012	Oh et al.	
2012/0145077	A1	6/2012	Chang et al.	
2012/0148743	A1	6/2012	Bulovic et al.	
2012/0174865	A1	7/2012	Choi et al.	
2012/0175605	A1	7/2012	Shin et al.	
2012/0183676	A1	7/2012	Sonoda et al.	
2012/0214263	A1	8/2012	Yamazaki et al.	
2012/0299016	A1	11/2012	Choi	
2012/0299023	A1	11/2012	Lee et al.	
2012/0299024	A1	11/2012	Lee et al.	
2012/0301614	A1	11/2012	Choi et al.	
2012/0301986	A1	11/2012	Choi et al.	
2012/0313251	A1	12/2012	Kato	
2013/0001528	A1	1/2013	Chang et al.	
2013/0008379	A1	1/2013	Chang et al.	
2013/0032829	A1	2/2013	Sung et al.	
2013/0157016	A1	6/2013	Kim	
2013/0217164	A1	8/2013	Kang et al.	
2013/0291796	A1	11/2013	Inoue et al.	
2013/0298829	A1	11/2013	Jo et al.	
2013/0341598	A1	12/2013	Chang et al.	
2014/0010957	A1	1/2014	Inoue et al.	
2014/0014917	A1	1/2014	Lee et al.	
2014/0014918	A1	1/2014	Han	
2014/0014920	A1	1/2014	Lee	
2014/0014921	A1	1/2014	Choi	
2014/0014924	A1	1/2014	Oh et al.	
2014/0014929	A1	1/2014	Lee et al.	
2014/0034917	A1	2/2014	Lee et al.	
2014/0045343	A1	2/2014	Choi et al.	
2014/0077168	A1	3/2014	Kim	
2014/0084262	A1	3/2014	Kim	
2014/0084263	A1	3/2014	Jin et al.	
2014/0110680	A1	4/2014	Choe	
2014/0131667	A1	5/2014	Chang	

FOREIGN PATENT DOCUMENTS

CN	1500904	A	6/2004
CN	1556872	A	12/2004
CN	1607868	A	4/2005
CN	1682569	A	10/2005
CN	1704501	A	12/2005
CN	1814854	A	8/2006
CN	1841696	A	10/2006
EP	1 413 644	A2	4/2004
EP	1 418 250	A2	5/2004
EP	1 518 940	A1	3/2005
EP	2354270	A1	8/2011
JP	57-194252	A2	11/1982
JP	2-247372		10/1990
JP	04-272170		9/1992

(56)

References Cited

FOREIGN PATENT DOCUMENTS

JP	5-22405	U1	3/1993	JP	2008-300056	12/2008
JP	5-98425	A2	4/1993	JP	2009-019243	1/2009
JP	5-230628	A2	9/1993	JP	2009-24208	A2 2/2009
JP	8-27568	A2	1/1996	JP	2009-049223	3/2009
JP	9-95776	A2	4/1997	JP	2009-81165	A2 4/2009
JP	10-50478		2/1998	JP	2009-87910	4/2009
JP	10-120171		5/1998	JP	2009-117231	A2 5/2009
JP	10-270535		10/1998	JP	2010-159167	A2 7/2010
JP	11-144865		5/1999	JP	2010-261081	A2 11/2010
JP	2000-068054		3/2000	JP	2011-47035	3/2011
JP	2000-282219		10/2000	JP	2011-146377	7/2011
JP	2000-323277		11/2000	JP	2012-92448	5/2012
JP	2001-28325	A2	1/2001	JP	2012-211352	11/2012
JP	2001-052862		2/2001	KR	1997-0008709	A 2/1997
JP	2001-093667		4/2001	KR	10-0257219	B1 2/2000
JP	2002-075638	A	3/2002	KR	10-2000-0019254	4/2000
JP	2002-175878		6/2002	KR	10-2000-0023929	5/2000
JP	2002-348659	A2	12/2002	KR	2001-0024652	3/2001
JP	2003-003250		1/2003	KR	2001-0030175	A 4/2001
JP	2003-077662		3/2003	KR	10-2001-0039298	A 5/2001
JP	2003-157973		5/2003	KR	10-2001-0059939	7/2001
JP	2003-197531	A2	7/2003	KR	10-2001-0092914	A 10/2001
JP	2003-297562		10/2003	KR	2001-0093666	A 10/2001
JP	2003-321767		11/2003	KR	20-0257218	11/2001
JP	2003-347394	A2	12/2003	KR	10-2002-0000201	1/2002
JP	2004-035964	A2	2/2004	KR	2002-0001555	1/2002
JP	2004-043898		2/2004	KR	2002-0025760	4/2002
JP	2004-76150	A2	3/2004	KR	10-2002-0050922	6/2002
JP	2004-91858	A2	3/2004	KR	10-2002-0090934	12/2002
JP	2004-103269		4/2004	KR	10-2002-0091457	A 12/2002
JP	2004-103341		4/2004	KR	10-2003-0001745	1/2003
JP	2004-107764	A2	4/2004	KR	2003-0034730	A 5/2003
JP	2004-137583	A2	5/2004	KR	10-2003-0043012	A 6/2003
JP	2004-143521	A2	5/2004	KR	2003-0046090	6/2003
JP	2004-169169	A	6/2004	KR	2003-0069684	A 8/2003
JP	2004-199919		7/2004	KR	10-0405080	B1 11/2003
JP	2004-225058		8/2004	KR	10-0406059	B1 11/2003
JP	2004-342455	A2	12/2004	KR	10-2003-0091947	12/2003
JP	2004-349101	A	12/2004	KR	10-2003-0093959	12/2003
JP	2004-355975		12/2004	KR	2003-0094033	A 12/2003
JP	2005-044592		2/2005	KR	10-2004-0014258	A 2/2004
JP	2005-101505		4/2005	KR	20-0342433	Y1 2/2004
JP	2005-122980	A	5/2005	KR	10-2004-0034537	4/2004
JP	2005-163099		6/2005	KR	10-2004-0039910	A 5/2004
JP	2005-165015	A2	6/2005	KR	10-0430336	B1 5/2004
JP	2005-174843	A	6/2005	KR	10-2004-0050045	6/2004
JP	2005-206939	A2	8/2005	KR	10-2004-0069281	8/2004
JP	2005-213616	A2	8/2005	KR	10-2004-0084747	10/2004
JP	2005-235568		9/2005	KR	10-2004-0087142	A 10/2004
JP	2005-293968		10/2005	KR	10-2004-0110718	A 12/2004
JP	2005-296737		10/2005	KR	10-0463212	B1 12/2004
JP	2006-28583	A2	2/2006	KR	10-2005-0018234	A 2/2005
JP	2006-172930	A2	6/2006	KR	10-2005-0024324	A 3/2005
JP	2006-176809	A2	7/2006	KR	10-2005-0028943	3/2005
JP	2006-210038	A	8/2006	KR	10-2005-0039140	A 4/2005
JP	2006-210038	A2	8/2006	KR	10-0483487	B1 4/2005
JP	2006-219760		8/2006	KR	10-2005-0062853	A 6/2005
JP	2006-275433		10/2006	KR	10-2005-0082644	A 8/2005
JP	2006-292955	A2	10/2006	KR	10-0520159	B1 10/2005
JP	2006-307247	A2	11/2006	KR	10-0532657	B1 12/2005
JP	2007-047293		2/2007	KR	10-2006-0006178	A 1/2006
JP	2007-66862		3/2007	KR	10-2006-0008602	1/2006
JP	2007-146219		6/2007	KR	10-2006-0018745	3/2006
JP	2007-157886		6/2007	KR	10-2006-0020050	3/2006
JP	2007-186740		7/2007	KR	10-2006-0045225	A 5/2006
JP	2007-242436		9/2007	KR	10-2006-0049050	5/2006
JP	2007-291506	A2	11/2007	KR	10-2006-0051746	A 5/2006
JP	2008-19477	A2	1/2008	KR	10-2006-0053926	A 5/2006
JP	2008-108628		5/2008	KR	10-2006-0056706	5/2006
JP	2008-121098		5/2008	KR	10-2006-0058459	5/2006
JP	2008-521165	A	6/2008	KR	10-2006-0059068	6/2006
JP	2008-156686		7/2008	KR	10-2006-0059323	A 6/2006
JP	2008-196003		8/2008	KR	10-2006-0060994	6/2006
JP	2008-248301	A2	10/2008	KR	10-2006-0065978	6/2006
JP	2008-274373		11/2008	KR	10-2006-0073367	6/2006
				KR	10-2006-0077887	A 7/2006
				KR	10-2006-0080475	7/2006
				KR	10-2006-0080481	7/2006
				KR	10-2006-0080482	7/2006

(56)

References Cited

FOREIGN PATENT DOCUMENTS

KR 10-2006-0081943 A 7/2006
 KR 10-2006-0083510 7/2006
 KR 10-2006-0092387 8/2006
 KR 10-2006-0098755 9/2006
 KR 10-2006-0104288 A 10/2006
 KR 10-2006-0104675 10/2006
 KR 10-2006-0104677 10/2006
 KR 10-2006-0109561 A 10/2006
 KR 10-2006-0109627 10/2006
 KR 10-0635903 10/2006
 KR 10-2006-0114462 A 11/2006
 KR 10-2006-0114477 A 11/2006
 KR 10-2006-0114573 A 11/2006
 KR 10-0645719 11/2006
 KR 10-0646160 B1 11/2006
 KR 10-2006-0123944 A 12/2006
 KR 10-0687007 B1 2/2007
 KR 10-2007-0025164 3/2007
 KR 10-0696547 B1 3/2007
 KR 10-0696550 B1 3/2007
 KR 10-0697663 3/2007
 KR 10-0698033 B1 3/2007
 KR 10-0700466 B1 3/2007
 KR 10-2007-0035796 4/2007
 KR 10-2007-0037848 A 4/2007
 KR 10-0711885 B1 4/2007
 KR 10-2007-0050793 5/2007
 KR 10-2009-0053417 A 5/2007
 KR 10-0723627 B1 5/2007
 KR 10-2007-0056190 A 6/2007
 KR 10-0726132 B1 6/2007
 KR 10-0736218 B1 7/2007
 KR 10-0739309 7/2007
 KR 10-0741142 B1 7/2007
 KR 10-2007-0078713 8/2007
 KR 10-2007-0080635 8/2007
 KR 10-2007-0091437 A 9/2007
 KR 10-2006-0028115 10/2007
 KR 10-2007-0097218 A 10/2007
 KR 10-2007-0098122 A 10/2007
 KR 10-2007-0101842 10/2007
 KR 10-2007-0105595 10/2007
 KR 10-0768212 B1 10/2007
 KR 10-0770653 B1 10/2007
 KR 10-2007-0112668 11/2007
 KR 10-2007-0114094 A 11/2007
 KR 10-0787457 B1 12/2007
 KR 10-2008-0001184 1/2008
 KR 10-2008-0003720 A 1/2008
 KR 10-2008-0007896 A 1/2008
 KR 10-2008-0009285 A 1/2008
 KR 10-0797787 B1 1/2008
 KR 10-0800125 1/2008
 KR 10-0815265 3/2008
 KR 10-2008-0036983 A 4/2008
 KR 10-0823508 B1 4/2008
 KR 10-0823511 B1 4/2008
 KR 10-2008-0044239 A 5/2008
 KR 10-2008-0044775 A 5/2008
 KR 10-2008-0046761 A 5/2008
 KR 10-0827760 B1 5/2008
 KR 10-2008-0048653 6/2008
 KR 10-2008-0055124 A 6/2008
 KR 10-2008-0057159 A 6/2008
 KR 10-0839380 B1 6/2008
 KR 10-2008-0060400 7/2008
 KR 10-2008-0061132 7/2008
 KR 10-2008-0061666 A 7/2008
 KR 10-2008-0061774 A 7/2008
 KR 10-2008-0062212 7/2008
 KR 10-2008-0076574 A 8/2008
 KR 10-2008-0088737 A 10/2008
 KR 10-2008-0104479 A 12/2008
 KR 10-2008-0104695 A 12/2008
 KR 10-2008-0109559 A 12/2008

KR 10-2009-0017910 A 2/2009
 KR 10-0889872 B1 3/2009
 KR 10-2009-0038733 4/2009
 KR 10-2009-0040618 A 4/2009
 KR 10-2009-0047953 A 5/2009
 KR 10-2009-0052155 A 5/2009
 KR 10-2009-0052828 A 5/2009
 KR 10-0899279 B1 5/2009
 KR 10-2009-0066996 A 6/2009
 KR 10-2009-0075887 A 7/2009
 KR 10-2009-0079765 A 7/2009
 KR 10-2009-0081717 A 7/2009
 KR 10-0908232 B1 7/2009
 KR 10-2009-0093161 9/2009
 KR 10-2009-0094911 A 9/2009
 KR 10-2009-0097453 9/2009
 KR 10-2009-0107702 10/2009
 KR 10-0922763 A 10/2009
 KR 10-2010-0000128 1/2010
 KR 10-2010-0000129 1/2010
 KR 10-2010-0002381 A 1/2010
 KR 10-2010-0026655 3/2010
 KR 10-2010-0038088 A 4/2010
 KR 10-2010-0044606 A 4/2010
 KR 10-2010-0047796 A 5/2010
 KR 10-0961110 B1 6/2010
 KR 10-2010-0090070 A 8/2010
 KR 10-2010-0099806 A 9/2010
 KR 10-2010-0119368 A 11/2010
 KR 10-2010-0126125 A 12/2010
 KR 10-2010-0128589 A 12/2010
 KR 10-2010-0130786 A 12/2010
 KR 10-2010-0133678 A 12/2010
 KR 10-2010-0138139 A 12/2010
 KR 10-1017654 B1 2/2011
 KR 10-2011-0021090 A 3/2011
 KR 10-2011-0022512 A 3/2011
 KR 10-2011-0032589 A 3/2011
 KR 10-2011-0082418 A 7/2011
 KR 10-2011-0101767 A 9/2011
 KR 10-2011-0110525 A 10/2011
 KR 10-2011-0120213 A 11/2011
 KR 10-2011-0138787 A 12/2011
 KR 10-2012-0006322 A 1/2012
 KR 10-2012-0006324 A 1/2012
 KR 10-2012-0012300 2/2012
 KR 10-2012-0042155 A 5/2012
 KR 10-2012-0065789 A 6/2012
 KR 10-2012-0080855 A 7/2012
 KR 10-2012-0081811 A 7/2012
 KR 10-1193186 B1 10/2012
 KR 10-2012-0131545 A 12/2012
 KR 10-2013-0007308 A 1/2013
 WO WO99/25894 5/1999
 WO 03043067 A1 5/2003
 WO WO2004016406 A1 2/2004
 WO 2008004792 A1 1/2008

OTHER PUBLICATIONS

Patent Abstracts of Japan, and English machine translation of Japanese Publication 2003-003250, 25 pages.

Korean Patent Abstracts, Publication No. 1020020086047, dated Nov. 18, 2002, for corresponding Korean Patent 10-0405080.

Korean Patent Abstracts, Publication No. 1020020088662, dated Nov. 29, 2002, for corresponding Korean Patent 10-0463212.

Korean Patent Abstracts, Publication No. 1020050045619, dated May 17, 2005, for corresponding Korean Patent 10-0520159.

Korean Patent Abstracts, Publication No. 1020040062203, dated Jul. 7, 2004, for corresponding Korean Patent 10-0646160.

Korean Patent Abstracts, Publication No. 1020060101987, dated Sep. 27, 2006, for corresponding Korean Patent 10-0687007.

Korean Patent Abstracts, Publication No. 1020020056238, dated Jul. 10, 2002, for corresponding Korean Patent 10-0698033.

Korean Patent Abstracts, Publication No. 1020050078637, dated Aug. 5, 2005, for corresponding Korean Patent 10-0700466.

Korean Patent Abstracts, Publication No. 1020070025164, dated Mar. 8, 2007, for corresponding Korean Patent 10-0711885.

(56)

References Cited

OTHER PUBLICATIONS

Korean Patent Abstracts, Publication No. 1020020034272, dated May 9, 2002, for corresponding Korean Patent 10-0726132.
 Korean Patent Abstracts, Publication No. 1020060126267, dated Dec. 7, 2006, for corresponding Korean Patent 10-0797787.
 Korean Patent Abstracts, Publication No. 1020010062735, dated Jul. 7, 2001, for corresponding Korean Patent 10-0827760.
 Korean Patent Abstracts, Publication No. 1020080038650, dated May 7, 2008, for corresponding Korean Patent 10-0839380.
 Korean Patent Abstracts, Publication No. 1020070050793, dated May 16, 2007, for corresponding Korean Patent 10-0815265.
 Korean Patent Abstracts, Publication No. 102000-0019254 dated Apr. 6, 2000, for corresponding Korean Patent No. 10-2007-0101842.
 English Abstract, Publication No. KR20080002189 dated Jan. 4, 2008, for corresponding Korean Patent 10-0800125.
 Korean Notice of Allowance dated Nov. 25, 2011 for Korean Patent Application No. 10-2010-0014277, 5 pages.
 Korean Notice of Allowance dated Sep. 28, 2011 for Korean Patent Application No. 10-2009-0042357, 5 pages.
 Korean Notice of Allowance dated Jan. 13, 2012 for Korean Patent Application No. 10-2009-0056529, 5 pages.
 Korean Office action dated Feb. 1, 2012 for Korean Application No. 10-2010-0011196, 4 pages.
 Korean Office action dated Feb. 1, 2012 for Korean Application No. 10-2010-0013848, 3 pages.
 Japanese Office Action, dated Aug. 21, 2012, corresponding to JP 2010-145075.
 Japanese Office Action, dated Sep. 4, 2012, corresponding to JP 2010-152846.
 Korean Office Notice of Allowance, dated Sep. 1, 2012, corresponding to KR 10-2010-0013848.
 Korean Office Notice of Allowance, dated Sep. 1, 2012, corresponding to KR 10-2010-0009160.
 Korean Office Action, dated Sep. 1, 2012, corresponding to KR 10-2010-0010136.
 Korean Office Notice of Allowance dated Apr. 30, 2012, for Korean Patent application 10-2010-0066992.
 Korean Office Notice of Allowance dated Jul. 20, 2012, for Korean Patent application 10-2010-0003545.
 U.S. Notice of Allowance, dated Mar. 18, 2013, corresponding to U.S. Appl. No. 12/795,001.
 U.S. Office action dated Dec. 20, 2012, corresponding to U.S. Appl. No. 12/984,289.
 U.S. Office action dated Feb. 26, 2013, corresponding to U.S. Appl. No. 12/794,093.
 U.S. Office action dated Mar. 15, 2013, corresponding to U.S. Appl. No. 12/813,786.
 U.S. Office action dated Mar. 18, 2013, corresponding to U.S. Appl. No. 12/984,231.
 U.S. Office action dated Mar. 19, 2013, corresponding to U.S. Appl. No. 13/194,759.
 U.S. Office action dated Mar. 22, 2013, corresponding to U.S. Appl. No. 12/987,569.
 U.S. Office action dated May 7, 2013, corresponding to U.S. Appl. No. 12/820,270.
 U.S. Office action dated Jun. 11, 2013, corresponding to U.S. Appl. No. 12/862,125.
 U.S. Office action dated Jun. 26, 2013, corresponding to U.S. Appl. No. 12/794,093.
 U.S. Office action dated Jul. 17, 2013, corresponding to U.S. Appl. No. 12/984,231.
 U.S. Office action dated Aug. 13, 2013, corresponding to U.S. Appl. No. 13/194,759.
 U.S. Office action dated Oct. 11, 2013, corresponding to U.S. Appl. No. 12/907,396.
 U.S. Office action dated Oct. 21, 2013, corresponding to U.S. Appl. No. 12/987,569.
 European Search Report dated May 13, 2011 for European Application No. 11250019.4 (6 pages).

European Search Report dated May 20, 2011 for European Application No. 10251404.9 (12 pages).
 European Search Report dated May 27, 2011 for European Application No. 10251514.5 (11 pages).
 European Search Report dated Sep. 6, 2010 for European Application No. 10250962.7 (5 pages).
 Japanese Patent Office Action dated Jan. 22, 2013 for Japanese Application No. 2010-116470, (3 pages).
 Japanese Patent Office Action dated Jan. 8, 2013 for Japanese Application No. 2011-000180 (3 pages).
 Japanese Patent Office Action dated Mar. 19, 2013 for Japanese Application No. 2011-097909, (3 pages).
 JPO Office action dated Apr. 1, 2014, for Japanese Patent application 2010-286245 (4 pages).
 JPO Office action dated Feb. 25, 2014, for corresponding Japanese Patent application 2013-128405 (3 pages).
 JPO Office action dated Jan. 28, 2014, for corresponding Japanese Patent application 2011-097909 (4 pages).
 KIPO Notice of Allowance dated Apr. 26, 2012 for Korean Application No. 10-2010-0066991 (5 pages).
 KIPO Notice of Allowance dated Aug. 24, 2012, issued to KR 10-2010-0066993 (5 pages).
 KIPO Notice of Allowance dated Oct. 27, 2011 for Korean Application No. 10-2010-0002381 (5 pages).
 KIPO Notice of Allowance dated Oct. 31, 2011, for Korean Patent application 10-2010-0014273, (5 pages).
 KIPO Notice of Allowance dated Sep. 1, 2012, for Korean Patent application 10-2010-0013847 (5 pages).
 KIPO Notice of Allowance dated Sep. 23, 2011 for Korean Application No. 10-2009-0055473 (5 pages).
 KIPO Notice of Allowance dated Sep. 28, 2011 for Korean Application No. 10-2009-0045201 (5 pages).
 KIPO Notice of Allowance dated Sep. 28, 2011 for Korean Application No. 10-2009-0052359 (5 pages).
 KIPO Notice of Allowance, dated Sep. 1, 2012, issued to KR 10-2010-0014276 (5 pages).
 KIPO Office action dated Apr. 2, 2012, issued to KR 10-2010-0066993 (4 pages).
 KIPO Office action dated Apr. 4, 2012, issued in KR Application No. 10-2009-0112796 (5 pages).
 KIPO Office Action dated Apr. 9, 2012 for Korean Application No. 10-2010-0031556 (4 pages).
 KIPO Office action dated Aug. 1, 2011, issued to KR 10-2009-0074001 (3 pages).
 KIPO Office Action dated Aug. 28, 2012, issued to KR 10-2010-0014274 (5 pages).
 KIPO Office action dated Feb. 1, 2012, for Korean Patent application 10-2010-0013847 (5 pages).
 KIPO Office action dated Feb. 1, 2012, issued to KR 10-2010-0014272 (4 pages).
 KIPO Office Action dated Feb. 6, 2012 for Korean Application No. 10-2010-0011480 (8 pages).
 KIPO Office Action dated Feb. 6, 2012 for Korean Application No. 10-2010-0011481 (7 pages).
 KIPO Office Action dated Feb. 6, 2012, issued to KR 10-2010-0014274 (9 pages).
 KIPO Office Action dated Feb. 6, 2012, issued to KR 10-2010-0021835 (4 pages).
 KIPO Office action dated Jan. 6, 2012, issued to KR Application No. 10-2010-0000897 (4 pages).
 KIPO Office action dated Jul. 1, 2011, issued to KR Application No. 10-2009-0072111 (4 pages).
 KIPO Office action dated Jun. 1, 2011, issued to KR Application No. 10-2009-0050528 (4 pages).
 KIPO Office action dated Mar. 21, 2012, issued to KR Application No. 10-2010-0065465 (5 pages).
 KIPO Registration Determination Certificate dated Jul. 2, 2012, for Korean Application No. 10-2010-0011480 (5 pages).
 KIPO Registration Determination Certificate dated Jul. 2, 2012, for Korean Application No. 10-2010-0011481 (5 pages).
 KIPO Registration Determination Certificate dated Nov. 30, 2011, for Korean application 10-2009-0056530 (5 pages).

(56)

References Cited

OTHER PUBLICATIONS

KIPO Registration Determination Certificate, dated Jul. 20, 2012, issued to KR Application No. 10-2010-0000897 (5 pages).
 Korean Registration Certificate dated Sep. 28, 2011 for Korean Application No. 10-2009-0045200 (5 pages).
 SIPO Certificate of Patent dated Aug. 14, 2013, for Chinese application 201010266406.6, (36 pages).
 SIPO Certificate of Patent dated Jul. 31, 2013, corresponding to Chinese Patent application 201110029291.3, (31 pages).
 SIPO Office action dated Dec. 17, 2013, for Chinese Patent application 201010216896.9 (6 pages).
 SIPO Office action dated Feb. 14, 2014, for corresponding Chinese Patent application 201010189614.0 (16 pages).
 SIPO Office action dated Mar. 11, 2014, for corresponding Chinese Patent application 201010189581.X (9 pages).
 SIPO Office Action dated May 29, 2013, for Chinese Application No. 201010189614.0 (12 pages).
 SIPO Office Action dated Nov. 28, 2012 for Chinese Application No. 201110029291.3 (11 pages).
 SIPO Office Action dated Oct. 9, 2012 for Chinese Application No. 201010266406.6 (6 pages).
 Taiwanese Office action dated Apr. 14, 2014, for Taiwanese Patent application 100114360 (20 pages).
 Taiwanese Office action dated Dec. 20, 2013, for Taiwanese Patent application 099116077 (8 pages).
 U.S. Interview Summary dated Mar. 11, 2014 for U.S. Appl. No. 12/813,786 (4 pages).
 U.S. Notice of Allowance dated Feb. 20, 2014, issued to U.S. Appl. No. 12/907,396 (13 pages).
 U.S. Notice of Allowance dated Feb. 28, 2014, issued to U.S. Appl. No. 13/279,077 (12 pages).
 U.S. Notice of Allowance dated Jun. 11, 2014, issued to U.S. Appl. No. 13/468,835 (62 pages).
 U.S. Notice of Allowance dated Jun. 30, 2014, issued to U.S. Appl. No. 12/907,396 (40 pages).
 U.S. Notice of Allowance dated May 9, 2014 for U.S. Appl. No. 13/194,759 (27 pages).
 U.S. Office action dated Apr. 1, 2013, issued to U.S. Appl. No. 12/784,774 (44 pages).
 U.S. Office action dated Apr. 18, 2014, issued to U.S. Appl. No. 12/814,816 (9 pages).
 U.S. Office action dated Apr. 29, 2013, issued to U.S. Appl. No. 12/820,355 (31 pages).
 U.S. Office Action dated Aug. 2, 2013 for U.S. Appl. No. 12/868,099 (32 pages).
 U.S. Office action dated Aug. 21, 2013 issued in cross-reference U.S. Appl. No. 12/820,355 (14 pages).
 U.S. Office action dated Aug. 7, 2013, issued to U.S. Appl. No. 13/015,357, (30 pages).
 U.S. Office action dated Aug. 8, 2013, for cross reference U.S. Appl. No. 13/093,707, (7 pages).
 U.S. Office Action dated Dec. 13, 2011 for U.S. Appl. No. 12/849,193 (30 pages).
 U.S. Office action dated Dec. 13, 2013, issued to U.S. Appl. No. 13/180,454 (18 pages).
 U.S. Office action dated Dec. 16, 2013 for U.S. Appl. No. 14/054,536 (35 pages).
 U.S. Office action dated Dec. 17, 2012, issued to U.S. Appl. No. 12/873,556 (37 pages).
 U.S. Office action dated Dec. 2, 2013, issued to U.S. Appl. No. 13/157,220 (33 pages).

U.S. Office action dated Dec. 26, 2012, issued to U.S. Appl. No. 12/815,673 (21 pages).
 U.S. Office action dated Feb. 11, 2014, for cross reference U.S. Appl. No. 13/178,472 (8 pages).
 U.S. Office action dated Feb. 6, 2014, for U.S. Appl. No. 12/984,231 (16 pages).
 U.S. Office action dated Jan. 25, 2013, issued to U.S. Appl. No. 13/015,357 (21 pages).
 U.S. Office action dated Jul. 24, 2013, issued to U.S. Appl. No. 12/784,804, (52 pages).
 U.S. Office action dated Jul. 3, 2013 in U.S. Appl. No. 12/873,689 (48 pages).
 U.S. Office action dated Jul. 5, 2013, issued to U.S. Appl. No. 12/873,556, (17 pages).
 U.S. Office Action dated Jun. 11, 2013 for U.S. Appl. No. 12/979,656 (50 pages).
 U.S. Office action dated Jun. 17, 2013, for cross reference U.S. Appl. No. 13/180,454, (23 pages).
 U.S. Office action dated Jun. 17, 2014, issued to U.S. Appl. No. 13/157,220 (36 pages).
 U.S. Office Action dated Jun. 21, 2011 for U.S. Appl. No. 12/862,153 (21 pages).
 U.S. Office action dated Mar. 17, 2014, for U.S. Appl. No. 12/950,361 (48 pages).
 U.S. Office Action dated Mar. 23, 2012 for U.S. Appl. No. 12/849,193 (17 pages).
 U.S. Office action dated May 21, 2014, issued to U.S. Appl. No. 13/014,225 (15 pages).
 U.S. Office action dated May 22, 2013, for cross reference U.S. Appl. No. 13/219,427, (26 pages).
 U.S. Office action dated May 24, 2013, for U.S. Appl. No. 13/279,077 (20 pages).
 U.S. Office action dated May 24, 2013, issued to U.S. Appl. No. 12/849,092 (31 pages).
 U.S. Office action dated May 6, 2014, issued to U.S. Appl. No. 13/467,998 (21 pages).
 U.S. Office action dated Nov. 20, 2013, for cross reference U.S. Appl. No. 12/868,099, (14 pages).
 U.S. Office action dated Nov. 22, 2013, issued to U.S. Appl. No. 13/198,591, (28 pages).
 U.S. Office action dated Nov. 25, 2013, issued to U.S. Appl. No. 13/176,701, (49 pages).
 U.S. Office action dated Nov. 4, 2013, for U.S. Appl. No. 13/219,427, (26 pages).
 U.S. Office action dated Oct. 1, 2013, issued to U.S. Appl. No. 12/849,092, (13 pages).
 U.S. Office Action dated Oct. 3, 2012 for U.S. Appl. No. 12/869,830 (28 pages).
 U.S. Office action dated Oct. 7, 2013, issued to U.S. Appl. No. 13/279,077, (29 pages).
 U.S. Office action dated Sep. 20, 2013, issued to U.S. Appl. No. 13/014,225, (33 pages).
 U.S. Office action dated Sep. 25, 2013, for U.S. Appl. No. 13/031,756, (34 pages).
 U.S. Office action dated Sep. 27, 2013, issued to U.S. Appl. No. 12/814,816 (19 pages).
 U.S. Patent Office Action dated May 16, 2013, issued to U.S. Appl. No. 13/235,337 (28 pages).
 US Office action dated Sep. 12, 2012, in U.S. Appl. No. 12/815,673 (26 pages).

* cited by examiner

FIG. 1




FIG. 2




FIG. 3A




FIG. 3B




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12





FIG. 13



**PATTERNING SLIT SHEET ASSEMBLY,
ORGANIC LAYER DEPOSITION
APPARATUS, METHOD OF
MANUFACTURING ORGANIC
LIGHT-EMITTING DISPLAY APPARATUS,
AND THE ORGANIC LIGHT-EMITTING
DISPLAY APPARATUS**

CROSS-REFERENCE TO RELATED
APPLICATION

This application claims priority to and the benefit of Korean Patent Application No. 10-2011-0050842, filed on May 27, 2011 in the Korean Intellectual Property Office, the entire content of which is incorporated herein by reference.

BACKGROUND

1. Field

Aspects of embodiments of the present invention relate to a patterning slit sheet assembly, an organic layer deposition apparatus, a method of manufacturing an organic light-emitting display apparatus, and the organic light-emitting display apparatus.

2. Description of the Related Art

Organic light-emitting display apparatuses have a larger viewing angle, better contrast characteristics, and a faster response rate than other display devices, and thus have drawn attention as next-generation display devices.

An organic light-emitting display device includes an intermediate layer, which includes an organic emission layer, between a first electrode and a second electrode that are arranged opposite to each other. The electrodes and the intermediate layers may be formed by various methods, one of which is a deposition method.

Typical high-definition organic light-emitting display apparatuses are relatively large. However, especially on a large substrate, it is difficult to form a thin film, such as the intermediate layer, in a fine pattern, and the luminous efficiency of the organic emission layer included in the intermediate layer may vary according to a deposition process. Thus, manufacturing of conventional organic light-emitting display devices having satisfactory driving voltage, current density, brightness, color purity, light-emission efficiency, and life-span characteristics has been limited.

SUMMARY

According to an aspect of embodiments of the present invention, a patterning slit sheet assembly, an organic layer deposition apparatus, and a method of manufacturing an organic light-emitting display apparatus perform a deposition process to deposit a thin film in a fine pattern. According to another aspect of embodiments of the present invention, an organic light-emitting display apparatus is manufactured having a thin film deposited in a fine pattern.

According to an embodiment of the present invention, a patterning slit sheet assembly for depositing a thin film in a pattern on a substrate spaced apart from the patterning slit sheet assembly by a predetermined distance, at least one of the substrate or the patterning slit sheet assembly being movable relative to the other, includes a patterning slit sheet including a slit unit, and a non-slit region that is located along edges of the slit unit, the patterning slit sheet being smaller than the substrate in at least one of a first direction or a second direction perpendicular to the first direction; a frame combined with the patterning slit sheet to support the patterning

slit sheet; and a shielding unit extending on at least one inner side of the frame and overlapping an area including the edges of the slit unit.

The shielding unit may be arranged on two inner side surfaces that face each other from among inner side surfaces of the frame.

The shielding unit may be formed covering inner side surfaces of the frame.

The slit unit may overlap a deposition area on the substrate, and may be larger than the deposition area.

Inner edges of the shielding unit may correspond to edge portions of a deposition area on the substrate.

According to another embodiment of the present invention, an organic layer deposition apparatus for forming an organic layer on a substrate includes a deposition source for discharging a deposition material; a deposition source nozzle unit arranged at a side of the deposition source and including a plurality of deposition source nozzles arranged in a first direction; and a patterning slit sheet assembly which includes a patterning slit sheet including a slit unit, and a non-slit region that is located along edges of the slit unit, the patterning slit sheet being smaller than the substrate in at least one of the first direction or a second direction perpendicular to the first direction; a frame combined with the patterning slit sheet to support the patterning slit sheet; and a shielding unit extending on at least one inner side of the frame and overlapping an area including the edges of the slit unit, the substrate being spaced apart from the organic layer deposition apparatus by a predetermined distance, and at least one of the substrate or the organic layer deposition apparatus being movable relative to the other.

The shielding unit may be arranged on inner side surfaces which face each other and are positioned in a direction perpendicular to the first direction, from among inner side surfaces of the frame.

Deposition may be performed while the substrate is moved relative to the organic layer deposition apparatus in the first direction.

The deposition source, the deposition source nozzle unit, and the patterning slit sheet assembly may be integrally formed as one body.

The deposition source, the deposition source nozzle unit, and the patterning slit sheet assembly may be integrally connected as one body by at least one connection member that guides movement of the deposition material.

The at least one connection member may seal a space between the deposition source, the deposition source nozzle unit, and the patterning slit sheet assembly.

Deposition source nozzles of the plurality of deposition source nozzles may be tilted at an angle.

The plurality of deposition source nozzles may include deposition source nozzles arranged in two rows in the first direction, and deposition source nozzles of the plurality of deposition source nozzles in the two rows may be tilted toward each other.

According to another embodiment of the present invention, an organic layer deposition apparatus for forming an organic layer on a substrate includes a deposition source for discharging a deposition material; a deposition source nozzle unit arranged at a side of the deposition source and including a plurality of deposition source nozzles arranged in a first direction; a patterning slit sheet assembly which includes a patterning slit sheet including a slit unit, and a non-slit region that is located along edges of the slit unit, the patterning slit sheet being smaller than the substrate in at least one of the first direction or a second direction perpendicular to the first direction; a frame combined with the patterning slit sheet to sup-

port the patterning slit sheet; and a shielding unit extending on at least one inner side of the frame and overlapping an area including the edges of the slit unit; and a barrier plate assembly including a plurality of barrier plates arranged between the deposition source nozzle unit and the patterning slit sheet in the first direction and partitioning a deposition space between the deposition source nozzle unit and the patterning slit sheet assembly into a plurality of sub-deposition spaces, the substrate being spaced apart from the organic layer deposition apparatus by a predetermined distance, and at least one of the substrate or the organic layer deposition apparatus being movable relative to the other.

The shielding unit may be arranged on inner side surfaces which face each other and are positioned in the first direction, from among inner side surfaces of the frame.

Deposition may be performed while the substrate is moved relative to the organic layer deposition apparatus.

The plurality of barrier plates may extend in the second direction.

The barrier plate assembly may include a first barrier plate assembly including a plurality of first barrier plates, and a second barrier plate assembly including a plurality of second barrier plates.

The first barrier plates and the second barrier plates may extend in the second direction.

The first barrier plates may be arranged to respectively correspond to the second barrier plates.

The deposition source may be spaced apart from the barrier plate assembly.

The barrier plate assembly may be spaced apart from the patterning slit sheet assembly.

According to another embodiment of the present invention, a method of manufacturing an organic light-emitting display apparatus includes forming a first electrode on a substrate; forming an intermediate layer including an organic emission layer on the first electrode; and forming a second electrode on the intermediate layer, and the forming of the intermediate layer is performed using an organic layer deposition apparatus including: a deposition source for discharging a deposition material; a deposition source nozzle unit arranged at a side of the deposition source and including a plurality of deposition source nozzles arranged in a first direction; and a patterning slit sheet assembly including: a patterning slit sheet including a slit unit, and a non-slit region that is located along edges of the slit unit, the patterning slit sheet being smaller than the substrate in at least one of the first direction or a second direction perpendicular to the first direction; a frame combined with the patterning slit sheet to support the patterning slit sheet; and a shielding unit extending on at least one inner side of the frame and overlapping an area including the edges of the slit unit, the substrate being spaced apart from the organic layer deposition apparatus by a predetermined distance, and deposition being performed while at least one of the substrate or the organic layer deposition apparatus is moved relative to the other in the first direction.

According to another embodiment of the present invention, a method of manufacturing an organic light-emitting display apparatus includes forming a first electrode on a substrate; forming an intermediate layer including an organic emission layer on the first electrode; and forming a second electrode on the intermediate layer, and the forming of the intermediate layer is performed using an organic layer deposition apparatus including: a deposition source for discharging a deposition material; a deposition source nozzle unit arranged at a side of the deposition source and including a plurality of deposition source nozzles arranged in a first direction; a patterning slit sheet assembly including: a patterning slit sheet

including a slit unit, and a non-slit region that is located along edges of the slit unit, the patterning slit sheet being smaller than the substrate in at least one of the first direction or a second direction perpendicular to the first direction; a frame combined with the patterning slit sheet to support the patterning slit sheet; and a shielding unit extending on at least one inner side of the frame and overlapping an area including the edges of the slit unit; and a barrier plate assembly including a plurality of barrier plates arranged between the deposition source nozzle unit and the patterning slit sheet assembly in the first direction and partitioning a space between the deposition source nozzle unit and the patterning slit sheet assembly into a plurality of sub-deposition spaces, the substrate being spaced apart from the organic layer deposition apparatus by a predetermined distance, and deposition being performed while at least one of the substrate or the organic layer deposition apparatus is moved relative to the other.

According to another embodiment of the present invention, an organic light-emitting display apparatus is manufactured using one of the methods.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and other features of the present invention will become more apparent by describing in further detail some exemplary embodiments thereof with reference to the attached drawings in which:

FIG. 1 is a schematic cross-sectional view of a patterning slit sheet assembly according to an embodiment of the present invention;

FIG. 2 is a plan view of the patterning slit sheet assembly of FIG. 1, viewed in a direction indicated by arrow "A";

FIG. 3A is a perspective view of a frame and a shielding unit of the patterning slit sheet assembly of FIG. 1;

FIG. 3B is a perspective view of a frame and a shielding unit of a patterning slit sheet assembly according to another embodiment of the present invention;

FIG. 4 is a schematic perspective view of an organic layer deposition apparatus according to an embodiment of the present invention;

FIG. 5 is a schematic side sectional view of the organic layer deposition apparatus of FIG. 4;

FIG. 6 is a schematic front sectional view of the organic layer deposition apparatus of FIG. 4;

FIG. 7 is a schematic perspective view of an organic layer deposition apparatus according to another embodiment of the present invention.

FIG. 8 is a schematic perspective view of an organic layer deposition apparatus according to another embodiment of the present invention.

FIG. 9 is a schematic perspective view of an organic layer deposition apparatus according to another embodiment of the present invention.

FIG. 10 is a schematic side sectional view of the organic layer deposition apparatus of FIG. 9;

FIG. 11 is a schematic front sectional view of the organic layer deposition apparatus of FIG. 9;

FIG. 12 is a schematic perspective view of an organic layer deposition apparatus according to another embodiment of the present invention; and

FIG. 13 is a schematic cross-sectional view of an organic light-emitting display device manufactured by using an organic layer deposition apparatus, according to an embodiment of the present invention.

DETAILED DESCRIPTION

Some exemplary embodiments of the present invention will be described more fully hereinafter with reference to the

accompanying drawings; however, embodiments of the present invention may be embodied in different forms and should not be construed as limited to the exemplary embodiments illustrated and set forth herein. Rather, these exemplary embodiments are provided by way of example for understanding of the invention and to convey the scope of the invention to those skilled in the art. As those skilled in the art would realize, the described embodiments may be modified in various ways, all without departing from the spirit or scope of the present invention.

FIG. 1 is a schematic cross-sectional view of a patterning slit sheet assembly 150 according to an embodiment of the present invention; FIG. 2 is a plan view of the patterning slit sheet assembly 150 viewed in a direction indicated by the arrow "A" in FIG. 1; and FIG. 3A is a perspective view of a frame and a shielding unit of the patterning slit sheet assembly 150. FIG. 3B is a perspective view of a frame and a shielding unit of a patterning slit sheet assembly according to another embodiment of the present invention.

Referring to FIG. 1, the patterning slit sheet assembly 150, in one embodiment, includes a patterning slit sheet 151, a frame 154, and a shielding unit 155.

Particularly, FIG. 1 illustrates a deposition process performed on a substrate 500 by using the patterning slit sheet assembly 150, according to an embodiment of the present invention. A deposition source 110 is disposed on a side of (e.g., below) the patterning slit sheet assembly 150, and the substrate 500 is disposed on an opposite side of (e.g., above) the patterning slit sheet assembly 150.

The patterning slit sheet 151, in one embodiment, includes a slit unit 152 and a non-slit region 153. The slit unit 152, in one embodiment, includes a plurality of slits (not shown) formed in a predetermined pattern. For purposes of clarity, the plurality of slits of the slit unit 152 are not particularly illustrated in FIGS. 1 and 2.

A deposition material contained in the deposition source 110 passes through the plurality of slits of the slit unit 152 and is then deposited on the substrate 500.

In the non-slit region 153, any patterns including slits are not formed. The patterning slit sheet 151 may be formed according to one of various methods. For example, the slit unit 152 may be formed by forming the plurality of slits by selectively etching a metal thin film, and the remaining region of the metal thin film that is not etched may be used as the non-slit region 153.

The patterning slit sheet 151, in one embodiment, is combined with the frame 154. The frame 154 is formed in a lattice shape, similar to a window frame. The frame 154 may be combined with one surface of the non-slit region 153 of the patterning slit sheet 151. In one embodiment, the frame 154 and the patterning slit sheet 151 are combined in such a manner that a predetermined tensile force is applied to the patterning slit sheet 151.

In particular, a degree of pattern precision of the patterning slit sheet 151 during a deposition process may be affected by a manufacturing error and/or a thermal expansion error of the patterning slit sheet 151. A counterforce technique may be used to minimize or reduce a manufacturing error of the patterning slit sheet 151. This is described according to one embodiment in further detail below. First, a tensile force is applied to the patterning slit sheet 151 by applying pressure to the patterning slit sheet 151 from the inside to the outside thereof. Next, a compression force is applied to the frame 154 in an opposite direction to the direction in which the external tensile force is applied to the patterning slit sheet 151, such that the compression force is in equilibrium with the external tensile force applied to the patterning slit sheet 151. Next, the

frame 154 and the patterning slit sheet 151 are combined, such as by welding, for example. Lastly, the external tensile force applied to the patterning slit sheet 151, which is in equilibrium with the compression force applied to the frame 154, is removed so as to apply the tensile force to the patterning slit sheet 151 via the frame 154. In one embodiment, when such precise extension, compression, and welding techniques as described above are used, the patterning slit sheet 151 may be manufactured with a manufacturing error of 2 μm or less.

In one embodiment, a tensile force may be applied to the patterning slit sheet 151, such as to a predetermined degree or greater such that the patterning slit sheet 151 may be prevented or substantially prevented from being deformed (e.g., sagging) during the deposition process, and a compression force may be applied to the frame 154, such as to a predetermined degree or greater. However, when a compression force is applied to the frame 154 to the predetermined degree or greater, the frame is likely to be deformed. In particular, when the size of the patterning slit sheet 151 is increased to perform a deposition process on the substrate 500 that is a large substrate, a greater tensile force should be applied to the patterning slit sheet 151 and a compression force applied to the frame 154 should also be increased to correspond to the greater tensile force. The frame 154 to which the greater compression force is applied may bend, and a manufacturing process is not easy to perform when the weight of the frame 154 is significantly increased to prevent the frame from bending.

According to an embodiment of the present invention, the slit unit 152 of the patterning slit sheet 151 is formed to be larger than a deposition area on which a deposition process is to be performed, and the above-described problem is avoided.

This will now be described in further detail. Referring to FIG. 1, a deposition area DA is disposed between non-deposition areas NA on the substrate 500. The deposition material in the deposition source 110 passes through the patterning slit sheet 151 and reaches the deposition area DA on the substrate 500 to perform a deposition process.

The slit unit 152 overlaps with the deposition area DA and is larger than the deposition area DA. That is, the slit unit 152 partially overlaps with the non-deposition areas NA.

Therefore, the non-slit region 153 is smaller and the region of the slit unit 152 having the plurality of slits is wider. If a tensile force of the same degree is applied to the patterning slit sheet 151, the larger the slit unit 152, the higher degree to which the patterning slit sheet 151 may be tensile-strained due to the plurality of slits that pass through the patterning slit sheet 151. In other words, a degree to which the patterning slit sheet 151 is tensile-strained is high when the slit unit 152 is large, provided the tensile force of the same degree is applied.

Thus, the larger the slit unit 152, the less the tensile force that may be applied to the patterning slit sheet 151. Accordingly, a compression force applied to the frame 154 may be lessened. Thus, the frame 154 is prevented or substantially prevented from being deformed and the thickness of the frame 154 does not need to be increased, thereby facilitating the manufacturing process.

The shielding unit 155, in one embodiment, is formed on inner side surfaces of the frame 154. The shielding unit 155 may be formed covering inner side surfaces of the frame 154, as illustrated in FIG. 3A, or a shielding unit 155' may be formed on two inner side surfaces that face each other from among the inner side surfaces of the frame 154, as illustrated in FIG. 3B. The structure of the shielding unit 155 may vary according to shapes and sizes of the substrate 500 which is a target deposition substrate, the patterning slit sheet 151, and the frame 154.

The shielding unit **155** overlaps with the non-deposition areas NA and corresponds to edge portions of the deposition area DA, as illustrated in FIG. 1. Since the slit unit **152** is larger than the deposition area DA, as described above, the deposition material in the deposition source **110** may be deposited not only on the deposition area DA but also on the non-deposition areas NA. In this case, an organic layer is not likely to be formed in a desired pattern. However, this is prevented or substantially prevented by the shielding unit **155**. In other words, the shielding unit **155** allows the deposition material in the deposition source **110** to be deposited only on the deposition area DA.

In one embodiment, the patterning slit sheet assembly **150** applies a tensile force to the patterning slit sheet **151** when the frame **154** and the patterning slit sheet **151** are combined with each other, thereby minimizing or reducing a manufacturing error of the patterning slit sheet **151** and preventing or substantially preventing the patterning slit sheet **151** from being deformed. Accordingly, a deposition process may be performed to deposit a thin film in a fine pattern on a substrate **500**.

In one embodiment, since the slit unit **152** of the patterning slit sheet **151** may be formed to be large, and particularly, to be larger than the deposition area DA, a tensile force applied to the patterning slit sheet **151** is reduced to lessen a compression force to be applied to the frame **154**, thereby preventing or substantially preventing the frame **154** from being deformed.

The shielding unit **155** is formed on the frame **154** such that the deposition material may not be deposited on the non-deposition areas NA, but on the deposition area DA, thereby increasing the efficiency of the deposition process to deposit a thin film in a fine pattern.

FIG. 4 is a schematic perspective view of an organic layer deposition apparatus **100** according to an embodiment of the present invention; FIG. 5 is a schematic side sectional view of the organic layer deposition apparatus **100**; and FIG. 6 is a schematic front sectional view of the organic layer deposition apparatus **100**. Referring to FIGS. 4 through 6, the organic layer deposition apparatus **100** includes a deposition source **110**, a deposition source nozzle unit **120**, and the patterning slit sheet assembly **150**.

In one embodiment, a deposition material **115** discharged from the deposition source **110** passes through the deposition source nozzle unit **120** and the patterning slit sheet assembly **150** and is then deposited onto the substrate **500** in a desired pattern. Although not shown, such a deposition process that uses the organic layer deposition apparatus **100** may be performed in a chamber that is maintained in a high vacuum. In addition, the temperature of the patterning slit sheet **151** is sufficiently lower than that of the deposition source **110**. In one embodiment, the temperature of the patterning slit sheet **151** may be about 100° C. or less. The temperature of the patterning slit sheet **151** should be sufficiently low so as to minimize or reduce thermal expansion of the patterning slit sheet **151**.

The substrate **500** may be a substrate for flat panel displays, for example. A large substrate, such as a mother glass, for manufacturing a plurality of flat panel displays, may be used as the substrate **500**. However, other substrates may be used. In one embodiment, deposition is performed while the substrate **500** is moved relative to the organic layer deposition apparatus **100**. The substrate **500** may be disposed on an electrostatic chuck **600** and may be then transferred.

In particular, in a conventional fine metal mask (FMM) deposition method, the size of an FMM is equal to the size of a substrate. Thus, since the size of the FMM has to be

increased as the substrate becomes larger, it is neither straightforward to manufacture a large FMM nor to extend an FMM to be accurately aligned with a pattern.

In the organic layer deposition apparatus **100** of the present invention, deposition may be performed while the organic layer deposition apparatus **100** or the substrate **500** is moved relative to the other. In other words, deposition may be continuously performed while the substrate **500**, which is disposed such as to face the organic layer deposition apparatus **100**, is moved in a Y-axis direction. That is, deposition may be performed in a scanning manner while the substrate **500** is moved in a direction indicated by the arrow "A" in FIGS. 4 and 5.

In the organic layer deposition apparatus **100** according to one embodiment, the patterning slit sheet **151** may be significantly smaller than an FMM used in a conventional deposition method. In one embodiment, in the organic layer deposition apparatus **100**, deposition is continuously performed (e.g., in a scanning manner) while the substrate **500** is moved in the Y-axis direction. Thus, the length of the patterning slit sheet **151** in at least one of the X-axis or the Y-axis directions may be significantly less than the length of the substrate **500** in at least one of the X-axis or the Y-axis directions. As described above, since the patterning slit sheet **151** may be formed to be significantly smaller than a FMM used in a conventional deposition method, it is relatively easy to manufacture the patterning slit sheet **151** according to embodiments of the present invention. In addition, using the patterning slit sheet **151**, which is smaller than the FMM used in the conventional deposition method, is more convenient in other processes, including etching and other subsequent processes, such as precise extension, welding, moving, and cleaning processes, compared to the conventional deposition method using the larger FMM. This is especially advantageous for a relatively large display device.

The deposition source **110** that contains and heats the deposition material **115** is disposed at a side facing the substrate **500**. The deposition material **115** is vaporized in the deposition source **110** and deposited on the substrate **500**.

In one embodiment, the deposition source **110** includes a crucible **112** filled with the deposition material **115**, and a cooling block **111** that heats the crucible **112** to vaporize the deposition material **115** in the crucible **112** toward a side of the crucible **112**, and in particular, toward the deposition source nozzle unit **120**. The cooling block **111** prevents or substantially prevents radiation of heat from the crucible **112** to the outside. The cooling block **111** may include a heater (not shown) that heats the crucible **112**.

The deposition source nozzle unit **120** is disposed at a side of the deposition source **110**, and in particular, at the side of the deposition source **110** facing the substrate **500**. The deposition source nozzle unit **120**, in one embodiment, includes a plurality of deposition source nozzles **121** arranged at intervals (e.g., equal intervals) in the Y-axis direction (e.g., a scanning direction of the substrate **500**). The deposition material **115** that is vaporized in the deposition source **110** passes through the deposition source nozzle unit **120** toward the substrate **500**. As described above, in one embodiment, the deposition source nozzle unit **120** includes the plurality of deposition source nozzles **121** arranged in the Y-axis direction (e.g., the scanning direction of the substrate **500**), and the size of a pattern formed of the deposition material **115** discharged through the slit unit **152** of the patterning slit sheet **151** is affected by the size of the deposition source nozzles **121** (since there may be only one line of the deposition source nozzles **121** in the X-axis direction). Thus, no shadow zone may be formed on the substrate **500**. In one embodiment,

since the plurality of deposition source nozzles **121** are arranged in the scanning direction of the substrate **500**, even if there is a difference in flux between the plurality of deposition source nozzles **121**, the difference may be compensated for and deposition uniformity may be maintained constant.

The patterning slit sheet assembly **150** that includes the patterning slit sheet **151**, the frame **154**, and the shielding unit **155**, is disposed between the deposition source **110** and the substrate **500**. The patterning slit sheet **151** includes the slit unit **152** and the non-slit region **153**. In the slit unit **152**, the plurality of slits are formed in an X-axis direction. The deposition material **115** that is vaporized in the deposition source **110** passes through the deposition source nozzle unit **120** and the patterning slit sheet **151**, and particularly, the slit unit **152**, toward the substrate **500**.

In one embodiment, the structure of the patterning slit sheet assembly **150** that includes the patterning slit sheet **151**, the frame **154**, and the shielding unit **155**, may be the same as described above with respect to FIGS. 1 through 3B, and thus further description thereof will not be repeated here.

The deposition source **110** and the deposition source nozzle unit **120** coupled to the deposition source **110** may be disposed apart from the patterning slit sheet assembly **150** by a predetermined distance. In one embodiment, the deposition source **110** and the deposition source nozzle unit **120** coupled to the deposition source **110** may be connected to the patterning slit sheet assembly **150** by connection members **135**. In one embodiment, the deposition source **110**, the deposition source nozzle unit **120**, and the patterning slit sheet assembly **150** may be integrally formed as one body by being connected to each other via the connection members **135**. The connection members **135** may guide the deposition material **115**, which is discharged through the deposition source nozzles **121**, to move straight and to not flow in the X-axis direction. In one embodiment, as illustrated in FIG. 4, the connection members **135** are formed only on left and right sides of the deposition source **110**, the deposition source nozzle unit **120**, and the patterning slit sheet assembly **150** to guide the deposition material **115** to not flow in the X-axis direction; however, aspects of the present invention are not limited thereto. For example, in another embodiment, the connection member **135** may be formed in the configuration of a sealed box to guide flow of the deposition material **115** in both the X-axis and Y-axis directions.

As described above, the organic layer deposition apparatus **100** according to one embodiment performs deposition while being moved relative to the substrate **500**. In one embodiment, in order to move the organic layer deposition apparatus **100** relative to the substrate **500**, the patterning slit sheet assembly **150** is separated from the substrate **500** by a predetermined distance.

In particular, in the conventional deposition method using a FMM, deposition is performed with the FMM in close contact with a substrate in order to prevent formation of a shadow zone on the substrate. However, when the FMM is used in close contact with the substrate, the contact may cause defects. In addition, in the conventional deposition method, the size of the mask has to be the same as the size of the substrate since the mask cannot be moved relative to the substrate. Thus, the size of the mask has to be increased as display devices become larger. However, it is not easy to manufacture such a large mask.

In the organic layer deposition apparatus **100** according to the present invention, the patterning slit sheet assembly **150** is disposed to be separated from the substrate **500** by a predetermined distance. Thus, it is possible to prevent or substan-

tially prevent defects from occurring when the patterning slit sheet assembly **150** contacts the substrate **500** during the deposition process.

In one embodiment, since the patterning slit sheet assembly **150**, and particularly, the patterning slit sheet **151** is formed to be smaller than the substrate **500**, the patterning slit sheet assembly **150** may be easily manufactured.

FIG. 7 is a schematic perspective view of an organic layer deposition apparatus **100'** according to another embodiment of the present invention. Referring to FIG. 7, the organic layer deposition apparatus **100'** includes the deposition source **110**, a deposition source nozzle unit **120'**, and the patterning slit sheet assembly **150**.

The deposition source **110**, in one embodiment, includes the crucible **112** filled with the deposition material **115**, and the cooling block **111** that heats the crucible **112** to vaporize the deposition material **115** in the crucible **112** toward the deposition source nozzle unit **120'**. The deposition source nozzle unit **120'** is disposed at a side of the deposition source **110**. The deposition source nozzle unit **120'** includes a plurality of deposition source nozzles **121'** arranged in the Y-axis direction. The patterning slit sheet assembly **150** is disposed between the deposition source **110** and the substrate **500**. In one embodiment, the deposition source **110** and the deposition source nozzle unit **120'** may be connected to the patterning slit sheet assembly **150** by the connection members **135**.

In one embodiment, the structure of the patterning slit sheet assembly **150** that includes the patterning slit sheet **151**, the frame **154**, and the shielding unit **155**, may be the same as that of embodiments described above, and thus further description thereof will not be repeated here.

In one embodiment, the plurality of deposition source nozzles **121'** formed in the deposition source nozzle unit **120'** are tilted at a predetermined angle, unlike in the deposition source nozzle unit **120** described above with reference to FIGS. 4 through 6. In one embodiment, the deposition source nozzles **121'** may include deposition source nozzles **121a** and **121b** arranged in two rows. The deposition source nozzles **121a** and **121b** may be arranged in two rows to alternate in a zigzag pattern. The deposition source nozzles **121a** and **121b** may be tilted at a predetermined angle on an X-Z plane.

In one embodiment, the deposition source nozzles **121a** and **121b** are arranged to be tilted at a predetermined angle. In one embodiment, the deposition source nozzles **121a** in a first row and the deposition source nozzles **121b** in a second row may be tilted to face each other. For example, the deposition source nozzles **121a** of the first row in a left part of the deposition source nozzle unit **120'** may be tilted to face a right side portion of the patterning slit sheet assembly **150**, and the deposition source nozzles **121b** of the second row in a right part of the deposition source nozzle unit **120'** may be tilted to face a left side portion of the patterning slit sheet assembly **150**.

Due to the structure of the organic layer deposition apparatus **100'** according to one embodiment, the deposition of the deposition material **115** may be adjusted to lessen a thickness variation between the center and the end portions of an organic layer on the substrate **500** and improve thickness uniformity of the organic layer. Moreover, utilization efficiency of the deposition material **115** may also be improved.

FIG. 8 is a schematic perspective view of an organic layer deposition apparatus according to another embodiment of the present invention.

Referring to FIG. 8, the organic layer deposition apparatus may include a plurality of organic layer deposition apparatuses, such as first, second, and third deposition apparatuses **100**, **200**, and **300**, each of which may have a same structure

as the organic layer deposition apparatus **100** illustrated in FIGS. **4** through **6**. The organic layer deposition apparatus according to the embodiment shown in FIG. **8** may include a multi-deposition source unit that consists of a plurality of deposition sources and that concurrently (e.g., simultaneously) discharge different deposition materials, such as for respectively forming a red (R) emission layer, a green (G) emission layer, and a blue (B) emission layer.

In one embodiment, the organic layer deposition apparatus includes the first organic layer deposition apparatus **100**, the second organic layer deposition apparatus **200**, and the third organic layer deposition apparatus **300**. Each of the first to third organic layer deposition apparatuses **100**, **200**, **300** may have the same structure as the organic layer deposition apparatus **100** described with reference to FIGS. **4** through **6**, and thus a detailed description thereof will not be repeated here.

Also, the structure of the patterning slit sheet assembly **150** that includes the patterning slit sheet **151**, the frame **154**, and the shielding unit **155** may be the same as that of the organic layer deposition apparatus **100** described above, and thus further description thereof will not be repeated here.

The deposition sources of the first organic layer deposition apparatus **100**, the second organic layer deposition apparatus **200**, and the third organic layer deposition apparatus **300** may contain different deposition materials, respectively. For example, the first organic layer deposition apparatus **100** may contain a deposition material for forming a red (R) emission layer, the second organic layer deposition apparatus **200** may contain a deposition material for forming a green (G) emission layer, and the third organic layer deposition apparatus **300** may contain a deposition material for forming a blue (B) emission layer.

In one embodiment, the red (R) emission layer, the green (G) emission layer, and the blue (B) emission layer may be concurrently (e.g., simultaneously) formed by using the multi-deposition source unit. Thus, a time needed to manufacture an organic light emitting display device may be significantly reduced. In addition, the organic light emitting display device may be manufactured using a reduced number of chambers, such that equipment costs may also be significantly reduced.

Although not illustrated in FIG. **8**, the patterning slit sheet assemblies **150** of the first organic layer deposition apparatus **100**, the second organic layer deposition apparatus **200**, and the third organic layer deposition apparatus **300** may be arranged to be offset by a distance (e.g., a constant distance) with respect to each other, thereby preventing or substantially preventing deposition regions corresponding to the patterning slit sheets **150** from overlapping with one another on a substrate **500**. In other words, if the first organic layer deposition apparatus **100**, the second organic layer deposition apparatus **200**, and the third organic layer deposition apparatus **300** are used to respectively deposit the R emission layer, the G emission layer, and the B emission layer, then a plurality of slits of the slit unit **152** of the patterning slit sheet **151** of the first organic layer deposition apparatus **100**, a plurality of slits of the slit unit **152** of the patterning slit sheet **151** of the second organic layer deposition apparatus **200**, and a plurality of slits of the slit unit **152** of the patterning slit sheet **151** of the third organic layer deposition apparatus **300** may be arranged to not be aligned with respect to one another, to respectively form the R emission layer, the G emission layer, and the B emission layer in different regions of the substrate **500**.

In one embodiment, the deposition materials for respectively forming the R emission layer, the G emission layer, and the B emission layer may be vaporized at different temperatures. Therefore, the temperatures of deposition sources of

the respective first to third organic layer deposition apparatuses **100**, **200**, **300** may be set to be different.

Although the organic layer deposition apparatus according to embodiment shown in FIG. **8** includes the three organic layer deposition apparatuses **100**, **200**, **300**, embodiments of the present invention are not limited thereto. For example, an organic layer deposition apparatus according to another embodiment of the present invention may include a plurality of organic layer deposition apparatuses, each of which contains a different deposition material. For example, an organic layer deposition apparatus according to another embodiment of the present invention may include five organic layer deposition apparatuses respectively containing materials for an R emission layer, a G emission layer, a B emission layer, an auxiliary R' layer of the R emission layer, and an auxiliary G' layer of the G emission layer.

As described above, an organic layer deposition apparatus may include a plurality of organic layer deposition apparatuses to concurrently (e.g., simultaneously) form a plurality of organic layers, thereby improving manufacturing yield and deposition efficiency. In addition, the overall manufacturing process may be simplified, and the manufacturing costs may be reduced.

FIG. **9** is a schematic perspective view of an organic layer deposition apparatus **400** according to another embodiment of the present invention; FIG. **10** is a schematic side sectional view of the organic layer deposition apparatus **400**; and FIG. **11** is a schematic front sectional view of the organic layer deposition apparatus **400**.

Referring to FIGS. **9** through **11**, the organic layer deposition apparatus **400** includes the deposition source **110**, a deposition source nozzle unit **420**, the patterning slit sheet assembly **150**, and a barrier plate assembly **130**. In one embodiment, although not illustrated in FIGS. **9** through **11** for purposes of clarity, the components of the organic layer deposition apparatus **400** may be disposed within a chamber that is maintained at an appropriate degree of vacuum. The chamber may be maintained at an appropriate degree of vacuum in order to allow the deposition material **115** to move in a substantially straight line through the organic layer deposition apparatus **400**.

In the chamber, the substrate **500** that is a deposition target substrate is transferred by the electrostatic chuck **600**. The substrate **500** may be a substrate for flat panel displays, for example. A large substrate, such as a mother glass, for manufacturing a plurality of flat panel displays, may be used as the substrate **500**. However, other substrates may be employed.

In one embodiment, the substrate **500** may be moved relative to the organic layer deposition apparatus **400**. For example, the substrate **500** may be moved in a direction of the arrow "A" relative to the organic layer deposition apparatus **400**.

Similar to the embodiments described above, in the organic layer deposition apparatus **400** according to one embodiment, the patterning slit sheet assembly **150** may be significantly smaller than a FMM used in a conventional deposition method. In one embodiment, in the organic layer deposition apparatus **400**, deposition is continuously performed (e.g., in a scanning manner) while the substrate **500** is moved (e.g., in the Y-axis direction). Thus, a length of the patterning slit sheet **151** (e.g., in the Y-axis direction) may be significantly less than a length of the substrate **500**, and a width of the patterning slit sheet **151** (e.g., in the X-axis direction) and a width of the substrate **500** (e.g., in the X-axis direction) may be substantially equal to each other. However, in one embodiment, the width of the patterning slit sheet **151** in the X-axis direction may be less than the width of the substrate **500** in the

X-axis direction, and deposition may be performed on the entire substrate **500** in the scanning manner while the substrate **500** or the organic layer deposition apparatus **400** is moved relative to the other.

As described above, since the patterning slit sheet **151** may be formed to be significantly smaller than a FMM used in a conventional deposition method, it is relatively easy to manufacture the patterning slit sheet **151** according to embodiments of the present invention.

The deposition source **110** that contains and heats the deposition material **115** is disposed at a side facing the substrate **500**. In one embodiment, the deposition source **110** includes the crucible **112** filled with the deposition material **115**, and the cooling block **111** surrounding the crucible **112**. The cooling block **111** prevents or substantially prevents radiation of heat from the crucible **112** to the outside. The cooling block **111** may include a heater (not shown) that heats the crucible **112**.

The deposition source nozzle unit **420** is disposed at a side of the deposition source **110**, and in particular, at the side of the deposition source **110** facing the substrate **500**. The deposition source nozzle unit **420**, in one embodiment, includes a plurality of deposition source nozzles **421** that may be arranged at intervals (e.g., equal intervals) in the X-axis direction. The deposition material **115** that is vaporized in the deposition source **110** passes through the deposition source nozzles **421** of the deposition source nozzle unit **420** toward the substrate **500** that is a deposition target substrate.

The barrier plate assembly **130** is disposed at a side of the deposition source nozzle unit **420**. The barrier plate assembly **130**, in one embodiment, includes a plurality of barrier plates **131**, and a barrier plate frame **132** that covers sides of the barrier plates **131**. The plurality of barrier plates **131**, in one embodiment, may be arranged parallel to each other at intervals (e.g., equal intervals) in the X-axis direction. In one embodiment, each of the barrier plates **131** may be arranged parallel to a Y-Z plane in FIG. 9, and may have a generally rectangular shape. The plurality of barrier plates **131** arranged as described above partition a deposition space between the deposition source nozzle unit **420** and the patterning slit sheet assembly **150** into a plurality of sub-deposition spaces S. In the organic layer deposition apparatus **400** according to one embodiment, as illustrated in FIG. 11, the deposition space is divided by the barrier plates **131** into the sub-deposition spaces S that respectively correspond to the deposition source nozzles **421** through which the deposition material **115** is discharged.

In one embodiment, the barrier plates **131** may be respectively disposed between adjacent deposition source nozzles **421**. In other words, each of the deposition source nozzles **421** may be disposed between two adjacent barrier plates **131**. In one embodiment, the deposition source nozzles **421** may be respectively located at the midpoints between pairs of adjacent barrier plates **131**. However, the present invention is not limited to this structure. For example, in another embodiment, a plurality of deposition source nozzles **421** may be disposed between two adjacent barrier plates **131**, and the deposition source nozzles **421** may be respectively located at the midpoint between the two adjacent barrier plates **131**.

In one embodiment, since the barrier plates **131** partition the space between the deposition source nozzle unit **420** and the patterning slit sheet assembly **150** into the plurality of sub-deposition spaces S as described above, the deposition material **115** discharged through each of the deposition source nozzles **421** is not mixed with the deposition material **115** discharged through the other deposition source nozzles **421**, passes through the slit unit **152** of the patterning slit sheet

assembly **150**, and is then deposited on the substrate **500**. In other words, the barrier plates **131** guide the deposition material **115**, which is discharged through the deposition source nozzles **421**, to move straight (i.e. flow in the Z-axis direction).

As described above, the deposition material **115** may be directed to move straight by installing the barrier plates **131**, such that a smaller shadow zone may be formed on the substrate **500** compared to an apparatus in which no barrier plates are installed. In one embodiment, the organic layer deposition apparatus **400** and the substrate **500** may be separated from each other by a predetermined distance. This will be described in further detail later herein.

In one embodiment, the barrier plate frame **132**, which covers the sides of the barrier plates **131**, maintains the positions of the barrier plates **131** and guides the deposition material **115**, which is discharged through the deposition source nozzles **421** to not flow in the Y-axis direction.

The deposition source nozzle unit **420** and the barrier plate assembly **130** may be separated from each other by a predetermined distance. This may prevent or substantially prevent heat radiated from the deposition source unit **110** from being conducted to the barrier plate assembly **130**. However, embodiments of the present invention are not limited thereto. For example, in another embodiment, an appropriate heat insulator (not shown) may be disposed between the deposition source nozzle unit **420** and the barrier plate assembly **130**, and the deposition source nozzle unit **420** and the barrier plate assembly **130** may be bound together with the heat insulator therebetween.

In one embodiment, the barrier plate assembly **130** may be constructed to be detachable from the organic layer deposition apparatus **400**. In the organic layer deposition apparatus **400** according to one embodiment, the deposition space may be enclosed by using the barrier plate assembly **130**, such that the deposition material **115** that remains undeposited is mostly deposited within the barrier plate assembly **130**. Thus, since the barrier plate assembly **130** may be constructed to be detachable from the organic layer deposition apparatus **400**, when a large amount of the deposition material **115** lies in the barrier plate assembly **130** after a long deposition process, the barrier plate assembly **130** may be detached from the organic layer deposition apparatus **400** and then placed in a separate deposition material recycling apparatus in order to recover the deposition material **115**. Due to the structure of the organic layer deposition apparatus **400** according to such an embodiment, a reuse rate of the deposition material **115** is increased, such that the deposition efficiency is improved and the manufacturing costs are reduced.

The patterning slit sheet assembly **150** is disposed between the deposition source **110** and the substrate **500**. The frame **154** has a shape similar to a window frame, and is combined with the patterning slit sheet **151**. The patterning slit sheet **151** includes the slit unit **152** and the non-slit region **153**. In one embodiment, in the slit unit **152**, a plurality of slits are formed in the X-axis direction and extend in the Y-axis direction.

In one embodiment, the structure of the patterning slit sheet assembly **150** that includes the patterning slit sheet **151**, the frame **154**, and the shielding unit **155** may be the same as described above with respect to the previously described embodiments, and thus further description will not be repeated here.

In the organic layer deposition apparatus **400** according to one embodiment, the total number of the plurality of slits of the slit unit **152** may be greater than that of the deposition source nozzles **421**. Further, the total number of the plurality of slits of the slit unit **152** disposed between two adjacent

15

barrier plates **131** may be greater than the total number of deposition source nozzles **421** disposed between two adjacent barrier plates **131**. The number of the plurality of slits of the slit unit **152** may be equal to that of deposition patterns to be formed on the substrate **500**.

The barrier plate assembly **130** and the patterning slit sheet assembly **150** may be disposed to be separated from each other by a predetermined distance, and may be connected by connection members **133**.

In one embodiment, the temperature of the barrier plate assembly **130** may increase to 100° C. or greater due to the deposition source **110** having a high temperature. Therefore, the barrier plate assembly **130** and the patterning slit sheet assembly **150** may be separated from each other by the predetermined distance in order to prevent or substantially prevent the heat of the barrier plate assembly **130** from being conducted to the patterning slit sheet assembly **150**.

As described above, the organic layer deposition apparatus **400** according to one embodiment performs deposition while being moved relative to the substrate **500**. In one embodiment, in order to move the organic layer deposition apparatus **400** relative to the substrate **500**, the patterning slit sheet assembly **150** is separated from the substrate **500** by a predetermined distance. In one embodiment, in order to prevent or substantially prevent formation of a relatively large shadow zone on the substrate **500** when the patterning slit sheet assembly **150**, and particularly, the patterning slit sheet **151** is disposed apart from the substrate **500**, the barrier plates **131** are arranged between the deposition source nozzle unit **420** and the patterning slit sheet assembly **150** to force the deposition material **115** to move in a straight direction. Thus, the size of the shadow zone that may be formed on the substrate **500** may be significantly reduced.

In the organic layer deposition apparatus **400** according to an embodiment of the present invention, the patterning slit sheet assembly **150** is disposed apart from the substrate **500** by a predetermined distance. Thus, in embodiments of the present invention, defects can be prevented which might otherwise occur where a patterning slit sheet assembly contacts a substrate during a deposition process.

Also, in one embodiment, since the patterning slit sheet assembly **150**, and particularly, the patterning slit sheet **151**, is formed to be smaller than the substrate **500**, the patterning slit sheet assembly **150** may be easily manufactured.

FIG. **12** is a schematic perspective view of an organic layer deposition apparatus **400'** according to another embodiment of the present invention.

Referring to FIG. **12**, the organic layer deposition apparatus **400'** includes the deposition source **110**, the deposition source nozzle unit **420**, the first barrier plate assembly **130**, a second barrier plate assembly **140**, and the patterning slit sheet assembly **150**. In one embodiment, although not illustrated in FIG. **12** for purposes of clarity, the components of the organic layer deposition apparatus **400'** may be disposed within a chamber (not shown) that is maintained at an appropriate degree of vacuum. The chamber may be maintained at an appropriate degree of vacuum in order to allow the deposition material **115** to move in a substantially straight line through the organic layer deposition apparatus **400'**.

The substrate **500**, which is a deposition target substrate, is disposed in the chamber. The deposition source **110** that contains and heats the deposition material **115** is disposed at an opposite side of the chamber to a side at which the substrate **500** is disposed. The structure of the deposition source **110** may be the same as that of the organic layer deposition apparatus **100** described above with reference to FIGS. **4** through **6**, and thus a detailed description thereof will not be

16

repeated here. The first barrier plate assembly **130** may also be configured the same as that of the organic layer deposition apparatus **400** described above and shown in FIGS. **9** through **11**, and thus a detailed description thereof will not be repeated here.

In one embodiment, the patterning slit sheet assembly **150** of the organic layer deposition apparatus **400'** includes the patterning slit sheet **151**, the frame **154**, and the shielding unit **155**, and may have the same structure as described above, and thus further description will not be repeated here.

In one embodiment, the second barrier plate assembly **140** is disposed at a side of the first barrier plate assembly **130**. The second barrier plate assembly **140** includes a plurality of second barrier plates **141** and a second barrier plate frame **142** that covers sides of the second barrier plates **141**.

The second barrier plates **141**, in one embodiment, may be arranged parallel to each other at intervals (e.g., equal intervals) in the X-axis direction. Each of the plurality of second barrier plates **141** may be formed to extend in a Y-Z plane in FIG. **12** (i.e. perpendicular to the X-axis direction).

The plurality of first barrier plates **131** and the plurality of second barrier plates **141** arranged as described above partition a deposition space between the deposition source nozzle unit **420** and the patterning slit sheet assembly **150**. In one embodiment, the deposition space is divided by the plurality of first barrier plates **131** and the plurality of second barrier plates **141** into sub-deposition spaces that respectively correspond to the plurality of deposition source nozzles **421** through which the deposition material **115** is discharged.

In one embodiment, the plurality of second barrier plates **141** may be disposed to respectively correspond to the plurality of first barrier plates **131**. In other words, the plurality of second barrier plates **141** may be aligned with respect to the plurality of first barrier plates **131**, respectively. That is, each pair of the corresponding first and second barrier plates **131** and **141** may be located on the same plane. In one embodiment, the first barrier plates **131** and the second barrier plates **141** respectively have the same thickness in the X-axis direction, but embodiments of the present invention are not limited thereto. For example, in another embodiment, the second barrier plates **141** are aligned with a plurality of slits of a slit unit **152** of the patterning slit sheet **151** and may be formed to be relatively thin, whereas the first barrier plates **131**, may not be as precisely aligned with the plurality of slits and may be formed to be relatively thick. Such an embodiment facilitates manufacturing of the organic layer deposition assembly **100**.

In one embodiment, a plurality of the organic layer deposition apparatuses **400'** may be consecutively arranged, as described above with respect to the embodiment shown in FIG. **8**.

FIG. **13** is a schematic cross-sectional view of an organic light-emitting display device manufactured by using an organic layer deposition apparatus, according to an embodiment of the present invention.

Referring to FIG. **13**, the organic light-emitting display device is formed on a substrate **30**. The substrate **30** may be formed of a transparent material, such as glass, plastic, or metal. A buffer layer **31** containing an insulating material is formed on an entire surface of the substrate **30**.

In one embodiment, a thin film transistor (TFT) **40**, a capacitor **50**, and an organic light-emitting device (OLED) **60** are disposed on the buffer layer **31**. The TFT **40** includes an active layer **41**, a gate electrode **42**, and a source/drain electrode **43**. The OLED **60** includes a first electrode **61**, a second electrode **62**, and an intermediate layer **63**.

In one embodiment, the active layer **41** is formed in a pattern (e.g., a predetermined pattern) on the buffer layer **31**.

17

The active layer **41** may include a p-type or n-type semiconductor material. A gate insulating layer **32** is formed on the active layer **41**. The gate electrode **42** is formed on a region of the gate insulating layer **32** corresponding to the active layer **41**. An interlayer insulating layer **33** is formed covering the gate electrode **42**, and the source/drain electrode **43** may be disposed on the interlayer insulating layer **43** to contact a predetermined region of the active layer **41**. A passivation layer **34** is formed covering the source/drain electrode **43**, and an additional insulating layer may be formed on the passivation layer **34** to planarize the passivation layer **34**.

The first electrode **61** is formed on the passivation layer **34**. The first electrode **61** is electrically connected to the drain electrode **43**. A pixel defining layer **35** is formed covering the first electrode **61**. An opening **64** is formed in the pixel defining layer **35**, and the intermediate layer **63** including an organic emission layer (not shown) is formed in a region defined by the opening **64**. The second electrode **62** is formed on the intermediate layer **63**.

The intermediate layer **63** including the organic emission layer may be formed by using a patterning slit sheet assembly and an organic layer deposition apparatus according to embodiments of the present invention, such as the patterning slit sheet assembly **150** and the organic layer deposition apparatus **100** including the patterning slit sheet assembly **150** described above and shown in FIG. 4.

In one embodiment, after the opening **64** is formed in the pixel defining layer **35**, the substrate **30** is transferred into a chamber (not shown). Then, a deposition process is performed using a desired deposition material to form the intermediate layer **63** in a desired pattern.

The organic layer deposition apparatuses according to the above-described embodiments of the present invention may be applied to form an organic or inorganic layer of an organic TFT, for example, and to form layers from various materials.

As described above, according to embodiments of the present invention, a deposition process may be performed to deposit a thin film in a fine pattern by using a patterning slit sheet assembly, an organic layer deposition apparatus, or a method of manufacturing an organic light-emitting display apparatus, and, according to another embodiment, the organic light-emitting display apparatus having the thin film deposited thereon may be manufactured.

While the present invention has been particularly shown and described with reference to some exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present invention as defined by the following claims.

What is claimed is:

1. A method of manufacturing an organic light-emitting display apparatus, the method comprising:

forming a first electrode on a substrate;
forming an intermediate layer including an organic emission layer on the first electrode; and
forming a second electrode on the intermediate layer,

wherein the forming of the intermediate layer is performed using an organic layer deposition apparatus including:
a deposition source for discharging a deposition material;

a deposition source nozzle unit arranged at a side of the deposition source and including a plurality of deposition source nozzles arranged in a first direction; and
a patterning slit sheet assembly including:

a patterning slit sheet including a slit unit having a plurality of slits, and non-slit region that is located along edges of the slit unit, the patterning slit sheet

18

being smaller than the substrate in at least one of the first direction or a second direction perpendicular to the first direction;

a frame combined with the patterning slit sheet to support the patterning slit sheet, a surface of the frame facing away from the deposition source being combined with a surface of the patterning slit sheet facing toward the deposition source in a state that a tensile force is applied to the patterning slit sheet and a compression force is applied to the frame; and

a shielding unit comprising a first portion extending on a first inner side of the frame to a first inner edge overlapping an area including an edge of the edges of the slit unit and at least a portion of at least one of the slits, and a second portion extending on a second inner side of the frame opposite the first inner side to a second inner edge overlapping an area including another edge of the edges of the slit unit, and at least a portion of at least one of the slits, the first and second inner edges being spaced apart in the second direction and corresponding to edge portions of a deposition area on the substrate, the first portion extending continuously on the first inner side of the frame from a third inner side of the frame to a fourth inner side of the frame opposite the third inner side, and the second portion extending continuously on the second inner side of the frame from the third inner side of the frame to the fourth inner side of the frame,

wherein the substrate is spaced apart from the organic layer deposition apparatus by a predetermined distance, and deposition is performed while at least one of the substrate or the organic layer deposition apparatus is moved relative to the other in the first direction.

2. A method of manufacturing an organic light-emitting display apparatus, the method comprising:

forming a first electrode on a substrate;
forming an intermediate layer including an organic emission layer on the first electrode; and

forming a second electrode on the intermediate layer, wherein the forming of the intermediate layer is performed using an organic layer deposition apparatus including:

a deposition source for discharging, a deposition material;

a deposition source nozzle unit arranged at a side of the deposition source and including a plurality of deposition source nozzles arranged in a first direction;

a patterning slit sheet assembly including:

a patterning slit sheet including a slit unit having a plurality of slits, and a non-slit region that is located along edges of the slit unit, the patterning slit sheet being smaller than the substrate in at least one of the first direction or a second direction perpendicular to the first direction;

a frame combined with the patterning slit sheet to support the patterning slit sheet, a surface of the frame facing away from the deposition source being combined with a surface of the patterning slit sheet facing toward the deposition source in a state that a tensile force is applied to the patterning slit sheet and a compression force is applied to the frame; and

a shielding unit comprising a first portion extending on a first inner side of the frame to a first inner edge overlapping an area including an edge of the edges

19

of the slit unit and at least a portion of at least one of the slits, and a second portion extending on a second inner side of the frame opposite the first inner side to a second inner edge overlapping an area including another edge of the edges of the slit unit and at least a portion of at least one of the slits, the first and second inner edges being spaced apart in the first direction and corresponding to edge portions of a deposition area on the substrate, the first portion extending continuously on the first inner side of the frame from a third inner side of the frame to a fourth inner side of the frame opposite the third inner side, and the second portion extending continuously on the second inner side of the frame from the third inner side of the frame to the fourth inner side of the frame; and

a barrier plate assembly including a plurality of barrier plates arranged between the deposition source nozzle unit and the patterning slit sheet assembly in the first direction and partitioning a space between the deposition source nozzle unit and the patterning slit sheet assembly into a plurality of sub-deposition spaces,

wherein the substrate is spaced apart from the organic layer deposition apparatus by a predetermined distance, and deposition is performed while at least

20

one of the substrate or the organic layer deposition apparatus is moved relative to the other.

3. The method of claim 1, wherein the shielding unit is arranged on two inner side surfaces that face each other from among inner side surfaces of the frame.

4. The method of claim 1, wherein the shielding unit is formed covering inner side surfaces of the frame.

5. The method of claim 1, wherein the slit unit overlaps the deposition area on the substrate, and is larger than the deposition area.

6. The method of claim 1, wherein the shielding unit is arranged between the deposition source nozzle unit and the patterning slit sheet, and is spaced apart from the patterning slit sheet.

7. The method of claim 1, wherein the shielding unit is arranged on two inner side surfaces that face each other from among inner side surfaces of the frame.

8. The method of claim 2, wherein the shielding unit is formed covering inner side surfaces of the frame.

9. The method of claim 2, wherein the slit unit overlaps the deposition area on the substrate, and is larger than the deposition area.

10. The method of claim 2, wherein the shielding unit is arranged between the deposition source nozzle unit and the patterning slit sheet, and is spaced apart from the patterning slit sheet.

* * * * *

专利名称(译)	图案化缝隙片组件，有机层沉积设备，制造有机发光显示设备的方法和有机发光显示设备		
公开(公告)号	US8906731	公开(公告)日	2014-12-09
申请号	US13/461669	申请日	2012-05-01
[标]申请(专利权)人(译)	李明博KI 李成BONG CHOI溟HWAN KIM HYUN MU		
申请(专利权)人(译)	李明博-KI 李成BONG 崔溟焕 KIM MU-HYUN		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LEE MYUNG KI LEE SUNG BONG CHOI MYONG HWAN KIM MU HYUN		
发明人	LEE, MYUNG-KI LEE, SUNG-BONG CHOI, MYONG-HWAN KIM, MU-HYUN		
IPC分类号	H01L51/56 C23C14/12 C23C14/04 H01L21/00 H01L51/00		
CPC分类号	H01L51/0011 C23C14/12 H01L51/56 C23C14/042		
优先权	1020110050842 2011-05-27 KR		
其他公开文献	US20120298970A1		
外部链接	Espacenet USPTO		

摘要(译)

一种图案化缝隙片组件，用于执行沉积工艺以在基板上以精细图案沉积薄膜。一种图案化缝隙片组件，包括：图案化缝隙片，包括狭缝单元；以及非缝隙区域，沿着所述缝隙单元的边缘设置，所述图案化缝隙片在第一方向或者至少一个方向上小于所述基板。垂直于第一方向的第二方向；框架与图案化缝隙片结合以支撑图案化缝隙片；屏蔽单元，在框架的至少一个内侧上延伸，并且与包括狭缝单元的边缘的区域重叠。

