



US 20150171353A1


(19) **United States**(12) **Patent Application Publication**
JEONG et al.(10) **Pub. No.: US 2015/0171353 A1**(43) **Pub. Date: Jun. 18, 2015**(54) **SILANE-BASED COMPOUND AND ORGANIC
LIGHT-EMITTING DEVICE INCLUDING THE
SAME**(52) **U.S. CL.**
CPC **H01L 51/0094** (2013.01); **H01L 51/5024**
(2013.01)(71) Applicant: **SAMSUNG DISPLAY CO., LTD.,**
Yongin-City (KR)(72) Inventors: **Eun-Jae JEONG**, Yongin-City (KR);
Jun-Ha PARK, Yongin-City (KR);
Mi-Eun JUN, Yongin-City (KR)(73) Assignee: **SAMSUNG DISPLAY CO., LTD.,**
Yongin-City (KR)(21) Appl. No.: **14/256,282**(22) Filed: **Apr. 18, 2014**(30) **Foreign Application Priority Data**

Dec. 17, 2013 (KR) 10-2013-0157524

Publication Classification(51) **Int. Cl.**
H01L 51/00 (2006.01)
H01L 51/50 (2006.01)(57) **ABSTRACT**

A silane-based compound and an organic light-emitting device including the same, the compound being represented by Formula 1:

<Formula 1>



10





FIG. 1



SILANE-BASED COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

[0001] Korean Patent Application No. 10-2013-0157524, filed on Dec. 17, 2013, in the Korean Intellectual Property Office, and entitled: "Silane-Based Compounds And Organic Light-Emitting Devices Comprising The Same," is incorporated by reference herein in its entirety.

BACKGROUND

[0002] 1. Field

[0003] Embodiments relate to a silane-based compound and an organic light-emitting device including the same.

[0004] 2. Description of the Related Art


[0005] Organic light-emitting devices (OLEDs), which are self-emitting devices, have advantages such as wide viewing angles, excellent contrast, quick response, high brightness, excellent driving voltage characteristics, and can provide multicolored images.

[0006] An organic light-emitting device may have a structure in which a first electrode, a hole transport region, an emission layer, an electron transport region, and a second electrode are sequentially disposed in this order on a substrate. Holes injected from the first electrode may move to the emission layer via the hole transport region, while electrons injected from the second electrode may move to the emission layer via the electron transport region. Carriers (e.g., the holes and electrons) may recombine in the emission layer to generate excitons. When the excitons drop from an excited state to a ground state, light is emitted.

SUMMARY

[0007] Embodiments are directed to a silane-based compound and an organic light-emitting device including the same.

[0008] According to one or more embodiments, there is provided a silane-based compound represented by Formula 1:



[0009] wherein, in Formula 1,

[0010] L_1 and L_2 are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

[0011] n_1 is an integer selected from 0 to 3,

[0012] n_2 is an integer selected from 1 to 3,

[0013] R_1 is selected from a hydrogen, a deuterium, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

[0014] a_1 is an integer selected from 1 to 3,

[0015] wherein at least one substituent of the substituted C_3 - C_{10} cycloalkylene group, the substituted C_1 - C_{10} heterocycloalkylene group, the substituted C_3 - C_{10} cycloalkenylene group, the substituted C_1 - C_{10} heterocycloalkenylene group, the substituted C_6 - C_{60} arylene group, the substituted C_1 - C_{60} heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_1 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{10} aryl group, the substituted C_1 - C_{60} heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from

[0016] a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

[0017] a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0018] a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a

monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0019] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₁₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group; and

[0020] —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), —B(Q₆)(Q₇),

[0021] R₂, R₃, and Q₁ to Q₇ are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a cyano group, a nitro group, a C₁-C₆₀ alkyl group, a C₆-C₆₀ aryl group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group,

[0022] a₂ is an integer selected from 1 to 3,

[0023] a₃ is an integer selected from 1 to 5,

[0024] m is an integer selected from 1 to 4, and

[0025] k is an integer selected from 1 to 4.

[0026] According to one or more embodiments, an organic light-emitting device includes: a first electrode; a second electrode disposed opposite to the first electrode; and an organic layer disposed between the first electrode and the second electrode and including an emission layer, wherein the organic layer includes the above-described silane-based compound.

BRIEF DESCRIPTION OF THE DRAWING

[0027] Features will be apparent to those of skill in the art by describing in detail exemplary embodiments with reference to the attached drawing in which:

[0028] FIG. 1 illustrates a schematic cross-sectional view of a structure of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

[0029] Example embodiments will now be described more fully hereinafter with reference to the accompanying drawing; however, they may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey exemplary implementations to those skilled in the art.


[0030] In the drawing FIGURE, the dimensions of layers and regions may be exaggerated for clarity of illustration. Like reference numerals refer to like elements throughout.

[0031] As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of

elements, modify the entire list of elements and do not modify the individual elements of the list.

[0032] According to an embodiment, there is provided a silane-based compound represented by Formula 1 below:

<Formula 1>



[0033] In Formula 1 above,

[0034] L₁ and L₂ may be each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0035] wherein at least one substituent of the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylylene group, the substituted C₁-C₆₀ heteroarylylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group may be selected from

[0036] a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxylic acid group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0037] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxylic acid group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0038] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a

monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0039] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxylic acid group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group; and

[0040] —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), and —B(Q₆)(Q₇), where Q₁ to Q₇ may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a cyano group, a nitro group, a C₁-C₆₀ alkyl group, a C₁-C₆₀ aryl group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

[0041] In some embodiments, L₁ and L₂ in Formula 1 may be each independently selected from


[0042] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronylene group, an ovalenylene group, a pyrrolylene group, a thienylene group, a furanylene group, a silolylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isooxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothienylene group, a benzosilolylene group, an isobenzothiazolylene group, a benzooxazolylene group, an isobenzooxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene

group, a benzocarbazolylene group, a dibenzocarbazolylene group, and a dibenzosilolylene group; and


[0043] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronylene group, an ovalenylene group, a pyrrolylene group, a thienylene group, a furanylene group, a silolylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isooxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothienylene group, a benzosilolylene group, an isobenzothiazolylene group, a benzooxazolylene group, an isobenzooxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, and a dibenzosilolylene group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coroneryl group, an obarenyl group, a pyrrolyl group, a thienyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothie

nyl group, a benzosilolyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazol group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothienyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, and a dibenzosilolyl group, but is not limited thereto.


[0044] In some other embodiments, L_{11} and L_{12} in Formula 1 may be each independently a group represented by one of Formulae 3-1 to 3-32, but is not limited thereto:




3-1




3-2




3-3




3-4



3-5




3-6




3-7

-continued


3-8




3-9




3-10




3-11




3-12




3-13




3-14




3-15




3-16













3-17



3-18




-continued




-continued

3-19




3-20




3-21

3-22



3-23

3-24



3-25

3-26

3-27

3-28

3-29

3-30

3-31

3-32

[0045] In Formulae 3-1 to 3-32,

[0046] Y_1 may be selected from $C(Q_{31})(Q_{32})$, $N(Q_{33})$, an oxygen atom, a sulfur atom, and $Si(Q_{34})(Q_{35})$.

[0047] Q_{31} to Q_{35} may be each independently selected from a hydrogen, a deuterium, C_1 - C_{20} alkyl group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group.

[0048] Z_1 and Z_2 may be each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group.

[0049] d_1 may be an integer selected from 1 to 4,

[0050] d_2 may be an integer selected from 1 to 3,


[0051] d_3 may be an integer selected from 1 to 6,

[0052] d_4 may be an integer selected from 1 to 8,


[0053] d5 may be 1 or 2, and

[0054] d6 may be an integer selected from 1 to 5.


[0055] In some other embodiments, L_{11} and L_{12} in Formula 1 may be each independently a group represented by one of Formulae 4-1 to 4-23, but is not limited thereto:




4-1




4-2




4-3




4-4




4-5




4-6




4-7




4-8




4-9




4-10




4-11




4-12




4-13




4-14



4-15




4-16




4-17

-continued


-continued




4-18




4-19




4-20



4-21



4-22



4-23

[0056] In Formula 1 above, n_1 , which indicates the number of L_1 s, may be an integer selected from 0, 1, 2, and 3. For example, n_1 in Formula 1 may be 0 or 1, but is not limited thereto. When n_1 is 0, a moiety represented by $(L_1)_{n_1}$ may be a single or direct bond. When n_1 is 2 or greater, a plurality of L_1 s may be identical to or different from each other.

[0057] In Formula 1 above, n_2 , which indicates the number of L_2 s, may be an integer selected from 1, 2, and 3. For example, n_2 in Formula 1 may be 1 or 2, but is not limited thereto. When n_2 is 2 or greater, a plurality of L_2 s may be identical to or different from each other.

[0058] In Formula 1 above, R_1 may be selected from a hydrogen, a deuterium, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic con-

densed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

[0059] wherein at least one substituent of the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_1 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_1 - C_{60} heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from

[0060] a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxylic acid group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

[0061] a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxylic acid group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0062] a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0063] a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxylic acid group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group; and

[0064] —N(Q_1)(Q_2), —Si(Q_3)(Q_4)(Q_5), and —B(Q_6)(Q_7), where Q_1 to Q_7 may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a cyano group, a nitro group, a C_1 - C_{60} alkyl group, a C_6 - C_{60} aryl group, a C_2 - C_{60} heteroaryl group, a monovalent non-aromatic con-

densed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

[0065] In some embodiments, R_1 in Formula 1 above may be selected from

[0066] a hydrogen, a deuterium, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group;

[0067] a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a cyano group, and a nitro group;

[0068] a phenyl group, a naphthyl group, a fluorenyl group, a benzofluorenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0069] a phenyl group, a naphthyl group, a fluorenyl group, a benzofluorenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one substituent selected from a deuterium, —F, —Cl, —Br, —I, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkyl group substituted with —F, —Cl, —Br or —I, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, and —Si(Q_3)(Q_4)(Q_5), where Q_3 to Q_5 may be each independently selected from a C_1 - C_{20} alkyl group and a C_6 - C_{60} aryl group. However, embodiments are not limited thereto.

[0070] In some other embodiments, R_1 in Formula 1 above may be selected from, but not limited to,

[0071] a hydrogen, a deuterium, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group;

[0072] a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group, each substituted with at least one of a deuterium, —F, a cyano group, and a nitro group;

[0073] a phenyl group, a naphthyl group, a fluorenyl group, an anthracenyl group, a pyridinyl group, a pyrazinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

[0074] a phenyl group, a naphthyl group, a fluorenyl group, an anthracenyl group, a pyridinyl group, a pyrazinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one of a deuterium, —F, a cyano group, a nitro group, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, —CF₃, a methoxy group, an ethoxy group, a tert-butoxy group, a phenyl group, a naphthyl





group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, —Si(CH₃), and —Si(Ph)₃.

[0075] In still other embodiments, R_1 in Formula 1 above may be selected from, but not limited to,







[0076] a hydrogen, a deuterium, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group;

[0077] a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group, each substituted with at least one of —F, a cyano group, and a nitro group; and









[0078] groups represented by Formulae 5-1 to 5-45:













-continued



-continued




-continued



-continued

5-21



5-22

5-23

5-24

5-25





5-26

5-27

5-28

5-29

5-30



5-31

5-32










5-33

5-34

5-35

5-36

-continued



[0079] In Formulae 5-1 to 5-45 above, * indicates a binding site with an adjacent atom.

[0080] In yet other embodiments, R_1 in Formula 1 above may be selected from, but not limited to,

[0081] a hydrogen, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, and an n-butyl group;

[0082] a methyl group, an ethyl group, an n-propyl group, and a tert-butyl group, each substituted with at least one of —F, a cyano group, and a nitro group; and

[0083] groups represented by Formulae 5-1, 5-2, 5-14, 5-17, and 5-35 to 5-45, above.

[0084] In Formula 1 above, a_1 , which indicates the number of R_1 s, may be an integer of 1 to 3. For example, a_1 may be 1, but is not limited thereto. When a_1 is an integer of 2 or greater, a plurality of R_1 s may be identical to or different from each other. However, embodiments are not limited thereto.

[0085] In Formula 1 above, R_2 and R_3 may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a cyano group, a nitro group, a C_1 - C_{60} alkyl group, a C_6 - C_{60} aryl group, a C_2 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

[0086] In some embodiments, R_2 and R_3 in Formula 1 above may be each independently selected from, but not limited to,


[0087] a hydrogen, a deuterium, —F, —Cl, —Br, —I, a cyano group, a nitro group, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group; and

[0088] a phenyl group, a naphthyl group, a fluorenyl group, a benzofluorenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, and a triazinyl group.


[0089] In Formula 1 above, a_2 , which indicates the number of R_2 s, may be an integer selected from 0 to 3. For example, a_2 may be 0, but is not limited thereto. When a_2 is an integer of 2 or greater, a plurality of R_2 s may be identical to or different from each other. However, embodiments are not limited thereto. When a_2 is 0, a ring that would be bound to R_2 may be unsubstituted.

[0090] In Formula 1 above, a_3 , which indicates the number of R_3 s, may be an integer selected from 0 to 5. For example, a_3 may be 0, but is not limited thereto. When a_3 is an integer of 2 or greater, a plurality of R_3 s may be identical to or different from each other. When a_3 is 0, a ring that would be bound to R_3 may be unsubstituted.

[0091] In Formula 1 above, m , which indicates the number of moieties represented by




(in which * indicates a binding site with an adjacent atom), may be an integer selected from 1 to 4. For example, m may be 1 or 2, but is not limited thereto. When m is an integer of 2 or greater, a plurality of moieties represented by




may be identical to or different from each other. However, embodiments are not limited thereto.

[0092] In Formula 1 above, k, which indicates the number of moieties represented by




(in which $*$ indicates a binding site with an adjacent atom), may be an integer selected from 1 to 4. For example, k may be 2 or 3, but is not limited thereto. When k is an integer of 2 or greater, a plurality of moieties represented by




may be identical to or different from each other. However, embodiments are not limited thereto.

[0093] In some embodiments, the silane-based compound of Formula 1 above may be a compound represented by one of Formulae 1-1 to 1-4 below, but is not limited thereto:




-continued


<Formula 1-2>



<Formula 1-3>



<Formula 1-4>



[0094] In Formulae 1-1 to 1-4 above,

[0095] L_{11} , L_{12} , L_{13} , L_{21} , L_{22} , L_{23} , and L_{24} may be each independently the same as groups defined for defined for L_1 and L_2 in Formula 1 above,

[0096] n_{11} , n_{12} , and n_{13} may be each independently the same as values defined for n_1 in Formula 1 above,

[0097] n_{21} to n_{24} may be each independently the same as values defined for n_2 in Formula 1 above,

[0098] R_{11} , R_{12} , and R_{13} may be each independently the same as groups defined for R_1 in Formula 1 above, and

[0099] m_1 to m_4 may be each independently the same as values defined for m in Formula 1 above.

[0100] In some embodiments, the silane-based compound of Formula 1 above may be a compound represented by one of

Formulae 1-1 to 1-4 above, in which L_{11} , L_{12} , L_{21} , L_{13} , L_{22} , L_{23} , and L_{24} in Formulae 1-1 to 1-4 above may be each independently a group represented by one of Formulae 4-1 to 4-23 above. However, embodiments are not limited thereto.

[0101] In some other embodiments, the silane-based compound of Formula 1 above may be a compound represented by one of Formulae 1-1 to 1-4 above, in which n_{11} , n_{12} , and n_{13} in Formulae 1-1 to 1-4 above may be each independently an integer of 0 or 1. However, embodiments are not limited thereto.

[0102] In still other embodiments, the silane-based compound of Formula 1 above may be a compound represented by one of Formula 1-1 to 1-4, in which n_{21} to n_{24} in Formulae 1-1 to 1-4 above may be each independently an integer of 1 or 2. However, embodiments are not limited thereto.

[0103] In yet other embodiments, the silane-based compound of Formula 1 above may be a compound represented


by one of Formula 1-1 to 1-4, in which R_{11} , R_{12} , and R_{13} in Formulae 1-1 to 1-4 may be each independently selected from [0104] a hydrogen, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, and an n-butyl group;

[0105] a methyl group, an ethyl group, an n-propyl group, and a tert-butyl group, each substituted with at least one of —F, a cyano group, and a nitro group; and

[0106] groups represented by Formulae 5-1, 5-2, 5-14, 5-17, and 5-35 to 5-45, above. However, embodiments are not limited thereto.

[0107] In yet still other embodiments, the silane-based compound of Formula 1 above may be a compound represented by one of Formulae 1-1 to 1-4 above, wherein m_1 to m_4 in Formulae 1-1 to 1-4 above may be each independently an integer of 1 or 2. However, embodiments are not limited thereto.


[0108] In some embodiments, the silane-based compound of Formula 1 above may be one of Compounds 1 to 40 below:



-continued


7

8




9


10



11




12




-continued


13



14




15



16



17



-continued



18

19





20

21





22

23





24

25





-continued
26

27





28

29





30

31



32



33



-continued



34

35





36

37




38


39



40



[0109] The silane-based compound of Formula 1 above includes at least one “benzocarbazole group” as represented by Formula 1' below.



[0110] Due to the inclusion of the benzocarbazole group as represented by Formula 1', the silane-based compound of Formula 1 may have high electrical stability and good charge transport ability.

[0111] The silane-based compound of Formula 1 above also may have improved blue emission characteristics and improved hole transport ability, and thus may be used as a blue emission material. The silane-based compound of Formula 1 above may also be used as a host along with any of a variety of phosphorescent or fluorescent dopants for red, green, blue, and white emission.

[0112] The benzocarbazole group in Formula 1' may have a relatively rigid structure, and the silane-based compound of Formula 1 above may have an improved glass transition temperature (Tg). Therefore, an organic light-emitting device manufactured using the silane-based compound of Formula 1 may have improved stability of thin layers, and improved lifetime characteristics.

[0113] An organic light-emitting device including the silane-based compound represented by Formula 1 above may also have a high luminance, a high efficiency, a low consumption power, and a long lifetime.

[0114] The silane-based compound of Formula 1 may be synthesized using a suitable organic synthesis method. Methods of synthesizing the silane-based compounds of Formula 1 may be understood by those of ordinary skill in the art based on the examples that will be described below.

[0115] The silane-based compound of Formula 1 above may be used between a pair of electrodes of an organic light-emitting device. For example, the silane-based compound of Formula 1 may be in an emission layer.

[0116] According to another embodiment, an organic light-emitting device includes a first electrode, a second electrode disposed opposite to the first electrode, and an organic layer disposed between the first electrode and the second electrode and including an emission layer, wherein the organic layer includes at least one of the silane-based compounds of Formula 1 described above.

[0117] As used herein, “(for example, the organic layer) including at least one silane-based compound means that “(the organic layer) including one of the silane-based compounds of Formula 1 above, or at least two different silane-based compounds of Formula 1 above”.

[0118] In some embodiments, the organic layer may include only Compound 1 above as a silane-based compound.

In this regard, Compound 1 may be present in the emission layer of the organic light-emitting device. In some embodiments, the organic layer may include Compounds 1 and 2 as silane-based compounds. In this regard, Compounds 1 and 2 may be present both in the same layer (for example, in the emission layer) or may be present in different layers (for example, in the emission layer and the electron transport region, respectively).

[0119] The organic layer may further include a hole transport region disposed between the first electrode and the emission layer, and the hole transport region may include at least one of a hole injection layer, a hole transport layer, a buffer layer, and an electron blocking layer.

[0120] The organic layer may further include an electron transport region disposed between the emission layer and the second electrode, and the electron transport region may include at least one of a hole blocking layer, an electron transport layer, and an electron injection layer.

[0121] As used herein, the term “organic layer” refers to a single layer and/or a plurality of layers disposed between the first and second electrodes of the organic light-emitting device. A material in the “organic layer” is not limited to an organic material.

[0122] Hereinafter, a structure of an organic light-emitting device according to an embodiment and a method of manufacturing the same will now be described with reference to FIG. 1.

[0123] FIG. 1 illustrates a schematic sectional view of an organic light-emitting device 10 according to an embodiment. Referring to FIG. 1, the organic light-emitting device 10 includes a first electrode 110, an organic layer 150, and a second electrode 190.

[0124] A substrate (not shown) may be disposed under the first electrode 110 or on the second electrode 190 in FIG. 1. The substrate may be a glass or transparent plastic substrate with good mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

[0125] For example, the first electrode 110 may be formed by depositing or sputtering a first electrode-forming material on the substrate 11. When the first electrode 110 is an anode, a material having a high work function may be used as the first electrode-forming material to facilitate hole injection. The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. Transparent and conductive materials such as ITO, IZO, SnO₂, and ZnO may be used to form the first electrode. The first electrode 110 as a semi-transmissive electrode or a reflective electrode may be formed of at least one material selected from magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), and magnesium-silver (Mg—Ag).

[0126] The first electrode 110 may have a single-layer structure or a multi-layer structure including a plurality of layers. For example, the first electrode 110 may have a three-layered structure of ITO/Ag/ITO, but is not limited thereto.

[0127] The organic layer 150 may be disposed on the first electrode 110. The organic layer 150 may include an emission layer (EML).

[0128] The organic layer 150 may further include a hole transport region disposed between the first electrode and the EML. The organic layer 150 may further include an electron transport region between the EML and the second electrode.

[0129] For example, the hole transport region may include at least one of a hole injection layer (HIL), a hole transport layer (HTL), a buffer layer, and an electron blocking layer (EBL). For example, the electron transport layer may include at least one of a hole blocking layer (HBL), an electron transport layer (ETL), and an electron injection layer (EIL). However, embodiments are not limited thereto.

[0130] The hole transport region may have a single-layered structure including a single material, a single-layered structure including a plurality of materials, or a multi-layered structure including a plurality of layers including different materials.

[0131] In some embodiments, the electron transport region may have a single-layered structure including a plurality of materials, or a multi-layered structure of HIL/HTL, HIL/HTL/buffer layer, HIL/buffer layer, HTL/buffer layer, or HIL/HTL/EBL, wherein these layers forming a multi-layered structure are sequentially disposed on the first electrode 110 in the order stated above. However, embodiments are not limited thereto.


[0132] When the hole transport region includes a HIL, the HIL may be formed on the first electrode 110 by using any of a variety of methods, for example, by using vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, inkjet printing, laser printing, laser induced thermal imaging (LITI), or the like.

[0133] When the HIL is formed using vacuum deposition, the deposition conditions may vary depending on the material that is used to form the HIL and the structure of the HIL. For example, the deposition conditions may be selected from the following conditions: a deposition temperature of about 100° C. to about 500° C., a degree of vacuum of about 10^{-8} to about 10^{-3} torr, and a deposition rate of about 0.01 to 100 Å/sec.


[0134] When the HIL is formed using spin coating, the coating conditions may vary depending on the material that is used to form the HIL and the structure of the HIL. For example, the coating conditions may be selected from the following conditions: a coating rate of about 2,000 rpm to about 5,000 rpm and a heat treatment temperature of about 800° C. to about 200° C.

[0135] When the hole transport region includes a HTL, the HTL may be formed on the first electrode 110 or the HIL by using any of a variety of methods, for example, by using vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, inkjet printing, laser printing, laser induced thermal imaging (LITI), or the like. When the HTL is formed using vacuum deposition or spin coating, the conditions for deposition and coating may be similar to the above-described deposition and coating conditions for forming the HIL, and accordingly will not be described in detail.

[0136] In some embodiments, the hole transport region may include at least one of m-MTDATA, TDATA, 2-TNATA, NPB, β -NPB, TPD, Spiro-TPD, Spiro-NPB, α -NPB, TAPC, HMTPD, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzene sulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201 below, and a compound represented by Formula 202 below.




-continued




NPB


-continued




α-NPB




β-NPB



TAPC




TPD




HMTDP



<Formula 201>



Spiro-TPD



Spiro-NPB



<Formula 202>

[0137] In Formulae 201 and 202,

[0138] L_{201} to L_{205} may be each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_3 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_3 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_2 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent condensed heteropolycyclic group,

[0139] at least one substituent of the substituted C_3 - C_{10} cycloalkylene group, the substituted C_3 - C_{10} heterocycloalkylene group, the substituted C_3 - C_{10} cycloalkenylene group, the substituted C_3 - C_{10} heterocycloalkenylene group, the substituted C_6 - C_{60} arylene group, the substituted C_2 - C_{60} heteroarylene group, the substituted divalent non-aromatic con-

group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group; and

[0156] a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

[0157] In Formulae 201 and 202, L₂₀₁ to L₂₀₅ may be defined as described above herein in conjunction with L₁, and R₂₀₁ to R₂₀₅ may be defined as described above herein in conjunction with R₁₁.

[0158] For example, in Formulae 201 and 202,

[0159] L₂₀₁ to L₂₀₅ may be each independently selected from

[0160] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzo-fluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysénylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a carbazolinylenylene group, and a triazinylene group; and

[0161] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzo-fluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysénylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a carbazolinylenylene group, and a triazinylene group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, a quinoliny group, an isoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, and a triazinyl group,

[0162] xa1 to xa4 may be each independently 0, 1, or 2,

[0163] xa5 may be 1, 2, or 3,


[0164] R₂₀₁ to R₂₀₅ may be each independently selected from

[0165] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinoliny group, an isoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, and a triazinyl group; and

[0166] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinoliny group, an isoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, and a triazinyl group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an azuleny group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinoliny group, an isoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, and a triazinyl group, but are not limited thereto.


[0167] The compound of Formula 201 may be a compound represented by Formula 201A below:

<Formula 201A>




[0168] For example, the compound of Formula 201 may be a compound represented by Formula 201 A-1, but is not limited thereto:

<Formula 201A-1>



[0169] The compound of Formula 202 may be a compound represented by Formula 202A, but is not limited thereto:



[0170] In Formulae 201A, 201A-1, and 202A,

[0171] L_{201} to L_{203} , $xa1$ to $xa3$, $xa5$, and R_{202} to R_{204} may be the same as those described above herein,

[0172] R_{211} may be defined as described above herein in conjunction with R_{203} ,

[0173] R_{213} to R_{216} may be each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_2 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic hetero-condensed polycyclic group.

[0174] For example, in Formulae 201A, 201A-1, and 202A,

[0175] L_{201} to L_{203} may be each independently selected from

[0176] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysénylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a carbazolylenylene group, and a triazinylenylene group; and

[0177] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysénylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a carbazolylenylene group, and a triazinylenylene group, each substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl

group, a pyrimidinyl group, a pyridazinyl group, a quinoliny group, an isoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, and a triazinyl group,

[0178] $xa1$ to $xa3$ may be each independently 0 or 1,

[0179] R_{203} , R_{211} , and R_{212} may be each independently selected from

[0180] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinoliny group, an isoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, and a triazinyl group; and

[0181] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinoliny group, an isoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinoliny group, an isoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, and a triazinyl group,

[0182] R_{213} and R_{214} may be each independently selected from

[0183] a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0184] a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinoliny group, an isoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, and a triazinyl group;

[0185] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinoliny group, an isoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, and a triazinyl group; and

[0186] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group,

a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group,

[0187] R₂₁₅ and R₂₁₆ may be each independently selected from

[0188] a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof,

[0189] a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

[0190] a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl

group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0191] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and


[0192] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, and

[0193] xa5 may be 1 or 2.


[0194] In Formulae 201A and 201A-1, R₂₁₃ and R₂₁₄ may be linked to each other to form a saturated or unsaturated ring.

[0195] The compound of Formula 201 and the compound of Formula 202 may each independently be selected from Compounds Compound HT1 to HT20, but are not limited thereto.

HT1





HT2



-continued



HT3

HT4



HT5



HT6



-continued



HT7

HT8



HT9



HT10



-continued



HT11

HT12





HT13

HT14





HT15

HT16





-continued
HT17

HT18



HT19

HT20




[0196] A thickness of the hole transport region may be from about 100 Å to about 10000 Å, and in some embodiments, from about 100 Å to about 1000 Å. When the hole transport region includes a HIL and a HTL, a thickness of the HIL may be from about 100 Å to about 10,000 Å, and in some embodiments, from about 100 Å to about 1,000 Å, and a thickness of the HTL may be from about 50 Å to about 2,000 Å, and in some embodiments, from about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the HIL, and the HTL are within these ranges, satisfactory hole transport characteristics may be obtained without a substantial increase in driving voltage.


[0197] The hole transport region may further include a charge-generating material to improve conductivity, in addition to the materials as described above. The charge-generating material may be homogeneously or inhomogeneously dispersed in the hole transport region.

[0198] The charge-generating material may be, for example, a p-dopant. The p-dopant may be one of quinone derivatives, metal oxides, and cyano group-containing compounds, but is not limited thereto. Non-limiting examples of the p-dopant are quinone derivatives such as tetracyanoquinodimethane (TCNQ), 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinodimethane (F4-TCNQ), and the like; metal oxides such as tungsten oxide, molybdenum oxide, and the like; and a Compound HT-D1 below.

<Compound HT-D1>



<F4-TCNQ>



[0199] The hole transport region may further include at least one of a buffer layer and an EBL, in addition to the HIL and HTL described above. The buffer layer may compensate for an optical resonance distance of light according to a wavelength of the light emitted from the EML, and thus may improve light-emission efficiency. A material in the buffer layer may be any material used in the hole transport region. The EBL may block migration of electrons from the electron transport region into EML.






[0200] The EML may be formed on the first electrode **110** or the hole transport region by using any of a variety of methods, for example, by using vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, inkjet printing, laser printing, laser induced thermal imaging (LITI), or the like. When the EML is formed using vacuum deposition or spin coating, the deposition and coating conditions for forming the EML may be similar to the above-described deposition and coating conditions for forming the HIL, and accordingly will not be described in detail.

[0201] When the organic light-emitting device **10** is a full color organic light-emitting device, the EML may be patterned into a red emission layer, a green emission layer, and a blue emission layer to correspond to individual subpixels, respectively. In some embodiments, the EML may have a structure in which a red emission layer, a green emission layer and a blue emission layer are stacked upon one another, or a structure including a mixture of a red light-emitting material, a green light-emitting material, and a blue light-emitting material without separation of layers for the different color emission, and thus may emit white light. In some embodiments, the EML may be a white EML. In this regard, the EML may further include a color converting layer or a color filter to convert white light into light of a desired color.


[0202] The EML may include a host and a dopant.

[0203] For example, the host may be a silane-based compound of Formula 1 above.

[0204] In some embodiments, the host may include at least one of TPBi, TBADN, ADN, CBP, CDBP, and TCP, in addition to the silane-based compound of Formula 1 above.



[0205] In some other embodiments, the host may include a compound represented by Formula 301.



<Formula 301>


[0206] In Formula 301,

[0207] Ar_{301}^1 may be selected from


[0208] a naphthalene group, a heptalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, and an indenoanthracene group; and

[0209] a naphthalene group, a heptalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene


-continued




H1




H7




H2




H8




H3




H9




H4




H10



H5




H6




H11


-continued




H12




H13



H14




H15




H16


-continued




H17



H18




H19




H20


-continued




H21




H22



H23




H24




H25


-continued




H26




H27




H28



H29




H30




H31

-continued


H32




H33



H34




H35




-continued


H36



H37




-continued




H38

-continued




H41


H39



H42




H40




[0228] In some other embodiments, the host may include at least one of Compounds H43 to H49, but is not limited thereto:

H43




-continued




H44

-continued





H47

H48



H45

H49




H46

[0229] The dopant for the EML may include at least one of a fluorescent dopant and a phosphorescent dopant.

[0230] The phosphorescent dopant may include an organic metal complex represented by Formula 401 below:

<Formula 401>



[0231] In Formula 401,

[0232] M may be selected from iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm),

[0233] X_{401} to X_{404} may be each independently a nitrogen or a carbon,

[0234] A_{401} and A_{402} ring may be each independently selected from a substituted or unsubstituted benzene group, a substituted or unsubstituted naphthalene group, a substituted or unsubstituted fluorene group, a substituted or unsubstituted spiro-fluorene group, a substituted or unsubstituted indene group, a substituted or unsubstituted pyrrole group, a substituted or unsubstituted thiophene group, a substituted or unsubstituted furan group, a substituted or unsubstituted imidazole group, a substituted or unsubstituted pyrazole group, a substituted or unsubstituted thiazole group, a substituted or unsubstituted isothiazole group, a substituted or unsubstituted oxazole group, a substituted or unsubstituted isooxazole group, a substituted or unsubstituted pyridine group, a substituted or unsubstituted pyrazine group, a substituted or unsubstituted pyrimidine group, a substituted or unsubstituted pyridazine group, a substituted or unsubstituted quinoline group, a substituted or unsubstituted isoquinoline group, a substituted or unsubstituted benzoquinoline group, a substituted or unsubstituted quinoxaline group, a substituted or unsubstituted quinazoline group, a substituted or unsubstituted carbazole group, a substituted or unsubstituted benzoimidazole group, a substituted or unsubstituted benzofuran group, a substituted or unsubstituted benzothiophene group, a substituted or unsubstituted isobenzothiophene group, a substituted or unsubstituted benzoxazole group, a substituted or unsubstituted isobenzoxazole group, a substituted or unsubstituted triazole group, a substituted or unsubstituted oxadiazole group, a substituted or unsubstituted triazine group, a substituted or unsubstituted dibenzofuran group, and a substituted or unsubstituted dibenzothiophene group,

[0235] at least one substituent of the substituted benzene group, the substituted naphthalene group, the substituted fluorene group, the substituted spiro-fluorene group, the substituted indene group, the substituted pyrrole group, the substituted thiophene group, the substituted furan group, the substituted imidazole group, the substituted pyrazole group, the substituted thiazole group, the substituted isothiazole group, the substituted oxazole group, the substituted isooxazole group, the substituted pyridine group, the substituted pyrazine group, the substituted pyrimidine group, the substituted pyridazine group, the substituted quinoline group, the substituted isoquinoline group, the substituted benzoquinoline group, the substituted quinoxaline group, the substituted quinazoline group, the substituted carbazole group, the substituted benzoimidazole group, the substituted benzofuran group, the substituted benzothiophene group, the substituted isobenzothiophene group, the substituted benzoxazole group, the substituted isobenzoxazole group, the substituted triazole group, the substituted oxadiazole group, the substituted triazine group, the substituted dibenzofuran group, and the substituted dibenzothiophene group may be selected from

[0236] a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

[0237] a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_2 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q_{401})(Q_{402}), —Si(Q_{403})(Q_{404})(Q_{405}), and —B(Q_{406})(Q_{407});

[0238] a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_2 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0239] a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_2 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_2 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q_{411})(Q_{412}), —Si(Q_{413})(Q_{414})(Q_{415}), and —B(Q_{416})(Q_{417}); and

[0240] —N(Q_{421})(Q_{422}), —Si(Q_{423})(Q_{424})(Q_{425}), and —B(Q_{426})(Q_{427}).

[0241] L_{401} may be an organic ligand,

[0242] xc1 may be 1, 2, or 3, and


[0243] xc2 may be 0, 1, 2, or 3.

[0244] For example, L_{401} may be a monovalent, divalent, or trivalent organic ligand. For example, L_{401} may be selected from a halogen ligand (for example, Cl or F), a diketone ligand (for example, acetylacetonate, 1,3-diphenyl-1,3-propanedionate, 2,2,6,6-tetramethyl-3,5-heptanedionate, or hexafluoroacetonate), a carboxylic acid ligand (for example, picolinate, dimethyl-3-pyrazole carboxylate, or benzoate), a carbon monoxide ligand, an isonitrile ligand, a cyano ligand, and a phosphorous ligand (for example, phosphine or phosphite), but is not limited thereto

[0245] When A_{401} in Formula 401 has at least two substituents, the at least two substituents of A_{401} may be linked to each other to form a saturated or unsaturated ring.

[0246] When A_{402} in Formula 401 has at least two substituents, the at least two substituents of A_{402} may be linked to each other to form a saturated or unsaturated ring.


[0247] When xc1 in Formula 401 is 2 or greater, the plurality of ligands in Formula 401, represented by




may be identical to or different from each other. When x_{c1} in Formula 401 is 2 or greater, A_{401} and A_{402} may be linked to A_{401} and A_{402} of another adjacent ligand directly or via a linker (for example, a C_1 - C_5 alkylene group, $-N(R')$ — (where R' is a C_1 - C_{10} alkyl group or a C_6 - C_{20} aryl group), or $-C(=O)-$).

[0248] The phosphorescent dopant may include at least one of Compounds PD1 to PD74, but is not limited thereto:


-continued




PD4




PD5




PD1




PD6




PD2



PD7




PD3




PD8


-continued




PD9




PD10



PD11




PD12




PD13


-continued




PD14




PD15



PD16




PD17



PD18


-continued



-continued


PD19

PD24




PD20

PD25




PD26

PD21




PD27

PD22








PD28

PD23




-continued




-continued


PD29




PD30




PD31



PD32



PD33



PD34






PD35

PD36







PD37

PD38

-continued



-continued



PD39

PD44

PD40

PD45

PD41

PD46

PD42


PD47

PD43


PD48

PD49


-continued




PD50




PD51




PD52



PD53




PD54




PD55


-continued




PD56




PD57



PD58




PD59




PD60

-continued




PD61

-continued




PD66


PD62




PD67




PD63




PD68




PD64




PD69




PD65



PD70




-continued




PD71

-continued




PD74


PD72



PD73




[0249] In some embodiments, the phosphorescent dopant may include PtOEP below:




PtOEP


[0250] The fluorescent dopant may include at least one of DPAVB, BDAVB, TBPe, DMC, DCJT, Courmarin 6, and a C545T below




DPAVB



BDAVB



[0251] For example, the fluorescent dopant may include a compound represented by Formula 501 below:



[0252] In Formula 501,

[0253] Ar_{501} may be selected from

[0254] a naphthalene group, a heptalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, and an indenoanthracene group; and

[0255] a naphthalene group, a heptalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a

dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, and an indenoanthracene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_2 - C_{60} hetero aryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q_{501})(Q_{502})(Q_{503}) (where Q_{501} to Q_{503} are each independently selected from a hydrogen, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_6 - C_{60} aryl group, and a C_2 - C_{60} heteroaryl group);

[0256] L_{501} to L_{503} may be defined as described above herein in conjunction with L_{201} ;

[0257] R_{501} and R_{502} may be each independently selected from


[0258] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazole group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0259] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, and a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,


[0260] $xd1$ to $xd3$ are each independently selected from 0, 1, 2, and 3, and

[0261] $xb4$ is selected from 1, 2, 3, and 4.

[0262] For example, the fluorescent dopant may include at least one of Compounds FD1 to FD8:




FD1



FD2


FD3

FD4




-continued

FD5



-continued

FD8



[0263] An amount of the dopant in the EML may be from about 0.01 parts to about 15 parts by weight based on 100 parts by weight of the host, but is not limited to this range.

[0264] A thickness of the EML may be about 100 Å to about 1000 Å, and in some embodiments, may be from about 200 Å to about 600 Å. When the thickness of the EML is within these ranges, the EML may have good light emitting ability without a substantial increase in driving voltage.

[0265] Next, the electron transport region may be formed on the EML.

[0266] The electron transport region may include at least one of a HBL, an ETL, and an EIL. However, embodiments are not limited thereto.


[0267] In some embodiments, the electron transport region may have a structure including an ETL/EIL or a HBL/ETL/EIL, wherein the layers forming a structure of the electron transport region may be sequentially stacked on the EML in the order stated above. However, embodiments are not limited thereto.

[0268] The electron transport region may include a HBL. When the EML includes a phosphorescent dopant, the HBL may prevent diffusion of triplet excitons or holes into the ETL from the EML.



[0269] When the electron transport region includes a HBL, the HBL may be formed on the EML by using any of a variety of methods, for example, by using vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, inkjet printing, laser printing, laser induced thermal imaging (LITI), or the like. When the HBL is formed using vacuum deposition or spin coating, the deposition and coating conditions for forming the HBL may be similar to the above-described deposition and coating conditions for forming the HIL, and accordingly will not be described in detail.

[0270] For example, the HBL may include at least one of BCP below and Bphen below. However, embodiments are not limited thereto.


FD6



FD7






BCP




[0271] A thickness of the HBL may be from about 20 Å to about 1,000 Å, and in some embodiments, from about 30 Å to about 300 Å. When the thickness of the HBL is within these ranges, the HBL may have improved hole blocking ability without a substantial increase in driving voltage.

[0272] The electron transport region may include an ETL. The ETL may be formed on the EML or the HBL by using any of a variety of methods, for example, by using vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, inkjet printing, laser printing, laser induced thermal imaging (LITI), or the like. When the ETL is formed using vacuum deposition or spin coating, the deposition and coating conditions for forming the ETL may be similar to the above-described deposition and coating conditions for forming the HIL, and accordingly will not be described in detail.

[0273] The ETL may further include at least one of BCP, Bphen, Alq₃, Balq, TAZ, and NTAZ below.



[0274] In some embodiments, the ETL may include at least one of compounds represented by Formula 601 below



Ar₆₀₁-(L₆₀₁)_{xe1}-E₆₀₁]_{xe2}

<Formula 601>

[0275] In Formula 601,

[0276] Ar₆₀₁ may be selected from

[0277] a naphthalene group, a heptalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, and an indenoanthracene group;

[0278] a naphthalene group, a heptalene group, a fluorene group, a spiro-fluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, and an indenoanthracene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a

C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ hetero aryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₃₀₁)(Q₃₀₂)(Q₃₀₃) (where Q₃₀₁ to Q₃₀₃ are each independently selected from a hydrogen, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₆-C₆₀ aryl group, and a C₁-C₆₀ heteroaryl group),

[0279] L₆₀₁ may be defined as described above herein in conjunction with L₂₀₁,

[0280] E₆₀₁ may be selected from

[0281] a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group; and

[0282] a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coroneryl group, an obarenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an


isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group,

[0283] xe1 may be selected from 0, 1, 2, and 3, and

[0284] xe2 may be selected from 1, 2, 3, and 4.

[0285] In some other embodiments, the ETL may include at least one of Compounds represented by Formula 602 below:

<Formula 602>



[0286] In Formula 602,

[0287] X₆₁₁ may be N or C-(L₆₁₁)_{xe611}-R₆₁₁, X₆₁₂ may be N or C-(L₆₁₂)_{xe612}-R₆₁₂, X₆₁₃ may be N or C-(L₆₁₃)_{xe613}-R₆₁₃, at least one of X₆₁₁ to X₆₁₃ may be N,

[0288] L₆₁₁ to L₆₁₆ may be defined as described above in conjunction L₂₀₁,

[0289] R₆₁₁ to R₆₁₆ may be each independently selected from






[0290] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolyl group, an isoquinolyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0291] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolyl group, an isoquinolyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an azulenyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a

pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, and


[0292] xe611 to xe616 may be each independently selected from, 0, 1, 2, and 3.

[0293] The compound of Formula 601 and the compound of Formula 602 may each independently include at least one of Compounds ET1 to ET15 illustrated below.




-continued

ET6




-continued


ET9




ET7



ET10




ET8




-continued

ET11





-continued

ET14




ET15

ET12




ET13




[0294] A thickness of the ETL may be from about 100 Å to about 1,000 Å, and in some embodiments, from about 150 Å to about 500 Å. When the thickness of the ETL is within these ranges, the ETL may have satisfactory electron transporting ability without a substantial increase in driving voltage.

[0295] In some embodiments the ETL may further include a metal-containing material, in addition to the above-described materials.

[0296] The metal-containing material may include a lithium (Li) complex. Non-limiting examples of the Li complex are compound ET-D1 below (lithium quinolate (LiQ)), and compound ET-D2 below.



ET-D1



ET-D2

[0297] The electron transport region may include an EIL that may facilitate injection of electrons from the second electrode 190.

[0298] The EIL may be formed on the ETL by using any of a variety of methods, for example, by using vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, inkjet printing, laser printing, laser induced thermal imaging (LITI), or the like. When the EIL is formed using vacuum deposition or spin coating, the deposition and coating conditions for forming the EIL may be similar to the above-described deposition and coating conditions for forming the HIL, and accordingly will not be described in detail.

[0299] The EIL may include at least one selected from LiF, NaCl, CsF, Li₂O, BaO, and LiQ.

[0300] A thickness of the EIL may be from about 1 Å to about 100 Å, and in some embodiments, from about 3 Å to about 90 Å. When the thickness of the EIL is within these ranges, the EIL may have satisfactory electron injection ability without a substantial increase in driving voltage.

[0301] The second electrode 190 may be disposed on the organic layer 150, as described above. The second electrode 190 may be a cathode as an electron injecting electrode. A material for forming the second electrode 190 may be a metal, an alloy, an electrically conductive compound, which have a low-work function, or a mixture thereof. Non-limiting examples of materials for forming the second electrode 190 are lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), and magnesium-silver (Mg—Ag). In some embodiments, a material for forming the second electrode 190 may be ITO or IZO. The second electrode 190 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode.

[0302] Although the organic light-emitting device of FIG. 1 is described above, embodiments are not limited thereto.

[0303] As used herein, a C₁-C₆₀ alkyl group refers to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms. Non-limiting examples of the C₁-C₆₀ alkyl group, a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. A C₁-C₆₀ alkylene group refers to a divalent group having the same structure as the C₁-C₆₀ alkyl.

[0304] As used herein, a C₁-C₆₀ alkoxy group refers to a monovalent group represented by -OA₁₀₁ (where A₁₀₁ is a C₁-C₆₀ alkyl group, as described above. Non-limiting examples of the C₁-C₆₀ alkoxy group, are a methoxy group, an ethoxy group, and an isopropoxy group.

[0305] As used herein, a C₂-C₆₀ alkenyl group has a structure including at least one carbon double bond in the middle or terminal of the C₂-C₆₀ alkyl group. Non-limiting examples of the C₂-C₆₀ alkenyl group, are an ethenyl group, a propenyl group, and a butenyl group. A C₂-C₆₀ alkylene group refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

[0306] As used herein, a C₂-C₆₀ alkynyl group has a structure including at least one carbon triple bond in the middle or terminal of the C₂-C₆₀ alkyl group. Non-limiting examples of the C₂-C₆₀ alkynyl group are an ethynyl group, and a propynyl group. A C₂-C₆₀ alkynylene group used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

[0307] As used herein, a C₃-C₁₀ cycloalkyl group refers to a monovalent, monocyclic hydrocarbon group having 3 to 10

carbon atoms. Non-limiting examples of the C₃-C₁₀ cycloalkyl group, are a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. A C₃-C₁₀ cycloalkylene group refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

[0308] As used herein, a C₃-C₁₀ heterocycloalkyl group refers to a monovalent monocyclic group having 3 to 10 carbon atoms in which at least one hetero atom selected from N, O, P, and S is included as a ring-forming atom. Non-limiting examples of the C₃-C₁₀ heterocycloalkyl group, are a tetrahydrofuran group, and a tetrahydrothiophenyl group. A C₃-C₁₀ heterocycloalkylene group refers to a divalent group having the same structure as the C₃-C₁₀ heterocycloalkyl group.

[0309] As used herein, a C₃-C₁₀ cycloalkenyl group refers to a monovalent monocyclic group having 3 to 10 carbon atoms that includes at least one double bond in the ring but does not have aromaticity. Non-limiting examples of the C₃-C₁₀ cycloalkenyl group, are a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. A C₃-C₁₀ cycloalkenylene group refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

[0310] As used herein, a C₃-C₁₀ heterocycloalkenyl group used herein refers to a monovalent monocyclic group having 3 to 10 carbon atoms that includes at least one double bond in the ring and in which at least one hetero atom selected from N, O, P, and S is included as a ring-forming atom. Non-limiting examples of the C₃-C₁₀ heterocycloalkenyl group, are a 2,3-dihydrofuran group, and a 2,3-dihydrothiophenyl group. A C₃-C₁₀ heterocycloalkenylene group used herein refers to a divalent group having the same structure as the C₃-C₁₀ heterocycloalkenyl group.

[0311] As used herein, a C₆-C₆₀ aryl group refers to a monovalent, aromatic carbocyclic aromatic group having 6 to 60 carbon atoms, and a C₆-C₆₀ arylene group refers to a divalent, aromatic carbocyclic group having 6 to 60 carbon atoms. Non-limiting examples of the C₆-C₆₀ aryl group are a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group, and the C₆-C₆₀ arylene group include at least two rings, the rings may be fused to each other.

[0312] As used herein, a C₂-C₆₀ heteroaryl group refers to a monovalent, aromatic carbocyclic aromatic group having 2 to 60 carbon atoms in which at least one hetero atom selected from N, O, P, and S is included as a ring-forming atom, and 2 to 60 carbon atoms. A C₂-C₆₀ heteroarylene group refers to a divalent, aromatic carbocyclic group having 2 to 60 carbon atoms in which at least one hetero atom selected from N, O, P, and S is included as a ring-forming atom. Non-limiting examples of the C₂-C₆₀ heteroaryl group are a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₂-C₆₀ heteroaryl and the C₂-C₆₀ heteroarylene include at least two rings, the rings may be fused to each other.

[0313] As used herein, a C₆-C₆₀ aryloxy group indicates -OA₁₀₂ (where A₁₀₂ is a C₆-C₆₀ aryl group, as described above), and a C₆-C₆₀ arylthio group indicates -SA₁₀₃ (where A₁₀₃ is a C₆-C₆₀ aryl group, as described above).

[0314] As used herein, a monovalent non-aromatic condensed polycyclic group refers to a monovalent group that includes at least two rings condensed to each other and includes only carbon atoms as ring-forming atoms and that

represents non-aromaticity as a whole. An example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. As used herein, a divalent non-aromatic condensed polycyclic group refers to a divalent group with the same structure as the monovalent non-aromatic condensed polycyclic group.

[0315] As used herein, a monovalent non-aromatic condensed heteropolycyclic group refers to a monovalent group that includes at least two rings condensed to each other and include carbon and hetero atoms selected from N, O, P and S as ring-forming atoms and that represents non-aromaticity as a whole. An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. As used herein, a divalent non-aromatic condensed heteropolycyclic group refers to a divalent group with the same structure as the monovalent non-aromatic condensed polycyclic group.

[0316] The acronym "Ph" used herein refers to phenyl, the acronym "Me" used herein refers to methyl, the acronym "Et" used herein refers to ethyl, and the acronym "tert-Bu" or "Bu" used herein refers to a tert-butyl or butyl.

[0317] One or more embodiments, which include silane-based compounds, and organic light-emitting devices including the same, will now be described in detail with reference to the following examples. In the following examples, the expression that "'B' instead of 'A' was used" means that the amounts of 'B' and 'A' were the same in equivalent amounts.


[0318] The following Examples and Comparative Examples are provided in order to highlight characteristics of one or more embodiments, but it will be understood that the Examples and Comparative Examples are not to be construed as limiting the scope of the embodiments, nor are the Comparative Examples to be construed as being outside the scope of the embodiments. Further, it will be understood that the embodiments are not limited to the particular details described in the Examples and Comparative Examples.

EXAMPLES


Synthesis Example 1

Synthesis of Compound 2

[0319]



-continued



1) Synthesis of Intermediate A

[0320] 1.91 g (10 mmol) of benzocarbazole, 5.90 g (25 mmol) of 1,4-dibromobenzene, 381 mg (2 mmol) of CuI, 5.53 g (40 mmol) of K_2CO_3 , and 53 mg (0.2 mmol) of 18-crown-6 were dissolved in 50 mL of 1,3-dimethyl-3,4,5,6-tetrahydro-(1H)-pyrimidinone (DMPU) to obtain a solution, which was then heated at about 170° C. for about 8 hours. The resulting reaction mixture was cooled down to room (ambient) temperature, and then filtered to remove a solid material, following by adding a small amount of ammonia water to the resulting filtrate and then washing three times with 30 mL of diethylether. The washed diethylether layer was collected and dried using $MgSO_4$, and dried under a reduced pressure to obtain a crude product, which was then purified using silica gel column chromatography to obtain about 2.42 g (Yield: 70%) of Intermediate A as white solid. This compound was identified using liquid chromatography-mass spectroscopy (LC-MS). $C_{20}H_{12}BrN$: M+ 346.0

2) Synthesis of Compound 2

[0321] 3.64 g (10.5 mmol) of Intermediate A was dissolved in 30 mL of tetrahydrofuran (THF), and 4.64 mL (11.6 mmol) of n-BuLi (2.5 M in hexane) was slowly dropwise added thereto at about -78° C. 1.05 mL (5.0 mmol) of dichlorophenylsilane was added to the reaction mixture, and then stirred at room temperature for about 5 hours. After completion of the reaction, 2 mL of an ammonium hydroxide solution was added to the reaction mixture, and then stirred for about 1 hour, followed by extraction with 50 mL of ethyl acetate three times. An ethyl acetate layer was collected, and dried using magnesium sulfate, followed by evaporating the solvent. The resulting residue was dissolved in a mixed solvent of ethyl

acetate and n-hexane (in a volume ratio of 1:4), and then filtered to remove undissolved solid, thereby obtaining about 2.32 g (Yield: 65%) of Compound 2 as white solid. This compound was identified using mass spectroscopy/fast atom bombardment (MS/FAB) and ^1H nuclear magnetic resonance (NMR).


[0322] $\text{C}_{52}\text{H}_{34}\text{N}_2\text{Si}$: cal. 714.25, found 715.30

[0323] ^1H NMR (400 MHz, CDCl_3) δ (ppm) 7.77 (d, 4H), 7.66 (d, 4H), 7.59 (d, 4H), 7.54 (s, 4H), 7.51-7.44 (m, 8H), 7.33-7.22 (m, 10H)

Synthesis Example 2

Synthesis of Compound 3

[0324]



[0325] 3.52 g (Yield: 58%) of Compound 3 as white solid 8 was synthesized in substantially the same manner as in the synthesis of Compound 2, except that trichlorophenylsilane, instead of dichlorodiphenylsilane, was used. This compound was identified using MS/FAB and ^1H NMR.


[0326] $\text{C}_{56}\text{H}_{41}\text{N}_3\text{Si}$: cal. 903.31, found 904.14

[0327] ^1H NMR (400 MHz, CDCl_3) δ (ppm) 7.77 (d, 6H), 7.66 (d, 6H) 7.62 (d, 2H), 7.54 (s, 6H), 7.51-7.44 (m, 12H), 7.33-7.28 (m, 2H), 7.24 (m, 7H)

Synthesis Example 3

Synthesis of Compound 7

[0328]



1) Synthesis of Intermediate B

[0329] 4.14 g (20 mmol) of 2-bromonaphthalene was dissolved in 30 mL of tetrahydrofuran (THF), and 8.4 mL (21 mmol) of n-BuLi (2.5 M in hexane) was slowly dropwise added thereto at about -78° C., and stirred for about 1 hour.

After 1.13 mL (10 mmol) of SiCl_4 was added to the reaction mixture, the resultant mixture was stirred at room temperature for 5 hours and then water was added thereto, followed by washing with 30 mL of diethylether three times. The washed diethylether layer was collected, was dried using MgSO_4 , and dried in a reduced pressure to obtain a crude product, which was then purified using silica gel column chromatography to obtain about 2.12 g (Yield: 60%) of Intermediate B as white oil. This compound was identified using LC-MS. $\text{C}_{20}\text{H}_{14}\text{Cl}_2\text{Si}$: $M+353.0$

2) Synthesis of Compound 7

[0330] 3.64 g (10.5 mmol) of Intermediate A was dissolved in 30 mL of tetrahydrofuran (THF), and 4.64 mL (11.6 mmol) of $n\text{-BuLi}$ (2.5 M in hexane) was slowly dropwise added thereto at about -78°C . 1.77 g (5.0 mmol) of Intermediate B was added to the reaction mixture, and then stirred at room temperature for about 5 hours. After completion of the reaction, 2 mL of an ammonium hydroxide solution was added to the reaction mixture, and then stirred for about 1 hour, followed by extraction with 50 mL of ethyl acetate three times. An ethyl acetate layer was collected and dried using magnesium sulfate, followed by evaporating the solvent. The resulting residue was purified using silica gel column chromatography to obtain 2.93 g (Yield: 72%) of Compound 7 as white solid. This compound was identified using MS/FAB and ^1H NMR.




[0331] $\text{C}_{60}\text{H}_{38}\text{N}_2\text{Si}$: cal. 814.28, found 815.12

[0332] ^1H NMR (400 MHz, CDCl_3) δ (ppm) 8.14 (m, 2H), 7.85 (d, 2H), 7.79-7.74 (m, 12H), 7.60-7.55 (m, 4H), 7.54 (s, 4H), 7.51-7.44 (m, 8H), 7.40-7.35 (m, 2H), 7.24 (d, 4H)

Synthesis Example 4

Synthesis of Compound 10

[0333]



1) Synthesis of Intermediate C

[0334] Intermediate C was synthesized in substantially the same manner as in the synthesis of Intermediate C, except that 1-bromonaphthalene, instead of 2-bromonaphthalene, was used. This compound was identified using LC-MS.

[0335] $\text{C}_{20}\text{H}_{14}\text{Cl}_2\text{Si}$: $M+353.0$

Synthesis of Compound 10

[0336] 2.69 g (Yield: 66%) of Compound 10 as white solid was synthesized in substantially the same manner as in the synthesis of Compound 7, except that Intermediate C, instead of intermediate B, was used. This compound was identified using MS/FAB and ^1H NMR.


[0337] $\text{C}_{60}\text{H}_{38}\text{N}_2\text{Si}$: cal. 814.28, found 815.33


[0338] ^1H NMR (400 MHz, CDCl_3) δ (ppm) 7.77 (d, 8H), 7.68 (d, 2H), 7.64 (d, 2H), 7.54 (s, 4H), 7.51-7.36 (m, 12H), 7.27 (d, 6H), 6.69 (d, 4H)

Synthesis Example 5

Synthesis of Compound 22

[0339]





1) Synthesis of Intermediate D

[0340] 1.91 g (10 mmol) of benzocarbazole, 1.57 g (5 mmol) of 1,3,5-tribromobenzene, 381 mg (2 mmol) of CuI, 5.53 g (40 mmol) of K_2CO_3 , and 53 mg (0.2 mmol) of 18-crown-6 were dissolved in 50 mL of 1,3-dimethyl-3,4,5,6-tetrahydro-(1H)-pyrimidinone (DMPU) to obtain a solution, which was then heated at about 170° C. for about 8 hours. The resulting reaction mixture was cooled down to room temperature, and then filtered to remove a solid material, following by adding a small amount of ammonia water to the resulting filtrate and then washing three times with 30 mL of diethylether. The washed diethylether layer was dried using $MgSO_4$, and dried in a reduced pressure to obtain a crude product, which was then purified using silica gel column chromatography to obtain about 0.80 g (Yield: 30%) of Intermediate D as white solid. This compound was identified using LC-MS. $C_{34}H_{19}BrN_2$: M+ 535.1

Synthesis of Compound 22

[0341] 5.62 g (10.5 mmol) of Intermediate D was dissolved in 30 mL of tetrahydrofuran (THF), and 4.64 mL (11.6 mmol) of n-BuLi (2.5 M in hexane) was slowly dropwise added


thereto at about -78° C. 0.60 mL (5.0 mmol) of dichlorodimethylsilane was added to the reaction mixture, and then stirred at room temperature for about 5 hours. After completion of the reaction, 2 mL of an ammonium hydroxide solution was added to the reaction mixture, and then stirred for about 1 hour, followed by extraction with 50 mL of ethyl acetate three times. An ethyl acetate layer was collected and dried using magnesium sulfate, followed by evaporating the solvent. The resulting residue was purified using silica gel column chromatography to obtain 2.57 g (Yield: 53%) of Compound 22 as white solid. This compound was identified using MS/FAB and 1H NMR. $C_{70}H_{44}N_4Si$: cal. 968.33, found 969.21

[0342] 1H NMR (400 MHz, $CDCl_3$) δ (ppm) 7.77 (d, 8H), 7.54 (s, 8H), 7.51-7.45 (m, 16H), 7.32 (s, 4H), 7.20 (s, 2H), 0.34 (s, 6H)

Synthesis Example 6

Synthesis of Compound 24

[0343]



[0344] 3.36 g (Yield: 64%) of Compound 24 as a white solid was synthesized in substantially the same manner as in the synthesis of Compound 22, except that dichlorodiphenylsilane, instead of dichlorodimethylsilane, was used. This compound was identified using MS/TAB and 1H NMR.

[0345] $C_{80}H_{48}N_4Si$: cal. 1092.36, found 1093.35

[0346] 1H NMR (400 MHz, $CDCl_3$) δ (ppm) 7.89 (d, 4H), 7.77 (d, 8H), 7.61 (s, 4H), 7.54 (s, 8H), 7.50-7.45 (m, 16H), 7.34 (t, 4H), 7.26-7.22 (m, 4H)


Example 1

[0347] To manufacture an anode, a Corning glass substrate (with ITO, Ag, and ITO layers having a thickness of about 70 Å, about 1,000 Å, and about 70 Å, respectively), was cut to a size of 50 mm×50 mm×0.5 mm and then sonicated in isopropyl alcohol and pure water each for five minutes, and then cleaned by irradiation of ultraviolet rays for 30 minutes and exposure to ozone. The resulting ITO/Ag/ITO substrate was mounted into a vacuum deposition device.


[0348] After 2-TNATA was vacuum-deposited on the anode to form an HIL having a thickness of 600 Å, NPB was deposited on the HIL to form a HTL having a thickness of

about 300 Å, and then Compound 2 (host) above and DPAVBi (dopant) below were co-deposited in a weight ratio of 91:9 on the HTL to form an EML having a thickness of about 250 Å.


[0349] BCP was deposited on the EML to form a hole blocking layer (HBL) having a thickness of about 50 Å, and then Alq3 was deposited on the HBL to form an electron transport layer (ETL) having a thickness of about 350 Å. LiF was deposited on the ETL to form an EIL having a thickness of about 10 Å, and Mg and Al was vacuum-deposited in a ratio of about 90:10 on the EIL to form a cathode having a thickness of about 160 Å, thereby completing the manufacture of an organic light-emitting device.




2-TNATA



NFB




BCP



DPAVBi

-continued



Example 2

[0350] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound 3, instead of Compound 2, was used to form the EML.

Example 3

[0351] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound 7, instead of Compound 2, was used to form the EML.

Example 4

[0352] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound 10, instead of Compound 2, was used to form the EML.

Example 5


[0353] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound 22, instead of Compound 2, was used to form the EML.

Example 6

[0354] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound 24, instead of Compound 2, was used to form the EML.


Comparative Example 1

[0355] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that CBP below, instead of Compound 2, was used to form the EML.




Comparative Example 2

[0356] An organic light-emitting device was manufactured in the same manner as in Example 1, except that Compound A below, instead of Compound 2, was used to form the EML.



Comparative Example 3

[0357] An organic light-emitting device was manufactured in the same manner as in Example 1, except that Compound B below, instead of Compound 2, was used to form the EML.



Evaluation Example 1

[0358] Driving voltages, current densities, luminances, efficiencies, and half-lifetimes of the organic light-emitting devices of Examples 1 to 6 and Comparative Examples 1 to 3 were evaluated using a Keithley Source-Measure Unit (SMU 236) and a PR650 (Spectroscan) Source Measurement Unit (available from Photo Research, Inc). The results are shown in Table 1, below. A half-lifetime was measured as the time taken until a measured initial luminance (assumed as 100%) was reduced to 50%).

TABLE 1

Example	EML host	Driving voltage (V)	Current density (mA/cm ²)	Luminance (cd/m ²)	Efficiency (cd/A)	Emission color	Half lifetime (hr @100 mA/cm ²)
Example 1	Compound 2	6.5	10	4,820	48.2	Green	74
Example 2	Compound 3	6.0	10	5,230	52.3	Green	69
Example 3	Compound 7	6.2	10	4,950	49.5	Green	125
Example 4	Compound 10	6.1	10	4,760	47.6	Green	130
Example 5	Compound 22	5.9	10	5,120	51.2	Green	110
Example 6	Compound 24	6.2	10	4,320	43.2	Green	80
Comparative Example 1	CBP	6.5	10	3,210	32.1	Green	32
Comparative Example 2	Compound A	6.3	10	3,820	38.2	Green	45
Comparative Example 3	Compound B	6.3	10	3,950	39.5	Green	50


[0359] Referring to Table 1, the organic light-emitting devices of Examples 1 to 6 were found to have improved luminances, improved efficiencies, and improved half-lifetimes, compared to those of the organic light-emitting devices of Comparative Examples 1 to 3.

[0360] As described above, according to the one or more of the above embodiments, an organic light-emitting device including a silane-based compound of Formula 1 may have a high luminance, a high efficiency, a low consumption power, and an improved lifetime.

[0361] Example embodiments have been disclosed herein, and although specific terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. In some instances, as would be apparent to one of ordinary skill in the art as of the filing of the present application, features, characteristics, and/or elements described in connection with a particular embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise specifically indicated. Accordingly, it will be understood by those of skill in the art that various changes in form and details may be made without departing from the spirit and scope of the present invention as set forth in the following claims.

What is claimed is:

1. A silane-based compound represented by Formula 1:



wherein, in Formula 1,

L_1 and L_2 are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

n_1 is an integer selected from 0 to 3,

n_2 is an integer selected from 1 to 3,

R_1 is selected from a hydrogen, a deuterium, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

a_1 is an integer selected from 1 to 3,

wherein at least one substituent of the substituted C_3 - C_{10} cycloalkylene group, the substituted C_1 - C_{10} heterocycloalkylene group, the substituted C_3 - C_{10} cycloalkenylene group, the substituted C_1 - C_{10} heterocycloalkenylene group, the substituted C_6 - C_{60} arylene group, the substituted C_1 - C_{60} heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C_1 - C_{60} alkyl group,

the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_1 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_1 - C_{60} heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group; and

—N(Q_1)(Q_2), —Si(Q_3)(Q_4)(Q_5), and —B(Q_6)(Q_7),

R_2 , R_3 , and Q_1 to Q_7 are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a cyano group, a nitro group, a C_1 - C_{60} alkyl group, a C_6 - C_{60} aryl group, a C_2 - C_{60} heteroaryl group, a monovalent non-

aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group,






a2 is an integer selected from 1 to 3,

a3 is an integer selected from 1 to 5,


m is an integer selected from 1 to 4, and

k is an integer selected from 1 to 4.


2. The silane-based compound as claimed in claim 1, wherein L_1 and L_2 are each independently a group represented by one of Formulae 3-1 to 3-32:




-continued



-continued



-continued




3-29

d4 is an integer selected from 1 to 8,


d5 is 1 or 2, and

d6 is an integer selected from 1 to 5.


3. The silane-based compound as claimed in claim 1, wherein L_1 and L_2 are each independently a group represented by one of Formulae 4-1 to 4-23:




3-30




4-1




3-31




4-2




3-32



4-3



4-4



4-5

wherein, in Formulae 3-1 to 3-32,

Y_1 is selected from $C(Q_{31})(Q_{32})$, $N(Q_{33})$, an oxygen atom, a sulfur atom, and $Si(Q_{34})(Q_{35})$,


Q_{31} to Q_{35} are each independently selected from a hydrogen, a deuterium, a C_1 - C_{20} alkyl group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group,

Z_1 and Z_2 are each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group and a salt thereof, a sulfonic acid group and a salt thereof, a phosphoric acid group and a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group,


d1 is an integer selected from 1 to 4,

d2 is an integer selected from 1 to 3,


d3 is an integer selected from 1 to 6,




4-6



4-7










4-8




4-9

-continued




-continued

4-10




4-17

4-11




4-18

4-12




4-19

4-13




4-20

4-14




4-21

4-22



4-23

4-15



4-16

4. The silane-based compound as claimed in claim 1, wherein n1 is 0 or 1.

5. The silane-based compound as claimed in claim 1, wherein n2 is 1 or 2.

6. The silane-based compound as claimed in claim 1, wherein R₁ is selected from:

a hydrogen, a deuterium, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group;

a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a cyano group and a nitro group;

a phenyl group, a naphthyl group, a fluorenyl group, a benzofluorenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

a phenyl group, a naphthyl group, a fluorenyl group, a benzofluorenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkyl group substituted with —F, —Cl, —Br, or —I, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, and —Si(Q_3)(Q_4)(Q_5), in which Q_3 to Q_5 are each independently selected from a C_1 - C_{20} alkyl group and a C_6 - C_{60} aryl group.

7. The silane-based compound as claimed in claim 1, wherein R_1 is selected from:

a hydrogen, a deuterium, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group;

a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group, each substituted with at least one of a deuterium, —F, a cyano group, and a nitro group;

a phenyl group, a naphthyl group, a fluorenyl group, an anthracenyl group, a pyridinyl group, a pyrazinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a phenyl group, a naphthyl group, a fluorenyl group, an anthracenyl group, a pyridinyl group, a pyrazinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one substituent selected from a deuterium, —F, a cyano group, a nitro group, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, a tert-butyl group, —CF₃, a methoxy group, an ethoxy group, a tert-butoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a


quinazolinyl group, a carbazolyl group, a triazinyl group, —Si(CH₃), and —Si(Ph)₃.

8. The silane-based compound as claimed in claim 1, wherein R_1 is selected from:


a hydrogen, a deuterium, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group;

a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group, each substituted with at least one of —F, a cyano group, and a nitro group; and


groups represented by Formulae 5-1 to 5-45:




5-1




5-2




5-3




5-4



5-5




5-6




5-7

-continued




-continued

5-8




5-14

5-9




5-15

5-10




5-16

5-11




5-17

5-12



5-18

5-13




5-19

5-20









5-21

5-22

5-23



-continued



-continued

5-24

5-55

5-26









5-27

5-28

5-29

5-30

5-31



5-32

5-33

5-34

5-35







5-36

5-37

5-38

5-39



-continued














wherein, in Formulae 5-1 to 5-45, * indicates a binding site with an adjacent atom.

9. The silane-based compound as claimed in claim 1, wherein R₁ is selected from:


a hydrogen, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, and an n-butyl group;
a methyl group, an ethyl group, an n-propyl group, and a tert-butyl group, each substituted with at least one of —F, a cyano group, and a nitro group; and
groups represented by the following Formulae 5-1, 5-2, 5-14, 5-17, and 5-35 to 5-45, in which * indicates a binding site with an adjacent atom:




-continued



-continued



5-44



5-45

10. The silane-based compound as claimed in claim 1, wherein a1 is 1.

11. The silane-based compound as claimed in claim 1, wherein R₂ and R₃ are each independently selected from:


a hydrogen, a deuterium, —F, —Cl, —Br, —I, a cyano group, a nitro group, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, an n-butyl group, a sec-butyl group, an iso-butyl group, and a tert-butyl group; and

a phenyl group, a naphthyl group, a fluorenyl group, a benzofluorenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, and a triazinyl group.


12. The silane-based compound as claimed in claim 1, wherein m is 1 or 2.

13. The silane-based compound as claimed in claim 1, wherein the silane-based compound represented by Formula 1 is represented by one of Formulae 1-1 to 1-4:

<Formula 1-1>




<Formula 1-2>




-continued

<Formula 1-3>



<Formula 1-4>



wherein, in Formulae 1-1 to 1-4,

L₁₁, L₁₂, L₁₃, L₂₁, L₂₂, L₂₃, and L₂₄ are each independently the same as groups defined for defined for L₁ and L₂ of Formula 1,

n11, n12, and n13 are each independently the same as values defined for n1 of Formula 1,


n21 to n24 are each independently the same as values defined for n2 of Formula 1,

R₁₁, R₁₂, and R₁₃ are each independently the same as groups defined for R₁ of Formula 1, and


m1 to m4 are each independently the same as values defined for m of Formula 1.

14. The silane-based compound as claimed in claim 13, wherein L₁₁, L₁₂, L₂₁, L₁₃, L₂₂, L₂₃, and L₂₄ are each independently a group represented by one of Formulae 4-1 to 4-23,


n11, n12, and n13 are each independently 0 or 1, and
n21 to n24 are each independently 1 or 2:




4-1




4-2




4-3




4-4




4-5




4-6




4-7




4-8



4-9




4-10




-continued


4-11




4-12




4-13




4-14




4-15



4-16




4-17




4-18


-continued




4-19




4-20



4-21



4-22




4-23

15. The silane-based compound as claimed in claim 13, wherein R_{11} , R_{12} , and R_{13} are each independently selected from:


a hydrogen, a methyl group, an ethyl group, an n-propyl group, an iso-propyl group, and an n-butyl group;

a methyl group, an ethyl group, an n-propyl group, and a tert-butyl group, each substituted with at least one of —F, a cyano group, and a nitro group; and


groups represented by Formulae 5-1, 5-2, 5-14, 5-17, and 5-35 to 5-45:



5-1




5-2




5-14


-continued




5-17




5-35




5-36




5-37




5-38




5-39




5-40




5-41



5-42




5-43



5-44

-continued


5-45



wherein, in Formulae 5-1, 5-2, 5-14, 5-17, and 5-35 to 5-45, * indicates a binding site with an adjacent atom.

16. The silane-based compound as claimed in claim **13**, wherein m1 to m4 are each independently 1 or 2.


17. The silane-based compound as claimed in claim **1**, wherein the silane-based compound represented by Formula **1** is one of Compounds **1** to **40**:



-continued


7

8




9


10



11




12




-continued


13




14




15



16




17




-continued


18




19




20




21




22




23











24



25




-continued




-continued

34


35




36




37




38



39



40



18. An organic light-emitting device, comprising:
 a first electrode;
 a second electrode opposite to the first electrode; and
 an organic layer between the first electrode and the second electrode, the organic layer including an emission layer,

wherein the organic layer includes the silane-based compound as claimed in claim 1.

19. The organic light-emitting device as claimed in claim 18, wherein the emission layer further includes a dopant, and the silane-based compound is a host.

20. The organic light-emitting device as claimed in claim **18**, wherein the organic layer further includes at least one of:
a hole transport region between the first electrode and the emission layer, and
an electron transport region between the emission layer and the second electrode.

* * * * *

专利名称(译)	硅烷基化合物和包括其的有机发光器件		
公开(公告)号	US20150171353A1	公开(公告)日	2015-06-18
申请号	US14/256282	申请日	2014-04-18
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	JEONG EUN JAE PARK JUN HA JUN MI EUN		
发明人	JEONG, EUN-JAE PARK, JUN-HA JUN, MI-EUN		
IPC分类号	H01L51/00 H01L51/50		
CPC分类号	H01L51/5024 H01L51/0094 H01L51/0072 H01L51/5012		
优先权	1020130157524 2013-12-17 KR		
其他公开文献	US9660204		
外部链接	Espacenet USPTO		

摘要(译)

基于硅烷的化合物和包含其的有机发光装置，该化合物由式1表示：

