



US 20190341437A1

(19) **United States**(12) **Patent Application Publication**
TANAKA(10) **Pub. No.: US 2019/0341437 A1**(43) **Pub. Date: Nov. 7, 2019**(54) **DISPLAY DEVICE INCLUDING DUAL GATE
OXIDE SEMICONDUCTOR TRANSISTOR***H01L 29/423* (2006.01)*H01L 29/66* (2006.01)(71) Applicant: **MIKUNI ELECTRON
CORPORATION**, Saitama (JP)(52) **U.S. Cl.**CPC *H01L 27/3262* (2013.01); *H01L 51/5218*
(2013.01); *H01L 29/78648* (2013.01); *H01L*
29/42384 (2013.01); *H01L 27/1288* (2013.01);
H01L 29/66969 (2013.01); *H01L 27/3248*
(2013.01); *H01L 29/7869* (2013.01); *H01L*
27/3258 (2013.01)(72) Inventor: **SAKAE TANAKA**, Saitama (JP)(21) Appl. No.: **16/516,749**(22) Filed: **Jul. 19, 2019****Related U.S. Application Data**(63) Continuation of application No. 16/100,145, filed on
Aug. 9, 2018, now Pat. No. 10,403,700, which is a
continuation of application No. 15/721,271, filed on
Sep. 29, 2017, now Pat. No. 10,074,709.(30) **Foreign Application Priority Data**

May 31, 2017 (JP) 2017-107278

Publication Classification(51) **Int. Cl.***H01L 27/32* (2006.01)*H01L 51/52* (2006.01)*H01L 29/786* (2006.01)**ABSTRACT**

A display device includes a driving transistor and an organic EL element. The driving transistor includes an oxide semiconductor layer; a first gate electrode that includes a region overlapping the oxide semiconductor layer; a first insulating layer between the first gate electrode and the oxide semiconductor layer; a second gate electrode that includes a region overlapping the oxide semiconductor layer and the first gate electrode; a second insulating layer between the second gate electrode and the oxide semiconductor layer; and a first and a second transparent conductive layer that are provided between the oxide semiconductor layer and the first insulating layer and each include a region contacting the oxide semiconductor layer. The organic EL element includes a first electrode; a second electrode; a light emitting layer between the first electrode and the second electrode; and an electron transfer layer between the light emitting layer and the first electrode.




FIG. 1




FIG. 2A




FIG. 2B




FIG. 3A




FIG. 3B




FIG. 4A




FIG. 4B




FIG. 5A




FIG. 5B




FIG. 6




FIG. 7




FIG. 8




FIG. 9A




FIG. 9B




FIG. 10A




FIG. 10B




FIG. 11A




FIG. 11B




FIG. 12




FIG. 13A




FIG. 13B




FIG. 14A




FIG. 14B




FIG. 15




FIG. 16A




FIG. 16B




FIG. 17




FIG. 18A




FIG. 18B




FIG. 19




FIG. 20A




FIG. 20B




FIG. 21A




FIG. 21B




FIG. 23A




FIG. 23B




FIG. 24A




FIG. 24B




FIG. 25A




FIG. 25B




FIG. 26




FIG. 27A




FIG. 27B




FIG. 28A




FIG. 28B




FIG. 29




FIG. 30A




FIG. 30B




FIG. 31A




FIG. 31B




FIG. 32A




FIG. 32B




FIG. 33A




FIG. 33B




FIG. 34




FIG. 35A




FIG. 35B




FIG. 36A




FIG. 36B




FIG. 37A




FIG. 37B




FIG. 38




FIG. 39




FIG. 40




FIG. 41A




FIG. 41B




FIG. 42




FIG. 43




FIG. 45A




FIG. 45B




FIG. 46




FIG. 47A




FIG. 47B




FIG. 48A




FIG. 48B




FIG. 49




FIG. 50A




FIG. 50B




FIG. 51




FIG. 52A




FIG. 52B




FIG. 53A




FIG. 53B




FIG. 54




FIG. 55A




FIG. 55B




FIG. 56A




FIG. 56B




FIG. 57




FIG. 58A




FIG. 58B




FIG. 59




FIG. 60A




FIG. 60B




FIG. 61A





FIG. 61B



DISPLAY DEVICE INCLUDING DUAL GATE OXIDE SEMICONDUCTOR TRANSISTOR

CROSS REFERENCE TO RELATED APPLICATIONS

[0001] This is a continuation of U.S. patent application Ser. No. 16/100,145 filed on Aug. 9, 2018, which is a continuation of U.S. patent application Ser. No. 15/721,271 filed on Sep. 29, 2017, which claims priority from Japanese Patent Application No. 2017-107278 filed on May 31, 2017. The contents of these applications are incorporated herein by reference in its entirety.

FIELD

[0002] The present invention relates to a structure of a display device. An embodiment of the present invention relates to a structure of a transistor and a display element included in a pixel of a display device.

BACKGROUND

[0003] An active matrix display device includes a display element and a transistor driving the display element that are provided in each of pixels thereof. Usable as the display element is a liquid crystal element including a pair of electrodes and a liquid crystal layer provided between the pair of electrodes or an organic electroluminescence element (hereinafter, referred to as an "organic EL element") including a cathode electrode, an anode electrode and a layer that is provided between the cathode electrode and the anode electrode and contains an organic electroluminescence material. The transistor is formed of an amorphous silicon semiconductor or a polycrystalline silicon semiconductor. Recently, a thin film transistor formed of an oxide semiconductor is also used.

[0004] For example, a display device including an organic EL element and a driving transistor that includes a semiconductor layer formed of silicon, a gate insulating layer and a gate electrode is disclosed (e.g., Japanese Laid-Open Patent Publication No. 2007-053286). Also, a display device including an organic EL element and a transistor driving the organic EL element that are integrally formed of an oxide semiconductor is disclosed (e.g., Japanese Laid-Open Patent Publication No. 2014-154382).

SUMMARY

[0005] A display device in an embodiment according to the present invention includes a substrate; and a plurality of pixels provided on the substrate. The plurality of pixels each include a driving transistor and an organic EL element electrically connected with the driving transistor. The driving transistor includes an oxide semiconductor layer; a first gate electrode including a region overlapping the oxide semiconductor layer, the first gate electrode being provided on a surface of the oxide semiconductor layer facing the substrate; a first insulating layer provided between the first gate electrode and the oxide semiconductor layer; a second gate electrode including a region overlapping the oxide semiconductor layer and the first gate electrode, the second gate electrode being provided on a surface of the oxide semiconductor layer opposite to the surface facing the substrate; a second insulating layer provided between the second gate electrode and the oxide semiconductor layer; and a first transparent conductive layer and a second trans-

parent conductive layer provided between the oxide semiconductor layer and the first insulating layer, the first transparent conductive layer and the second transparent conductive layer each including a region in contact with the oxide semiconductor layer. The organic EL element includes a light-transmissive first electrode; a second electrode provided to face the first electrode; a light emitting layer provided between the first electrode and the second electrode; and an electron transfer layer provided between the light emitting layer and the first electrode. The first electrode is continuous from the first transparent conductive layer.

[0006] A display device in an embodiment according to the present invention includes a substrate; and a plurality of pixels provided on the substrate. The plurality of pixels each include a driving transistor and an organic EL element electrically connected with the driving transistor. The driving transistor includes an oxide semiconductor layer; a first gate electrode including a region overlapping the oxide semiconductor layer, the first gate electrode being provided on a surface of the oxide semiconductor layer facing the substrate; a first insulating layer provided between the first gate electrode and the oxide semiconductor layer; a second gate electrode including a region overlapping the oxide semiconductor layer and the first gate electrode, the second gate electrode being provided on a surface of the oxide semiconductor layer opposite to the surface facing the substrate; and a second insulating layer provided between the second gate electrode and the oxide semiconductor layer. The organic EL element includes a light-transmissive first electrode; a second electrode provided to face the first electrode; a light emitting layer provided between the first electrode and the second electrode; and an electron transfer layer provided between the light emitting layer and the first electrode. The first electrode is continuous from the first transparent conductive layer.

BRIEF DESCRIPTION OF DRAWINGS

[0007] FIG. 1 is a cross-sectional view showing a structure of a transistor in an embodiment according to the present invention;

[0008] FIG. 2A shows a method for producing the transistor in an embodiment according to the present invention, and shows a stage of forming a first gate electrode;

[0009] FIG. 2B shows the method for producing the transistor in an embodiment according to the present invention, and shows a stage of forming a first insulating layer, a transparent conductive film, and an oxide semiconductor layer;

[0010] FIG. 3A shows the method for producing the transistor in an embodiment according to the present invention, and shows a stage of exposure performed by use of a multi-gradation photomask;

[0011] FIG. 3B shows the method for producing the transistor in an embodiment according to the present invention, and shows a stage where a resist mask is formed;

[0012] FIG. 4A shows the method for producing the transistor in an embodiment according to the present invention, and shows a stage of etching a second conductive film and a third conductive film;

[0013] FIG. 4B shows the method for producing the transistor in an embodiment according to the present invention, and shows a stage of etching the third conductive film;

[0014] FIG. 5A shows the method for producing the transistor in an embodiment according to the present invention, and shows a stage of forming an oxide semiconductor layer;

[0015] FIG. 5B shows the method for producing the transistor in an embodiment according to the present invention, and shows a stage of forming a second insulating layer and a fourth conductive film;

[0016] FIG. 6 is a plan view showing a structure of a display device in an embodiment according to the present invention;

[0017] FIG. 7 shows an equivalent circuit of a pixel in the display device in an embodiment according to the present invention;

[0018] FIG. 8 is a plan view showing a structure of a pixel in the display device in an embodiment according to the present invention;

[0019] FIG. 9A is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line A1-A2 in FIG. 8;

[0020] FIG. 9B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B1-B2 in FIG. 8;

[0021] FIG. 10A shows a structure of a display device and an influence of charges during an operation of the display device;

[0022] FIG. 10B shows a period in which a signal is applied to a gate electrode during the operation of the display device;

[0023] FIG. 11A shows a cross-sectional structure of a transistor in an embodiment according to the present invention;

[0024] FIG. 11B shows a cross-sectional structure of a transistor in an embodiment according to the present invention;

[0025] FIG. 12 is a plan view showing a method for producing the display device in an embodiment according to the present invention;

[0026] FIG. 13A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A1-A2 in FIG. 12;

[0027] FIG. 13B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B1-B2 in FIG. 12;

[0028] FIG. 14A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A1-A2 in FIG. 12;

[0029] FIG. 14B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B1-B2 in FIG. 12;

[0030] FIG. 15 is a plan view showing the method for producing the display device in an embodiment according to the present invention;

[0031] FIG. 16A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A1-A2 in FIG. 15;

[0032] FIG. 16B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B1-B2 in FIG. 15;

[0033] FIG. 17 is a plan view showing a method for producing the display device in an embodiment according to the present invention;

[0034] FIG. 18A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A1-A2 in FIG. 17;

[0035] FIG. 18B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B1-B2 in FIG. 17;

[0036] FIG. 19 is a plan view showing the method for producing the display device in an embodiment according to the present invention;

[0037] FIG. 20A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A1-A2 in FIG. 19;

[0038] FIG. 20B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B1-B2 in FIG. 19;

[0039] FIG. 21A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A1-A2 in FIG. 19;

[0040] FIG. 21B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B1-B2 in FIG. 19;

[0041] FIG. 22A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A1-A2 in FIG. 19;

[0042] FIG. 22B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B1-B2 in FIG. 19;

[0043] FIG. 23A is a cross-sectional view showing a method for producing a display device in an embodiment according to the present invention, taken along line A1-A2 in FIG. 19;

[0044] FIG. 23B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B1-B2 in FIG. 19;

[0045] FIG. 24A is a cross-sectional view showing a method for producing a display device in an embodiment according to the present invention, taken along line A1-A2 in FIG. 19;

[0046] FIG. 24B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B1-B2 in FIG. 19;

[0047] FIG. 25A is a cross-sectional view showing a method for producing a display device in an embodiment according to the present invention, taken along line A1-A2 in FIG. 19;

[0048] FIG. 25B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B1-B2 in FIG. 19;

[0049] FIG. 26 is a plan view showing a method for producing a display device in an embodiment according to the present invention;

[0050] FIG. 27A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A3-A4 in FIG. 26;

[0051] FIG. 27B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B3-B4 in FIG. 26;

[0052] FIG. 28A is a cross-sectional view showing a method for producing a display device in an embodiment according to the present invention, taken along line A3-A4 in FIG. 26;

[0053] FIG. 28B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B3-B4 in FIG. 26;

[0054] FIG. 29 is a plan view showing a method for producing the display device in an embodiment according to the present invention;

[0055] FIG. 30A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A3-A4 in FIG. 29;

[0056] FIG. 30B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B3-B4 in FIG. 29;

[0057] FIG. 31A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A3-A4 in FIG. 29;

[0058] FIG. 31B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B3-B4 in FIG. 29;

[0059] FIG. 32A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A3-A4 in FIG. 29;

[0060] FIG. 32B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B3-B4 in FIG. 29;

[0061] FIG. 33A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A3-A4 in FIG. 29;

[0062] FIG. 33B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B3-B4 in FIG. 29;

[0063] FIG. 34 is a plan view showing the method for producing the display device in an embodiment according to the present invention;

[0064] FIG. 35A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A3-A4 in FIG. 34;

[0065] FIG. 35B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B3-B4 in FIG. 34;

[0066] FIG. 36A is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line A3-A4 in FIG. 34;

[0067] FIG. 36B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B3-B4 in FIG. 34;

[0068] FIG. 37A is a cross-sectional view showing a method for producing a display device in an embodiment according to the present invention, taken along line A3-A4 in FIG. 34;

[0069] FIG. 37B is a cross-sectional view showing the method for producing the display device in an embodiment according to the present invention, taken along line B3-B4 in FIG. 34;

[0070] FIG. 38 is a plan view showing a structure of a pixel in a display device in an embodiment according to the present invention;

[0071] FIG. 39 is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line A5-A6 in FIG. 38;

[0072] FIG. 40 is a plan view showing a structure of a pixel in a display device in an embodiment according to the present invention;

[0073] FIG. 41A is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line A7-A8 in FIG. 40;

[0074] FIG. 41B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B5-B6 in FIG. 40;

[0075] FIG. 42 is a plan view showing a structure of a pixel in a display device in an embodiment according to the present invention;

[0076] FIG. 43 is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line A9-A10 in FIG. 42;

[0077] FIG. 44 is a plan view showing a structure of a pixel in a display device in an embodiment according to the present invention;

[0078] FIG. 45A is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line A11-A12 in FIG. 44;

[0079] FIG. 45B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B7-B8 in FIG. 44;

[0080] FIG. 46 is a plan view showing a method for producing a transistor in an embodiment according to the present invention, and shows a process of directing laser light to decrease a resistance of the oxide semiconductor layer;

[0081] FIG. 47A is a cross-sectional view showing a method for producing a transistor in an embodiment according to the present invention, and shows a process of directing the laser light from the second gate electrode side;

[0082] FIG. 47B is a cross-sectional view showing a method for producing a transistor in an embodiment according to the present invention, and shows a process of directing the laser light from the first gate electrode side;

[0083] FIG. 48A is a cross-sectional view showing a method for producing a transistor in an embodiment according to the present invention, and shows a process of directing the laser light from the second gate electrode side;

[0084] FIG. 48B is a cross-sectional view showing a method for producing a transistor in an embodiment according to the present invention, and shows a process of directing the laser light from the first gate electrode side;

[0085] FIG. 49 is a plan view showing a structure of a pixel in a display device in an embodiment according to the present invention;

[0086] FIG. 50A is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line A13-A14 in FIG. 49;

[0087] FIG. 50B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B9-B10 in FIG. 49;

[0088] FIG. 51 is a plan view showing a structure of a pixel in a display device in an embodiment according to the present invention;

[0089] FIG. 52A is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line A15-A16 in FIG. 51;

[0090] FIG. 52B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B11-B12 in FIG. 51;

[0091] FIG. 53A is a cross-sectional view showing a structure of a pixel in a display device in an embodiment according to the present invention, taken along line A15-A16 in FIG. 51;

[0092] FIG. 53B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B11-B12 in FIG. 51;

[0093] FIG. 54 is a plan view showing a structure of a pixel in a display device in an embodiment according to the present invention;

[0094] FIG. 55A is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line A17-A18 in FIG. 54;

[0095] FIG. 55B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B13-B14 in FIG. 54;

[0096] FIG. 56A is a cross-sectional view showing a structure of a pixel in a display device in an embodiment according to the present invention, taken along line A17-A18 in FIG. 54;

[0097] FIG. 56B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B13-B14 in FIG. 54;

[0098] FIG. 57 is a plan view showing a structure of a pixel in a display device in an embodiment according to the present invention;

[0099] FIG. 58A is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line A19-A20 in FIG. 57;

[0100] FIG. 58B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B15-B16 in FIG. 57;

[0101] FIG. 59 is a plan view showing a structure of a pixel in a display device in an embodiment according to the present invention;

[0102] FIG. 60A is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line A21-A22 in FIG. 59;

[0103] FIG. 60B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B17-B18 in FIG. 59;

[0104] FIG. 61A is a cross-sectional view showing a structure of a pixel in a display device in an embodiment according to the present invention, taken along line A21-A22 in FIG. 59;

[0105] FIG. 61B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B17-B18 in FIG. 59;

[0106] FIG. 62A is a cross-sectional view showing a structure of a pixel in a display device in an embodiment according to the present invention, taken along line A19-A20 in FIG. 57; and

[0107] FIG. 62B is a cross-sectional view showing the structure of the pixel in the display device in an embodiment according to the present invention, taken along line B15-B16 in FIG. 57.

DESCRIPTION OF EMBODIMENTS

[0108] Hereinafter, embodiments of the present invention will be described with reference to the drawings and the like. The present invention may be carried out in various embodiments, and should not be construed as being limited to any of the following embodiments. In the drawings, components may be shown schematically regarding the width, thickness, shape and the like, instead of being shown in accordance with the actual sizes, for the sake of clear illustration. The drawings are merely examples and do not limit the present invention in any way. In the specification and the drawings, components that are substantially the same as those described or shown previously bear the identical reference signs thereto (or the identical reference signs followed by letters "a", "b" or the like), and detailed descriptions thereof may be omitted. The terms "first", "second" and the like used for elements are merely provided for distinguishing the elements and do not have any other significance unless otherwise specified.

[0109] In the specification and the claims, an expression that a component is "on" another component encompasses a

case where such a component is in contact with the another component and also a case where such a component is above or below the another component, namely, a case where still another component is provided between such a component and the another component, unless otherwise specified.

[0110] In order to increase the productivity of display devices, it is needed to shorten the time from when a transparent insulating substrate is prepared until an active matrix element substrate is completed. However, for producing an active matrix element substrate including a complementary circuit that includes a transistor formed of polycrystalline silicon, eight or more photomasks are required. Polycrystalline silicon films produced by laser annealing are varied in the crystallinity, and thus have a problem of deteriorating the display quality when being used for a driving transistor.

[0111] In the meantime, a transistor formed of an oxide semiconductor requires precise control on the carrier concentration. An oxide semiconductor is a type of compound semiconductor containing a plurality of metal oxides, and thus requires, in a production process thereof, control on the composition, on the oxygen deficiency, and on impurities. In order to control the carrier concentration of a channel by contriving the device structure, it is effective to provide a back gate. However, this has problems of complicating the structure and increasing the number of photomasks needed to produce the device.

[0112] In the case where the driving transistor is formed of oxide semiconductor, a drain of the transistor is connected with a cathode of the organic EL element. Therefore, an electron transfer layer of the organic EL element needs to be formed before a light emitting element; namely, the organic EL element needs to have a so-called inverted stack structure. The organic EL element of an inverted stack structure has a problem of not having characteristics equivalent to the characteristics of an organic EL element having a normal stack structure, in which the light emitting layer is stacked on a hole transfer layer. Some of the embodiments described below provide a display device solving one or a plurality of these problems.

Embodiment 1

1-1. Transistor Structure

[0113] FIG. 1 is a cross-sectional view showing a structure of a transistor 100a in embodiment 1 according to the present invention. The transistor 100a includes a first gate electrode 104, a first insulating layer 106, an oxide semiconductor layer 112, a second insulating layer 114, and a second gate electrode 116, which are provided on a substrate 102 having an insulating surface.

[0114] The first gate electrode 104 is located to face one of two main surfaces of the oxide semiconductor layer 112 (surface facing the substrate 102). The first insulating layer 106 is located between the oxide semiconductor layer 112 and the first gate electrode 104. The second gate electrode 116 is located to face the other main surface of the oxide semiconductor layer 112 (surface opposite to the surface facing the substrate 102). The second insulating layer 114 is located between the oxide semiconductor layer 112 and the second gate electrode 116. The first gate electrode 104 and the second gate electrode 116 are located to partially overlap each other while having the first insulating layer 106, the oxide semiconductor layer 112 and the second insulating

layer 114 between the first gate electrode 104 and the second gate electrode 116. In the transistor 100a, a channel is formed in a region where the oxide semiconductor layer 112 overlaps the first gate electrode 104 and the second gate electrode 116. The first insulating layer 106 acts as a gate insulating film in a region where the oxide semiconductor layer 112 and the first gate electrode 104 overlap each other. The second insulating layer 114 acts as a gate insulating film in a region where the oxide semiconductor layer 112 and the second gate electrode 116 overlap each other.

[0115] A first transparent conductive layer 108a and a second transparent conductive layer 108b are located between the oxide semiconductor layer 112 and the first insulating layer 106. The first transparent conductive layer 108a and the second transparent conductive layer 108b are provided in contact with the oxide semiconductor layer 112. The first transparent conductive layer 108a and the second transparent conductive layer 108b are located such that one end of the first transparent conductive layer 108a and one end of the second transparent conductive layer 108b overlap the first gate electrode 104 and the second gate electrode 116. One of the first transparent conductive layer 108a and the second transparent conductive layer 108b acts as a source region, and the other of the first transparent conductive layer 108a and the second transparent conductive layer 108b acts as a drain region. In the structure shown in FIG. 1, the one ends of the first transparent conductive layer 108a and the second transparent conductive layer 108b overlap the first gate electrode 104 and the second gate electrode 116. Therefore, the oxide semiconductor layer 112 does not include any offset region (region having a high resistance). Thus, the level of on-current is increased.

[0116] A first line 110a is provided in contact with the first transparent conductive layer 108a, and a second line 110b is provided in contact with the second transparent conductive layer 108b. The first line 110a is located between the first transparent conductive layer 108a and the oxide semiconductor layer 112, and the second line 110b is located between the second transparent conductive layer 108b and the oxide semiconductor layer 112. The first line 110a and the second line 110b are respectively located in contact with the first transparent conductive layer 108a and the second transparent conductive layer 108b. This decreases the number of photolithography steps as described below. In the transistor 100a in this embodiment, A region where a channel is formed in the oxide semiconductor layer 112 is separated from the first line 110a or the second line 110b. Therefore, the oxide semiconductor layer 112 is prevented from being contaminated with a metal material usable for the first line 110a and the second line 110b.

1-2. Operations and Functions of the Transistor

[0117] In the transistor 100a, the first gate electrode 104 is located to face one of the two main surfaces of the oxide semiconductor layer 112, and the second gate electrode 116 is located to face the other main surface of the oxide semiconductor layer 112. With such a structure, a constant potential (fixed potential) may be applied to one of the first gate electrode 104 and the second gate electrode 116, so that either one of the first gate electrode 104 and the second first gate electrode 116 act as a back gate. The transistor 100a is substantially of an n-channel type. Therefore, for example, one of the first gate electrode 104 and the second gate electrode 116 may be supplied with a potential lower than a

source potential, so that the gate electrode supplied with such a potential acts as a back gate electrode. Thus, a threshold voltage of the transistor **100a** is controlled. The first gate electrode **104** and the second gate electrode **116** of the transistor **100a** may be supplied with the same gate voltage, so that the transistor **100a** acts as a dual gate transistor. Thus, the transistor **100a** increases the level of on-current and improves the frequency characteristics.

1-3. Oxide Semiconductor Layer

[**0118**] The oxide semiconductor layer **112** contains one or a plurality of elements selected from indium (In), zinc (Zn), gallium (Ga), tin (Sn), aluminum (Al), and magnesium (Mg). For example, an oxide semiconductor material used to form the oxide semiconductor layer **112** may be a four-component oxide material, a three-component oxide material, a two-component oxide material or a one-component oxide material showing semiconductor characteristics. Examples of the four-component oxide material include an $\text{In}_2\text{O}_3\text{—Ga}_2\text{O}_3\text{—SnO}_2\text{—ZnO}$ -based oxide material and the like. Examples of the three-component oxide material include an $\text{In}_2\text{O}_3\text{—Ga}_2\text{O}_3\text{—ZnO}$ -based oxide material, an $\text{In}_2\text{O}_3\text{—SnO}_2\text{—ZnO}$ -based oxide material, an $\text{In}_2\text{O}_3\text{—Al}_2\text{O}_3\text{—ZnO}$ -based oxide material, a $\text{Ga}_2\text{O}_3\text{—SnO}_2\text{—ZnO}$ -based oxide material, a $\text{Ga}_2\text{O}_3\text{—Al}_2\text{O}_3\text{—ZnO}$ -based oxide material, an $\text{SnO}_2\text{—Al}_2\text{O}_3\text{—ZnO}$ -based oxide material, and the like. Examples of the two-component oxide material include an $\text{In}_2\text{O}_3\text{—ZnO}$ -based oxide material, an $\text{SnO}_2\text{—ZnO}$ -based oxide material, an $\text{Al}_2\text{O}_3\text{—ZnO}$ -based oxide material, an MgO—ZnO -based oxide material, an $\text{SnO}_2\text{—MgO}$ -based oxide material, an $\text{In}_2\text{O}_3\text{—MgO}$ -based oxide material, and the like. Examples of the one-component oxide material include an In_2O_3 -based metal oxide material, an SnO_2 -based metal oxide material, a ZnO -based metal oxide material, and the like. The above-listed oxide semiconductors may include silicon (Si), nickel (Ni), tungsten (W), hafnium (Hf), or titanium (Ti). For example, the In—Ga—Zn—O -based oxide material is an oxide material containing at least In, Ga and Zn. There is no specific limitation on the composition ratio thereof. In other words, the oxide semiconductor layer **112** may be formed of a thin film represented by chemical formula $\text{InMO}_3(\text{ZnO})_m$ ($m>0$). M represents one or a plurality of metal elements selected from Ga, Al, Mg, Ti, Ta, W, Hf and Si. The oxide material contained in each of the four-component oxide materials, the three-component oxide materials, the two-component oxide materials and one-component oxide materials listed above is not limited to having a stoichiometric composition, but may have a composition shifted from the stoichiometric composition.

[**0119**] The oxide semiconductor layer **112** is formed by sputtering. For example, the oxide semiconductor layer **112** may be formed by use of a sputtering target compatible to any of the four-component oxide materials, the three-component oxide materials, the two-component oxide materials and the one-component oxide materials listed above and also by use of, as sputtering gas, noble gas such as argon (Ar), xenon (Xe) or the like or mixed gas of noble gas and oxygen (O_2).

[**0120**] The oxide semiconductor layer **112** desirably has a carrier concentration of about $1 \times 10^{15}/\text{cm}^3$ to $5 \times 10^{18}/\text{cm}^3$ in order to form a channel layer of the transistor **100a**. As long as the carrier concentration of the oxide semiconductor layer **112** is in this range, a normally-off transistor is formed. In

addition, an on-current/off-current ratio (on/off ratio) of about 10^7 to 10^{10} is provided.

1-4. Transparent Conductive Layers

[**0121**] The first transparent conductive layer **108a** and the second transparent conductive layer **108b** are formed of a metal oxide material, a metal nitride material, or a metal oxide nitride material, all of which are conductive. Examples of the metal nitride material usable for the first transparent conductive layer **108a** and the second transparent conductive layer **108b** include indium tin oxide ($\text{In}_2\text{O}_3\text{·SnO}_2\text{:ITO}$), indium zinc oxide ($\text{In}_2\text{O}_3\text{·ZnO:IZO}$), and tin oxide (SnO_2). Such a metal oxide material forms a good ohmic contact with the oxide semiconductor layer **112**.

[**0122**] Examples of the metal oxide material usable for the first transparent conductive layer **108a** and the second transparent conductive layer **108b** also include titanium oxide (TiO_x) and the like. Examples of the metal nitride material usable for the first transparent conductive layer **108a** and the second transparent conductive layer **108b** include titanium nitride (TiN_x), zirconium nitride (ZrN_x), and the like. Examples of the metal oxide nitride material usable for the first transparent conductive layer **108a** and the second transparent conductive layer **108b** include titanium oxide nitride (TiO_xN_y), tantalum oxide nitride (TaO_xN_y), zirconium oxide nitride (ZrO_xN_y), hafnium oxide nitride (HfO_xN_y), and the like. The metal oxide materials, the metal nitride materials, and the metal oxide nitride materials described above may contain trace amount of metal element in order to improve the conductivity. For example, titanium oxide doped with niobium ($\text{TiO}_x\text{:Nb}$) may be used. Use of such a metal oxide material, such a metal nitride material, or such a metal oxide nitride material guarantees stability even in the case where the first transparent conductive layer **108a** and the second transparent conductive layer **108b** are in contact with the first line **110a** and the second line **110b**, respectively. Namely, use of such a metal oxide material, such a metal nitride material, or such a metal oxide nitride material prevents an oxidation-reduction reaction (local cell reaction) with aluminum (Al) having a lower potential.

1-5. Insulating Layers

[**0123**] The first insulating layer **106** and the second insulating layer **114** are formed of an inorganic insulating material. Examples of the inorganic insulating material usable for the first insulating layer **106** and the second insulating layer **114** include silicon oxide, silicon nitride, silicon oxide nitride, aluminum oxide, and the like. The first insulating layer **106** and the second insulating layer **114** each have a single-layer structure, or a stack structure including a plurality of films, formed of such an organic insulating material. For example, the first insulating layer **106** may include a silicon nitride film and a silicon oxide film stacked in this order from the substrate **102** side. The second insulating layer **114** may include a silicon oxide film and a silicon nitride film stacked in this order from the oxide semiconductor layer **112** side. The first insulating layer **106** and the second insulating layer **114**, in the case of including a plurality of organic insulating films, alleviate the action of an internal stress and also improve the barrier property against water vapor or the like.

[**0124**] It is preferable that surfaces of the first insulating layer **106** and the second insulating layer **114** that are in

contact with the oxide semiconductor layer **112** are formed of a silicon oxide film, a silicon oxide nitride film or an aluminum oxide film. Since such an oxide insulating film is in contact with the oxide semiconductor layer **112** (in other words, a nitride insulating film is not in contact with the oxide semiconductor layer **112**), diffusion of impurities such as hydrogen or the like, which generates a donor in the oxide semiconductor layer **112**, is suppressed. Since the oxide insulating film is provided in contact with the oxide semiconductor layer **112**, a defect (donor) caused by oxygen deficiency is prevented from being caused to the oxide semiconductor layer **112**.

1-6. Gate Electrodes

[0125] The first gate electrode **104** and the second gate electrode **116** are formed of a metal material such as aluminum (Al), molybdenum (Mo), tungsten (W), zirconium (Zr) or the like. For example, the first gate electrode **104** and the second gate electrode **116** may each be formed of a film of aluminum (Al), a molybdenum-tungsten alloy (MoW), or the like. The first gate electrode **104** and the second gate electrode **116** may be formed of an aluminum alloy, a copper alloy, or a silver alloy. Examples of the aluminum alloy usable for the first gate electrode **104** and the second gate electrode **116** include an aluminum-neodymium alloy (Al—Nd), an aluminum-neodymium-nickel alloy (Al—Nd—Ni), an aluminum-carbon-nickel alloy (Al—C—Ni), a copper-nickel alloy (Cu—Ni), and the like. Alternatively, the first gate electrode **104** and the second gate electrode **116** may each be formed of a transparent conductive film of indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO) or the like.

1-7. Lines

[0126] The first line **110a** and the second line **110b** are formed of a metal material having a high conductivity such as aluminum (Al), copper (Cu) or the like. For example, the first line **110a** and the second line **110b** are formed of an aluminum alloy, a copper alloy, or a silver alloy. Examples of the aluminum alloy usable for the first line **110a** and the second line **110b** include an aluminum-neodymium alloy (Al—Nd), an aluminum-titanium alloy (Al—Ti), an aluminum-silicon alloy (Al—Si), an aluminum-neodymium-nickel alloy (Al—Nd—Ni), an aluminum-carbon-nickel alloy (Al—C—Ni), a copper-nickel alloy (Cu—Ni), and the like. Use of such a metal material provides heat resistance and decreases the line resistance.

1-8 Production Method

[0127] Now, a method for producing the transistor **100a** will be described. FIG. 2A shows a stage of forming the first gate electrode **104** on the substrate **102**. The substrate **102** may be, for example, a transparent insulating substrate. The transparent insulating substrate is formed of non-alkali glass such as aluminosilicate glass, aluminoborosilicate glass or the like, or quartz.

[0128] First, a first conductive film **103** is formed on one surface of the substrate **102**. Then, a resist mask is formed on the first conductive film **103** by a photolithography step, and the first gate electrode **104** is formed by an etching step. The first conductive film **103** is not limited to having any specific thickness, but is formed to have a thickness of about 100 nm to 2000 nm. It is preferable that the first gate

electrode **104** has tapered ends as seen in a cross-sectional view. The first gate electrode **104** has tapered ends and thus is covered with the first insulating layer **106** with certainty. Therefore, in the etching step of forming the first gate electrode **104**, it is preferable to perform anisotropic etching on the first conductive film **103** while chemically milling the resist mask; namely, to perform so-called taper etching. The resist mask that is left after the formation of the first gate electrode **104** is removed by use of a releasing solution or by an ashing process.

[0129] FIG. 2B shows a stage of forming the first insulating layer **106**, a second conductive film **107**, and a third conductive film **109** on the first gate electrode **104**. From the second conductive film **107**, the first transparent conductive layer **108a** and the second transparent conductive layer **108b** are formed. From the third conductive film **109**, the first line **110a** and the second line **110b** are formed. The first insulating layer **106** is formed of an inorganic insulating film. For example, the first insulating layer **106** may be a film formed of one or a plurality of materials selected from silicon oxide, silicon nitride, and silicon oxide nitride. In this case, the first insulating layer **106** is formed by plasma CVD (Chemical Vapor Deposition). Alternatively, the first insulating layer **106** may be an aluminum oxide film. In this case, the first insulating layer **106** is formed by sputtering by use of an alumina sputtering target. The first insulating layer **106** is used as a gate insulating layer. Therefore, the first insulating layer **106** is formed to have a thickness of about 100 nm to 500 nm.

[0130] The second conductive film **107** used to form the first transparent conductive layer **108a** and the second transparent conductive layer **108b** is formed of a metal oxide material, a metal nitride material or a metal oxide nitride material, all of which are conductive. The second conductive film **107** is formed by sputtering. The second conductive film **107** used to form the first transparent conductive layer **108a** and the second transparent conductive layer **108b** is formed of, for example, a conductive metal oxide material to have a thickness of 30 nm to 200 nm. The third conductive film **109** used to form the first line **110a** and the second line **110b** is formed of a metal material or an alloy material by sputtering. The third conductive film **109** used to form the first line **110a** and the second line **110b** is formed of a metal material to have a thickness of 200 nm to 2000 nm in order to have a low resistance.

[0131] FIG. 3A shows a lithography step of forming the first line **110a**, the second line **110b**, the first transparent conductive layer **108a** and the second transparent conductive layer **108b**. In this example, a multi-gradation exposure method (halftone exposure method) is used. Specifically, the patterns of the first line **110a**, the second line **110b**, the first transparent conductive layer **108a** and the second transparent conductive layer **108b** are formed by one photomask.

[0132] A positive photoresist film **205** is formed on the third conductive film **109**. A multi-gradation photomask **201** is used for exposing the photoresist mask **205** to light. A multi-gradation photomask is available in two types: a gray tone photomask, which has a multi-gradation scale pattern (like a pattern **203**) having slits of a resolution equal to, or lower than, the resolution of an exposure device and realizes multi-gradation exposure by the slits blocking a part of light; and a halftone photomask, which realizes multi-gradation exposure by use of a semi-transmissive film. In this embodiment, both types of multi-gradation photomask are usable.

As a result of using the multi-gradation photomask **201** for the exposure, the photoresist film **205** has three portions formed therein, namely, an exposed portion, a gradation-exposed portion, and a non-exposed portion.

[0133] Then, the photoresist film **205** is developed to form a resist mask **207a** including regions having different thicknesses as shown in FIG. 3B. As shown in FIG. 3B, the resist mask **207a** is thicker in a region corresponding to regions of the third conductive film **109** where the first line **110a** and the second line **110b** are to be formed, and is thinner in the remaining region.

[0134] The third conductive film **109** and the second conductive film **107** are etched by use of the resist mask **207a**. There is no specific limitation on the conditions for the etching. For example, the third conductive film **109**, which is formed of a metal material, is wet-etched by use of a mixed acid etchant, and the second conductive film **107**, which is formed of a metal oxide material, is dry-etched by use of chlorine-based gas. On this stage, the first transparent conductive layer **108a** and the second transparent conductive layer **108b** are formed. After the etching, an ashing process is performed to remove the thinner region of the resist mask **207a** to expose a surface of the third conductive film **109**. FIG. 4A shows a resist mask **207b** after the ashing process. The resist mask **207b** is left on the third conductive film **109**.

[0135] Next, etching is performed on the exposed third conductive film **109**. This etching is wet-etching performed by use of, for example, a mixed acid etchant. The second conductive film **107**, which is formed of a metal oxide material or the like, is not easily etched away by the mixed acid etchant, and thus the selection ratio is relatively high. Therefore, the shape of the first transparent conductive layer **108a** and the second transparent conductive layer **108b** below the third conductive film **109** is kept unchanged. FIG. 4B shows a stage where the first line **110a** and the second line **110b** are formed as a result of the etching performed on the third conductive film **109**. After the third conductive film **109** is etched, the resist mask **207b** is removed by ashing.

[0136] Surfaces of the first transparent conductive layer **108a** and the second transparent conductive layer **108b** already formed are exposed to oxygen plasma by the ashing process. However, titanium (Ti), tantalum (Ta), hafnium (Hf) or zirconium (Zr) contained as a component of the first transparent conductive layer **108a** and the second transparent conductive layer **108b** is conductive even when being oxidized. Therefore, even though being exposed to oxygen plasma, the surfaces of the first transparent conductive layer **108a** and the second transparent conductive layer **108b** form a good contact with the oxide semiconductor layer **112** formed in a later step.

[0137] FIG. 5A shows a stage of forming the oxide semiconductor layer **112**. The oxide semiconductor layer **112** is formed to cover the first transparent conductive layer **108a**, the second transparent conductive layer **108b**, the first line **110a**, and the second line **110b**. The oxide semiconductor layer **112** is formed by sputtering. As a sputtering target, a sintered oxide semiconductor material is used. The oxide semiconductor layer **112** is formed to have a thickness of 20 nm to 100 nm, for example, 30 nm to 50 nm.

[0138] FIG. 5B shows a stage of forming the second insulating layer **114** and a fourth conductive film **115** on the oxide semiconductor layer **112**. The second insulating layer **114** is formed in substantially the same manner as the first

insulating layer **106**. The fourth conductive film **115** is formed in substantially the same manner as the first conductive film **103**. Then, the fourth conductive film **115** is etched to form the second gate electrode **116**. Thus, the transistor **110a** shown in FIG. 1 is produced.

[0139] According to the method for producing the transistor **100a** in this embodiment, a multi-gradation photomask is used to decrease the number of photomasks required to produce the transistor **100a**. The use of the multi-gradation photomask allows a plurality patterns (the first transparent conductive layer **108a**, the second transparent conductive layer **108b**, the first line **110a** and the second line **110b**) to be formed by performing exposure merely once. This increases the productivity of integrated circuit elements each including the transistor **100a** and also decreases the production cost.

[0140] As shown in FIG. 1, neither the first line **110a** nor the second line **110b** overlaps the first gate electrode **104** or the second gate electrode **116**. The first line **110a** and the second line **110b** are located as far as possible from the channel region of the transistor **100a** (region where the first gate electrode **104** and the second gate electrode **116** overlap the oxide semiconductor layer **112**), so that the channel region is prevented from being contaminated with a metal element. For example, copper (Cu), which may be used as a material of the first line **110a** and the second line **110b**, is a killer impurity to the oxide semiconductor, which is an n-type semiconductor (impurity that deteriorates the characteristics of the oxide semiconductor and destroys the oxide semiconductor). In this embodiment, the first line **110a** and the second line **110b** are located as far as possible from the channel region of the transistor **110a**. Therefore, even if the first line **110a** and the second line **110b** contain copper (Cu), the oxide semiconductor layer **112** is suppressed from being contaminated with copper (Cu).

Embodiment 2

[0141] In embodiment 2, an example of display device **120** including a transistor having substantially the same structure as that of the transistor described in embodiment 1 will be described. As shown in FIG. 6, the display device **120** includes a display region **121** including a plurality of pixels **122**, a scanning line driving circuit **123**, and a data line driving circuit **125**. Although not shown in FIG. 6, the plurality of pixels **122** each include an organic EL element acting as a display element and a transistor driving the organic EL element.

2-1. Equivalent Circuit

[0142] FIG. 7 is an equivalent circuit diagram of each of the pixels **122** included in the display device **120** in this embodiment. The pixel **122** includes a selection transistor **124**, a driving transistor **126**, a capacitance element **128**, and an organic EL element **130**. The selection transistor **124** and the driving transistor **126** each have substantially the same structure as that of the transistor **100a** described in embodiment 1. Namely, FIG. 7 shows the transistors of a dual gate structure. The selection transistor **124** includes a first gate electrode **104b** and a second gate electrode **116b**, and the driving transistor **126** includes a first gate electrode **104a** and a second gate electrode **116a**.

[0143] In FIG. 7, the selection transistor **124** and the driving transistor **126** are each of an n-channel type. Gates

of the selection transistor **124** (the first gate electrode **104b** and the second gate electrode **116b**) are connected with a gate signal line **132a**. One of input/output terminals (source and drain) of the selection transistor **124** is connected with a data signal line **134**, and the other of the input/output terminals is connected with gates of the driving transistor **126** (the first gate electrode **104a** and the second gate electrode **116a**). The gates of the driving transistor **126** (the first gate electrode **104a** and the second gate electrode **116a**) are connected with the other of the input/output terminals of the selection transistor **124**. A drain of the driving transistor **126** is connected with the organic EL element **130**, and a source of the driving transistor **126** is connected with a second common line **136b**. One of two terminals of the capacitance element **128** is connected with the other of the input/output terminals (source and drain) of the selection transistor **124**. The other of the two terminals of the capacitance element **128** is connected with a first common line **136a**. The first common line **136a** and the second common line **136b** are supplied with, for example, ground potential. [0144] One of two terminals of the organic EL element **130** is connected with the drain of the driving transistor **126**, and the other of the two terminals of the organic EL element **130** is connected with a power supply line **138**. The power supply line **138** is supplied with a power supply potential VDD, which is higher than the potential of each of the common lines **136a** and **136b**. In this embodiment, the terminal of the organic EL element **130** that is connected with the drain of the driving transistor **126** is a cathode electrode, and the terminal of the organic EL element **130** that is connected with the power supply line **138** is an anode electrode.

2-2. Pixel Structure

[0145] FIG. 8 shows an example of planar structure of a pixel **122a** corresponding to the equivalent circuit shown in FIG. 7. FIG. 9A shows a cross-sectional structure taken along line A1-A2 in FIG. 8, and FIG. 9B shows a cross-sectional structure taken along line B1-AB in FIG. 8. FIG. 9A shows a cross-sectional structure of the driving transistor **126** and the organic EL element **130**. FIG. 9B shows a cross-sectional structure of the selection transistor **124** and the capacitance element **128**. The following description will be made with reference to FIG. 8, FIG. 9A and FIG. 9B. In the plan view of the pixel **122a** shown in FIG. 8A, the structure of the organic EL element **130** is omitted.

2-2-1. Driving Transistor

[0146] The driving transistor **126** has substantially the same structure as that of the transistor **100a** described in embodiment 1. Specifically, the driving transistor **126** includes the first gate electrode **104a**, the first insulating layer **106**, a first oxide semiconductor layer **112a**, the second insulating layer **114**, and the second gate electrode **116a**, which are stacked. The first gate electrode **104a** is provided between the substrate **102** and the first insulating layer **106**. The second gate electrode **116a** is provided on the second insulating layer **114** (on the surface of the second insulating layer **114** opposite to the surface thereof facing the substrate **102**).

[0147] The first transparent conductive layer **108a** and the second transparent conductive layer **108b** are provided between the first insulating layer **106** and the first oxide

semiconductor layer **112a**. The first transparent conductive layer **108a** and the second transparent conductive layer **108b** are provided to hold the first gate electrode **104a** and the second gate electrode **116a** therebetween as seen in a plan view. The first transparent conductive layer **108a** and the second transparent conductive layer **108b** are provided in contact with the first oxide semiconductor layer **112a**.

[0148] The first transparent conductive layer **108a** of the driving transistor **126**, or a region of the driving transistor **126** where the first transparent conductive layer **108a** is in contact with the first oxide semiconductor layer **112a**, is a drain region. The second transparent conductive layer **108b** of the driving transistor **126**, or a region of the driving transistor **126** where the second oxide semiconductor layer **112b** is in contact with the second transparent conductive layer **108b**, is a source region.

[0149] The second transparent conductive layer **108b** of the driving transistor **126** is electrically connected with the first oxide semiconductor layer **112a**, the first common line **136a** and the second common line **136b**. The first common line **136a** is provided in the same layer structure as that of the first gate electrode **104a**, and the second common line **136b** is provided in the same layer structure as that of the data signal line **134** which electrically connected to the selection transistor **124**. The first common line **136a** and the second transparent conductive layer **108b** are electrically connected with each other via a first contact hole **117a** formed in the first insulating layer **106**. The second common line **136b** is in direct contact with a top surface of the second transparent conductive layer **108b**.

[0150] The first insulating layer **106** includes, for example, a first silicon nitride film **141a** and a first silicon oxide film **140a** stacked in this order from the substrate **102** side. The second insulating layer **114** includes a second silicon oxide film **140b** and a second silicon nitride film **141b** stacked in this order from the first oxide semiconductor layer **112a** side.

[0151] A channel of the driving transistor **126** is formed in a region where the first oxide semiconductor layer **112a** overlaps the first gate electrode **104a** and the second gate electrode **116a**. Therefore, the first oxide semiconductor layer **112a** is provided in contact with the silicon oxide films **140a** and **140b** in the region where the channel is formed. The first oxide semiconductor layer **112a** is provided in contact with the insulating oxide films, and thus generation of oxygen deficiency in the first oxide semiconductor layer **112a** is suppressed. It is desirable that the silicon oxide films **140a** and **140b** do not have oxygen deficiency so as not to draw out oxygen from the first oxide semiconductor layer **112a**. Rather, it is even preferable that the silicon oxide films **140a** and **140b** contain an excessive amount of oxygen. A reason for this is that the silicon oxide films **140a** and **140b**, in the case of containing an excessive amount of oxygen, may be a source of oxygen for the first oxide semiconductor layer **112a**. The “silicon oxide film containing an excessive amount of oxygen” encompasses a silicon oxide film containing an excessive amount of oxygen with respect to the chemical stoichiometric composition, and also encompasses a silicon oxide film containing an excessive amount of oxygen in a lattice thereof. The first insulating layer **106** and the second insulating layer **114** may be formed of silicon oxide nitride or aluminum oxide instead of silicon oxide.

[0152] The driving transistor **126** is covered with a flattening layer **142**. The flattening layer **142** is formed of an organic resin material such as, for example, an acrylic resin,

a polyimide resin, an epoxy resin, a polyamide resin or the like. The flattening layer **142** is formed as follows. A composition containing a precursor of an organic resin material is applied, and a surface of the film formed by the composition is flattened by a levelling action of the film. In another embodiment, the flattening layer **142** may be formed as follows. An inorganic insulating film such as a silicon oxide film or the like is formed by plasma CVD or the like, and then a surface of the inorganic insulating film is flattened by chemical mechanical polishing (CMP).

[0153] An opening **144** is provided in the flattening layer **142** and the second insulating layer **114**. A first electrode **146**, which is the cathode electrode of the organic EL element **130**, is located to overlap the opening **144**. The organic EL element **130** is formed of a plurality of layers stacked in the region of the opening **144**.

[0154] In this embodiment, the driving transistor **126** has a dual gate structure, and thus improves the current driving capability thereof. Therefore, the driving transistor **126** provides a sufficient level of current to drive the organic EL element **130**. Even if the operating point of the organic EL element **130** is changed, the driving transistor **126** provides constant current driving in accordance with the change in the operating point.

2-2-2. Selection Transistor

[0155] The selection transistor **124** has substantially the same structure as that of the transistor **100a** described in embodiment 1. Specifically, the selection transistor **124** includes the first gate electrode **104b**, the first insulating layer **106**, a second oxide semiconductor layer **112b**, the second insulating layer **114**, and the second gate electrode **116b**, which are stacked. A channel of the second transistor **124** is formed in a region where the second oxide semiconductor layer **112b** overlaps the first gate electrode **104b** and the second gate electrode **116b**. A third transparent conductive layer **108c** and a fourth transparent conductive layer **108d** are provided between the first insulating layer **106** and the second oxide semiconductor layer **112b**. The third transparent conductive layer **108c** and the fourth transparent conductive layer **108d** are provided in contact with the second oxide semiconductor layer **112b**, and thus act as a source region and a drain region. The third transparent conductive layer **108c** and the fourth transparent conductive layer **108d** are provided to hold the first gate electrode **104b** and the second gate electrode **116b** therebetween as seen in a plan view.

[0156] The third transparent conductive layer **108c** is electrically connected with the data signal line **134**. The data signal line **134** is provided in the same layer structure as that of the line layer **110** provided between the transparent conductive layer **108** and the oxide semiconductor layer **112** described in the embodiment 1. The data signal line **134** is in direct contact with a top surface of the third transparent conductive layer **108c**. The second oxide semiconductor layer **112b** extends to a region where the data signal line **134** is located and covers the data signal line **134**. The data signal line **134** is in direct contact with the third transparent conductive layer **108c** and thus has a larger contact area size than in the case where the data signal line **134** is connected with the third transparent conductive layer **108c** via a contact hole. Therefore, the contact resistance is decreased. A top surface and side surfaces of the data signal line **134** are covered with the second oxide semiconductor layer **112b**,

and thus the data signal line **134** is not exposed to an oxidizing atmosphere or a reducing atmosphere during the production of the display device **120**. Therefore, the data signal line **134** suppresses the resistance at a surface thereof from increasing.

2-2-3. Capacitance Element

[0157] The capacitance element **128** includes a first capacitance electrode **160a**, the first insulating layer **106**, the fourth transparent conductive layer **108d**, and a second capacitance electrode **160b**. The first capacitance electrode **160a** is provided in the same layer structure as that of the first gate electrode **104**, and the second capacitance electrode **160b** is provided in the same layer structure as that of the data signal line **134**. The fourth transparent conductive layer **108d** is electrically connected with the second capacitance electrode **160b**, and thus substantially acts as the electrode of the capacitance element **128**.

[0158] The second oxide semiconductor layer **112b** and the second insulating layer **114** are provided on the second capacitance electrode **160b**. The second capacitance electrode **160b** is electrically connected with the second gate electrode **116a** via a second contact hole **117b** running through the second insulating layer **114** and the second oxide semiconductor layer **112b**.

2-2-4. Organic EL Element

[0159] The organic EL element **130** includes the first electrode **146** corresponding to the cathode electrode, an electron transfer layer **148**, an electron injection layer **150**, a light emitting layer **152**, a hole transfer layer **154**, a hole injection layer **156**, and a second electrode **158** corresponding to the anode electrode, which are stacked from the substrate **102** side. A structure of an organic EL element in which a hole transfer layer, a light emitting layer, an electron transfer layer, and a cathode electrode are stacked in this order from the side of the anode electrode close to the substrate is referred to as a "normal stack structure". In the organic EL element **130** in this embodiment, the electron transfer layer **148**, the light emitting layer **152**, the hole transfer layer **154** and the like are stacked in this order from the side of the cathode electrode close to the substrate **102**. This structure is referred to as an "inverted stack structure". In this embodiment, the driving transistor **126** is of an n-channel type. Therefore, if the organic EL element has a normal stack structure, the source is connected with the anode electrode. In this case, there is a problem that the level of drain current of the driving transistor is changed in accordance with the change in the characteristics of the organic EL element. However, in the case where the organic EL element **130** has an inverted stack structure as in this embodiment, the drain of the n-channel type driving transistor **126** is connected with the cathode of the organic EL element **130**. Therefore, a circuit configuration in which the drain current is not much influenced by the change in the characteristics of the organic EL element **130** is provided.

[0160] On a top surface of the flattening layer **142** and in the opening **144** provided in the flattening layer **142** and the second insulating layer **114**, the electron transfer layer **148**, the electron injection layer **150**, the light emitting layer **152**, the hole transfer layer **154**, the hole injection layer **156**, and the second electrode **158** acting as the anode electrode are stacked. A region where a stacked body including these

elements overlaps the first electrode **146** corresponding to the cathode electrode is a light emitting region of the organic EL element **130**.

[0161] The organic EL element **130** in this embodiment is of a so-called bottom emission type, which outputs light toward the substrate **102**. Hereinafter, each of the layers included in the organic EL element **130** will be described in detail.

2-2-4-1. Cathode Electrode

[0162] As a material of a cathode electrode of an organic EL element, an aluminum-lithium alloy (AlLi), a magnesium-silver alloy (MgAg) or the like is conventionally used. However, these materials are easily deteriorated by the influence of oxygen or moisture in the air, and thus are difficult to handle. These materials for the cathode electrode are metal materials, and thus are not suitable to an organic EL element that has an inverted stack structure and is of a bottom emission type.

[0163] In the organic EL element **130** in this embodiment, the first electrode **146**, which is a cathode electrode, is formed of a transparent conductive material, and thus a bottom emission type structure is realized for the organic EL element **130**. Specifically, the first transparent conductive layer **108a** of the driving transistor **126** extends to the region of the organic EL element **130** to act as the first electrode **146**, which is a cathode electrode. With such an arrangement, the driving transistor **126** and the organic EL element **130** are electrically connected with each other with a simple structure. For example, in the case where an interlayer insulating layer is provided between the driving transistor and the organic EL element, a contact hole needs to be provided to connect the driving transistor and the organic EL element. By contrast, the structure of the first pixel **122a** in this embodiment does not require a contact hole.

[0164] The first electrode **146** as the cathode electrode is formed of the same conductive film as that of the first transparent conductive layer **108a**. The first transparent conductive layer **108a** is formed of a metal oxide material, a metal nitride material, or a metal oxide nitride material, all of which are conductive. A conductive film formed of such a material has a bandgap of 2.8 eV or greater, preferably of 3.0 eV or greater, and therefore transmits almost all of light of a visible region. Therefore, such a material is usable for an electrode on the light output side of the organic EL element **130**.

[0165] On the first electrode **146** corresponding to the cathode electrode, the first oxide semiconductor layer **112a** extending from the driving transistor **126** may be provided. The oxide semiconductor layer **112a** has a bandgap of 3 eV or greater, and thus is visible light-transmissive. As described below, in this embodiment, the electron transfer layer **148** is formed of a metal oxide. The first oxide semiconductor layer **112a** formed of the same material, or the same type of material, as the electron transfer layer **148** is located between the electron transfer layer **148** and the first electrode **146** corresponding to the cathode electrode, so that formation of an electron injection barrier is prevented. In other words, the first oxide semiconductor layer **112a** extending from the channel region of the driving transistor **126** may be used as a part of the electron transfer layer **148** in contact with the first electrode **146** corresponding to the cathode electrode.

2-2-4-2. Electron Transfer Layer

[0166] The electron transfer layer **148** is formed of a metal oxide material. Examples of the metal oxide material usable for the electron transfer layer **148** include substantially the same materials described in embodiment 1, specifically, a four-component oxide material, a three-component oxide material, a two-component oxide material, and a one-component oxide material. These metal oxide materials may be in an amorphous state, a crystalline state or a mixed phase of an amorphous state and a crystalline state. The electron transfer layer **148** is formed of, for example, one or a plurality of materials selected from an oxide of indium, an oxide of zinc, an oxide of gallium (Ga), and an oxide of tin (Sn). Such a metal oxide material should not absorb visible light and needs to be transparent, and thus is required to have a bandgap of 3.0 eV or greater. The electron transfer layer **148** may have a maximum possible thickness to prevent short circuiting between the anode electrode and the cathode electrode. The electron transfer layer **148** may be formed by sputtering, vacuum vapor deposition, application or the like. The electron transfer layer **148** is formed by such a method to have a thickness of 50 nm to 1000 nm.

[0167] The electron transfer layer **148** has a carrier concentration of $1/10$ or less, preferably $1/100$ or less, of that of the oxide semiconductor layer **112a**. In other words, the carrier concentration of the region where the oxide semiconductor layer **112a** is in contact with the electron transfer layer **148** is at least 10 times, preferably 100 times, the carrier concentration of the electron transfer layer **148**. Specifically, the carrier concentration of the electron transfer layer **148** is 10^{13} to $10^{17}/\text{cm}^3$, whereas the carrier concentration of the oxide semiconductor layer **112a** is 10^{15} to $10^{19}/\text{cm}^3$. The difference between the carrier concentrations of the electron transfer layer **148** and the oxide semiconductor layer **112a** is at least one digit, preferably at least two digits. The oxide semiconductor layer **112a** has a carrier concentration of 10^{15} to $10^{19}/\text{cm}^3$, and thus decreases the resistance loss in the electric connection between the driving transistor **126** and the organic EL element **130**, and suppresses the driving voltage from increasing. In the case where the carrier concentration of the electron transfer layer **148** is $10^{20}/\text{cm}^3$ or greater, the excited state in the light emitting layer **152** is deactivated and the light emission efficiency is decreased. By contrast, in the case where the carrier concentration of the electron transfer layer **148** is less than $10^{13}/\text{cm}^3$, the number of carriers supplied to the light emitting layer **152** is decreased and thus a sufficient level of luminance is not provided. As described above, the oxide semiconductor layer **112a** extending from the driving transistor **126** is provided in contact with the electron transfer layer **148**, and the carrier concentrations of the oxide semiconductor layer **112a** and the electron transfer layer **148** are made different from each other, so that the driving voltage is prevented from increasing and the light emission efficiency of the organic EL element **130** is improved.

2-2-4-3. Electron Injection Layer

[0168] In an organic EL element, an electron injection layer is used in order to decrease the energy barrier and thus to inject the electrons from the cathode electrode into an electron transfer material. In this embodiment, the electron injection layer **150** is used in order to allow the electrons to be injected easily from the electron transfer layer **148**

formed of an oxide semiconductor into the light emitting layer **152**. Thus, the electron injection layer **150** is provided between the electron transfer layer **148** and the light emitting layer **152**.

[0169] It is desirable that the electron injection layer **150** is formed of a material having a small work function in order to allow the electrons to be injected easily into the light emitting layer **150** formed of an organic material. The electron injection layer **150** is formed of an oxide of calcium (Ca) and an oxide of aluminum (Al). The electron injection layer **150** is preferably formed of, for example, C12A7 ($12\text{CaO} \cdot 7\text{Al}_2\text{O}_3$) electride. C12A7 ($12\text{CaO} \cdot 7\text{Al}_2\text{O}_3$) electride has semiconductor characteristics, is controllable to have a desired level of resistance from a high resistance to a low resistance, and has a work function of 2.4 eV to 3.2 eV, which is about the same as that of an alkaline metal. For these reasons, C12A7 ($12\text{CaO} \cdot 7\text{Al}_2\text{O}_3$) electride is preferably usable for the electron injection layer **150**.

[0170] The electron injection layer **150** of C12A7 electride is formed by sputtering by use of a polycrystal of C12A7 electride as a target. C12A7 electride has semiconductor characteristics, and thus the electron injection layer **150** may be formed to have a thickness of 1 nm to 100 nm. Regarding C12A7 electride, it is preferable that the molar ratio of Ca:Al is in the range of 13:13 to 11:16. C12A7 electride is formed by sputtering and thus is preferably amorphous. Alternatively, C12A7 electride may be crystalline.

[0171] C12A7 electride is stable in the atmosphere, and thus has an advantage of being easier to handle than an alkaline metal compound conventionally used for an electron injection layer such as lithium fluoride (LiF), lithium oxide (Li_2O), sodium chloride (NaCl), potassium chloride (KCl), or the like. Use of C12A7 electride makes it unnecessary to work in dry air or inactive gas during the formation of the organic EL element **130**. The conditions for the formation of the organic EL element **130** are alleviated.

[0172] C12A7 electride has a large ionization potential. Therefore, the electron injection layer **150**, when being located to face the hole transfer layer **154** while having the light emitting layer **152** between the electron injection layer **150** and the hole injection layer **154** therebetween, acts as a hole block layer. Namely, the electron injection layer **150** formed of C12A7 electride is provided between the electron transfer layer **148** and the light emitting layer **152**, so that holes injected into the light emitting layer **152** are suppressed from running to the first **146** as the cathode electrode, and thus the light emission efficiency is improved.

2-2-4-4. Light Emitting Layer

[0173] The light emitting layer **152** may be formed of any of various materials. For example, the light emitting layer **152** may be formed of a fluorescent compound emitting fluorescence or phosphorescent compound emitting phosphorescence.

[0174] Examples of light emitting material emitting blue light usable for the light emitting layer **152** include N,N'-bis[4-(9H-carbazole-9-yl)phenyl]-N,N'-diphenylstilbene-4,4'-diamine (YGAS2S), 4-(9H-carbazole-9-yl)-4'-(10-phenyl-9-anthryl)triphenylamine (YGAPA), and the like. Examples of light emitting material emitting green light usable for the light emitting layer **152** include N-(9,10-diphenyl-2-anthryl)-N,9-diphenyl-9H-carbazole-3-amine (2PCAPA), N-[9,10-bis(1,1'-biphenyl-2-yl)-2-anthryl]-N,9-diphenyl-9H-carbazole-3-amine (2PCABPhA), N-(9,10-di-

phenyl-2-anthryl)-N,N',N'-triphenyl-1,4-phenylenediamine (2DPAPA), N-[9,10-bis(1,1'-biphenyl-2-yl)-2-anthryl]-N,N',N'-triphenyl-1,4-phenylenediamine (2DPABPhA), N-[9,10-bis(1,1'-biphenyl-2-yl)]-N-[4-(9H-carbazole-9-yl)phenyl]-N-phenylanthracene-2-amine (2YGABPhA), N,N,9-triphenylanthracene-9-amine (DPhAPhA), and the like. Examples of light emitting material emitting red light usable for the light emitting layer **152** include N,N,N',N'-tetrakis(4-methylphenyl)tetracene-5,11-diamine (p-mPhTD), 7,13-diphenyl-N,N,N',N'-tetrakis(4-methylphenyl)acenaphtho[1,2-a]fluoranthene-3,10-diamine (p-mPhAFD), and the like. A phosphorescent material such as bis[2-(2'-benzo[4,5- α]thienyl)pyridinato-N,C^{3'}]iridium(III)acetylacetonate ($\text{Ir}(\text{btp})_2(\text{acac})$) or the like is also usable.

[0175] The light emitting layer **152** may be formed of any of various known materials other than the above-listed materials. The light emitting layer **152** may be formed by vapor deposition, transfer, spin-coating, spray-coating, gravure printing, or the like. The light emitting layer **152** may have an optionally selected thickness, and has a thickness of, for example, 10 nm to 100 nm.

2-2-4-5. Hole Transfer Layer

[0176] The hole transfer layer **154** is formed of a material having hole transferability. The hole transfer layer **154** is formed of, for example, an arylamine-based compound, an amine compound containing a carbazole group, an amine compound containing a fluorene derivative, or the like. Examples of materials usable for the hole transfer layer **154** include organic materials such as 4,4'-bis[N-(naphthyl)-N-phenyl-amino]biphenyl (α -NPD), N,N'-bis(3-methylphenyl)-(1,1'-biphenyl)-4,4'-diamine (TPD), 2-TNANA, 4,4',4''-tris(N-(3-methylphenyl)N-phenylamino)triphenylamine (MTDATA), 4,4'-N,N'-dicarbazolebiphenyl (CBP), 4,4'-bis[N-(9,9-dimethylfluorene-2-yl)-N-phenylamino]biphenyl (DFLDPBi), 4,4'-bis[N-(spiro-9,9'-bifluorene-2-yl)-N-phenylamino]biphenyl (BSPB), spiro-NPD, spiro-TPD, airo-TAD, TNB, and the like.

[0177] The hole transfer layer **154** is formed of a common film formation method such as vacuum vapor deposition, application or the like. The hole transfer layer **154** is formed by such a method to have a thickness of 10 nm to 500 nm. The hole transfer layer **154** may be omitted.

2-2-4-6. Hole Injection Layer

[0178] The hole injection layer **156** is formed of a material having a high capability of injecting holes into an organic layer. Examples of materials having a high capability of injecting holes and usable for the hole injection layer **156** include metal oxides such as an oxide of molybdenum, an oxide of vanadium, an oxide of ruthenium, an oxide of tungsten, an oxide of manganese and the like. Examples of materials having a high capability of injecting holes and usable for the hole injection layer **156** also include organic compounds such as phthalocyanine (H_2Pc), copper (II) phthalocyanine (CuPc), vanadylphthalocyanine (VoPc), 4,4',4''-tris(N,N-diphenylamino)triphenylamine (TDATA), 4,4',4''-tris(N-(3-methylphenyl)-N-phenylamino)triphenylamine (MTDATA), 4,4'-bis[N-(4-diphenylaminophenyl)-N-phenylamino]biphenyl (DPAB), 4,4'-bis[N-{4-[N'-(3-methylphenyl)-N'-phenylamino]phenyl}-N-phenylamino]biphenyl (DNPTD), 1,3,5-tris[N-(4-diphenylaminophenyl)-N-phenylamino]benzene (DPA3B), 3-[N-(9-phenylcarbazole-

3-yl)-N-phenylamino]-9-phenylcarbazole (PCzPCA1), 3,6-bis[N-(9-phenylcarbazole-3-yl)-N-phenylamino]-9-phenylcarbazole (PCzPCA2), 3-[N-(1-naphthyl)-N-(9-phenylcarbazole-3-yl)amino]-9-phenylcarbazole (PCzPCN1), 2,3,6,7,10,11-hexacyano-1,4,5,8,9,12-hexaazatriphenylene (HAT-CN), and the like.

[0179] The hole injection layer 156 is formed of a common film formation method such as vacuum vapor deposition, application or the like. The hole injection layer 156 is formed by such a method to have a thickness of 1 nm to 100 nm.

2-2-4-7. Anode Electrode

[0180] The second electrode 158 corresponding to the anode electrode is formed of a metal material, an alloy or a conductive compound having a high work function (specifically, 4.0 eV or greater). The second electrode 158 corresponding to the anode electrode is formed of, for example, indium tin oxide (ITO), indium zinc oxide (IZO), indium oxide containing tungsten oxide and zinc oxide (IWZO), or the like. The second electrode 158 corresponding to the anode electrode of such a conductive metal oxide material is formed by vacuum vapor deposition or sputtering. In this embodiment, the organic EL element 130 is of a bottom emission type. Therefore, it is preferable that the second electrode 158 corresponding to the anode electrode is light reflective or has a light reflective surface. A film of a conductive metal oxide such as indium tin oxide (ITO), indium zinc oxide (IZO) or the like is light-transmissive. Therefore, the second electrode 158 may include a metal film of aluminum (Al), silver (Ag) or the like at a surface thereof that is opposite to a surface facing the hole injection layer 156. Although not shown in FIG. 8, FIG. 9A and FIG. 9B, a passivation layer blocking transmission of oxygen (O₂) or moisture (H₂O) may be provided on the second electrode 158 corresponding to the anode electrode in substantially the entirety of the display region 121.

[0181] As described above, in this embodiment, the pixel 122a in which the driving transistor 126 exhibiting n-channel type conductivity and the organic EL element 130 are electrically connected with each other is realized. In this case, the organic EL element 130 may have an inverted stack structure, in which the electron transfer layer 148, the electron injection layer 150, the light emitting layer 152, the hole transfer layer 154, the hole injection layer 156 and the like are stacked appropriately from the side of the first electrode 146, which is the cathode electrode. Since the first electrode 146, which is the cathode electrode, does not need to be formed of an alkaline metal material, the reliability of the display device 120 is improved. In addition, the electron transfer layer 148 and the electron injection layer 150, which are located in lower layers, are formed of an inorganic insulating material. Therefore, even if an organic layer is formed on these inorganic insulating layers, the characteristics are suppressed from decreasing by denaturing or the like. Thus, the characteristics of the organic EL element are stabilized.

2-3. Transistor Structure

[0182] As shown in FIG. 9A and FIG. 9B, the pixel 122a in this embodiment has a structure in which the anode electrode 158 covers the entire surfaces of the driving transistor 126 and the selection transistor 124. The driving

transistor 126 and the selection transistor 124 each have a dual gate structure; specifically, the oxide semiconductor layer 112, where the channel region is formed, is provided between the first gate electrode 104 and the second gate electrode 116.

[0183] FIG. 10A is a cross-sectional view of a bottom gate type transistor 300. The transistor 300 includes a gate electrode 304, a first electrode 306, a first transparent conductive layer 308a, a second transparent conductive layer 308b, a first line 310a, a second line 310b, an oxide semiconductor layer 312, a second insulating layer 314, a flattening layer 342, and an anode electrode 358, which are stacked on a substrate 302. In the bottom gate type transistor 300, the back channel side (the side of the oxide semiconductor layer 312 facing the anode electrode 358) is likely to be influenced by the anode electrode 358. Specifically, the anode electrode 358 has a positive potential, and an interface between the oxide semiconductor layer 312 and the second insulating layer 314 (back channel interface), and the anode electrode 358, are separated from each other by an interval of about 3 μm to 5 μm. Therefore, positive charges are accumulated on the back channel side of the oxide semiconductor layer 312. When the positive charges are easily accumulated on the back channel side, there occurs a problem that the threshold voltage of the transistor 300 is shifted to a negative side (the transistor 300 becomes a normally-off transistor).

[0184] This phenomenon will be described with reference to FIG. 10B based on a method for driving a display device. While the display device is driven, as shown in FIG. 10B, a period T_g in which an on-voltage V_{gon} is applied to the gate electrode 304 of the transistor 300 that drives the organic EL element 300 is much shorter than one frame period T_f (T_f > T_g). In a period, other than the period in which a positive on-voltage V_{gon} is applied to the gate electrode 304 of the transistor 300, namely, in the period (T_f - T_g), a negative off-voltage V_{goff} is applied to the gate electrode 304. To the anode electrode 358, a positive constant voltage (VDD) is kept applied. Therefore, charges in the second insulating layer 314 and the flattening layer 342 are drifted by an electric field generated in the anode electrode 358 and the gate electrode 304, and as a result, the positive charges are accumulated on the back channel side.

[0185] In order to solve such an inconvenience, it is preferable that gate electrodes are provided above and below the oxide semiconductor layer 112 as in this embodiment. In this case, the second gate electrode 116 is grounded to have a constant potential or is supplied with the same voltage as that of the first electrode 104, so that the potential on the back channel side is stabilized.

[0186] FIG. 11A shows an embodiment of the transistor 100a. In this embodiment, the transistor 100a has a structure in which the first gate electrode 104 in a lower layer and the second gate electrode 116 in an upper layer each overlap both of the first transparent conductive layer 108a and the second transparent conductive layer 108b, which correspond to the source and drain electrodes. The first gate electrode 104 having width W_{bottom} in a channel length direction overlaps each of the first transparent conductive layer 108a and the second transparent conductive layer 108b by width W_{ov1}. The second gate electrode 116 having width W_{top} in the channel length direction overlaps each of the first transparent conductive layer 108a and the second transparent conductive layer 108b by width W_{ov2}. Since the first gate

electrode **104** and the second gate electrode **116** each partially overlap both of the first transparent conductive layer **108a** and the second transparent conductive layer **108b**, the channel region in the oxide semiconductor layer **112** is substantially blocked against the external electric field. Therefore, even if the anode electrode **158** is located to cover the entire surface of the transistor **100a**, the transistor **100a** is not influenced by the electric field of the anode electrode **158**. Thus, the threshold voltage of the transistor **100a** is prevented from being changed along with time.

[0187] FIG. 11B shows an embodiment of the transistor **100a**. In this embodiment, the transistor **100a** has a structure in which the second gate electrode **116** in an upper layer overlaps both of the first transparent conductive layer **108a** and the second transparent conductive layer **108b** corresponding to the source and drain electrodes, and the first gate electrode **104** overlaps neither the first transparent conductive layer **108a** nor the second transparent conductive layer **108b**. The second gate electrode **116** having width W_{top} in the channel length direction overlaps each of the first transparent conductive layer **108a** and the second transparent conductive layer **108b** by width W_{ov2} . By contrast, width W_{bottom} of the first gate electrode **104** in the channel length direction is narrower than the interval between the first transparent conductive layer **108a** and the second transparent conductive layer **108b**, and the first gate electrode **104** is offset by width W_{off} from the first transparent conductive layer **108a** and the second transparent conductive layer **108b**. Since at least the second gate electrode **116** partially overlaps both of the first transparent conductive layer **108a** and the second transparent conductive layer **108b**, the channel region in the oxide semiconductor layer **112** is substantially blocked against the external electric field. Therefore, the threshold voltage of the transistor **100a** is prevented from being changed along with time. Specifically, the area size of the region where the second gate electrode **116** overlaps the oxide semiconductor layer **112** is larger than the area size of the region where the first gate electrode **104** overlaps the oxide semiconductor layer **112**. For this reason, the influence of the charges that may be accumulated on the back channel side is blocked. In other words, the first gate electrode **104** and the second gate electrode **116** overlap each other as seen in a plan view, and the second gate electrode **116** covers the first gate electrode **104**, and therefore, the influence of the charges that may be accumulated on the back channel side is blocked.

[0188] In consideration of the alignment precision of a photomask in a lithography step, it is preferable that width W_{top} of the second gate electrode **116** is larger than width W_{bottom} of the first gate electrode **104** ($W_{top} > W_{bottom}$). The width of the second gate electrode **116** is made larger than the width of the first gate electrode **104**, so that there is a margin for the alignment precision of the photomask in the lithography step. Therefore, the channel region formed in the oxide semiconductor layer **112** is covered with the second gate electrode **116** with certainty.

2-4. Method for Producing the Display Device

[0189] An example of method for producing the display device **120** in an embodiment according to the present invention will be described. In the following description, the same explanations as those on the method for producing the

transistor **100a** provided in embodiment 1 will be omitted, and only the differences will be provided.

[0190] FIG. 12, FIG. 13A and FIG. 13B show a stage of forming the first gate electrodes **104a** and **104b**, the first capacitance electrode **160a** and the first common line **136a** on the substrate **102**, and a stage of forming the first insulating layer **106**. FIG. 12 is a plan view of a region corresponding to one pixel **122a**. FIG. 13A is a cross-sectional view taken along line A1-A2 in FIG. 12, and FIG. 13B is a cross-sectional view taken along line B1-B2 in FIG. 12.

[0191] As shown in FIG. 12, FIG. 13A and FIG. 13B, the first common line **136a** and the first capacitance electrode **160a** are formed of the same conductive film as that of the first gate electrodes **104a** and **104b**. Therefore, the first gate electrode **104a** and the gate signal line **132a** are formed as one continuous pattern formed of a conductive film in the same layer. Similarly, the first common line **136a** and the first capacitance electrode **160a** are formed as one continuous pattern formed of a conductive film in the same layer.

[0192] The first insulating layer **106** is formed on the first gate electrodes **104a** and **104b**, the first common line **136a**, and the first capacitance electrode **160a**. For example, the first insulating layer **106** is formed by stacking the first silicon nitride film **141a** and the first silicon oxide film **140a** from the substrate **102** side. The first silicon nitride film **141a** is formed by plasma CVD by use of gas such as SiH_4 , NH_3 , N_2 or the like as source gas. The first silicon oxide film **140a** is also formed by plasma CVD by use of SiH_4 , N_2O , $\text{Si}(\text{OC}_2\text{H}_5)_4$ (tetraethoxysilane), $\text{Si}(\text{OCH}_3)_4$ (tetramethoxysilane) or the like optionally. The first insulating layer **106** is formed on substantially the entire surface of the substrate **102**.

[0193] FIG. 14A and FIG. 14B show a stage where the second conductive film **107** and the third conductive film **109** are formed on the first insulating layer **106**, and the resist mask **207a**, the resist mask **207b**, a resist mask **207c** and a resist mask **207d** are formed thereon by use of a multi-gradation photomask. As shown in FIG. 14A, the first contact hole **117a** is formed in advance in the first insulating layer **106** in order to expose the first common line **136a**. The resist masks **207a**, **207b**, **207c** and **207d** are formed such that regions thereof corresponding to regions of the third conductive film **109** that are to become the second common line **136b** (FIG. 14A) and the data signal line **134** (FIG. 14B) are thicker than the remaining region. The second conductive film **107** is formed of a transparent conductive material, and the third conductive film **109** is formed of a metal material.

[0194] FIG. 15, FIG. 16A and FIG. 16B show a state where the third conductive film **109** and the second conductive film **107** are etched by use of the resist masks **207a**, **207b**, **207c** and **207d**. FIG. 15 is a plan view of a region corresponding to one pixel **122a**. FIG. 16A is a cross-sectional view taken along line A1-A2 in FIG. 15, and FIG. 16B is a cross-sectional view taken along line B1-B2 in FIG. 15.

[0195] The first transparent conductive layer **108a**, the second transparent conductive layer **108b**, the third transparent conductive layer **108c** and the fourth transparent conductive layer **108d** are formed on the first insulating layer **106**. The first transparent conductive layer **108a** and the second transparent conductive layer **108b** are formed such that ends of the first transparent conductive layer **108a** and the second transparent conductive layer **108b** overlap

the first gate electrode **104a** while having the first insulating layer **106** between the first transparent conductive layer **180a**/the second transparent conductive layer **108b** and the first gate electrode **104a**. The third transparent conductive layer **108c** and the fourth transparent conductive layer **108d** are formed such that ends of the third transparent conductive layer **108c** and the fourth transparent conductive layer **108d** overlap the first gate electrode **104b** while having the first insulating layer **106** between the third transparent conductive layer **108c**/the fourth transparent conductive layer **108d** and the first gate electrode **104b**. The second common line **136b** is formed on the second transparent conductive layer **108b**. The second common line **136b** is formed on the surface of the second transparent conductive layer **108b**. In this state, the first common line **136a**, the second transparent conductive layer **108b** and the second common layer **136b** are electrically connected with each other.

[0196] The second capacitance electrode **160b** is formed in contact with a top surface of the fourth transparent conductive layer **108d**. The second capacitance electrode **160b** is located to at least partially overlap the first capacitance electrode **160a** while having the fourth transparent conductive layer **108d** and the first insulating layer **106** between the second capacitance electrode **160b** and the first capacitance electrode **160a**. The capacitance element is formed in a region where the first capacitance electrode **160a** and the second capacitance electrode **160b** overlap each other while having the first insulating layer **106** therebetween.

[0197] The data signal line **134** is formed of the third conductive film **109**. The data signal line **134** is formed in contact with a top surface of the third transparent conductive layer **108c**. In this state, the third transparent conductive layer **108c** and the data signal line **134** are electrically connected with each other. The third transparent conductive layer **108c** is provided along the data signal line **134**, and thus is electrically connected with the data signal line **134** with certainty.

[0198] An end of the second common line **136b** is located inner to an end of the second transparent conductive layer **108b**. With such an arrangement, even though the second transparent conductive layer **108b** and the second common line **136b** are stacked on each other, the ends thereof form a stepped portion. Therefore, the step coverage of the oxide semiconductor layer **112** and the second insulating layer **114** formed in a later stage is in a good state. Similarly, an end of the data signal line **134** is located inner to an end of the third transparent conductive layer **108c**, and an end of the second capacitance electrode **160b** is located inner to an end of the fourth transparent conductive layer **108d**. Therefore, the step coverage of the oxide semiconductor layer **112** and the second insulating layer **114**, which are to be formed on these ends in a later stage, are in a good state.

[0199] FIG. 17, FIG. 18A and FIG. 18B show a stage of forming the oxide semiconductor layer **112**, the second insulating layer **114** and the fourth conductive film **115**. FIG. 17 is a plan view of a region corresponding to one pixel **122a**. FIG. 18A is a cross-sectional view taken along line A1-A2 in FIG. 17, and FIG. 18B is a cross-sectional view taken along line B1-B2 in FIG. 17.

[0200] The first oxide semiconductor layer **112a** is formed to cover substantially the entire surfaces of the first transparent conductive layer **108a** and the second transparent conductive layer **108b**. The second oxide semiconductor

layer **112b** is formed to cover substantially the entire surfaces of the third transparent conductive layer **108c** and the fourth transparent conductive layer **108d**. The first oxide semiconductor layer **112a** and the second oxide semiconductor layer **112b** are formed as follows. An oxide semiconductor film is formed by sputtering by use of an oxide semiconductor as a target, and is subjected to a lithography step. As a result, the first oxide semiconductor layer **112a** and the second oxide semiconductor layer **112b** having a predetermined shape described above are formed. The first oxide semiconductor layer **112a** is formed in contact with, and thus is electrically connected with, the first transparent conductive layer **108a** and the second transparent conductive layer **108b**. The second oxide semiconductor layer **112b** is formed in contact with, and thus is electrically connected with, the third transparent conductive layer **108c** and the fourth transparent conductive layer **108d**.

[0201] The second insulating layer **114** is formed on the first oxide semiconductor layer **112a** and the second oxide semiconductor layer **112b**. The second insulating layer **114** is formed by, for example, stacking the second silicon oxide film **140b** and the second silicon nitride film **141b** in this order from the oxide semiconductor layer **112** side. As a result, the first silicon oxide film **140a** is formed below the oxide semiconductor layer **112**, and the second silicon oxide film **140b** is formed above the oxide semiconductor layer **112**. The oxide semiconductor layer **112** is held between the oxide insulating films, and thus is suppressed from having a defect (donor level) caused thereto by oxygen deficiency.

[0202] It is desirable that the silicon oxide films **140a** and **140b** do not have oxygen deficiency so as not to draw out oxygen from the first oxide semiconductor layer **112a**. Rather, it is even preferable that the silicon oxide films **140a** and **140b** contain an excessive amount of oxygen. The second insulating layer **114**, after being formed, is heat-treated at a temperature of 250° C. to 400° C., and thus oxygen is diffused from the first silicon oxide film **140a** and the second silicon oxide film **140b** to the first oxide semiconductor **112a** and the second oxide semiconductor layer **112b**. Since such heat treatment is performed, even if the oxide semiconductor layer **112** includes oxygen deficiency, the oxygen deficiency is compensated for by oxygen diffused from the oxide semiconductor layer **112**, and the defect, which would become a donor level, is extinguished. Therefore, the resistance is increased.

[0203] In the second layer **114**, the second contact hole **117b** is formed in a region overlapping the second capacitance electrode **160b**. Then, the fourth conductive film **115** is formed. The fourth conductive film **114** is formed in substantially the same manner as the first conductive film **103**.

[0204] FIG. 19, FIG. 20A and FIG. 20B show a stage of forming the second gate electrode **116**. FIG. 19 is a plan view of a region corresponding to one pixel **122a**. FIG. 20A is a cross-sectional view taken along line A1-A2 in FIG. 19, and FIG. 20B is a cross-sectional view taken along line B1-B2 in FIG. 19.

[0205] The second gate electrode **116** is formed by a lithography step and an etching step performed on the fourth conductive film **115**. The second gate electrode **116a** is formed to include a region overlapping the first gate electrode **104a**. The second gate electrode **116b** is formed to include a region overlapping the first gate electrode **104b**. As a result, the driving transistor **126** and the selection transistor

124 are formed. The capacitance element **128** is electrically connected with the second gate electrode **116a** via the contact hole **117b**.

[0206] As shown in FIG. 21A and FIG. 21B, the flattening layer **142** is formed to bury the selection transistor **124**, the driving transistor **126** and the capacitance element **128**. The flattening layer **142** is formed of an organic resin material such as, for example, an acrylic resin, a polyimide resin, an epoxy resin, a polyamide resin or the like. In the flattening layer **142**, the opening **144** is formed in a region overlapping the first electrode **146**, which is the cathode electrode, in order to expose the first oxide semiconductor layer **112a**. In the case where the flattening layer **142** is formed of a photosensitive resin material, the opening **144** is formed by exposure to light by use of a photomask. Before the flattening layer **142** is formed, an opening is formed in advance in the second insulating layer **114** in a region corresponding to the opening **144**. Alternatively, an opening that exposes the first oxide semiconductor layer **112a** may be formed in the second insulating layer **114** in the step of forming the opening **144** in the flattening layer **142**. It is preferable that the opening **144** in the flattening layer **142** has a tapered inner wall in order to allow the organic EL element **130** to be formed easily.

[0207] FIG. 22A and FIG. 22B show a stage of forming the electron transfer layer **148** and the electron injection layer **150**. The electron transfer layer **148** is formed of a metal oxide material. Examples of the metal oxide material usable for the electron transfer layer **148** include substantially the same materials described in embodiment 1, specifically, a four-component oxide material, a three-component oxide material, a two-component oxide material, and a one-component oxide material. The electron transfer layer **148** is formed by sputtering by use of any of the above-listed materials as a sputtering target. The electron injection layer **150** is formed of C12A7 electride. The electron injection layer **150** may be formed by sputtering by use of C12A7 electride as a sputtering target. In this case, the sputtering may be performed by use of at least one type of gas selected from the group consisting of He (helium), Ne (neon), N₂ (nitrogen), Ar (argon), NO (nitrogen monoxide), Kr (krypton), and Xe (xenon). The electron transfer layer **148** and the electron injection layer **150** are used commonly in a plurality of pixels **122a**, and therefore are formed on substantially the entirety of a region where the pixels **122a** are located.

[0208] Then, the light emitting layer **152**, the hole transfer layer **154**, the hole injection layer **156** and the second electrode **158** as the anode electrode are formed. As a result, the pixel structure shown in FIG. 9A and FIG. 9B is formed. The light emitting layer **152** is formed of different light emitting materials for red pixels, green pixels and blue pixels. In the case where light emitted from the light emitting layer **152** has a white light emission spectrum, the light emitting layer **152** may be formed in substantially the entirety of the display region **121** as a layer common to all the pixels **122a**. The hole transfer layer **154** and the hole injection layer **156** are each formed on substantially the entirety of the region where the pixels **122a** are located, as layers common to all the pixels **122a**. The second electrode **158** as the anode electrode is used as a common electrode to the pixels **122a**, and therefore is formed on substantially the entirety of the region where the pixels **122a**.

[0209] According to the method for producing the display device **120** in this embodiment, a multi-gradation photo-

mask is used to decrease the number of photomasks required to produce the display device **120**. The use of the multi-gradation photomask allows a plurality patterns (the first transparent conductive layer **108a**, the second transparent conductive layer **108b**, the third transparent conductive layer **108c**, the fourth transparent conductive layer **108d**, the data signal line **134**, the second common line **136b**, and the like) to be formed by performing exposure merely once. This increases the productivity of display devices **120** and also decreases the production cost.

[0210] In this embodiment, both of the selection transistor **124** and the driving transistor **126** are of a dual gate type. The present invention is not limited to this. For example, the selection transistor **124** may be a top gate type transistor with no first gate electrode **104b**. The pixel circuit is not limited to having a configuration shown in FIG. 7. The transistors and the organic EL element in this embodiment are applicable to a pixel circuit including three transistors for one pixel.

Embodiment 3

[0211] In embodiment 3, another embodiment of the method for producing the display device **120** according to the present invention will be described. In the following description, differences from embodiment 2 will be described.

[0212] This method is substantially the same as in embodiment 2 until the stage of forming the second gate electrode **116**. On the second gate electrode **116**, the flattening layer **142** is formed. FIG. 23A is a cross-sectional structure taken along line A1-A2 in FIG. 19, and shows the stage of forming the flattening layer **142**.

[0213] In this embodiment, the flattening layer **142** is formed of an insulating film having polarity. The flattening layer **142** is formed of, for example, a straight chain-type fluorine organic material. Example of the straight chain-type fluorine organic material usable for the flattening layer **142** include a fluoroalkylsilane (FAS)-based material. Example of the fluoroalkylsilane (FAS)-based material include H₁₁H₂H, 2H-perfluorodecyltrichlorosilane (FDTS), tridecafluoro-1,1,2,2-tetrahydrooctyltrichlorosilane (FOTS), and the like.

[0214] The flattening layer **142** is formed of a straight chain-type fluorine organic material, and thus has a liquid-repelling surface. In more detail, the flattening layer **142** contains bipolar molecules and side chains, and therefore, as schematically shown in FIG. 23A, negative charges are generated at the surface of the flattening layer **142** because of a microlayer separation phenomenon. The opening **144** exposing the first oxide semiconductor layer **112a** is formed in the flattening layer **142**, and then, the electron transfer layer **148** is formed.

[0215] FIG. 23B shows a stage where the electron transfer layer **148** is formed. The electron transfer layer **148** is formed of a metal oxide material. Examples of the metal oxide material usable for the electron transfer layer **148** include substantially the same materials described in embodiment 1, specifically, a four-component oxide material, a three-component oxide material, a two-component oxide material, and a one-component oxide material. These oxide materials are each a type of degenerate semiconductor, and have n-type conductivity, with which the major carrier is an electron.

[0216] Negative charges are generated at the surface of the flattening layer **142** because of the microlayer separation

phenomenon. As a result, a region, of the electron transfer layer **148** having an n-type conductivity, that is in contact with the surface of the flattening layer **148** is depleted. Such a depleted region **149** of the electron transfer layer **148** becomes a high resistance region with almost no carrier. By contrast, a region, of the electron transfer layer **148**, that is in contact with the oxide semiconductor layer **112a**, remains as it is without being depleted. The electron transfer layer **148** having an n-type conductivity is formed in substantially the entirety of the display region **121**. The depleted region **149** of the electron transfer layer **148** is in positional correspondence with a region between the pixels. The pixels adjacent to each other are insulated from each other by the depleted region **149**. Therefore, the level of leak current flowing laterally via the electron transfer layer **148** is decreased.

[0217] Conventionally, it is considered that in order to produce an organic EL element, a hole injection layer, a hole transfer layer, a light emitting layer, an electron transfer layer, an electron injection layer and a cathode electrode need to be continuously formed in vacuum without being exposed to the air. By contrast, in this embodiment according to the present invention, the electron transfer layer **148** and the electron injection layer **150** are formed of an oxide semiconductor, which is stable even when being exposed to the air. Thus, the conditions for producing an organic EL element have a certain degree of freedom. Specifically, in this embodiment according to the present invention, the organic EL element may be produced as follows. First, the electron transfer layer **148** and the electron injection layer **150** are formed in vacuum by use of a sputtering device. Then, after the pressure is returned to the atmospheric pressure, the hole transfer layer **154**, the hole injection layer **156** and the anode electrode **158** are formed by another film formation device. Therefore, a device for producing the organic EL element is prevented from being enlarged, and the line balance of the production process is easily adjusted. This embodiment according to the present invention has various advantages that, for example, the production adjustment is easily done while maintenance of the production device is performed, and that the production efficiency is improved.

Embodiment 4

[0218] In embodiment 4, the pixel structure is different from that in embodiment 2. In the following description, differences from embodiment 2 will be described.

4-1. Pixel Structure 1

[0219] FIG. 24A and FIG. 24B shows a structure of a pixel **122b** in a display device in this embodiment. FIG. 24A shows a cross-sectional structure taken along line A1-A2 in the plan view of FIG. 8, and FIG. 24B shows a cross-sectional structure taken along line B1-B2 in the plan view of FIG. 8.

[0220] As shown in FIG. 24A, in the pixel **122b**, the electron transfer layer **148** is individually provided in correspondence with each organic EL element **130**. In other words, the electron transfer layer **148** is not provided in substantially the entirety of the display region **121**, but one electron transfer layer **148** is individually provided for each pixel **122b**. In this case, it is preferable that the electron transfer layer **148** has an area size larger than that of the

opening **144** and smaller than the light emitting layer **152**. Namely, it is preferable that an end of the electron transfer layer **148** is located outer to an end of the opening **144** and inner to an end of the light emitting layer **152**. Therefore, as shown in FIG. 24B, the electron transfer layer **148** is not located in a region where the selection transistor **124** is provided. Since the electron transfer layer **148** is formed to be larger than the opening **144**, the light emitting layer **152** is prevented from contacting the oxide semiconductor layer **122a**. Since the electron transfer layer **148** is formed to be smaller than the light emitting layer **152**, the hole transfer layer **154** is prevented from contacting the electron transfer layer **148**.

[0221] The electron transfer layer **148** is formed of a metal oxide material. A resist mask is formed by a lithography step, and dry etching or wet etching is performed to easily form the electron transfer layer **148**. The electron transfer layer **148** is formed of a metal oxide material and therefore has an n-type conductivity. As shown in FIG. 24A, since the electron transfer layer **148** is formed individually for each pixel **122b**, the level of leak current between the pixels **122b** is decreased. In the case where the electron injection layer **150** is formed of C12A7 electride, the electron injection layer **150** does not increase the level of leak current between adjacent pixels **122b** because C12A7 electride has a high resistance. Therefore, in the case of being formed of C12A7 electride, the electron injection layer **150** may be provided in substantially the entirety of the display region **121** without causing the problem of leak current.

[0222] As described above, the electron transfer layer **148** is individually provided for the organic EL element **130** in each pixel **122b**, so that the undesirable possibility that the leak current between the pixels **122b** (in other words, crosstalk) is generated is solved.

4-2. Pixel Structure 2

[0223] The two layers of the electron transfer layer **148** and the electron injection layer **150** may be formed by a lithography step and an etching step. FIG. 25A and FIG. 25B shows a structure of the pixel **122c** in such a case. FIG. 25A shows a cross-sectional structure taken along line A1-A2 in the plan view of FIG. 8. FIG. 25B shows a cross-sectional structure taken along line B1-B2 in the plan view of FIG. 8.

[0224] In the case where the electron transfer layer **148** and the electron injection layer **150** are individually provided for each pixel **122b**, it is preferable that the electron transfer layer **148** and the electron injection layer **150** each have an area size smaller than that of the light emitting layer **152**. Namely, it is preferable that ends of the electron transfer layer **148** and the electron injection layer **150** are located outer to the end of the opening **144** and inner to the end of the light emitting layer **152**. In other words, it is preferable that the electron transfer layer **148** and the electron injection layer **150** each have such a size that is covered with the light emitting layer **152**. The electron transfer layer **148** and the electron injection layer **150** are each smaller than the light emitting layer **152**, so that the hole transfer layer **154** is prevented from contacting the electron transfer layer **148**.

[0225] The electron transfer layer **148** and the electron injection layer **150** are individually provided for the organic EL element **130** in each pixel **122b**, so that the undesirable possibility that the leak current between the pixels **122b** (in other words, crosstalk) is generated is solved.

[0226] In this embodiment, the electron transfer layer 148 and the electron injection layer 150 are formed of an oxide semiconductor, and thus are allowed to be patterned by a lithography step so as to be provided individually for the organic EL element 130 in each pixel 122b. Namely, the generation of the leak current between the pixels 122b (in other words, crosstalk) is prevented and the image quality of the display device is improved merely by adding one photomask for the production process.

Embodiment 5

[0227] In embodiment 5, one of, or both of, the electron transfer layer 148 and the electron injection layer 150 are individually provided for each pixel, but in a different form from that of embodiment 4. In the following description, mainly differences from embodiment 4 will be described.

5-1. Pixel Structure 1

[0228] FIG. 26 shows an example of planar structure of a pixel 122c in this embodiment. FIG. 27A shows a cross-sectional structure taken along line A3-A4 in FIG. 26, and FIG. 27B shows a cross-sectional structure taken along line B3-B4 in FIG. 26. FIG. 27A shows the cross-sectional structure of the driving transistor 126 and the organic EL element 130. FIG. 27B shows the cross-sectional structure of the selection transistor 124 and the capacitance element 128. The following description will be made with reference to FIG. 26, FIG. 27A and FIG. 27B when necessary. The plan view of the pixel 122c shown in FIG. 26 omits the organic EL element 130.

[0229] As shown in FIG. 26 and FIG. 27A, the electron transfer layer 148 is in contact with a top surface of the oxide semiconductor layer 112a, and is individually provided for each of the pixels 122c. Therefore, as shown in FIG. 27B, the electron transfer layer 148 is not provided in a region where the selection transistor 124 is provided.

[0230] The electron transfer layer 148 is formed of an oxide semiconductor, like the oxide semiconductor layer 112a. In this case, the oxide semiconductor material used for the electron transfer layer 148 and the oxide semiconductor material used for the oxide semiconductor layer 112a are made different from each other, so that the electron transfer layer 148 is selectively processed on the oxide semiconductor layer 112a. Specifically, the electron transfer layer 148 is formed of an oxide semiconductor that is etched faster than the oxide semiconductor for the oxide semiconductor layer 112a, so that the electron transfer layer 148 is selectively processed.

[0231] It is preferable that the electron transfer layer 148 is formed of, for example, a zinc (Zn)-based oxide semiconductor not containing tin (Sn) (e.g., ZnSiO_x, ZnMgO_x, ZnGaO_x, etc.) and the oxide semiconductor layer 112a is formed of, for example, a tin (Sn)-based oxide semiconductor not containing zinc (Zn), magnesium (Mg) or the like (e.g., InGaSnO_x, InWSnO_x, InSiSnO_x, etc.). In other words, it is preferable that the electron transfer layer 148 contains zinc oxide and at least one selected from silicon oxide, magnesium oxide and gallium oxide, and that the oxide semiconductor layer 112a contains tin oxide, indium oxide, and at least one selected from gallium oxide, tungsten oxide and silicon oxide. With such an arrangement, the etching rate on the oxide semiconductor used for the electron transfer layer 148 is made different from the etching rate on

the oxide semiconductor used for the oxide semiconductor layer 112a, and thus the selection ratio is made high. Specifically, the etching rate on the electron transfer layer 148 is made higher than that on the oxide semiconductor layer 112a. The bandgap relationship between the electron transfer layer 148 and the oxide semiconductor layer 112a is made optimal. Specifically, the bandgap of the electron transfer layer 148 is made larger than that of the oxide semiconductor layer 112a. For example, in the case where the bandgap of the oxide semiconductor layer 112a is 3.0 eV or greater, the bandgap of the electron transfer layer 148 is preferably greater than, or equal to, the bandgap of the oxide semiconductor layer 112a, and more preferably 3.4 eV or greater. In the case where the bandgap of the electron transfer layer 148 is 3.4 eV or greater, blue light is not absorbed and thus the reliability is improved.

[0232] Before the flattening layer 142 is formed, the electron transfer layer 148 is formed by patterning performed by a lithography step and an etching step. Thus, the electron transfer layer 148 is formed by microscopic processing. Since the electron transfer layer 148 is individually provided for each pixel, the level of leak current flowing between adjacent pixels is decreased to suppress the generation of crosstalk like in embodiment 4.

5-2. Pixel Structure 2

[0233] The two layers of the electron transfer layer 148 and the electron injection layer 150 may be individually formed, for each of the pixels 122c, on the oxide semiconductor layer 112a. FIG. 28A and FIG. 28B show the structure of the pixel 122c in such a case. FIG. 28A shows a cross-sectional structure taken long line A3-A4 in the plan view of FIG. 26, and FIG. 28B shows a cross-sectional structure taken long line B3-B4 in the plan view of FIG. 26.

[0234] As shown in FIG. 28A, the electron transfer layer 148 and the electron injection layer 150 are individually provided, for each pixel 122c, on the oxide semiconductor layer 112a. Therefore, as FIG. 28B, neither the electron transfer layer 148 nor the electron transfer layer 148 and the electron injection layer 150 is provided in a region where the selection transistor 124 is provided. In this manner, the electron transfer layer 148 and the electron injection layer 150 are individually provided for the organic EL element in each pixel, so that the level of leak current flowing between adjacent pixels is decreased to suppress the generation of crosstalk.

5-3-1. Production Method 1

[0235] A method for producing the display device in this embodiment will be described with reference to the drawings. In the following description, mainly differences from embodiment 2 will be described.

[0236] FIG. 29, FIG. 30A and FIG. 30B show a stage where the gate electrodes 104 (the first gate electrode 104a and the second gate electrode 104b), the first insulating layer 106, the transparent conductive layers 108 (the first transparent conductive layer 108a through the fourth transparent conductive layer 108d), the data signal line 134, the first common line 136a, and the second common line 136b are formed on the substrate 102, and a layer to become the oxide semiconductor layer 112 and a layer to become the electron transfer layer 148 are formed on substantially the entire surface of the substrate 102. FIG. 29 is a plan view on this

stage (the first insulating layer 106, the layer to become the oxide semiconductor layer 112 and the layer to become the electron transfer layer 148 formed on substantially the entire surface of the substrate 102 are omitted). FIG. 30A shows a cross-sectional structure taken along line A3-A4 in FIG. 29, and FIG. 30B shows a cross-sectional structure taken along line B3-B4 in FIG. 29.

[0237] The layer to become the oxide semiconductor layer 112 and the layer to become the electron transfer layer 148 are formed of a metal oxide material, and thus may be continuously formed by use of a sputtering device. In this case, as described above, it is preferable that the layer to become the oxide semiconductor layer 112 and the layer to become the electron transfer layer 148 are formed of different metal oxide materials (in other words, different oxide semiconductor materials).

[0238] FIG. 31A and FIG. 31B show a stage of forming a photoresist film 205 on the layer to become the oxide semiconductor layer 112 and the layer to become the electron transfer layer 148 and exposing the photoresist film 205 by use of a photomask. As the photomask, the multi-gradation photomask 201 having the multi-gradation pattern 203 is used like in embodiment 1. In this case, a middle exposed portion of the multi-gradation photomask 201 corresponds to the oxide semiconductor layer 112, and the non-exposed portion of the multi-gradation photomask 201 corresponds to the electron transfer layer 148.

[0239] Then, the photoresist mask 205 is developed to form a resist mask 207a as shown in FIG. 32A and FIG. 32B. The resist mask 207a has portions of different thicknesses. FIG. 32A shows a state where the resist mask 207a is thicker in a portion corresponding to a region where the electron transfer layer 148 is to be formed, and is thinner in a portion corresponding to a region where the first oxide semiconductor layer 112a and the second oxide semiconductor layer 112b are to be formed.

[0240] The layer to become the electron transfer layer 148 and the layer to become the oxide semiconductor layer 112 are etched by use of the resist mask 207a. On this stage, the first oxide semiconductor layer 112a and the second oxide semiconductor layer 112b are formed. The layer to become the electron transfer layer 148 remains in substantially the same pattern as that of the first oxide semiconductor layer 112a and the second oxide semiconductor layer 112b. After the etching, an ashing process is performed to remove the thinner portion of the resist mask 207a and thus to expose a surface of the layer to become the electron transfer layer 148. FIG. 33A and FIG. 33B show the resist mask 207a after the ashing process. As shown in FIG. 33A, the resist mask 207a remains while covering a part of the layer to become the electron transfer layer 148.

[0241] Then, the exposed portion of the layer to become the electron transfer layer 148 is etched. As shown in FIG. 34 (plan view) and FIG. 35A and FIG. 35B (cross-sectional views), the electron transfer layer 148 is selectively formed on the first oxide semiconductor layer 112a as a result of the etching. As described above, the electron transfer layer 148 is formed of a material having a higher etching rate than that of the material of the first oxide semiconductor layer 112a. With such an arrangement, the electron transfer layer 148 is formed on the first oxide semiconductor layer 112a while the first oxide semiconductor layer 112a and the second oxide semiconductor layer 112b remain without being etched

away. After the electron transfer layer 148 is formed by etching, the resist mask 207a is removed by an ashing process.

[0242] Then, as shown in FIG. 36A and FIG. 36B, the second insulating layer 114, the second gate electrodes 116a and 116b, and the flattening layer 142 are formed. In the flattening layer 142, the opening 144 is formed, and the electron injection layer 150 is formed. As shown in FIG. 36A and FIG. 36B, the electron injection layer 150 is formed on the top surface of the flattening layer 150 and in the opening 144 and is in contact with the electron transfer layer 148.

[0243] After this, the light emitting layer 152, the hole transfer layer 154, the hole injection layer 156 and the anode electrode 158 are formed. As a result, the pixel 122c of the display device shown in FIG. 26, FIG. 27A and FIG. 27B is formed.

[0244] In this embodiment, the multi-gradation photomask is used to form the electron transfer layer 148 on the first oxide semiconductor layer 112a without increasing the number of photomasks. The positions of the oxide semiconductor layer 112a and the electron transfer layer 148 are determined by one photomask, and thus the oxide semiconductor layer 112a and the electron transfer layer 148 are both formed with high precision even in the case where the pixels are microscopic. Also in this embodiment, the number of photomasks and the number of photolithography steps do not need to be increased, and thus the production cost is suppressed from increasing.

5-3-2. Production Method 2

[0245] On the stage shown in FIG. 30A and FIG. 30B, the electron injection layer 150 may be stacked on the electron transfer layer 148 and the method described in 5-3-1 may be performed. Specifically, the multi-gradation photomask may be used to form the electron transfer layer 148 and the electron injection layer 150 by etching. As a result, as shown in FIG. 37A and FIG. 37B, the electron transfer layer 148 and the electron injection layer 150 may be selectively formed on the first oxide semiconductor layer 112a.

[0246] Then, the flattening layer 142 is formed, and the opening 144 is formed in the flattening layer 142. The light emitting layer 152, the hole transfer layer 154, the hole injection layer 156 and the anode electrode 158 are formed. As a result, the pixel 122c shown in FIG. 28A and FIG. 28B is formed.

[0247] In this embodiment, like in the case described in 5-3-1, the multi-gradation photomask is used to provide the electron transfer layer 148 and the electron injection layer 150 on the first oxide semiconductor layer 112a without increasing the number of photomasks.

Embodiment 6

[0248] In embodiment 6, an example of pixel of a display device of a so-called top emission type, in which light from the organic EL element 130 is output in a direction opposite to the substrate 102, will be described. In the following description, differences from embodiment 2 will be described.

[0249] FIG. 38 is a plan view of a pixel 122d of a display device 120 in this embodiment. FIG. 39 shows a cross-sectional structure taken along line A5-A6 in FIG. 38. The selection transistor 124, the driving transistor 126, the

capacitance element **128** and the organic EL element **130** in the pixel **122d** each have substantially the same structure as that in embodiment 2.

[0250] The pixel **122d** includes a reflective layer **162** in a region overlapping the first electrode **146**, which is a cathode electrode. The reflective layer **162** is provided below the first electrode **146** with the first insulating layer **106** being located between the reflective layer **162** and the first electrode **146**. The reflective layer **162** is formed in, for example, the same layer as that of the first gate electrode **104**. Namely, the reflective layer **162** is formed of the first conductive layer **103** described in embodiment 2. The second electrode **158**, which is an anode electrode, is formed of a transparent conductive material such as indium tin oxide, indium zinc oxide or the like.

[0251] In this embodiment, the first electrode **146**, which is the cathode electrode, is formed of a transparent conductive material. Light emitted by the light emitting layer **152**, except for a component thereof propagating in the organic EL element **130** as wave guide light, radiates at least toward the first electrode **146**, which is the cathode electrode, and toward the second electrode **158**, which is the anode electrode. The light directed from the light emitting layer **152** toward the first electrode **146**, which is the cathode electrode, is transmitted through the first electrode **146**, which is the cathode electrode, and the first insulating layer **106**, and is reflected by the reflective layer **162**. The light reflected by the reflective layer **162** is partially output from the second electrode **158**, which is the anode electrode. In order to increase the intensity of the output light, it is preferable that the reflective layer **162** includes a metal film of a material having a high reflectance such as aluminum (Al), silver (Ag) or the like at a surface thereof facing the first electrode **146**, which is the cathode electrode.

[0252] In FIG. 38 and FIG. 39, an end of the reflective layer **162** is located inner to an end of the first electrode **146**, which is the cathode electrode. This embodiment is not limited to this. The reflective layer **162** is provided below the first electrode **146** with the first insulating layer **106** being located between the reflective layer **162** and the first electrode **146**. Therefore, the reflective layer **162** may be wider than the first electrode **146**, which is the cathode electrode. The reflective layer **162** may be provided to be continuous throughout the plurality of pixels **122d**, unless the reflective layer **162** is in contact with the first gate electrode **104** or the gate signal line **132**.

[0253] As described above, in this embodiment, the reflective layer **162** is provided below the first electrode **146**, which is the cathode electrode, and thus the display device **120** including the pixel **122d** of a top emission type is realized. In this case, the reflective layer **162** may be formed of the same conductive film as that of the first gate electrode **104**. Therefore, the number of the steps of the production process is not increased.

Embodiment 7

[0254] In embodiment 7, the pixel structure is different from that in embodiment 2. FIG. 40 is a plan view of a pixel **122e**. FIG. 41A shows a cross-sectional structure taken along line A7-A8 in FIG. 40, and FIG. 41B shows a cross-sectional structure taken along line B5-B6 in FIG. 40. The pixel **122e** has substantially the same equivalent circuit as that shown in FIG. 7. In the following description, differences from embodiment 2 will be described.

[0255] In the pixel **122e**, the data signal line **134** and the second common line **136b** are formed of the fourth conductive film **115** described in embodiment 2. Specifically, the data signal line **134** and the second common line **136b** are provided on the second in layer **114**.

[0256] The second common line **136b** is electrically connected with the first common line **136a** via the first contact hole **117a** running through the first insulating layer **106** and the second insulating layer **114**. The second common line **136b** is in contact with the first oxide semiconductor layer **112a** via a third contact hole **117c** running through the second insulating layer **114**. The second common line **136b** is in contact with the first oxide semiconductor layer **112a** in a region where the first transparent conductive layer **108a** also overlaps the common line **136b** and the first oxide semiconductor layer **112a**. This region corresponds to the source region of the driving transistor **126**. Therefore, the second common line **136b** is electrically connected with the first common line **136a** and the source region of the driving transistor **126**.

[0257] The data signal line **134** is in contact with the second oxide semiconductor layer **112b** in a fourth contact hole **117d** running through the second insulating layer **114**. The data signal line **134** is in contact with the second oxide semiconductor layer **112b** in a region where the third transparent conductive layer **108c** also overlaps the data signal line **134** and the second oxide semiconductor layer **112b**. This region corresponds to the source or drain region of the selection transistor **124**. Therefore, the data signal line **134** is electrically connected with the source or drain region of the selection transistor **124**.

[0258] The capacitance element **128** is formed in a region where the first capacitance electrode **160a** and the second capacitance electrode **160b** overlap each other while having the first insulating layer **106** therebetween. In this embodiment, the second capacitance electrode **160b** is formed of a portion of the fourth transparent conductive layer **108d** and the second oxide semiconductor layer **112a** extending from the selection transistor **124** onto the first capacitance electrode **160a**. In this region, it is preferable that the second oxide semiconductor layer **112b** has a low resistance so as to act as an electrode. In this region, the second oxide semiconductor layer **112b** may be removed. The second gate electrode **116a** is in contact with the second capacitance electrode **160b** via the second contact hole **117b**, and thus the driving transistor **126** and the capacitance element **128** are electrically connected with each other.

[0259] In this embodiment, the data signal line **134** and the second common line **136b** are formed in the same conductive layer as that of the second gate electrode **116**. Therefore, in the pixel **122e**, the selection transistor **124** and the data signal line **134** are electrically connected with each other with certainty, the driving transistor **126** and the second common line **136b** are electrically connected with each other with certainty, and the driving transistor **126** and the capacitance element **128** are electrically connected with each other with certainty.

Embodiment 8

[0260] In embodiment 8, an example of pixel of a display device of a so-called top emission type, in which light from the organic EL element **130** is output in a direction opposite

to the substrate **102**, will be described. In the following description, differences from embodiment 4 will be described.

[0261] FIG. 42 is a plan view of a pixel **122f** of a display device **120** in this embodiment. FIG. 43 shows a cross-sectional structure taken along line A9-A10 in FIG. 42. The selection transistor **124**, the driving transistor **126**, the capacitance element **128** and the organic EL element **130** in the pixel **122f** each have substantially the same structure as that in embodiment 4.

[0262] Like in embodiment 6, the pixel **122f** includes the reflective layer **162** in a region overlapping the first electrode **146**, which is a cathode electrode. The reflective layer **162** is provided below the first electrode **146** with the first insulating layer **106** being located between the reflective layer **162** and the first electrode **146**. The reflective layer **162** is formed in, for example, the same layer as that of the first gate electrode **104**. Namely, the reflective layer **162** is formed of the first conductive layer **103** described in embodiment 2. The second electrode **158**, which is an anode electrode, is formed of a transparent conductive material such as indium tin oxide, indium zinc oxide or the like.

[0263] The pixel **122f** of a top emission type may have a pixel structure in which the data signal line **134** and the second common line **136b** are formed in the same layer as that of the second gate electrode **116**.

[0264] In FIG. 42 and FIG. 43, an end of the reflective layer **162** is located inner to an end of the first electrode **146**, which is the cathode electrode. This embodiment is not limited to this. The reflective layer **162** is provided below the first electrode **146** with the first insulating layer **106** being located between the reflective layer **162** and the first electrode **146**. Therefore, the reflective layer **162** may be wider than the first electrode **146**, which is the cathode electrode. The reflective layer **162** may be provided to be continuous throughout the plurality of pixels **122d**, unless the reflective layer **162** is in contact with the first gate electrode **104** or the gate signal line **132**.

[0265] In this embodiment, the reflective layer **162** is provided below the first electrode **146**, which is the cathode electrode, and thus the display device **120** including the pixel **122f** of a top emission type is realized. In this case, the reflective layer **162** may be formed of the same conductive film as that of the first gate electrode **104**. Therefore, the number of the steps of the production process is not increased.

Embodiment 9

[0266] In embodiment 9, the pixel structure is different from that in embodiment 4. FIG. 44 is a plan view of a pixel **122g**. FIG. 45A shows a cross-sectional structure taken along line A11-A12 in FIG. 44, and FIG. 45B shows a cross-sectional structure taken along line B7-Ab8 in FIG. 44. The pixel **122g** has substantially the same equivalent circuit as that shown in FIG. 7. In the following description, differences from embodiment 4 will be described.

[0267] In the pixel **122g** in this embodiment, the transparent conductive layer **108** and the oxide semiconductor layer **112** are stacked in an order different from that in embodiment 4. Namely, the oxide semiconductor layer **112** is provided on the first insulating layer **106**, and the transparent conductive layer **108** is provided on the oxide semiconductor layer **112**. Specifically, in the driving transistor **126**, the first transparent conductive layer **108a** and the second

transparent conductive layer **108b** are provided on the first oxide semiconductor layer **112a**. The second transparent conductive layer **108b** is extended to the region of the organic EL element **130**, and acts as the first electrode **146**, which is a cathode electrode, in this region. In the selection transistor **124**, the third transparent conductive layer **108c** and the fourth transparent conductive layer **108d** are provided on the second oxide semiconductor layer **112b**.

[0268] As can be seen, the transistors are realized even in the case where the order of stacking the oxide semiconductor layer **112** and the transparent conductive layer **108** is changed. In this structure, in the case where the oxide semiconductor layer **112** and the transparent conductive layer **108** have a certain level of etching rate ratio (in the case where the etching rate of the oxide semiconductor layer **112** is lower than that of the transparent conductive layer **108**), the multi-gradation photomask described in embodiment 2 may be used to form the oxide semiconductor layer **112** and the transparent conductive layer **108** by processing. Thus, the number of photomasks required for the production process is decreased, and the steps of the production process is also decreased.

[0269] In this embodiment, as shown in FIG. 45A, the second common line **136b** is in contact with the second transparent conductive layer **108b** via the third contact hole **117c**. As shown in FIG. 45B, the data signal line **134** is in contact with the third transparent conductive layer **108c** via the fourth contact hole **117d**. As can be seen, the data signal line **134** and the second common line **136b** are in contact with the transparent conductive layer **108**, and thus the contact resistance is decreased.

Embodiment 10

[0270] FIG. 46 shows a stage in a method for forming a transistor **100b** including the first gate electrode **104**, the first insulating layer **106**, the oxide semiconductor layer **112**, the second insulating layer **114** and the second gate electrode **116**. On the stage shown in FIG. 46, source and drain regions **118** having a lower resistance than that of a channel region is formed in the oxide semiconductor layer **112**.

[0271] FIG. 46 shows a process of irradiating the oxide semiconductor layer **112** with laser light from the substrate **102** side to form the source and drain regions **118** having a resistance lower than that of the oxide semiconductor layer **112**. It is preferable that the laser light used in this process has a short wavelength so as to be absorbed into the oxide semiconductor layer **112**, which has a wide bandgap. It is preferable that the oxide semiconductor layer **112** is irradiated with ultraviolet laser light such as, for example, KrF excimer laser light (wavelength: 248 nm), XeCl excimer laser light (wavelength: 308 nm), XeF excimer laser light (wavelength: 351 nm) or the like.

[0272] In the case where the laser process shown in FIG. 46 is performed, the substrate **102** is required to have such a level of transparency as to transmit the ultraviolet laser light sufficiently. Therefore, it is preferable that the substrate **102** is formed of non-alkali glass or quartz. In the case where the substrate **102** has a low transmittance for light in an ultraviolet range or the substrate **102** absorbs the light in an ultraviolet range, the laser light may be directed from the oxide semiconductor layer **112** side as shown in FIG. 47, so that a low resistance region is formed.

[0273] In the case where the laser light is directed from the substrate **102** side, a region of the oxide semiconductor layer

112 that overlaps the first gate electrode **104** is not irradiated with the laser light because the laser light is blocked by the first gate electrode **104**. By contrast, the regions of the oxide semiconductor layer **112** not overlapping the first gate electrode **104** are irradiated with the laser light transmitted through the substrate **102**. The irradiation with the laser light rapidly raises the temperature of the oxide semiconductor layer **112**. This causes oxygen deficiency, and thus a donor level is generated in the oxide semiconductor layer **112**. As a result, these regions have a resistance thereof decreased. **[0274]** This process may be performed in a state where a contact hole is provided in the second insulating layer **114** and a third line **110c** and a fourth line **110d** are provided. The regions having the resistance thereof decreased act as a source region **118a** and a drain region **118b** of the transistor **110b**.

[0275] In the laser process shown in FIG. **46** performed to form the transistor **110b**, the first gate electrode **104** is used as a mask blocking the laser light. Thus, the source region **118a** and the drain region **118b** are formed in a self-aligned manner.

[0276] As shown in FIG. **47A**, the laser process may be performed on a transistor **110c** including the first line **110a** and the second line **110b** provided between the oxide semiconductor layer **112** and the second insulating layer **114** while being in contact with the oxide semiconductor layer **112**. In this case also, the source region **118a** and the drain region **118b** are formed.

[0277] FIG. **47A** shows an embodiment in which the oxide semiconductor layer **112** is irradiated with the laser light from the second electrode **116** side. Regions of the oxide semiconductor layer **112** that overlap the second electrode **116**, the first line **110a** and the second line **110b** are not irradiated with the laser light. The remaining region of the oxide semiconductor layer **112** is irradiated with the laser light, and has the resistance thereof decreased. As shown in FIG. **47A**, in a region of the oxide semiconductor layer **112** that is between a region thereof overlapping the second gate electrode **116** and a region thereof overlapping each of the first line **110a** and the second line **110b**, the resistance is decreased. In a region of the oxide semiconductor layer **112** that is outer to the region thereof overlapping each of the first line **110a** and the second line **110b**, the resistance is decreased.

[0278] In the structure shown in FIG. **47A**, the source region **118a** and the drain region **118b** are provided adjacent to a channel region where the oxide semiconductor layer **112** is held between the first gate electrode **104** and the second gate electrode **116**. Namely, an offset region having a high resistance is not provided between the channel region and the source region or between the channel region and the drain region. Therefore, the level of on-current is prevented from decreasing. Unlike in the transistor **100a** described in embodiment 1, it is not necessary that the first line **110a** and the second line **110b** overlap each of the first electrode **104** and the second electrode **116**. Therefore, the source-gate coupling capacitance and the drain-gate coupling capacitance are decreased.

[0279] FIG. **47B** shows an embodiment in which the oxide semiconductor layer **112** is irradiated with the laser light from the first gate electrode **104** side. In this case, regions of the oxide semiconductor layer **112** that do not overlap the first gate electrode **104** are irradiated with the laser light. As a result, regions of the oxide semiconductor layer **112** that

are below the first line **110a** and the second line **110b** also have a resistance thereof decreased. With such a process, the resistance of the source region **118a** and the drain region **118b** is further decreased. The contact resistance between the source region **118a** and the first line **110a**, and the contact resistance between the drain region **118b** and the second line **110b**, are also decreased. Like in the structure shown in FIG. **46**, the first gate electrode **104** is used as a mask, and the source region **118a** and the drain region **118b** are formed in a self-aligned manner. Therefore, an offset region having a high resistance is not provided, and the level of on-current is prevented from decreasing.

[0280] As shown in FIG. **47A** and FIG. **47B**, the first gate electrode **104** or the second gate electrode **116** is used as a mask blocking the laser light, so that the source region **118a** and the drain region **118b** are formed in the oxide semiconductor layer **112** in a self-aligned manner. This increases the productivity of the integrated circuit elements including the transistor **100C** and decreases the production cost.

[0281] As described in embodiment 2, in consideration of the alignment precision of the photomask, it is preferable that width W_{top} of the second gate electrode **116** is larger than width W_{bottom} of the first gate electrode **104** ($W_{top} > W_{bottom}$). FIG. **48A** shows an embodiment in which the oxide semiconductor layer **112** is irradiated with the laser light from the second gate electrode **116** side in the case where the second gate electrode **116** is wider than the first gate electrode **104**.

[0282] FIG. **48A** shows an embodiment in which the laser light is directed from the second gate electrode **116** side in the case where width W_{top} of the second gate electrode **116** is larger than width W_{bottom} of the first gate electrode **104**. A region of the oxide semiconductor layer that is irradiated with the laser light has the resistance thereof decreased. In the case shown in FIG. **48A**, the positions of the source region **118a** and the drain region **118b** adjacent to the channel region of the oxide semiconductor layer **112** are determined by the second gate electrode **116**. In other words, the source region **118a** and the drain region **118b** are formed in a self-aligned manner by the second gate electrode **116**. By contrast, ends of the first gate electrode **104** does not match ends of the source region **118a** and the drain region **118b**, and offset regions each having width W_{off} are present. However, the offset regions with respect to the first gate electrode **104** are included in the channel region for the second gate electrode **116**. Therefore, the influence of the offset regions on static characteristics of the transistor **100C** is small.

[0283] FIG. **48B** shows an embodiment in which the laser light is directed from the first gate electrode **104** side in the case where width W_{top} of the second gate electrode **116** is larger than width W_{bottom} of the first gate electrode **104**. In the case shown in FIG. **48B**, the positions of the source region **118a** and the drain region **118b** adjacent to the channel region of the oxide semiconductor layer **112** are determined by the first gate electrode **104**. Therefore, the source region **118a** and the drain region **118b** formed in the oxide semiconductor layer **112** include regions overlapping the second gate electrode **116**. Such regions each have width W_{ov} . As can be seen, the source region **118a** and the drain region **118b** have the regions overlapping the second gate electrode **116**. Therefore, a high resistance region is not formed between the source region **118a** and the second gate electrode **116** or between the drain region **118b** and the

second gate electrode **116**. Thus, the level of on-current of the transistor **100c** is prevented from decreasing.

[0284] In this embodiment, the source region **118a** and the drain region **118b** are formed in a self-aligned manner by the first gate electrode **104** or the second gate electrode **116**. In consideration of the alignment precision in the lithography step, it is preferable that width W_{top} of the second gate electrode **116** is larger than width W_{bottom} of the first gate electrode **104** ($W_{top} > W_{bottom}$). Namely, the second gate electrode **116** on the upper layer is made wider than the first gate electrode **104** in the lower layer, so that there is a margin for the alignment precision of the photomask in the lithography step. Therefore, the channel region formed in the oxide semiconductor layer **112** is covered with the second gate electrode **116** with certainty.

Embodiment 11

[0285] In embodiment 11, an example of applying the structure of the transistor described in embodiment 7 to a display device **120** will be described.

11-1. Pixel Structure 1

[0286] FIG. 49 is a plan view of a pixel **122h** of a display device **120** in embodiment 11. FIG. 50A shows a cross-sectional structure taken along line A13-A14 in FIG. 49, and FIG. 50B shows a cross-sectional structure taken along line B9-B10 in FIG. 49. The following description will be made with reference to FIG. 49, FIG. 50A and FIG. 50B.

[0287] The first oxide semiconductor layer **112a** includes a region overlapping the first gate electrode **104a** and the second gate electrode **116a**, and the second oxide semiconductor layer **112b** includes a region overlapping the first gate electrode **104b** and the second gate electrode **116b**. The driving transistor **126** includes the first source region **118a** and the first drain region **118b** provided in a region of the first oxide semiconductor layer **112a** that is outer to the region thereof overlapping the first gate electrode **104a**. The selection transistor **124** includes a first source/drain region **118c** and a second source/drain region **118d** provided in a region of the second oxide semiconductor layer **112b** that is outer to the region thereof overlapping the first gate electrode **104b**.

[0288] As described above in embodiment 7, the first source region **118a**, the first drain region **118b**, the first source/drain region **118c** and the second source/drain region **118d** are low-resistance regions generated as a result of being irradiated with laser light from the substrate **102** side. The first gate electrodes **104a** and **104b** are used as masks against laser irradiation. Therefore, in each of the driving transistor **126** and the selection transistor **124**, regions of the oxide semiconductor layer **112** other than the region thereof corresponding to the channel region have a resistance thereof decreased.

[0289] In the organic EL element **130**, the regions of the first oxide semiconductor layer **112a** having the resistance thereof decreased is used as the first electrode **146**, which is the cathode electrode. In the capacitance element **128**, the first capacitance electrode **160a** formed in the same layer as that of the first gate electrode **104** overlaps the second oxide semiconductor layer **112b**. Therefore, the region of the oxide semiconductor layer **112** that overlaps the first capacitance electrode **160a** does not have a resistance thereof decreased. For this reason, a wide opening is formed in the second

insulating layer **114** to enlarge a region where the second gate electrode **116a** is in contact with the second oxide semiconductor layer **112b** and overlaps the first capacitance electrode **160a**. With such an arrangement, the second gate electrode **116a** also acts as the other capacitance electrode.

11-2. Pixel Structure 2

[0290] As described above in embodiment 4, the electron transfer layer **148** may be individually provided for each pixel. FIG. 51, FIG. 52A and FIG. 52B show a structure of a pixel **122h** in this case. FIG. 51 is a plan view of the pixel **122h** in a display **120** in this embodiment. FIG. 52A shows a cross-sectional structure taken along line A15-A16 in FIG. 51, and FIG. 52B shows a cross-sectional structure taken along line B11-B12 in FIG. 51.

[0291] As shown in FIG. 51, the opening **144** provided in the flattening layer **142** exposes the inside of the first electrode **146** formed as a result of the resistance of the oxide semiconductor layer **112** being decreased. As shown in FIG. 52A, the electron transfer layer **148** is in contact with the first electrode **146** exposed by the opening **144**. The electron transfer layer **148** is individually provided for each pixel. For example, the electron transfer layer **148** is not provided in the entirety of the pixel **122h**. For example, as shown in FIG. 52B, the electron transfer layer **148** does not need to be provided in a region where the selection transistor **124** is provided. Like in embodiment 4, since the electron transfer layer **148** is formed to be larger than the opening **144**, the light emitting layer **152** is prevented from contacting the oxide semiconductor layer **112a**. Since the electron transfer layer **148** is formed to be smaller than the light emitting layer **152**, the hole transfer layer **154** is prevented from contacting the electron transfer layer **148**.

[0292] As shown in FIG. 52A, since an end of the electron transfer layer **148** is located outer to the opening **144** (on the top surface of the flattening layer **142**), the first electrode **146** formed of an oxide semiconductor is not exposed outside. Namely, the first electrode **146** is not exposed to be etched when the electron transfer layer **148** is formed by etching. Therefore, the first electrode **146** is not extinguished by over-etching. This allows the first electrode **146** (in other words, the oxide semiconductor layer **112a**) to be formed to have the same thickness as that of the channel region of the transistor.

11-3. Pixel Structure 3

[0293] As described above in embodiment 4, the two layers of the electron transfer layer **148** and the electron injection layer **150** may be formed by a lithography step and an etching step. FIG. 53A and FIG. 53B show a structure of the pixel **122h** in such a case. FIG. 53A shows a cross-sectional structure taken along line A15-A16 in the plan view of FIG. 51, and FIG. 53B shows a cross-sectional structure taken along line B11-B12 in the plan view of FIG. 51.

[0294] As shown in FIG. 53A, both of the electron transfer layer **148** and the electron injection layer **150** are provided in correspondence with the organic EL element **130** in each pixel **122h**. In this case, as shown in FIG. 53B, neither electron transfer layer **148** nor the electron injection layer **150** is provided in a region where the selection transistor **124** is provided. The electron transfer layer **148** and the electron

injection layer 150 shown in FIG. 53A and FIG. 53B each have substantially the same structure as that in embodiment 4.

[0295] As can be seen, in this embodiment, the driving transistor 126 and the selection transistor 124 included in the pixel 122h both have a source region and a drain region formed as a result of the resistance of the oxide semiconductor layer 112 being decreased. This simplifies the structure of the transistors, and decreases the source-gate coupling capacitance and the drain-gate coupling capacitance. [0296] In this embodiment, the channel region of each of the driving transistor 126 and the selection transistor 124, and the first electrode 146 acting as the cathode electrode of the organic EL element 130, are formed of the same oxide semiconductor layer 112. The source/drain regions 118 and the second electrode 146 have resistances thereof decreased as a result of being irradiated with laser light. This simplifies the production process. In addition, since electron transfer layer 148 is individually formed for the organic EL element 130 in each pixel 122h, the undesirable possibility that the leak current between the pixels 122h (in other words, crosstalk) is generated is solved.

Embodiment 12

12-1. Pixel Structure

[0297] The pixel described in embodiment 11 may include a reflective electrode 164 in the organic EL element 130. FIG. 54, FIG. 55A and FIG. 55B show a structure of a pixel 122i including the reflective electrode 164 provided between the first electrode 146 and the electron transfer layer 148. FIG. 54 is a plan view showing a first structure of the pixel 122i. FIG. 55A shows a cross-sectional structure taken along line A17-A18 in FIG. 54, and FIG. 55B shows a cross-sectional structure taken along line B13-B14 in FIG. 54.

[0298] As shown in FIG. 54 and FIG. 55A, the reflective electrode 164 is provided to be wider than the first electrode 146. An outer end of the reflective electrode 164 is located outer to the opening 144. As shown in FIG. 55A, the reflective electrode 164 is in contact with the first electrode 146. On the first electrode 146, the second insulating layer 114 is provided. Therefore, the reflective electrode 164 is formed after the opening 144a exposing the first electrode 146 is formed in the second insulating layer 114. The reflective electrode 164 may be formed of the same conductive layer as that of the second gate electrode 116 (the common line 136 is also formed of the same conductive layer). Since the reflective electrode 164 is formed of the same conductive layer as that of the second gate electrode 116 as described above, the number of steps of the production process is decreased. Namely, the reflective electrode 164 is formed merely by forming the opening 144a in the second insulating layer 114 without adding any other step.

[0299] In the case where the pixel 122h is of a top emission type, in which light from the organic EL element 130 is output from the second electrode 158 side, it is preferable that the reflective electrode 164 is provided on the first electrode 146 side. It is preferable that the reflective electrode 164 includes a metal layer having a high reflectance at a surface thereof facing the electron transfer layer 148. The reflective electrode 164 may include, for example, a first metal layer 166a formed of aluminum (Al), an aluminum alloy, silver (Ag) or the like. Examples of the aluminum alloy usable for the first metal layer 166a include

an aluminum-neodymium alloy (Al—Nd), an aluminum-neodymium-nickel alloy (Al—Nd—Ni), an aluminum-carbon-nickel (Al—C—Ni), a copper-nickel alloy (Cu—Ni), and the like.

[0300] An aluminum film may undesirably cause an oxidation-reduction reaction when directly contacting the first electrode 146, which is formed of an oxide semiconductor. In order to avoid this, a second metal layer 166b formed of a metal material such as titanium (Ti), tantalum (Ta), molybdenum (Mo) or the like may be provided between the first electrode 146 and the first metal layer 166a.

[0301] On the reflective electrode 164, the flattening layer 142 is provided. A surface of the reflective electrode 164 is exposed by an opening 144b formed in the flattening layer 142. The electron transfer layer 148 is in contact with the reflective electrode 164 via the opening 144b formed in the flattening layer 142. A thin film formed of an aluminum-lithium alloy (AlLi), a magnesium-silver alloy (MgAg) or the like may be provided between the reflective electrode 164 and the electron transfer layer 148.

12-2. Pixel Structure 2

[0302] FIG. 56A and FIG. 56B show a second structure of the pixel 122i. FIG. 56A shows a cross-sectional structure taken along line A17-A18 in the plan view of FIG. 54, and FIG. 56B shows a cross-sectional structure taken along line B13-B14 in the plan view of FIG. 54. In the second structure, the electron transfer layer 148 and the electron injection layer 150 are individually provided for each pixel 122i, like in embodiment 11. Even in the case where the electron transfer layer 148 and the electron injection layer 150 are individually provided for each pixel 122i, the organic EL element 130 may include the reflective electrode 164.

12-3. Pixel Structure 3

[0303] FIG. 57 is a plan view showing a third structure of the pixel 122i. FIG. 58A shows a cross-sectional structure taken along line A19-A20 in FIG. 57, and FIG. 58B shows a cross-sectional structure taken along line B15-B16 in FIG. 57. In the third structure, the reflective electrode 164 is provided below the second insulating layer 114. In this case, the reflective electrode 164 is formed as follows. The oxide semiconductor layer 112, the first metal layer 166a and the second metal layer 166b are formed on substantially the entire surface of the substrate 102, and the reflective electrode 164 is formed by use of a multi-gradation photomask as described above in embodiment 5.

[0304] FIG. 62A and FIG. 62B show an embodiment in which the electron transfer layer 148 and the electron injection layer 150 are individually provided for each pixel 122i, like in embodiment 11, in the third structure. Even in the case where the electron transfer layer 148 and the electron injection layer 150 are individually provided for each pixel 122i, the organic EL element 130 may include the reflective electrode 164.

[0305] As can be seen, in this embodiment, the reflective electrode 164 is provided in the organic EL element 130, so that the intensity of the light output from the top emission type pixel is increased. Namely, the current efficiency of the organic EL element 130 is increased. In this case, the reflective electrode 164 is formed of the same conductive layer as that of the second gate electrode 116. Therefore, the

number of steps of the production process does not need to be significantly increased to form the reflective electrode 164 in the organic EL element 130.

Embodiment 13

[0306] In embodiment 13, the electron transfer layer 148 is provided on the oxide semiconductor layer 112a like in embodiment 5. FIG. 59 is a plan view of a pixel 122j in this embodiment. FIG. 60A shows a cross-sectional structure taken along line A21-A22 in FIG. 59, and FIG. 60B shows a cross-sectional structure taken along line B17-B18 in FIG. 59.

[0307] The first electrode 146 in contact with the electron transfer layer 148 is provided in the same layer as that of the oxide semiconductor layer 112a included in the driving transistor 126, and has the resistance thereof decreased as a result of being irradiated with laser light from the substrate 102 side. The electron transfer layer 148 is formed by use of a multi-gradation photomask as in the steps shown in FIG. 31A, FIG. 31B, FIG. 32A, FIG. 32B, FIG. 33A, FIG. 33B, FIG. 34, FIG. 35A, FIG. 35B, FIG. 36A and FIG. 36B in embodiment 5.

[0308] FIG. 61A and FIG. 61B show a cross-sectional structure of the pixel 122j. In the structure shown in FIG. 61A and FIG. 61B, the electron transfer layer 148 and the electron injection layer 150 provided on the first electrode 146 are formed by use of a multi-gradation photomask, unlike in the structure shown in FIG. 60A and FIG. 60B.

[0309] The first electrode 146 formed in the oxide semiconductor layer 122 has the resistance thereof decreased as a result of being irradiated with laser light in the ultraviolet range from the substrate 102 side. This decreases the contact resistance between the first electrode 146 and the electron transfer layer 148, and thus a good ohmic junction is formed.

[0310] It is preferable that the oxide semiconductor layer 112a and the first electrode 146 are formed of a tin (Sn)-based oxide semiconductor not containing zinc (Zn), magnesium (Mg) or the like (e.g., InGaSnO_x , InWSnO_x , InSiSnO_x , etc.), and that the electron transfer layer 148 is formed of a zinc (Zn)-based oxide semiconductor not containing tin (Sn) (e.g., ZnSiO_x , ZnMgO_x , ZnGaO_x , etc.). With such an arrangement, the etching rate on the oxide semiconductor used for the electron transfer layer 148 is made different from the etching rate on the oxide semiconductor used for the oxide semiconductor layer 112a, and thus the selection ratio is increased. In addition, the bandgap relationship of the oxide semiconductor layer 112a and the first electrode 146 with respect to the electron transfer layer 148 is made optimal. Specifically, the bandgap of the electron transfer layer 148 is made larger than that of the oxide semiconductor layer 112a and the first electrode 146. For example, the bandgap of the electron transfer layer 148 is preferably 3.4 eV or greater. In the case where the bandgap of the electron transfer layer 148 is 3.4 eV or greater, blue light is not absorbed and thus the reliability is improved.

[0311] The entirety of, or a part of, the illustrative embodiments disclosed above may be defined by the following supplementary Notes. Any embodiment of the present invention is not limited to any of the following.

Supplementary Note 1.

[0312] A display device includes a substrate; and a plurality of pixels provided on the substrate. The plurality of

pixels each include a driving transistor and an organic EL element electrically connected with the driving transistor; the driving transistor includes: an oxide semiconductor layer; a first gate electrode including a region overlapping the oxide semiconductor layer, the first gate electrode being provided on a surface of the oxide semiconductor layer facing the substrate; a first insulating layer provided between the first gate electrode and the oxide semiconductor layer; a second gate electrode including a region overlapping the oxide semiconductor layer and the first gate electrode, the second gate electrode being provided on a surface of the oxide semiconductor layer opposite to the surface facing the substrate; and a second insulating layer provided between the second gate electrode and the oxide semiconductor layer; and the organic EL element includes: a light-transmissive first electrode; a second electrode provided to face the first electrode; a light emitting layer provided between the first electrode and the second electrode; and an electron transfer layer provided between the light emitting layer and the first electrode; wherein the first electrode is continuous from the first transparent conductive layer.

Supplementary Note 2.

[0313] The display device according to supplementary Note 1, wherein the second gate electrode has a width in a channel length direction larger than a width of the first gate electrode in the channel length direction.

Supplementary Note 3.

[0314] The display device according to supplementary Note 1, wherein the region of the second gate electrode overlapping the oxide semiconductor layer has an area size larger than an area size of the region of the first gate electrode overlapping the oxide semiconductor layer.

Supplementary Note 4.

[0315] The display device according to supplementary Note 1, wherein the electron transfer layer has a carrier concentration higher than a carrier concentration of the oxide semiconductor layer.

Supplementary Note 5.

[0316] The display device according to supplementary Note 1, wherein the electron transfer layer has a bandgap of 3.4 eV or greater, and the oxide semiconductor layer has a bandgap of 3.0 eV or greater.

Supplementary Note 6.

[0317] The display device according to supplementary Note 1, wherein the organic EL element further includes an electron injection layer provided between the electron transfer layer and the light emitting layer.

Supplementary Note 7.

[0318] The display device according to supplementary Note 6, wherein the electron injection layer is formed of C12A7 ($12\text{CaO} \cdot 7\text{Al}_2\text{O}_3$) electride.

Supplementary Note 8.

[0319] The display device according to supplementary Note 1, wherein the electron transfer layer is formed of a

zinc (Zn)-based oxide semiconductor not containing tin (Sn), and the oxide semiconductor layer is formed of a tin (Sn)-based oxide semiconductor containing neither zinc (Zn) nor magnesium (Mg).

Supplementary Note 9.

[0320] The display device according to supplementary Note 8, wherein: the electron transfer layer contains at least one selected from zinc oxide, silicon oxide, magnesium oxide and gallium oxide; and the oxide semiconductor layer contains tin oxide, indium oxide and at least one selected from gallium oxide, tungsten oxide and silicon oxide.

Supplementary Note 10.

[0321] The display device according to supplementary Note 1, further comprising a flattening layer burying the driving transistor; wherein: the flattening layer has an opening exposing a top surface of the first electrode; and the electron transfer layer, the light emitting layer and the second electrode are provided continuously on the top surface of the first electrode, on an inner wall of the opening and on a top surface of the flattening layer.

Supplementary Note 11.

[0322] The display device according to supplementary Note 10, wherein: the organic EL element further includes a hole transfer layer and a hole injection layer provided between the light emitting layer and the second electrode; the hole transfer layer and the hole injection layer are provided continuously for the plurality of pixels; and the electron transfer layer is individually provided for each of the plurality of pixels.

Supplementary Note 12.

[0323] The display device according to supplementary Note 10, wherein:

[0324] the organic EL element further includes a hole transfer layer and a hole injection layer provided between the light emitting layer and the second electrode; the hole transfer layer and the hole injection layer are provided continuously for the plurality of pixels; and the electron transfer layer and the electron injection layer are individually provided for each of the plurality of pixels.

Supplementary Note 13.

[0325] The display device according to supplementary Note 11, wherein an end of the electron transfer layer is located outer to the opening and inner to an end of the light emitting layer.

Supplementary Note 14.

[0326] The display device according to supplementary Note 12, wherein an end of the electron transfer layer and an end of the electron injection layer are located outer to the opening and inner to an end of the light emitting layer.

Supplementary Note 15.

[0327] The display device according to supplementary Note 1, further comprising a reflective electrode provided between the first electrode and the electron transfer layer.

Supplementary Note 16.

[0328] The display device according to supplementary Note 15, wherein the reflective electrode is provided in the same layer as that of the second gate electrode.

1. A display device, comprising:

- an oxide semiconductor layer on a substrate;
- a first gate electrode between the substrate and the oxide semiconductor layer;
- a second gate electrode on a side of the oxide semiconductor layer opposite to the substrate;
- a first insulating layer between the first gate electrode and the oxide semiconductor layer;
- a second insulating layer between the oxide semiconductor layer and the second gate electrode;
- a first transparent conductive layer and a second transparent conductive layer on the substrate side of the oxide semiconductor layer;
- a gate signal line between the substrate and the first insulating layer; and
- a data signal line between the first transparent conductive layer and the oxide semiconductor layer,

wherein

- the first transparent conductive layer and the second transparent conductive layer are spaced apart from each other,
- the first gate electrode and the second gate electrode have a region overlapping a region where the first transparent conductive layer and the second transparent conductive layer are spaced apart from each other,
- the first transparent conductive layer and the second transparent conductive layer are in contact with the oxide semiconductor layer,
- the first gate electrode is continuous with the gate signal line in the same layer, and
- the second gate electrode is connected to the gate signal line via a contact hole which though the first insulating layer and the second insulating layer in a region outside the oxide semiconductor layer.

2. The display device according to claim 1,

wherein a surface of the oxide semiconductor layer facing the substrate has a first region in contact with the first transparent conductive layer and a second region in contact with the second transparent conductive layer.

3. The display device according to claim 1,

wherein the data signal line is electrically connected to the oxide semiconductor layer and the first transparent conductive layer.

4. The display device according to claim 3,

wherein a first end of the first transparent conductive layer overlaps the first gate electrode and the second gate electrode, and a first end of the second transparent conductive layer overlaps the first gate electrode and the second gate electrode.

5. The display device according to claim 4,

wherein the data signal line is arranged on a second end opposite to the first end of the first transparent conductive layer.

6. The display device according to claim 5,

wherein the oxide semiconductor layer has a channel region overlapping the first gate electrode and the second gate electrode,

wherein the first end of the first transparent conductive layer is adjacent to the channel region, and the first end of the second transparent conductive layer is adjacent to the channel region, and

wherein the data signal line is arranged apart from the channel region.

7. The display device according to claim 1,

wherein the oxide semiconductor layer contains at least one element, or a plurality of elements selected from indium (In), zinc (Zn), gallium (Ga), tin (Sn), aluminum (Al), and magnesium (Mg), and

wherein the first transparent conductive layer and the second transparent conductive layer are conductive metal oxide.

8. A display device, comprising:

a gate signal line on a substrate;

a data signal line intersecting the gate signal line;

a first gate electrode continuous with the gate signal line;

a first insulating layer on the gate signal line and the first gate electrode;

an oxide semiconductor layer on the first insulating layer and including a region overlapping the first gate electrode;

a first transparent conductive layer and a second transparent conductive layer between the first insulating layer and the oxide semiconductor layer;

a second insulating layer on the oxide semiconductor layer; and

a second gate electrode on the second insulating layer and including a region overlapping the first gate electrode and the oxide semiconductor layer,

wherein

the first transparent conductive layer and the second transparent conductive layer are spaced apart from each other,

the first gate electrode and the second gate electrode have a region overlapping a region where the first transparent conductive layer and the second transparent conductive layer are spaced apart from each other,

the first transparent conductive layer and the second transparent conductive layer are in contact with the oxide semiconductor layer,

the second gate electrode is connected to the gate signal line via a contact hole which though the first insulating layer and the second insulating layer in a region outside the oxide semiconductor layer, and

the data signal line is arranged between the first transparent conductive layer and the oxide semiconductor layer.

9. The display device according to claim 8,

wherein the data signal line is in contact with the oxide semiconductor layer and the first transparent conductive layer.

10. The display device according to claim 9,

wherein a first end of the first transparent conductive layer and a first end of the second transparent conductive layer are arranged to face each other, and

wherein the first end of the first transparent conductive layer and the first end of the second conductive layer are overlap the first gate electrode and the second gate electrode.

11. The display device according to claim 10,

wherein the data signal line is arranged on a second end opposite to the first end of the first transparent conductive layer.

12. The display device according to claim 10,

wherein the oxide semiconductor layer has a channel region overlapping the first gate electrode and the second gate electrode,

wherein the first end of the first transparent conductive layer is adjacent to the channel region, and the first end of the second transparent conductive layer is adjacent to the channel region, and

wherein the data signal line is arranged apart from the channel region.

13. The display device according to claim 9,

wherein the oxide semiconductor layer is overlapped the data signal line.

14. The display device according to claim 8,

wherein the oxide semiconductor layer contains at least one element, or a plurality of elements selected from indium (In), zinc (Zn), gallium (Ga), tin (Sn), aluminum (Al), and magnesium (Mg).

15. The display device according to claim 8,

wherein the first transparent conductive layer and the second transparent conductive layer are conductive metal oxide.

16. The display device according to claim 8,

wherein a width of the second gate electrode is larger than a width of the first gate electrode.

17. The display device according to claim 8,

wherein an area in which the second gate electrode overlaps with the oxide semiconductor layer is larger than an area in which the first gate electrode overlaps with the oxide semiconductor layer.

18. The display device according to claim 8,

further comprising a first capacitance electrode between the substrate and the first insulating layer and a second capacitance electrode overlapping the first capacitance electrode on the first insulating layer, and

wherein the second transparent conductive layer extends between the first insulating layer and the second capacitance electrode and is in contact with the second capacitance electrode.

* * * * *

