



US 20170309863A1

(19) **United States**(12) **Patent Application Publication**
KATO(10) **Pub. No.: US 2017/0309863 A1**(43) **Pub. Date: Oct. 26, 2017**(54) **ORGANIC EL DISPLAY DEVICE**(52) **U.S. Cl.**(71) Applicant: **Japan Display Inc.**, Tokyo (JP)CPC **H01L 51/5253** (2013.01); **H01L 27/3246**
(2013.01); **H01L 27/3258** (2013.01)(72) Inventor: **Daisuke KATO**, Tokyo (JP)(21) Appl. No.: **15/643,538**(57) **ABSTRACT**(22) Filed: **Jul. 7, 2017****Related U.S. Application Data**

(63) Continuation of application No. 15/409,739, filed on Jan. 19, 2017, now Pat. No. 9,735,394, which is a continuation of application No. 14/818,555, filed on Aug. 5, 2015, now Pat. No. 9,583,544.

Foreign Application Priority Data

(30) Aug. 8, 2014 (JP) 2014-162537

Publication Classification(51) **Int. Cl.**
H01L 51/52 (2006.01)
H01L 27/32 (2006.01)
H01L 27/32 (2006.01)

A bank partitions a plurality of pixels and has an opening in each of the plurality of pixels. An organic layer includes a light emitting layer, and covers the bank opening. A first inorganic barrier layer is formed of an inorganic material, and covers the bank and the organic layer. A plurality of organic barrier portions are formed of organic materials, and are disposed on the first inorganic barrier layer. A second inorganic barrier layer is formed of the inorganic material, and covers the first inorganic barrier layer and the plurality of organic barrier portions. A recessed portion is formed on the bank and the first inorganic barrier layer (for example, the recessed portion is formed in an area which covers a contact hole), and a portion of the organic barrier portion is formed in the recessed portion.




FIG. 1




FIG.2




FIG.3





FIG.5



ORGANIC EL DISPLAY DEVICE

CROSS-REFERENCE TO RELATED APPLICATION

[0001] The present application claims priority from Japanese application JP2014-162537 filed on Aug. 8, 2014, the content of which is hereby incorporated by reference into this application.

BACKGROUND OF THE INVENTION

1. Field of the Invention

[0002] The present invention relates to an organic EL display device.

2. Description of the Related Art

[0003] An organic electro luminescence (EL) display device includes a lower electrode disposed in each pixel and a bank disposed on an outer periphery of the lower electrode and partitions pixels adjacent to each other. In addition, the organic el display device includes an organic layer including a light emitting layer. The organic layer covers the bank and the lower electrode. The bank includes a bank opening in each of the pixels, and the organic layer is in contact with the lower electrode inside the bank opening. In addition, generally, the organic layer is likely to be deteriorated due to moisture infiltration to the organic layer. For this reason, in the related art, a barrier structure which covers the organic layer has been proposed. JP2007-184251A, Japanese Patent No. 4303591, and JP2010-272270A disclose a barrier structure formed of a plurality of layers.

[0004] A pin hole may be caused in a barrier structure due to foreign particles such as dust in some cases. When the pin hole is caused, moisture infiltrates into the pin hole, and thereby an organic layer is deteriorated.

[0005] The inventors of the present application have examined the barrier structure including a plurality of barrier layers which are formed of inorganic materials, and an organic material. In the examined barrier structure, a first barrier layer covers the organic layer including a light emitting layer. The organic material is dispersed on the first barrier layer (a portion in which the organic material is formed is referred to as an "organic portion"). When a foreign particle exists on the first barrier layer, the organic portion is formed so as to surround the foreign particle. A second barrier layer covers the first barrier layer and the organic portion. According to this structure, an uneven surface (that is, a difference in level) around the foreign particle is decreased by the organic portion. Therefore, even a second barrier layer with a small thickness can completely cover the foreign particle. That is, even when the thickness of the second barrier layer is made small, the second barrier layer is not ruptured around the foreign particle. As a result, it is possible to efficiently prevent moisture from infiltrating into the organic layer. The organic portion forming the barrier structure is formed as follows. A solvent including the organic material is sprayed on the first barrier layer. The sprayed solvent coheres around the foreign particle due to surface tension of the solvent. Then, the cohered solvent is solidified to become the organic portion.

[0006] However, in a process of forming the organic portion, the organic portions are formed around not only the foreign particle, but also an circumference of the bank

opening (the circumference means a corner between a side surface of the bank and an upper surface of the lower electrode. In other words, the circumference means an area closer to the edge of the bank opening). A refractive index of the organic portion and a refractive index of the barrier layer are different from one another. Due to this, the organic portions result to form a multiple interference film, and color of a light beam emitted from a center portion of the bank opening is different from that of a light beam emitted from the circumference.

[0007] The present invention has been made in view of the relevant problem, and an object of the present invention is to provide an organic el display device which is capable of reducing an amount of organic materials stored in the circumference of the bank opening when forming a barrier structure which includes the organic material.

[0008] (1) According to an aspect of the present invention, there is provided an organic EL display device including: a bank partitioning a plurality of pixels, and having an opening formed in each of the plurality of pixels; an organic layer including a light emitting layer, and including a portion formed inside the opening of the bank; a first barrier layer formed of an inorganic material, and covering the bank and the organic layer; a plurality of organic portions formed of organic materials, and disposed on the first barrier layer; and a second barrier layer formed of an inorganic material, and covering the first barrier layer and the plurality of organic portions. A recessed portion is formed on the bank and the first barrier layer. A portion of the plurality of organic portions is formed in the recessed portion.

[0009] (2) The organic EL display device according to (1) may further include a TFT provided in each of the plurality of pixels; a planarization film covering the TFT; and a lower electrode provided in each of the plurality of pixels, formed on the planarization film, and connected to the TFT via a contact hole formed on the planarization film. The bank covers the contact hole, and the recessed portion on the bank and the first barrier layer is a portion which is recessed due to the contact hole.

[0010] (3) In the organic EL display device according to (2), a thickness of the bank is smaller than a thickness of the planarization film.

[0011] (4) In the organic EL display device according to (1), each of the plurality of pixels has, in the bank and the first barrier layer, the recessed portion in which the organic portion is disposed.

[0012] (5) In the organic EL display device according to (1), an area in which the organic portion does not exist is formed between the first barrier layer and the second barrier layer.

BRIEF DESCRIPTION OF THE DRAWINGS

[0013] FIG. 1 is a plane view schematically illustrating an organic EL display device according to the present invention.

[0014] FIG. 2 is a circuit diagram illustrating an example of a circuit which is formed on a TFT substrate.

[0015] FIG. 3 is a plane view of the organic EL display device according to the invention.

[0016] FIG. 4 is a sectional view taken along line IV-IV shown in FIG. 3.

[0017] FIG. 5 is a diagram illustrating a state where foreign particle is mixed.

DETAILED DESCRIPTION OF THE INVENTION

[0018] Hereinafter, an embodiment of the present Invention will be described with reference to the drawings. Note that, disclosure in the present specification is merely one example. A modification which maintains the spirit of the invention and is suitably made by those skilled in the art is surely contained in the scope of the invention. In addition, in order to make the description of the drawings mere clear, a width, a thickness, and a shape of each portion in the present embodiment may be schematically represented as compared with the actual embodiment in some cases. The description of the drawings is merely an example, and does not limit the interpretation of the invention.

[0019] FIG. 1 is a plane view schematically illustrating an organic electro luminescence (EL) display device 2 according to the invention. The organic EL display device 2 includes a thin film transistor (TFT) substrate 12, and a counter substrate 13 facing the TFT substrate 12. A filler 30 (refer to FIG. 4) is filled between these substrates. The organic EL display device 2 has a plurality of pixels PX which are arrayed in a display area I in a horizontal direction and a vertical direction.

[0020] FIG. 2 is a circuit diagram illustrating an example of a circuit formed on the TFT substrate 12. A plurality of scanning signal lines GL extending in the horizontal direction, a plurality of video signal lines DL extending in the vertical direction are formed on the TFT substrate 12. An area which is surrounded by two scanning signal lines GL adjacent to each other and two video signal lines DL adjacent to each other is one pixel PX. Power supply lines CSL are formed on the TFT substrate 12. As described below, an organic layer 18 including a light emitting layer, a driving TFT element 10 for controlling the electric charge supply to the organic layer 18, or the like is formed on the TFT substrate 12 (refer to FIG. 4). As illustrated in FIG. 2, the driving TFT element 10, a storage capacitor CPR, and a switching TFT 11 are formed in each of the pixels PX. In addition, an organic light-emitting diode OD is formed in each of the pixels PX. The organic light-emitting diode OD is formed of the organic layer 18, and a lower electrode A (for example, an anode electrode) and an upper electrode 20 (for example, a cathode electrode) (refer to FIG. 4). The switching TFT 11 is turned on by applying a gate voltage to the scanning signal line GL. At this time, a video signal is supplied from the video signal line DL, and then electric charges are accumulated in the storage capacitor CPR. In addition, the driving TFT element 10 is turned on by accumulating the electric charges in the storage capacitor CPR, and electric current flows from the power supply line CSL to the organic light-emitting diode OD, thereby emitting the organic light-emitting diode OD.

[0021] The plurality of pixels PX form one pixel unit. FIG. 3 is a plans view of the TFT substrate 12 illustrating one pixel unit. FIG. 4 is a sectional view of the organic EL display device 2 taken along line IV-IV shown in FIG. 3. For example, as illustrated in FIG. 3, four pixels form one pixel unit. The four pixels PX include, for example, a red pixel PX, a green pixel PX, a blue pixel PX, and a white pixel PX. The four pixels PX are disposed, for example, in two columns and two rows. The disposition of the pixels PX which form the pixel unit is not limited to that as illustrated in FIG. 3. For example, the four pixels PX forming one pixel unit may be arrayed in one direction (for example, in the

horizontal direction). In addition, the number of pixels PX forming one pixel unit is not limited to four as illustrated in FIG. 3. For example, one pixel unit may be formed of three pixels PX (for example, the red pixel PX, the green pixel PX, and the blue pixel PX). The display device 2 may be a color filter type or a separate coloring type. That is, the organic layer 18 as described below is formed in the entire display area so as to emit white light, and a color filter corresponding to a color of each of the pixels may be formed on the counter substrate 13 (the color filter type). The organic layer 18 may be separated for each pixel so as to emit light with the color of each pixel (the separate coloring type).

[0022] As illustrated in FIG. 4, the lower electrode 4 is formed on the TFT substrate 12. The lower electrode 4 is formed in each of the pixels PX. The TFT substrate 12 is provided with a bank 16 partitioning the plurality of pixels PX. In FIG. 3, an area of the bank 16 is hatched. As illustrated in FIG. 4, the bank 16 surrounds the outer periphery of each lower electrode 4 and overlaps a peripheral edge of the lower electrode 4. The bank 16 has a bank opening A in each of the pixels PX, and the lower electrode 4 is exposed to the bank opening A. In addition, a plurality of contact holes CH are formed on the TFT substrate 12. The contact hole CH is covered with the bank 16. In an example illustrated in FIG. 3, the lower electrode 4 is formed into a rectangular shape, and the contact hole CH is formed in each of the pixels PX.

[0023] As illustrated in FIG. 4, the TFT substrate 12 includes a planarization film 14 on a layer below the lower electrode 4. The TFT substrate 12 includes a substrate 8, and a circuit layer including the driving TFT element 10 is formed on an upper surface of the substrate 8. The driving TFT element 10 is a switching element for controlling the electric current which flows into the lower electrode 4 (in FIG. 4, a detailed structure of the driving TFT element 10 is omitted). The planarization film 14 covers the circuit layer. In addition, the planarization film 14 in each of the pixels includes the aforementioned contact hole CH (a through hole passing through the planarization film 14). The lower electrode 4 is connected to the driving TFT element 10 via the contact hole CH. A reference symbol D1 indicates the film thickness of the planarization film 14.

[0024] As described above, the TFT substrate 12 is formed of an insulator, and has the bank 16 formed on the lower electrode 4. The bank opening A is formed on the bank 16. For example, as illustrated in FIG. 3, the bank opening A is formed into an shape in a planar view. In a forming process of the bank 16, first, a layer of the insulator (a material of the bank 16) is formed on the lower electrode 4. Thereafter, a portion corresponding to the bank opening A is removed from the formed layer. In this way, the bank 16 is formed. As illustrated in FIG. 4, the bank 16 includes an area CV covering the contact hole CH. For example, as illustrated in FIG. 3, the four pixels PX which form one pixel unit are formed in such a manner that the areas CV of the four pixels PX are connected to each other at a center portion C in the one pixel unit. That is, the bank openings A of the four pixels PX are disposed so as to surround the center portion C of the four pixels PX. The position or shape of the bank opening A is not limited to that as illustrated in FIG. 3.

[0025] The bank 16 includes a recessed portion 16a which is recessed due to the contact hole CH in the area CV covering the contact hole CH. In the present embodiment, a film thickness D2 of the bank 16 (a distance between the

lower electrode 4 and the upper surface of the bank 26) is small. For example, it is preferable that the film thickness D2 of the bank 16 is smaller than the film thickness D1 of the planarization film 14. Therefore, the undulation (the recessed portion 16a) corresponding to cross-sectional shapes of the planarization film 14 and the lower electrode 4 is easily formed in the bank 16. The film thickness D2 of the bank 16 may be smaller than half of the film thickness D1 of the planarization film 14. The recessed portion 16a of the bank 16 formed in the area CV is made due to the undulation of the planarization film 14 and the lower electrode 4 in a process where the bank 16 is formed on the lower electrode 4.

[0026] The TFT substrate 12 includes an element of the organic light-emitting diode OD as illustrated in FIG. 2 in addition to the lower electrode 4. That is, the TFT substrate 12 has the organic layer 18 including a light emitting layer which emits light due to the phenomenon of organic electroluminescence, and the upper electrode 20. When a voltage is applied to the lower electrode 4 and the upper electrode 20 through the driving TFT element 10, holes and electrons are injected into each of the organic layer 18 from the lower electrode 4 and the upper electrode 20, and the injected holes and electrons are coupled in the light emitting layer to emit light. The bank 16 prevents a short circuit from being generated between the lower electrode 4 and the upper electrode 20.

[0027] The organic layer 16 includes a portion formed inside the bank opening A. In an example illustrated in FIG. 4, the organic layer 18 is consecutively formed on an end portion of the bank 16 and the lower electrode 4. The upper electrode 20 is consecutively formed on, and covers the bank 16 and the organic layer 18. The upper electrode 20 includes a recessed portion which is recessed due to the contact hole CH in the area CV covering the contact hole CH. In addition, the upper electrode 20 has an uneven portion which is swollen in response to the shape of the bank 16 in a circumference P (an edge portion of the bank opening A) of the bank opening A. In the process of forming the organic layer 18 and the upper electrode 20, the recessed portion and the uneven portion are generated on the organic layer 18 and the upper electrode 20 in response to undulations of the cross-sectional shape of the lower electrode 4 and the bank 16 (that is, convexo-concave of the lower electrode 4 and the bank 16).

[0028] The organic layer 18 and the upper electrode 20 are covered with a barrier layer 22. That is, the barrier layer 22 is consecutively formed on the upper electrode 20 (to cover the upper electrode 20). The barrier layer 22 protects the organic light-emitting diode (particularly, the organic layer 18) from moisture.

[0029] The counter substrate 13 (refer to FIG. 1) is disposed above the barrier layer 22. The filler 30 is filled between the barrier layer 22 and the counter substrate 13.

[0030] As illustrated in FIG. 4, the barrier layer 22 has a multi-layer structure in which a plurality of organic barrier portions 26 are sandwiched between a first inorganic barrier layer 24 and a second inorganic barrier layer 28. The first inorganic barrier layer 24 is provided to protect the organic layer 18 from moisture. The first inorganic barrier layer 24 is consecutively formed on the upper electrode 20 as illustrated in FIG. 4, and covers the bank 16 and the organic layer 18. The first inorganic barrier layer 24 is formed of an inorganic material which prevents moisture from infiltrating.

The inorganic material is, for example, SiN, but is not limited to SiN. The first inorganic barrier layer 24 may be formed of one or a plurality of layers. For example, the first inorganic barrier layer 24 may include a SiN layer and a SiO layer. In this case, the SiO layer may constitute an upper layer of the first inorganic barrier layer 24, and may be in contact with the organic barrier portions 26 and the second inorganic barrier layer 28. With this configuration, it is possible to improve adhesive properties between the organic barrier portions 26 and the first inorganic barrier layer 24. The first inorganic barrier layer 24 has a recessed portion which is recessed due to the contact hole CH in the area CV. In addition, the first inorganic barrier layer 24 has an uneven portion which is swollen in response to the shape of the bank 16 in the circumference P. The first inorganic barrier layer 24 can be formed on the upper electrode 20 by using, for example, a plasma CVD method. The recessed portion and the uneven portions of the first inorganic barrier layer 24 are formed in response to undulations of the shape of the upper electrode 20 in the process of forming the first inorganic barrier layer 24. A pin hole h is formed on the first inorganic barrier layer 24 because of foreign particle 21. FIG. 5 is a diagram illustrating a state where the foreign particle 21 is mixed in the first inorganic barrier layer 24. As illustrated in FIG. 5, the pin hole h is formed on the bottom of the foreign particle 21. This pin hole h causes moisture infiltration from the outside.

[0031] The plurality of organic barrier portions 26 are disposed on the first inorganic barrier layer 24. It is possible to fill the pin hole h with the plurality of organic barrier portions 26. These organic barrier portions 26 are formed of organic materials (for example, an acrylic resin, a polyimide resin, and an epoxy resin), and dispersed on the first inorganic barrier layer 24. That is, as illustrated in FIG. 4 and FIG. 5, the organic barrier portion 26 is formed in the recessed portion (that is, the area CV) and the uneven portion (that is, the circumference P in the bank opening A) which are formed on the first inorganic barrier layer 24. When the foreign particle 21 is mixed in the first inorganic barrier layer 24, the organic barrier portion 26 surrounds the foreign particle 21 as illustrated in FIG. 5, and thus, the pin hole h is filled with the organic barrier portion 26.

[0032] These organic barrier portions 26 are formed by spraying a solvent which is obtained by mixing the organic material and a polymerization initiator to the first inorganic barrier layer 24 under the vacuum condition. Specifically, the solvent is intermittently sprayed by a certain amount. At this time, the supplying conditions of the solvent (a supplying time, the temperature of a substrate, the atmosphere for forming a film, or the like) are adjusted so that the organic material does not form a film which is consecutively formed on the first inorganic barrier layer 24. The attached organic materials exhibit behavior as a liquid, and thus easily cohere by its surface tension in a spot that is not flattened, and do not easily cohere in a flat place. For this reason, the organic materials are stored in the recessed portion, the uneven portion (that is, the circumference P), and the pin hole h formed on the first inorganic barrier layer 24. The organic materials are not easily stored in other places. Accordingly, the plurality of organic barrier portions 26 are dispersed on the first inorganic barrier layer 24.

[0033] When the foreign particle 21 is mixed, the second inorganic barrier layer 28 is formed so as to completely cover the foreign particle 21. Similar to the first inorganic

barrier layer **24**, the second inorganic barrier layer **23** is formed of an inorganic material which prevents moisture from infiltrating. The inorganic material is, for example, SiN, but is not limited to SiN, similar to the material of the first inorganic barrier layer **24**. The second inorganic barrier layer **23** may be formed of one or a plurality of layers similar to the first inorganic barrier layer **24**. The second inorganic barrier layer **28** is consecutively formed on, and covers the first inorganic barrier layer **24** and the plurality of organic barrier portions **26**, as illustrated in FIG. 4 and FIG. 5. The second inorganic barrier layer **23** is formed, for example, by using the plasma CVD method. The foreign particle **21** is surrounded by the organic barrier portion **26** which is filled in the pin hole h. For this reason, the second inorganic barrier layer **28** is not ruptured due to the foreign particle **21**, but can completely cover the foreign particle **21**. Accordingly, even when the foreign particle **21** is mixed as illustrated in FIG. 5, the barrier layer **22** can protect the organic light-emitting diode OD from moisture by employing this multi-layer structure.

[0034] The organic barrier portion **26** formed in the uneven portion (that is, the circumference P) in the first inorganic barrier layer **24** results to make a multiple interference film due to the difference of an optical refractive index between the organic barrier portion **26** and the inorganic barrier layers **24** and **28**, and thus has an effect on the light emission from the pixel. In addition, an amount of the organic barrier portion **26** in a pixel sensitively depends on the unevenness of the circumference P in the bank opening A. Since the unevenness of each of the pixels is not exactly the same as one another, optical properties of the pixels vary according to the unevenness. Accordingly, it is preferable to lessen the amount of the organic material stored in the uneven portion to thereby reduce the size of the organic barrier portions **26** formed in the uneven portion.

[0035] In the organic EL display device **2**, the recessed portion is formed on the first inorganic barrier layer **24** due to the recessed portion **16a** formed in the bank **16**. For example, in the example illustrated in FIG. 4, in the area CV, the recessed portion is formed on the first inorganic barrier layer **24** due to the recessed portion **16a** of the bank **16** which is formed in the area CV and covers the contact hole CH. Accordingly, in the process of forming the organic barrier portion **26**, the organic material is stored not only in the circumference P (that is, the uneven portion in the first inorganic barrier layer **24**) in the bank opening A, but also the recessed portion **16a**. Therefore, it is possible to lessen the amount of the organic material stored in the circumference P in the bank opening A to thereby reduce the size of the organic barrier portions **26** formed in the circumference P.

[0036] As described above, the recessed portion in the area CV which is formed on the bank **16**, the organic layer **18**, and the first inorganic barrier layer **24** is formed by using the contact hole CH. Thus, a process (for example, an etching process) of forming the recessed portion may not be additionally performed. A relationship between the thickness of the planarization film **14** and the thickness of each of the bank **16**, the organic layer **18**, and the first inorganic barrier layer **24** is designed so that the recessed portion in the first inorganic barrier layer **24** is made due to the contact hole CH of the planarization film **14**. For example, the film thickness D2 of the bank **16** is smaller than the film thickness D1 of

the planarization film **14**. Thus, the size of the recessed portion of the bank **16** becomes larger.

[0037] The organic EL display device **2** is manufactured as follows. The circuit layer including the driving TFT element **10** is formed on the upper surface of the substrate **8**. Then, the planarization film **14** for covering the circuit layer is formed on the substrate **8**. In addition, the contact hole (the through hole) CH is formed on the planarization film **14**. The contact hole can be formed through a photolithography process. The lower electrode **4** is formed above the planarization film **14**. The lower electrode **4** is formed in each of the pixels. The bank **16** is formed above the lower electrode **4**. The bank **16** is patterned so as to include the opening A in each of the pixels. The recessed portion **16a** is formed in the bank **16**. The recessed portion **16a** is formed due to the contact hole CH. The organic layer **18** including the light emitting layer is formed on the bank **16** and the lower electrode **4**. The organic layer **18** includes a portion formed inside the bank opening A and comes in contact the lower electrode **4**. The organic layer **18** may be formed by vacuum deposition method or may be formed by printing method. The upper electrode **20** is formed on the organic layer **18** so as to cover the organic layer **18**. Then, the first inorganic barrier layer **24** for covering the bank **16**, the organic layer **18**, and the upper electrode **20** is formed of the inorganic material, as described above, the first inorganic barrier layer **24** can be formed on the upper electrode **20** by, for example, the plasma CVD method. The thickness of each of the organic layer **18**, the upper electrode **20**, and the first inorganic barrier layer **24** is smaller than that of the bank **16**, and thus the recessed portion due to the recessed portion **16a** of the bank **16** is formed on the first inorganic barrier layer **24** as well. Thereafter, as described above, the organic material is sprayed on the first inorganic barrier layer **24**, and the plurality of organic barrier portions **26** formed of the organic material are formed on the first inorganic barrier layer **24**. At this time, a portion of the organic barrier portion **26** is formed at a position due to the recessed portion **16a** of the bank **16**. In addition, a portion of the organic barrier portion **26** is formed in the circumference in the bank opening A as well. Thereafter, the second inorganic barrier layer **28** which covers the first inorganic barrier layer **24** and the plurality of organic barrier portions **26** is formed of the inorganic material. The organic EL display device **2** is obtained by applying the filler **30** on the second inorganic barrier layer **28**, and bonding the counter substrate **13** to the TFT substrate **12**.

[0038] In the organic EL display device **2**, the organic barrier portion **26** is also formed at a position due to the recessed portion **16a**. For this reason, it is possible to reduce the amount of the organic barrier portion **26** stored in the circumference P while forming the sufficient amount of the organic barrier portion **26** so as to surround the foreign particle **21**. As a result, it is possible to reduce the variation of optical properties among the pixels while maintaining moisture blocking properties for the organic layer **18**.

[0039] The present invention is not limited to the above embodiment, and various modifications are possible. For example, the configuration described in the above embodiment may be replaced with substantially the same configuration, a configuration which exhibits the same effects, or a configuration which achieves the same object.

[0040] For example, the first inorganic barrier layer **24** may have a layered structure constituted by the inorganic

material (for example, SiN) layer and the SiO layer thereon. With the SiO layer, it is possible to prompt the cohesion of the organic material due to the surface tension.

[0041] In addition, for example, the film thickness D2 of the bank 16 may be greater than the film thickness D1. In addition, for example, the recessed portion 16a may be formed in the bank 16 through etching. For example, when the film thickness D2 of the bank 16 is large, and thus the recessed portion 16a is not easily formed in the area CV, the recessed portion 16a may be formed in the bank 16 through the etching. In addition, when the recessed portion 16a is formed in the bank 16 through the etching, the recessed portion 16a may be formed over the entirety of the plurality of pixels PX (for example, over the plurality of pixels PX forming one pixel unit).

[0042] Further, the recessed portion 16a which is formed in the bank 16 may be formed anywhere without being limited to the area CV which covers the contact hole CH.

What is claimed is:

1. An organic EL display device comprising:
 - a substrate;
 - a planarization layer on the substrate;
 - a lower electrode on the planarization layer;
 - a bank on the lower electrode;
 - an upper electrode on the bank;
 - a first inorganic barrier layer on the upper electrode;
 - a first organic portion on the first inorganic barrier layer;
 - and
 - a second inorganic barrier layer on the first inorganic barrier layer;
 wherein the bank has a circumference,
 - the first inorganic barrier layer has an uneven portion along the circumference,
 - the first organic portion is in the circumference,
 - the first inorganic barrier layer and the second inorganic barrier layer contact directly in the circumference, and
 - the first inorganic barrier layer or the second inorganic barrier layer is made of SiO.
2. The organic EL display device according to claim 1, comprising:
 - a second organic portion on the first inorganic barrier layer,
 wherein the first organic portion and the second organic portion are between the first inorganic barrier layer and the second inorganic barrier layer.
3. The organic EL display device according to claim 2, wherein
 - the bank is swollen in the circumference and the circumference has an opening inside.
4. The organic EL display device according to claim 2, comprising:
 - a third organic portion outside the circumference and between the first inorganic barrier layer and the second inorganic barrier layer.
5. The organic EL display device according to claim A, wherein
 - the bank has a recessed portion outside the circumference and on a recessed part of the planarization film and the first inorganic barrier layer and a surface of the third organic layer are shaped along the recessed portion.
6. The organic EL display device according to claim 2, wherein

the first inorganic barrier layer and the second inorganic barrier layer contact directly between the second organic portion and the third organic portion.

7. The organic EL display device according to claim 1, wherein

along a direction perpendicular to an upper surface of the substrate, the planarization film, the first inorganic barrier layer and the second inorganic barrier layer are laminated in a region where the bank or the first organic portion is not laminated.

8. The organic EL display device according to claim 1, wherein

at least one of the first inorganic barrier layer and the second inorganic barrier layer has multi layers and one layer of the multi layers is made of SiO and contacts the first organic portion and the second inorganic barrier layer directly.

9. An organic EL display device comprising:

- a substrate;
 - a planarization layer on the substrate;
 - a lower electrode on the planarization layer;
 - a bank on the lower electrode;
 - an upper electrode on the bank;
 - a first inorganic barrier layer on the upper electrode;
 - a first organic portion and a second organic portion on the first inorganic barrier layer; and
 - a second inorganic barrier layer on the first inorganic barrier layer;
- wherein the first inorganic barrier layer has a circumference of an uneven portion,
- the first inorganic barrier layer and the second inorganic barrier layer contact directly between the first organic portion and the second organic portion, and
- the first inorganic barrier layer or the second inorganic barrier layer is made of SiO.

10. The organic EL display device according to claim 9, wherein

the first organic portion contacts the first inorganic barrier layer and the second inorganic barrier layer directly and the second organic portion contacts the first inorganic barrier layer and the second inorganic barrier layer directly.

11. The organic EL display device according to claim 9, wherein

the bank has two swollen regions adjacent each other.

12. The organic EL display device according to claim 9, comprising:

- a third organic portion outside the uneven portion and between the first inorganic barrier layer and the second inorganic barrier layer.

13. The organic EL display device according to claim 12, wherein

the first inorganic barrier layer has a recessed portion and the third organic portion is on the recessed portion. 14.

The organic EL display device according to claim 9, wherein

the first organic portion and the second organic portion are in the circumference.

15. The organic EL display device according to claim 9, wherein

along a direction perpendicular to an upper surface of the substrate, the planarization film, the first inorganic barrier layer and the second inorganic barrier layer are

laminated in a region where the bank, the first organic portion or the second layer is not laminated.

16. The organic EL display device according to claim **9**, wherein

the first inorganic barrier layer or the second inorganic barrier layer has inorganic barrier layers and one of the inorganic barrier layers is made of SiO and contacts the first organic portion and the second inorganic barrier layer directly.

17. The organic EL display device according to claim **12**, wherein

the first inorganic barrier layer has a recessed portion outside the uneven portion and the third organic portion is on the recessed portion.

18. An organic EL display device comprising:

a substrate;

a planarization layer on the substrate; a lower electrode on the planarization layer;

a bank on the lower electrode;

an upper electrode on the bank;

a first inorganic barrier layer on the upper electrode;

a first organic portion and a second organic portion on the first inorganic barrier layer; and

a second inorganic barrier layer on the first inorganic barrier layer;

wherein the first inorganic barrier layer and the second inorganic barrier layer contact directly between the first organic portion and the second organic portion, the first inorganic barrier layer has an uneven portion with a circumference,

the first organic portion and the second organic portion are on the circumference and

the first inorganic barrier layer or the second inorganic barrier layer is made of SiO.

19. An organic EL display device comprising:

a substrate;

a planarization film on the substrate;

a lower electrode on the planarization film;

a bank on the lower electrode;

an organic light emitting layer on the lower electrode and the bank;

an upper electrode on the organic light emitting layer;

a first barrier layer which is arranged on the upper electrode and includes a first inorganic compound film made of a silicon and a nitride and a second inorganic compound film made of a silicon and an oxide on the first inorganic compound film;

a first organic layer on the first barrier layer;

a second organic layer on the first barrier layer; and

a second barrier layer which is arranged on the first barrier layer and the first and the second organic layers and includes a third inorganic compound film and a fourth inorganic compound film, wherein

the bank covers an edge portion of the lower electrode and has an opening exposing a part of a surface of the lower electrode,

a first region in which the planarization film, the first barrier layer, and the second barrier layer are laminated and in which the bank and the first and the second organic layers are not formed is arranged on the substrate, a second region in which the planarization film, the first

barrier layer, the first organic layer, and the second barrier layer are laminated and in which the bank is not formed is arranged on the substrate.

a third region in which the planarization film, the bank, the first barrier layer, and the second barrier layer are laminated and in which the first and the second organic layers are not formed is arranged on the substrate, and

a fourth region in which the bank, the first barrier layer, the second organic layer, and the second barrier layer are laminated and in which the planarization film is not formed is arranged on the substrate.

20. A organic EL display device comprising:

a substrate;

a planarization film on the substrate;

a lower electrode on the planarization film;

a bank on the lower electrode;

an organic light emitting layer on the lower electrode and the bank;

an upper electrode on the organic light emitting layer;

a first barrier layer on the upper electrode;

a first organic layer on the first barrier layer;

a second organic layer on the first barrier layer; and

a second barrier layer on the first barrier layer and the first and the second organic layers,

wherein

the bank covers an edge portion of the lower electrode and has an opening exposing a part of a surface of the lower electrode,

a first region in which the planarization film, the first barrier layer, and the second barrier layer are laminated and in which the bank and the first and the second organic layers are not formed is arranged on the substrate,

a second region in which the planarization film, the first barrier layer, the first organic layer, and the second barrier layer are laminated and in which the bank is not formed is arranged on the substrate,

a third region in which the planarization film, bank, the first barrier layer, and the second barrier layer are laminated and in which the first and the second organic layers are not formed is arranged on the substrate, and

a fourth region in which the bank, the first barrier layer, the second

organic layer, and the second barrier layer are laminated and in which the planarization film is not formed is arranged on the substrate.

* * * * *

专利名称(译)	有机el显示设备		
公开(公告)号	US20170309863A1	公开(公告)日	2017-10-26
申请号	US15/643538	申请日	2017-07-07
[标]申请(专利权)人(译)	株式会社日本显示器		
申请(专利权)人(译)	日本展示INC.		
当前申请(专利权)人(译)	日本展示INC.		
[标]发明人	KATO DAISUKE		
发明人	KATO, DAISUKE		
IPC分类号	H01L51/52 H01L27/32		
CPC分类号	H01L51/5253 H01L27/3246 H01L27/3258		
优先权	2014162537 2014-08-08 JP		
其他公开文献	US9899630		
外部链接	Espacenet USPTO		

摘要(译)

存储体划分多个像素并且在多个像素中的每个像素中具有开口。有机层包括发光层，并覆盖堤开口。第一无机阻挡层由无机材料形成，并覆盖堤和有机层。多个有机阻挡部分由有机材料形成，并设置在第一无机阻挡层上。第二无机阻挡层由无机材料形成，并覆盖第一无机阻挡层和多个有机阻挡部分。凹陷部分形成在堤岸和第一无机阻挡层上（例如，凹陷端口离子形成在覆盖接触孔的区域中），并且有机阻挡部分的一部分形成在凹陷部分中。

