



US008389986B2

(12) **United States Patent**
Kim et al.(10) **Patent No.:** **US 8,389,986 B2**
(45) **Date of Patent:** **Mar. 5, 2013**(54) **CONDENSED-CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**WO WO 2006/098229 A1 9/2006
WO WO 2010/083872 A2 7/2010
WO WO 2010/110553 A2 9/2010(75) Inventors: **Hee-Yeon Kim**, Yongin (KR);
Seung-Gak Yang, Yongin (KR);
Jeoung-In Yi, Yongin (KR); **Jae-Yong Lee**, Yongin (KR); **Yoon-Hyun Kwak**, Yongin (KR)(73) Assignee: **Samsung Display Co., Ltd.**, Yongin, Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 132 days.

(21) Appl. No.: **13/078,491**(22) Filed: **Apr. 1, 2011**(65) **Prior Publication Data**

US 2011/0240979 A1 Oct. 6, 2011


(30) **Foreign Application Priority Data**Apr. 1, 2010 (KR) 10-2010-0029992
Mar. 29, 2011 (KR) 10-2011-0028212(51) **Int. Cl.**
H01L 51/00 (2006.01)(52) **U.S. Cl.** **257/40**; 257/103; 257/E51.018;
257/E51.026; 257/E51.028; 548/418(58) **Field of Classification Search** 257/40,
257/103, E51.018, E51.026, E51.028; 548/418
See application file for complete search history.(56) **References Cited****U.S. PATENT DOCUMENTS**5,843,607 A 12/1998 Hu et al.
5,952,115 A * 9/1999 Hu et al. 428/690
7,456,424 B2 11/2008 Wu et al.
2008/0014464 A1 1/2008 Kawamura et al.
2008/0124572 A1 5/2008 Mizuki et al.
2009/0066225 A1 3/2009 Kimura et al.
2009/0295276 A1 12/2009 Asari et al.
2009/0302742 A1 12/2009 Komori et al.**FOREIGN PATENT DOCUMENTS**DE 198 31 427 A1 1/2000
EP 0 906 948 A1 4/1999
EP 0 908 787 A2 4/1999
EP 0906947 A1 4/1999
EP 2080762 A1 7/2009
JP 2008-251394 A 10/2008
KR 10 2007-0110371 A 11/2007
KR 10 2008-0085000 A 9/2008
KR 10 2008-0085001 A 9/2008
KR 10 2009-0021174 A 2/2009
KR 10 2009-0035729 A 4/2009
KR 10 2009-0086057 A 8/2009
KR 10-2010-0131629 A 12/2010
KR 10-2010-0131745 A 12/2010
KR 10-2010-0131939 A 12/2010
KR 10-2011-0011578 A 2/2011**OTHER PUBLICATIONS**Bocchi, Vittorio, et al., "Synthesis and Characterization of New Indole Trimers and Tetramers," *Tetrahedron*, vol. 42, No. 18, 1986, pp. 5019-5024.Domiano, Paolo, et al., "Synthesis and structure of 1-(2-amino)phenyl-2-phenyl-12*H*-indolo[3,2-*c*]carbazole ethylacetate solvate, a new indolocarbazole compound," *Journal of Crystallographic and Spectroscopic Research*, vol. 19, No. 2, 1989, pp. 277-287.Frost, Jonathan R., et al., "Intermolecular Trapping by Indole of a Spiroindolenine Intermediate Formed During the Bischler-Napieralski Cyclisation of N-acetyltryptamine," *Heterocycles*, vol. 28, No. 1, 1989, pp. 175-182.Ishii, Hisashi, et al., "Polymerisation of Indole. Part 3. Two Indolylquinolines, an Indole Tetramer, and the Dihydro Derivative of the Indole Dimer," *Journal of the Chemical Society, Perkin Transactions 1*, 1988, pp. 2387-2395.Laronze-Cochard, Marie, et al., "Synthesis and biological evaluation of new penta- and heptacyclic indolo- and quinolinocarbazole ring systems obtained via Pd⁰ catalysed reductive N-heteroannulation," *Organic & Biomolecular Chemistry*, vol. 8, 2010, pp. 4625-4636.Lengvinaite, S., et al., "Indolo[3,2-*b*]carbazole-based functional derivatives as materials for light emitting diodes," *Dyes and Pigments*, vol. 85, 2010, pp. 183-188.Liu, Zhiqiang, et al., "TPA-active D- π -D fluorophores with rigid, planar cores from phenylene to indenofluorene and indolocarbazole," *Dyes and Pigments*, vol. 86, 2010, pp. 63-67.Nebel, Claude, et al., "Dibenzo[2,3:5,6]pyrrolizino[1,7-*bc*]indolo[1,2,3-*lm*]carbazole: a new electron donor," *New Journal of Chemistry*, vol. 34, 2010, pp. 1243-1246.Yudina, Larisa N., et al., "Synthesis and alkylation of indolo[3,2-*b*]carbazoles," *Tetrahedron*, vol. 59, 2003, pp. 1265-1275.

(Continued)

Primary Examiner — Tu-Tu Ho

(74) *Attorney, Agent, or Firm* — Lee & Morse, P.C.(57) **ABSTRACT**

A condensed-cyclic compound and an OLED including the same, the condensed-cyclic compound represented by Formula 1 below:

**27 Claims, 1 Drawing Sheet**

OTHER PUBLICATIONS


Zhao, Hua-Ping, et al., "Effect of substituents on the properties of indolo[3,2-*b*]carbazole-based hole-transporting materials," *Organic Electronics*, vol. 8, 2007, pp. 673-682.

Zhao, Hua-Ping, et al., "Indolo[3,2-*b*]carbazole: Promising building block for highly efficient electroluminescent materials," *Organic Electronics*, vol. 10, 2009, pp. 925-931.

Zhao, Hua-Ping, et al., "Structure and electronic properties of triphenylamine-substituted indolo[3,2-*b*]carbazole derivatives as hole-transporting materials for organic light-emitting diodes," *Chemical Physics Letters*, vol. 439, 2007, pp. 132-137.

European Search Report issued in corresponding application, EP 11 16 0544, dated Jul. 5, 2011.

* cited by examiner



1

CONDENSED-CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

BACKGROUND

1. Field

Embodiments relate to a condensed-cyclic compound and organic light-emitting devices including the same.

2. Description of the Related Art

Organic light-emitting devices (OLEDs), which are self-emitting devices, have advantages, e.g., a wide viewing angle, excellent contrast, quick response, high brightness, excellent driving voltage characteristics, and can provide multicolored images.

A typical OLED may have a structure including, e.g., a substrate, and an anode, a hole transport layer (HTL), an emission layer (EML), an electron transport layer (ETL), and a cathode, which are sequentially stacked on the substrate. In this regard, the HTL, the EML, and the ETL may be organic thin films formed of organic compounds.


An operating principle of an OLED having the above-described structure is as follows.

When a voltage is applied between the anode and the cathode, holes injected from the anode move to the EML via the HTL, and electrons injected from the cathode move to the EML via the ETL. The holes and electrons recombine in the EML to generate excitons. When the excitons drop from an excited state to a ground state, light is emitted.

SUMMARY

It is a feature of an embodiment to provide a condensed-cyclic compound and an organic light-emitting device including the same.


At least one of the above and other features and advantages may be realized by providing a condensed-cyclic compound represented by Formula 1 below:



Formula 1

wherein, in Formula 1:

ring A is represented by Formula 2 below or Formula 3 below:




Formula 2

2

-continued

Formula 3



R_1 through R_{12} are each independently a hydrogen atom, a heavy hydrogen atom (deuterium), a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C_1 - C_{30} alkyl group, a substituted or unsubstituted C_2 - C_{30} alkenyl group, a substituted or unsubstituted C_2 - C_{30} alkynyl group, a substituted or unsubstituted C_1 - C_{30} alkoxy group, a first substituent represented by $-(Ar_1)_a-Ar_{11}$, a second substituent represented by $-N[-(Ar_2)_b-Ar_{12}][-(Ar_3)_c-Ar_{13}]$, or a third substituent represented by $-(Ar_4)_d-N[(Ar_5)_e-Ar_{15}][-(Ar_6)_f-Ar_{16}]$,

at least one of R_1 through R_{12} is the third substituent;

Ar_1 through Ar_6 , among the first through third substituents, are each independently a substituted or unsubstituted C_1 - C_{30} alkylene group, a substituted or unsubstituted C_2 - C_{30} alkenylene group, a substituted or unsubstituted C_5 - C_{30} arylene group, or a substituted or unsubstituted C_3 - C_{30} heteroarylene group;

Ar_{11} , Ar_{12} , Ar_{13} , Ar_{15} , and Ar_{16} , among the first through third substituents, are each independently a hydrogen atom, a halogen atom, a heavy hydrogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C_1 - C_{30} alkyl group, a substituted or unsubstituted C_2 - C_{30} alkenyl group, a substituted or unsubstituted C_2 - C_{30} alkynyl group, a substituted or unsubstituted C_1 - C_{30} alkoxy group, a substituted or unsubstituted C_5 - C_{30} aryl group or a substituted or unsubstituted C_3 - C_{30} heteroaryl group;

a , b , c , e , and f are each independently an integer of 0 to 10; d is an integer of 1 to 10; and

"a" groups of Ar_1 in the group of $-(Ar_1)_a-Ar_{11}$ of the first substituent are identical to or different from each other; "b" groups of Ar_2 in the group of $-(Ar_2)_b-Ar_{12}$ of the second substituent are identical to or different from each other; "c" groups of Ar_3 in the group of $-(Ar_3)_c-Ar_{13}$ of the second substituent are identical to or different from each other; "e" groups of Ar_5 in the group of $-(Ar_5)_e-Ar_{15}$ of the third substituent are identical to or different from each other; and "f" groups of Ar_6 in the group of $-(Ar_6)_f-Ar_{16}$ of the third substituent are identical to or different from each other.

Ar_1 through Ar_6 may each independently be a substituted or unsubstituted C_5 - C_{14} arylene group or a substituted or unsubstituted C_3 - C_{14} heteroarylene group.

Ar_1 through Ar_6 may each independently be a phenylene group, a C_1 - C_{10} alkylphenylene group, a di(C_1 - C_{10} alkyl)phenylene group, a (C_6 - C_{14} aryl)phenylene group, a di(C_6 - C_{14} aryl)phenylene group, a carbazolylene group, a C_1 - C_{10} alkylcarbazolylene group, a di(C_1 - C_{10} alkyl)carbazolylene group, a C_6 - C_{14} arylcarbazolylene group, a di(C_6 - C_{14} aryl)carbazolylene group, a fluorenylene group, a C_1 - C_{10} alkylfluorenylene group, a di(C_1 - C_{10} alkyl)fluorenylene group, a (C_6 - C_{14} aryl)fluorenylene group, a di(C_6 - C_{14} aryl)fluorenylene group, a naphthylene group, a C_1 - C_{10} alkyl naphthylene group, a di(C_1 - C_{10} alkyl)naphthylene group, a (C_6 - C_{14} aryl)naphthylene group, a di(C_6 - C_{14} aryl)naphthylene group,

3


an anthrylene group, a C₁-C₁₀ alkylanthrylene group, a di(C₁-C₁₀ alkyl)anthrylene group, a (C₆-C₁₄ aryl)anthrylene group, a di(C₆-C₁₄ aryl)anthrylene group, a pyridinylene group, a C₁-C₁₀ alkylpyridinylene group, a di(C₁-C₁₀ alkyl)pyridinylene group, a (C₆-C₁₄ aryl)pyridinylene group, a di(C₆-C₁₄ aryl)pyridinylene group, a quinolinylene group, a C₁-C₁₀ alkylquinolinylene group, a di(C₁-C₁₀ alkyl)quinolinylene group, a (C₆-C₁₄ aryl)quinolinylene group, a di(C₆-C₁₄ aryl)quinolinylene group, a benzoimidazolylene group, a C₁-C₁₀ alkylbenzoimidazolylene group, a di(C₁-C₁₀ alkyl)benzoimidazolylene group, a (C₆-C₁₄ aryl)benzoimidazolylene group, a di(C₆-C₁₄ aryl)benzoimidazolylene group, an imidazopyridinylene group, a C₁-C₁₀ alkylimidazopyridinylene group, a di(C₁-C₁₀ alkyl)imidazopyridinylene group, a (C₆-C₁₄ aryl)imidazopyridinylene group, a di(C₆-C₁₄ aryl)imidazopyridinylene group, an imidazopyrimidinylene group, a C₁-C₁₀ alkylimidazopyrimidinylene group, a di(C₁-C₁₀ alkyl)imidazopyrimidinylene group, a (C₆-C₁₄ aryl)imidazopyrimidinylene group, or a di(C₆-C₁₄ aryl)imidazopyrimidinylene group.

Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ may each independently be a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C₁-C₁₀ alkyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, a substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₁-C₁₀ alkoxy group, a substituted or unsubstituted C₅-C₁₄ aryl group, or a substituted or unsubstituted C₃-C₁₄ heteroaryl group.


Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ may each independently be a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, an ethenyl group, a propenyl group, a butenyl group, a pentenyl group, an acetylenyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a C₁-C₁₀alkyl phenyl group, a di(C₁-C₁₀alkyl)phenyl group, a (C₆-C₁₄aryl)phenyl group, a di(C₆-C₁₄aryl)phenyl group, a carbazolyl group, a C₁-C₁₀alkyl carbazolyl group, a di(C₁-C₁₀alkyl) carbazolyl group, a C₆-C₁₄aryl carbazolyl group, a di(C₆-C₁₄aryl) carbazolyl group, a fluorenyl group, a C₁-C₁₀alkylfluorenyl group, a di(C₁-C₁₀alkyl)fluorenyl group, a (C₆-C₁₄aryl)fluorenyl group, a di(C₆-C₁₄aryl)fluorenyl group, a naphthyl group, a C₁-C₁₀alkylnaphthyl group, a di(C₁-C₁₀alkyl)naphthyl group, a (C₆-C₁₄aryl)naphthyl group, a di(C₆-C₁₄aryl)naphthyl group, an anthryl group, a C₁-C₁₀alkylanthryl group, a di(C₁-C₁₀alkyl)anthryl group, a (C₆-C₁₄aryl)anthryl group, a di(C₆-C₁₄aryl)anthryl group, a pyridinyl group, a pyridinylene group, a C₁-C₁₀alkylpyridinyl group, a di(C₁-C₁₀alkyl)pyridinyl group, a (C₆-C₁₄aryl)pyridinyl group, a di(C₆-C₁₄aryl)pyridinyl group, a quinolinyl group, a C₁-C₁₀alkylquinolinyl group, a di(C₁-C₁₀alkyl)quinolinyl group, a (C₆-C₁₄aryl)quinolinyl group, a di(C₆-C₁₄aryl)quinolinyl group, a benzoimidazolyl group, a C₁-C₁₀alkylbenzoimidazolyl group, a di(C₁-C₁₀alkyl)benzoimidazolyl group, a (C₆-C₁₄aryl)benzoimidazolyl group, a di(C₆-C₁₄aryl)benzoimidazolyl group, an imidazopyridinyl group, a C₁-C₁₀alkylimidazopyridinyl group, a di(C₁-C₁₀alkyl)imidazopyridinyl group, a (C₆-C₁₄aryl)imidazopyridinyl group, a di(C₆-C₁₄aryl)imidazopyridinyl group, an imidazopyrimidinyl group, a C₁-C₁₀alkylimidazopyrimidinyl group, a di(C₁-C₁₀alkyl)imidazopyrimidinyl group, a (C₆-C₁₄aryl)imidazopyrimidinyl group, or a di(C₆-C₁₄aryl)imidazopyrimidinyl group.

Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ may each independently be represented by any one of Formulae 4A through 4G below:


4




Formula 4A




Formula 4B




Formula 4C




Formula 4D



Formula 4E




Formula 4F




Formula 4G

and wherein, in Formulae 4A to 4G Z₁, Z₂, Z₁₁, and Z₁₂ are each independently a hydrogen atom, a heavy hydrogen atom, a C₁-C₁₀alkyl group, a C₁-C₁₀ alkoxy group, or a C₆-C₁₄ aryl group, p and q are each independently an integer of 1 to 8, and * is a bonding site with Ar₁, Ar₂, Ar₃, Ar₅, or Ar₆.


Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ may each independently be represented by any one of Formula 5A through 5E below:



Formula 5A




Formula 5B



Formula 5C


5

-continued



Formula 5D

5



Formual 5E


10

15

and wherein, in Formulae 5A to 5E, * is a bonding site with Ar_1 , Ar_2 , Ar_3 , Ar_5 , or Ar_6 .


a, b, c, e, and f may each independently be 0, 1, 2, or 3, and d is 1, 2, or 3.

The second substituent and $-\text{N}[(\text{Ar}_5)_e-\text{Ar}_{15}][-(\text{Ar}_6)_f-\text{Ar}_{16}]$ of the third substituent may each independently be represented by any one of Formulae 6A through 6K below:



Formula 6A


35



Formula 6B

45

50



Formula 6C


55

60


65

6


-continued




Formula 6D



Formula 6E




Formula 6F




Formula 6G


-continued




Formula 6H



Formula 6I



Formula 6J



Formula 6K



and wherein, in Formulae 6A to 6K Z_1 through Z_4 and Z_{11} through Z_{14} are each independently a hydrogen atom, a heavy hydrogen atom, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, or a C_6 - C_{14} aryl group, p, q, r, and s are each independently an integer of 1 to 8, and * is a bonding site with Ar_4 or with a ring atom constituting a backbone of Formula 1.

R_1 through R_{12} may each independently be a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, the first substituent, the second substituent, or the third substituent; "a" in the first substituent is 0; "b" and "c" in the second substituent are each 0 or 1; d in the third substituent is 1 or 2, and e and f in the third substituent are each independently 0 or 1; Ar_2 through Ar_6 , among the first substituent through the third substituent, are each independently a substituted or unsubstituted C_5 - C_{14} arylene group or a substituted or unsubstituted C_3 - C_{14} heteroarylene group; and Ar_{11} , Ar_{12} , Ar_{13} , Ar_{15} , and Ar_{16} , among the first substituent through the third substituent, are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C_1 - C_{10} alkyl group, a substituted or unsubstituted C_2 - C_{10} alkenyl group, a substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_1 - C_{10} alkoxy group, a substituted or unsubstituted C_5 - C_{14} aryl group, or a substituted or unsubstituted C_3 - C_{14} heteroaryl group.

R_1 through R_{12} may each independently be a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, the first substituent, the second substituent, or the third substituent; "a" in the first substituent is 0; "b" and "c" in the second substituent are each independently 0 or 1; "d" of the third substituent is 1 or 2, and "e" and "f" in the third substituent are each independently 0 or 1; Ar_2 through Ar_6 , among the first substituent through the third substituent, are each independently a phenylene group, a C_1 - C_{10} alkylphenylene group, a di(C_1 - C_{10} alkyl)phenylene group, a (C_6 - C_{14} aryl)phenylene group, a di(C_6 - C_{14} aryl)phenylene group, a carbazolyene group, a C_1 - C_{10} alkylcarbazolyene group, a di(C_1 - C_{10} alkyl)carbazolyene group, a C_6 - C_{14} arylcarbazolyene group, a di(C_6 - C_{14} aryl)carbazolyene group, a fluorenylene group, a C_1 - C_{10} alkylfluorenylene group, a di(C_1 - C_{10} alkyl)fluorenylene group, a (C_6 - C_{14} aryl)fluorenylene group, a di(C_6 - C_{14} aryl)fluorenylene group, a naphthylylene group, a C_1 - C_{10} alkylnaphthylylene group, a di(C_1 - C_{10} alkyl)naphthylylene group, a (C_6 - C_{14} aryl)naphthylylene group, a di(C_6 - C_{14} aryl)naphthylylene group, an anthrylene group, a C_1 - C_{10} alkylanthrylene group, a di(C_1 - C_{10} alkyl)anthrylene group, a (C_6 - C_{14} aryl)anthrylene group, a di(C_6 - C_{14} aryl)anthrylene group, a pyridinylylene group, a C_1 - C_{10} alkylpyridinylylene group, a di(C_1 - C_{10} alkyl)pyridinylylene group, a (C_6 - C_{14} aryl)pyridinylylene group, a di(C_6 - C_{14} aryl)pyridinylylene group, a quinolinylylene group, a C_1 - C_{10} alkylquinolinylylene group, a di(C_1 - C_{10} alkyl)quinolinylylene group, a (C_6 - C_{14} aryl)quinolinylylene group, a di(C_6 - C_{14} aryl)quinolinylylene group, a benzoimidazolylylene group, a C_1 - C_{10} alkylbenzoimidazolylylene group, a di(C_1 - C_{10} alkyl)benzoimidazolylylene group, a (C_6 - C_{14} aryl)benzoimidazolylylene group, a di(C_6 - C_{14} aryl)benzoimidazolylylene group, an imidazopyridinylylene group, a C_1 - C_{10} alkylimidazopyridinylylene group, a di(C_1 - C_{10} alkyl)imidazopyridinylylene group, a (C_6 - C_{14} aryl)imidazopyridinylylene group, a di(C_6 - C_{14} aryl)imidazopyridinylylene group, an imidazopyrimidinylylene group, a C_1 - C_{10} alkylimidazopyrimidinylylene group, a di(C_1 - C_{10} alkyl)imidazopyrimidinylylene group, a (C_6 - C_{14} aryl)imidazopyrimidinylylene group, or a di(C_6 - C_{14} aryl)imidazopyrimidinylylene group; Ar_{11} , Ar_{12} , Ar_{13} , Ar_{15} , and Ar_{16} , among the first substituent through the third substituent, are each independently


a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, pentyl group, an ethenyl group, a propenyl group, a butenyl group, a pentenyl group, an acetly group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a C₁-C₁₀ alkylphenyl group, a di(C₁-C₁₀ alkyl)phenyl group, a (C₆-C₁₄ aryl)phenyl group, a di(C₆-C₁₄ aryl)phenyl group, a carbazolyl group, a C₁-C₁₀ alkyl carbazolyl group, a di(C₁-C₁₀ alkyl)carbazolyl group, a C₆-C₁₄ arylcarbazolyl group, a di(C₆-C₁₄ aryl)carbazolyl group, a fluorenyl group, a C₁-C₁₀ alkylfluorenyl group, a di(C₁-C₁₀ alkyl)fluorenyl group, a (C₆-C₁₄ aryl)fluorenyl group, a di(C₆-C₁₄ aryl)fluorenyl group, a naphthyl group, a C₁-C₁₀ alkyl naphthyl group, a di(C₁-C₁₀ alkyl)naphthyl group, a (C₆-C₁₄ aryl)naphthyl group, a di(C₆-C₁₄ aryl)naphthyl group, an anthryl group, a C₁-C₁₀ alkylanthryl group, a di(C₁-C₁₀ alkyl)anthryl group, a (C₆-C₁₄ aryl)anthryl group, a di(C₆-C₁₄ aryl)anthryl group, a pyridinyl group, a C₁-C₁₀ alkylpyridinyl group, a di(C₁-C₁₀ alkyl)pyridinyl group, a (C₆-C₁₄ aryl)pyridinyl group, a di(C₆-C₁₄ aryl)pyridinyl group, a quinolinyl group, a C₁-C₁₀ alkylquinolinyl group, a di(C₁-C₁₀ alkyl)quinolinyl group, a (C₆-C₁₄ aryl)quinolinyl group, a di(C₆-C₁₄ aryl)quinolinyl group, a benzoimidazolyl group, a C₁-C₁₀ alkylbenzoimidazolyl group, a di(C₁-C₁₀ alkyl)benzoimidazolyl group, a (C₆-C₁₄ aryl)benzoimidazolyl group, a di(C₆-C₁₄ aryl)benzoimidazolyl group, an imidazopyridinyl group, a C₁-C₁₀ alkylimidazopyridinyl group, a di(C₁-C₁₀ alkyl)imidazopyridinyl group, a (C₆-C₁₄ aryl)imidazopyridinyl group, a di(C₆-C₁₄ aryl)imidazopyridinyl group, an imidazopyrimidinyl group, a C₁-C₁₀ alkylimidazopyrimidinyl group, a di(C₁-C₁₀ alkyl)imidazopyrimidinyl group, a (C₆-C₁₄ aryl)imidazopyrimidinyl group, or a di(C₆-C₁₄ aryl)imidazopyrimidinyl group.

The condensed-cyclic compound represented by Formula 1 may be represented by any one of Formulae 2a through 2d below:




-continued

Formula 2c



Formula 2d




wherein, in Formulae 2a to 2d R₁ through R₁₂ are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, the first substituent, the second substituent, or the third substituent; Ar₁ through Ar₆, among the first to third substituents, are each independently a substituted or unsubstituted C₁-C₃₀ alkylene group, a substituted or unsubstituted C₂-C₃₀ alkenylene group, a substituted or unsubstituted C₅-C₃₀ arylenylene group, or a substituted or unsubstituted C₃-C₃₀ heteroarylenylene group; Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆, among the first to third substituents, are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₅-C₃₀ aryl group, or a substituted or unsubstituted C₃-C₃₀ heteroaryl group; a, b, c, e, and f are each independently an integer of 0 to 10; d is an integer of 1 to 10; and "a" groups of Ar₁ in the group of —(Ar₁)_a—Ar₁₁ of the first substituent are identical to or different from each other; "b" groups of Ar₂ in the group of —(Ar₂)_b—Ar₁₂ of the second substituent are identical to or different from each other; "c" groups of Ar₃ in the group of —(Ar₃)_c—Ar₁₃ of the second substituent are identical to or different from each other; "e" groups of Ar₅ in the group of —(Ar₅)_e—Ar₁₅ of the third substituent are identical to or different from each other; and "f" groups of Ar₆ in the group of —(Ar₆)_f—Ar₁₆ of the third substituent are identical to or different from each other.

Ar₄ may include at least one of a phenylene group, a C₁-C₁₀ alkylphenylene group, a di(C₁-C₁₀ alkyl)phenylene group, a (C₆-C₁₄ aryl)phenylene group, a di(C₆-C₁₄ aryl)phenylene group, a carbazolylenylene group, a C₁-C₁₀ alkylcarbazolylenylene group, a di(C₁-C₁₀ alkyl)carbazolylenylene group, a C₆-C₁₄ arylcarbazolylenylene group, a di(C₆-C₁₄ aryl)carbazolylenylene group, a


11

fluorenylene group, a C₁-C₁₀ alkylfluorenylene group, a di(C₁-C₁₀ alkyl)fluorenylene group, a (C₆-C₁₄ aryl)fluorenylene group, a di(C₆-C₁₄ aryl)fluorenylene group, a naphthylene group, a C₁-C₁₀ alkyl naphthylene group, a di(C₁-C₁₀ alkyl)naphthylene group, a (C₆-C₁₄ aryl)naphthylene group, a di(C₆-C₁₄ aryl)naphthylene group, an anthrylene group, a C₁-C₁₀ alkylanthrylene group, a di(C₁-C₁₀ alkyl)anthrylene group, a (C₆-C₁₄ aryl)anthrylene group, and a di(C₆-C₁₄ aryl)anthrylene group; and d may be 1, 2, or 3.


The second substituent and —N[(Ar₅)_e—Ar₁₅][—(Ar₆)_f—Ar₁₆] of the third substituent may each independently be represented by any one of Formulae 6A through 6K below:




Formula 6A



Formula 6B




Formula 6C




Formula 6D

12


-continued




Formula 6E



Formula 6F






Formula 6G



Formula 6H

13

-continued



and in Formulae 6A to 6K Z_1 through Z_4 and Z_{11} through Z_{14} are each independently a hydrogen atom, a heavy hydrogen atom, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, or a C_6 - C_{14} aryl group, p , q , r , and s are each independently an integer of 1 to 8, and $*$ is a bonding site with Ar_4 or with a ring atom constituting a backbone of Formula 1.

The condensed-cyclic compound represented by Formula 1 may be represented by any one of Formulae 3a through 3e below:

14

Formula 6I

5

10

15

Formula 6J

20

25

Formula 6K

40

45

50

55

60






Formula 3a

Formula 3b

Formula 3c

Formula 3d

Formula 3e




15

wherein, in Formulae 3a to 3e R_1 through R_{12} are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C_1 - C_{30} alkyl group, a substituted or unsubstituted C_2 - C_{30} alkenyl group, a substituted or unsubstituted C_2 - C_{30} alkynyl group, a substituted or unsubstituted C_1 - C_{30} alkoxy group, the first substituent, the second substituent, or the third substituent; Ar_1 through Ar_6 , among the first to third substituents, are each independently a substituted or unsubstituted C_1 - C_{30} alkylene group, a substituted or unsubstituted C_2 - C_{30} alkenylene group, a substituted or unsubstituted C_5 - C_{30} arylene group, or a substituted or unsubstituted C_3 - C_{30} heteroarylene group; Ar_{11} , Ar_{12} , Ar_{13} , Ar_{15} , and Ar_{16} are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C_1 - C_{30} alkyl group, a substituted or unsubstituted C_2 - C_{30} alkenyl group, a substituted or unsubstituted C_2 - C_{30} alkynyl group, a substituted or unsubstituted C_1 - C_{30} alkoxy group, a substituted or unsubstituted C_5 - C_{30} aryl group, or a substituted or unsubstituted C_3 - C_{30} heteroaryl group; a, b, c, e, and f are each independently an integer of 0 to 10; d is an integer of 1 to 10; "a" groups of Ar_1 in the group of $-(Ar_1)_a-Ar_{11}$ of the first substituent are identical to or different from each other; "b" groups of Ar_2 in the group of $-(Ar_2)_b-Ar_{12}$ of the second substituent are identical to or different from each other; "c" groups of Ar_3 in the group of $-(Ar_3)_c-Ar_{13}$ of the second substituent are identical to or different from each other; "e" groups of Ar_5 in the group of $-(Ar_5)_e-Ar_{15}$ of the third substituent are identical to or different from each other; and "f" groups of Ar_6 in the group of $-(Ar_6)_f-Ar_{16}$ of the third substituent are identical to or different from each other.

Ar_4 may include at least one of a phenylene group, a C_1 - C_{10} alkylphenylene group, a di(C_1 - C_{10} alkyl)phenylene group, a (C_6 - C_{14} aryl)phenylene group, a di(C_6 - C_{14} aryl)phenylene group, a carbazolyene group, a C_1 - C_{10} alkylcarbazolyene group, a di(C_1 - C_{10} alkyl)carbazolyene group, a C_6 - C_{14} arylcarbazolyene group, a di(C_6 - C_{14} aryl)carbazolyene group, a fluorenylene group, a C_1 - C_{10} alkylfluorenylene group, a di(C_1 - C_{10} alkyl)fluorenylene group, a (C_6 - C_{14} aryl)fluorenylene group, a di(C_6 - C_{14} aryl)fluorenylene group, a naphthylene group, a C_1 - C_{10} alkylnaphthylene group, a di(C_1 - C_{10} alkyl)naphthylene group, a (C_6 - C_{14} aryl)naphthylene group, a di(C_6 - C_{14} aryl)naphthylene group, an anthrylene group, a C_1 - C_{10} alkylanthrylene group, a di(C_1 - C_{10} alkyl)anthrylene group, a (C_6 - C_{14} aryl)anthrylene group, and a di(C_6 - C_{14} aryl)anthrylene group; and d may be 1, 2, or 3.


The second substituent and $-N[-(Ar_5)_e-Ar_{15}]$ [$-(Ar_6)_f-Ar_{16}$] of the third substituent and may each independently be represented by any one of Formulae 6A through 6K below:




Formula 6A

16


-continued




Formula 6B



Formula 6C







Formula 6D



Formula 6E

17


-continued



18


-continued

Formula 6F



Formula 6J

Formula 6G



Formula 6K

Formula 6H

and in Formulae 6A to 6K Z_1 through Z_4 and Z_{11} through Z_{14} are each independently a hydrogen group, a heavy hydrogen atom, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, or a C_6 - C_{14} aryl group, p , q , r , and s are each independently an integer of 1 to 8, and $*$ is a bonding site with Ar_4 or with a ring atom constituting a backbone of Formula 1.

At least one of the above and other features and advantages may also be realized by providing an organic light-emitting device including a first electrode, a second electrode opposite to the first electrode, and a first layer between the first electrode and the second electrode, the first layer including the condensed-cyclic compound of an embodiment.

The first layer may include at least one of a hole injection layer, a hole transport layer, an emission layer, an electron transport layer, and an electron injection layer.

The organic light-emitting device may further include, between the first electrode and the second electrode, at least one of a hole injection layer, a hole transport layer, an emission layer, a hole blocking layer, an electron transport layer, and an electron injection layer.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and other features and advantages will become more apparent to those of ordinary skill in the art by describing in detail exemplary embodiments with reference to the attached drawings, in which:


FIG. 1 illustrates a schematic sectional view of an organic light-emitting diode (OLED) according to an embodiment.

Korean Patent Application No. 10-2010-0029992, filed on Apr. 1, 2010, in the Korean Intellectual Property Office, and entitled: "Condensed-Cyclic Compound and Organic Light-Emitting Device Including the Same;" and Korean Patent Application No. 10-2011-0028212, filed on Mar. 29, 2011, in the Korean Intellectual Property Office, and entitled: "Condensed-Cyclic Compound and Organic Light-Emitting Device Including the Same;" are incorporated by reference herein in their entirety.

Example embodiments will now be described more fully hereinafter with reference to the accompanying drawings; however, they may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art.


In the drawing figures, the dimensions of layers and regions may be exaggerated for clarity of illustration. It will also be understood that when a layer or element is referred to as being "on" another layer or substrate, it can be directly on the other layer or substrate, or intervening layers may also be present. Further, it will be understood that when a layer is referred to as being "under" another layer, it can be directly under, and one or more intervening layers may also be present. In addition, it will also be understood that when a layer is referred to as being "between" two layers, it can be the only layer between the two layers, or one or more intervening layers may also be present. Like reference numerals refer to like elements throughout.

A condensed-cyclic compound according to an embodiment is represented by Formula 1 below:




Formula 1

In Formula 1, a ring A is represented by Formula 2 below or Formula 3 below:



Formula 2



Formula 3

In Formula 1, C₁ is the same carbon as C₁ in Formula 2 and C₁ in Formula 3. In addition, in Formula 1, C₂ is the same carbon as C₂ in Formula 2 and C₂ in Formula 3. In Formulae 1, 2, and 3, R₁ through R₁₂ may each independently be, e.g., a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a first substituent represented by —(Ar₁)_a—Ar₁₁, a second substituent represented by —N[(Ar₂)_b—Ar₁₂](—(Ar₃)_c—Ar₁₃), and/or a third substituent represented by —(Ar₄)_d—N[(Ar₅)_e—Ar₁₅](—(Ar₆)_f—Ar₁₆), wherein at least one of R₁ through R₁₂ is —(Ar₄)_d—N[(Ar₅)_e—Ar₁₅](—(Ar₆)_f—Ar₁₆), that is, the third substituent;

Ar₁ through Ar₆, among the first to third substituents, may each independently be, e.g., a substituted or unsubstituted C₁-C₃₀ alkylene group, a substituted or unsubstituted C₂-C₃₀ alkenylene group, a substituted or unsubstituted C₅-C₃₀ arylene group, and/or a substituted or unsubstituted C₃-C₃₀ heteroarylene group. For example, Ar₁ to Ar₆ may each independently be a substituted or unsubstituted C₅-C₁₄ arylene group and/or a substituted or unsubstituted C₃-C₁₄ heteroarylene group, but are not limited thereto. In an implementation, Ar₁ to Ar₆ may each independently be a substituted or unsubstituted C₆-C₁₄ arylene group.

For example, Ar₁ through Ar₆, among the first to third substituents, may each independently be a substituted or unsubstituted phenylene group, a substituted or unsubstituted pentalenylene group, a substituted or unsubstituted indenylene group, a substituted or unsubstituted naphthylene group, a substituted or unsubstituted azulenylene group, a substituted or unsubstituted heptalenylene group, a substituted or unsubstituted indacenylene group, a substituted or unsubstituted acenaphthylenylene group, a substituted or unsubstituted fluorenylene group, a substituted or unsubstituted phenalenylene group, a substituted or unsubstituted phenanthrenylene group, a substituted or unsubstituted anthracenylene group, a substituted or unsubstituted fluoranthenylene group, a substituted or unsubstituted triphenylenylene group, a substituted or unsubstituted pyrenylene group, a substituted or unsubstituted chrysene group, a substituted or unsubstituted naphthacene group, a substituted or unsubstituted picenylene group, a substituted or unsubstituted perylene group, a substituted or unsubstituted pentaphenylene group, a substituted or unsubstituted hexacenylene group, a substituted or unsubstituted pyrrolylene group, a substituted or unsubstituted pyrazolylene group, a substituted or unsubstituted imidazolylene group, a substituted or unsubstituted imidazolynylene group, a substituted or unsubstituted imidazopyridynylene group, a substituted or unsubstituted imidazopyrimidinylene group, a substituted or unsubstituted pyridynylene group, a substituted or unsubstituted pyrazinylene group, a substituted or unsubstituted pyrimidinylene group, a substituted or unsubstituted indolylene group, a substituted or unsubstituted purinylene group, a substituted or unsubstituted quinolynylene group, a substituted or unsubstituted phthalazinylene group, a substituted or unsubstituted indolizynylene group, a substituted or unsubstituted naphthyridynylene group, a substituted or unsubstituted quinazolinylene group, a substituted or unsubstituted cinnolynylene group, a substituted or unsubstituted indazolylene group, a substituted or unsubstituted carbazolylene group, a substituted or unsubstituted phenazinylene group, a substituted or unsubstituted phenanthridynylene group, a substituted or unsubstituted pyranylene group, a substituted or unsubstituted chromenylene group, a substituted or unsubstituted ben-

zofuranylene group, a substituted or unsubstituted thiophenylene group, a substituted or unsubstituted benzothiophenylene group, a substituted or unsubstituted isothiazolylene group, a substituted or unsubstituted benzimidazolylene group, and/or a substituted or unsubstituted isoxazolylene group, but are not limited thereto.

For example, Ar₁ to Ar₆ may each independently be a phenylene group, a C₁-C₁₀ alkylphenylene group, a di(C₁-C₁₀ alkyl)phenylene group, a (C₆-C₁₄ aryl)phenylene group, a di(C₆-C₁₄ aryl)phenylene group, a carbazolylene group, a C₁-C₁₀ alkylcarbazolylene group, a di(C₁-C₁₀ alkyl)carbazolylene group, a C₆-C₁₄ arylcarbazolylene group, a di(C₆-C₁₄ aryl)carbazolylene group, a fluorenylene group, a C₁-C₁₀ alkylfluorenylene group, a di(C₁-C₁₀ alkyl)fluorenylene group, a (C₆-C₁₄ aryl)fluorenylene group, a di(C₆-C₁₄ aryl)fluorenylene group, a naphthylene group, a C₁-C₁₀ alkyl-naphthylene group, a di(C₁-C₁₀ alkyl)naphthylene group, a (C₆-C₁₄ aryl)naphthylene group, a di(C₆-C₁₄ aryl)naphthylene group, an anthrylene group, a C₁-C₁₀ alkylanthrylene group, a di(C₁-C₁₀ alkyl)anthrylene group, a (C₆-C₁₄ aryl)anthrylene group, a di(C₆-C₁₄ aryl)anthrylene group, a pyridinylene group, a C₁-C₁₀ alkylpyridinylene group, a di(C₁-C₁₀ alkyl)pyridinylene group, a (C₆-C₁₄ aryl)pyridinylene group, a di(C₆-C₁₄ aryl)pyridinylene group, a quinolinylene group, a C₁-C₁₀ alkylquinolinylene group, a di(C₁-C₁₀ alkyl)quinolinylene group, a (C₆-C₁₄ aryl)quinolinylene group, a di(C₆-C₁₄ aryl)quinolinylene group, a benzimidazolylene group, a C₁-C₁₀ alkylbenzimidazolylene group, a di(C₁-C₁₀ alkyl)benzimidazolylene group, a (C₆-C₁₄ aryl)benzimidazolylene group, a di(C₆-C₁₄ aryl)benzimidazolylene group, an imidazopyridinylene group, a C₁-C₁₀ alkylimidazopyridinylene group, a di(C₁-C₁₀ alkyl)imidazopyridinylene group, a (C₆-C₁₄ aryl)imidazopyridinylene group, a di(C₆-C₁₄ aryl)imidazopyridinylene group, an imidazopyrimidinylene group, a C₁-C₁₀ alkylimidazopyrimidinylene group, a di(C₁-C₁₀ alkyl)imidazopyrimidinylene group, a (C₆-C₁₄ aryl)imidazopyrimidinylene group, and/or a di(C₆-C₁₄ aryl)imidazopyrimidinylene group, but are not limited thereto.

For example, Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆, among the first to third substituents, may each independently be a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₅-C₃₀ aryl group and a substituted or unsubstituted C₃-C₃₀ heteroaryl group. For example, Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ may each independently be a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C₁-C₁₀ alkyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, a substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₁-C₁₀ alkoxy group, a substituted or unsubstituted C₅-C₁₄ aryl group, and/or a substituted or unsubstituted C₃-C₁₄ heteroaryl group, but are not limited thereto. In an implementation, Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆, among the first to third substituents may each independently be a substituted or unsubstituted C₆-C₃₀ aryl group.

For example, Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ may each independently be a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, an ethenyl group, a propenyl group, a butenyl group, a pentenyl group, an acethyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a substituted or unsubstituted phenyl group, a substi-


tuted or unsubstituted pentalenyl group, a substituted or unsubstituted indenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted azulenyl group, a substituted or unsubstituted heptalenyl group, a substituted or unsubstituted indacenyl group, a substituted or unsubstituted acenaphthyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted phenalenyl group, a substituted or unsubstituted phenanthrenyl group, a substituted or unsubstituted anthracenyl group, a substituted or unsubstituted fluoranthenyl group, a substituted or unsubstituted triphenylenyl group, a substituted or unsubstituted pyrenylenyl group, a substituted or unsubstituted chrysenyl group, a substituted or unsubstituted naphthacenyl group, a substituted or unsubstituted picenyl group, a substituted or unsubstituted perylenyl group, a substituted or unsubstituted pentaphenyl group, a substituted or unsubstituted hexacenyl group, a substituted or unsubstituted pyrrolyl group, a substituted or unsubstituted pyrazolyl group, a substituted or unsubstituted imidazolyl group, a substituted or unsubstituted imidazolynyl group, a substituted or unsubstituted imidazopyridinyl group, a substituted or unsubstituted imidazopyrimidinyl group, a substituted or unsubstituted pyridinyl group, a substituted or unsubstituted pyrazinyl group, a substituted or unsubstituted pyrimidinyl group, a substituted or unsubstituted indolyl group, a substituted or unsubstituted purinyl group, a substituted or unsubstituted quinolinyl group, a substituted or unsubstituted phthalazinyl group, a substituted or unsubstituted indolizynyl group, a substituted or unsubstituted naphthyridinyl group, a substituted or unsubstituted quinazolinyl group, a substituted or unsubstituted cinnolinyl group, a substituted or unsubstituted indazolyl group, a substituted or unsubstituted carbazolyl group, a substituted or unsubstituted phenazinyl group, a substituted or unsubstituted phenanthridinyl group, a substituted or unsubstituted pyranyl group, a substituted or unsubstituted chromenyl group, a substituted or unsubstituted benzofuranyl group, a substituted or unsubstituted thiophenyl group, a substituted or unsubstituted benzothiophenyl group, a substituted or unsubstituted isothiazolyl group, a substituted or unsubstituted benzimidazolyl group, and/or a substituted or unsubstituted isoxazolyl group, but are not limited thereto.

For example, Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ may each independently be a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, an ethenyl group, a propenyl group, a butenyl group, a pentenyl group, an acethyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a C₁-C₁₀ alkyl phenyl group, a di(C₁-C₁₀ alkyl)phenyl group, a (C₆-C₁₄ aryl)phenyl group, a di(C₆-C₁₄ aryl)phenyl group, a carbazolyl group, a C₁-C₁₀ alkyl carbazolyl group, a di(C₁-C₁₀ alkyl)carbazolyl group, a C₆-C₁₄ aryl carbazolyl group, a di(C₆-C₁₄ aryl)carbazolyl group, a fluorenyl group, a C₁-C₁₀ alkyl fluorenyl group, a di(C₁-C₁₀ alkyl)fluorenyl group, a (C₆-C₁₄ aryl)fluorenyl group, a di(C₆-C₁₄ aryl)fluorenyl group, a naphthyl group, a C₁-C₁₀ alkyl naphthyl group, a di(C₁-C₁₀ alkyl)naphthyl group, a (C₆-C₁₄ aryl)naphthyl group, a di(C₆-C₁₄ aryl)naphthyl group, an anthryl group, a C₁-C₁₀ alkyl anthryl group, a di(C₁-C₁₀ alkyl)anthryl group, a (C₆-C₁₄ aryl)anthryl group, a di(C₆-C₁₄ aryl)anthryl group, a pyridinyl group, a quinolinylene group, a C₁-C₁₀ alkyl pyridinyl group, a di(C₁-C₁₀ alkyl)pyridinyl group, a (C₆-C₁₄ aryl)pyridinyl group, a di(C₆-C₁₄ aryl)pyridinyl group, a quinolinyl group, a C₁-C₁₀ alkyl quinolinyl group, a di(C₁-C₁₀ alkyl)quinolinyl group, a (C₆-C₁₄ aryl)quinolinyl group, a di(C₆-C₁₄ aryl)quinolinyl


23

group, a benzoimidazolyl group, a C₁-C₁₀ alkyl benzoimidazolyl group, a di(C₁-C₁₀ alkyl)benzoimidazolyl group, a (C₆-C₁₄ aryl)benzoimidazolyl group, a di(C₆-C₁₄ aryl)benzoimidazolyl group, an imidazopyridinyl group, a C₁-C₁₀ alkyl imidazopyridinyl group, a di(C₁-C₁₀ alkyl)imidazopyridinyl group, a (C₆-C₁₄ aryl)imidazopyridinyl group, a di(C₆-C₁₄ aryl)imidazopyridinyl group, an imidazopyrimidinyl group, a C₁-C₁₀ alkyl imidazopyrimidinyl group, a di(C₁-C₁₀ alkyl)imidazopyrimidinyl group, a (C₆-C₁₄ aryl)imidazopyrimidinyl group, and/or a di(C₆-C₁₄ aryl)imidazopyrimidinyl group. Examples of the C₁-C₁₀ alkyl group may include a methyl group, an ethyl group, a propyl group, a butyl group, and a pentyl group, and examples of the C₅-C₁₄ aryl group may include a phenyl group, a naphthyl group, and an anthryl group, but are not limited thereto.


For example, Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ may each independently be represented by any one of Formulae 4A through 4G below, but are not limited thereto:




Formula 4A




Formula 4B




Formula 4C




Formula 4D



Formula 4E



Formula 4F



Formula 4G


In Formulae 4A through 4G, Z₁, Z₂, Z₁₁ and Z₁₂ may each independently be, e.g., a hydrogen atom, a heavy hydrogen atom, a C₁-C₁₀alkyl group, a C₁-C₁₀alkoxy group, and/or a C₆-C₁₄ aryl group, p and q may each independently be an integer of 1 to 8, and * is a binding site with Ar₁, Ar₂, Ar₃, Ar₅, or Ar₆. When a in the first substituent is 0, Ar₁₁ may be represented by any one of Formulae 4A through 4G, * in Formulae 4A through 4G is a binding site with one of the ring

24


atoms constituting a backbone of Formula 1, which is easily understood by one of ordinary skill in the art.

For example, Z₁, Z₂, Z₁₁ and Z₁₂ may each independently be a hydrogen atom, a heavy hydrogen atom, a methyl group, an ethyl group, a propyl group, a butyl group, a methoxy group, an ethoxy group, a propoxy group, a phenyl group, a naphthyl group, and/or an anthryl group.


For example, Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ may each independently be represented by one of Formulae 5A through 5E below, but are not limited thereto:




Formula 5A




Formula 5B



Formula 5C



Formula 5D



Formula 5E

In Formulae 5A to 5E, * is a binding site with Ar₁, Ar₂, Ar₃, Ar₅, or Ar₆.

For example, when a in the first substituent is 0, and Ar₁₁ is represented by any one of Formulae 5A through 5E, * in Formulae 5A through 5E is a binding site with one of the ring atoms constituting a backbone of Formula 1, which is easily understood by one of ordinary skill in the art.

a, b, c, e, and f may each independently be an integer of 0 to 10. For example, a, b, c, e, and f may each independently be 0, 1, 2, or 3, but are not limited thereto.






For example, when a=0, the first substituent may be Ar₁₁, and Ar₁₁ may be connected directly to a ring atom constituting a backbone of Formula 1. When a=0, the first substituent may be, e.g., a substituted or unsubstituted C₅-C₃₀ aryl group or a substituted or unsubstituted C₃-C₃₀ hetero aryl group.

For example, when b=0, Ar₁₂ in the second substituent may be connected directly to N, like in a case when c, e, and f=0.

d may be an integer of 1 to 10. For example, d may be 1, 2, or 3, but is not limited thereto.

The second substituent and —N[(Ar₅)_e—Ar₁₅] [(Ar₆)_f—Ar₁₆] of the third substituent may each independently be represented by one of Formulae 6A through 6K below:

25



26

-continued

Formula 6A

5

10

Formula 6B

15

20

Formula 6C

25

30

35

Formula 6D

40

45





50

Formula 6E

55

60

65



Formula 6F


Formula 6G

Formula 6H


Formula 6I

27

-continued



Formula 6J



Formula 6K

In Formulae 6A through 6K, Z_1 through Z_4 and Z_{11} through Z_{14} may each independently be, e.g., a hydrogen atom, a heavy hydrogen atom, a C_1 - C_{10} alkyl group (e.g., a methyl group, an ethyl group, a propyl group, a butyl group, and a pentyl group), a C_1 - C_{10} alkoxy group (e.g., a methoxy group, an ethoxy group, a propoxy group, a butoxy group, and a pentoxy group), and/or a C_6 - C_{14} aryl group (e.g., a phenyl group, a naphthyl group, and an anthryl group), p , q , r , and s may each independently be an integer of 1 to 8, and $*$ is a binding site with Ar_4 or with ring atoms constituting a backbone of Formula 1. In an implementation, q may be an integer from 1 to 7, and r and s may be an integer from 1 to 4.

In Formula 1, “a” groups of Ar_1 in the group of $-(Ar_1)_a-$ Ar_{11} of the first substituent may be identical to or different from each other; “b” groups of Ar_2 in the group of $-(Ar_2)_b-$ Ar_{12} of the second substituent may be identical to or different from each other; “c” groups of Ar_3 in the group of $-(Ar_3)_c-$ Ar_{13} of the third substituent may be identical to or different from each other; “e” groups of Ar_5 in the group of $-(Ar_5)_e-$ Ar_{15} of the third substituent may be identical to or different from each other; and “f” groups of Ar_6 in the group of $-(Ar_6)_f-$ Ar_{16} of the third substituent may be identical to or different from each other.

Preferably, at least one of R_1 through R_{12} in the condensed-cyclic compound represented by Formula 1 is $-(Ar_4)_d-N$ $[-(Ar_5)_e-Ar_{15}][-(Ar_6)_f-Ar_{16}]$ (the third substituent), wherein d is an integer of 1 through 10. Thus, preferably, Ar_4 is present in the condensed-cyclic compound of an embodiment. That is, a backbone including a combination of Formula 1 and Formula 2, or a backbone including a combination

28


of Formula 1 and Formula 3 is preferably connected to a group represented by $-N[-(Ar_5)_e-Ar_{15}][-(Ar_6)_f-Ar_{16}]$ via Ar_4 . A lack or an insufficiency of electrons may be prevented at carbon sites constituting three benzene rings that are fused in the backbone of Formula 1 by Ar_4 , which may prevent oxidation at the carbon sites. Thus, although the condensed-cyclic compound represented by Formula 1 may be attacked by nucleophilic particles, deterioration of the condensed-cyclic compound may be substantially prevented. Thus, an organic light-emitting device (OLED) including the condensed-cyclic compound represented by Formula 1 may have improved performance, e.g., a current density, efficiencies, brightness, and lifetime.

In Formula 1, R_1 through R_{12} may each independently be, e.g., a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, the first substituent, the second substituent, and/or the third substituent; a in the first substituent may be 0 (that is, when any one of R_1 through R_{12} may be the first substituent, Ar_{11} may be connected directly to a ring atom constituting the backbone of Formula 1); b and c in the second substituent may each independently be 0 or 1; d in the third substituent may be 1 or 2, and e and f in the third substituent may each independently be 0 or 1; and Ar_2 through Ar_6 in the first substituent through the third substituent may each independently be, e.g., a substituted or unsubstituted C_5 - C_{14} arylene group and/or a substituted or unsubstituted C_3 - C_{14} heteroarylene group; and Ar_{11} , Ar_{12} , Ar_{13} , Ar_{15} , and Ar_{16} , among the first substituent through the third substituent, may each independently be, e.g., a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C_1 - C_{10} alkyl group, a substituted or unsubstituted C_2 - C_{10} alkenyl group, a substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_1 - C_{10} alkoxy group, a substituted or unsubstituted C_5 - C_{14} aryl group, and/or a substituted or unsubstituted C_3 - C_{14} heteroaryl group. In an implementation, Ar_2 to Ar_6 may each independently be a substituted or unsubstituted C_6 - C_{14} arylene group.

For example, R_1 through R_{12} may each independently be a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, the first substituent, the second substituent, and the third substituent; a in the first substituent may be 0; b and c in the second substituent may each independently be 0 or 1; d in the third substituent may be 1 or 2, e and f in the third substituent may each independently be 0 or 1; Ar_2 through Ar_6 in the first substituent through third substituent may each independently be a phenylene group, a C_1 - C_{10} alkyl phenylene group, a $di(C_1-C_{10} \text{ alkyl})$ phenylene group, a $(C_6-C_{14} \text{ aryl})$ phenylene group, a $di(C_6-C_{14} \text{ aryl})$ phenylene group, a carbazolyene group, a C_1 - C_{10} alkylcarbazolyene group, a $di(C_1-C_{10} \text{ alkyl})$ carbazolyene group, a $C_6-C_{14} \text{ arylcarbazolyene}$ group, a $di(C_6-C_{14} \text{ aryl})$ carbazolyene group, a fluorenylene group, a C_1 - C_{10} alkylfluorenylene group, a $di(C_1-C_{10} \text{ alkyl})$ fluorenylene group, a $(C_6-C_{14} \text{ aryl})$ fluorenylene group, a $di(C_6-C_{14} \text{ aryl})$ fluorenylene group, a naphthylene group, a C_1 - C_{10} alkyl naphthylene group, a $di(C_1-C_{10} \text{ alkyl})$ naphthylene group, a $(C_6-C_{14} \text{ aryl})$ naphthylene group, a $di(C_6-C_{14} \text{ aryl})$ naphthylene group, an anthrylene group, a C_1 - C_{10} alkylanthrylene group, a $di(C_1-C_{10} \text{ alkyl})$ anthrylene group, a $(C_6-C_{14} \text{ aryl})$ anthrylene group, a $di(C_6-C_{14} \text{ aryl})$ anthrylene group, a pyridinylene group, a C_1 - C_{10} alkylpyridinylene group, a $di(C_1-C_{10} \text{ alkyl})$ pyridinylene group, a $(C_6-C_{14} \text{ aryl})$ pyridinylene group, a $di(C_6-C_{14} \text{ aryl})$ pyridinylene group, a quinolinylene group, a C_1 - C_{10} alkylquinolinylene group, a $di(C_1-C_{10} \text{ alkyl})$ quinolinylene group, a $(C_6-C_{14} \text{ aryl})$ quinolinylene group, a $di(C_6-C_{14} \text{ aryl})$ quinolinylene group, a benzoimidazolyene group, a

C₁-C₁₀alkylbenzoimidazolylenes group, a di(C₁-C₁₀ alkyl)benzoimidazolylenes group, a (C₆-C₁₄aryl)benzoimidazolylenes group, a di(C₆-C₁₄aryl)benzoimidazolylenes group, an imidazopyridinylene group, a C₁-C₁₀alkylimidazopyridinylene group, a di(C₁-C₁₀alkyl)imidazopyridinylene group, a (C₆-C₁₄aryl)imidazopyridinylene group, a di(C₆-C₁₄aryl)imidazopyridinylene group, an imidazopyrimidinylene group, a C₁-C₁₀alkylimidazopyrimidinylene group, a di(C₁-C₁₀alkyl)imidazopyrimidinylene group, a (C₆-C₁₄aryl)imidazopyrimidinylene group, and/or a di(C₆-C₁₄ aryl)imidazopyrimidinylene group; Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆, among the first substituent through third, substituent may each independently be a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a methyl group, an ethyl group, a propyl group, a buthyl group, a penthyl group, an ethenyl group, a propenyl group, a butenyl group, a pentenyl group, an acetyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a C₁-C₁₀ alkylphenyl group, a di(C₁-C₁₀ alkyl)phenyl group, a (C₆-C₁₄ aryl)phenyl group, a di(C₆-C₁₄aryl)phenyl group, a carbazoyl group, a C₁-C₁₀alkyl carbazoyl group, a di(C₁-C₁₀alkyl)carbazoyl group, a C₆-C₁₄aryl carbazoyl group, a di(C₆-C₁₄aryl)carbazoyl group, a fluorenyl group, a C₁-C₁₀alkylfluorenyl group, a di(C₁-C₁₀alkyl)fluorenyl group, a (C₆-C₁₄aryl)fluorenyl group, a di(C₆-C₁₄aryl)fluorenyl group, a naphthyl group, a C₁-C₁₀alkylnaphthyl group, a di(C₁-C₁₀alkyl)naphthyl group, a (C₆-C₁₄aryl)naphthyl group, a di(C₆-C₁₄ aryl)naphthyl group, an anthryl group, a C₁-C₁₀alkylanthryl group, a di(C₁-C₁₀alkyl)anthryl group, a (C₆-C₁₄aryl)anthryl group, a di(C₆-C₁₄aryl)anthryl group, a pyridinyl group, a C₁-C₁₀alkylpyridinyl group, a di(C₁-C₁₀alkyl)pyridinyl group, a (C₆-C₁₄aryl)pyridinyl group, a di(C₆-C₁₄aryl)pyridinyl group, a quinolinyl group, a C₁-C₁₀alkylquinolinyl group, a di(C₁-C₁₀alkyl)quinolinyl group, a (C₆-C₁₄aryl)quinolinyl group, a di(C₆-C₁₄aryl)quinolinyl group, a benzoimidazoly group, a C₁-C₁₀alkylbenzoimidazoly group, a di(C₁-C₁₀alkyl)benzoimidazoly group, a (C₆-C₁₄aryl)benzoimidazoly group, a di(C₆-C₁₄aryl)benzoimidazoly group, an imidazopyridinyl group, a C₁-C₁₀alkylimidazopyridinyl group, a di(C₁-C₁₀alkyl)imidazopyridinyl group, a (C₆-C₁₄aryl)imidazopyridinyl group, a di(C₆-C₁₄aryl)imidazopyridinyl group, an imidazopyrimidinyl group, a C₁-C₁₀alkylimidazopyrimidinyl group, a di(C₁-C₁₀alkyl)imidazopyrimidinyl group, a (C₆-C₁₄aryl)imidazopyrimidinyl group, and/or a di(C₆-C₁₄ aryl)imidazopyrimidinyl group, but are not limited thereto.


In an implementation, the condensed-cyclic compound represented by Formula 1 may be represented by any one of Formulae 2a through 2d below (a ring 'A' in Formula 1 is represented by Formula 2):




Formula 2a

-continued


Formula 2b



Formula 2c



Formula 2d



In Formulae 2a through 2d, R₁ through R₁₂, Ar₁ through Ar₆, Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, Ar₁₆, a, b, c, d, and f may be defined as described above.

In Formulae 2a through 2d, Ar₄ may be, e.g., a phenylene group, a C₁-C₁₀ phenylene group, a di(C₁-C₁₀alkyl)phenylene group, a (C₆-C₁₄ aryl)phenylene group, a di(C₆-C₁₄ aryl)phenylene group, a carbazoylene group, a C₁-C₁₀alkylcarbazoylene group, a di(C₁-C₁₀alkyl)carbazoylene group, a C₆-C₁₄arylcarbazoylene group, a di(C₆-C₁₄aryl)carbazoylene group, a fluorenylene group, a C₁-C₁₀alkylfluorenylene group, a di(C₁-C₁₀alkyl)fluorenylene group, a (C₆-C₁₄aryl)fluorenylene group, a di(C₆-C₁₄aryl)fluorenylene group, a naphthylene group, a C₁-C₁₀alkylnaphthylene group, a di(C₁-C₁₀alkyl)naphthylene group, a (C₆-C₁₄aryl)naphthylene group, a di(C₆-C₁₄aryl)naphthylene group, an anthrylene group, a C₁-C₁₀alkylanthyrene group, a di(C₁-C₁₀alkyl)anthrylene group, a (C₆-C₁₄aryl)anthrylene group, a di(C₆-C₁₄aryl)anthrylene group, a pyridinyne group, a C₁-C₁₀alkylpyridinyne group, a di(C₁-C₁₀alkyl)pyridinyne group, a (C₆-C₁₄aryl)pyridinyne group, a quinolinylene group, a C₁-C₁₀alkylquinolinylene group, a di(C₁-C₁₀alkyl)quinolinylene group, a (C₆-C₁₄aryl)quinolinylene group, a di(C₆-C₁₄aryl)quinolinylene group, a benzoimidazolylene group, a C₁-C₁₀alkylbenzoimidazolylene group, a di(C₁-C₁₀alkyl)benzoimidazolylene group, a (C₆-C₁₄aryl)benzoimidazolylene group,

31

zolylene group, a di(C₆-C₁₄aryl)benzoimidazolylene group, an imidazopyridinylene group, a C₁-C₁₀alkylimidazopyridinylene group, a di(C₁-C₁₀alkyl)imidazopyridinylene group, a (C₆-C₁₄aryl)imidazopyridinylene group, a di(C₆-C₁₄aryl)imidazopyridinylene group, an imidazopyrimidinylene group, a C₁-C₁₀alkylimidazopyrimidinylene group, a di(C₁-C₁₀alkyl)imidazopyrimidinylene group, a (C₆-C₁₄aryl)imidazopyrimidinylene group, or a di(C₆-C₁₄aryl)imidazopyrimidinylene group. In Formulae 2a through 2d, d may be 1, 2, or 3. For example, in Formulae 2a through 2d, Ar₄ may be a phenylene group and d may be 1 or 2, but the present embodiment is not limited thereto.


—N[(Ar₅)_e—Ar₁₅][(Ar₆)_f—Ar₁₆] of the third substituent represented by —(Ar₄)_d—N[(Ar₅)_e—Ar₁₅][(Ar₆)_f—Ar₁₆] in Formulae 2a through 2d may be represented by any one of Formulae 6A through 6K.

In Formulae 2a through 2c, R₁ and R₈ may each be, e.g., the first substituent, and “a” in the first substituent may be 0. For example, in Formulae 2a through 2c, R₁ and R₈ may be the first substituent, “a” in the first substituent may be 0, and Ar₁₁ may be a substituted or unsubstituted C₅-C₁₄ aryl group or a substituted or unsubstituted C₃-C₁₄ heteroaryl group. In detail, in Formulae 2a through 2c, R₁ and R₈ may each independently be, e.g., a phenyl group.


In Formula 2d, R₈ may be the first substituent and “a” in the first substituent may be 0. For example, in Formula 2d, R₈ may be the first substituent, “a” in the first substituent may be 0, and Ar₁₁ may be a substituted or unsubstituted C₅-C₁₄ aryl group and/or a substituted or unsubstituted C₃-C₁₄ heteroaryl group. In detail, in Formula 2d, R₁ and R₈ may each be a phenyl group.

In an implementation, the condensed-cyclic compound represented by Formula 1 may be represented by any one of Formulae 3a through 3e below (a ring ‘A’ in Formula 1 is represented by Formula 3):

Formula 3a




Formula 3b




32

-continued


Formula 3c



Formula 3d



Formula 3e



In Formulae 3a through 3e, R₁ through R₁₂, Ar₁ through Ar₆, Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, Ar₁₆, a, b, c, d, and f may be defined as described above.

In Formulae 3a through 3e, Ar₄ may be, e.g., a phenylene group, a C₁-C₁₀ phenylene group, a di(C₁-C₁₀alkyl)phenylene group, a (C₆-C₁₄aryl)phenylene group, a di(C₆-C₁₄aryl)phenylene group, a carbazolylene group, a C₁-C₁₀alkylcarbazolylene group, a di(C₁-C₁₀alkyl)carbazolylene group, a C₆-C₁₄arylcarbazolylene group, a di(C₆-C₁₄aryl)carbazolylene group, a fluorenylene group, a C₁-C₁₀alkylfluorenylene group, a di(C₁-C₁₀alkyl)fluorenylene group, a (C₆-C₁₄aryl)fluorenylene group, a di(C₆-C₁₄aryl)fluorenylene group, a naphthylene group, a C₁-C₁₀alkylnaphthylene group, a di(C₁-C₁₀alkyl)naphthylene group, a (C₆-C₁₄aryl)naphthylene group, an anthrylene group, a C₁-C₁₀alkylanthrylene group, a di(C₁-C₁₀alkyl)anthrylene group, a (C₆-C₁₄aryl)anthrylene group, a di(C₆-C₁₄aryl)anthrylene group, a pyridinylene group, a C₁-C₁₀alkylpyridinylene group, a di(C₁-C₁₀alkyl)pyridinylene group, a (C₆-C₁₄aryl)pyridinylene group, a di(C₆-

33

C₁₄aryl)pyridinylene group, a quinolinylene group, a C₁-C₁₀alkylquinolinylene group, a di(C₁-C₁₀alkyl)quinolinylene group, a (C₆-C₁₄aryl)quinolinylene group, a di(C₆-C₁₄aryl)quinolinylene group, a benzoimidazolylene group, a C₁-C₁₀alkylbenzoimidazolylene group, a di(C₁-C₁₀alkyl)benzoimidazolylene group, a (C₆-C₁₄aryl)benzoimidazolylene group, a di(C₆-C₁₄aryl)benzoimidazolylene group, an imidazopyridinylene group, a C₁-C₁₀alkylimidazopyridinylene group, a di(C₁-C₁₀alkyl)imidazopyridinylene group, a (C₆-C₁₄aryl)imidazopyridinylene group, a di(C₆-C₁₄aryl)imidazopyridinylene group, an imidazopyrimidinylene group, a C₁-C₁₀alkylimidazopyrimidinylene group, a di(C₁-C₁₀alkyl)imidazopyrimidinylene group, a (C₆-C₁₄aryl)imidazopyrimidinylene group, and/or a di(C₆-C₁₄aryl)imidazopyrimidinylene group. In Formulae 3a through 3e, d may be 1, 2, or 3. For example, in Formulae 3a through 3e, Ar₄ may be a phenylene group and d may be 1 or 2, but the present embodiment is not limited thereto.

In Formulae 3a through 3e, —N[(Ar₅)_e—Ar₁₅][—(Ar₆)_f—Ar₁₆] of the third substituent represented by —(Ar₄)_d—N[(Ar₅)_e—Ar₁₅][—(Ar₆)_f—Ar₁₆] may be represented by any one of Formulae 6A through 6K.

In Formulae 3a through 3d, R₁ and R₈ may each be, e.g., a first substituent and “a” in the first substituent may be 0. For example, in Formulae 3a through 3d, R₁ and R₈ may each be the first substituent, “a” in the first substituent may be 0, and Ar₁₁ may be a substituted or unsubstituted C₅-C₁₄ aryl group and/or a substituted or unsubstituted C₃-C₁₄ heteroaryl group. In detail, in Formulae 3a through 3d, R₁ and R₈ may each be a phenyl group.


In Formula 3e, R₈ may be, e.g., the first substituent and “a” in the first substituent may be 0. For example, in Formula 3e, R₈ may be the first substituent, “a” in the first substituent may be 0, and Ar₁₁ may be a substituted or unsubstituted C₅-C₁₄ aryl group and/or a substituted or unsubstituted C₃-C₁₄ heteroaryl group. In detail, in Formula 3e, R₁ and R₈ may each be a phenyl group.

In an implementation, the condensed-cyclic compound represented by Formula 1 may be Compounds 1 through 27 below, but is not limited thereto:


34

-continued


Compound 2




Compound 3



Compound 4




Compound 1



35

-continued

Compound 5



5

10


15

20

36


-continued

Compound 8



25

Compound 6




30

35

40

45

Compound 7




50

55


60

65

Compound 9




Compound 10



37

-continued

Compound 11



5

10


15

20

38

-continued


Compound 14



25

Compound 15

Compound 12




30


35

40

45



Compound 13




50

55

60

65


Compound 16



39

-continued

Compound 17



5

10


15

20

40


-continued

Compound 20



Compound 18

25




Compound 21

30

35

40

45




Compound 19

50


55

60

65




Compound 22



41

-continued

Compound 23




5

10

15

20


Compound 24



25

30

Compound 25




35

40

45

Compound 26



50

55


60

65

42

-continued

Compound 27



Examples of the unsubstituted C_1 - C_{30} alkyl group used herein may include methyl, ethyl, propyl, isobutyl, sec-butyl, pentyl, iso-amyl, hexyl, and the like. In the substituted C_1 - C_{30} alkyl group, at least one hydrogen atom of the unsubstituted C_1 - C_{30} alkyl group described above may be substituted with, e.g., a heavy hydrogen atom, a halogen atom, a hydroxyl group, a nitro group, a cyano group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or salts thereof, a sulfonic acid group or salts thereof, a phosphoric acid or salts thereof, a C_1 - C_{30} alkyl group, a C_2 - C_{30} alkenyl group, a C_2 - C_{30} alkynyl group, a C_6 - C_{30} aryl group, a C_2 - C_{20} heteroaryl group, $-N(Q_1)(Q_2)$, or $-Si(Q_3)(Q_4)(Q_5)$, wherein Q_1 through Q_5 may each independently be a hydrogen atom, a heavy hydrogen atom, a C_1 - C_{30} alkyl group, a C_2 - C_{30} alkenyl group, a C_2 - C_{30} alkynyl group, a C_6 - C_{30} aryl group, and a C_2 - C_{20} heteroaryl group. The substituted or unsubstituted C_1 - C_{30} alkylene group may be, e.g., a divalent linking group having the same structure as the substituted or unsubstituted C_1 - C_{30} alkyl group described above.

The unsubstituted C_1 - C_{30} alkoxy group may be a group represented by $-OA$, wherein A is an unsubstituted C_1 - C_{30} alkyl group described above. Examples of the unsubstituted C_1 - C_{30} alkoxy group may include a methoxy group, an ethoxy group, and an isopropoxy group. At least one of the hydrogen atoms in the alkoxy group may be substituted with the substituents described above in conjunction with the substituted C_1 - C_{30} alkyl group.

The unsubstituted C_2 - C_{30} alkenyl group may be a hydrocarbon chain having a carbon-carbon double bond in a center or at a terminus of the unsubstituted C_2 - C_{30} alkyl group. Examples of the alkenyl group may include an ethenyl group, a propenyl group, a butenyl group, and the like. At least one hydrogen atom in the unsubstituted C_2 - C_{30} alkenyl group may be substituted with the substituents described in conjunction with the substituted C_1 - C_{30} alkyl group. The substituted or unsubstituted C_2 - C_{30} alkenylene group may be a divalent linking group having the same structure as the substituted or unsubstituted C_2 - C_{30} alkenyl group described above.

The unsubstituted C_2 - C_{30} alkynyl group may be a hydrocarbon chain having at least one carbon-carbon triple bond in a center or at a terminus of the C_2 - C_{30} alkyl group. Examples of the unsubstituted C_2 - C_{20} alkynyl group may include ethynyl, propynyl, and the like. At least one hydrogen atom in the alkynyl group may be substituted with the substituents described above in conjunction with the C_1 - C_{30} alkyl group.

The unsubstituted C_5 - C_{30} aryl group may be a monovalent group having a carbocyclic aromatic system having 5 to 30 carbon atoms including at least one aromatic ring. The unsubstituted C_5 - C_{30} arylene group may be a divalent group having a carbocyclic aromatic system having 5 to 30 carbon atoms including at least one aromatic ring. When the aryl group and the arylene group have at least two rings, they may be fused to each other. At least one hydrogen atom in the aryl group and the arylene group may be substituted with the substituents described above in conjunction with the C_1 - C_{30} alkyl group.

Examples of the substituted or unsubstituted C_5 - C_{30} aryl group may include a phenyl group, a C_1 - C_{10} alkylphenyl group (e.g., an ethylphenyl group), a C_1 - C_{10} alkylbiphenyl group (e.g., an ethylbiphenyl group), a halophenyl group (e.g., an o-, m- or p-fluorophenyl group and a dichlorophenyl group), a dicyanophenyl group, a trifluoromethoxyphenyl group, an o-, m- or p-tolyl group, an o-, m- or p-cumenyl group, a mesityl group, a phenoxyphenyl group, a (α,α -dimethylbenzene)phenyl group, a (N,N'-dimethyl)aminophenyl group, a (N,N'-diphenyl)aminophenyl group, a pentalenyl group, an indenyl group, a naphthyl group, a halonaphthyl group (e.g., a fluoronaphthyl group), a C_1 - C_{10} alkyl-naphthyl group (e.g., a methyl-naphthyl group), a C_1 - C_{10} alkoxy-naphthyl group (e.g., a methoxy-naphthyl group), an anthracenyl group, an azulenyl group, a heptalenyl group, an acenaphth-ylenyl group, a phenalenyl group, a fluorenyl group, an anthraquinolyl group, a methylanthryl group, a phenanthryl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, an ethyl-chrysenyl group, a picenyl group, a perylenyl group, a chloroperlylenyl group, a pentaphenyl group, a pentacenyl group, a tetraphenylenyl group, a hexaphenyl group, hexacenyl group, a rubicenyl group, a coronenyl group, a trinaphthylenyl group, a heptaphenyl group, a heptacenyl group, a pyranthrenyl group, and/or an ovalenyl group. Examples of the substituted C_5 - C_{30} aryl group may be inferred based on those of the unsubstituted C_5 - C_{30} aryl group and the substituted C_1 - C_{30} alkyl group described above. Examples of the substituted or unsubstituted C_5 - C_{30} arylene group may be inferred based on examples of the substituted or unsubstituted C_5 - C_{30} aryl group.

The unsubstituted C_3 - C_{30} heteroaryl group may be a monovalent group having at least one aromatic ring having at least one heteroatom including at least one of N, O, P, and S. The unsubstituted C_3 - C_{30} heteroarylene group may be a divalent group having at least one aromatic ring having at least one of the heteroatoms including, e.g., N, O, P, and S. In this regard, when the heteroaryl group and the heteroarylene group have at least two rings, they may be fused to each other. At least one hydrogen atom in the heteroaryl group and the heteroarylene group may be substituted with the substituents described above in conjunction with the C_1 - C_{30} alkyl group.

Examples of the unsubstituted C_3 - C_{30} heteroaryl group may include a pyrazolyl group, an imidazolyl group, an oxazolyl group, a thiazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a pyridinyl group, a pyridazinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, an indolyl group, a quinolinyl group, an isoquinolinyl group, a benzoimidazolyl group, an imidazopyridinyl group, and/or an imidazopyrimidinyl group. Examples of the unsubstituted C_3 - C_{30} heteroarylene group

may be inferred based on examples of the substituted or unsubstituted C_6 - C_{30} arylene group.

The condensed-cyclic compound of Formula 1 may be synthesized by using organic synthesis. A method of synthesizing the condensed-cyclic compound may be inferred based on Examples that will be described later.

The condensed-cyclic compound of Formula 1 may be used in an organic light-emitting device. According to another embodiment, an organic light-emitting device may include a first electrode, a second electrode disposed opposite to the first electrode, and a first layer disposed between the first electrode and the second electrode, wherein the first layer include the condensed-cyclic compound of Formula 1 described above.

The first layer may be at least one of a HTL, a HIL, a functional layer having both a hole injection function and a hole transport function, an EML, an ETL and an EIL, but is not limited thereto. For example, the first layer may be at least one of a HTL, a HIL, a functional layer having both a hole injection function and a hole transport function, and an EML, but is not limited thereto. In addition, various known layers may be used as the first layer, according to a structure of an OLED to be embodied.

FIG. 1 illustrates a schematic sectional view of an organic light-emitting device (OLED) 10 according to an embodiment. Hereinafter, a method of manufacturing an organic light-emitting device according to an embodiment and an organic light-emitting device according to an embodiment will now be described with reference to FIG. 1.

Referring to FIG. 1, the OLED 10 according to the present embodiment may include a substrate 11, a first electrode 13, an organic layer 15, and a second electrode 17, which are sequentially stacked in this order.

The substrate 11, which may be any suitable substrate that is used in conventional organic light-emitting devices, may be, e.g., a glass substrate or a transparent plastic substrate with excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

The first electrode 13 may be formed by, e.g., depositing or sputtering a material that is used to form the first electrode 13 on the substrate. When the first electrode 13 constitutes an anode, the material used to form the first electrode 13 may be a high work-function material so as to facilitate hole injection. The first electrode 13 may be a reflective electrode or a transmission electrode. Transparent and conductive materials, e.g., ITO, IZO, SnO_2 , and ZnO, may be used to form the first electrode 13. The first electrode 13 may be formed as a reflective electrode using, e.g., magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), or the like.

The organic layer 15 may be disposed on the first electrode 13. The term "organic layer" used herein indicates any layer interposed between the first electrode 13 and the second electrode 17. The organic layer 15 may not be formed of pure organic materials, and may also include, e.g., a metal complex.

The organic layer 15 may include the first layer including the condensed-cyclic compound of Formula 1. The organic layer may further include at least one of a hole injection layer (HIL), a hole transport layer (HTL), a functional layer having

45


both a hole injection function and a hole transport function, an emissive layer (EML), a hole blocking layer (HBL), an electron transport layer (ETL), and an electron injection layer (EIL). For example, the first layer is a HTL, the organic layer 15 may further include a HIL, an EML, an ETL, and an EIL, in addition to the first layer, but is not limited thereto.

The HIL may be formed on the first electrode 13 by, e.g., vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, or the like.

When the HIL is formed using vacuum deposition, vacuum deposition conditions may vary according to the compound that is used to form the HIL, and the desired structure and thermal properties of the HIL to be formed. For example, the vacuum deposition may be performed at a temperature of about 100° C. to about 500° C., a pressure of about 10⁻⁸ torr to about 10⁻³ torr, and a deposition rate of about 0.01 to about 100 Å/sec. However, the deposition conditions are not limited thereto.


When the HIL is formed using spin coating, the coating conditions may vary according to the compound that is used to form the HIL, and the structure and thermal properties of the HIL to be formed. For example, the coating rate may be in the range of about 2000 to about 5000 rpm, and a temperature at which heat treatment is performed to remove a solvent after coating may be in the range of about 80° C. to about 200° C. However, the coating conditions are not limited thereto.

The HIL may be formed of at least one of the condensed-cyclic compound represented by Formula 1 and any suitable material that is commonly used to form a HIL. Examples of the known material that can be used to form the HIL may include, but are not limited to, N,N'-diphenyl-N,N'-bis-[4-(phenyl-m-tolyl-amino)-phenyl]-biphenyl-4,4'-diamine, (DNTPD), a phthalocyanine compound such as copperphthalocyanine, 4,4',4''-tris(3-methylphenylphenylamino)triphenylamine (m-MTDATA), N,N'-di(1-naphthyl)-N,N'-diphenylbenzidine (NPB), TDATA, 2T-NATA, polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), and polyaniline/poly(4-styrenesulfonate) (PANI/PSS).




46

-continued



TDATA



2T-NATA


The thickness of the HIL may be, e.g., about 100 Å to about 10,000 Å. Maintaining the thickness of the HIL at about 100 Å to about 10,000 Å may help ensure that the HIL has excellent hole injecting ability without a substantial increase in driving voltage. In an implementation, the thickness of the HIL may be, e.g., about 100 Å to about 1,000 Å.

Then, the HTL may be formed on the HIL by using, e.g., vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, or the like. When the HTL is formed using vacuum deposition or spin coating, the conditions for deposition and coating may be similar to those for the formation of the HIL, though the conditions for the deposition and coating may vary according to the material that is used to form the HTL.

The HTL may include, or may be formed of the condensed-cyclic compound represented by Formula 1 as described above. The first layer including the condensed-cyclic compound represented by Formula 1 may be the HTL. If the first layer is not a HTL, the HTL may be formed using any suitable

47

hole transporting material. Examples of the known hole transporting material may include: a carbazole derivative such as N-phenylcarbazole or polyvinylcarbazole; an amine derivative having an aromatic condensation ring, such as N,N'-bis(3-methylphenyl)-N,N'-diphenyl-[1,1'-biphenyl]-4,4'-diamine (TPD) illustrated below; and a triphenylamine-based material, such as 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA). Among these materials, TCTA may not only transport holes but may also inhibit excitons from being diffused into the EML.




TPD

The thickness of the HTL may be about 50 Å to about 1,000 Å. Maintaining the thickness of the HTL at about 50 Å to about 1,000 Å may help ensure that the HTL has excellent hole transporting ability without a substantial increase in driving voltage. In an implementation, the thickness of the HTL may be, e.g., about 100 Å to about 800 Å.

Alternatively, the functional layer having both a hole injection function and a hole transport function may be formed instead of the HIL and the HTL. The functional layer may be formed of a known material for forming the functional layer.

At least one of the HIL, the HTL, and the functional layer may further include a charge-generating material so as to improve conductivity of a layer, in addition to the condensed-cyclic compound of Formula 1, the known material for the HIL, and the known material for the HTL.

The charge-generating material may be a p-dopant. Examples of the p-dopant unlimitedly include quinone derivatives, such as tetracyanoquinodimethane (TCNQ) and 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinodimethane (F4TCNQ); metal oxides, such as a tungsten oxide and a molybdenum oxide; and a cyano group-containing compound represented by Compound 100 below, but are not limited thereto.




Compound 100

48


When the HIL, the HTL, or the functional layer further includes the charge-generating material, the charge-generating material may be homogeneously or nonuniformly dispersed in the HIL, the HTL, or the functional layer.

Then, the EML may be formed on the HTL or the functional layer by using, e.g., vacuum deposition, spin coating, casting, LB deposition, or the like. When the EML is formed using vacuum deposition or spin coating, the deposition and coating conditions may be similar to those for the formation of the HIL, though the conditions for deposition and coating may vary according to the material that is used to form the EML.


The EML may be formed of at least one of the condensed-cyclic compound of Formula 1 and any suitable light-emitting material (including both a host and a dopant). Example of the host may include Alq₃, 4,4'-N,N'-dicarbazole-biphenyl (CBP), poly(n-vinylcarbazole) (PVK), 9,10-di(naphthalene-2-yl)anthracene (ADN), TCTA, 1,3,5-tris(N-phenylbenzimidazole-2-yl)benzene (TPBI), 3-tert-butyl-9,10-di-2-naphthylanthracene (TBADN), E3, and distyrylarylene (DSA), but are not limited thereto.



TPBI




TBADN




E3

49




PVK






ADN

The dopant may be at least one of a fluorescent dopant or a phosphorescent dopant. The phosphorescent dopant may be an organic metal complex including Ir, Pt, Os, Re, Ti, Zr, Hf, or a combination of at least two thereof, but is not limited thereto.

Examples of suitable red dopants may include, but are not limited to, PtOEP, Ir(piq)₃, and Btp₂Ir(acac).




PtOEP



F₂Irpq(F₂ppy)₂Ir(tmd)Ir(dfppz)₃

50

-continued

Ir(piq)₃Btp₂Ir(acac)


Examples of suitable green dopants may include Ir(ppy)₃ (ppy=phenylpyridine), Ir(ppy)₂(acac), and Ir(mpyp)₃, but are not limited thereto.

Ir(ppy)₃Ir(ppy)₂(acac)Ir(mpyp)₃

Examples of suitable blue dopants may include F₂Irpq, (F₂ppy)₂Ir(tmd), Ir(dfppz)₃, ter-fluorene, 4,4'-bis(4-diphenylaminostyryl)biphenyl (DPAVB), and 2,5,8,11-tetra-tert-butyl pherylene (TBPe), but are not limited thereto.


51

-continued



DPAVBi

52



TBPc

When the EML includes both a host and a dopant, an amount of the dopant may be about 0.01 to about 15 parts by weight, based on 100 parts by weight of the host, but is not limited thereto.


The thickness of the EML may be about 100 Å to about 1,000 Å. Maintaining the thickness of the EML at about 100 Å to about 1,000 Å may help ensure that the EML has excellent light emitting ability without a substantial increase in driving voltage. In an implementation, the thickness of the EML may be, e.g., about 200 Å to about 600 Å.

When a phosphorescent dopant is also used to form the EML, a HBL may be formed between the HTL and the EML by using, e.g., vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, or the like, in order to prevent diffusion of triplet excitons or holes into an ETL. When the HBL is formed using vacuum deposition or spin coating, the conditions for deposition and coating may be similar to those for the formation of the HIL, although the conditions for deposition and coating may vary according to the material that is used to form the HBL. Any suitable material that is commonly used to form a HBL may be used. Examples of materials for forming the HBL may include an oxadiazole derivative, a triazole derivative, and a phenanthroline derivative, but are not limited thereto.

The thickness of the HBL may be about 50 Å to about 1,000 Å. In an implementation, the thickness of the HBL may be, e.g., about 100 Å to about 300 Å. Maintaining the thickness of the HBL at about 50 Å to about 1,000 Å may help ensure that the HBL has an excellent hole blocking ability without a substantial increase in driving voltage.

Then, an ETL may be formed on the HBL or EML by, e.g., vacuum deposition, spin coating, casting, or the like. When the ETL is formed using vacuum deposition or spin coating, the deposition and coating conditions may be similar to those for the formation of the HIL, though the deposition and coating conditions may vary according to the material that is used to form the ETL. A material that is used to form the ETL may

be a material that can stably transport electrons injected from the electron injecting electrode (cathode) and any suitable material may be used. Examples of materials for forming the ETL may include a quinoline derivative, such as tris(8-quinolinorate)aluminum (Alq₃), TAZ, BAlq, and beryllium bis (benzoquinolin-10-olate (Bebq₂), but are not limited thereto.





TAZ


The thickness of the ETL may be, e.g., about 100 Å to about 1,000 Å. In an implementation, the thickness of the ETL may be, e.g., about 150 Å to about 500 Å. Maintaining the thickness of the ETL at about 100 Å to about 1,000 Å may help ensure that the ETL has satisfactory electron transporting ability without a substantial increase in driving voltage.

Alternatively, the ETL may include an electron transporting organic compound and a metal-containing material. Examples of the electron transporting organic compound include AND(9,10-di(naphthalene-2-yl)anthracene); and anthracene-based compounds represented by Compounds 101 or 102 below, but are not limited thereto.

53



The metal-containing material may include an Li complex. Examples of the Li complex unlimitedly include lithium quinolate (LiQ) or Compound 103 below.



Then, an EIL may be formed on the ETL. The EIL may be formed of any suitable material facilitating injection of electrons from the cathode.

Examples of materials for forming the EIL may include LiF, NaCl, CsF, Li₂O, and BaO. The deposition and coating conditions for the EIL may be similar to those for the forma-

54

tion of the HIL, though the deposition and coating conditions may vary according to the material that is used to form the EIL.

The thickness of the EIL may be about 1 Å to about 100 Å. Maintaining the thickness of the EIL at about 1 Å to about 100 Å may help ensure that the EIL has satisfactory electron injection ability without a substantial increase in driving voltage. In an implementation, the thickness of the EIL may be, e.g., about 3 Å to about 90 Å.

Finally, the second electrode 17 may be disposed on the organic layer 15. The second electrode 17 may be a cathode that is an electron injection electrode. A second electrode forming metal may be a metal having a low work function, an alloy having a low work function, an electro-conductive compound, or mixtures thereof. In this regard, the second electrode 17 may be formed of, e.g., lithium (Li), magnesium (Mg), aluminum (Al), aluminum (Al)-lithium (Li), calcium (Ca), magnesium (Mg)-indium (In), magnesium (Mg)-silver (Ag), or the like, and may be formed as a thin film type transmission electrode. In an implementation, the transmission electrode may be formed of, e.g., indium tin oxide (ITO) or indium zinc oxide (IZO) to manufacture a top-emission type light-emitting device.

When the first layer from among the OLED is the HIL, the HTL, or the functional layer, the first layer may further include the charge-generating material described above, in addition to the condensed-cyclic compound of Formula 1 above. Alternatively, when the first layer is the EML, the first layer may further include the phosphorescent dopant described above, in addition to the condensed-cyclic compound of Formula 1. As such, the first layer is not limited to the above description.

Hereinafter, one or more embodiments will be described in detail with reference to the following examples. These examples are not intended to limit the purpose and scope of the one or more embodiments.


EXAMPLE

Synthesis Example 1

Synthesis of Compound 1


Compound F was synthesized through Reaction Scheme 1a below:

Reaction Scheme 1a




55


-continued




B



C




D



E

56

-continued



F

Synthesis of Compound B

34.9 g (0.31 mole) of 1,4-cyclohexanedione, 90 g (0.62 mol) of phenylhydrazin.HCl, and 1 mL of acetic acid were put into a 1 L one-neck round flask, and 600 mL of ethanol was added thereto. The resulting mixture was heated at 50° C. for 1 hour, and was cooled to room temperature. The resulting solid was filtered, was washed several times with ethanol, and was dried in a vacuum to collect 73 g of pink Compound A with a yield of 80%. 600 mL of acetic acid and 120 mL of sulfuric acid were put into a 5 L one-neck round flask, and were cooled in an ice bath. 217.5 g (0.74 mole) of Compound A was added to the resulting mixture, and was strongly stirred at 0° C. for 10 minutes. The ice bath was removed, and the resulting mixture was stirred at room temperature for 10 minutes. The resulting mixture was heated by a heating mantle. The heating was stopped at a temperature of about 45° C., and the resulting mixture was stirred. When the resulting mixture was stable, the resulting mixture was slowly cooled to room temperature, and was stirred at room temperature. The resulting solid was filtered, was washed with acetic acid, water, and ethyl ether in this order, and was dried in a vacuum to collect 51 g of Compound B with a yield 26.7%.

¹H NMR (300 MHz, DMSO-d₆) δ 11.01 (2H), 8.19 (2H), 8.10 (2H), 7.45 (2H), 7.36 (2H), 7.12 (2H)

Synthesis of Compound C

30 g (0.117 mol) of Compound B was mixed with 1 L of 1,2-dichlorobenzene to obtain a mixture. 6.2 g (0.2 eq.) of 18-crown-6, 129.5 g (8 eq.) of K₂CO₃, 29.8 g (4 eq.) of Cu and 99.4 g (3 eq.) of bromobenzene were added to the mixture, and were heated to a temperature of 180° C. The resulting mixture was maintained to a temperature of about 170 to about 180° C. for two days to obtain a mixture. Then, the resulting mixture was cooled to room temperature, and was washed several times with toluene while being filtered by a silica gel pad. The filtered solution was concentrated. Methanol was added to the filtered solution to precipitate a solid, and then the precipitated solid compound was filtered. The resulting mixture was dried in a vacuum while being washed with ethylacetate to collect 14.4 g of Compound C with a yield of 21.7%.

¹H NMR (300 MHz, DMSO) δ 8.31 (2H), 8.21 (2H), 7.90 (6H), 7.72 (4H), 7.40 (4H), 7.24 (2H)

57

Synthesis of Compound D

4.08 g (10 mmol) of Compound C was added to 100 mL of 80% acetic acid, and then 1.357 g (5.35 mmol) of Iodine (I_2) and 0.333 g (1.46 mmol) of periodic acid (H_5IO_6) in a solid state were added to the mixture. Then the mixture was stirred at 80° C. for 2 hours in a nitrogen atmosphere. After completion of the reaction, the reaction product was extracted three times with 50 mL of dichloromethane to collect organic layers. The organic layers were dried over magnesium sulfate, and the remaining solvent was evaporated. The residue was isolated and purified using silica gel column chromatography to obtain 6.14 g of Compound D with a yield of 87%.

1H NMR (300 MHz, DMSO) δ 8.28 (1H), 8.25 (1H), 8.06 (1H), 7.90-7.86 (6H), 7.71 (4H), 7.38-7.32 (4H), 7.21 (2H)

Synthesis of Compound F

5.34 g (10 mmol) of Compound D, 0.5 mmol of [1,1'-bis(diphenylphosphino)ferrocene]dichloropalladium(II): $PdCl_2(dppf)$, 2.66 g (10.5 mmol) of bis(pinacolate)diboron, and 3.92 g (20 mmol) of potassium acetate were added to 200 mL of dimethyl sulfoxide (DMSO), and were stirred at 90° C. for 6 hours under a nitrogen atmosphere. The resulting mixture was cooled to room temperature and then was put into 300 mL of water to form white precipitates. The white precipitates were filtered while being washed several times with water to collect a solid compound, and then was dried at a reduced pressure to collect 4.65 g of Compound E with a yield of 87%. Compound E was dissolved in 150 mL of toluene, 2.46 g (8.7 mmol) of 1-bromo-4-iodobenzene, 200 mg (2 mol %) of tetrakis(triphenylphosphane)palladium(0): $Pd(PPh_3)_4$, and 2.4 g (17.4 mmol) of K_2CO_3 aqueous solution were added to the resulting mixture. The resulting mixture was maintained at 80° C. for 6 hours. After completion of the reaction, the reaction product was extracted three times with 50 mL of dichloromethane to collect organic layers. The organic layers were dried over magnesium sulfate, and the remaining solvent was evaporated. The residue was isolated and purified using silica gel column chromatography to obtain 6.2 g of Compound F with a yield of 79%.


1H NMR (300 MHz, DMSO) δ 8.25 (1H), 8.17 (1H), 8.10 (1H), 7.99 (2H), 7.95-7.87 (5H), 7.83-7.80 (6H), 7.76-7.72 (4H), 7.70-7.58 (3H)

Synthesis of Compound 1

Compound 1 was synthesized through Reaction Scheme 1b below:

58

Reaction Scheme 1b



Compound 1

3 g (5.32 mmol) of Compound F and 1.08 g (6.38 mmol) of diphenylamine were dissolved in toluene, and 97.4 mg (0.11 mmol) of tris(dibenzylideneacetone)dipalladium: $Pd_2(dba)_3$ and then 22 mg (0.11 mmol) tri(t-butyl)phosphine were added to the resulting mixture under a nitrogen atmosphere. Then, 1.62 g (15.96 mmol) of $NaOtBu$ was added to the resulting mixture, and then was stirred at 80° C. for 4 hours. The resulting mixture was cooled to room temperature and then extracted three times with dichloromethane to collect organic layers. The organic layers were dried over magnesium sulfate, and the remaining solvent was evaporated. The residue was isolated and purified using silica gel column chromatography to obtain 2.64 g of Compound 1 with a yield of 76%.



1H NMR (300 MHz, DMSO) δ 8.25 (1H), 8.14 (2H), 8.06 (1H), 7.97 (2H), 7.88-7.79 (11H), 7.73 (2H), 7.58-7.41 (6H), 7.37 (2H), 7.24 (2H), 7.08-6.96 (4H)

Synthesis Example 2

Synthesis of Compound 3

Compound 3 was synthesized through Reaction Scheme 2 below:

Reaction Scheme 2



Compound 3

3 g (5.32 mmol) of Compound F and 2.31 g (6.38 mmol) of the amine compound were added to toluene, and then 97.4 mg (0.11 mmol) of tris(dibenzylideneacetone)dipalladium(0): $\text{Pd}_2(\text{dba})_3$ and 22 mg (0.11 mmol) of tri(t-butyl)phosphine were added to the resulting mixture in a nitrogen atmosphere. Then, 1.62 g (15.96 mmol) of NaOtBu was added to the resulting mixture, and then was stirred at 80°C . for 4 hours. The resulting mixture was cooled to room temperature and then extracted three times with dichloromethane to collect organic layers. The organic layers were dried over magnesium sulfate, and the remaining solvent was evaporated. The residue was isolated and purified using silica gel column chromatography to obtain 3.11 g of Compound 3 with a yield of 69%.

^1H NMR (300 MHz, DMSO) δ 8.34 (1H), 8.27 (1H), 8.09-8.03 (4H), 7.98-7.94 (3H), 7.90-7.88 (3H), 7.82-7.78 (14H), 7.73-7.70 (5H), 7.58-7.50 (2H), 7.23-7.08 (6H), 1.78 (6H)

Synthesis Example 3


Synthesis of Compound 9

Compound 9 was synthesized through Reaction Scheme 3 below:


61

62

Reaction Scheme 3



G



Compound 9

35

Compound 9 was synthesized in the same manner in Synthesis Example 1, except that 1,3-cyclohexanedione was used instead of 1,4-cyclohexanedione during the synthesis of Compound B of Synthesis Example 1 to synthesize Compound G instead of Compound F, and Compound G was used


¹H NMR (300 MHz, DMSO) δ 8.37 (1H), 8.03 (1H), 7.96-7.89 (3H), 7.53-7.34 (11H), 7.28 (2H), 7.21-7.09 (7H), 7.05-6.91 (4H), 6.87 (4H),

Synthesis Example 4

Synthesis of Compound 11

Compound 11 was synthesized through Reaction Scheme 4 below:


Reaction Scheme 4



G

63

-continued



Compound 11


Compound 11 was synthesized in the same manner in Synthesis Example 2, except that 1,3-cyclohexanedione was used instead of 1,4-cyclohexanedione during the synthesis of Compound B of Synthesis Example 2 to synthesis Compound G instead of Compound F, and Compound G was used instead of Compound F.

^1H NMR (300 MHz, DMSO) δ 8.36 (1H), 8.28 (1H), 8.11-7.96 (6H), 7.90 (3H), 7.93-7.80 (13H), 7.78-7.66 (6H), 7.58-7.50 (3H), 7 (2H), 1.78 (6H)

Synthesis Example 5

Synthesis of Compound 26


Compound 26 was synthesized through Reaction Scheme 5 below:



E

64

-continued



H


45

50

55

60

65



Compound 26

65

Compound 26 was synthesized in the same manner in Synthesis Example 2, except that Compound H was synthesized by using 4,4'-dibromobiphenyl instead of 1-bromo-4-iodobenzene while synthesizing Compound F in Synthesis Example 1, Compound H was used instead of Compound F in Synthesis Example 2, and the amine compound of Reaction Scheme 5 was used instead of the amine compound of Reaction Scheme 2.


¹H NMR (300 MHz, DMSO) δ 8.36 (1H), 8.27 (1H), 7.96-7.82 (4H), 7.73-7.56 (9H), 7.52-7.47 (6H), 7.37-7.25 (8H), 7.19 (2H), 7.07-6.91 (4H), 6.86-6.63 (4H), 1.78 (6H).

Synthesis Example 6


Synthesis of Compound 27

Compound 27 was synthesized through Reaction Scheme 6 below:

Reaction Scheme 6




E



I

66

-continued



Compound 27

Compound 27 was synthesized in the same manner in Synthesis Example 2, except that Compound I was synthesized by using 1,4-dibronaphthalene instead of 1-bromo-4-iodobenzene while synthesizing Compound F in Synthesis Example 1, Compound I was used instead of Compound F in Synthesis Example 2, and the amine compound of Reaction Scheme 6 was used instead of the amine compound of Reaction Scheme 2.



¹H NMR (300 MHz, DMSO) δ 8.53 (1H), 8.42 (1H), 8.12-7.99 (4H), 7.82-7.74 (3H), 7.68-7.59 (5H), 7.52-7.50 (8H), 7.53-7.42 (3H), 7.37-7.23 (6H), 7.11-6.73 (5H), 6.62 (1H), 1.78 (6H)

Comparative Synthesis Example A

Synthesis of Compound A

Compound A was synthesized through Reaction Scheme 7 below:

Reaction Scheme 7



Compound A (2.85 g and 70% yield) was synthesized in the same manner in Synthesis Example 2, except that Compound D was used instead of Compound F.


¹H MNM (300 MHz, DMSO) δ 8.34 (1H), 8.05 (1H), 7.89 (1H), 7.90-7.64 (3H), 7.61-7.55 (8H), 7.73-7.55 (8H), 7.48-7.35 (6H), 7.31-7.28 (2H), 6.81-6.73 (3H), 6.71 (1H), 6.13 (1H), 1.78 (6H)

Comparative Synthesis Example B

Synthesis of Compound B


Compound B was synthesized through Reaction Scheme 8 below:

Reaction Scheme 8



69

-continued



Compound B

5 g (13.5 mmol) of 3-iodo-9-phenylcarbazole and 2.2 g (10.8 mmol) of 4-bromophenyl boronic acid were dissolved in THF, $\text{Pd}(\text{PPh}_3)_4$ (2 mol %) and then an aqueous solution of K_2CO_3 were added thereto, and the mixture was reacted for 4 hours at 80°C . After the reaction, the mixture was extracted 3 times with 150 mL of dichloromethane, and then residues obtained by drying an acquired organic layer with magnesium sulfate and evaporating a solvent was separated and purified via a silicagel tube chromatography. 4.2 g (10.6 mmol) of the compound obtained as such and 2.2 g (12.7 mmol) of diphenylamine were dissolved in toluene, and 195 mg (0.22 mmol) of tris(dibenzylideneacetone)dipalladium: $\text{Pd}_2(\text{dba})_3$ and 44 mg (0.22 mmol) of tri(t-butyl)phosphine were added thereto under a nitrogen atmosphere. Then, 3.24 g (31.92 mmol) of NaOtBu was added to the mixture, and stirred for 4 hours at 80°C . The mixture obtained as such was cooled down at room temperature, extracted 3 times with dichloromethane, and then residues obtained by drying an acquired organic layer with magnesium sulfate and evaporating a solvent was separated and purified via a silicagel tube chromatography, thereby obtaining Compound B (4.5 g, 85% yield).

^1H NMR (300 MHz, DMSO) δ 8.54 (1H), 7.95 (2H), 7.84-7.78 (2H), 7.66 (2H), 7.62-7.58 (4H), 7.46-7.31 (4H), 7.28-7.21 (5H), 7.06 (2H), 6.89-6.71 (2H), 6.67 (2H)

Example 1

A $15\ \Omega/\text{cm}^2$ (1200 Å) ITO glass substrate (available from Corning Co.) was cut to a size of 50 mm×50 mm×0.7 mm,

70

ultrasonically washed with isopropyl alcohol for 5 minutes and then with pure water for 5 minutes, and washed again with UV ozone for 30 minutes. Then, m-MTDATA was vacuum-deposited on the ITO to form a HIL having a thickness of 750 Å, and then Compound 1 above was vacuum-deposited on the HIL to form a HTL having a thickness of 150 Å. 97 wt % of DSA as a host and 3 wt % of TBPe as a dopant were deposited on the HTL to form an EML with a thickness of 300 Å. Alq3 was vacuum-deposited on the EML to form an ETL having a thickness of 200 Å. LiF was vacuum-deposited on the ETL to form an EIL having a thickness of 80 Å and Al was vacuum-deposited on the EIL to form a cathode having a thickness of 3,000 Å.

Example 2

An OLED was manufactured in the same manner as in Example 1, except that Compound 3 was used instead of Compound 1 as a material of a HTL.

Example 3

An OLED was manufactured in the same manner as in Example 1, except that Compound 9 was used instead of Compound 1 as a material of a HTL.

Example 4

An OLED was manufactured in the same manner as in Example 1, except that Compound 11 was used instead of Compound 1 as a material of a HTL.

Example 5

An OLED was manufactured in the same manner as in Example 1, except that Compound 26 was used instead of Compound 1 as a material of a HTL.

Example 6

An OLED was manufactured in the same manner as in Example 1, except that Compound 27 was used instead of Compound 1 as a material of a HTL.

Comparative Example 1

An OLED was manufactured in the same manner as in Example 1, except that α -NPD was used instead of Compound 1 as a material of a HTL.

Comparative Example 2

An OLED was manufactured in the same manner as in Example 1, except that Compound A was used instead of Compound 1 as a material of a HTL.

Comparative Example 3

An OLED was manufactured in the same manner as in Example 1, except that Compound B was used instead of Compound 1 as a material of a HTL.

Evaluation Example

Luminescent efficiency and half lifetime (at initial brightness of 1000 nit) of the OLEDs manufactured in Examples 1 through 6 and Comparative Examples 1 through 3 were evalu-

71

ated by using a PR650 Spectroscan Source Measurement Unit (available from PhotoResearch company). The results are shown in Table 1 below:

TABLE 1

	HTL Compound	Luminescent Efficiency (cd/A)	Half Lifetime (Time) @1000 nit
Example 1	Compound 1	4.39	10000
Example 2	Compound 3	4.76	8900
Example 3	Compound 9	4.63	7900
Example 4	Compound 11	4.75	9500
Example 5	Compound 26	4.25	9600
Example 6	Compound 27	4.59	8200
Comparative Example 1	α -NPD	3.86	4600
Comparative Example 2	Compound A	4.03	2000
Comparative Example 3	Compound B	3.12	5300


Referring to Table 1, the OLEDs of Examples 1 through 6 were found to have improved efficiencies and lifetime characteristics, as compared to the OLED of Comparative Examples 1 through 3.

The OLED including the condensed-cyclic compound represented by Formula 1 may have excellent performance, for example, high efficiencies and long lifetime.

Exemplary embodiments have been disclosed herein, and although specific terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. Accordingly, it will be understood by those of ordinary skill in the art that various changes in form and details may be made without departing from the spirit and scope of the present invention as set forth in the following claims.


What is claimed is:

1. A condensed-cyclic compound represented by Formula 1 below:



wherein, in Formula 1:


ring A is represented by Formula 2 below or Formula 3 below:



72

-continued

Formula 3



R_1 through R_{12} are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C_1 - C_{30} alkyl group, a substituted or unsubstituted C_2 - C_{30} alkenyl group, a substituted or unsubstituted C_2 - C_{30} alkynyl group, a substituted or unsubstituted C_1 - C_{30} alkoxy group, a first substituent represented by $-(Ar_1)_a-Ar_{11}$, a second substituent represented by $-N[-(Ar_2)_b-Ar_{12}][-(Ar_3)_c-Ar_{13}]$, or a third substituent represented by $-(Ar_4)_d-N[-(Ar_5)_e-Ar_{15}][-(Ar_6)_f-Ar_{16}]$,

at least one of R_1 through R_{12} is the third substituent;

Ar_1 through Ar_6 , among the first through third substituents, are each independently a substituted or unsubstituted C_1 - C_{30} alkylene group, a substituted or unsubstituted C_2 - C_{30} alkenylene group, a substituted or unsubstituted C_5 - C_{30} arylene group, or a substituted or unsubstituted C_3 - C_{30} heteroarylene group;

Ar_{11} , Ar_{12} , Ar_{13} , Ar_{15} , and Ar_{16} , among the first to third substituents, are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C_1 - C_{30} alkyl group, a substituted or unsubstituted C_2 - C_{30} alkenyl group, a substituted or unsubstituted C_2 - C_{30} alkynyl group, a substituted or unsubstituted C_1 - C_{30} alkoxy group, a substituted or unsubstituted C_5 - C_{30} aryl group or a substituted or unsubstituted C_3 - C_{30} heteroaryl group;

a , b , c , e , and f are each independently an integer of 0 to 10; d is an integer of 1 to 10; and

"a" groups of Ar_1 in the group of $-(Ar_1)_a-Ar_{11}$ of the first substituent are identical to or different from each other; "b" groups of Ar_2 in the group of $-(Ar_2)_b-Ar_{12}$ of the second substituent are identical to or different from each other; "c" groups of Ar_3 in the group of $-(Ar_3)_c-Ar_{13}$ of the second substituent are identical to or different from each other; "e" groups of Ar_5 in the group of $-(Ar_5)_e-Ar_{15}$ of the third substituent are identical to or different from each other; and "f" groups of Ar_6 in the group of $-(Ar_6)_f-Ar_{16}$ of the third substituent are identical to or different from each other.

2. The condensed-cyclic compound as claimed in claim 1, wherein Ar_1 through Ar_6 are each independently a substituted or unsubstituted C_5 - C_{14} arylene group or a substituted or unsubstituted C_3 - C_{14} heteroarylene group.

3. The condensed-cyclic compound as claimed in claim 1, wherein Ar_1 through Ar_6 are each independently a phenylene group, a C_1 - C_{10} alkylphenylene group, a di(C_1 - C_{10} alkyl)phenylene group, a (C_6 - C_{14} aryl)phenylene group, a di(C_6 - C_{14} aryl)phenylene group, a carbazolyene group, a C_1 - C_{10} alkylcarbazolyene group, a di(C_1 - C_{10} alkyl)carbazolyene group, a C_6 - C_{14} arylcarbazolyene group, a di(C_6 - C_{14} aryl)carbazolyene group, a fluorenylene group, a C_1 - C_{10} alky-


lfluorenylene group, a di(C₁-C₁₀ alkyl)fluorenylene group, a (C₆-C₁₄ aryl)fluorenylene group, a di(C₆-C₁₄ aryl)fluorenylene group, a naphthylene group, a C₁-C₁₀ alkyl naphthylene group, a di(C₁-C₁₀ alkyl) naphthylene group, a (C₆-C₁₄ aryl) naphthylene group, a di(C₆-C₁₄ aryl) naphthylene group, an anthrylene group, a C₁-C₁₀ alkyl anthrylene group, a di(C₁-C₁₀ alkyl) anthrylene group, a (C₆-C₁₄ aryl) anthrylene group, a di(C₆-C₁₄ aryl) anthrylene group, a pyridinylene group, a C₁-C₁₀ alkyl pyridinylene group, a di(C₁-C₁₀ alkyl) pyridinylene group, a (C₆-C₁₄ aryl) pyridinylene group, a di(C₆-C₁₄ aryl) pyridinylene group, a quinolinylene group, a C₁-C₁₀ alkyl quinolinylene group, a di(C₁-C₁₀ alkyl) quinolinylene group, a (C₆-C₁₄ aryl) quinolinylene group, a di(C₆-C₁₄ aryl) quinolinylene group, a benzoimidazolylene group, a C₁-C₁₀ alkyl benzoimidazolylene group, a di(C₁-C₁₀ alkyl) benzoimidazolylene group, a (C₆-C₁₄ aryl) benzoimidazolylene group, a di(C₆-C₁₄ aryl) benzoimidazolylene group, an imidazopyridinylene group, a C₁-C₁₀ alkyl imidazopyridinylene group, a di(C₁-C₁₀ alkyl) imidazopyridinylene group, a (C₆-C₁₄ aryl) imidazopyridinylene group, a di(C₆-C₁₄ aryl) imidazopyridinylene group, an imidazopyrimidinylene group, a C₁-C₁₀ alkyl imidazopyrimidinylene group, a di(C₁-C₁₀ alkyl) imidazopyrimidinylene group, a (C₆-C₁₄ aryl) imidazopyrimidinylene group, or a di(C₆-C₁₄ aryl) imidazopyrimidinylene group.

4. The condensed-cyclic compound as claimed in claim 1, wherein Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C₁-C₁₀ alkyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, a substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₁-C₁₀ alkoxy group, a substituted or unsubstituted C₅-C₁₄ aryl group, or a substituted or unsubstituted C₃-C₁₄ heteroaryl group.


5. The condensed-cyclic compound as claimed in claim 1, wherein Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, an ethenyl group, a propenyl group, a butenyl group, a pentenyl group, an acethly group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a C₁-C₁₀ alkyl phenyl group, a di(C₁-C₁₀ alkyl) phenyl group, a (C₆-C₁₄ aryl) phenyl group, a di(C₆-C₁₄ aryl) phenyl group, a carbazolyl group, a C₁-C₁₀ alkyl carbazolyl group, a di(C₁-C₁₀ alkyl) carbazolyl group, a C₆-C₁₄ aryl carbazolyl group, a di(C₆-C₁₄ aryl) carbazolyl group, a fluorenyl group, a C₁-C₁₀ alkyl fluorenyl group, a di(C₁-C₁₀ alkyl) fluorenyl group, a (C₆-C₁₄ aryl) fluorenyl group, a di(C₆-C₁₄ aryl) fluorenyl group, a naphthyl group, a C₁-C₁₀ alkyl naphthyl group, a di(C₁-C₁₀ alkyl) naphthyl group, a (C₆-C₁₄ aryl) naphthyl group, a di(C₆-C₁₄ aryl) naphthyl group, an anthryl group, a C₁-C₁₀ alkyl anthryl group, a di(C₁-C₁₀ alkyl) anthryl group, a (C₆-C₁₄ aryl) anthryl group, a di(C₆-C₁₄ aryl) anthryl group, a pyridinyl group, a pyridinylene group, a C₁-C₁₀ alkyl pyridinyl group, a di(C₁-C₁₀ alkyl) pyridinyl group, a (C₆-C₁₄ aryl) pyridinyl group, a di(C₆-C₁₄ aryl) pyridinyl group, a quinolinyl group, a C₁-C₁₀ alkyl quinolinyl group, a di(C₁-C₁₀ alkyl) quinolinyl group, a (C₆-C₁₄ aryl) quinolinyl group, a di(C₆-C₁₄ aryl) quinolinyl group, a benzoimidazolyl group, a C₁-C₁₀ alkyl benzoimidazolyl group, a di(C₁-C₁₀ alkyl) benzoimidazolyl group, a (C₆-C₁₄ aryl) benzoimidazolyl group, a di(C₆-C₁₄ aryl) benzoimidazolyl group, an imidazopyridinyl group, a C₁-C₁₀ alkyl imidazopyridinyl group, a di(C₁-C₁₀ alkyl) imidazopyridinyl group, a (C₆-C₁₄ aryl) imidazopyridinyl group, a di(C₆-C₁₄ aryl) imida-

zopyridinyl group, an imidazopyrimidinyl group, a C₁-C₁₀ alkyl imidazopyrimidinyl group, a di(C₁-C₁₀ alkyl) imidazopyrimidinyl group, a (C₆-C₁₄ aryl) imidazopyrimidinyl group, or a di(C₆-C₁₄ aryl) imidazopyrimidinyl group.


6. The condensed-cyclic compound as claimed in claim 1, wherein Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ are each independently represented by any one of Formulae 4A through 4G below:




Formula 4A




Formula 4B




Formula 4C




Formula 4D



Formula 4E



Formula 4F




Formula 4G

and

wherein, in Formulae 4A to 4G:

Z₁, Z₂, Z₁₁, and Z₁₂ are each independently a hydrogen atom, a heavy hydrogen atom, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, or a C₆-C₁₄ aryl group, p and q are each independently an integer of 1 to 8, and * is a bonding site with Ar₁, Ar₂, Ar₃, Ar₅, or Ar₆.


7. The condensed-cyclic compound as claimed in claim 1, wherein Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ are each independently represented by any one of Formula 5A through 5E below:



Formula 5A

75

-continued



Formula 5B

5

Formula 5C

10

Formula 5D

15

Formula 5E

20

25

30


and

wherein, in Formulae 5A to 5E, * is a bonding site with Ar₁, Ar₂, Ar₃, Ar₅, or Ar₆.

8. The condensed-cyclic compound as claimed in claim 1, wherein:

a, b, c, e, and f are each independently 0, 1, 2, or 3, and d is 1, 2, or 3.

9. The condensed-cyclic compound as claimed in claim 1, wherein the second substituent and —N[(Ar₅)_e—Ar₁₅][—(Ar₆)_f—Ar₁₆] of the third substituent are each independently represented by any one of Formulae 6A through 6K below:



Formula 6A

50

Formula 6B


55

60

65

76

-continued



Formula 6C





Formula 6D

Formula 6E

Formula 6F

77

-continued




78

-continued

Formula 6K

Formula 6G



Formula 6H

20 and

wherein, in Formulae 6A to 6K:

Z_1 through Z_4 and Z_{11} through Z_{14} are each independently a hydrogen atom, a heavy hydrogen atom, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, or a C_6 - C_{14} aryl group,

p , q , r , and s are each independently an integer of 1 to 8, and

$*$ is a bonding site with Ar_4 or with a ring atom constituting a backbone of Formula 1.

Formula 6I

10. The condensed-cyclic compound as claimed in claim 1, wherein R_1 through R_{12} are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, the first substituent, the second substituent, or the third substituent; “a” in the first substituent is 0; “b” and “c” in the second substituent are each 0 or 1; d in the third substituent is 1 or 2, and e and f in the third substituent are each independently 0 or 1; Ar_2 through Ar_6 , among the first substituent through the third substituent, are each independently a substituted or unsubstituted C_5 - C_{14} arylene group or a substituted or unsubstituted C_3 - C_{14} heteroarylene group; and Ar_{11} , Ar_{12} , Ar_{13} , Ar_{15} , and Ar_{16} , among the first substituent through the third substituent, are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C_1 - C_{10} alkyl group, a substituted or unsubstituted C_2 - C_{10} alkenyl group, a substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_1 - C_{10} alkoxy group, a substituted or unsubstituted C_5 - C_{14} aryl group, or a substituted or unsubstituted C_3 - C_{14} heteroaryl group.


Formula 6J

11. The condensed-cyclic compound as claimed in claim 1, wherein R_1 through R_{12} are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, the first substituent, the second substituent, or the third substituent; “a” in the first substituent is 0; “b” and “c” in the second substituent are each independently 0 or 1; “d” of the third substituent is 1 or 2, and “e” and “f” in the third substituent are each independently 0 or 1; Ar_2 through Ar_6 , among the first substituent through the third substituent, are each independently a phenylene group, a C_1 - C_{10} alkylphenylene group, a di(C_1 - C_{10} alkyl)phenylene group, a (C_6 - C_{14} aryl)phenylene group, a di(C_6 - C_{14} aryl)phenylene group, a carbazolyene group, a C_1 - C_{10} alkylcarbazolyene group, a di(C_1 - C_{10} alkyl)carbazolyene group, a C_6 - C_{14} arylcarbazolyene group, a di(C_6 - C_{14} aryl)carbazolyene group, a fluorenylene group, a C_1 - C_{10} alkylfluore-


nylene group, a di(C₁-C₁₀ alkyl)fluorenylene group, a (C₆-C₁₄ aryl)fluorenylene group, a di(C₆-C₁₄ aryl)fluorenylene group, a naphthylene group, a C₁-C₁₀ alkyl naphthylene group, a di(C₁-C₁₀ alkyl)naphthylene group, a (C₆-C₁₄ aryl)naphthylene group, a di(C₆-C₁₄ aryl)naphthylene group, an anthrylene group, a C₁-C₁₀ alkyl anthrylene group, a di(C₁-C₁₀ alkyl)anthrylene group, a (C₆-C₁₄ aryl)anthrylene group, a di(C₆-C₁₄ aryl)anthrylene group, a pyridinylene group, a C₁-C₁₀ alkyl pyridinylene group, a di(C₁-C₁₀ alkyl)pyridinylene group, a (C₆-C₁₄ aryl)pyridinylene group, a di(C₆-C₁₄ aryl)pyridinylene group, a quinolinyne group, a C₁-C₁₀ alkyl quinolinyne group, a di(C₁-C₁₀ alkyl)quinolinyne group, a (C₆-C₁₄ aryl)quinolinyne group, a di(C₆-C₁₄ aryl)quinolinyne group, a benzoimidazolylene group, a C₁-C₁₀ alkyl benzoimidazolylene group, a di(C₁-C₁₀ alkyl)benzoimidazolylene group, a (C₆-C₁₄ aryl)benzoimidazolylene group, a di(C₆-C₁₄ aryl)benzoimidazolylene group, an imidazopyridinylene group, a C₁-C₁₀ alkyl imidazopyridinylene group, a di(C₁-C₁₀ alkyl)imidazopyridinylene group, a (C₆-C₁₄ aryl)imidazopyridinylene group, a di(C₆-C₁₄ aryl)imidazopyridinylene group, an imidazopyrimidinylene group, a C₁-C₁₀ alkyl imidazopyrimidinylene group, a di(C₁-C₁₀ alkyl)imidazopyrimidinylene group, a (C₆-C₁₄ aryl)imidazopyrimidinylene group, or a di(C₆-C₁₄ aryl)imidazopyrimidinylene group; Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆, among the first substituent through the third substituent, are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, an ethenyl group, a propenyl group, a butenyl group, a pentenyl group, an acetly group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a C₁-C₁₀ alkyl phenyl group, a di(C₁-C₁₀ alkyl)phenyl group, a (C₆-C₁₄ aryl)phenyl group, a di(C₆-C₁₄ aryl)phenyl group, a carbazolyl group, a C₁-C₁₀ alkyl carbazolyl group, a di(C₁-C₁₀ alkyl)carbazolyl group, a C₆-C₁₄ aryl carbazolyl group, a di(C₆-C₁₄ aryl)carbazolyl group, a fluorenyl group, a C₁-C₁₀ alkyl fluorenyl group, a di(C₁-C₁₀ alkyl)fluorenyl group, a (C₆-C₁₄ aryl)fluorenyl group, a di(C₆-C₁₄ aryl)fluorenyl group, a naphthyl group, a C₁-C₁₀ alkyl naphthyl group, a di(C₁-C₁₀ alkyl)naphthyl group, a (C₆-C₁₄ aryl)naphthyl group, a di(C₆-C₁₄ aryl)naphthyl group, an anthryl group, a C₁-C₁₀ alkyl anthryl group, a di(C₁-C₁₀ alkyl)anthryl group, a (C₆-C₁₄ aryl)anthryl group, a di(C₆-C₁₄ aryl)anthryl group, a pyridinyl group, a C₁-C₁₀ alkyl pyridinyl group, a di(C₁-C₁₀ alkyl)pyridinyl group, a (C₆-C₁₄ aryl)pyridinyl group, a di(C₆-C₁₄ aryl)pyridinyl group, a quinolinyne group, a C₁-C₁₀ alkyl quinolinyne group, a di(C₁-C₁₀ alkyl)quinolinyne group, a (C₆-C₁₄ aryl)quinolinyne group, a di(C₆-C₁₄ aryl)quinolinyne group, a benzoimidazolyl group, a C₁-C₁₀ alkyl benzoimidazolyl group, a di(C₁-C₁₀ alkyl)benzoimidazolyl group, a (C₆-C₁₄ aryl)benzoimidazolyl group, a di(C₆-C₁₄ aryl)benzoimidazolyl group, an imidazopyridinyl group, a C₁-C₁₀ alkyl imidazopyridinyl group, a di(C₁-C₁₀ alkyl)imidazopyridinyl group, a (C₆-C₁₄ aryl)imidazopyridinyl group, a di(C₆-C₁₄ aryl)imidazopyridinyl group, an imidazopyrimidinyl group, a C₁-C₁₀ alkyl imidazopyrimidinyl group, a di(C₁-C₁₀ alkyl)imidazopyrimidinyl group, a (C₆-C₁₄ aryl)imidazopyrimidinyl group, or a di(C₆-C₁₄ aryl)imidazopyrimidinyl group.

12. The condensed-cyclic compound as claimed in claim 1, wherein the condensed-cyclic compound represented by Formula 1 is represented by any one of Formulae 2a through 2d below:


Formula 2a




Formula 2b



Formula 2c



Formula 2d



wherein, in Formulae 2a to 2d:

R₁ through R₁₂ are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, the first substituent, the second substituent, or the third substituent;

Ar₁ through Ar₆, among the first to third substituents, are each independently a substituted or unsubstituted C₁-C₃₀ alkylene group, a substituted or unsubstituted C₂-C₃₀ alkenylene group, a substituted or unsubstituted C₃-C₃₀ arylene group, or a substituted or unsubstituted C₃-C₃₀ heteroarylene group;

81

Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆, among the first to third substituents, are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₅-C₃₀ aryl group, or a substituted or unsubstituted C₃-C₃₀ heteroaryl group;

a, b, c, e, and f are each independently an integer of 0 to 10; d is an integer of 1 to 10; and


“a” groups of Ar₁ in the group of —(Ar₁)_a—Ar₁₁ of the first substituent are identical to or different from each other; “b” groups of Ar₂ in the group of —(Ar₂)_b—Ar₁₂ of the second substituent are identical to or different from each other; “c” groups of Ar₃ in the group of —(Ar₃)_c—Ar₁₃ of the second substituent are identical to or different from each other; “e” groups of Ar₅ in the group of —(Ar₅)_e—Ar₁₅ of the third substituent are identical to or different from each other; and “f” groups of Ar₆ in the group of —(Ar₆)_f—Ar₁₆ of the third substituent are identical to or different from each other.

13. The condensed-cyclic compound as claimed in claim 12, wherein:

Ar₄ includes at least one of a phenylene group, a C₁-C₁₀ alkylphenylene group, a di(C₁-C₁₀ alkyl)phenylene group, a (C₆-C₁₄ aryl)phenylene group, a di(C₆-C₁₄ aryl)phenylene group, a carbazolylenylene group, a C₁-C₁₀ alkylcarbazolylenylene group, a di(C₁-C₁₀ alkyl)carbazolylenylene group, a C₆-C₁₄ arylcarbazolylenylene group, a di(C₆-C₁₄ aryl)carbazolylenylene group, a fluorenylenylene group, a C₁-C₁₀ alkylfluorenylenylene group, a di(C₁-C₁₀ alkyl)fluorenylenylene group, a (C₆-C₁₄ aryl)fluorenylenylene group, a di(C₆-C₁₄ aryl)fluorenylenylene group, a naphthylenylene group, a C₁-C₁₀ alkynaphthylenylene group, a di(C₁-C₁₀ alkyl)naphthylenylene group, a (C₆-C₁₄ aryl)naphthylenylene group, a di(C₆-C₁₄ aryl)naphthylenylene group, an anthrylenylene group, a C₁-C₁₀ alkylanthrylenylene group, a di(C₁-C₁₀ alkyl)anthrylenylene group, a (C₆-C₁₄ aryl)anthrylenylene group, and a di(C₆-C₁₄ aryl)anthrylenylene group; and

d is 1, 2, or 3.


14. The condensed-cyclic compound as claimed in claim 12, wherein the second substituent and —N[—(Ar₅)_e—Ar₁₅] [—(Ar₆)_f—Ar₁₆] of the third substituent are each independently represented by any one of Formulae 6A through 6K below:




Formula 6A

82


-continued




Formula 6B




Formula 6C



Formula 6D







Formula 6E



Formula 6F

83


-continued



84

-continued

Formula 6G



Formula 6H

20

and

in Formulae 6A to 6K:

25 Z_1 through Z_4 and Z_{11} through Z_{14} are each independently a hydrogen atom, a heavy hydrogen atom, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, or a C_6 - C_{14} aryl group,


30 p , q , r , and s are each independently an integer of 1 to 8, and

* is a bonding site with Ar_4 or with a ring atom constituting a backbone of Formula 1.


Formula 6I

15. The condensed-cyclic compound as claimed in claim 1, wherein the condensed-cyclic compound represented by Formula 1 is represented by any one of Formulae 3a through 3e below:

Formula 6J



55




Formula 3a

Formula 3b

85


-continued



Formula 3c

5

10




Formula 3d

15

20

25



Formula 3e

30

35

wherein, in Formulae 3a to 3e:

R₁ through R₁₂ are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, the first substituent, the second substituent, or the third substituent;

Ar₁ through Ar₆, among the first to third substituents, are each independently a substituted or unsubstituted C₁-C₃₀ alkylene group, a substituted or unsubstituted C₂-C₃₀ alkenylene group, a substituted or unsubstituted C₅-C₃₀ arylene group, or a substituted or unsubstituted C₃-C₃₀ heteroarylene group;

Ar₁₁, Ar₁₂, Ar₁₃, Ar₁₅, and Ar₁₆ are each independently a hydrogen atom, a heavy hydrogen atom, a halogen atom, a hydroxyl group, a cyano group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₅-C₃₀ aryl group, or a substituted or unsubstituted C₃-C₃₀ heteroaryl group;

86

a, b, c, e, and f are each independently an integer of 0 to 10; d is an integer of 1 to 10;


“a” groups of Ar₁ in the group of —(Ar₁)_a—Ar₁₁ of the first substituent are identical to or different from each other; “b” groups of Ar₂ in the group of —(Ar₂)_b—Ar₁₂ of the second substituent are identical to or different from each other; “c” groups of Ar₃ in the group of —(Ar₃)_c—Ar₁₃ of the second substituent are identical to or different from each other; “e” groups of Ar₅ in the group of —(Ar₅)_e—Ar₁₅ of the third substituent are identical to or different from each other; and “f” groups of Ar₆ in the group of —(Ar₆)_f—Ar₁₆ of the third substituent are identical to or different from each other.

16. The condensed-cyclic compound as claimed in claim 15, wherein:


Ar₄ includes at least one of a phenylene group, a C₁-C₁₀ alkylphenylene group, a di(C₁-C₁₀ alkyl)phenylene group, a (C₆-C₁₄ aryl)phenylene group, a di(C₆-C₁₄ aryl)phenylene group, a carbazolyne group, a C₁-C₁₀ alkylcarbazolyne group, a di(C₁-C₁₀ alkyl)carbazolyne group, a C₆-C₁₄ arylcarbazolyne group, a di(C₆-C₁₄ aryl)carbazolyne group, a fluorenylene group, a C₁-C₁₀ alkylfluorenylene group, a di(C₁-C₁₀ alkyl)fluorenylene group, a (C₆-C₁₄ aryl)fluorenylene group, a di(C₆-C₁₄ aryl)fluorenylene group, a naphthylene group, a C₁-C₁₀ alkyl naphthylene group, a di(C₁-C₁₀ alkyl) naphthylene group, a (C₆-C₁₄ aryl) naphthylene group, an anthrylene group, a C₁-C₁₀ alkylanthrylene group, a di(C₁-C₁₀ alkyl)anthrylene group, a (C₆-C₁₄ aryl)anthrylene group, and a di(C₆-C₁₄ aryl)anthrylene group;

and d is 1, 2, or 3.

17. The condensed-cyclic compound as claimed in claim 15, wherein the second substituent and —N[(Ar₅)_e—Ar₁₅] [(Ar₆)_f—Ar₁₆] of the third substituent are each independently represented by any one of Formulae 6A through 6K below:







Formula 6A



Formula 6B

87

-continued

**88**


-continued

Formula 6C

5

10

15




Formula 6G

Formula 6D

20

25

30




Formula 6H

Formula 6E

35

40

45



Formula 6I


Formula 6F

50

55

60


65



Formula 6J

89

-continued



and

in Formulae 6A to 6K:

Z_1 through Z_4 and Z_{11} through Z_{14} are each independently a hydrogen group, a heavy hydrogen atom, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, or a C_6 - C_{14} aryl group,

p , q , r , and s are each independently an integer of 1 to 8, and

$*$ is a bonding site with Ar_4 or with a ring atom constituting a backbone of Formula 1.

18. An organic light-emitting device, comprising:

a first electrode,

a second electrode opposite to the first electrode, and

a first layer between the first electrode and the second electrode, the first layer including the condensed-cyclic compound of claim 1.

19. The organic light-emitting device as claimed in claim 18, wherein the first layer includes at least one of a hole injection layer, a hole transport layer, a functional layer hav-

Formula 6K

90

ing both hole injection function and hole transport function, an emission layer, an electron transport layer, and an electron injection layer.

20. The organic light-emitting device as claimed in claim 18, further comprising, between the first electrode and the second electrode, at least one of a hole injection layer, a hole transport layer, a functional layer having both hole injection function and hole transport function, an emission layer, a hole blocking layer, an electron transport layer, and an electron injection layer.

21. The organic light-emitting device as claimed in claim 20, wherein at least one of the hole injection layer, the hole transport layer, or the functional layer further comprises a charge-generating material.

22. The organic light-emitting device as claimed in claim 20, wherein the emission layer comprises a host and a dopant, wherein the dopant is a fluorescent dopant or a phosphorescent dopant.

23. The organic light-emitting device as claimed in claim 22, wherein the phosphorescent dopant is an organic metal complex comprising at least one of iridium, platinum, osmium, rhenium, titanium, zirconium, and hafnium.

24. The organic light-emitting device as claimed in claim 20, wherein the electron transport layer comprises an electron transporting organic material and a metal-containing material.

25. The organic light-emitting device as claimed in claim 24, wherein the metal-containing material comprises a lithium complex.

26. The organic light-emitting device as claimed in claim 18, wherein the first layer is a hole injection layer, a hole transport layer, or a functional layer having both hole injection function and hole transport function, and further comprises a charge-generating material.

27. The organic light-emitting device as claimed in claim 18, wherein the first layer is an emission layer, and further comprises a phosphorescent dopant.

* * * * *

专利名称(译)	缩合环状化合物和包括其的有机发光器件		
公开(公告)号	US8389986	公开(公告)日	2013-03-05
申请号	US13/078491	申请日	2011-04-01
[标]申请(专利权)人(译)	金喜善YEON 杨SEUNG珏 易JEOUNG IN 李在镕 KWAK YOON HYUN		
申请(专利权)人(译)	金喜善妍 杨升GAK 易JEOUNG-IN 李在镕 KWAK YOON-HYUN		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KIM HEE YEON YANG SEUNG GAK YI JEOUNG IN LEE JAE YONG KWAK YOON HYUN		
发明人	KIM, HEE-YEON YANG, SEUNG-GAK YI, JEOUNG-IN LEE, JAE-YONG KWAK, YOON-HYUN		
IPC分类号	H01L51/00		
CPC分类号	C07D487/04 C09K11/06 H05B33/14 H01L51/006 H01L51/0072 C09K2211/1007 C09K2211/1011 C09K2211/1029 H01L51/0081 H01L51/5048 H01L2251/308 H01L51/0055		
优先权	1020100029992 2010-04-01 KR 1020110028212 2011-03-29 KR		
其他公开文献	US20110240979A1		
外部链接	Espacenet USPTO		

摘要(译)

缩合环化合物和包含其的OLED，由下式1表示的稠环化合物：

