



US010062853B2

(12) **United States Patent**
Jung et al.

(10) **Patent No.:** **US 10,062,853 B2**
(45) **Date of Patent:** **Aug. 28, 2018**

(54) **CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

(71) Applicants: **SAMSUNG ELECTRONICS CO., LTD.**, Suwon-si, Gyeonggi-do (KR); **Samsung SDI Co., Ltd.**, Yongin-si, Gyeonggi-do (KR)

(72) Inventors: **Yongsik Jung**, Yongin-si (KR); **Miyoung Chae**, Suwon-si (KR); **Jhunmo Son**, Yongin-si (KR); **Dalho Huh**, Suwon-si (KR); **Eunsuk Kwon**, Suwon-si (KR); **Sangmo Kim**, Hwaseong-si (KR); **Saeyoun Lee**, Suwon-si (KR); **Soonok Jeon**, Seoul (KR); **Yeonsook Chung**, Seoul (KR); **Hosuk Kang**, Suwon-si (KR); **Jongsoo Kim**, Suwon-si (KR)

(73) Assignees: **SAMSUNG ELECTRONICS CO., LTD.**, Gyeonggi-Do (KR); **SAMSUNG SDI CO., LTD.**, Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **15/346,090**

(22) Filed: **Nov. 8, 2016**

(65) **Prior Publication Data**
US 2017/0358755 A1 Dec. 14, 2017

(30) **Foreign Application Priority Data**

Jun. 9, 2016 (KR) 10-2016-0071733

(51) **Int. Cl.**
H01L 51/50 (2006.01)
H01L 51/00 (2006.01)
C07D 209/86 (2006.01)
C09K 11/02 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 51/0072** (2013.01); **C07D 209/86** (2013.01); **C09K 11/025** (2013.01); **H01L 51/5012** (2013.01); **H01L 51/5096** (2013.01)

(58) **Field of Classification Search**
CPC C09D 209/86; C07D 209/86; H01L 51/50
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,361,637 B2	1/2013	Kinoshita
9,273,000 B2	3/2016	Hayashi et al.
2017/0365796 A1	12/2017	Kim et al.

FOREIGN PATENT DOCUMENTS

JP	2010-245063 A	10/2010	
JP	2011-044365	* 3/2011	 H01L 51/50
JP	2011-044365 A	3/2011	
JP	2011-192524 A	9/2011	
JP	2011-256143 A	12/2011	

* cited by examiner

Primary Examiner — Gregory D Clark

(74) *Attorney, Agent, or Firm* — Cantor Colburn LLP


(57) **ABSTRACT**


A condensed cyclic compound represented by Formula 1:

$Ar_1-L_1-L_2-Ar_2$ Formula 1

wherein in Formula 1, Ar_1 , Ar_2 , L_1 , and L_2 are the same as described in the specification.

20 Claims, 1 Drawing Sheet





1

CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

This application claims priority to Korean Patent Application No. 10-2016-0071733, filed on Jun. 9, 2016, in the Korean Intellectual Property Office, and all the benefits accruing therefrom under 35 U.S.C. § 119, the content of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

One or more embodiments relate to a condensed cyclic compound and an organic light-emitting device including the same.

2. Description of the Related Art

Organic light-emitting devices (OLEDs) are self-emission devices that have wide viewing angles, high contrast ratios, and short response times. In addition, OLEDs display excellent brightness, driving voltage, and response speed characteristics, and produce full-color images.

In an example, an organic light-emitting device includes an anode, a cathode, and an organic layer disposed between the anode and the cathode, wherein the organic layer includes an emission layer. A hole transport region may be disposed between the anode and the emission layer, and an electron transport region may be disposed between the emission layer and the cathode. Holes provided from the anode may move toward the emission layer through the hole transport region, and electrons provided from the cathode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, recombine in the emission layer to produce excitons. These excitons transition from an excited state to a ground state, thereby generating light.


Various types of organic light emitting devices are known. However, there still remains a need in OLEDs having low driving voltage, high efficiency, high brightness, and long lifespan.

SUMMARY

One or more embodiments include a novel condensed cyclic compound and an organic light-emitting device including the same.


Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

According to one or more embodiments, a condensed cyclic compound is represented by Formula 1:



Formula 1



Formula 2




2

-continued


Formula 3




Formula 4A




Formula 4B




Formula 4C



Formula 4D



Formula 4E



Formula 4F

In Formula 1,

Ar₁ may be a group represented by Formula 2,Ar₂ may be a group represented by Formula 3,

L₁ may be selected from a group represented by Formula 4A, a group represented by Formula 4B, and a group represented by Formula 4C, and L₂ may be selected from a group represented by Formula 4D, a group represented by Formula 4E, and a group represented by Formula 4F, wherein a case in which L₁ is a group represented by Formula 4C and L₂ is a group represented by Formula 4F is excluded,

R₁ to R₄, R₁₁ to R₁₄, R₂₁ to R₂₄, R₃₁ to R₃₄, and R₄₁ to R₄₉ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group (CN), a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group (provided that the substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group is not a substituted or unsubstituted carbazolyl group), —N(Q₄)(Q₅), and —B(Q₆)(Q₇), the number of cyano group(s) (CN) included in a group represented by *L₁-L₂-* in Formula 1 may be 1, 2, 3, or 4,

a1 to a9 may each independently an integer selected from 0 to 5,

* and *' may each be a binding site to a neighboring atom, at least one of substituents of the substituted carbazolyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

deuterium, —CD₃, —CD₂H, —CDH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group (provided that the non-aromatic condensed heteropolycyclic group is not a carbazolyl group);

a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group (provided that the non-aromatic condensed heteropolycyclic group is not a carbazolyl group), each substituted with at least one selected from deuterium, —CD₃, —CD₂H, —CDH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group (provided that the non-aromatic condensed heteropolycyclic group is not a carbazolyl group), —N(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and

—N(Q₃₄)(Q₃₅) and —B(Q₃₆)(Q₃₇),

wherein Q₄ to Q₇, Q₂₄ to Q₂₇, and Q₃₄ to Q₃₇ may each independently be selected from hydrogen, deuterium, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substi-

tuted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group (provided that the substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group is not a substituted or unsubstituted carbazolyl group).

According to one or more embodiments, an organic light-emitting device includes:

a first electrode,
a second electrode, and
an organic layer disposed between the first electrode and the second electrode,

wherein the organic layer includes an emission layer and at least one condensed cyclic compound represented by Formula 1.

BRIEF DESCRIPTION OF THE DRAWING

These and/or other aspects will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with FIG. 1 which is a schematic view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the figures, to explain aspects of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

It will be understood that when an element is referred to as being “on” another element, it can be directly in contact with the other element or intervening elements may be present therebetween. In contrast, when an element is referred to as being “directly on” another element, there are no intervening elements present.

It will be understood that, although the terms first, second, third etc. may be used herein to describe various elements, components, regions, layers, and/or sections, these elements, components, regions, layers, and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer, or section from another element, component, region, layer, or section. Thus, a first element, component, region, layer, or section discussed below could be termed a second element, component, region, layer, or section without departing from the teachings of the present embodiments.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, the singular forms “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

The term “or” means “and/or.” It will be further understood that the terms “comprises” and/or “comprising,” or “includes” and/or “including” when used in this specification, specify the presence of stated features, regions, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, regions, integers, steps, operations, elements, components, and/or groups thereof.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this general inventive concept belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

Exemplary embodiments are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein should not be construed as limited to the particular shapes of regions as illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated may be rounded. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the precise shape of a region and are not intended to limit the scope of the present claims.

“About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” can mean within one or more standard deviations, or within $\pm 30\%$, 20% , 10% , 5% of the stated value.

An aspect provides a condensed cyclic compound represented by Formula 1 below:



Formula 1


In Formula 1,

Ar_1 may be selected from a group represented by Formula 2,


Ar_2 may be a group represented by Formula 3,

L_1 may be selected from a group represented by Formula 4A, a group represented by Formula 4B, and a group represented by Formula 4C, L_2 may be selected from a group represented by Formula 4D, a group represented by Formula 4E, and a group represented by Formula 4F, wherein a case in which L_1 is a group represented by Formula 4C and L_2 is a group represented by Formula 4F is excluded:


Formula 2




Formula 3




Formula 4A




Formula 4B




Formula 4C




Formula 4D



Formula 4E



-continued



Formula 4F

In Formulae 1 to 3 and 4A to 4F, R_1 to R_4 , R_{11} to R_{14} , R_{21} to R_{24} , R_{31} to R_{34} , and R_{41} to R_{49} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group (CN), a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group (provided that the substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group is not a substituted or unsubstituted carbazolyl group), —N(Q_4)(Q_5), and —B(Q_6)(Q_7),

wherein Q_4 to Q_7 may each independently be selected from hydrogen, deuterium, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group (provided that the substituted or unsubstituted non-aromatic condensed heteropolycyclic group is not a substituted or unsubstituted carbazolyl group).

In an embodiment, R_1 to R_4 , R_{11} to R_{14} , R_{21} to R_{24} , R_{31} to R_{34} , and R_{41} to R_{49} may each independently be selected from:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group (CN), a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl

group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, imidazopyrimidinyl group, an imidazopyridinyl group, a pyridoindolyl group, a benzofuopyridinyl group, a benzothienopyridinyl group, a pyrimidoindolyl group, a benzofuopyrimidinyl group, a benzothienopyrimidinyl group, a phenoxazinyl group, a pyridobenzoaxazinyl group, and pyridobenzothiazinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, imidazopyrimidinyl group, an imidazopyridinyl group, a pyridoindolyl group, a benzofuopyridinyl group, a benzothienopyridinyl group, a pyrimidoindolyl group, a benzofuopyrimidinyl group, a benzothienopyrimidinyl group, a phenoxazinyl group, a pyridobenzoaxazinyl group, and a pyridobenzothiazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a fluorenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a phthalazinyl group, a quinoxalinyl group, a cinnolinyl group, a quinazolinyl group, —N(Q_{34})(Q_{35}), and —B(Q_{36})(Q_{37}); and

—N(Q_4)(Q_5) and —B(Q_6)(Q_7),

wherein Q_4 to Q_7 and Q_{34} to Q_{37} may each independently be selected from hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl

group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group.

In one or more embodiments, R_1 to R_4 , R_{11} to R_{14} , R_{21} to R_{24} , R_{31} to R_{34} , and R_{41} to R_{49} may each independently be selected from:

hydrogen, deuterium, and a cyano group (CN);

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, a cyano group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, R_1 to R_4 , R_{11} to R_{14} , R_{21} to R_{24} and R_{31} to R_{34} , and R_{41} to R_{49} may each independently be selected from hydrogen and a cyano group (CN), but embodiments of the present disclosure are not limited thereto.

a_1 in Formula 4A indicates the number of groups R_{41} , and may be an integer selected from 0 to 5, wherein, when a_1 is two or more, two or more groups R_{41} may be identical to or different from each other. a_2 to a_9 may be understood by using the description of a_1 and the structures of Formulae 4A to 4F.

For example, a_1 to a_9 may each independently be 0, 1, or 2, but embodiments of the present disclosure are not limited thereto.

In one or more embodiments, at least one selected from R_3 , R_{13} , R_{23} , and R_{33} in Formulae 2 and 3 may be a cyano group. In an embodiment, one, two, or three selected from R_3 , R_{13} , R_{23} , and R_{33} in Formulae 2 and 3 may be a cyano group. In one or more embodiments, one or two selected from R_3 and R_{13} in Formula 2 may be a cyano group, or one or two selected from R_{23} and R_{33} in Formula 3 may be a cyano group.

In one or more embodiments, in Formula 1,

i) when L_1 is a group represented by Formula 4A, L_2 may be selected from a group represented by Formula 4D, a group represented by Formula 4E, and a group represented by Formula 4F;

ii) when L_1 is a group represented by Formula 4B, L_2 may be selected from a group represented by Formula 4D, a group represented by Formula 4E, and a group represented by Formula 4F; and

iii) when L_1 is a group represented by Formula 4C, L_2 may be selected from a group represented by Formula 4D and a group represented by Formula 4E.

A case in which, in Formula 1, L_1 is a group represented by Formula 4C and L_2 is a group represented by Formula 4F is excluded. That is, a group represented by $*-L_1-L_2-*$ in Formula 1 may be a substituted terphenylene group (for example, a terphenylene group substituted with at least one cyano group).

The number of cyano group(s) included in the group represented by $*-L_1-L_2-*$ in Formula 1 may be 1, 2, 3, or 4, and the number of cyano group(s) included in the condensed cyclic compound represented by Formula 1 may be 1, 2, 3, or 4. In other words, the number of cyano group(s) included in the condensed cyclic compound represented by Formula 1 is 1, 2, 3, or 4, provided that the group represented by $*-L_1-L_2-*$ in Formula 1 necessarily includes a cyano group.

In an embodiment, when the number of cyano group(s) included in the condensed cyclic compound represented by Formula 1 is 1, the number of cyano group(s) included in the group represented by $*-L_1-L_2-*$ in Formula 1 may be 1;

when the number of cyano group(s) included in the condensed cyclic compound represented by Formula 1 is 2, the number of cyano group(s) included in the group represented by $*-L_1-L_2-*$ in Formula 1 may be 1 or 2; when the number of cyano group(s) included in the condensed cyclic compound represented by Formula 1 is 3, the number of cyano group(s) included in the group represented by $*-L_1-L_2-*$ in Formula 1 may be 1, 2, or 3; and when the number of cyano group(s) included in the condensed cyclic compound represented by Formula 1 is 4, the number of cyano group(s) included in the group represented by $*-L_1-L_2-*$ in Formula 1 may be 1, 2, 3, or 4.

In an embodiment, one, two, three, or four substituents of $*-L_1-L_2-*$ in Formula 1 may each independently be selected from:


a cyano group; and

a phenyl group, a biphenyl group, and a terphenyl group, each substituted with at least one cyano group.


In an embodiment, the number of carbazole rings in the condensed cyclic compound represented by Formula 1 may be 2. That is, the condensed cyclic compound represented by Formula 1 may not further include, in its molecular structure, a substituted or unsubstituted carbazolyl group, except for the group represented by Formula 2 and the group represented by Formula 3.

In an embodiment, the condensed cyclic compound may be represented by one of Formulae 1-1 to 1-28:

Formula 1-1







Formula 1-2







11

-continued

**12**

-continued



Formula 1-3

Formula 1-7

Formula 1-4

Formula 1-8

Formula 1-5


Formula 1-9

Formula 1-6

Formula 1-10

13

-continued




Formula 1-11

5

10

15

Formula 1-12




20

25

30

35


Formula 1-13



45

50


Formula 1-14



65


14

-continued




Formula 1-15

Formula 1-16




40

Formula 1-17







Formula 1-18



15

-continued



Formula 1-19





Formula 1-20

Formula 1-21

Formula 1-22

16

-continued



Formula 1-23



Formula 1-24

Formula 1-25

Formula 1-26

17





-continued



Formula 1-27

Formula 1-28

18



In Formulae 1-1 to 1-28,

Ar₁ and Ar₂ are the same as described above,

R₅₁ to R₅₈ and R₆₁ to R₆₄ are each independently the same as described in connection with R₄₁, and

the number of cyano group(s) in R₅₁ to R₅₈ and R₆₁ to R₆₄ may be 1, 2, 3, or 4.

For example, R₅₁ to R₅₈ and R₆₁ to R₆₄ in Formulae 1-1 to 1-28 may each independently be selected from:

hydrogen, deuterium, and a cyano group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, a cyano group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

One, two, three, or four selected from R₅₁ to R₅₈ and R₆₁ to R₆₄ in Formulae 1-1 to 1-28 may each independently be selected from:

a cyano group; and





a phenyl group, a biphenyl group, and a terphenyl group, each substituted with at least one cyano group.

One, two, three, or four selected from R₅₁ to R₅₈ and R₆₁ to R₆₄ in Formulae 1-1 to 1-28 may be a cyano group.





The condensed cyclic compound may be selected from Compounds 1 to 260, but embodiments of the present disclosure are not limited thereto:

19

-continued





**20**

-continued







21

-continued





**22**

-continued







23

-continued





**24**

-continued







25

-continued





**26**

-continued







27

-continued





**28**

-continued







29

-continued





**30**

-continued







31

-continued





**32**

-continued







33

-continued





**34**

-continued







35

-continued

**36**


-continued



37

-continued

77




5

10

15

78




20

25

30

35

79




40

45

50

80



55


60

65


38

-continued


81




82



83







84







39

-continued


**40**

-continued



41

-continued




93

5

10

15

94




20

25

30

35

95




40

45

50

96




55

60

65


42

-continued




97


98



99








100








43

-continued





**44**

-continued








45

-continued

**46**


-continued




47

-continued

119




120



35


40

121



122

55

**48**


-continued

123

5

10

15




124

20

25

30




35

40

125

45


50



126


60

65




49

-continued







50

-continued







51

-continued


**52**

-continued




53

-continued





**54**

-continued



55

-continued



56

-continued

151

155

5

10

15

152

20

25

156

30

35

153

40

45

50




157

154

55


60

65



57

-continued



158

5

10

15

20

25


159

30

35

40


45

50
160

65


58

-continued




161

162






163







59

-continued





**60**

-continued








61

-continued





**62**

-continued







63

-continued





**64**

-continued







65

-continued


**66**

-continued



67

-continued




196

5

10

197

15




20

25

198


30



35

199

40




45

50

200

55




60


65

68


-continued




201



202







203







204

69

-continued





**70**

-continued







71

-continued





**72**

-continued






73

-continued




**74**

-continued







75

-continued

**76**


-continued



77

-continued

235




5

10

15

236




20

25

237

30




35

40

238


45

50



239

55




60

65


78

-continued


240




241



242







243







79

-continued





**80**

-continued



81

-continued



82

-continued

252

5

10

15

253

20

25

30

254

35

40

45





255

50

55

60

65



256


257

258

259

83

-continued



In the condensed cyclic compound represented by Formula 1, L_1 may be selected from the group represented by Formula 4A, the group represented by Formula 4B, and the group represented by Formula 4C, and L_2 may be selected from the group represented by Formula 4D, the group represented by Formula 4E, and the group represented by Formula 4F, wherein a case in which L_1 is the group represented by Formula 4C and L_2 is the group represented by Formula 4F is excluded. That is, the group represented by $^*L_1-L_2-^*$ in the condensed cyclic compound represented by Formula 1 necessarily includes a terphenylene group. In this regard, Ar_1 and Ar_2 necessarily include at least one ortho- or meta-connection, when respectively connected to L_1 and L_2 , thereby providing a sufficiently high triple energy as to enable blue fluorescence. Excellent electron mobility effects of a terphenylene group may provide excellent charge transport characteristics.

The group represented by $^*L_1-L_2-^*$ in Formula 1 may include one, two, three, or four cyano group(s), and the condensed cyclic compound represented by Formula 1 may include one, two, three, or four cyano group(s). Therefore, the condensed cyclic compound may have a relatively low lowest unoccupied molecular orbital (LUMO) energy level (that is, a relatively great LUMO energy absolute value), and excellent electron mobility characteristics. Due to these features, the condensed cyclic compound may have electric characteristics that are suitable for use as a material for forming an organic light-emitting device, for example, a material for forming a host in an emission layer. Accordingly, an organic light-emitting device including the condensed cyclic compound may have high efficiency and long lifespan.

The highest occupied molecular orbital (HOMO), LUMO, triplet (T_1) energy levels, and singlet (S_1) energy levels of Compounds 1 to 31 and Compounds A to C were evaluated by using a DFT method of Gaussian program in which structural optimizing is executed at the level of B3LYP/6-31G(d,p).


TABLE 1

Compound No.	HOMO (eV)	LUMO (eV)	T_1 (eV)	S_1 (eV)
1	-5.403	-1.681	3.066	3.224
2	-5.458	-1.674	3.082	3.383
8	-5.509	-1.790	3.010	3.260
11	-5.514	-1.897	2.990	3.119
12	-5.668	-1.948	2.984	3.201
21	-5.540	-1.875	3.094	3.301
22	-5.551	-1.859	3.076	3.307


84

TABLE 1-continued


Compound No.	HOMO (eV)	LUMO (eV)	T_1 (eV)	S_1 (eV)
5				
31	-5.513	-1.799	3.065	3.206
32	-5.640	-1.794	3.067	3.327
38	-5.600	-2.034	2.998	3.126
41	-5.641	-2.053	3.081	3.220
51	-5.597	-1.904	3.063	3.175
61	-5.933	-1.982	3.098	3.443
10				
91	-5.607	-2.120	2.924	3.023
157	-5.483	-1.681	2.982	3.350
160	-5.524	-1.886	2.973	3.314
A	-5.531	-1.802	3.024	3.274
B	-5.437	-1.758	3.074	3.258
C	-5.378	-1.280	3.071	3.556



Compound A



Compound B



Compound C

Referring to Table 1, it was confirmed that the condensed cyclic compound represented by Formula 1 has excellent electric characteristics, for example, a high T_1 energy level.

A method of synthesizing the condensed cyclic compound represented by Formula 1 may be understood by referring to Synthesis Examples below.

As described above, the condensed cyclic compound represented by Formula 1 is suitable for an organic layer of an organic light-emitting device, for example, a host or emitter (for example, TADF emitter) of an emission layer in the organic layer.

Accordingly, another aspect of embodiments of the present disclosure provides an organic light-emitting device including:

- a first electrode;
 - a second electrode; and
 - an organic layer disposed between the first electrode and the second electrode,
- wherein the organic layer includes an emission layer, and wherein the organic layer includes at least one of the condensed cyclic compounds represented by Formula 1.

The organic light-emitting device may have, due to the inclusion of the organic layer including the condensed cyclic compound represented by Formula 1, low driving voltage, high efficiency, high brightness, high quantum emission efficiency, and a long lifespan.

For example, the condensed cyclic compound represented by Formula 1 may be included in the emission layer.

In an embodiment, the condensed cyclic compound represented by Formula 1 may be included in the emission layer, and the condensed cyclic compound represented by Formula 1 may be a delayed fluorescent material.

In an embodiment, the emission layer may include a host and a dopant (an amount of the host is greater than an amount of the dopant), and the host may include the condensed cyclic compound represented by Formula 1. The condensed cyclic compound acting as the host may transfer energy to the dopant based on a delayed fluorescent emission mechanism. The dopant may include at least one selected from a fluorescent dopant and a phosphorescent dopant. The dopant may be selected from any known dopants. The host may further include any host selected from known hosts.

In one or more embodiments, the emission layer may include a host and a dopant (an amount of the host is greater than an amount of the dopant), and the dopant may include the condensed cyclic compound represented by Formula 1. The condensed cyclic compound acting as the dopant may emit delayed fluorescence to the dopant based on a delayed fluorescent emission mechanism. The host may be selected from known dopants.

The emission layer may emit red, green, or blue light.

In an embodiment, the emission layer may be a blue emission layer including a phosphorescent dopant, but embodiments of the present disclosure are not limited thereto.

In an embodiment, the condensed cyclic compound represented by Formula 1 may be included in an electron transport region constituting the organic light-emitting device.

For example, the electron transport region of the organic light-emitting device may include at least one selected from a hole blocking layer and an electron transport layer, and at least one selected from an electron blocking layer and an electron transport layer may include the condensed cyclic compound represented by Formula 1.

In an embodiment, the electron transport region of the organic light-emitting device may include a hole blocking layer that includes the condensed cyclic compound represented by Formula 1. The hole blocking layer may directly contact the emission layer.

The expression that “(an organic layer) includes at least one of the condensed cyclic compounds” as used herein may include a case in which “(an organic layer) includes identical condensed cyclic compounds represented by Formula 1” and a case in which “(an organic layer) includes two or more different condensed cyclic compounds represented by Formula 1.”

For example, the organic layer may include, as the condensed cyclic compound, only Compound 1. In this regard, Compound 1 may be included in an emission layer of the organic light-emitting device. In one or more embodiments, the organic layer may include, as the condensed cyclic compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may be included in either an identical layer (for example, Compound 1 and Compound 2 all may be included in an emission layer), or different layers.

The first electrode may be an anode, which is a hole injection electrode, and the second electrode may be a cathode, which is an electron injection electrode; or the first electrode may be a cathode, which is an electron injection electrode, and the second electrode may be an anode, which is a hole injection electrode.

For example, the first electrode may be an anode, and the second electrode may be a cathode, and the organic layer may include:

i) a hole transport region that is disposed between the first electrode and the emission layer, wherein the hole transport region may include at least one selected from a hole injection layer, a hole transport layer, and an electron blocking layer, and

ii) an electron transport region that is disposed between the emission layer and the second electrode, wherein the electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

The term “organic layer” as used herein refers to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of the organic light-emitting device. The “organic layer” may include, in addition to an organic compound, an organometallic complex including metal.

FIG. 1 is a schematic view of an organic light-emitting device 10 according to an embodiment. Hereinafter, the structure of an organic light-emitting device according to an embodiment and a method of manufacturing an organic light-emitting device according to an embodiment will be described in connection with FIG. 1. The organic light-emitting device 10 includes a first electrode 11, an organic layer 15, and a second electrode 19, which are sequentially stacked.

A substrate may be additionally disposed under the first electrode 11 or above the second electrode 19. For use as the substrate, any substrate that is used in general organic light-emitting devices may be used, and the substrate may be a glass substrate or a transparent plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water-resistance.

The first electrode 11 may be formed by depositing or sputtering a material for forming the first electrode 11 on the substrate. The first electrode 11 may be an anode. The material for forming the first electrode 11 may be selected from materials with a high work function to facilitate hole injection. The first electrode 11 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. The material for forming the first electrode may be, for example, indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), and zinc oxide (ZnO). In one or more embodiments, magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), potassium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be used as the material for forming the first electrode.

The first electrode 11 may have a single-layered structure or a multi-layered structure including two or more layers.

87

For example, the first electrode **11** may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode **110** is not limited thereto.

The organic layer **15** is disposed on the first electrode **11**.

The organic layer **15** may include a hole transport region, an emission layer, and an electron transport region.

The hole transport region may be disposed between the first electrode **11** and the emission layer.

The hole transport region may include at least one selected from a hole injection layer, a hole transport layer, an electron blocking layer, and a buffer layer.

The hole transport region may include only either a hole injection layer or a hole transport layer. In one or more embodiments, the hole transport region may have a hole injection layer/hole transport layer structure or a hole injection layer/hole transport layer/electron blocking layer structure, which are sequentially stacked in this stated order from the first electrode **11**.

A hole injection layer may be formed on the first electrode **11** by using one or more suitable methods selected from vacuum deposition, spin coating, casting, or Langmuir-Blodgett (LB) deposition.


When a hole injection layer is formed by vacuum deposition, the deposition conditions may vary according to a material that is used to form the hole injection layer, and the structure and thermal characteristics of the hole injection layer. For example, the deposition conditions may include a deposition temperature of about 100 to about 500° C., a vacuum pressure of about 10⁻⁸ to about 10⁻³ torr, and a deposition rate of about 0.01 to about 100 Angstroms per second (Å/sec). However, the deposition conditions are not limited thereto.

When the hole injection layer is formed using spin coating, coating conditions may vary according to the material used to form the hole injection layer, and the structure and thermal properties of the hole injection layer. For example, a coating speed may be from about 2,000 revolutions per minute (rpm) to about 5,000 rpm, and a temperature at which a heat treatment is performed to remove a solvent after coating may be from about 80° C. to about 200° C. However, the coating conditions are not limited thereto.

Conditions for forming a hole transport layer and an electron blocking layer may be understood by referring to conditions for forming the hole injection layer.


The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB, β-NPB, TPD, Spiro-TPD, Spiro-NPB, methylated-NPB, TAPC, HMTDP, 4,4',4"-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzene sulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrene sulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrene sulfonate) (PANI/PSS), a compound represented by Formula 201 below, and a compound represented by Formula 202 below:

88





89


-continued




NPB

 β -NPB

TPD




Spiro-TPD




Spiro-NPB

90


-continued



methylated NPB




TAPC



HMTPD


Formula 201



91

-continued

Formula 202



Ar₁₀₁ and Ar₁₀₂ in Formula 201 may each independently be selected from:

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, and a pentacenylene group; and

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, and a pentacenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

In Formula 201, xa and xb may each independently be an integer selected from 0 to 5, or 0, 1, or 2. For example, xa is 1 and xb is 0, but xa and xb are not limited thereto.

R₁₀₁ to R₁₀₈, R₁₁₁ to R₁₁₀, and R₁₂₁ to R₁₂₄ in Formulae 201 and 202 may each independently be selected from:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, and a C₁-C₁₀ alkyl group (for example, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, and so on), and a C₁-C₁₀ alkoxy group (for example, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, and so on);

a C₁-C₁₀ alkyl group or a C₁-C₁₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

92

thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, and a pyrenyl group; and

a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, and a pyrenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, and a C₁-C₁₀ alkoxy group, but embodiments are not limited thereto.


R₁₀₉ in Formula 201 may be selected from:

a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group; and

a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group.

According to an embodiment, the compound represented by Formula 201 may be represented by Formula 201A, but is not limited thereto:

Formula 201A




R₁₀₁, R₁₁₁, R₁₁₂, and R₁₀₉ in Formula 201A may be understood by referring to the description provided herein.

For example, the compound represented by Formula 201, and the compound represented by Formula 202 may include compounds HT1 to HT20 illustrated below, but are not limited thereto:

93

HT1



94

-continued

HT3

5

10

15

20

25

30

35

40


45

50

55



60

65



HT2


HT4



95

-continued

HT5

**96**

-continued

HT7


5

10

15

20

25



HT8


30

35

40

HT6

45





HT9

50

55

60


65



97


-continued

HT10


**98**

-continued


HT12





HT13



HT14




HT15




99

-continued




HT16



HT17



HT18



HT19




HT20

A thickness of the hole transport region may be in a range of about 100 Angstroms (Å) to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes a hole injection layer and a hole transport layer, the thickness of the hole injection layer may be in a range of about 100 Å to about 10,000 Å, and for example, about 100 Å to about 1,000 Å, and the thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, and for example, about 100 Å to about 1,500 Å. While not wishing to be bound by theory, it is understood that when the thicknesses of the hole transport region, the hole injection layer and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.


The charge-generation material may be, for example, a p-dopant. The p-dopant may be one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments are not limited thereto. Non-limiting examples of the p-dopant are a quinone derivative, such as tetracyanoquinonodimethane (TCNQ) or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonodimethane (F4-TCNQ); a metal oxide, such as a tungsten oxide or a molybdenum oxide; and a cyano group-containing compound, such as Compound HT-D1 or HP-1, but are not limited thereto.

Compound HT-D1




101

-continued



F4-TCNQ




HP-1

The hole transport region may include a buffer layer.

Also, the buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, and thus, efficiency of a formed organic light-emitting device may be improved.

Then, an emission layer (EML) may be formed on the hole transport region by vacuum deposition, spin coating, casting, LB deposition, or the like. When the emission layer is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied to form the hole injection layer although the deposition or coating conditions may vary depending on the material that is used to form the emission layer.

The electron transport region may further include an electron blocking layer. The electron blocking layer may include, for example, mCP, but a material therefor is not limited thereto.



mCP

When the organic light-emitting device is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and a blue emission layer. In one or more embodiments, due to a stack structure including a red emission layer, a green emission layer, and/or a blue emission layer, the emission layer may emit white light.

The emission layer may include the condensed cyclic compound represented by Formula 1. For example, the emission layer may include the compound represented by Formula 1 alone. In one or more embodiments, the emission layer may include a host and a dopant, and the host may

102

include the condensed cyclic compound represented by Formula 1. In one or more embodiments, the emission layer may include a host and a dopant, and the dopant may include the condensed cyclic compound represented by Formula 1.


In one or more embodiments, the dopant in the emission layer may be a phosphorescent dopant, and the phosphorescent dopant may include an organometallic compound represented by Formula 81 below:

10

15

20

Formula 81



In Formula 81,

M may be selected from iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm);

Y₁ to Y₄ may each independently be selected from carbon (C) and nitrogen (N);

Y₁ and Y₂ may be linked via a single bond or a double bond, and Y₃ and Y₄ are linked via a single bond or a double bond;

CY₁ and CY₂ may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-fluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a benzimidazole group, a benzofuran group, a benzothiothiophene group, an isobenzothiothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, and a dibenzothiothiophene group, and CY₁ and CY₂ are optionally linked through a single bond or an organic linking group;

R₈₁ and R₈₂ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, —SF₅, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted mon-

103

ovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{Si}(\text{Q}_3)(\text{Q}_4)(\text{Q}_5)$, and $-\text{B}(\text{Q}_6)(\text{Q}_7)$,

a81 and a82 may each independently be an integer selected from 1 to 5,





n81 may be an integer selected from 0 to 4,

n82 may be 1, 2, or 3, and

L_{81} may be a monovalent organic ligand, a divalent organic ligand, or a trivalent organic ligand.






R_{81} and R_{82} may be the same as described in connection with Riot

The phosphorescent dopant may include at least one selected from Compounds PD1 to PD78 and FIr_6 , but embodiments of the present disclosure are not limited thereto:



104

-continued



PD5

PD6






PD7

PD8

PD9

105

-continued


**106**

-continued

PD10

5


10



PD11

15

20




25

30

35

40




PD12

PD13

45

50


55



PD14

60

65



PD15

PD16






PD17

PD18

PD19

107

-continued

**108**

-continued

PD20

5

10

15

PD21

20

25

30

PD22

35

40

PD23

45







50

PD24

55

60

65



PD25

PD26

PD27






PD28

PD29

PD30

109

-continued


**110**

-continued

PD31

5

10




PD32

15

20


25



PD33

30

35




PD34

40

45

50





PD35

55

60

65



PD36

PD37

PD38






PD39

PD40

PD41

111

-continued

**112**

-continued

PD42

5

10




15

PD43

20

25

30



PD44 35



40

45

PD45

50


55



PD46

60

65



PD47

PD48

PD49






PD50

PD51

PD52

113

-continued

**114**

-continued

PD53

PD58

5

10

PD54

15

20

25

30

35

40

45

PD55

50

55

60

65

PD56

PD57

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61

PD62

PD58

PD59

PD60

PD61






PD62

PD58

PD59

115


-continued

**116**

-continued

PD63

5




10

15

PD64

20

25




30

PD65

35


40



PD66

45

50




55

PD67

60

65



PD68

PD69







PD70

PD71

PD72

117


-continued



118

-continued


PD73



PD74

15 In one or more embodiments, the phosphorescent dopant may include PtOEP:

PD75



PD76

35 When the emission layer includes a host and a dopant, an amount of the dopant may be in a range of about 0.01 to about 20 parts by weight based on about 100 parts by weight of the host, but embodiments of the present disclosure are not limited thereto.

PD77

40 A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. While not wishing to be bound by theory, it is understood that when the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.

PD78

45 Then, an electron transport region may be disposed on the emission layer.


50 The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

55 For example, the electron transport region may have a hole blocking layer/electron transport layer/electron injection layer structure or an electron transport layer/electron injection layer structure, but the structure of the electron transport region is not limited thereto. The electron transport layer may have a single-layered structure or a multi-layered structure including two or more different materials.


60 Conditions for forming the hole blocking layer, the electron transport layer, and the electron injection layer which constitute the electron transport region may be understood by referring to the conditions for forming the hole injection layer.

65 When the electron transport region includes a hole blocking layer, the hole blocking layer may include, for example, at least one of BCP and Bphen, but may also include other materials.

119





BCP



Bphen

A thickness of the hole blocking layer may be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. While not wishing to be bound by theory, it is understood that when the thickness of the hole blocking layer is within these ranges, the hole blocking layer may have improved hole blocking ability without a substantial increase in driving voltage.


The electron transport layer may further include at least one selected from BCP, Bphen, Alq₃, BALq, TAZ, and NTAZ:

Alq₃


BALq

120

-continued




TAZ




NTAZ

In one or more embodiments, the electron transport layer may include at least one selected from Compounds ET1, ET2, and ET3, but embodiments are not limited thereto:

ET1




ET2



121



-continued



A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. While not wishing to be bound by theory, it is understood that when the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.

Also, the electron transport layer may further include, in addition to the materials described above, a metal-containing material.

The metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2:



The electron transport region may include an electron injection layer (EIL) that promotes flow of electrons from the second electrode **19** thereinto.

The electron injection layer may include at least one selected from LiF, NaCl, CsF, Li₂O, and BaO.

A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. While not wishing to be bound by theory, it is understood that when the thickness of the electron injection layer is within the range described above, the electron

122

injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

The second electrode **19** is disposed on the organic layer **15**. The second electrode **19** may be a cathode. A material for forming the second electrode **19** may be selected from metal, an alloy, an electrically conductive compound, and a combination thereof, which have a relatively low work function. For example, lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), potassium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be used as a material for forming the second electrode **19**. In one or more embodiments, to manufacture a top emission type light-emitting device, a transmissive electrode formed using ITO or IZO may be used as the second electrode **19**.

Hereinbefore, the organic light-emitting device has been described with reference to FIG. 1, but is not limited thereto.

The term “C₁-C₆₀ alkyl group” as used herein refers to a linear or branched saturated aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms. Non-limiting examples thereof include a methyl group, an ethyl group, a propyl group, an iso-butyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. The term “C₁-C₆₀ alkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

The term “C₁-C₆₀ alkoxy group” as used herein refers to a monovalent group represented by—OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group). Non-limiting examples thereof include a methoxy group, an ethoxy group, and an isopropoxy (iso-propoxy) group.

The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group formed by including at least one carbon-carbon double bond in the middle or at the terminus of the C₂-C₆₀ alkyl group. Examples thereof include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkenylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

The term “C₂-C₆₀ alkynyl group” as used herein refers to a hydrocarbon group formed by including at least one carbon-carbon triple bond in the middle or at the terminus of the C₂-C₆₀ alkyl group. Examples thereof include an ethynyl group, and a propynyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

The term “C₃-C₁₀ cycloalkyl group” as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms. Non-limiting examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The term “C₃-C₁₀ cycloalkylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

The term “C₁-C₁₀ heterocycloalkyl group” as used herein refers to a monovalent saturated monocyclic group having at least one heteroatom selected from N, O, P, Si and S as a ring-forming atom and 1 to 10 carbon atoms. Non-limiting examples thereof include a tetrahydrofuranyl group and a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkyl group.

The term “C₃-C₁₀ cycloalkenyl group” as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof, and which is not aromatic. Non-limiting

examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. The term “C₃-C₁₀ cycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

The term “C₁-C₁₀ heterocycloalkenyl group” as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, P, Si, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one carbon-carbon double bond in its ring. Non-limiting examples of the C₂-C₁₀ heterocycloalkenyl group include a 2,3-dihydrofuranyl group and a 2,3-dihydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkenyl group.

The term “C₆-C₆₀ aryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and the term “C₆-C₆₀ arylene group” as used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Non-limiting examples of the C₆-C₆₀ aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

The term “C₁-C₆₀ heteroaryl group” as used herein refers to a monovalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, P, Si, and S as a ring-forming atom, and 1 to 60 carbon atoms. The term “C₁-C₆₀ heteroarylene group,” as used herein refers to a divalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, P, Si, and S as a ring-forming atom, and 1 to 60 carbon atoms. Non-limiting examples of the C₁-C₆₀ heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the rings may be fused to each other.

The term “C₆-C₆₀ aryloxy group” as used herein refers to —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and a C₆-C₆₀ arylthio group used herein indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

The term “monovalent non-aromatic condensed polycyclic group” as used herein refers to a monovalent group that has two or more rings condensed to each other, only carbon atoms (for example, the number of carbon atoms may be in a range of 8 to 60) as a ring-forming atom, and which is non-aromatic in the entire molecular structure. Non-limiting examples of the monovalent non-aromatic condensed polycyclic group include a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group,” as used herein, refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

The term “monovalent non-aromatic condensed heteropolycyclic group” as used herein refers to a monovalent group that has two or more rings condensed to each other, has a heteroatom selected from N, O, P, Si, and S, other than carbon atoms (for example, the number of carbon atoms may be in a range of 2 to 60), as a ring-forming atom, and which is non-aromatic in the entire molecular structure. Non-limiting examples of the monovalent non-aromatic condensed heteropolycyclic group include a carbazolyl group. The term “divalent non-aromatic condensed heteropolycyclic group,” as used herein, refers to a divalent group having

the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

At least one of substituents of the substituted C₃-C₁₀ cycloalkylene group, substituted C₁-C₁₀ heterocycloalkylene group, substituted C₃-C₁₀ cycloalkenylene group, substituted C₁-C₁₀ heterocycloalkenylene group, substituted C₆-C₆₀ arylene group, substituted C₁-C₆₀ heteroarylene group, a substituted divalent non-aromatic condensed polycyclic group, a substituted divalent non-aromatic condensed heteropolycyclic group, substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₃₁)(Q₃₂)(Q₃₃),

wherein Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group and a monovalent non-aromatic condensed heteropolycyclic group.

When a group containing a specified number of carbon atoms is substituted with any of the groups listed in the preceding paragraph, the number of carbon atoms in the resulting “substituted” group is defined as the sum of the carbon atoms contained in the original (unsubstituted) group and the carbon atoms (if any) contained in the substituent. For example, when the term “substituted C₁-C₃₀ alkyl” refers to a C₁-C₃₀ alkyl group substituted with C₆-C₃₀ aryl group, the total number of carbon atoms in the resulting aryl substituted alkyl group is C₇-C₆₀.

The term “a biphenyl group” as used herein refers to a monovalent group in which two benzenes are linked via a single bond.

The term “a terphenyl group” as used herein refers to a monovalent group in which three benzenes are linked via a single bond. The term “terphenylene group” as used herein refers to a divalent group having the same structure as that of the terphenyl group.

Hereinafter, a compound and an organic light-emitting device according to embodiments are described in detail with reference to Synthesis Example and Examples. However, the organic light-emitting device is not limited thereto. The wording “B was used instead of A” used in describing Synthesis Examples means that an amount of A used was identical to an amount of B used, in terms of a molar equivalent.


125

EXAMPLES

Synthesis Example 1

Synthesis of Compound 1

Compound 1 was synthesized according to Reaction Scheme 1:



Synthesis of Intermediate (A)

15.0 grams (g) (89.7 millimoles, mmol) of carbazole was dissolved in 200 milliliters (mL) of DMF, and cooled to a temperature of 0° C. 3.77 g (94.19 mmol) of hydrogenated sodium (NaH, 60% dispersion in mineral oil) was slowly added thereto, and the resultant was stirred for 30 minutes at a temperature of 0° C. To the reaction mixture, 27.2 g (98.7 mmol) of 3'-bromo-5'-fluoro-[1,1'-biphenyl]-2-carbonitrile that had been diluted in 100 mL of DMF was slowly added for 10 minutes. The reaction temperature was raised to 150° C., and the resultant was stirred for 18 hours. Once the reaction was completed, the reaction product was cooled to room temperature, a saturated ammonium chloride (NH₄Cl)

126

aqueous solution was added thereto, and an organic layer was extracted and isolated therefrom by using dichloromethane (DCM). Water was removed therefrom by using anhydrous magnesium sulfate (MgSO₄), and the resultant was filtered and concentrated under reduced pressure. The product was separated by silica gel column chromatography, thereby completing the preparation of 24.3 g (yield of 64%) of Intermediate (A), which is the target compound.

LC-Mass (calculated: 422.04 grams per mole (g/mol), found: [M+1]⁺=423 g/mol).

3'-bromo-5'-fluoro-[1,1'-biphenyl]-2-carbonitrile was synthesized by using the synthesis method disclosed by WO 2002/074773 and WO 2003/006464.

Synthesis of Compound 1


10.0 g (23.6 mmol) of Intermediate (A), 10.5 g (28.4 mmol) of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole, 1.37 g (1.18 mmol) of tetrakis(triphenylphosphine)palladium(0) (Pd(PPh₃)₄), and 8.16 g (59.1 mmol) of potassium carbonate were added to a mixed solution including 50 mL of THF and 25 mL of water, and the mixture was stirred under reflux. Once the reaction was completed, the reaction solution was cooled to room temperature, an aqueous solution layer was removed by extraction, and the remaining product was filtered through silica gel under reduced pressure. The product was separated therefrom by silica gel column chromatography, thereby completing the preparation of 11.6 g (yield of 84%) of Compound 1, which is the target compound.

LC-Mass (calculated: 585.22 g/mol, found: [M+1]⁺=586 g/mol).

Synthesis Example 2


Synthesis of Compound 2

Compound 2 was synthesized according to Reaction Scheme 2:



127

-continued



Synthesis of Intermediate (B)

26.2 g (yield of 69%) of Intermediate (B), which is the target compound, was prepared in the same manner as Intermediate (A), except that 27.2 g (98.7 mmol) of 3'-bromo-5'-fluoro-[1,1'-biphenyl]-3-carbonitrile was used instead of 3'-bromo-5'-fluoro-[1,1'-biphenyl]-2-carbonitrile.

LC-Mass (calculated: 422.04 g/mol, found: $[M+1]^+ = 423$ g/mol).

3'-bromo-5'-fluoro-[1,1'-biphenyl]-3-carbonitrile was synthesized by using the synthesis method disclosed by WO 2002/074773 and WO 2003/006464.

Synthesis of Compound 2

11.2 g (yield of 81%) of Compound 2, which is the target compound, was prepared in the same manner as Compound 1, except that 10.0 g (23.6 mmol) of Intermediate (B) was used instead of Intermediate (A).


LC-Mass (calculated: 585.22 g/mol, found: $[M+1]^+ = 586$ g/mol).

Synthesis Example 3

Synthesis of Compound 8






Compound 8 was synthesized according to Reaction Scheme 3:

Reaction Scheme 3



128

-continued



129

Synthesis of Intermediate (C)

28.9 g (yield of 81%) of Intermediate (C), which is the target compound, was prepared in the same manner as Intermediate (A), except that 24.8 g (98.7 mmol) of 3-bromo-5-fluoro-1,1'-biphenyl was used instead of 3'-bromo-5'-fluoro-[1,1'-biphenyl]-2-carbonitrile.

LC-Mass (calculated: 397.05 g/mol, found: $[M+1]^+=398$ g/mol).

Synthesis of Intermediate (D)

19.9 g (yield of 64%) of Intermediate (D), which is the target compound, was prepared in the same manner as Intermediate (A), except that 19.7 g (98.7 mmol) of 3-bromo-5-fluorobenzonitrile was used instead of 3'-bromo-5'-fluoro-[1,1'-biphenyl]-2-carbonitrile.

LC-Mass (calculated: 346.01 g/mol, found: $[M+1]^+=347$ g/mol).

Synthesis of Intermediate (E)

15.0 g (43.2 mmol) of Intermediate (D), 13.2 g (51.8 mmol) of bis(pinacolato)diboron, 1.76 g (2.16 mmol) of $\text{PdC}_2(\text{dppf})\cdot\text{CH}_2\text{Cl}_2$, and 12.7 g (130 mmol) of potassium acetate were dissolved in 145 mL of DMF, and the mixture was stirred for 20 hours at a temperature of 100°C . Once the reaction was completed, the reaction solution was cooled to room temperature, and was filtered through silica gel under reduced pressure. The filtrate was concentrated therefrom by silica gel column chromatography. The product was recrystallized by using dichloromethane (DCM)/n-hexane thereby completing the preparation of 11.9 g (yield of 70%) of Intermediate (E), which is the target compound.

LC-Mass (calculated: 394.19 g/mol, found: $[M+1]^+=395$ g/mol).

Synthesis of Compound 8


10.9 g (yield of 74%) of Compound 8, which is the target compound, was prepared in the same manner as Compound 1, except that 10.0 g (25.1 mmol) of Intermediate (C) was used instead of Intermediate (A) and 11.9 g (30.1 mmol) of Intermediate (E) was used instead of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole.

LC-Mass (calculated: 585.22 g/mol, found: $[M+1]^+=586$ g/mol).

Synthesis Example 4

Synthesis of Compound 11

Compound 11 was synthesized according to Reaction Scheme 4:



130

Synthesis of Compound 11


9.95 g (yield of 69%) of Compound 11, which is the target compound, was prepared in the same manner as Compound 1, except that 11.2 g (28.4 mmol) of Intermediate (E) was used instead of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole.

LC-Mass (calculated: 610.22 g/mol, found: $[M+1]^+=611$ g/mol).

Synthesis Example 5

Synthesis of Compound 12

Compound 12 was synthesized according to Reaction Scheme 5:



Synthesis of Compound 12


9.38 g (yield of 65%) of Compound 12, which is the target compound, was prepared in the same manner as Compound 1, except that 10.0 g (23.6 mmol) of Intermediate (B) was used instead of Intermediate (A) and 11.2 g (28.4 mmol) of Intermediate (E) was used instead of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole.

LC-Mass (calculated: 610.22 g/mol, found: $[M+1]^+=611$ g/mol).

Synthesis Example 6


Synthesis of Compound 21

Compound 21 was synthesized according to Reaction Scheme 6:



131

-continued



Synthesis of Intermediate (F)

20.3 g (yield of 58%) of Intermediate (F), which is the target compound, was prepared in the same manner as Intermediate (A), except that 15.0 g (78.0 mmol) of 9H-carbazole-3-carbonitrile was used instead of carbazole.

LC-Mass (calculated: 447.04 g/mol, found: $[M+1]^+ = 448$ g/mol).

Synthesis of Compound 21

8.85 g (yield of 65%) of Compound 21, which is the target compound, was prepared in the same manner as Compound 1, except that 10.0 g (22.3 mmol) of Intermediate (F) was used instead of Intermediate (A).


LC-Mass (calculated: 610.22 g/mol, found: $[M+1]^+ = 611$ g/mol).

132

Synthesis Example 7

Synthesis of Compound 22

Compound 22 was synthesized according to Reaction Scheme 7:



Synthesis of Intermediate (G)

22.7 g (yield of 65%) of Intermediate (G), which is the target compound, was prepared in the same manner as Intermediate (B), except that 15.0 g (78.0 mmol) of 9H-carbazole-3-carbonitrile was used instead of carbazole.

LC-Mass (calculated: 447.04 g/mol, found: $[M+1]^+ = 448$ g/mol).

Synthesis of Compound 22

9.67 g (yield of 71%) of Compound 22, which is the target compound, was prepared in the same manner as Compound 1, except that 10.0 g (22.3 mmol) of Intermediate (G) was used instead of Intermediate (A).


LC-Mass (calculated: 610.22 g/mol, found: $[M+1]^+ = 611$ g/mol).

133

Synthesis Example 8

Synthesis of Compound 31

Compound 31 was synthesized according to Reaction Scheme 8:



Synthesis of Intermediate H

10.0 g (52.0 mmol) of 9H-carbazole-3-carbonitrile, 22.1 g (78.0 mmol) of 1-bromo-3-iodobenzene, 1.98 g (10.4 mmol) of copper iodide (CuI), 28.8 g (208 mmol) of potassium carbonate (K_2CO_3), and 3.75 g (20.8 mmol) of 1,10-phenanthroline were dissolved in 175 mL of DMF, and the mixture was stirred under reflux for 24 hours. Once the reaction was completed, the reaction product was cooled to room temperature, and filtered through silica gel under reduced pressure. The filtrate was concentrated under reduced pressure. The product was separated by silica gel column chromatography, thereby completing the preparation of 13.4 g (yield of 74%) of Intermediate (H), which is the target compound.

LC-Mass (calculated: 346.01 g/mol, found: $[M+1]^+=347$ g/mol).

Synthesis of Intermediate (I)

8.29 g (yield of 73%) of Intermediate (I), which is the target compound, was prepared in the same manner as Intermediate (E), except that 10.0 g (28.8 mmol) of Intermediate (H) was used instead of Intermediate (D).

LC-Mass (calculated: 394.19 g/mol, found: $[M+1]^+=395$ g/mol).

Synthesis of Compound 31


Compound 31 6.67 g (yield of 66%), which is the target compound, was prepared in the same manner as Compound 1, except that 7.82 g (19.8 mmol) of Intermediate (I) was used instead of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole.

LC-Mass (calculated: 610.22 g/mol, found: $[M+1]^+=611$ g/mol).

Synthesis Example 9

Synthesis of Compound 32

Compound 32 was synthesized according to Reaction Scheme 9:



Synthesis of Compound 32

7.07 g (yield of 70%) of Compound 32, which is the target compound, was prepared in the same manner as Compound 31, except that 7.00 g (16.5 mmol) of Intermediate (B) was used instead of Intermediate (A).




LC-Mass (calculated: 610.22 g/mol, found: $[M+1]^+=611$ g/mol).

135

Synthesis Example 10

Synthesis of Compound 38

Compound 38 was synthesized according to Reaction Scheme 10:



Synthesis of Intermediate J

16.0 g (yield of 55%) of Intermediate (J), which is the target compound, was prepared in the same manner as Intermediate (D), except that 15.0 g (78.0 mmol) of 9H-carbazole-3-carbonitrile was used instead of carbazole.

136

LC-Mass (calculated: 371.01 g/mol, found: $[\text{M}+1]^+=372$ g/mol).

Synthesis of Intermediate (K)

7.64 g (yield of 72%) of Intermediate (K), which is the target compound, was prepared in the same manner as Intermediate (E), except that 7.48 g (17.8 mmol) of Intermediate (J) was used instead of Intermediate (D).

LC-Mass (calculated: 419.18 g/mol, found: $[\text{M}+1]^+=420$ g/mol).

Synthesis of Compound 38


6.16 g (yield of 73%) of Compound 38, which is the target compound, was prepared in the same manner as Compound 8, except that 6.95 g (16.6 mmol) of Intermediate (K) was used instead of Intermediate (E).

LC-Mass (calculated: 610.22 g/mol, found: $[\text{M}+1]^+=611$ g/mol).

Synthesis Example 11


Synthesis of Compound 41

Compound 41 was synthesized according to Reaction Scheme 11:



137

-continued



Synthesis of Intermediate (L)

8.22 g (yield of 32%) of Intermediate (L), which is the target compound, was prepared in the same manner as Intermediate (A), except that 15.0 g (69.1 mmol) of 9H-carbazole-3,6-dicarbonitrile was used instead of carbazole.

LC-Mass (calculated: 472.03 g/mol, found: $[M+1]^+=473$ g/mol).

Synthesis of Compound 41


5.16 g (yield of 48%) of Compound 41, which is the target compound, was prepared in the same manner as Compound 1, except that 8.00 g (16.9 mmol) of Intermediate (L) was used instead of Intermediate (A).

LC-Mass (calculated: 635.21 g/mol, found: $[M+1]^+=636$ g/mol).

Synthesis Example 12




Synthesis of Compound 51

Compound 51 was synthesized according to Reaction Scheme 12:



138

-continued



Synthesis of Intermediate (M)

9.00 g (yield of 35%) of Intermediate (M), which is the target compound, was prepared in the same manner as Intermediate (H), except that 15.0 g (69.1 mmol) of 9H-carbazole-3,6-dicarbonitrile was used instead of 9H-carbazole-3-carbonitrile.

LC-Mass (calculated: 371.01 g/mol, found: $[M+1]^+=372$ g/mol).

Synthesis of Intermediate (N)

5.47 g (yield of 54%) of Intermediate (N), which is the target compound, was prepared in the same manner as Intermediate (E), except that 9.00 g (24.2 mmol) of Intermediate (M) was used instead of Intermediate (D).

LC-Mass (calculated: 419.18 g/mol, found: $[M+1]^+=420$ g/mol).

Synthesis of Compound 51

3.99 g (yield of 59%) of Compound 51, which is the target compound, was prepared in the same manner as Compound 1, except that 5.35 g (12.8 mmol) of Intermediate (N) was used instead of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole.


LC-Mass (calculated: 635.21 g/mol, found: $[M+1]^+=636$ g/mol).

139

Synthesis Example 13

Synthesis of Compound 61

Compound 61 was synthesized according to Reaction Scheme 13:



Synthesis of Compound 61


4.67 g (yield of 47%) of Compound 61, which is the target compound, was prepared in the same manner as Compound 21, except that 7.39 g (18.7 mmol) of Intermediate (I) was used instead of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole.

LC-Mass (calculated: 635.21 g/mol, found: $[M+1]^+=636$ g/mol).

Synthesis Example 14

Synthesis of Compound 91

Compound 91 was synthesized according to Reaction Scheme 14:



Synthesis of Compound 91

6.73 g (yield of 64%) of Compound 91, which is the target compound, was prepared in the same manner as Compound

140


1, except that 8.32 g (19.8 mmol) of Intermediate (K) was used instead of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole.

LC-Mass (calculated: 635.21 g/mol, found: $[M+1]^+=636$ g/mol).

Synthesis Example 15

Synthesis of Compound 157

Compound 157 was synthesized according to Reaction Scheme 15:



Synthesis of Compound 157

11.2 g (yield of 81%) of Compound 157, which is the target compound, was prepared in the same manner as Compound 2, except that 10.5 g (28.4 mmol) of 9-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole was used instead of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole.



LC-Mass (calculated: 585.22 g/mol, found: $[M+1]^+=586$ g/mol).

141

Synthesis Example 16

Synthesis of Compound 160

Compound 160 was synthesized according to Reaction Scheme 16:



Compound 160

Synthesis of Compound 160

9.26 g (yield of 68%) of Compound 160, which is the target compound, was prepared in the same manner as Compound 21, except that 9.88 g (26.8 mmol) of 9-(4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole was used instead of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole.


LC-Mass (calculated: 610.22 g/mol, found: $[M+1]^+=611$ g/mol).

142

Synthesis Example 17

Synthesis of Compound A

Compound A was synthesized according to Reaction Scheme 17:



Compound A

Synthesis of Compound A


12.8 g (yield of 87%) of Compound A, which is the target compound, was prepared in the same manner as Compound 1, except that 10.0 g (28.8 mmol) of Intermediate (D) was used instead of Intermediate (A).

LC-Mass (calculated: 509.19 g/mol, found: $[M+1]^+=510$ g/mol).

Synthesis Example 18


Synthesis of Compound B

Compound B was synthesized according to Reaction Scheme 18:



143

-continued



Compound B

Synthesis of Compound B

12.4 g (yield of 70%) of Compound B, which is the target compound, was prepared in the same manner as Compound 1, except that 15.2 g (28.4 mmol) of 9,9'-(5-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)-1,3-phenylene)bis(9H-carbazole) was used instead of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole.


LC-Mass (calculated: 750.28 g/mol, found: $[M+1]^+ = 751$ g/mol).

Synthesis Example 19

Synthesis of Compound C


Compound C was synthesized according to Reaction Scheme 19:

Reaction Scheme 19



144

-continued



Compound C

Synthesis of Intermediate (O)

12.1 g (yield of 72%) of Intermediate (O), which is the target compound, was prepared in the same manner as Intermediate (E), except that 15.0 g (37.7 mmol) of Intermediate (C) was used instead of Intermediate (D).

Synthesis of Compound C

8.70 g (yield of 68%) of Compound C, which is the target compound, was prepared in the same manner as Compound 8, except that 10.7 g (24.1 mmol) of Intermediate (O) was used instead of Intermediate (E).

LC-Mass (calculated: 636.26 g/mol, found: $[M+1]^+ = 637$ g/mol).


Evaluation Example 1

Thermal Characteristics Evaluation

Compounds 38 and A were thermally analyzed by thermogravimetric analysis (TGA) and differential scanning calorimetry (DSC) (N_2 atmosphere, a temperature range: from room temperature to 600° C. (10 degrees Centigrade per minute, ° C./min)-TGA, from room temperature to 400° C.-DSC, and Pan Type: Pt Pan in disposable Al pan (TGA), disposable Al pan(DSC)). Results thereof are shown in Table 2. Referring to Table 2, it was confirmed that Compound 38 has excellent thermal stability compared to Compound A.

TABLE 2


Compound No.	Tg (° C.)	Td (° C.) (0.1%)
Compound 38	153	387
Compound A	114	347



38

145

TABLE 2-continued



A

Example 1

A glass substrate with a 1,500 Angstrom (Å)-thick indium tin oxide (ITO) electrode (first electrode, anode) thereon was sonicated in distilled water. When the sonication with distilled water was completed, the resultant was sonicated using a solvent, such as iso-propyl alcohol, acetone, or methanol. The obtained resultant was dried and transferred to a plasma washer, washed with oxygen plasma for 5 minutes therein, and transferred to a vacuum depositing device.

Compound HT3 and Compound HP-1 were co-deposited on the ITO electrode of the glass substrate to form a hole injection layer having a thickness of 100 Å, Compound HT3 was deposited on the hole injection layer to form a hole transport layer having a thickness of 1,300 Å, and mCP was deposited on the hole transport layer to form an electron blocking layer having a thickness of 100 Å, thereby completing the formation of a hole transport region.

Compound 1 (host) and Flr6 (dopant, 10 percent by weight, wt %) were co-deposited on the hole transport region to form an emission layer having a thickness of 400 Å.

BCP was vacuum-deposited on the emission layer to form a hole blocking layer having a thickness of 100 Å, Compound ET3 and Liq were vacuum-codeposited on the hole

146

blocking layer to form an electron transport layer having a thickness of 300 Å, Liq was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Al was deposited on the electron injection layer to form a second electrode (cathode) having a thickness of 1,200 Å, thereby completing manufacture of an organic light-emitting device.

Examples 2 to 16 and Comparative Examples 1 to 3

Organic light-emitting devices were manufactured in the same manner as in Example 1, except that, in forming the emission layer, as a host, Compounds shown in Table 3 were used instead of Compound 1.

Evaluation Example 2

Evaluation on Characteristics of Organic Light-emitting Devices

A current-density change according to voltage, a luminescent change, and luminescent efficiency of the organic light-emitting devices of Examples 1 to 16 and Comparative Examples 1 to 3 were measured. Measurement methods used herein are described below, and results thereof are shown in Table 3.

(1) Change in Current Density According to Voltage

Regarding an organic light-emitting device, current flowing in a unit device was measured by using a current-voltage meter (Keithley 2400) while a voltage was raised from 0 volts (V) to 10 V, and the measured current was divided by an area.

(2) Change in Luminance According to Voltage

The luminance of an organic light-emitting device was measured by using a luminance meter (Minolta Cs-1000A) while a voltage was raised from 0 V to 10 V.

(3) Luminance Efficiency Measurement

Current efficiency (candelas per ampere, cd/A) at the same current density (10 milliamperes per square centimeter, mA/cm²) was calculated by using the current density and the luminance, respectively obtained in (1) and (2).

(4) Durability Measurement


A time that had lapsed when the initial luminance of 100% was reduced to 95% thereof was evaluated.

TABLE 3


	Host	Driving voltage (relative value)	Current efficiency (relative value)	Durability (relative value)	Color
Example 1	Compound 1	94%	115%	108%	Blue
Example 2	Compound 2	93%	120%	106%	Blue
Example 3	Compound 8	91%	118%	112%	Blue
Example 4	Compound 11	84%	130%	131%	Blue
Example 5	Compound 12	86%	127%	125%	Blue
Example 6	Compound 21	84%	131%	124%	Blue
Example 7	Compound 22	86%	121%	119%	Blue
Example 8	Compound 31	89%	117%	121%	Blue
Example 9	Compound 32	86%	120%	118%	Blue
Example 10	Compound 38	81%	135%	143%	Blue
Example 11	Compound 41	92%	108%	110%	Blue
Example 12	Compound 51	93%	104%	115%	Blue
Example 13	Compound 61	89%	110%	114%	Blue
Example 14	Compound 91	87%	115%	121%	Blue
Example 15	Compound 157	96%	108%	104%	Blue
Example 16	Compound 160	88%	110%	118%	Blue

TABLE 3-continued


	Host	Driving voltage (relative value)	Current efficiency (relative value)	Durability (relative value)	Color
Comparative Example 1	Compound A	100%	100%	100%	Blue
Comparative Example 2	Compound B	135%	64%	26%	Blue
Comparative Example 3	Compound C	141%	32%	15%	Blue



Compound A



Compound B



Compound C

60

The condensed cyclic based compound according to embodiments has excellent electric characteristics and thermal stability. Accordingly, an organic light-emitting device including the condensed cyclic based compound may have a low driving voltage, high efficiency, high power, high quantum luminescent efficiency, and a long lifespan.








It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

149

While one or more embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present disclosure as defined by the following claims.

What is claimed is:


1. A condensed cyclic compound represented by Formula 1:



150

-continued

Formula 4E



Formula 4F

Formula 1

Formula 2

Formula 3

Formula 4A

Formula 4B

Formula 4C

Formula 4D

wherein, in Formula 1,

Ar_1 is a group represented by Formula 2,

Ar_2 is a group represented by Formula 3,

L_1 is selected from a group represented by Formula 4A, a group represented by Formula 4B, and a group represented by Formula 4C, L_2 is selected from a group represented by Formula 4D, a group represented by Formula 4E, and a group represented by Formula 4F, wherein a case in which L_1 is the group represented by Formula 4C and L_2 is the group represented by Formula 4F is excluded,

R_1 to R_4 , R_{11} to R_{14} , R_{21} to R_{24} , R_{31} to R_{34} , and R_{41} to R_{49} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group (CN), a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, a substituted or unsubstituted C_1-C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group (provided that the substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group is not a substituted or unsubstituted carbazolyl group), —N(Q_4)(Q_5), and —B(Q_6)(Q_7),

the number of cyano group(s) (CN) in a group represented by $*-L_1-L_2-*$ in Formula 1 is 1, 2, 3, or 4,

a_1 to a_9 are each independently an integer selected from 0 to 5,

$*$ and $*'$ each indicate a binding site to a neighboring atom,

at least one of substituents of the substituted carbazolyl group, substituted C_6-C_{60} aryl group, substituted C_6-C_{60} aryloxy group, substituted C_6-C_{60} arylthio group, substituted C_1-C_{60} heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group is selected from

deuterium, —CD₃, —CD₂H, —CDH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_1-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a

monovalent non-aromatic condensed heteropolycyclic group (provided that the non-aromatic condensed heteropolycyclic group is not a carbazolyl group);

a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group (provided that the non-aromatic condensed heteropolycyclic group is not a carbazolyl group), each substituted with at least one selected from deuterium, —CD₃, —CD₂H, —CDH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazine group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group (provided that the non-aromatic condensed heteropolycyclic group is not a carbazolyl group), —N(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and —N(Q₃₄)(Q₃₅) and —B(Q₃₆)(Q₃₇), wherein Q₄ to Q₇, Q₂₄ to Q₂₇ and Q₃₄ to Q₃₇ are each independently selected from hydrogen, deuterium, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazine group, a hydrazine group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group (provided that the substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group is not a substituted or unsubstituted carbazolyl group).

2. The condensed cyclic compound of claim 1, wherein R₁ to R₄, R₁₁ to R₁₄, R₂₁ to R₂₄, R₃₁ to R₃₄, and R₄₁ to R₄₉ are each independently selected from: hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group (CN), a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazine group, a hydrazine group, a hydrazine group, a hydrazine group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl

group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyridazinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoidolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, imidazopyrimidinyl group, an imidazopyridinyl group, a pyridoindolyl group, a benzofuopyridinyl group, a benzothienopyridinyl group, a pyrimidoindolyl group, a benzofuopyrimidinyl group, a benzothienopyrimidinyl group, a phenoxazinyl group, a pyridobenzoaxazinyl group, and a pyridobenzothiazinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyridazinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoidolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, imidazopyrimidinyl group, an imidazopyridinyl group, a pyridoindolyl group, a benzofuopyridinyl group, a benzothienopyridinyl group, a pyrimidoindolyl group, a benzofuopyrimidinyl group, a benzothienopyrimidinyl group, a phenoxazinyl group, a pyridobenzoaxazinyl group, and a pyridobenzothiazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazine group, a hydrazine group, a hydrazine group, a hydrazine group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a fluorenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a phthalazinyl

153

group, a quinoxaliny group, a cinnoliny group, a quinazoliny group, $-N(Q_{34})(Q_{35})$, and $-B(Q_{36})(Q_{37})$; and

$-N(Q_4)(Q_5)$ and $-B(Q_6)(Q_7)$,

wherein Q_4 to Q_7 and Q_{34} to Q_{37} are each independently selected from hydrogen, C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group.

3. The condensed cyclic compound of claim 1, wherein R_1 to R_4 , R_{11} to R_{14} , R_{21} to R_{24} , R_{31} to R_{34} , and R_{41} to R_{49} are each independently selected from:

hydrogen, deuterium, and a cyano group (CN);

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group and a dibenzothiophenyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, a cyano group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

4. The condensed cyclic compound of claim 1, wherein at least one selected from R_3 , R_{13} , R_{23} , and R_{33} in Formulae 2 and 3 is a cyano group.

5. The condensed cyclic compound of claim 1, wherein a_1 to a_9 in Formulae 4A to 4F are each independently 0, 1, or 2.

6. The condensed cyclic compound of claim 1, wherein one, two, three, or four substituents of $*-L_1-L_2-*$ in Formula 1 are each independently selected from:

hydrogen, deuterium, and a cyano group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, a cyano group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

7. The condensed cyclic compound of claim 1, wherein one, two, three, or four substituents of $*-L_1-L_2-*$ in Formula 1 are each independently selected from:

a cyano group; and

a phenyl group, a biphenyl group, and a terphenyl group, each substituted with at least one cyano group.


8. The condensed cyclic compound of claim 1, wherein the number of cyano group(s) in the condensed cyclic compound represented by Formula 1 is 1, 2, 3, or 4.

9. The condensed cyclic compound of claim 1, wherein the number of carbazole ring systems in the condensed cyclic compound represented by Formula 1 is 2.


10. The condensed cyclic compound of claim 1, wherein the condensed cyclic compound is represented by one of Formulae 1-1 to 1-28:

154


Formula 1-1




Formula 1-2



Formula 1-3




Formula 1-4



155


-continued



Formula 1-5

156

-continued



Formula 1-9

5


10

15

20

Formula 1-6

Formula 1-10



25


30

35

40

Formula 1-7

Formula 1-11




45

50

Formula 1-8


Formula 1-12



55


60

65




157
-continued


Formula 1-13




Formula 1-14



Formula 1-15




Formula 1-16




158
-continued


Formula 1-17




Formula 1-18




Formula 1-19



Formula 1-20




Formula 1-21




159


-continued




Formula 1-22



Formula 1-23




Formula 1-24




Formula 1-25

160


-continued



Formula 1-26



Formula 1-27



Formula 1-28

wherein, in Formulae 1-1 to 1-28,

Ar₁ and Ar₂ are the same as described in claim 1,

R₅₁ to R₅₈ and R₆₁ to R₆₄ are each independently the same as described in connection with R₄₁ in claim 1, and the number of cyano group(s) in R₅₁ to R₅₈ and R₆₁ to R₆₄ is 1, 2, 3, or 4.

11. The condensed cyclic compound of claim 10, wherein R₅₁ to R₅₈ and R₆₁ to R₆₄ are each independently selected from:

hydrogen, deuterium, and a cyano group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, a cyano group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

12. The condensed cyclic compound of claim 10, wherein one, two, three, or four selected from R₅₁ to R₅₈ and R₆₁ to R₆₄ are each independently selected from:




a cyano group; and

a phenyl group, a biphenyl group, and a terphenyl group, each substituted with at least one cyano group.

161





13. The condensed cyclic compound of claim 10, wherein one, two, three, or four selected from R_{51} to R_{58} and R_{61} to R_{64} are a cyano group.

14. A condensed cyclic compound selected from Com-
pounds 1 to 260:




162

-continued



163

-continued




8

5

10

15


9



20

25

30




10

40

45

50

11




55

60


65

164


-continued




12



13




14



15

165
-continued




16

5

10

15

17




20

25

18

35




40

45

50

19




55


60

65

166
-continued




20




21

22




23



167

-continued

24




5

10

15

25




20

25

30

35




26

40

45

50

27



55


60

65


168

-continued


28




29



30




31



169

-continued




32

5

10

15

33




20

25

30

34

35




40

45

50

35




55

60


65

170


-continued




36



37







38







39

171

-continued





**172**

-continued







173

-continued





**174**

-continued







175

-continued


**176**

-continued



177

-continued




64

5

10

15

65




20

25

30

35




66

40

45

50

67




55

60

65


178

-continued




68

69







70

71







179

-continued

**180**

-continued



72

76

73

77

74

78

75

79

5

10

15

20

25

30

35

40

45

50





55

60





65

181

-continued


**182**

-continued



183

-continued




88

5

10

15


89



20

25

30




90

40

45

50

91




55

60


65

184


-continued




92



93







94







95

185

-continued


**186**

-continued




187

-continued






**188**

-continued







189

-continued


**190**

-continued




191

-continued





**192**

-continued







193

-continued







194

-continued







195


-continued

**196**

-continued



197
-continued




147

5

10

15

148




20

25

30

35




149

40

45

50

150




55


60

65


198
-continued




151



152




153



154

199

-continued



155

5

10

15

20

156

25

30

35

40

45

157

50


55

60

65

200



-continued



158


159

160



201

-continued



161

5


10

15

20


202

-continued



164

162 25




30

35


40

45



165


163 50



55

60


65




166

203

-continued






**204**

-continued







205

-continued





**206**

-continued







207

-continued





**208**

-continued








209

-continued





**210**

-continued



211

-continued

**212**

-continued

201

205

5

10

15

202

20

25

30

35

203

40

45





50

204

55





60

65







213

-continued





**214**

-continued







215

-continued







216

-continued







217

-continued


**218**

-continued




219

-continued


**220**

-continued



221

-continued




242

5

10

243 15




20

25

30

35




244

40

45

50

245




55

60


65

222


-continued




246



247




248



249

223

-continued




250

5

10

15


251



20

25


252



35

40

253




55

60

65


224

-continued



254

255



30


35

40


45

50

256






257



225

-continued

**226**

15. An organic light-emitting device, comprising
a first electrode;
a second electrode; and
an organic layer disposed between the first electrode and the second electrode,
wherein the organic layer comprises an emission layer,
and
wherein the organic layer comprises at least one of the condensed cyclic compounds represented by Formula 1 of claim 1.
16. The organic light-emitting device of claim 15, wherein the first electrode is an anode,
the second electrode is a cathode, and
the organic layer comprises a hole transport region disposed between the first electrode and the emission layer and an electron transport region disposed between the emission layer and the second electrode,
wherein the hole transport region comprises at least one selected from a hole injection layer, a hole transport layer, and an electron blocking layer, and
wherein the electron transport region comprises at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.
17. The organic light-emitting device of claim 15, wherein the emission layer comprises the condensed cyclic compound represented by Formula 1.
18. The organic light-emitting device of claim 15, wherein the emission layer comprises a host and a dopant,
the host comprises the condensed cyclic compound represented by Formula 1, and
an amount of the host is greater than an amount of the dopant.
19. The organic light-emitting device of claim 18, wherein the emission layer is a layer that emits blue light.
20. The organic light-emitting device of claim 16, wherein the electron transport region comprises the hole blocking layer, and the hole blocking layer comprises the condensed cyclic compound represented by Formula 1.

* * * * *

专利名称(译)	缩合环状化合物和包括其的有机发光器件		
公开(公告)号	US10062853	公开(公告)日	2018-08-28
申请号	US15/346090	申请日	2016-11-08
[标]申请(专利权)人(译)	三星电子株式会社		
申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD. 三星SDI CO. , LTD.		
当前申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD. 三星SDI CO. , LTD.		
[标]发明人	JUNG YONGSIK CHAE MIYOUNG SON JHUNMO HUH DALHO KWON EUNSUK KIM SANGMO LEE SAEYOUN JEON SOONOK CHUNG YEONSOOK KANG HOSUK KIM JONGSOO		
发明人	JUNG, YONGSIK CHAE, MIYOUNG SON, JHUNMO HUH, DALHO KWON, EUNSUK KIM, SANGMO LEE, SAEYOUN JEON, SOONOK CHUNG, YEONSOOK KANG, HOSUK KIM, JONGSOO		
IPC分类号	H01L51/50 H01L51/00 C07D209/86 C09K11/02		
CPC分类号	H01L51/0072 C07D209/86 C09K11/025 H01L51/5096 H01L51/5012 H01L51/5016		
代理机构(译)	康托科尔伯恩LLP		
审查员(译)	CLARK , GREGORYð		
优先权	1020160071733 2016-06-09 KR		
其他公开文献	US20170358755A1		
外部链接	Espacenet		

摘要(译)

式1表示的耦合环状化合物：Ar 1 -L 1 -L 2 -Ar 2 公式1 其中，在式1中，Ar 1 Ar 2 ，L 1 和L 2 与说明书中所述相同。

