



US010135029B2

(12) **United States Patent**
Kamiya

(10) **Patent No.:** **US 10,135,029 B2**
(45) **Date of Patent:** **Nov. 20, 2018**

(54) **DISPLAY DEVICE**

(71) Applicant: **Japan Display Inc.**, Minato-ku (JP)

(72) Inventor: **Akinori Kamiya**, Minato-ku (JP)

(73) Assignee: **Japan Display Inc.**, Minato-ku (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **15/408,925**

(22) Filed: **Jan. 18, 2017**

(65) **Prior Publication Data**

US 2017/0250373 A1 Aug. 31, 2017

(30) **Foreign Application Priority Data**

Feb. 25, 2016 (JP) 2016-034588

(51) **Int. Cl.**

H01L 27/32 (2006.01)

H01L 51/52 (2006.01)

H01L 27/12 (2006.01)

H01L 51/56 (2006.01)

(52) **U.S. Cl.**

CPC **H01L 51/5256** (2013.01); **H01L 27/3244** (2013.01); **H01L 27/1248** (2013.01); **H01L 27/1262** (2013.01); **H01L 51/56** (2013.01); **H01L 2251/301** (2013.01); **H01L 2251/303** (2013.01); **H01L 2251/5338** (2013.01)

(58) **Field of Classification Search**

CPC H01L 51/5256; H01L 2251/301; H01L 2251/303; H01L 2251/5338; H01L 51/56; H01L 27/1248; H01L 27/1262

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,268,695 B1 * 7/2001 Affinito H01L 51/5256
313/504
6,570,325 B2 * 5/2003 Graff H01L 51/5256
313/502
7,612,498 B2 * 11/2009 Sano H01L 51/5256
313/506
7,741,769 B2 * 6/2010 Hayashi H01L 51/5246
313/498
7,804,240 B2 * 9/2010 Shim H05B 33/04
313/504

(Continued)

FOREIGN PATENT DOCUMENTS

JP 2000-223264 8/2000
JP 2004-63462 2/2004

(Continued)

Primary Examiner — Mary Wilczewski


(74) *Attorney, Agent, or Firm* — Oblon, McClelland, Maier & Neustadt, L.L.P.

(57)

ABSTRACT

A display device includes: a light emitting element including a light emitting layer, and a first electrode and a second electrode that hold the light emitting layer therebetween; and a sealing layer on the light emitting element, wherein the sealing layer includes an organic layer, and a first inorganic layer and a second inorganic layer that hold the organic layer from an upper side and a lower side. A peripheral part of the first inorganic layer and a peripheral part of the second inorganic layer are connected around an outer perimeter of the organic layer and vertically overlap with each other so as not to cover an edge surface of each other's from a lateral side. At least one of the first inorganic layer and the second inorganic layer is an Aluminum Oxide film.

18 Claims, 6 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

8,169,132 B2 * 5/2012 Oh H01L 51/5256
257/100
8,552,634 B2 * 10/2013 Kim H01L 51/5271
313/504
8,569,951 B2 * 10/2013 Ryu H01L 51/5256
313/504
8,772,824 B2 * 7/2014 Lee H01L 27/00
257/100
9,257,674 B2 * 2/2016 Lee H01L 51/5256
9,490,450 B2 * 11/2016 Kang H01L 51/5256
9,681,501 B2 * 6/2017 Nam H01L 51/448
9,705,107 B2 * 7/2017 Kim H01L 51/5256
2002/0125822 A1 * 9/2002 Graff H01L 51/5256
313/506
2003/0085654 A1 * 5/2003 Hayashi H01L 51/529
313/506
2003/0164677 A1 9/2003 Miyaguchi et al.
2003/0197197 A1 * 10/2003 Brown H01L 51/5246
257/200
2004/0056269 A1 3/2004 Chen
2004/0232832 A1 * 11/2004 Kubota H01L 51/5256
313/512
2004/0239241 A1 * 12/2004 Wittmann H01L 51/0097
313/511
2005/0156513 A1 * 7/2005 Sano H01L 51/5256
313/504
2005/0181212 A1 * 8/2005 Schaepekens H01L 51/5256
428/411.1
2006/0220548 A1 * 10/2006 Menda H01L 51/5243
313/512
2008/0238301 A1 * 10/2008 Shim H05B 33/04
313/504
2009/0267487 A1 * 10/2009 Kwack H01L 51/5256
313/503
2011/0140163 A1 * 6/2011 Oh H01L 51/5256
257/100
2011/0140164 A1 * 6/2011 Seo H01L 51/5256
257/100
2012/0146492 A1 * 6/2012 Ryu H01L 51/5256
313/512
2013/0181602 A1 * 7/2013 Kang H01L 51/5256
313/504
2014/0048780 A1 * 2/2014 Song H01L 51/5253
257/40
2014/0138634 A1 * 5/2014 Lee H01L 27/00
257/40
2014/0138651 A1 * 5/2014 Oh H01L 51/5253
257/40
2014/0175397 A1 * 6/2014 Lee H01L 51/5253
257/40
2014/0217371 A1 * 8/2014 Kim H01L 51/5256
257/40
2014/0312363 A1 * 10/2014 Ryu H01L 51/5256
257/88
2014/0322527 A1 * 10/2014 Cho C23C 16/44
428/339

2015/0014636 A1 * 1/2015 Kang H01L 51/5253
257/40
2015/0021565 A1 1/2015 Min et al.
2015/0060786 A1 * 3/2015 Kwak H01L 51/5253
257/40
2015/0091030 A1 * 4/2015 Lee H01L 27/3246
257/91
2015/0228927 A1 * 8/2015 Kim H01L 51/5203
257/40
2015/0249229 A1 * 9/2015 Song H01L 51/5253
257/40
2015/0380684 A1 * 12/2015 Yan H01L 51/56
257/40
2015/0380685 A1 * 12/2015 Lee H01L 51/5243
257/40
2016/0043347 A1 * 2/2016 Sun H01L 51/5259
257/40
2016/0049443 A1 * 2/2016 Kim H01L 51/0023
257/91
2016/0049614 A1 * 2/2016 Gao G02B 5/3033
257/40
2016/0095172 A1 * 3/2016 Lee C23C 16/401
313/504
2016/0137769 A1 * 5/2016 Kwack C07C 69/54
257/40
2016/0141551 A1 * 5/2016 Seo H01L 51/5253
257/40
2016/0149165 A1 * 5/2016 Kim H01L 51/5284
257/40
2016/0164031 A1 * 6/2016 Pieper C08J 7/045
257/13
2016/0190503 A1 * 6/2016 Chang H01L 51/5253
257/40
2016/0226024 A1 * 8/2016 Park H01L 51/5256
2016/0254490 A1 * 9/2016 Ryu H01L 51/5256
257/40
2016/0268540 A1 * 9/2016 Kim H01L 51/5246
2016/0306472 A1 * 10/2016 Park G06F 3/0412
2016/0322601 A1 * 11/2016 Lee H01L 51/5256
2016/0336542 A1 * 11/2016 Chen H01L 21/67167
2016/0351852 A1 * 12/2016 Kim H01L 51/5256
2017/0018737 A1 * 1/2017 Kim H01L 51/5256
2017/0025640 A1 * 1/2017 Kim H01L 51/5256
2017/0062537 A1 * 3/2017 Kim H01L 27/3248
2017/0069876 A1 * 3/2017 Popp H01L 51/448
2017/0092896 A1 * 3/2017 Nakamura H01L 51/5256
2017/0115438 A1 * 4/2017 Choi G02B 5/3016
2017/0141313 A1 * 5/2017 Min C23C 14/042
2017/0149017 A1 * 5/2017 Lee H01L 51/5256
2017/0186999 A1 * 6/2017 Lee H01L 27/323
2017/0250373 A1 * 8/2017 Kamiya H01L 51/5256

FOREIGN PATENT DOCUMENTS

JP 4303591 7/2009
JP 2015-23023 2/2015
WO WO 03/028903 A2 4/2003

* cited by examiner

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5





FIG. 6



1

DISPLAY DEVICE

CROSS-REFERENCE TO RELATED APPLICATION

The present application claims priority from Japanese application JP2016-034588 filed on Feb. 25, 2016, the content of which is hereby incorporated by reference into this application.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a display device.

2. Description of the Related Art

Since a light emitting element layer such as an organic electroluminescence layer deteriorates by absorbing moisture, it is necessary to cover it with a sealing film to shut it off from an atmosphere. When SiN is used as a material for the sealing layer, the film thickness increases, and in the case of a flexible display, when it is bent, the sealing film possibly cracks. Further, according to some method of forming the film, SiN includes H₂, and thus if a thin film transistor is formed with a transparent amorphous oxide semiconductor (TAOS), a threshold voltage (V_{th}) gets shifted when a diffusion of H₂ reaches TAOS.

Japanese Unexamined Patent Publication No. 2015-023023 and Japanese Patent No. 4303591 disclose sealing films that include an Aluminum Oxide film, but the Aluminum Oxide film is sealed by another film. Japanese Unexamined Patent Publication No. 2000-223264 discloses a sealing film that includes an Aluminum Oxide film. Japanese Unexamined Patent Publication No. 2004-063462 discloses a sealing film for which a diamond like carbon is used. Regarding a display device, needs for narrowing down a width of a frame that surrounds a display region are increasing, but such needs are not considered in those patent documents.

SUMMARY OF THE INVENTION

It is an object of the present invention to form a sealing layer that accommodates itself to the narrowing of a frame, has increased flexibility, and prevents intrusion of moisture, and it is also an object of the present invention to stabilize a semiconductor property, that is, for example, to prevent the diffusion of H₂ to control a shift of threshold voltage of a thin film transistor formed with the transparent amorphous oxide semiconductor (TAOS).

A display device according to the present invention includes: a light emitting element including a light emitting layer, and a first electrode and a second electrode that hold the light emitting layer therebetween; and a sealing layer on the light emitting element, wherein the sealing layer includes an organic layer, and a first inorganic layer and a second inorganic layer that hold the organic layer from an upper side and a lower side, a peripheral part of the first inorganic layer and a peripheral part of the second inorganic layer are connected around an outer perimeter of the organic layer and vertically overlap with each other so as not to cover an edge surface of each other's from a lateral side, and at least one of the first inorganic layer and the second inorganic layer is an Aluminum Oxide film. According to the present invention, the peripheral part of the first inorganic

2

layer and the peripheral part of the second inorganic layer do not cover the edge surface of each other's. Therefore, compared with the case where the peripheral part of one of these covers the edge surface of the peripheral part of the other's, a formation region of the sealing layer becomes small, and the device can accommodate itself to the narrowing of a frame. Further, since one layer in the sealing layer is an Aluminum Oxide film, it is possible to form the sealing layer that can be bent easily and contains no moisture.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates a planar view of a display device according to an embodiment of the present invention.

FIG. 2 illustrates a II-II line cross sectional view of a display device illustrated in FIG. 1.

FIG. 3 illustrates a magnified view of part III encircled by a chain line in FIG. 2.

FIG. 4 illustrates a cross sectional view of an edge part of a display device illustrated in FIG. 2.

FIG. 5 illustrates a cross sectional view of a display device according to a first variation of the embodiment.

FIG. 6 illustrates a cross sectional view of a display device according to a second variation of the embodiment.

DETAILED DESCRIPTION OF THE INVENTION

Embodiments of the present invention are illustrated with reference to the accompanying drawings as follows. Note that the present invention can be used in various modes which do not depart from the spirit of the present invention, and should not be interpreted within a description of exemplary embodiments illustrated below.

While the width, thickness, shape, and the like of each component in the drawings may be illustrated schematically as compared with the actual embodiments in order to clarify the explanation, these are merely examples and the interpretation of the present invention should not be limited thereto. Furthermore, in the specification or respective drawings, the same reference symbols may be applied to elements that have functions similar to those that have already been illustrated in another drawing and an explanation of such elements may be omitted as appropriate.

Further, in the detailed explanation of the present invention, when a positional relationship between one component and another component is defined, unless specified otherwise, the words "on" and "under" are not applied only to a case where the other component is located directly on or directly under the one component, but may also be applied to a case where still another component is interposed between the one component and the other component.

FIG. 1 is a planer view of a display device according to an embodiment of the present invention. As a display device **100**, an organic electroluminescence display device is mentioned as an example. The display device **100** is configured to combine unit pixels of a plurality of colors composed of, for example, red, green and blue (subpixels) to form a pixel of full color (a pixel) and display an image of full color in a display region **10**.

FIG. 2 is a II-II line cross sectional view of the display device illustrated in FIG. 1. The display device **100** has a curved shape, and a spacer **12** is arranged inside the curvature. The spacer **12** works as a guide that restricts the curvature of the display device **100**. An integrated circuit

chip **14** is provided on the display device **100**, and a flexible printed circuit (FPC) **16** is connected to the display device **100**.

FIG. **3** is a magnified view of part III encircled by a chain line in FIG. **2**. The display device **100** has a first substrate **18** made of a material having flexibility such as resin. The first substrate **18** is located inside the curvature illustrated in FIG. **2**. Inside the curvature, at least on the backside of the display region **10** of the display device **100**, a first reinforcing film **20** is attached to the first substrate **18**. Further, as illustrated in FIG. **2**, a second reinforcing film **22** is attached so as to be opposed to the first reinforcing film **20**, and the first reinforcing film **20** and the second reinforcing film **22** are attached to each other via an adhesive **24** to thereby maintain the curved state of the display device **100**.

As illustrated in FIG. **3**, on the first substrate **18**, an undercoat layer **26** is formed that becomes a barrier against impurities that are contained by the first substrate **18** itself, and a semiconductor layer **28** is formed thereon. A source electrode **30** and a drain electrode **32** are connected electrically to the semiconductor layer **28**, and a gate insulation film **34** is formed so as to cover the semiconductor layer **28**. A gate electrode **36** is formed on the gate insulation film **34**, and an interlayer insulation film **38** is formed so as to cover the gate electrode **36**. The source electrode **30** and the drain electrode **32** penetrate the gate insulation film **34** and the interlayer insulation film **38**. A thin film transistor **40** is constituted by the semiconductor layer **28**, the source electrode **30**, the drain electrode **32** and the gate electrode **36**. A passivation film **42** is provided so as to cover the thin film transistor **40**.

A planarization layer **44** is provided on the passivation film **42**. A plurality of pixel electrodes **46** (e.g. anodes) arranged to correspond to each of the plurality of unit pixels are provided on the planarization layer **44**. The planarization layer **44** is formed so that at least a surface where the pixel electrode **46** is provided is planarized. The pixel electrode **46** is electrically connected to one of the source electrode **30** and the drain electrode **32** on the semiconductor layer **28** through a contact hole **48** that penetrates the planarization layer **44** and the passivation film **42**.

An insulation layer **50** is formed on the planarization layer **44** and the pixel electrode **46**. The insulation layer **50** is put on a peripheral part of the pixel electrode **46**, and is configured to form an opening at a part (e.g. a central part) of the pixel electrode **46**. A bank to surround the part of the pixel electrode **46** is formed by the insulation layer **50**.

A light emitting layer **52** is provided on the pixel electrode layer **46**. The light emitting layer **52** is provided individually (separately) for each pixel electrode **46**, and is configured to be put also on the insulation layer **50**. In this case, the light emitting layer **52** emits light in blue, red and green in correspondence with respective pixels. As a variation, the light emitting layer **52** may be configured to be located on the plurality of pixel electrodes **46** to form a continuous layer and made to emit light in white, and in such a case a color filter is provided.

On the light emitting layer **52**, a common electrode (e.g. a cathode) is provided. The common electrode is formed to be put on the insulation layer **50** that constitutes the bank. A light emitting element **56** is constituted by the light emitting layer **52**, and the pixel electrode **46** (the anode) and the common electrode (the cathode) that hold the light emitting layer **52** therebetween. The light emitting layer **52** is held between the pixel electrode **46** and the common electrode **54**, and emits light with its luminance controlled by a current that runs therebetween. Between the light emitting layer **52**

and the pixel electrode **46** (the anode), at least one of a hole injection layer and a hole transport layer (not shown) may be provided. Between the light emitting layer **52** and the common electrode **54** (the cathode), at least one of an electron injection layer and an electron transport layer (not shown) may be provided.

The light emitting element **56** is covered by a sealing layer **58** laminated on the common electrode **54** to be sealed and is shut off from moisture. The sealing layer **58** includes an organic layer **60**, and a first inorganic layer **62** and a second inorganic layer **64** that hold the organic layer **60** from an upper side and a lower side. Both of the first inorganic layer **62** and the second inorganic layer **64** are Aluminum Oxide films. The thickness of the Aluminum Oxide films is in the range of 25 nm to 100 nm, and is preferably around 25 nm, in particular. Since at least one layer in the sealing layer **58** is an Aluminum Oxide film, the sealing layer **58** can be bent easily and is configured to contain no moisture.

FIG. **4** is a cross sectional view of an edge part of the display device illustrated in FIG. **2**. A peripheral part of the first inorganic layer **62** and a peripheral part of the second inorganic layer **64** vertically overlap with each other so as to seal the organic layer **60** at its outer perimeter. The peripheral part of the first inorganic layer **62** and the peripheral part of the second inorganic layer **64** do not cover an edge surface of each other's from a lateral side. That is, a tip of one of the first inorganic layer **62** and the second inorganic layer **64** is not located farther than the peripheral part of the other's. Therefore, compared with the case where the peripheral part of one of these covers an edge surface of the peripheral part of the other's, a formation region of the sealing layer **58** becomes small, and the device can accommodate itself to the narrowing of a frame.

To the sealing layer **58**, a second substrate **68** made of a material having flexibility such as resin is attached with an intervention of an adhesive layer **66**. On the front side of the curvature of the display device **100**, a third reinforcing film **70** is attached to the second substrate **68** (see FIG. **2**).

FIG. **5** is a cross sectional view of a display device according to a first variation of the embodiment. This example is the same with the above embodiment in that a first inorganic layer **162** is the Aluminum Oxide film. A second inorganic layer **164** is a Silicon Nitride film. A thickness of the Silicon Nitride film is around 1 μm . A sealing layer **158** includes an organic layer **160**, and the first inorganic layer **162** and the second inorganic layer **164** that hold the organic layer **160** from an upper side and a lower side.

FIG. **6** is a cross sectional view of a display device according to a second variation of the embodiment. This example is the same with the above embodiment in that a second inorganic layer **264** is the Aluminum Oxide film. A first inorganic layer **262** is a Silicon Nitride film. A thickness of the Silicon Nitride film is around 1 μm . A sealing layer **258** includes an organic layer **260**, and the first inorganic layer **262** and the second inorganic layer **264** that hold the organic layer **260** from an upper side and a lower side.

The display device **100** is not limited to be an organic electroluminescence display device, and may be a display device that is provided with a light emitting element such as a quantum-dot light emitting diode (QLED) for each pixel or may be a liquid crystal display device.

While there have been described what are at present considered to be certain embodiments of the invention, it will be understood that various modifications may be made

5

thereto, and it is intended that the appended claims cover all such modifications as fall within the true spirit and scope of the invention.

What is claimed is:

1. A display device comprising:

a substrate

a light emitting element on the substrate, the light emitting element including a light emitting layer, a first electrode, and a second electrode, the first electrode and the second electrode holding the light emitting layer therebetween; and

a sealing layer on the light emitting element,

wherein the sealing layer comprises an organic layer, a first inorganic layer, and a second inorganic layer, the first inorganic layer and the second inorganic layer holding the organic layer from an upper side and a lower side,

the first inorganic layer and the second inorganic layer include respective peripheral parts connected to each other around an outer perimeter of the organic layer and vertically overlap with each other so as not to cover an edge surface of each other's from a lateral side,

the peripheral parts include a first area outside and adjacent to the outer perimeter of the organic layer, the first area including a point where the first and second inorganic layers contact each other, a second area outer from the point in the first area toward a peripheral edge of the display device, and a third area outer from the second area toward the peripheral edge of the display device,

the second area is higher than the first area,

the third area is lower than the second area, and

at least one of the first inorganic layer and the second inorganic layer is an Aluminum Oxide film.

2. The display device according to claim 1,

wherein one of the first inorganic layer and the second inorganic layer is an Aluminum Oxide film, and

the other one of the first inorganic layer and the second inorganic layer is a Silicon Nitride film.

3. The display device according to claim 1,

wherein the display device is configured to bend at a portion which includes the first inorganic layer and the second inorganic layer.

4. The display device according to claim 3,

wherein one of the first inorganic layer and the second inorganic layer is an Aluminum Oxide film, and

the other one of the first inorganic layer and the second inorganic layer is a silicon nitride film.

5. The display device according to claim 1,

wherein the third area is a recessed area, and the second area is a raised area.

6. The display device according to claim 1,

wherein a first distance between the first inorganic layer at the first area and the substrate is shorter than a second distance between the first inorganic layer at the second area and the substrate.

7. The display device according to claim 6,

wherein the first distance is longer than a third distance between the first inorganic layer at the third area and the substrate.

8. The display device according to claim 6,

wherein a fourth distance between the second inorganic layer at the first area and the substrate is shorter than a fifth distance between the second inorganic layer at the second area and the substrate.

6

9. The display device according to claim 8,

wherein the fourth distance is longer than a sixth distance between the second inorganic layer at the third area and the substrate.

10. The display device according to claim 1,

wherein thickness of the Aluminum Oxide film is from 25 nm to 100 nm.

11. A display device comprising:

a substrate;

a light emitting element on the substrate, the light emitting element including a light emitting layer, a first electrode, and a second electrode, the first electrode and the second electrode holding the light emitting layer therebetween; and

a sealing layer on the light emitting element,

wherein the sealing layer comprises an organic layer, a first inorganic layer, and a second inorganic layer, the first inorganic layer and the second inorganic layer holding the organic layer from an upper side and a lower side,

the first inorganic layer and the second inorganic layer include respective peripheral parts connected to each other around an outer perimeter of the organic layer and vertically overlap with each other so as not to cover an edge surface of each other's from a lateral side,

the peripheral parts include a first area outside and adjacent to the outer perimeter of the organic layer, the first area including a point where the first and second inorganic layers contact each other, a second area outer from the point in the first area toward a peripheral edge of the display device, and a third area outer from the second area toward the peripheral edge of the display device toward a peripheral edge of the display device,

the second area is higher than the first area,

the third area is lower than the second area,

the display device is configured to bend at a portion which includes the first inorganic layer and the second inorganic layer, the portion having a shape of a curve, the first inorganic layer is an Aluminum Oxide film, and the first inorganic layer is closer to an inside of the curve than the second inorganic layer at the portion.

12. The display device according to claim 11, wherein the second inorganic layer is a Silicon Nitride film.

13. The display device according to claim 11,

wherein the third area is a recessed area, and the second area is a raised area.

14. The display device according to claim 11,

wherein a first distance between the first inorganic layer at the first area and the substrate is shorter than a second distance between the first inorganic layer at the second area and the substrate.

15. The display device according to claim 14,

wherein the first distance is longer than a third distance between the first inorganic layer at the third area and the substrate.

16. The display device according to claim 14,

wherein a fourth distance between the second inorganic layer at the first area and the substrate is shorter than a fifth distance between the second inorganic layer at the second area and the substrate.

17. The display device according to claim 16,

wherein the fourth distance is longer than a sixth distance between the second inorganic layer at the third area and the substrate.

18. The display device according to claim **11**,
wherein thickness of the Aluminum Oxide film is from 25
nm to 100 nm.

* * * * *

专利名称(译)	显示设备		
公开(公告)号	US10135029	公开(公告)日	2018-11-20
申请号	US15/408925	申请日	2017-01-18
[标]申请(专利权)人(译)	株式会社日本显示器		
申请(专利权)人(译)	日本展示INC.		
当前申请(专利权)人(译)	日本展示INC.		
[标]发明人	KAMIYA AKINORI		
发明人	KAMIYA, AKINORI		
IPC分类号	H01L27/32 H01L51/52 H01L51/56 H01L27/12		
CPC分类号	H01L51/5256 H01L27/3244 H01L27/1248 H01L2251/5338 H01L51/56 H01L2251/301 H01L2251/303 H01L27/1262 H01L51/0097		
优先权	2016034588 2016-02-25 JP		
其他公开文献	US20170250373A1		
外部链接	Espacenet		

摘要(译)

一种显示装置，包括：发光元件，包括发光层；以及第一电极和第二电极，其将发光层保持在其间；和发光元件上的密封层，其中密封层包括有机层，以及从上侧和下侧保持有机层的第一无机层和第二无机层。第一无机层的周边部分和第二无机层的周边部分围绕有机层的外周连接并且彼此垂直地重叠，以便不从侧面覆盖彼此的边缘表面。第一无机层和第二无机层中的至少一个是氧化铝膜。

