



US010256418B2

(12) **United States Patent**
Kim et al.

(10) **Patent No.:** **US 10,256,418 B2**
(45) **Date of Patent:** **Apr. 9, 2019**

(54) **ORGANOMETALLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

(71) Applicants: **Samsung Electronics Co., Ltd.**,
Suwon-si, Gyeonggi-do (KR); **Samsung SDI Co., Ltd.**, Yongin-si, Gyeonggi-do (KR)

(72) Inventors: **Wook Kim**, Suwon-si (KR); **Miyoung Chae**, Suwon-si (KR); **Dalho Huh**, Suwon-si (KR); **Hyunjung Kim**, Suwon-si (KR); **Kangmun Lee**, Suwon-si (KR); **Namheon Lee**, Suwon-si (KR)

(73) Assignees: **SAMSUNG ELECTRONICS CO., LTD.**, Gyeonggi-Do (KR); **SAMSUNG SDI CO., LTD.**, Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 287 days.

(21) Appl. No.: **14/599,792**

(22) Filed: **Jan. 19, 2015**

(65) **Prior Publication Data**

US 2015/0333278 A1 Nov. 19, 2015

(30) **Foreign Application Priority Data**

May 16, 2014 (KR) 10-2014-0059303

(51) **Int. Cl.**
H01L 51/00 (2006.01)
C07F 15/00 (2006.01)
H01L 51/50 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 51/0085** (2013.01); **C07F 15/0033** (2013.01); **H01L 51/5012** (2013.01); **H01L**

51/5016 (2013.01); **H01L 51/5068** (2013.01); **H01L 51/5084** (2013.01)

(58) **Field of Classification Search**

CPC **H01L 51/0085**; **H01L 51/5016**; **H01L 51/5012**; **H01L 51/5084**; **H01L 51/5068**; **C07F 15/0033**

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,247,088 B2	8/2012	Ren et al.	
2005/0260446 A1 *	11/2005	Mackenzie	 C07F 15/002 428/690
2010/0052516 A1 *	3/2010	Ren	 C09K 11/06 313/504

FOREIGN PATENT DOCUMENTS

JP	2003-272861	9/2003
JP	2009511655	3/2009

OTHER PUBLICATIONS

Florian Kessler, et al., "Near-UV to red-emitting charged bis-cyclometallated iridium(III) complexes for light-emitting electrochemical cells", The Royal Society of Chemistry, Dalton Transactions, 2012, 180-191

* cited by examiner

Primary Examiner — Alexander C Kollias

(74) *Attorney, Agent, or Firm* — Cantor Colburn LLP


(57) **ABSTRACT**

An organometallic compound represented by Formula 1:

$M(L_1)_{n1}(L_2)_{n2}$ Formula 1

wherein in Formula 1, M, L₁, L₂, n₁, and n₂ are defined in the detailed description.

4 Claims, 1 Drawing Sheet



1

ORGANOMETALLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

This application claims priority to Korean Patent Application No. 10-2014-0059303, filed on May 16, 2014, in the Korean Intellectual Property Office, and all the benefits accruing therefrom under 35 U.S.C. § 119, the content of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

The present disclosure relates to organometallic compounds and organic light-emitting devices including the same.

2. Description of the Related Art

Organic light emitting devices (OLEDs) are self-emission devices that have wide viewing angles, high contrast ratios, and short response times. In addition, OLEDs exhibit excellent brightness, driving voltage, and response speed characteristics, and produce full-color images.

A typical organic light-emitting device includes an anode, a cathode, and an organic layer that is disposed between the anode and the cathode and includes an emission layer. A hole transport region may be disposed between the anode and the emission layer, and an electron transport region may be disposed between the emission layer and the cathode. Holes provided from the anode may move toward the emission layer through the hole transport region, and electrons provided from the cathode may move toward the emission layer through the electron transport region. The holes and the electrons are recombined in the emission layer to produce excitons. These excitons change from an excited state to a ground state, thereby generating light.

Various types of organic light emitting devices are known. However, there still remains a need in OLEDs having low driving voltage, high efficiency, high brightness, and long lifespan.

SUMMARY

Provided are novel organometallic compounds and organic light-emitting devices including the same.

Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

According to an aspect, an organometallic compound is represented by Formula 1:



wherein in Formula 1,

M may be selected from Ir, Pt, Os, Ti, Zr, Hf, Eu, Tb, and Tm;

L₁ may be selected from ligands represented by Formula 2;

L₂ may be selected from a monovalent organic ligand, a divalent organic ligand, a trivalent organic ligand, and a tetravalent organic ligand, and is different from L₁;


n1 may be 1, 2, or 3;

n2 may be 0, 1, 2, or 4;

2

when n1 is two or more, ligands L₁ may be identical or different, and when n2 is two or more, ligands L₂ may be identical to different;

Formula 2



wherein in Formula 2,

X₁ is N or C(R₁);

X₂ is N or C(R₂);

X₃ is N or C(R₃); and

X₄ is N or C(R₄);

R₁ to R₈ may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₂-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), and —B(Q₆)(Q₇),

provided that each of R₅ to R₈ is not simultaneously a hydrogen;

*and *' each indicates a binding site to M in Formula 1;

at least one of substituents of the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₂-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₂-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and —N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), and —B(Q₃₆)(Q₃₇),

wherein Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₇ may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

According to another aspect, an organic light-emitting device includes:

- a first electrode;
- a second electrode; and
- an organic layer disposed between the first electrode and the second electrode,

wherein the organic layer includes an emission layer, and further includes at least one organometallic compound represented by Formula 1.

The organometallic compound may be included in the emission layer, the organometallic compound included in the emission layer may act as a dopant, and the emission layer may further include a host.

BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other aspects will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with FIG. 1 which is a schematic view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the figures, to explain aspects of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

It will be understood that when an element is referred to as being “on” another element, it can be directly in contact with the other element or intervening elements may be present therebetween. In contrast, when an element is referred to as being “directly on” another element, there are no intervening elements present.

It will be understood that, although the terms first, second, third etc. may be used herein to describe various elements, components, regions, layers, and/or sections, these elements, components, regions, layers, and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer, or section from another element, component, region, layer, or section. Thus, a first element, component, region, layer, or section discussed below could be termed a second element, component, region, layer, or section without departing from the teachings of the present embodiments.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, the singular forms “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

It will be further understood that the terms “comprises” and/or “comprising,” or “includes” and/or “including” when used in this specification, specify the presence of stated features, regions, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, regions, integers, steps, operations, elements, components, and/or groups thereof.

Spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the figures. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation


depicted in the figures. For example, if the device in the figures is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the exemplary term “below” can encompass both an orientation of above and below. The device may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein interpreted accordingly.

“About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” can mean within one or more standard deviations, or within $\pm 30\%$, 20% , 10% , 5% of the stated value.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

Exemplary embodiments are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein should not be construed as limited to the particular shapes of regions as illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated may be rounded. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the precise shape of a region and are not intended to limit the scope of the present claims.

An organometallic compound according to an embodiment is represented by Formula 1:



Formula 1

M in Formula 1 may be selected from iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm).

For example, M in Formula 1 may be iridium or platinum, but is not limited thereto.

In Formula 1,


L_1 is selected from ligands represented by Formula 2,

L_2 is selected from a monovalent organic ligand, a divalent organic ligand, a trivalent organic ligand, and a tetravalent organic ligand, and

L_2 is different from L_1 .

L_1 and L_2 in Formula 2 will be described in detail later.

Formula 2



In Formula 1, n_1 is 1, 2, or 3, and n_2 is 0, 1, 2, 3, or 4.

The organometallic compound represented by Formula 1 is “neutral.” That is, the organometallic compound represented by Formula 1 is not a salt consisting of the pair of a cation and an anion. Accordingly, a layer including the organometallic compound represented by Formula 1 may be formed by deposition. For example, a layer including the organometallic compound represented by Formula 1 may be effectively formed by deposition at a temperature of about 100° to about 500° C., at a vacuum degree of about 10^{-8} to about 10^{-3} torr, and at a deposition speed of about 0.01 to about 100 Angstrom per second ($\text{\AA}/\text{sec}$). Accordingly, a device including the organometallic compound represented by Formula 1 may have improved manufacturing workability.

In Formula 2,

X_1 may be N or C(R_1),

X_2 may be N or C(R_2),

X_3 may be N or C(R_3), and

X_4 may be N or C(R_4).

For example, in Formula 2,

X_1 may be C(R_1),

X_2 may be C(R_2),

X_3 may be C(R_3), and

X_4 may be C(R_4),

but they are not limited thereto.

R_1 to R_8 are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_2 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q_1)(Q_2), —Si(Q_3)(Q_4)(Q_5), and —B(Q_6)(Q_7), provided that each of R_5 to R_8 in Formula 2 is not simultaneously a hydrogen. In other words, at least one of R_5 to R_8 , which are substituents of a pyridine ring in Formula 2, is selected from substituents other than hydrogen. Q_1 to Q_7 may be understood by referring to a detailed description thereof to be provided later.

According to an embodiment, in Formula 2, R_1 to R_8 may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_2 - C_{20} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q_3)(Q_4)(Q_5).

In some embodiments, R_1 to R_8 in Formula 2 may be each independently selected from

a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a phenyl group, a naphthyl group, a pyridinyl group, and a pyrimidinyl group;

a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a quinoxaliny group, a quinazolinyl group, a cinnoliny group, a carbazolyl group, a phenanthroliny group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a quinoxaliny group, a quinazolinyl group, a cinnoliny group, a carbazolyl group, a phenanthroliny group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl

group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a quinoxaliny group, a quinazolinyl group, a cinnoliny group, a carbazolyl group, a phenanthroliny group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q_3)(Q_4)(Q_5); and

—Si(Q_3)(Q_4)(Q_5),

wherein Q_3 to Q_5 and Q_{33} to Q_{35} may be each independently selected from a hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinoliny group, and an isoquinoliny group, but they are not limited thereto.

In some embodiments, R_1 to R_8 in Formula 2 may be each independently selected from

a hydrogen, —F, a cyano group, a nitro group, a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decanyl group, an isodecanyl group, a sec-decanyl group, a tert-decanyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group;

a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decanyl group, an isodecanyl group, a sec-decanyl group, a tert-decanyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from —F, a cyano group, a nitro group, a

9


phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, and $-\text{Si}(\text{Q}_{33})(\text{Q}_{34})(\text{Q}_{35})$; and

$-\text{Si}(\text{Q}_3)(\text{Q}_4)(\text{Q}_5)$,


wherein Q_3 to Q_5 and Q_{33} to Q_{35} may be each independently selected from a hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, but they are not limited thereto.

For example, L_1 in Formula 1 may be selected from a ligand represented by Formula 2A below through a ligand represented by Formula 2D below, but is not limited thereto.


Formula 2A




Formula 2B



Formula 2C



Formula 2D



10

R_1 to R_7 in Formulae 2A to 2D may be understood by referring to the corresponding description provided herein, and R_5 to R_7 in Formulae 2A to 2D are not simultaneously a hydrogen.

* and *' in Formulae 2A to 2D are binding sites to M in Formula 1.

For example, R_5 to R_7 in Formulae 2A to 2D may be each independently selected from







a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decanyl group, an isodecanyl group, a sec-decanyl group, a tert-decanyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group; and

a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decanyl group, an isodecanyl group, a sec-decanyl group, a tert-decanyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from $-\text{F}$, a cyano group, a nitro group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, and $-\text{Si}(\text{Q}_{33})(\text{Q}_{34})(\text{Q}_{35})$; and

R_1 to R_4 may be each independently selected from a hydrogen, $-\text{F}$, a cyano group, a nitro group, a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decanyl group, a sec-decanyl group, a tert-decanyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, and $-\text{Si}(\text{Q}_3)(\text{Q}_4)(\text{Q}_5)$,

wherein Q_3 to Q_5 and Q_{33} to Q_{35} may be each independently selected from a hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, but they are not limited thereto.

L_2 in Formula 1 may be selected from a ligand represented by Formula 3 below, a ligand represented by Formula 4 below, and a ligand represented by one of Formulae 5-1 to 5-4:



Y_1 to Y_4 in Formula 3 are each independently carbon (C) or nitrogen (N).

For example, in Formula 3, Y_1 may be N and Y_4 may be C, but they are not limited thereto.

For example, in Formula 3, Y_2 and Y_3 may be C, but they are not limited thereto.

In Formula 3, Y_1 and Y_2 may be linked to each other via a single bond or a double bond, and Y_3 and Y_4 may be linked to each other via a single bond or a double bond.


In Formula 3, CY_1 and CY_2 may be each independently a C_5-C_{60} carbocyclic group or a C_2-C_{60} heterocyclic group, and optionally, CY_1 and CY_2 may be linked to each other via a single bond or a first linking group.

For example, in Formula 3, CY_1 and CY_2 may be each independently a benzene, a naphthalene, a fluorene, a spirofluorene, an indene, a pyrrole, a thiophene, a furan, a imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isooxazole, a triazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, a quinoline, an isoquinoline, a benzoquinoline, a quinoxaline, a quinazoline, a carbazole, a benzimidazole, a benzofuran, a benzothiophene, an isobenzothiophene, a benzooxazole, an isobenzooxazole, a triazole, a tetrazole, an oxadiazole, a triazine, a dibenzofuran, a dibenzothiophene, a benzofuopyridine, or a benzothienopyridine.

Formula 3

According to an embodiment, in Formula 3, CY_1 may be a pyridine, a triazole, an imidazole, a pyrazole, a benzofuopyridine, or a benzothienopyridine, and CY_2 may be a benzene or a pyridine, but they are not limited thereto.


5 In some embodiments, in Formula 3, CY_1 and CY_2 are linked to each other via a single bond or a first linking group, and the first linking group may be represented by Formula 6 below:



Formula 6

Formula 4

10 Z_{31} in Formula 6 may be $*-O-*$, $*-S-*$, $*-N(Q_{41})-*$, $*-C(Q_{42})(Q_{43})-*$, $*-C(Q_{44})=C(Q_{45})-*$, or



Formula 5-1

Q_{41} to Q_{49} may be each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl

25 group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, and a C_1-C_{60} alkoxy group;

Formula 5-2

Formula 5-3

a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, and a C_1-C_{60} alkoxy group, each substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_3-C_{10} cycloalkyl group, a C_2-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_2-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_2-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

Formula 5-4

35 a C_3-C_{10} cycloalkyl group, a C_2-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_2-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_2-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group; or

40 a C_3-C_{10} cycloalkyl group, a C_2-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_2-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_2-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, a C_1-C_{60} alkoxy group, a C_3-C_{10} cycloalkyl group, a C_2-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_2-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_2-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

13

aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group; and

c1 is an integer of 1 to 10, and when c1 is 2 or more, groups Z₃₁ may be identical or different.

Q₄₁ to Q₄₉ may be understood by referring to a detailed description to be stated herein in connection with Z₁.


For example, R₄₁ to R₄₉ in Formula 6 may be each independently selected from

a hydrogen atom, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a phenyl group, a naphthyl group, a pyridinyl group, and a pyrimidinyl group; and

a phenyl group, a naphthyl group, a pyridinyl group, and a pyrimidinyl group; but they are not limited thereto.

For example, in Formula 3, CY₁ and CY₂ may be linked to each other via a single bond or a first linking group, the first linking group may be represented by *—C(Q₄₄)(Q₄₄)₄₅—* or



(that is, b1 in Formula 6 is 1), and Q₄₄ to Q₄₉ may be each independently a hydrogen, a C₁-C₁₀ alkyl group, or a C₁-C₁₀ alkoxy group, but they are not limited thereto.

In Formula 4,

X₁₁ may be N or C(R₁₁),

X₁₂ may be N or C(R₁₂),

X₁₃ may be N or C(R₁₃), and

X₁₄ may be N or C(R₁₄).

For example, in Formula 4,

X₁₁ may be C(R₁₁),

X₁₂ may be C(R₁₂),

X₁₃ may be C(R₁₃), and

X₁₄ may be C(R₁₄), but they are not limited thereto.

Z₁, Z₂, and R₁₁ to R₁₄ may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₂-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group. Z₃ to Z₉ may be understood by referring to the description provided herein in connection with Z₁.

14

tuted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₂-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), and —B(Q₆)(Q₇);

Examples of Z₁, Z₂, and R₁₁ to R₁₄ may be understood by referring to detailed examples of R₁ presented herein.

a and b in Formula 3 may be each independently an integer of 1 to 5. For example, a and b may be each independently 1 or 2, but they are not limited thereto.

* and *' in Formulae 3 and 4 are binding sites to M in Formula 1.

Y₅ and Y₆ in Formula 5-1 may be each independently carbon (C) or nitrogen (N).

Y₅ and Y₆ in Formula 5-1 may be linked to each other via a single bond or a double bond.

CY₃ in Formula 5-1 may be a C₅-C₆₀ carbocyclic group or a C₂-C₆₀ heterocyclic group. Examples of CY₃ in Formula 5-1 may be understood by referring to examples stated herein in connection with CY₁ and CY₂.

Z₃ to Z₉ in Formulae 5-1 to 5-4 may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₂-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group. Z₃ to Z₉ may be understood by referring to the description provided herein in connection with Z₁.

A₁ in Formulae 5-3 may be P or As.

X_{11a} and X_{11b} in Formula 5-4 may be each independently N, O, N(R₃₄), P(R₃₅)(R₃₆), or As(R₃₇)(R₃₈). R₃₄ to R₃₈ may be understood by referring to the description provided herein in connection with Z₁.







R_{33a} in Formula 5-4 may be a single bond, a double bond, a substituted or unsubstituted C₁-C₅ alkylene group, or a substituted or unsubstituted C₂-C₅ alkenylene group.

* and *' in Formulae 5-1 to 5-4 are binding sites to M in Formula 1.

In an embodiment, L₂ in Formula 1 may be selected from the ligand represented by Formula 3 and the ligand represented by Formula 4.

In some embodiments, L₂ in Formula 1 may be selected from a ligand represented by Formula 3-1 to a ligand represented by 3-142, but is not limited thereto:


15




16

-continued


Formula 3-1




Formula 3-2



Formula 3-3




Formula 3-4



Formula 3-5

Formula 3-6



Formula 3-7






Formula 3-8

Formula 3-9

Formula 3-10


Formula 3-11

17
-continued




18
-continued


Formula 3-12




Formula 3-13




Formula 3-14



Formula 3-15



Formula 3-16



Formula 3-17






Formula 3-18

Formula 3-19

Formula 3-20


Formula 3-21

19
-continued




20
-continued


Formula 3-22




Formula 3-23




Formula 3-24



Formula 3-25



Formula 3-26



Formula 3-27

Formula 3-28






Formula 3-29

Formula 3-30

Formula 3-31


21

-continued


**22**

-continued


Formula 3-32




Formula 3-33




Formula 3-34



Formula 3-35



Formula 3-36



Formula 3-37

Formula 3-38






Formula 3-39

Formula 3-40

Formula 3-41


23

-continued


**24**

-continued


Formula 3-42




Formula 3-43




Formula 3-44



Formula 3-45



Formula 3-46



Formula 3-47

Formula 3-48






Formula 3-49

Formula 3-50

Formula 3-51


25

-continued


**26**

-continued


Formula 3-52




Formula 3-53




Formula 3-54



Formula 3-55



Formula 3-56



Formula 3-57

Formula 3-58






Formula 3-59

Formula 3-60

Formula 3-61


27

-continued


**28**

-continued


Formula 3-62




Formula 3-63




Formula 3-64



Formula 3-65



Formula 3-66



Formula 3-67

Formula 3-68






Formula 3-69

Formula 3-70

Formula 3-71

29

-continued




30

-continued

Formula 3-72

5




10

Formula 3-73

15

20



25

Formula 3-74


30

35

40

Formula 3-75

45




50

55

Formula 3-76

60



65

Formula 3-77






Formula 3-78

Formula 3-79

Formula 3-80

31


-continued

**32**

-continued

Formula 3-81


5



10

Formula 3-82

15




20

25

Formula 3-83

30




35

40

Formula 3-84

45



50

55

Formula 3-85

60

65

Formula 3-86






Formula 3-87

Formula 3-88

Formula 3-89


33

-continued


**34**

-continued


Formula 3-90




Formula 3-91



Formula 3-92



Formula 3-93



Formula 3-94

Formula 3-95






Formula 3-96

Formula 3-97

Formula 3-98

35

-continued




36

-continued

Formula 3-99

5




10

15

Formula 3-100


20



25

Formula 3-101


35



40

Formula 3-102


45



50

Formula 3-103

55



60

65

Formula 3-104

Formula 3-105






Formula 3-106

Formula 3-107

Formula 3-108

37


-continued




38

-continued


Formula 3-109




Formula 3-110




Formula 3-111



Formula 3-112



Formula 3-113



Formula 3-114

Formula 3-115






Formula 3-116

Formula 3-117

Formula 3-118

39

-continued




40

-continued

Formula 3-119

5




10

15

Formula 3-120


20



25

Formula 3-121


30



35

Formula 3-122

40




45

50

Formula 3-123

55



60

65

Formula 3-124

Formula 3-125





Formula 3-126

Formula 3-127

Formula 3-128


41

-continued


**42**

-continued


Formula 3-129




Formula 3-130



Formula 3-131



Formula 3-132



Formula 3-133





Formula 3-134

Formula 3-135

Formula 3-136

43


-continued



44


-continued

Formula 3-137



Formula 3-141

Formula 3-138



Formula 3-142

Formula 3-139

30 Examples of Z_1 , Z_2 , Z_{1a} , Z_{1b} , Z_{2a} , Z_{2b} , Z_{2c} , and Q_{44} to Q_{49} in Formulae 3-1 to 3-142 may be understood by referring to examples presented herein in connection with R_1 .

For example, Z_1 , Z_2 , Z_{1a} , Z_{1b} , Z_{2a} , Z_{2b} , Z_{2c} , and Q_{44} to Q_{49} in Formulae 3-1 to 3-142 may be each independently selected from

35 a hydrogen atom, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

40 a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group;

45 a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group;

Formula 3-140

50 a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, and $-Si(Q_{33})(Q_{34})(Q_{35})$; and

$-Si(Q_3)(Q_4)(Q_5)$,

55 wherein Q_3 to Q_5 and Q_{33} to Q_{35} may be each independently selected from a hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a

45

pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group.

In Formulae 3-1 to 3-142,

a4 and b4 may be each independently 1, 2, 3, or 4;

a3 and b3 may be each independently 1, 2, or 3;

a2 and b2 may be each independently 1 or 2; and

* and *' are binding sites to M in Formula 1.

In some embodiments, L_2 in Formula 1 may be selected from a ligand represented by Formula 3-2, a ligand represented by Formula 3-132, and a ligand represented by Formula 4, and in Formulae 3-2, 3-132, and 4;

X_{11} may be $C(R_{11})$,

X_{12} may be $C(R_{12})$,

X_{13} may be $C(R_{13})$, and

X_{14} may be $C(R_{14})$;

Z_1 , Z_2 , Z_{1a} , Z_{1b} , and R_{11} to R_{14} may be each independently selected from

a hydrogen atom, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group;


a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, and —Si(Q_{33})(Q_{34})(Q_{35}); and

—Si(Q_3)(Q_4)(Q_5),

wherein Q_3 to Q_5 and Q_{33} to Q_{35} may be each independently selected from a hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group.

a4 and b4 may be each independently 1, 2, 3, or 4; a3 and b3 may be each independently 1, 2, or 3; a2 and b2 may be each independently 1 or 2; and * and *' are binding sites to M in Formula 1, but they are not limited thereto.

In some embodiments, L_2 in Formula 1 may be selected from a ligand represented by Formula 3-2A to a ligand represented by 3-2I and a ligand represented by Formula 4A, but is not limited thereto:



Formula 3-2A

55

60

65

46


-continued

Formula 3-2B

5

10

15




Formula 3-2C

20

25

30

35




Formula 3-2D


40

45


50



Formula 3-2E







Formula 3-2F



47

-continued




* and *' in Formulae 3-2A to 3-2I and 4A are binding sites to M in Formula 1.

In some embodiments, the organometallic compound may be represented by Formulae 1A or 1B below, but is not limited thereto:


48

Formula 3-2G



Formula 1B

Formula 3-2H



30

M, R₁ to R₉, Z₁, Z₂, a, b, R₁₁ to R₁₄, Y₁ to Y₄, CY₁, CY₂, n₁, and n₂ in Formulae 1A and 1B may be understood by referring to the description presented herein.

Formula 3-2I

For example, in Formulae 1A and 1B,

n₁ may be 1, 2, or 3;

n₂ may be 0, 1, or 2;

Y₁ to Y₄ are each independently carbon (C) or nitrogen (N);

Y₁ and Y₂ are linked to each other via a single bond or a double bond, and Y₃ and Y₄ are linked to each other via a single bond or a double bond;

CY₁ and CY₂ may be each independently a benzene, a naphthalene, a fluorene, a spiro-fluorene, an indene, a pyrrole, a thiophene, a furan, an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isooxazole, a triazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, a quinoline, an isoquinoline, a benzoquinoline, a quinoxaline, a quinoxaline, a carbazole, a benzimidazole, a benzofuran, a benzothiophene, an isobenzothiophene, a benzooxazole, an isobenzooxazole, a triazole, a tetrazole, an oxadiazole, a triazine, a dibenzofuran, a dibenzothiophene, a benzofuro-pyridine, or a benzothienopyridine;

Formula 4A

R₁ to R₈, Z₁, Z₂, and R₁₁ to R₁₄ may be each independently selected from

a hydrogen, —F, a cyano group, a nitro group, a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decanyl group, an isodecanyl group, a sec-decanyl group, a tert-decanyl group, a methoxy group, an ethoxy group, a propoxy group, a

49

butoxy group, a pentoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group;

a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decanyl group, an isodecanyl group, a sec-decanyl group, a tert-decanyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from —F, a cyano group, a nitro group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, and —Si(Q₃₃)(Q₃₄)(Q₃₅); and

—Si(Q₃)(Q₄)(Q₅),

wherein Q₃ to Q₅ and Q₃₃ to Q₃₅ may be each independently selected from a hydrogen, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, provided that each of R₅ to R₈ is not simultaneously a hydrogen;

a and b may be each independently 1, 2, or 3.

In some embodiments, in Formula 1A, Y₁ may be nitrogen (N), Y₄ may be carbon (C), CY₁ may be a pyridine, a triazole, an imidazole, a pyrazole, a benzofuopyridine, or a benzothienopyridine, and CY₂ may be a benzene or a pyridine, but they are not limited thereto.

n1 in Formula 1 indicates the number of L₁, and may be 1, 2, or 3, and when n1 is 2 or more, two or more L₁ may be identical or different.





n2 in Formula 1 indicates the number of L₂, and may be 0, 1, 2, 3, or 4, and when n2 is 2 or more, two or more L₂ may be identical or different.

In some embodiments, in Formula 1, n1 is 3, n2 is 0, and M is iridium; and i) L₁ includes only ligands represented by Formula 2A (in Formula 2A, R₁ to R₄ are a hydrogen, and R₇ is a phenyl group) and thus, three L₁ are identical, or ii) L₁ includes two ligands represented by Formula 2A (in Formula 2A, R₁ to R₄ are a hydrogen, and R₇ is a phenyl group) and one ligand represented by Formula 2B (in Formula 2B, R₁ to R₄ are a hydrogen, R₆ is a methyl group, and R₇ is a phenyl group).

In some other embodiments, in Formula 1, n1 is 1, n2 is 2, and M is iridium; and i) L₂ includes only two ligands represented by Formula 3-2A and thus, two L₂ may be identical, or ii) L₂ includes the ligand represented by Formula 3-2A and the ligand represented by Formula 3-2B and thus, two L₂ may be different.





The organometallic compound represented by Formula 1 may include any one selected from Compounds 1 to 33, but is not limited thereto:

50



51

-continued

**52**

-continued

5

5

10

15

20

6

25

30

35

7

40

45






50

8

55

60

65



9

10





11

12

13

53

-continued

**54**

-continued

14

5

10

15

15

20

25

30

16

35

40

45

50

17

55

60





65

18

19





20

21



55

-continued

**56**


-continued

22

5

10

15




26

23

20

25

30



27

24


35

40

45

50

25




28

29

55





60

65



57

-continued




Since n_1 of the organometallic compound represented by Formula 1, which indicates the number of L_1 , is not zero, the organometallic compound represented by Formula 1 necessarily includes at least one ligand represented by Formula 2.

58

In Formula 2, a “pyridine-based ring” and a “benzimidazole-based ring” are linked to each other via an N—C bond (see Formula 2'). In Formula 2, each of R_5 to R_8 , which are substituents of the “pyridine-based ring,” cannot simultaneously be a hydrogen. That is, at least one of R_5 to R_8 , which are substituents of the “pyridine-based ring” in Formula 2, is a substituent that is not a hydrogen. Accordingly, in the organometallic compound represented by Formula 1, stability due to electrons in a lowest unoccupied molecular orbital (LUMO) level may improve, and thus, the organometallic compound represented by Formula 1 may have excellent electrochemical stability. Thus, an organic light-emitting device including the organometallic compound represented by Formula 1 has high-purity blue emission, in addition to high efficiency, high brightness, and long lifespan.

Formula 2'

31



32

For example, the organometallic compound represented by Formula 1 enables emission of deep blue light which has a maximum emission wavelength of about 435 nanometers (nm) to about 500 nm, the x color coordinate of about 0.14 to about 0.20 (for example, in a range of about 0.14 to about 0.18) and the y color coordinate of about 0.10 to about 0.30 (for example, in a range of about 0.15 to about 0.25).

The highest occupied molecular orbital (HOMO), LUMO, singlet (S_1) energy level, and triplet (T_1) energy level of each of Compounds 1 to 33 were evaluated according to DFT method using Gaussian program (structural optimization was performed at B3LYP, 6-31G(d,p) levels), and the evaluation results are shown in Table 1 below.

33

TABLE 1

Compound No.	HOMO (eV)	LUMO (eV)	S_1 energy level (eV)	T_1 energy level (eV)
1	-5.26	-1.52	2.84	2.76
2	-5.23	-1.78	2.76	2.70
3	-5.16	-1.51	2.83	2.75
4	-5.22	-1.47	2.84	2.77
5	-5.54	-1.79	2.96	2.86
6	-5.74	-2.06	2.89	2.83
7	-5.15	-1.25	3.25	2.94
8	-5.70	-1.67	3.40	2.94
9	-5.90	-1.86	3.40	3.01
10	-5.91	-1.86	3.42	2.87
11	-5.79	-1.58	3.53	2.85
12	-5.28	-1.79	2.94	2.79
13	-5.27	-1.64	3.06	2.86
14	-5.27	-1.60	3.11	2.87
15	-5.20	-1.72	2.93	2.78
16	-5.19	-1.58	3.05	2.86
17	-5.19	-1.50	3.11	2.90
18	-5.19	-1.47	3.08	2.84
19	-5.14	-1.43	3.08	2.84

TABLE 1-continued

Compound No.	HOMO (eV)	LUMO (eV)	S ₁ energy level (eV)	T ₁ energy level (eV)
20	-5.13	-1.42	3.08	2.84
21	-5.52	-1.78	3.14	2.89
22	-5.47	-1.74	3.14	2.96
23	-5.46	-1.73	3.14	2.96
24	-5.28	-1.92	2.85	2.72
25	-5.20	-1.86	2.83	2.70
26	-5.18	-1.84	2.83	2.70
27	-5.44	-2.03	2.92	2.77
28	-5.40	-2.00	2.91	2.76
29	-5.39	-1.99	2.91	2.76
30	-5.13	-1.29	3.22	2.97
31	-5.11	-1.27	3.22	3.01
32	-5.25	-1.48	3.13	2.89
33	-5.21	-1.40	3.17	2.97

Referring to Table 1, it is confirmed that Compounds 1 to 33 have HOMO, LUMO, S₁ energy levels and T₁ energy level that are suitable for use as a material for an organic light-emitting device. Accordingly, the organometallic compound represented by Formula 1 has electric characteristics that are suitable for use as a material for an organic light-emitting device.

Synthesis methods of the organometallic compound represented by Formula 1 may be apparent to one of ordinary skill in the art by referring to Synthesis Examples provided below.

The organometallic compound represented by Formula 1 is suitable for use in an organic layer of an organic light-emitting device, for example, for use as a dopant in an emission layer of the organic layer. Thus, another aspect provides an organic light-emitting device that includes:

a first electrode;

a second electrode; and

an organic layer that is disposed between the first electrode and the second electrode,

wherein the organic layer including an emission layer and at least one of the organometallic compound represented by Formula 1.

The organic light-emitting device may have, due to the inclusion of an organic layer including the organometallic compound represented by Formula 1, low driving voltage, high efficiency, high brightness, and long lifespan. An organic light-emitting device including the organometallic compound represented by Formula 1 enables emission of deep blue light which has a maximum emission wavelength of about 435 nm to about 500 nm, the x color coordinate of about 0.14 to about 0.20 (for example, in a range of about 0.14 to about 0.18) and the y color coordinate of about 0.10 to about 0.25 (for example, in a range of about 0.15 to about 0.25).

The organometallic compound of Formula 1 may be used between a pair of electrodes of an organic light-emitting device. For example, the organometallic compound represented by Formula 1 may be included in the emission layer. In this regard, the organometallic compound may act as a dopant, and the emission layer may further include a host

(that is, an amount of the organometallic compound represented by Formula 1 may be smaller than that of the host).

The expression “(an organic layer) includes at least one organometallic compounds” used herein may include a case in which “(an organic layer) includes identical organometallic compounds of Formula 1 and a case in which (an organic layer) includes two or more different organometallic compounds of Formula 1.

For example, the organic layer may include, as the organometallic compound, only Compound 1. In this regard, Compound 1 may be situated in an emission layer of the organic light-emitting device. In some embodiments, the organic layer may include, as the organometallic compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may be situated in an identical layer (for example, Compound 1 and Compound 2 all may be situated in an emission layer).

The first electrode may be an anode, which is a hole injection electrode, and the second electrode may be a cathode, which is an electron injection electrode, or the first electrode may be a cathode, which is an electron injection electrode, or the second electrode may be an anode, which is a hole injection electrode.

For example, the first electrode may be an anode, and the second electrode may be a cathode, and the organic layer may include

i) a hole transport region that is disposed between the first electrode and the emission layer, wherein the hole transport region includes at least one of a hole injection layer, a hole transport layer, and an electron blocking layer, and

ii) an electron transport region that is disposed between the emission layer and the second electrode, wherein the electron transport region includes at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

The term “organic layer” used herein refers to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of an organic light-emitting device. The “organic layer” may include, in addition to an organic compound, an organometallic complex including metal.

FIG. 1 is a schematic view of an organic light-emitting device 10 according to an embodiment. Hereinafter, the structure of an organic light-emitting device according to an embodiment and a method of manufacturing an organic light-emitting device according to an embodiment will be described in connection with FIG. 1. The organic light-emitting device 10 includes a first electrode 11, an organic layer 15, and a second electrode 19, which are sequentially stacked.

A substrate may be additionally disposed under the first electrode 11 or above the second electrode 19. For use as the substrate, any substrate that is used in general organic light-emitting devices may be used, and the substrate may be a glass substrate or transparent plastic substrate, each with excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water repellency.

The first electrode 11 may be formed by depositing or sputtering a material for forming the first electrode on the substrate. The first electrode 11 may be an anode. The material for the first electrode 11 may be selected from

61

materials with a high work function to make holes be easily injected. The first electrode **11** may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. The material for the first electrode **11** may be indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), zinc oxide (ZnO), or the like. In some embodiments, magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be used.

The first electrode **11** may have a single-layer structure or a multi-layer structure including two or more layers. For example, the first electrode **11** may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode **11** is not limited thereto.

The organic layer **15** is disposed on the first electrode **11**.

The organic layer **15** may include a hole transport region, an emission layer, and an electron transport region.

The hole transport region may be disposed between the first electrode **11** and the emission layer.

The hole transport region may include at least one of a hole injection layer, a hole transport layer, an electron blocking layer, and a buffer layer.

The hole transport region may include only either a hole injection layer or a hole transport layer. The hole injection layer may have a single-layer structure or a multi-layer structure. For example, the hole transport region may have a structure of hole injection layer/hole transport layer, a structure of hole injection layer/hole transport layer/electron blocking layer, and a structure of first hole injection layer/second hole injection layer/electron blocking layer, each stacked in this stated order on the first electrode **11**, but the structure of the hole transport region is not limited thereto.

When the hole transport region includes a hole injection layer (HIL), the hole injection layer may be formed on the first electrode **11** by using various methods, such as vacuum deposition, spin coating, casting, or Langmuir-Blodgett (LB).

When a hole injection layer is formed by vacuum deposition, the deposition conditions may vary according to a material that is used to form the hole injection layer, and the structure and thermal characteristics of the hole injection layer. For example, the deposition conditions may include a deposition temperature of about 100 to about 500° C., a vacuum pressure of about 10⁻⁸ to about 10⁻³ torr, and a deposition rate of about 0.01 to about 100 Å/sec. However, the deposition conditions are not limited thereto.


When the hole injection layer is formed using spin coating, coating conditions may vary according to the material used to form the hole injection layer, and the structure and thermal properties of the hole injection layer. For example, a coating speed may be from about 2,000 revolutions per minute (rpm) to about 5,000 rpm, and a temperature at which a heat treatment is performed to remove a solvent after coating may be from about 80° C. to about 200° C. However, the coating conditions are not limited thereto.

Conditions for a hole transport layer and an electron blocking layer may be understood by referring to conditions for forming the hole injection layer.


62

The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB, β-NPB, TPD, Spiro-TPD, Spiro-NPB, methylated NPB, TAPC, HMTPD, 4,4',4"-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201 below, and a compound represented by Formula 202 below:

m-MTDATA




TDATA



63

-continued

2-TNATA



5


10

15

20

25


NPB



30

35

40


 β -NPB

45

50

55

TPD




60

65

64

-continued

Spiro-TPD




15

20

25

Spiro-NPB




30

35

40

methylated NPB




45

50

55


TAPC



60

65


HMTPD




65

-continued

Formula 201



Formula 202



Ar₁₀₁ to Ar₁₀₂ in Formula 201 may be each independently selected from

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, and a pentacenylene group; and

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, and a pentacenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

In Formula 201, xa and xb may be each independently an integer of 0 to 5, for example 0, 1, or 2. For example, xa may be 1 and xb may be 0, but they are not limited thereto.

66

R₁₀₁ to R₁₀₈, R₁₁₁ to R₁₁₉ and R₁₂₁ to R₁₂₄ in Formulae 201 and 202 may be each independently selected from

a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group (for example, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, and so on), and a C₁-C₁₀ alkoxy group (for example, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, or a pentoxy group);

a C₁-C₁ alkyl group and a C₁-C₁₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, and a phosphoric acid or a salt thereof;

a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, and a pyrenyl group; and

a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, and a pyrenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, or a C₁-C₁₀ alkoxy group, but they are not limited thereto.


R₁₀₉ in Formula 201 may be selected from

a phenyl group, a naphthyl group, an anthracenyl group and a pyridinyl group; and

a phenyl group, a naphthyl group, an anthracenyl group and a pyridinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group.

According to an embodiment, the compound represented by Formula 201 may be represented by Formula 201A, but is not limited thereto:


Formula 201A



67

R₁₀₁, R₁₁₁, R₁₁₂, and R₁₀₉ in Formula 201A may be understood by referring to the description provided herein.

For example, the compound represented by Formula 201, and the compound represented by Formula 202 may include compounds HT1 to HT20 illustrated below, but are not limited thereto.



HT1

5

10

15

20

25

30

35

40

HT2


45

50

55


60

65


**68**

-continued

HT3




HT4



69

-continued

HT5



70

-continued

HT7


5

10

15

20

25



HT8


30

35

40

HT6

45





HT9

50

55

60


65



71


-continued

HT10


**72**

-continued


HT12




HT13




HT14



HT11




HT15







73

-continued



74

-continued




A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes a hole injection layer and a hole transport layer, the thickness of the hole injection layer may be in a range of about 100 Å to about 10,000 Å, and for example, about 100 Å to about 1,000 Å, and the thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, and for example, about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.


For example, the hole transport region may include a first hole injection layer and a second hole injection layer, and the second hole injection layer may include the electron-generation material alone or together with other materials.

The charge-generation material may be, for example, a p-dopant. The p-dopant may be one of a quinone derivative, a metal oxide, and a cyano group-containing compound, but is not limited thereto. Non-limiting examples of the p-dopant are a quinone derivative, such as tetracyanoquinonodimethane (TCNQ) or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonodimethane (F4-TCNQ); a metal oxide, such as a tungsten oxide or a molybdenum oxide; and a cyano group-containing compound, such as Compound HT-D1 or Compound HT-D2 below, but are not limited thereto.




75

-continued



F4-TCNQ



Compound HT-D2

The hole transport region may include a buffer layer.


Also, the buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, and thus, efficiency of a formed organic light-emitting device may be improved.

Then, an emission layer (EML) may be formed on the hole transport region by vacuum deposition, spin coating, casting, LB deposition, or the like. When the emission layer is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied to form the hole injection layer although the deposition or coating conditions may vary according to the material that is used to form the emission layer.

The emission layer may include a host and a dopant, and the dopant may include the organometallic compound represented by Formula 1.

The host may be any known host. The host may include, for example, identical compounds or two different compounds.


For example, the host may be CBP, CDBP, TCP, or mCP, but is not limited thereto.




CBP

76


-continued



CDBP



TCP



mCP

When the organic light-emitting device is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and a blue emission layer. According to another embodiment, due to a stacked structure including a red emission layer, a green emission layer, and/or a blue emission layer, the emission layer may emit white light.

When the emission layer includes a host and a dopant, an amount of the dopant may be in a range of about 0.01 to about 15 parts by weight based on 100 parts by weight of the host, but is not limited thereto.

A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.

Then, an electron transport region may be disposed on the emission layer.



The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

For example, the electron transport region may have a structure of hole blocking layer/electron transport layer/electron injection layer or a structure of electron transport layer/electron injection layer, but the structure of the electron transport region is not limited thereto. The electron transport layer may have a single-layered structure or a multi-layer structure including two or more different materials.

77



Conditions for forming the hole blocking layer, the electron transport layer, and the electron injection layer which constitute the electron transport region may be understood by referring to the conditions for forming the hole injection layer.

When the electron transport layer includes a hole blocking layer, the hole blocking layer may include, for example, at least one of BCP and Bphen, but may also include other materials.



A thickness of the hole blocking layer may be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thickness of the hole blocking layer is within these ranges, the hole blocking layer may have improved hole blocking ability without a substantial increase in driving voltage.


The electron transport layer may further include at least one selected from BCP, Bphen, Alq₃, Balq, TAZ, and NTAZ.




78

-continued

TAZ




NTAZ




In some embodiments, the electron transport layer may include at least one selected from ET1 and ET19, but are not limited thereto.

ET1




ET2



79

-continued




80



-continued

ET3

ET6





ET4







ET5

ET8






81

-continued




**82**

-continued



83

-continued




84

-continued

ET16

ET19




20 A thickness of the electron transport layer may be in a
 range of about 100 Å to about 1,000 Å, for example, about
 150 Å to about 500 Å. When the thickness of the electron
 transport layer is within the range described above, the
 electron transport layer may have satisfactory electron trans-
 port characteristics without a substantial increase in driving
 voltage.

Also, the electron transport layer may further include, in
 addition to the materials described above, a metal-contain-
 ing material.

The metal-containing material may include a Li complex.
 The Li complex may include, for example, Compound
 ET-D1 (lithium quinolate, LiQ) or ET-D2.

35

ET-D1




40

ET-D2

ET18

45



50

The electron transport region may include an electron
 injection layer (EIL) that allows electrons to be easily
 provided from a second electrode 19.

The electron injection layer may include at least one
 selected from, LiF, NaCl, CsF, Li₂O, BaO, and LiQ.

A thickness of the electron injection layer may be in a
 range of about 1 Å to about 100 Å, about 3 Å to about 90
 Å. When the thickness of the electron injection layer is
 within the range described above, the electron injection layer
 may have satisfactory electron injection characteristics with-
 out a substantial increase in driving voltage.

The second electrode 19 is disposed on the organic layer
 15. The second electrode 19 may be a cathode. A material for
 forming the second electrode 19 may be selected from metal,

an alloy, an electrically conductive compound, and a combination thereof, which have a relatively low work function. For example, lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be used as a material for forming the second electrode 19. To manufacture a top emission type light-emitting device, a transmissive electrode formed using ITO or IZO may be used as the second electrode 19.

Hereinbefore, the organic light-emitting device has been described with reference to FIG. 1, but is not limited thereto.

A C₁-C₆₀ alkyl group used herein refers to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms. Detailed examples thereof are a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. A C₁-C₆₀ alkylene group used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

A C₁-C₆₀ alkoxy group used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group). Detailed examples thereof are a methoxy group, an ethoxy group, and an isopropoxy group.

A C₂-C₆₀ alkenyl group used herein refers to a hydrocarbon group formed by substituting at least one carbon double bond in the middle or at the terminal of the C₂-C₆₀ alkyl group. Detailed examples thereof are an ethenyl group, a propenyl group, and a butenyl group. A C₂-C₆₀ alkenylene group used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

A C₂-C₆₀ alkynyl group used herein refers to a hydrocarbon group formed by substituting at least one carbon triple bond in the middle or at the terminal of the C₂-C₆₀ alkyl group. Detailed examples thereof are an ethynyl group, and a propynyl group. A C₂-C₆₀ alkynylene group used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

A C₃-C₁₀ cycloalkyl group used herein refers to a monovalent hydrocarbon monocyclic group having 3 to 10 carbon atoms. Detailed examples thereof are a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. A C₃-C₁₀ cycloalkylene group used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

A C₂-C₁₀ heterocycloalkyl group used herein refers to a monovalent monocyclic group having at least one hetero atom selected from N, O, P, and S as a ring-forming atom and 2 to 10 carbon atoms. Detailed examples thereof are a tetrahydrofuranyl group, and a tetrahydrothiophenyl group. A C₂-C₁₀ heterocycloalkylene group used herein refers to a divalent group having the same structure as the C₂-C₁₀ heterocycloalkyl group.

A C₃-C₁₀ cycloalkenyl group used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one double bond in the ring thereof and does not have aromaticity. Detailed examples thereof are a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. A C₃-C₁₀ cycloalkenylene group used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

A C₂-C₁₀ heterocycloalkenyl group used herein refers to a monovalent monocyclic group that has at least one hetero atom selected from N, O, P, and S as a ring-forming atom, 2 to 10 carbon atoms, and at least one double bond in its ring. Detailed examples of the C₂-C₁₀ heterocycloalkenyl group are a 2,3-dihydrofuranyl group and a 2,3-dihydrothiophenyl group. A C₂-C₁₀ heterocycloalkenylene group used herein

refers to a divalent group having the same structure as the C₂-C₁₀ heterocycloalkenyl group.

A C₆-C₆₀ aryl group used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C₆-C₆₀ arylene group used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Detailed examples of the C₆-C₆₀ aryl group are a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

A C₂-C₆₀ heteroaryl group used herein refers to a monovalent group having a carbocyclic aromatic system that has at least one hetero atom selected from N, O, P, and S as a ring-forming atom, and 2 to 60 carbon atoms. A C₂-C₆₀ heteroarylene group used herein refers to a divalent group having a carbocyclic aromatic system that has at least one hetero atom selected from N, O, P, and S as a ring-forming atom, and 2 to 60 carbon atoms. Examples of the C₂-C₆₀ heteroaryl group are a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₂-C₆₀ heteroaryl group and the C₂-C₆₀ heteroarylene group each include two or more rings, the rings may be fused to each other.

A C₆-C₆₀ aryloxy group used herein indicates —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and a C₆-C₆₀ arylthio group used herein indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

A monovalent non-aromatic condensed polycyclic group used herein refers to a monovalent group (for example, having 8 to 60 carbon atoms) that has two or more rings condensed to each other, only carbon atoms as ring forming atoms, wherein the molecular structure as a whole is non-aromatic in the entire molecular structure. A detailed example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. A divalent non-aromatic condensed polycyclic group used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

A monovalent non-aromatic condensed heteropolycyclic group used herein refers to a monovalent group (for example, having 2 to 60 carbon atoms) that has two or more rings condensed to each other, has a heteroatom selected from N, O, P, and S, other than carbon atoms, as ring forming atoms, wherein the molecular structure as a whole is non-aromatic in the entire molecular structure. An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. A divalent non-aromatic condensed heteropolycyclic group used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

At least one of substituents of the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₂-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₂-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino

group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and

$$-\text{N}(\text{Q}_{31})(\text{Q}_{32}), \quad -\text{Si}(\text{Q}_{33})(\text{Q}_{34})(\text{Q}_{35}), \quad \text{and} \quad -\text{B}(\text{Q}_{36})(\text{Q}_{37}),$$

wherein Q_1 to Q_7 , Q_{11} to Q_{17} , Q_{21} to Q_{27} , and Q_{31} to Q_{37} may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_2 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_2 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

For example, at least one of substituents of the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group,

the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₂-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₂-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, and a C_1-C_{60} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazoyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl

group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuran-
 5 nyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophe-
 10 nyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

a phenyl group, a pentalenyl group, an indenyl group, a
 15 naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-
 fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl
 20 group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl
 25 group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a
 30 naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuran-
 35 nyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophe-
 40 nyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a
 45 salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an
 50 indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-
 fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl
 55 group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl
 60 group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a
 65 naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenan-

thridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuran-
 nyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophe-
 nyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and

—N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), and —B(Q₃₆)(Q₃₇),

wherein Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇ and Q₃₁ to Q₃₇ may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-
 fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl
 20 group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a
 30 naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuran-
 35 nyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophe-
 40 nyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group.
 45

Hereinafter, a compound and an organic light-emitting device according to embodiments are described in detail with reference to Synthesis Example and Examples. However, the organic light-emitting device is not limited thereto. The wording "B was used instead of A" used in describing Synthesis Examples means that a molar equivalent of A was identical to a molar equivalent of B.


91

EXAMPLES

Synthesis Example 1

Synthesis of Intermediate A-1

Intermediate A-1 was synthesized as shown in Reaction Scheme 1.



Synthesis of Intermediate A-2

Intermediate A-3 (25 g), phenyl boronic acid (10.74 g), Pd(PPh₃)₄ (3.05 g), K₂CO₃ (24.3 g), and THF (333 mL), and distilled water (166 mL) were all placed in a 1 L reaction container, and then refluxed under nitrogen for 12 hours. When the reaction stopped, the result was cooled to room temperature, and then, an aqueous layer was removed, and an organic layer collected was washed once with 5% brine (500 mL) and once with distilled water (500 mL). The resultant organic layer was dried with MgSO₄, and then, a solvent was removed therefrom, and then, the result was refined by silica gel column chromatography using a mixed solvent including ethyl acetate (EA) and n-hexane (at a ratio of 3:97) solvent to obtain Intermediate A-2 (12.4 g).

LC-MS (m/z): 233.98 [M+1]

92

Synthesis of Intermediate A-1

Intermediate A-2 (10 g), benzimidazole (5 g), KOt-Bu (6.7 g), CuI (0.4 g), benzotriazole (0.5 g), and dimethylsulfoxide (50 mL) were all placed in a 100 mL reaction container, and then, refluxed under nitrogen for 12 hours. When the reaction stopped, the result was cooled to room temperature, and then, ethyl acetate (1 L) and 0.1 N HCl aqueous solution (1 L) were added thereto, and then, an organic layer was isolated and washed with 5% brine (1 L). The resultant organic layer was dried with MgSO₄, and then, a solvent was removed therefrom, and then, the result was refined by silica gel column chromatography using a mixed solvent including EA and n-hexane (at a ratio of 50:50) solvent to obtain Intermediate A-1 (4.98 g).

LC-MS (m/z): 272.21 [M+1]

Synthesis Example 2

Synthesis of Intermediate B-1

Synthesis of Intermediate B-2

Intermediate B-2 was synthesized in the same manner as used to synthesize Intermediate A-2 in Synthesis Example 1, except that Intermediate B-3 shown in Table 2 was used instead of Intermediate A-3. The synthesis yield and MS data of Intermediate B-2 are shown in Table 2.

Synthesis of Intermediate B-1

Intermediate B-1 was synthesized in the same manner as used to synthesize Intermediate A-1 in Synthesis Example 1, except that Intermediate B-2 was used instead of Intermediate A-2. The synthesis yield and MS data of Intermediate B-1 are shown in Table 2.

Synthesis Example 3

Synthesis of Intermediate C-1

Synthesis of Intermediate C-2

Intermediate C-2 was synthesized in the same manner as used to synthesize Intermediate A-2 in Synthesis Example 1, except that Intermediate C-3 shown in Table 2 was used instead of Intermediate A-3. The synthesis yield and MS data of Intermediate C-2 are shown in Table 2.

Synthesis of Intermediate C-1

Intermediate C-1 was synthesized in the same manner as used to synthesize Intermediate A-1 in Synthesis Example 1, except that Intermediate C-2 was used instead of Intermediate A-2. The synthesis yield and MS data of Intermediate C-1 are shown in Table 2.

Synthesis Example 4

Synthesis of Intermediate D-1


Intermediate D-1 was synthesized in the same manner as used to synthesize Intermediate A-1 in Synthesis Example 1, except that in synthesizing A-1, Intermediate D-2 was used instead of Intermediate A-2. The synthesis yield and MS data of Intermediate D-1 are shown in Table 2.

93

Synthesis Example 5

Synthesis of Compound 1

Compound 1 was synthesized as shown in Reaction Scheme 2.



94

Synthesis of Intermediate E-2

$\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ (18.7 g), E-3 (30 g), 2-ethoxyethanol (225 mL), and distilled water (75 mL) were all placed in a 1 L reaction container, and then, refluxed under nitrogen for 12 hours. When the reaction stopped, the result was cooled to room temperature. Then, distilled water (750 mL) was added to the reaction container and a solid produced was filtered, followed by being washed with distilled water (1 L), and then vacuum dried at a temperature of 60° C. for 12 hours to prepare Intermediate E-2 (23.7 g).

MALDI-TOF (m/z): 1216.05 [M] $^+$

Synthesis of Intermediate E-1

Intermediate E-2 (23 g), AgCF_3SO_3 (10.2 g), and acetonitrile (500 mL) were all placed in a 1 L reaction container, and then under nitrogen, refluxed for 12 hours. When the reaction stopped, the result was cooled to room temperature, and then, celite filtration was performed thereon to concentrate the residual filtrate, which was then vacuum dried for 12 hours to obtain Intermediate E-1 (27.3 g).

MALDI-TOF (m/z): 573.06 [$\text{M}-2\text{ACN}, -\text{Otf}$] $^+$

Synthesis of Compound 1

Intermediate E-1 (5 g), Intermediate A-1 (4.2 g), and 2-ethoxyethanol (150 mL) were all placed in a 500 mL reaction container, and then, under nitrogen, refluxed for 12 hours. When the reaction stopped, the result was cooled to room temperature, and then, distilled water (300 mL) was added thereto, and a solid produced was filtered, and washed with distilled water (200 mL). The resultant solid was dried and then refined by silica gel chromatography using a mixed solvent including dichloromethane and methanol (at a ratio of 90 to 10) to obtain Compound 1 (2.6 g).

MALDI-TOF (m/z): 843.16 [M] $^+$

Synthesis Example 6

Synthesis of Compound 2

Compound 2 was synthesized in the same manner as in Synthesis Example 5, except that in synthesizing Compound 1, Intermediate B-1 shown in Table 2 was used instead of Intermediate A-1. The synthesis yield and MS data of Compound 2 are shown in Table 2.

95

Synthesis Example 7

Synthesis of Compound 3

Compound 3 was synthesized in the same manner as in Synthesis Example 5, except that in synthesizing Compound 1, Intermediate C-1 shown in Table 2 was used instead of Intermediate A-1. The synthesis yield and MS data of Compound 3 are shown in Table 2.

Synthesis Example 8

Synthesis of Compound 4

Compound 4 was synthesized in the same manner as in Synthesis Example 5, except that in synthesizing Compound 1, Intermediate D-1 shown in Table 2 was used instead of Intermediate A-1. The synthesis yield and MS data of Compound 4 are shown in Table 3.

Synthesis Example 9

Synthesis of Compound 5

Compound 5 was synthesized in the same manner as in Synthesis Example 5, except that Intermediate F-3 shown in Table 2 was used instead of Intermediate E-3. The synthesis yield and MS data of Compound 5 are shown in Table 2.

Synthesis Example 10

Synthesis of Compound 6


Compound 6 was synthesized in the same manner as in Synthesis Example 5, except that Intermediate G-3 shown in Table 2 was used instead of Intermediate E-3. The synthesis yield and MS data of Compound 6 are shown in Table 2.

96

Synthesis Example 11

Synthesis of Compound 7

Compound 7 was synthesized as shown in Reaction Scheme 3.



$\text{Ir}(\text{COD})_2\text{BF}_4$ (4.0 g), Intermediate D-1 (10.14 g), and 1,2-propanediol (150 mL) were all placed in a 500 mL reaction container, and then, under nitrogen, refluxed for 12 hours. When the reaction stopped, the result was cooled to room temperature, and then, distilled water (300 mL) was added thereto, and a solid produced was filtered, and washed with distilled water (1 L). The resultant solid was dried, and then refined by silica gel chromatography using a mixed solvent including dichloromethane and methanol (at a ratio of 90 to 10) to obtain Compound 7 (2.4 g).

MALDI-TOF (m/z): 943.37 $[\text{M}]^+$

TABLE 2

Reactant	Product	Yield of product (%)	MS (m/z) of product
A-3	A-2	60	233.98

TABLE 2-continued











Reactant	Product	Yield of product (%)	MS (m/z) of product
 B-3	 B-2	66	233.98
 C-3	 C-2	56	233.98
 A-2	 A-1	43	272.11
 B-2	 B-1	36	272.11
 C-2	 C-1	25	272.11

TABLE 2-continued









Reactant	Product	Yield of product (%)	MS (m/z) of product
 D-2	 D-1	56	252.14
 E-3	 E-2	62	1216.05
 F-3	 F-2	72	1220.03
 G-3	 G-2	52	1316.03

TABLE 2-continued








Reactant	Product	Yield of product (%)	MS (m/z) of product
 E-2	 E-1	89	573.06
 F-2	 F-1	85	575.05
 G-2	 G-1	83	623.05
E1 + A1	 Compound 1	50	843.16

TABLE 2-continued







Reactant	Product	Yield of product (%)	MS (m/z) of product
E1 + B1	 Compound 2	48	843.16
E1 + C1	 Compound 3	38	843.16
E1 + D1	 Compound 4	56	823.19
F1 + A1	 Compound 5	33	845.15

TABLE 2-continued

Reactant	Product	Yield of product (%)	MS (m/z) of product
G1 + A1	 Compound 6	49	893.15
D-1	 Compound 7	32	943.37

Evaluation Example 1

Photoluminescence (PL) Spectrum and Color Purity Evaluation

Compound 1 was diluted at a concentration of 10 mM in toluene, and PL of Compound 1 in solution was measured by using an ISC PC1 spectrofluorometer equipped with a xenon lamp. This experiment was performed on Compounds 2 to 7, and PL spectra of Compounds 1 to 7 were evaluated and results thereof are shown in Table 3.

PMMA in CH₂Cl₂ solution and 8 percent by weight (wt %) of Compound 1 were mixed, and the obtained mixture was coated on a quartz substrate by using a spin coater, and then heat treated in an oven at a temperature of 80° C., and cooled to room temperature to obtain a film. Color-coordination-in-film of Compound 1 was evaluated using a Hamamatsu photonics absolute PL quantum yield measurement system that is equipped with a xenon light source, a monochromator, a photonic multichannel analyzer, and an integrating sphere, and uses PLQY measurement software (Hamamatsu Photonics, Ltd., Shizuoka, Japan). This experiment was performed on Compounds 2 to 7, and results thereof are shown in Table 3.

TABLE 3

Compound No.	1 st & 2 nd PL _{max} (nm)	CIE _{x,y}	Half width (nm)
1	458, 481	(0.15, 0.25)	70
2	454, 480	(0.15, 0.23)	64
3	452, 480	(0.15, 0.22)	62
4	452, 477	(0.14, 0.20)	70
5	441, 469	(0.15, 0.15)	61
6	444, 471	(0.15, 0.18)	70
7	467	(0.18, 0.23)	119

From Table 3, it was confirmed that Compounds 1 to 7 have excellent luminescent characteristics.

Evaluation Example 2

Evaluation on HOMO, LUMO, and Triplets (T1) Energy Levels of Synthesized Compounds

HOMO, LUMO and T1 energy levels of Compounds 1 to 7 were evaluated according to the method indicated in Table 4, and results thereof are shown in Table 5.

TABLE 4

HOMO energy level evaluation method	Each compound was diluted at a concentration of 1×10^{-5} M in CHCl_3 , and an UV absorption spectrum thereof was measured at room temperature by using a Shimadzu UV-350 spectrometer, and a HOMO energy level thereof was calculated by using an optical band gap (Eg) from an edge of the absorption spectrum.
LUMO energy level evaluation method	A potential (V)-current (A) graph of each compound was obtained by using cyclic voltammetry (CV) (electrolyte: 0.1M Bu_4NClO_4 /solvent: CH_2Cl_2 /electrode: 3 electrode system (working electrode: GC, reference electrode: Ag/AgCl, auxiliary electrode: Pt)), and then, from reduction onset of the graph, a LUMO energy level of the compound was calculated.
T1 energy level evaluation method	A mixture (each compound was dissolved in an amount of 1 mg in 3 cc of toluene) of toluene and each compound was loaded into a quartz cell, and then, the resultant quartz cell was loaded into liquid nitrogen (77K) and a photoluminescence spectrum thereof was measured by using a device for measuring photoluminescence, and the obtained spectrum was compared with a photoluminescence spectrum measured at room temperature, and peaks observed only at low temperature were analyzed to calculate T1 energy levels.

TABLE 5

Compound No.	HOMO (eV) (calc.)	LUMO (eV) (calc.)	T1 energy level (eV)
1	-5.94	-2.97	2.71
2	-5.92	-3.15	2.73
3	-5.93	-3.05	2.71
4	-5.92	-2.84	2.73
5	-6.05	-2.95	2.81
6	-6.11	-3.02	2.80
7	-5.93	-2.82	2.70

From Table 5, it was confirmed that Compounds 1 to 7 have electric characteristics that are suitable for use as a material for forming an organic light-emitting device.

Evaluation Example 3

Thermal Characteristics Evaluation of Synthesized Compounds

Each of Compounds 1 to 7 was subjected to thermal analysis (N_2 atmosphere, temperature range: room temperature to 800°C . ($10^\circ\text{C}/\text{min}$)-TGA, room temperature to 400°C .-DSC, Pan Type: Pt Pan in disposable Al Pan(TGA), disposable Al pan(DSC)) using thermo gravimetric analysis (TGA) and differential scanning calorimetry (DSC), and obtained results are shown in Table 6 below. As shown in Table 6, it was confirmed that the synthesized compounds had excellent thermal stability.

TABLE 6

Compound No.	Td (1%) ($^\circ\text{C}$.)
1	364
2	369
3	362
4	351
5	366
6	362
7	363

Example 1

A glass substrate with a 1,500 Å-thick ITO (indium tin oxide) electrode (first electrode, anode) formed thereon was washed with distilled water and sonicated with ultrasonic waves. When the washing with distilled water was com-

pleted, sonication washing was performed using a solvent, such as isopropyl alcohol, acetone, or methanol. The result was dried and then transferred to a plasma washer, and the resultant substrate was washed with oxygen plasma for 5 minutes and then, transferred to a vacuum depositing device.

Compound HT3 was vacuum deposited on the ITO electrode on the glass substrate to form a first hole injection layer having a thickness of 3,500 Å, and then, Compound HT-D1 was vacuum deposited on the first hole injection layer to form a second hole injection layer having a thickness of 300 Å, and TAPC was vacuum deposited on the second hole injection layer to form an electron blocking layer having a thickness of 100 Å, thereby completing the formation of a hole transport region.

mCP (host) and Compound 1 (dopant, 7 wt %) were co-deposited on the hole transport region to form an emission layer having a thickness of 300 Å.

Compound ET3 was vacuum deposited on the emission layer to form an electron transport layer having a thickness of 250 Å, and then, ET-D1 (Liq) was deposited on the electron transport layer to form an electron injection layer having a thickness of 5 Å, and an Al second electrode (cathode) having a thickness of 1,000 Å was formed on the electron injection layer, thereby completing manufacturing of an organic light-emitting device.

Example 2

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an emission layer, as a dopant, Compound 2 was used instead of Compound 1.

Example 3

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an emission layer, as a dopant, Compound 3 was used instead of Compound 1.

Example 4

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an emission layer, as a dopant, Compound 4 was used instead of Compound 1.

109

Example 5

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an emission layer, as a dopant, Compound 5 was used instead of Compound 1.

Example 6


An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an emission layer, as a dopant, Compound 6 was used instead of Compound 1.

Example 7

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an emission layer, as a dopant, Compound 7 was used instead of Compound 1.

Comparative Example 1

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an emission layer, as a dopant, Compound A was used instead of Compound 1.




110

Comparative Example 2

An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an emission layer, as a dopant, Compound B was used instead of Compound 1.

Compound B



Evaluation Example 4

Evaluation on Characteristics of an Organic Light-Emitting Device

The current density, brightness, and luminescence efficiency, and half-lifespan according to voltage of the organic light-emitting devices manufactured according to Examples 1 to 7, and Comparative Examples 1 and 2 were measured, the measurement method is described in detail below, and results thereof are shown in Table 7. T_{80} lifespan indicates a period of time (hr) taken for the brightness to reach 80% with respect to 100% of initial brightness:

(1) Change in Current Density According to Voltage

Regarding the manufactured organic light-emitting device, a current flowing in a unit device was measured by using a current-voltage meter (Keithley 2400) while a voltage was raised from 0 volts (V) to 10 V, and the measured current value was divided by an area.

(2) Change in Brightness According to Voltage

Regarding the manufactured organic light-emitting device, brightness was measured by using Minolta Cs-1000A while a voltage was raised from 0 V to 10 V.

(3) Luminescence Efficiency Measurement

Current efficiency (candelas per ampere, cd/A) was measured at the same current density (10 milliamperes per square centimeter, mA/cm²) by using brightness, current density, and voltage measured according to (1) and (2).

TABLE 7

	Host Dopant	Driving Voltage	Current efficiency	Brightness	T_{80} Lifespan	Color coordinate	
		(V)	(cd/A)	(cd/m ²)	(hr)	CIE x	CIE y
Example 1	mCP Compound 1	6.2	16.3	500	8.2	0.15	0.24
Example 2	mCP Compound 2	6.4	18.2	500	7.1	0.15	0.22
Example 3	mCP Compound 3	6.1	15.4	500	10.1	0.15	0.21
Example 4	mCP Compound 4	6.6	13.7	500	3.2	0.15	0.20
Example 5	mCP Compound 5	6.5	10.6	500	1.2	0.14	0.15
Example 6	mCP Compound 6	6.6	11.9	500	2.8	0.15	0.17
Example 7	mCP Compound 7	6.5	13.9	500	5.6	0.16	0.24
Comparative Example 1	mCP Compound A	6.8	10.4	500	0.7	0.15	0.21
Comparative Example 2	mCP Compound B	6.6	12.1	500	0.3	0.17	0.26

111

From Table 7, it was confirmed that the organic light-emitting devices of Examples 1 to 7 had, compared to the organic light-emitting devices of Comparative Examples 1 and 2, similar color purity, low driving voltage, high current density, high brightness, and long lifespan. Although not limited to a particular theory, as shown in Table 7, the organic light-emitting devices of Examples 1 to 7 have substantially prolonged lifespan characteristics compared to the organic light-emitting devices of Comparative Examples 1 and 2. While not wanting to be bound by a theory, it is understood that when each of R_5 to R_8 in Formula 2 is not simultaneously a hydrogen (that is, R_5 to R_8 in Formula 2 include at least one substituent that is not a hydrogen), stability of a pyridine ring of Formula 2 associated with a LUMO level of the organometallic compound described above Formula 1 improves.

The organometallic compound according to embodiments has excellent electric characteristics and thermal stability. Accordingly, an organic light-emitting device including the organometallic compound may have a low driving voltage, high efficiency, high brightness, and a long lifespan.

It should be understood that the exemplary embodiments described therein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

While one or more embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present inventive concept as defined by the following claims.

What is claimed is:


1. An organic light-emitting device comprising:

a first electrode;

a second electrode; and

an organic layer disposed between the first electrode and the second electrode,

wherein the organic layer comprises an emission layer, and further comprises at least one organometallic compound represented by Formula 1:



Formula 1

wherein in Formula 1,

M is Ir;

L_1 is selected from ligands represented by Formulae 2A, 2C, and 2D;

L_2 is selected from ligands represented by Formulae 3-1 and 3-2, and is different from L_1 ;


$n1$ is 1, 2, or 3;

$n2$ is 0, 1, or 2;


when $n1$ is two or more, ligands L_1 are identical or different, and when $n2$ is two or more, L_2 are identical or different;

112


Formula 2A



Formula 2C



Formula 2D




wherein in Formulae 2A, 2C, and 2D,

R_1 to R_4 are each hydrogen,



R_5 to R_7 are each independently selected from an isobutyl group and a phenyl group; and

and each indicates a binding site to M in Formula 1;

Formula 3-1



-continued



Z_1 is hydrogen, Z_2 is $-F$,

b4 is 2;

and

*and*¹ each indicates a binding site to M in Formula 1.

2. The organic light-emitting device of claim 1, wherein
the first electrode is an anode,
the second electrode is a cathode, and
the organic layer comprises

i) a hole transport region disposed between the first electrode and the emission layer, wherein the hole transport region comprises at least one of a hole injection layer, a hole transport layer, and an electron blocking layer, and

ii) an electron transport region disposed between the emission layer and the second electrode, wherein the electron transport region comprises at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

3. The organic light-emitting device of claim 2, wherein the emission layer comprises the organometallic compound of claim 1 and a host,

wherein an amount of the organometallic compound in the emission layer is smaller than an amount of the host.

4. An organic light-emitting device comprising:

a first electrode;

a second electrode; and

an organic layer disposed between the first electrode and the second electrode wherein

the organometallic compound is one of Compounds 1 to 7:

Formula 3-2

5

10

15

Formula 4

20

25

30

35

40




45

50

55



60

65



115

-continued



116

-continued

4

5



10

5

15

20

25



* * * * *

6

7

专利名称(译)	有机金属化合物和包括其的有机发光器件		
公开(公告)号	US10256418	公开(公告)日	2019-04-09
申请号	US14/599792	申请日	2015-01-19
[标]申请(专利权)人(译)	三星电子株式会社		
申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD. 三星SDI CO. , LTD		
当前申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD. , 三星SDI CO. , LTD. ,		
[标]发明人	KIM WOOK CHAE MIYOUNG HUH DALHO KIM HYUNJUNG LEE KANGMUN LEE NAMHEON		
发明人	KIM, WOOK CHAE, MIYOUNG HUH, DALHO KIM, HYUNJUNG LEE, KANGMUN LEE, NAMHEON		
IPC分类号	H01L51/00 C07F15/00 H01L51/50		
CPC分类号	H01L51/0085 C07F15/0033 H01L51/5084 H01L51/5016 H01L51/5068 H01L51/5012		
代理机构(译)	康托科尔伯恩LLP		
优先权	1020140059303 2014-05-16 KR		
其他公开文献	US20150333278A1		
外部链接	Espacenet		

摘要(译)

由式1表示的有机金属化合物： $M(L_1)_{n1}(L_2)_{n2}$ 20032003公式1 其中在式1中，M，L₁，L₂，n₁和n₂在详述中定义。

Formula 2

