




US 20160380210A1

(19) **United States**(12) **Patent Application Publication**
KIM et al.(10) **Pub. No.: US 2016/0380210 A1**(43) **Pub. Date: Dec. 29, 2016**(54) **CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**(71) Applicants: **Samsung Electronics Co., Ltd.**,
Suwon-si (KR); **Samsung SDI Co., Ltd.**,
Yongin-si (KR)(72) Inventors: **Hyunjung KIM**, Suwon-si (KR);
Miyoung CHAE, Suwon-si (KR);
Sangmo KIM, Hwaseong-si (KR);
Soonok JEON, Seoul (KR); **Yeonsook CHUNG**,
Seoul (KR); **Yongsik JUNG**, Yongin-si (KR);
Dalho HUH, Suwon-si (KR); **Youngmok SON**,
Hwaseong-si (KR); **Namheon LEE**, Suwon-si (KR)(21) Appl. No.: **15/145,158**(22) Filed: **May 3, 2016**(30) **Foreign Application Priority Data**Jun. 23, 2015 (KR) 10-2015-0089088
Mar. 31, 2016 (KR) 10-2016-0039619**Publication Classification**(51) **Int. Cl.**
H01L 51/00 (2006.01)
C09K 11/02 (2006.01)
C07D 209/86 (2006.01)
C09K 11/06 (2006.01)(52) **U.S. Cl.**
CPC **H01L 51/0072** (2013.01); **C09K 11/06**
(2013.01); **H01L 51/009** (2013.01); **H01L**
51/0085 (2013.01); **H01L 51/008** (2013.01);
C09K 11/02 (2013.01); **C07D 209/86**
(2013.01); **H01L 51/5206** (2013.01)(57) **ABSTRACT**

A condensed cyclic compound represented by Formula 1:

Formula 1



wherein, in Formula 1, groups and variables are the same as described in the specification.





FIG. 1



CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims priority to Korean Patent Application No. 10-2015-0089088, filed on Jun. 23, 2015 in the Korean Intellectual Property Office and Korean Patent Application No. 10-2016-0039619, filed on Mar. 31, 2016 in the Korean Intellectual Property Office, and all the benefits accruing therefrom under 35 U.S.C. §119, the contents of which are incorporated herein in their entirety by reference.

BACKGROUND

[0002] 1. Field

[0003] The present disclosure relates to a condensed cyclic compound and an organic light-emitting device including the same.

[0004] 2. Description of the Related Art

[0005] Organic light-emitting devices (OLEDs) are self-emission devices that have wide viewing angles, high contrast ratios, and short response times. In addition, OLEDs exhibit high brightness, low driving voltage, and high response speed characteristics, and produce full-color images, compared to conventional organic light-emitting devices.

[0006] A typical organic light-emitting device includes an anode, a cathode, and an organic layer that is disposed between the anode and the cathode, wherein the organic layer includes an emission layer. A hole transport region may be disposed between the anode and the emission layer, and an electron transport region may be disposed between the emission layer and the cathode. Holes provided from the anode may move toward the emission layer through the hole transport region, and electrons provided from the cathode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, are recombined in the emission layer to produce excitons. These excitons change from an excited state to a ground state, thereby generating light.

[0007] Different types of organic light emitting devices are known. However, there still remains a need in OLEDs having low driving voltage, high efficiency, high brightness, and long lifespan.


SUMMARY

[0008] Provided are a novel condensed cyclic compound and an organic light-emitting device including the same.

[0009] Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented exemplary embodiments.

[0010] According to an aspect of an exemplary embodiment, a condensed cyclic compound is represented by Formula 1:

Formula 1



[0011] wherein, in Formula 1,

[0012] X_1 is N or C(R_1), X_2 is N or C(R_2), X_3 is N or C(R_3), X_4 is N or C(R_4), X_5 is N or C(R_5), X_6 is N or C(R_6), X_7 is N or C(R_7), X_8 is N or C(R_8), X_{11} is N or C(R_{11}), X_{12} is N or C(R_{12}), X_{13} is N or C(R_{13}), X_{14} is N or C(R_{14}), X_{15} is N, C(R_{15}), or a carbon atom connected to $^{*-(L_1)_{a1}-*}$, X_{16} is N, C(R_{16}), or a carbon atom connected to $^{*-(L_1)_{a1}-*}$, X_{17} is N, C(R_{17}), or a carbon atom connected to $^{*-(L_1)_{a1}-*}$, and X_{18} is N, C(R_{18}), or a carbon atom connected to $^{*-(L_1)_{a1}-*}$, wherein one of X_{15} to X_{18} is connected to $^{*-(L_1)_{a1}-*}$,

[0013] ring A_1 is selected from a C_5 - C_{60} carbocyclic group and a C_3 - C_{60} heterocyclic group including at least one heteroatom selected from O, S, and Si,

[0014] L_1 is selected from

[0015] a phenylene group, a pyridinylene group, a pyrimidinylene group, a pyrazinylene group, a pyridazinylene group, a triazinylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylene group; and

[0016] a phenylene group, a pyridinylene group, a pyrimidinylene group, a pyrazinylene group, a pyridazinylene group, a triazinylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $—Si(Q_{11})(Q_{12})(Q_{13})$,

[0017] L_2 is selected from

[0018] a phenylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylene group; and

[0019] a phenylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $—Si(Q_{11})(Q_{12})(Q_{13})$,

[0020] a_1 and a_2 are each independently an integer selected from 0 to 5, wherein when a_1 is 2 or greater, two or more groups L_1 are identical to or different from each other,

and when a_2 is 2 or greater, two or more groups L_2 are identical to or different from each other,

[0021] R_1 to R_8 , R_{11} to R_{18} , and R_{31} are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group (—CN), a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q_1)(Q_2)(Q_3),

[0022] b_1 is an integer selected from 0 to 4,

[0023] c_1 is an integer selected from 1 to 4,

[0024] at least one substituent of the substituted C_1 - C_{60} alkyl group, substituted C_2 - C_{60} alkenyl group, substituted C_2 - C_{60} alkynyl group, substituted C_1 - C_{60} alkoxy group, substituted C_3 - C_{10} cycloalkyl group, substituted C_1 - C_{10} heterocycloalkyl group, substituted C_3 - C_{10} cycloalkenyl group, substituted C_1 - C_{10} heterocycloalkenyl group, substituted C_6 - C_{60} aryl group, substituted C_6 - C_{60} aryloxy group, substituted C_6 - C_{60} arylthio group, substituted C_1 - C_{60} heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group is selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q_{21})(Q_{22})(Q_{23}),

[0025] wherein Q_1 to Q_3 , Q_{11} to Q_{13} , and Q_{21} to Q_{23} are each independently selected from a hydrogen, a deuterium, a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group

[0026] in $^*(L_1)_{a_1}$ —*, * and are each a binding site to a neighboring atom.

[0027] According to an aspect of another exemplary embodiment, an organic light-emitting device includes:

[0028] a first electrode;

[0029] a second electrode; and

[0030] an organic layer disposed between the first electrode and the second electrode,

[0031] wherein the organic layer includes an emission layer and at least one condensed cyclic compound represented by Formula 1.

BRIEF DESCRIPTION OF THE DRAWINGS

[0032] These and/or other aspects will become apparent and more readily appreciated from the following description of the exemplary embodiments, taken in conjunction with the accompanying drawing in which:

[0033] FIG. 1 is a schematic cross-sectional view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

[0034] Reference will now be made in detail to exemplary embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present exemplary embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the exemplary embodiments are merely described below, by referring to the figures, to explain aspects. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

[0035] It will be understood that when an element is referred to as being “on” another element, it can be directly in contact with the other element or intervening elements may be present therebetween. In contrast, when an element is referred to as being “directly on” another element, there are no intervening elements present.

[0036] It will be understood that, although the terms first, second, third etc. may be used herein to describe various elements, components, regions, layers, and/or sections, these elements, components, regions, layers, and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer, or section from another element, component, region, layer, or section. Thus, a first element, component, region, layer, or section discussed below could be termed a second element, component, region, layer, or section without departing from the teachings of the present embodiments.

[0037] The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, the singular forms “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

[0038] The term “or” means “and/or.” It will be further understood that the terms “comprises” and/or “comprising,” or “includes” and/or “including” when used in this specification, specify the presence of stated features, regions, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, regions, integers, steps, operations, elements, components, and/or groups thereof.


[0039] Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this general inventive concept belongs. It will

be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

[0040] “About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” can mean within one or more standard deviations, or within $\pm 30\%$, 20% , 10% , 5% of the stated value.

[0041] Exemplary embodiments are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein should not be construed as limited to the particular shapes of regions as illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated may be rounded. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the precise shape of a region and are not intended to limit the scope of the present claims.

[0042] According to one or more exemplary embodiments, a condensed cyclic compound represented by Formula 1 is provided:



[0043] In Formula 1, X_1 may be N or $C(R_1)$, X_2 may be N or $C(R_2)$, X_3 may be N or $C(R_3)$, X_4 may be N or $C(R_4)$, X_5 may be N or $C(R_5)$, X_6 may be N or $C(R_6)$, X_7 may be N or $C(R_7)$, X_8 may be N or $C(R_8)$, X_{11} may be N or $C(R_{11})$, X_{12} may be N or $C(R_{12})$, X_{13} may be N or $C(R_{13})$, X_{14} may be N or $C(R_{14})$, X_{15} may be N, $C(R_{15})$, or a carbon atom connected to $^*(L_1)_{a1}-^*$, X_{16} may be N, $C(R_{16})$, or a carbon atom connected to $^*(L_1)_{a1}-^*$, X_{17} may be N, $C(R_{17})$, or a carbon atom connected to $^*(L_1)_{a1}-^*$, and X_{18} may be N, $C(R_{18})$, or a carbon atom connected to $^*(L_1)_{a1}-^*$, wherein one of X_{15} to X_{18} may be connected to $^*(L_1)_{a1}-^*$. * and * may be each a binding site to a neighboring atom.

[0044] For example, in Formula 1, X_1 may be $C(R_1)$, X_2 may be $C(R_2)$, X_3 may be $C(R_3)$, X_4 may be $C(R_4)$, X_5 may be $C(R_5)$, X_6 may be $C(R_6)$, X_7 may be $C(R_7)$, X_8 may be N or $C(R_8)$, X_{11} may be $C(R_{11})$, X_{12} may be $C(R_{12})$, X_{13} may

be $C(R_{13})$, X_{14} may be $C(R_{14})$, X_{15} may be $C(R_{15})$ or a carbon atom connected to $^*(L_1)_{a1}-^*$, X_{16} may be $C(R_{16})$ or a carbon atom connected to $^*(L_1)_{a1}-^*$, X_{17} may be $C(R_{17})$ or a carbon atom connected to $^*(L_1)_{a1}-^*$, and X_{18} may be $C(R_{18})$ or a carbon atom connected to $^*(L_1)_{a1}-^*$, wherein one of X_{15} to X_{18} may be connected to $^*(L_1)_{a1}-^*$.

[0045] In Formula 1, ring A_1 may be selected from a C_5 - C_{60} carbocyclic group and a C_3 - C_{60} heterocyclic group that includes at least one heteroatom selected from O, S, and Si. When ring A_1 is a C_3 - C_{60} heterocyclic group, the C_3 - C_{60} heterocyclic group includes at least one heteroatom selected from O, S, and Si as a ring-forming atom. That is, for example, ring A_1 may not be a C_3 - C_{60} heterocyclic group that includes N as a ring-forming atom. For example, ring A_1 may not be a pyridine ring, a pyrimidine ring, a triazine ring, or a carbazole ring.

[0046] For example, in Formula 1, ring A_1 may be selected from a cyclopentane ring, a cyclohexane ring, a cyclopentene ring, a cyclohexene ring, a cycloheptene ring, a benzene ring, a pentalene ring, an indene ring, a naphthene ring, an azulene ring, a heptalene ring, an indacene ring, an acenaphthene ring, a fluorene ring, a spirobifluorene ring, a phenalene ring, a phenanthrene ring, an anthracene ring, a fluoranthene ring, a triphenylene ring, a pyrene ring, a chrysene ring, a naphthacene ring, a picene ring, a perylene ring, a pentaphene ring, a hexacene ring, a furane ring, a thiophene ring, a benzofurane ring, a benzothiophene ring, a dibenzofurane ring, and a dibenzothiophene ring.

[0047] According to an embodiment, in Formula 1, ring A_1 may be each independently selected from a benzene ring, a dibenzofurane ring, and a dibenzothiophene ring, but embodiments are not limited thereto.

[0048] In Formula 1, L_1 may be selected from

[0049] a phenylene group, a pyridinylene group, a pyrimidinylene group, a pyrazinylene group, a pyridazinylene group, a triazinylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylene group; and

[0050] a phenylene group, a pyridinylene group, a pyrimidinylene group, a pyrazinylene group, a pyridazinylene group, a triazinylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, and —Si(Q_{11})(Q_{12})(Q_{13}), and

[0051] L_2 may be selected from

[0052] a phenylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylene group; and

[0053] a phenylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10}

alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-\text{Si}(\text{Q}_{11})(\text{Q}_{12})(\text{Q}_{13})$.

[0054] For example, in Formula 1, L_1 may be selected from

[0055] a phenylene group, a pyridinylene group, a pyrimidinylene group, a pyrazinylene group, a pyridazinylene group, a triazinylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylylene group; and

[0056] a phenylene group, a pyridinylene group, a pyrimidinylene group, a pyrazinylene group, a pyridazinylene group, a triazinylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylylene group, each substituted with at least one selected from a deuterium, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-\text{Si}(\text{Q}_{11})(\text{Q}_{12})(\text{Q}_{13})$, and

[0057] L_2 may be selected from


[0058] a phenylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylylene group; and

[0059] a phenylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylylene group, each substituted with at least one selected from a deuterium, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-\text{Si}(\text{Q}_{11})(\text{Q}_{12})(\text{Q}_{13})$.


[0060] wherein Q_{11} to Q_{13} may be each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group.

[0061] According to an embodiment, in Formula 1, L_1 may be selected from groups represented by Formulae 3-1 to 3-56, and L_2 may be selected from groups represented by Formulae 3-1, 3-15, 3-28, and 3-41 to 3-56:


-continued




Formula 3-1




Formula 3-2




Formula 3-3




Formula 3-4




Formula 3-5




Formula 3-6




Formula 3-7




Formula 3-8




Formula 3-9




Formula 3-10




Formula 3-11




Formula 3-12




Formula 3-13














Formula 3-14



Formula 3-15



-continued



Formula 3-16

Formula 3-17

Formula 3-18

Formula 3-19

Formula 3-20

Formula 3-21

Formula 3-22










Formula 3-23

Formula 3-24

Formula 3-25

Formula 3-26

-continued



Formula 3-27

Formula 3-28

Formula 3-29

Formula 3-30

Formula 3-31










Formula 3-32

Formula 3-33

Formula 3-34

Formula 3-35

-continued



Formula 3-36

Formula 3-37

Formula 3-38

Formula 3-39

Formula 3-40










Formula 3-41

Formula 3-42

Formula 3-43

Formula 3-44

-continued



Formula 3-45

Formula 3-46

Formula 3-47

Formula 3-48

Formula 3-49


Formula 3-50

Formula 3-51


Formula 3-52

Formula 3-53


-continued



Formula 3-54



Formula 3-55



Formula 3-56

[0062] In Formulae 3-1 to 3-56,

[0063] Y_1 may be selected from O, S, and $C(Z_3)(Z_4)$,

[0064] Z_1 to Z_4 may be each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-Si(Q_{11})(Q_{12})(Q_{13})$,

[0065] wherein Q_{11} to Q_{13} may be each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

[0066] d_4 may be an integer selected from 0 to 4,[0067] d_3 may be an integer selected from 0 to 3,[0068] d_2 may be an integer selected from 0 to 2, and[0069] $*$ and $*'$ may be each independently a binding site to a neighboring atom.


[0070] In Formula 1, a_1 denotes the number of groups L_1 , and is an integer selected from 0 to 5. When a_1 is 0, $*(L_1)_{a_1}-*$ is a single bond, and when a_1 is 2 or greater, two or more groups L_1 may be identical to or different from each other. Descriptions of a_2 may be the same as defined in reference to a_1 in Formula 1.

[0071] In Formula 1, a_1 and a_2 may be each independently an integer selected from 0 to 5.[0072] For example, in Formula 1, a_1 and a_2 may be each independently 0, 1, or 2, but embodiments are not limited thereto.[0073] According to an embodiment, in Formula 1, a_1 may be 0.[0074] According to another embodiment, in Formula 1, when a_1 is not 0, at least one of groups L_1 may be selected from groups represented by Formulae 3-15 to 3-56.[0075] In some embodiments, in Formula 1, when a_1 is not 0, all of groups L_1 may be each independently selected from groups represented by Formulae 3-15 to 3-56.


[0076] In some embodiments, in Formula 1,

[0077] L_1 may be selected from groups represented by Formulae 3-15, 3-28, 3-41, and 3-51,[0078] L_2 may be selected from groups represented by Formulae 3-1, 3-15, 3-28, 3-41, and 3-51, and[0079] a_1 and a_2 may be each independently 0, 1, or 2,


[0080] but embodiments are not limited thereto.

[0081] In Formula 1, a group represented by $*(L_1)_{a_1}-*$ may be selected from groups represented by Formulae 3-41 to 3-56.[0082] In some embodiments, in Formula 1, a group represented by $*(L_1)_{a_1}-*$ may be selected from groups represented by Formulae 4-1 to 4-39:


Formula 4-1




Formula 4-2




Formula 4-3




Formula 4-4




Formula 4-5



Formula 4-6




Formula 4-7




Formula 4-8


-continued




Formula 4-9




Formula 4-10




Formula 4-11




Formula 4-12




Formula 4-13



Formula 4-14




Formula 4-15




Formula 4-16


-continued




Formula 4-17




Formula 4-18




Formula 4-19




Formula 4-20



Formula 4-21




Formula 4-22




Formula 4-23


-continued




Formula 4-24




Formula 4-25




Formula 4-26



Formula 4-27




Formula 4-28




Formula 4-29


-continued




Formula 4-30




Formula 4-31




Formula 4-32




Formula 4-33



Formula 4-34




Formula 4-35




Formula 4-36


-continued



Formula 4-37



Formula 4-38



Formula 4-39

[0083] In Formulae 4-1 to 4-39, X_{21} may be N or C(Z_{21}), X_{22} may be N or C(Z_{22}), X_{23} may be N or C(Z_{23}), X_{24} may be N or C(Z_{24}), X_{31} may be N or C(Z_{31}), X_{32} may be N or C(Z_{32}), X_{33} may be N or C(Z_{33}), X_{34} may be N or C(Z_{34}), X_{41} may be N or C(Z_{41}), X_{42} may be N or C(Z_{42}), X_{43} may be N or C(Z_{43}), and X_{44} may be N or C(Z_{44}), but at least one of X_{21} to X_{24} may not be N, at least one of X_{31} to X_{34} may not be N, and at least one of X_{41} to X_{44} may not be N,

[0084] Z_{21} to Z_{24} , Z_{31} to Z_{34} , and Z_{41} to Z_{44} may be each independently selected from a hydrogen, a deuterium, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$,

[0085] wherein Q_{11} to Q_{13} may be each independently a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

[0086] * and *' may be each independently a binding site to a neighboring atom.

[0087] According to an embodiment, none, one, two, or three atoms among all ring-forming atoms in each of Formulae 4-1 to 4-39 may be nitrogen.

[0088] According to another embodiment, none, one, or two atoms among all ring-forming atoms in each of Formulae 4-1 to 4-39 may be nitrogen.

[0089] In some embodiments, none or one atom among all ring-forming atoms in each of Formulae 4-1 to 4-39 may be nitrogen.

[0090] In some embodiments, in each of Formulae 4-1 to 4-39, X_{21} may be C(Z_{21}), X_{22} may be C(Z_{22}), X_{23} may be C(Z_{23}), X_{24} may be C(Z_{24}), X_{31} may be C(Z_{31}), X_{32} may be C(Z_{32}), X_{33} may be C(Z_{33}), X_{34} may be C(Z_{34}), X_{41} may be C(Z_{41}), X_{42} may be C(Z_{42}), X_{43} may be C(Z_{43}), and X_{44} may be C(Z_{44}) (That is, none of the ring-forming atoms in each of Formulae 4-1 to 4-39 may be nitrogen).

[0091] In Formula 1, R_1 to R_8 , R_{11} to R_{18} , and R_{31} may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group (—CN), a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$.

[0092] For example, in Formula 1, R_1 to R_8 , R_{11} to R_{18} , and R_{31} may be each independently selected from

[0093] a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0094] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, and a triazinyl group;

[0095] a cyclopentyl group, a cyclohexyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridi-

nyl group, a quinoxaliny group, a quinazoliny group, a cinnoliny group, a phenanthridiny group, an acridiny group, a phenanthroliny group, a phenaziny group, a benzoxazoliny group, a benzoimidazoliny group, a furany group, a benzofurany group, a thiopheny group, a benzothiopheny group, a thiazoliny group, an isothiazoliny group, a benzothiazoliny group, an isoxazoliny group, an oxazoliny group, a triazoliny group, a tetrazoliny group, an oxadiazoliny group, a triazininy group, a dibenzofurany group, a dibenzothiopheny group, an imidazopyrimidiny group, and an imidazopyridiny group;

[0096] a cyclopentyl group, a cyclohexyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a phthalazinyl group, a naphthyridinyl group, a quinoxaliny group, a quinazoliny group, a cinnoliny group, a phenanthridiny group, an acridiny group, a phenanthroliny group, a phenaziny group, a benzoxazoliny group, a benzoimidazoliny group, a furany group, a benzofurany group, a thiopheny group, a benzothiopheny group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofurany group, a dibenzothiopheny group, an imidazopyrimidinyl group, and an imidazopyridinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_2 - C_{20} alkenyl group, a C_2 - C_{20} alkynyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a fluorenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinoliny group, an isoquinoliny group, a phthalazinyl group, a quinoxaliny group, a cinnoliny group, a quinazoliny group and $-\text{Si}(Q_{21})(Q_{22})(Q_{23})$; and

[0097] $-\text{Si}(Q_1)(Q_2)(Q_3)$.

[0098] wherein Q_1 to Q_3 and Q_{21} to Q_{23} may be each independently selected from a hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a fluorenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinoliny group, an isoquinoliny group, a phthalazinyl group, a quinoxaliny group, a cinnoliny group, a quinazoliny group, and a quinazoliny group.

[0099] According to an embodiment, in Formula 1, R_1 to R_8 , R_{11} to R_{18} , and R_{31} may be each independently

[0100] a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino

group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, and a C_1 - C_{10} alkoxy group;

[0101] a C_1 - C_{10} alkyl group and a C_1 - C_{10} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

[0102] a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofurany group, and a dibenzothiophenyl group;

[0103] a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofurany group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofurany group, a dibenzothiophenyl group, and $-\text{Si}(Q_{21})(Q_{22})(Q_{23})$; and

[0104] $-\text{Si}(Q_1)(Q_2)(Q_3)$.

[0105] Q_1 to Q_3 and Q_{21} to Q_{23} may be each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofurany group, and a dibenzothiophenyl group.

[0106] According to another embodiment, in Formula 1, R_1 to R_8 , R_{11} to R_{18} , and R_{31} may be each independently selected from

[0107] a hydrogen, a deuterium, —F, a cyano group, a C_1 - C_{10} alkyl group, and a C_1 - C_{10} alkoxy group;

[0108] a C_1 - C_{10} alkyl group and a C_1 - C_{10} alkoxy group, each substituted with at least one selected from a deuterium, —F, and a cyano group;

[0109] a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofurany group, and a dibenzothiophenyl group;

[0110] a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofurany group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofurany group, a dibenzothiophenyl group, and $-\text{Si}(Q_{21})(Q_{22})(Q_{23})$; and

[0111] $-\text{Si}(Q_1)(Q_2)(Q_3)$.

[0112] wherein Q_1 to Q_3 and Q_{21} to Q_{23} may be each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofurany group, and a dibenzothiophenyl group.


[0113] According to an embodiment, in Formula 1, at least one of X_3 , X_6 , X_{13} , and X_{16} may be C(CN).

[0114] In Formula 1, b1 may denote the number of groups R_{31} which may be an integer selected from 0 to 4. When b1 is 2 or greater, two or more groups R_{31} may be identical to or different from each other.


[0115] For example, in Formula 1, b1 and b2 may be 0, 1, or 2.

[0116] In Formula 1, c1 may be an integer selected from 1 to 4. That is, ring A_1 may essentially include at least one cyano group. For example, in Formula 1, c1 may be 1 or 2.


[0117] According to an embodiment, in Formula 1, a group represented by




may be selected from groups represented by Formulae 5-1 to 5-60:




Formula 5-1




Formula 5-2




Formula 5-3




Formula 5-4




Formula 5-5



Formula 5-6




Formula 5-7




-continued


Formula 5-8




Formula 5-9




Formula 5-10




Formula 5-11




Formula 5-12




Formula 5-13



Formula 5-14












Formula 5-15



Formula 5-16

-continued



Formula 5-17

Formula 5-18

Formula 5-19

Formula 5-20

Formula 5-21










Formula 5-22

Formula 5-23

Formula 5-24

Formula 5-25

-continued



Formula 5-26

Formula 5-27

Formula 5-28

Formula 5-29

Formula 5-30










Formula 5-31

Formula 5-32


Formula 5-33

Formula 5-34



-continued



-continued




Formula 5-53




Formula 5-54

may be selected from groups represented by Formulae 5-1 to 5-3, 5-31, 5-39, 5-47, and 5-55, but embodiments are not limited thereto.


[0120] A condensed cyclic compound represented by Formula 1 may be represented by one of Formulae 1A to 1D:




Formula 5-55




Formula 5-56




Formula 5-57




Formula 5-58




Formula 5-59




Formula 5-60



Formula 1A



Formula 1B




Formula 1C

[0118] In Formulae 5-1 to 5-60, * may denote a binding site to a neighboring atom.

-continued

Formula 1D



[0121] In Formulae 1A to 1D, ring A_1 , L_1 , L_2 , a_1 and a_2 , R_1 to R_8 , R_{11} to R_{18} , R_{31} , b_1 , and c_1 may be understood by referring to the description provided herein.

[0122] For example, in Formulae 1A to 1D, ring A_1 may be selected from a benzene ring, a dibenzofurane ring, and a dibenzothiophene ring,

[0123] L_1 may be selected from groups represented by Formulae 3-15, 3-28, 3-41, and 3-51,

[0124] L_2 may be selected from groups represented by Formulae 3-1, 3-15, 3-28, 3-41, and 3-51,

[0125] a_1 and a_2 may be each independently selected from 0, 1, and 2,

[0126] R_1 to R_8 , R_{11} to R_{18} , and R_{31} may be each independently selected from

[0127] a hydrogen, a deuterium, —F, a cyano group, a C_1 - C_{10} alkyl group, and a C_1 - C_{10} alkoxy group;

[0128] a C_1 - C_{10} alkyl group and a C_1 - C_{10} alkoxy group, each substituted with at least one selected from a deuterium, —F, and a cyano group;

[0129] a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

[0130] a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q_{21})(Q_{22})(Q_{23}); and


[0131] —Si(Q_1)(Q_2)(Q_3),

[0132] wherein Q_1 to Q_3 and Q_{21} to Q_{23} may be each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

[0133] b_1 may be 0 or 1, and

[0134] c_1 may be 1 or 2.

[0135] According to another embodiment, in Formulae 1A to 1D, a group represented by




may be selected from groups represented by Formulae 5-1 to 5-3, 5-31, 5-39, 5-47, and 5-55, but embodiments are not limited thereto.


[0136] In some embodiments, in Formulae 1A to 1D, at least one of R_3 , R_6 , R_{13} , and R_{16} may be a cyano group.

[0137] In some embodiments, the number of cyano groups in Formula 1 may be 1, 2, 3, or 4.


[0138] A compound represented by Formula 1 may be one of Compounds 1 to 336, but embodiments are not limited thereto:




1



2




3




4

-continued




5


-continued




9




6




10




7



11




8




12


-continued




13




14



15




16




17


-continued




18




19



20




21




22

-continued




23

-continued




27


24




25




28




29








26




-continued








-continued




-continued




-continued




-continued




42




45




43



46








44








47


-continued



-continued




-continued




58


-continued




62




59




63




60



64




61




65


-continued




66



67




68




69


-continued




70



71




72




73

-continued




74


-continued




78




75



79




80




81


76




77




-continued




82



83




84




85


-continued



86




87




88

-continued




89


-continued




92




90



93







91








94


-continued










-continued




-continued



-continued




-continued




112


-continued




116




113




117




114



118




115




119

-continued




120


-continued




123




121



124




122




125

-continued




126

-continued




129


127




130




128



131




-continued




132


-continued




135




133



136




134




137

-continued




138


-continued




141




139



142




140




143


-continued



-continued




-continued




152


-continued




156




153




157




154



158









155






159





-continued




-continued



-continued




-continued




173


-continued




177




174




175



178




176



179


-continued

180




-continued


183




181




184




182



185




-continued




186

-continued




189



187



188












190




191


-continued




-continued




201




202



203




204




205


-continued




206



207




208




209

-continued


210




211



212




213




-continued


214




215




216



217




-continued




218


-continued




222




219




223




220



224




221




225


-continued




226



227




228




229


-continued



230




231



232


-continued

233




-continued


236




234




237






235







238




-continued



-continued




-continued




246


-continued




249




247



250






248






251


-continued




-continued




-continued




-continued




259




262






260







263




-continued




-continued




-continued




271




272



273




274




275


-continued




276




277



278




279




280

-continued


281




282



283




284




-continued


285




286



287




-continued




288


-continued




291




289



292






290







293


-continued









-continued




-continued




-continued




-continued




309




310




311




312




-continued




314




315



316




-continued




317


-continued




321




318




322




319



323



320




324


-continued

-continued


325




328




326




329




327




330




-continued



-continued




-continued



336

[0139] In Formula 1, “ring B” is bonded to “N” of “ring A” via $*(L_1)_{a1}-*$ (see Formula 1’).

[0140] In this regard, the condensed cyclic compound represented by Formula 1 may have a high triplet (T_1) energy level. Accordingly, although not limited to a particular theory, an electronic device, such as an organic light-emitting device including the condensed cyclic compound represented by Formula 1 (e.g., an organic light-emitting device including an emission layer that includes the condensed cyclic compound represented by Formula 1) may emit deep blue light at a high color purity.



[0141] Also, in Formula 1, L_2 may be selected from

[0142] a phenylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylylene group; and

[0143] a phenylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10}

alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q_{11})(Q_{12})(Q_{13}).


[0144] In this regard, for example, the condensed cyclic compound represented by Formula 1 may have a higher triplet energy level than that of a virtual compound that has the same structure as Formula 1 except that L_2 is a nitrogen-containing ring. Therefore, although not limited to a particular theory, an electronic device, for example, an organic light-emitting device including the condensed cyclic compound represented by Formula 1 (e.g., an organic light-emitting device including an emission layer that includes the condensed cyclic compound represented by Formula 1), may emit deep blue light at a high color purity.

[0145] Also, a difference between S_1 (singlet) energy level and T_1 (triplet) energy level of the condensed cyclic compound represented by Formula 1 may be relatively small. In this regard, the condensed cyclic compound represented by Formula 1 may be used as a thermally activated delayed fluorescence (TADF) emitter.

[0146] For example, the results of HOMO, LUMO, T_1 , and S_1 energy levels of Compounds 1, 13, 37, 97, 109, 169, 223, and 325 and Compounds B and C simulated and measured by using a density functional theory (“DFT”) method of Gaussian program (structurally optimized at a level of B3LYP, 6-31 G(d,p)) are shown in Table 1.

TABLE 1


Compound No.	HOMO (eV)	LUMO (eV)	T_1 (eV)	S_1 (eV)
1	-5.475	-1.541	3.145	3.313
13	-5.29	-1.768	3.011	3.087
37	-5.307	-1.78	3.043	3.135
97	-5.398	-1.683	3.133	3.194
109	-5.386	-1.739	3.02	3.17
169	-5.316	-1.750	3.000	3.190
223	-5.167	-1.694	3.030	3.140
325	-5.231	-1.691	3.044	3.222
Compound B	-5.194	-1.65	2.8	3.212
Compound C	-5.233	-2.536	2.413	2.451



Compound B

TABLE 1-continued

Compound No.	HOMO (eV)	LUMO (eV)	T ₁ (eV)	S ₁ (eV)
--------------	-----------	-----------	---------------------	---------------------



Compound C

[0147] A method of synthesizing the condensed cyclic compound represented by Formula 1 may be understood by one of ordinary skill in the art by referring to Synthesis Examples described below.

[0148] Therefore, the condensed cyclic compound represented by Formula 1 may be appropriate for use as an organic layer of an organic light-emitting device, for example, as a host or an emitter (e.g., a TADF emitter) of an emission layer in the organic layer. According to another aspect of an embodiment, an organic light-emitting device includes:

[0149] a first electrode;

[0150] a second electrode; and

[0151] an organic layer that is disposed between the first electrode and the second electrode,

[0152] wherein the organic layer includes an emission layer and at least one condensed cyclic compound represented by Formula 1.

[0153] When the organic light-emitting device includes the organic layer including the condensed cyclic compound represented by Formula 1, the organic light-emitting device may have low driving voltage, high efficiency, high luminance, high quantum efficiency, and long lifespan.

[0154] The condensed cyclic compound represented by Formula 1 may be included between a pair of electrodes of the organic light-emitting device. In some embodiments, the condensed cyclic compound may be included in at least one selected from the emission layer, a hole transport region (for example, including at least one selected from a hole injection layer, a hole transport layer, and an electron blocking layer) disposed between the first electrode and the emission layer, and an electron transport region (for example, including at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer) disposed between the emission layer and the second electrode.

[0155] In some embodiments, the condensed cyclic compound represented by Formula 1 may be included in the emission layer. Here, the condensed cyclic compound included in the emission layer may be a host, and the

emission layer may further include a dopant (a fluorescent dopant or a phosphorescent dopant), wherein an amount of the condensed cyclic compound is larger than an amount of the dopant. The emission layer may be a green emission layer or a blue emission layer that emits green light or blue light. According to an embodiment, the condensed cyclic compound represented by Formula 1 may be included in the emission layer, the emission layer may further include a phosphorescent dopant, and the emission layer may emit blue light.

[0156] In some embodiments, the condensed cyclic compound represented by Formula 1 may be included in the emission layer, and the condensed cyclic compound may be a TADF emitter. Here, the emission layer may include the condensed cyclic compound represented by Formula 1 only or may further include a host and/or a dopant in addition to the condensed cyclic compound represented by Formula 1.

[0157] As used herein, the expression “(an organic layer) includes at least one condensed cyclic compound” may include an embodiment in which “(an organic layer) includes identical condensed cyclic compounds represented by Formula 1 and an embodiment in which (an organic layer) includes two or more different condensed cyclic compounds represented by Formula 1.

[0158] For example, the organic layer may include only Compound 1 as the condensed cyclic compound. In this regard, Compound 1 may be included in the emission layer of the organic light-emitting device. In some embodiments, the organic layer may include Compound 1 and Compound 2 as the condensed cyclic compounds. In this regard, Compound 1 and Compound 2 may be included in the same layer (for example, both Compound 1 and Compound 2 may be included in the emission layer) or in different layers, respectively.

[0159] The first electrode may be anode, which is a hole injection electrode, and the second electrode may be a cathode, which is an electron injection electrode. Alternatively, the first electrode may be a cathode, which is an electron injection electrode, and the second electrode may be an anode, which is a hole injection electrode.

[0160] For example, the first electrode may be an anode, the second electrode may be a cathode, the organic layer may include a hole transport region disposed between the first electrode and the emission layer and an electron transport region disposed between the emission layer and the second electrode, wherein the hole transport region includes at least one selected from a hole injection layer, a hole-transport layer, and an electron blocking layer, and wherein the electron transport region includes at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

[0161] As used herein, the term the “organic layer” refers to a single and/or a plurality of layers disposed between the first electrode and the second electrode in an organic light-emitting device. The “organic layer” may include not only organic compounds but also organometallic complexes including metals.

[0162] FIG. 1 is a schematic view of an organic light-emitting device 10 according to an embodiment. Hereinafter, a structure and a method of manufacturing the organic light-emitting device according to an embodiment will be described with reference to FIG. 1. The organic light-

emitting device **10** includes a first electrode **11**, an organic layer **15**, and a second electrode **19**, which are sequentially layered in the stated order.

[0163] A substrate may be additionally disposed under the first electrode **11** or on the second electrode **19**. The substrate may be a conventional substrate that is used in an organic light-emitting device, such as glass substrate or a transparent plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water repellency.

[0164] The first electrode **11** may be formed by depositing or sputtering a first electrode material on the substrate. The first electrode **11** may be an anode. The first electrode material may be selected from materials with a high work function for an easy hole injection. The first electrode **11** may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. The first electrode material may be selected from an indium tin oxide (ITO), an indium zinc oxide (IZO), a tin oxide (SnO_2), and a zinc oxide (ZnO). In some embodiments, a metal such as magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be used as the first electrode material.

[0165] The first electrode **11** may have a single layer structure or a multi-layer structure including a plurality of layers. For example, the first electrode **11** may have a triple-layer structure of ITO/Ag/ITO, but embodiments are not limited thereto.

[0166] The organic layer **15** is disposed on the first electrode **11**.

[0167] The organic layer **15** may include a hole transport region, an emission layer, and an electron transport region.

[0168] The hole transport region may be disposed between the first electrode **11** and the emission layer.

[0169] The hole transport region may include at least one selected from a hole injection layer, hole transport layer, electron blocking layer, and buffer layer.

[0170] The hole transport region may only include a hole injection layer or a hole transport layer. Alternatively, the hole transport region may include a structure in which a hole injection layer/a hole transport layer or a hole injection layer/a hole transport layer/an electron blocking layer are sequentially layered on the first electrode **11**.

[0171] When the hole transport region includes a hole injection layer, the hole injection layer HIL may be formed on the first electrode **11** by using various methods such as vacuum-deposition, spin coating, casting, and Langmuir-Blodgett (LB) method.


[0172] When a hole injection layer is formed by vacuum deposition, the deposition conditions may vary depending on a material that is used to form the hole injection layer and the structure and thermal characteristics of the hole injection layer. For example, the deposition conditions may include a deposition temperature of about 100°C . to about 500°C ., a vacuum pressure of about 10^{-8} torr to about 10^{-3} torr, and a deposition rate of about 0.01 Angstroms per second (Å/sec) to about 100 Å/sec. However, the deposition conditions are not limited thereto.

[0173] When the hole injection layer is formed by spin coating, the coating conditions may vary depending on a material used to form the hole injection layer and the structure and thermal characteristics of the hole injection layer. For example, a coating rate may be from about 2,000 revolutions per minute (rpm) to about 5,000 rpm, and a


temperature at which a heat treatment is performed to remove a solvent after coating may be from about 80°C . to about 200°C . However, the coating conditions are not limited thereto.

[0174] The conditions for forming a hole transport layer and an electron blocking layer may be inferred based on the conditions for forming the hole injection layer.

[0175] The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB, β -NPB, TPD, Spiro-TPD, Spiro-NPB, methylated NPB, TAPC, HMTPD, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzene sulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), (polyaniline)/poly(4-styrenesulfonate) (Pani/PSS), a compound represented by Formula 201 below, and a compound represented by Formula 202 below:




m-MTDATA











TDATA

-continued




-continued




-continued

Formula 201



Formula 202



[0176] In Formula 201, Ar₁₀₁ and Ar₁₀₂ may be each independently selected from

[0177] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, and a pentacenylene group; and

[0178] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, and a pentacenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

[0179] In Formula 201, xa and xb may be each independently an integer selected from 0 to 5 or may be 0, 1, or 2. For example, xa may be 1 and xb may be 0, but embodiments are not limited thereto.

[0180] In Formulae 201 and 202, R₁₀₁ to R₁₀₈, R₁₁₁ to R₁₁₉, and R₁₂₁ to R₁₂₄ may be each independently selected from

[0181] a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group (e.g., a methyl group, an ethyl group, a propyl group, a butyl group, pentyl group, or a hexyl group), and a C₁-C₁₀ alkoxy group (e.g., a methoxy group, an ethoxy group, a propoxy group, a butoxy group, or a pentoxy group);

[0182] a C₁-C₁₀ alkyl group and a C₁-C₁₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

[0183] a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, and a pyrenyl group; and

[0184] a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, and a pyrenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, and a C₁-C₁₀ alkoxy group, but embodiments are not limited thereto.

[0185] In Formula 201, R₁₀₉ may be selected from


[0186] a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group; and

[0187] a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group.

-continued

HT2

Formula 201A






[0189] In Formula 201A, R₁₀₁, R₁₁₁, R₁₁₂, and R₁₀₉ may be understood by referring to the description provided herein.

[0190] For example, the compound represented by Formula 201 and the compound represented by Formula 202 may include Compounds HT1 to HT20, but embodiments are not limited thereto:

HT3


HT1




-continued

-continued


HT4




HT6



HT5




HT7




-continued

-continued


HT8




HT10



HT9




HT11




-continued

HT12




-continued


HT16




HT17




HT18




HT19




HT13



HT14




HT15



-continued

HT20




[0191] A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Angstroms (Å), for example, about 100 Å to about 1,000 Å. While not wishing to be bound by a theory, it is understood that when the hole transport region includes at least one of a hole injection layer and a hole transport layer, the thickness of the hole injection layer may be in a range of about 100 Å to about 10,000 Å, and for example, about 100 Å to about 1,000 Å, and the thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, and for example, about 100 Å to about 1,500 Å. While not wishing to be bound by a theory, it is understood that when the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, hole transporting characteristics may be satisfactory without a substantial increase in driving voltage.


[0192] The hole transport region may further include, in addition to the mentioned materials above, a charge-generating material to improve conductive properties. The charge-generating material may be homogeneously or non-homogeneously dispersed throughout the hole transport region.

[0193] The charge-generating material may be, for example, a p-dopant. The p-dopant may be one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments are not limited thereto. Non-limiting examples of the p-dopant are a quinone derivative, such as tetracyanoquinonodimethane (TCNQ) or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonodimethane (F4-TCNQ); a metal oxide, such as a tungsten oxide or a molybdenum oxide; and a cyano group-containing compound, such as Compound HT-D1 or HP-1, but embodiments are not limited thereto.

Compound HT-D1




-continued



F4-TCNQ

HP-1




[0194] The hole transport region may further include a buffer layer.

[0195] The buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer to improve the efficiency of an organic light-emitting device.

[0196] Then, an emission layer may be formed on the hole transport region by vacuum deposition, spin coating, casting, LB deposition, or the like. When the emission layer is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied to form the hole injection layer although the deposition or coating conditions may vary depending on the material that is used to form the emission layer.

[0197] The hole transport region may further include an electron blocking layer. The electron blocking layer may include, for example, mCP, but embodiments are not limited thereto.



mCP

[0198] When the organic light-emitting device is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and a blue emission layer. Alternatively, the emission layer may have a structure in which the red emission layer, the green emission layer, and/or the blue emission layer are layered to emit white light or other various embodiments are possible.

[0199] The emission layer may include the condensed cyclic compound represented by Formula 1. The emission layer may further include a dopant. The dopant may include at least one selected from a fluorescent dopant and a phosphorescent dopant.


[0200] In some embodiments, the emission layer may include the condensed cyclic compound represented by Formula 1 only, and the condensed cyclic compound may be a TADF emitter.

[0201] In some embodiments, the emission layer may include the condensed cyclic compound represented by Formula 1, the condensed cyclic compound may be a TADF emitter, and the emission layer may further include any host which is not the condensed cyclic compound represented by Formula 1.

[0202] For example, a host in the emission layer may include the condensed cyclic compound represented by Formula 1.

[0203] The dopant in the emission layer may include a fluorescent dopant which emits light according to a fluorescent emission mechanism or a phosphorescent dopant which emits light according to a phosphorescent emission mechanism.

[0204] According to an embodiment, the dopant in the emission layer may be a phosphorescent dopant, and the phosphorescent dopant may include an organometallic compound represented by Formula 81:



Formula 81

[0205] wherein, in Formula 81,

[0206] M may be selected from iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm),

[0207] Y₁ to Y₄ may be each independently carbon (C) or nitrogen (N),

[0208] Y₁ and Y₂ are linked via a single bond or a double bond, and Y₃ and Y₄ are linked via a single bond or a double bond,

[0209] CY₁ and CY₂ may be each independently selected from a benzene ring, a naphthalene ring, a fluorene ring, a spiro-fluorene ring, an indene ring, a pyrrole ring, a thiophene ring, a furan ring, an imidazole ring, a pyrazole ring, a thiazole ring, an isothiazole ring, an oxazole ring, an isoxazole ring, a pyridine ring, a pyrazine ring, a pyrimidine ring, a pyridazine ring, a quinoline ring, an isoquinoline ring, a benzoquinoline ring, a quinoxaline ring, a quinoxaline ring, a carbazole ring, a benzimidazole ring, a benzofuran ring, a benzothiophene ring, an isobenzothiophene ring, a benzoxazole ring, an isobenzoxazole ring, a triazole ring, a tetrazole ring, an oxadiazole ring, a triazine ring, a

dibenzofuran ring, or a dibenzothiophene ring, and CY₁ and CY₂ are optionally further linked to each other through an organic linking group,

[0210] R₈₁ and R₈₂ may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, —SF₅, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), and —B(Q₆)(Q₇),

[0211] a₈₁ and a₈₂ may be each independently an integer selected from 1 to 5,

[0212] n₈₁ may be an integer selected from 0 to 4,


[0213] n₈₂ may be 1, 2, or 3,

[0214] L₈₁ may be a monovalent organic ligand, a divalent organic ligand, or a trivalent organic ligand, and


[0215] Q₁ to Q₇ may have the same definitions as Q₁ to Q₃ in —Si(Q₁)(Q₂)(Q₃) in Formula 1.

[0216] R₈₁ and R₈₂ may be understood by referring to the description provided herein in connection with R₁₁.

[0217] The phosphorescent dopant may include at least one selected from Compounds PD1 to PD78, and Flr₆, but embodiments are not limited thereto:








PD1




PD2

-continued




-continued

PD3




PD8

PD4




PD9

PD5




PD10

PD6




PD11

PD7




PD12


-continued




PD13




PD14



PD15




PD16




PD17


-continued




PD18




PD19



PD20




PD21




PD22


-continued




PD23




PD24



PD25




PD26




PD27


-continued




PD28




PD29



PD30








PD31



PD32


-continued



-continued


PD33

PD38




PD34

PD39




PD35

PD40




PD36

PD41




PD37


PD42




-continued




PD43




PD44



PD45




PD46




PD47


-continued




PD48




PD49




PD50



PD51








PD52








PD53

-continued



-continued



PD54

PD59

PD55

PD60

PD56

PD61


PD57

PD62


PD58

PD63


-continued




PD64




PD65



PD66




PD67




PD68


-continued




PD69




PD70



PD71








PD72




PD73

-continued



-continued


PD74



PD75

[0218] In some embodiments, the phosphorescent dopant may include PtOEP:

PD76



PD77

[0219] When the emission layer includes a host and a dopant, an amount of the dopant may be in a range of about 0.01 part to about 20 parts by weight based on 100 parts by weight of the host, but embodiments are not limited thereto.

[0220] A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within this range, light-emission characteristics may be excellent without a substantial increase in driving voltage.

[0221] Then, an electron transport region may be disposed on the emission layer.

[0222] The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer, but embodiments are not limited thereto.

PD78


[0223] For example, the electron transport region may have a structure of a hole blocking layer/an electron transport layer/an electron injection layer or an electron transport layer/an electron injection layer, but embodiments are not limited thereto. The electron transport layer may have a single layer structure or a multi-layer structure including two or more different materials.

[0224] The conditions for forming a hole blocking layer, an electron transport layer, and an electron injection layer may be inferred based on the conditions for forming the hole injection layer.


[0225] When the electron transport region includes a hole blocking layer, the hole blocking layer may include, for

example, at least one selected from BCP and Bphen, but embodiments are not limited thereto.


-continued




BCP



Bphen



TAZ




NTAZ


[0226] A thickness of the hole blocking layer may be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thickness of the hole blocking layer is within these ranges, the hole blocking layer may have improved hole blocking ability without a substantial increase in driving voltage.

[0227] The electron transport layer may further include at least one selected from BCP, Bphen, Alq₃, BAlq, TAZ, and NTAZ.


[0228] In some embodiments, the electron transport layer may include at least one selected from Compounds ET1, ET2, and ET3, but embodiments are not limited thereto.



Alq₃




BAlq




ET1

-continued

ET2



ET3




[0229] A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. While not wishing to be bound by a theory, it is understood that when the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.

[0230] The electron transport layer may further include a metal-containing material in addition to the materials described above.


[0231] The metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2.

ET-D1



-continued

ET-D2



[0232] The electron transport region may include an electron injection layer that allows electrons to be easily provided from the second electrode 19.

[0233] The electron injection layer may include at least one selected from, LiF, NaCl, CsF, Li₂O, and BaO.

[0234] A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. While not wishing to be bound by a theory, it is understood that when the thickness of the electron injection layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

[0235] The second electrode 19 is disposed on the organic layer 15. The second electrode 19 may be a cathode. A second electrode material may be selected from a metal, an alloy, an electrically conductive compound, and a combination thereof, which have a relatively low work function. For example, lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be used as second electrode material. To manufacture a top emission-type light-emitting device, a transmissive electrode formed using ITO or IZO may be used as the second electrode 19.

[0236] Hereinbefore, the organic light-emitting device has been described with reference to FIG. 1, but embodiments are not limited thereto.

[0237] A C₁-C₆₀ alkyl group as used herein refers to a linear or branched aliphatic saturated hydrocarbon monovalent group having 1 to 60 carbon atoms. Detailed examples thereof are a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. A C₁-C₆₀ alkylene group as used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

[0238] A C₁-C₆₀ alkoxy group as used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group). Detailed examples thereof are a methoxy group, an ethoxy group, and an isopropoxy group.

[0239] A C₂-C₆₀ alkenyl group as used herein refers to a hydrocarbon group formed by placing at least one carbon-carbon double bond in the middle or at the terminal of the C₂-C₆₀ alkyl group. Detailed examples thereof are an ethenyl group, a propenyl group, and a butenyl group. A C₂-C₆₀ alkenylene group used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

[0240] A C₂-C₆₀ alkynyl group as used herein refers to a hydrocarbon group formed by placing at least one carbon-

carbon triple bond in the middle or at the terminal of the C₂-C₆₀ alkyl group. Detailed examples thereof are an ethynyl group and a propynyl group. A C₂-C₆₀ alkynylene group as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

[0241] A C₃-C₁₀ cycloalkyl group as used herein refers to a monovalent monocyclic saturated hydrocarbon group including 3 to 10 carbon atoms. Detailed examples thereof are a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. A C₃-C₁₀ cycloalkylene group as used herein refers to a divalent group having the same structure as a C₃-C₁₀ cycloalkyl group.

[0242] A C₁-C₁₀ heterocycloalkyl group as used herein refers to a monovalent saturated monocyclic group including at least one heteroatom selected from N, O, P, Si and S as a ring-forming atom and 1 to 10 carbon atoms. Detailed examples thereof are a tetrahydrofuranyl group and a tetrahydrothiophenyl group. A C₁-C₁₀ heterocycloalkylene group as used herein refers to a divalent group having the same structure as a C₁-C₁₀ heterocycloalkyl group.

[0243] A C₃-C₁₀ cycloalkenyl group as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof, and which is not aromatic. Detailed examples thereof are a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. A C₃-C₁₀ cycloalkenylene group as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

[0244] A C₁-C₁₀ heterocycloalkenyl group as used herein refers to a monovalent monocyclic group including at least one heteroatom selected from N, O, P, Si and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one double bond in its ring. Detailed examples of the C₂-C₁₀ heterocycloalkenyl group are a 2,3-dihydrofuranyl group and a 2,3-dihydrothiophenyl group. A C₁-C₁₀ heterocycloalkenylene group as used herein refers to a divalent group having the same structure as a C₁-C₁₀ heterocycloalkenyl group.

[0245] A C₆-C₆₀ aryl group as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C₆-C₆₀ arylene group as used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Detailed examples of the C₆-C₆₀ aryl group are a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

[0246] A C₁-C₆₀ heteroaryl group as used herein refers to a monovalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, P, Si and S as a ring-forming atom, and 1 to 60 carbon atoms. A C₁-C₆₀ heteroarylene group as used herein refers to a divalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom, and 1 to 60 carbon atoms. Examples of the C₁-C₆₀ heteroaryl group are a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the rings may be fused to each other.

[0247] A C₆-C₆₀ aryloxy group as used herein indicates —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and a C₆-C₆₀ arylthio group as used herein indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

[0248] A monovalent non-aromatic condensed polycyclic group as used herein refers to a monovalent group that has two or more rings condensed to each other, only carbon atoms (for example, the number of carbon atoms may be in a range of 8 to 60) as ring-forming atoms, wherein the molecular structure as a whole is non-aromatic in the entire molecular structure. Detailed examples of the non-aromatic condensed polycyclic group include a fluorenyl group. A divalent non-aromatic condensed polycyclic group as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

[0249] A monovalent non-aromatic condensed heteropolycyclic group as used herein refers to a monovalent group that has a plurality of rings condensed with each other, has a heteroatom selected from N, O, P, Si and S, other than carbon atoms (for example, the number of carbon atoms may be in a range of 1 to 60), as ring-forming atoms, wherein the molecular structure as a whole is non-aromatic in the entire molecular structure. The monovalent non-aromatic condensed heteropolycyclic group includes a carbazolyl group. A divalent non-aromatic condensed heteropolycyclic group as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0250] At least one substituent of the substituted C₃-C₁₀ cycloalkylene group, substituted C₁-C₁₀ heterocycloalkylene group, substituted C₃-C₁₀ cycloalkenylene group, substituted C₁-C₁₀ heterocycloalkenylene group, substituted C₆-C₆₀ arylene group, substituted C₁-C₆₀ heteroarylene group, substituted divalent non-aromatic condensed polycyclic group, substituted divalent non-aromatic condensed heteropolycyclic group, substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group (where, a carbazolyl group is excepted from the monovalent non-aromatic condensed heteropolycyclic group) and —Si(Q₃₁)(Q₃₂)(Q₃₃).

[0251] wherein Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may be each independently selected from a hydrogen,

a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group (where, a carbazolyl group is excepted from the monovalent non-aromatic condensed heteropolycyclic group).

[0252] When a group containing a specified number of carbon atoms is substituted with any of the substituents listed above, the number of carbon atoms in the resulting “substituted” group may be the number of atoms contained in the original (base) group plus the number of carbon atoms (if any) contained in the substituent. For example, the “substituted C₁-C₃₀ alkyl” may refer to a C₁-C₃₀ alkyl group substituted with C₆₋₆₀ aryl group, in which the total number of carbon atoms may be C₇-C₉₀.

[0253] The “biphenyl group” used therein refers to “a phenyl group substituted with a phenyl group”.


[0254] Hereinafter, a compound and an organic light-emitting device according to embodiments are described in detail with reference to Synthesis Example and Examples. However, the organic light-emitting device is not limited thereto. The wording “B was used instead of A” used in describing Synthesis Examples means that an amount of A used was identical to an amount of B used, in terms of a molar equivalent.

EXAMPLE

Synthesis Example 1

Synthesis of Compound 13

[0255]




[0256] 18 grams (g) (54.15 millimoles (mmol)) of 9H-2,9'-bicarbazole, 5.88 milliliters (mL) (54.15 mmol) of 2-fluorobenzonitrile, and 2.16 g (54.15 mmol) of 60% sodium hydride were added to 200 mL of DMF in a round bottom flask, and the mixture was heated under reflux for 12 hours. Once the reaction was completed, the reaction product was cooled to room temperature. 600 mL of methanol was added dropwise and the product crystallized. The solid was filtered, and washed with water and methanol. The resultant solid was dried in a vacuum oven to obtain Compound 13 (17 g, the yield of 72%).

[0257] MS (m/z, [M]⁺): 433.2

Synthesis Example 2

Synthesis of Compound 109

[0258]




[0259] 10 g (20.64 mmol) of 2-(2'-(9H-carbazol-9-yl)-[1,1'-biphenyl]-2-yl)-9H-carbazole, 11.26 g (61.91 mmol) of 2-bromobenzonitrile, 0.39 g (6.19 mmol) of copper, and 8.55 g (61.91 mmol) of potassium carbonate were added to 200 mL of DMF in a round bottom flask, and the mixture was heated under reflux for 48 hours. Once the reaction was completed, the reaction product was cooled to room temperature, and the solvent was removed therefrom. The resultant was dissolved in hot toluene and filtered through silica. Methylene chloride (MC) and ethyl acetate (EA) were added to the filtrate for crystallization, and the resultant was filtered. The resultant solid was dried in a vacuum oven to obtain Compound 109 (8.34 g, the yield of 69%).

[0260] MS (m/z, [M]⁺): 585.2

Synthesis Example 3

Synthesis of Compound 169

[0261]




[0262] 10 g (24.48 mmol) of 3-(9H-carbazol-9-yl)phenyl iodide, 16.82 g (73.44 mmol) of 2-iodobenzonitrile, 0.47 g (7.34 mmol) of copper, and 10.15 g (73.44 mmol) of potassium carbonate were added to 200 mL of DMF in a round bottom flask, and the mixture was heated under reflux for 48 hours. Once the reaction was completed, the reaction product was cooled to room temperature. 600 mL of methanol was added dropwise and the product crystallized. The solid was filtered, and washed with water and methanol. The resultant solid was dried in a vacuum oven to obtain Compound 169 (10.7 g, the yield of 86%).

[0263] MS (m/z, [M]⁺): 509.3

Synthesis Example 4

Synthesis of Compound 223

[0264]



[0265] 26.426 g (49.45 mmol) of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-bicarbazole, 7.5 g (41.2 mmol) of 2-bromobenzonitrile, 1.9 g (1.65 mmol) of tetrakis(triphenylphosphine)palladium [Pd(PPh₃)₄], and 17.085 g (123.61 mmol) of potassium carbonate were added to 200 mL of THF and 100 mL of distilled water in a round bottom flask, and the mixture was heated under reflux for 12 hours. Once the reaction was completed, the reaction product was cooled to room temperature, and THF layer was separated from distilled water. The THF layer separated therefrom was added dropwise to 600 mL of methanol and the product crystallized. Then, the solid was


filtered, and washed with water and methanol. The resultant solid was dried in a vacuum oven to obtain Compound 223 (17.85 g, the yield of 85%).

[0266] MS (m/z, [M]⁺): 509.4

Synthesis Example 5

Synthesis of Compound 325

[0267]



[0268] 28.176 g (46.15 mmol) of 3-(3-(9H-carbazol-9-yl)phenyl)-9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole, 7 g (38.46 mmol) of 2-bromobenzonitrile, 1.7 g (1.54 mmol) of tetrakis(triphenylphosphine)palladium [Pd(PPh₃)₄], and 15.946 g (115.37 mmol) of potassium carbonate were added to 200 mL of THF and 100 mL of distilled water in a round bottom flask, and the mixture was heated under reflux for 12 hours. Once the reaction was completed, the reaction product was cooled to room temperature, and THF was separated from distilled water. The THF separated therefrom was added dropwise to

600 mL of methanol and the product crystallized. The solid was filtered, and washed with water and methanol. The resultant solid was dried in a vacuum oven to obtain Compound 325 (16.89 g, the yield of 75%).

[0269] MS (m/z, [M]⁺): 585.5

Evaluation Example 1

Evaluation on HOMO and LUMO Energy Levels

[0270] HOMO and LUMO energy levels of Compounds 13, 109, 169, 223, and 325 were evaluated according to the method indicated in Table 2, and results thereof are shown in Table 3.

TABLE 2

HOMO energy level evaluation method	A potential (V)-current (A) graph of each compound was obtained by using cyclic voltammetry (CV) (electrolyte: 0.1molar (M) Bu ₄ NClO ₄ /solvent: CH ₂ Cl ₂ /electrode: 3 electrode system (working electrode: GC, reference electrode: Ag/AgCl, auxiliary electrode: Pt)). Then, from reduction onset of the graph, a HOMO energy level of the compound was calculated.
LUMO energy level evaluation method	Each compound was diluted at a concentration of 1 × 10 ⁻⁵ M in CHCl ₃ , and an UV absorption spectrum thereof was measured at room temperature by using Shimadzu UV-350 Spectrometer. A LUMO energy level thereof was calculated by using an optical band gap (E _g) from an edge of the absorption spectrum.

TABLE 3

Compound No.	HOMO (eV) (found)	LUMO (eV) (found)
13	-5.63	-2.16
109	-5.64	-2.12
169	-5.67	-2.14
223	-5.61	-2.08
325	-5.65	-2.13

[0271] From Table 3, it is confirmed that Compounds 13, 109, 169, 223, and 325 have electric characteristics that are suitable for use as a material for forming an organic light-emitting device.

Evaluation Example 2

Thermal Characteristics Evaluation


[0272] Each of Compounds 13, 109, 169, 223, 325, and A was subjected to thermal analysis (N₂ atmosphere, temperature range: room temperature to 800° C. (10° C./min)-TGA, room temperature to 400° C.-DSC, Pan Type: Pt Pan in disposable Al Pan (TGA), disposable Al pan (DSC)) using thermogravimetric analysis (TGA) and differential scanning calorimetry (DSC), and the obtained results are shown in Table 4 below. As shown in Table 4, it was confirmed that Compounds 13, 109, 169, 223, and 325 had excellent thermal stability than that of Compound A.

TABLE 4

Compound No.	Tg (° C.)
13	104
109	125
169	121

TABLE 4-continued

Compound No.	Tg (° C.)
223	109
325	117
Compound A	72



Compound A

Example 1

[0273] A glass substrate with a 1,500 Angstrom (Å)-thick ITO (Indium tin oxide) electrode (first electrode, anode) formed thereon was washed with distilled water and ultrasonic waves. When the washing with distilled water was completed, sonification washing was performed using a solvent, such as isopropyl alcohol, acetone, or methanol. The result was dried and then transferred to a plasma washer, and the resultant substrate was washed with oxygen plasma for 5 minutes and transferred to a vacuum depositor.

[0274] Compound HT3 and Compound HP-1 were co-deposited on the ITO electrode on the glass substrate to form a hole injection layer having a thickness of 100 Å. Compound HT3 was deposited on the hole injection layer to form a hole transport layer having a thickness of 1,300 Å, and mCP was deposited on the hole transport layer to form an electron blocking layer having a thickness of 150 Å, thereby completing the manufacture of a hole transport region.

[0275] Compound 13 (host) and FIr6 (dopant, 10 percent by weight (wt %)) were co-deposited on the hole transport region to form an emission layer having a thickness of 300 Å.

[0276] BCP was vacuum deposited on the emission layer to form a hole blocking layer having a thickness of 100 Å. Compound ET3 and Liq were vacuum deposited on the hole blocking layer to form an electron transport layer having a thickness of 250 Å. Then, Liq was deposited on the electron transport layer to form an electron injection layer having a thickness of 5 Å, and Al second electrode (cathode) having a thickness of 1,000 Å was formed on the electron injection layer, thereby completing the manufacture of an organic light-emitting device.

Examples 2 to 5 and Comparative Example 1

[0277] Organic light-emitting devices were manufactured in the same manner as in Example 1, except that the compounds shown in Table 5 were used, as a host, instead of Compound 13 in the formation of the emission layer.

Evaluation Example 3


Evaluation on Characteristics of Organic Light-Emitting Devices

[0278] The driving voltage, current density, luminous efficiency, power efficiency, quantum efficiency, and lifespan of the organic light-emitting devices of Examples 1 to 5 and


Comparative Example 1 were measured by using a current-voltage meter (Keithley 2400) and a luminance meter (Minolta Cs-1000A), and results thereof are shown in Table 5. T₉₅ (at 500 candelas per square meter (cd/m²)) in Table 5 indicates an amount of time that lapsed when the luminance is decreased from 100% of the initial luminance to 95% of the initial luminance.

TABLE 5


	Host	Driving voltage (V)	Luminous Efficiency (cd/A)	Power Efficiency (lm/W)	Quantum Efficiency (%)	T ₉₅ (hr)
Example 1	13	4.2	33.25	24.89	17.8	1.54
Example 2	109	4.94	20.44	13.00	10.8	1.00
Example 3	169	4.91	36.33	23.25	19.9	3.94
Example 4	223	3.99	34.90	27.48	19	1.93
Example 5	325	4.32	30.94	22.53	17	2.45
Comparative Example 1	Compound A	6.85	15.27	7.03	8.9	0.54



13






109



169

TABLE 5-continued

Host	Driving voltage (V)	Luminous Efficiency (cd/A)	Power Efficiency (lm/W)	Quantum Efficiency (%)	T ₉₅ (hr)
 223					
 325					
 Compound A					

[0279] Referring to Table 5, it was confirmed that the organic light-emitting devices of Examples 1 to 5 have a lower driving voltage, a higher luminous efficiency, a higher power efficiency, a higher quantum efficiency, and a longer lifespan than the organic light-emitting device of Comparative Example 1.

[0280] As described above, according to the one or more of the above embodiments of the present inventive concept, a condensed cyclic compound has excellent electric characteristics and thermal stability, and thus an organic light-emitting device including the condensed cyclic compound may have low driving voltage, high luminous efficiency, high power efficiency, high quantum efficiency, and long lifespan characteristics.


[0281] It should be understood that exemplary embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each exemplary embodiment should typically be considered as available for other similar features or aspects in other exemplary embodiments.

[0282] While one or more exemplary embodiments have been described with reference to the figures, it will be

understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present disclosure as defined by the following claims.

What is claimed is:

1. A condensed cyclic compound represented by Formula 1:



wherein, in Formula 1,

X_1 is N or C(R_1), X_2 is N or C(R_2), X_3 is N or C(R_3), X_4 is N or C(R_4), X_5 is N or C(R_5), X_6 is N or C(R_6), X_7 is N or C(R_7), X_8 is N or C(R_8), X_{11} is N or C(R_{11}), X_{12} is N or C(R_{12}), X_{13} is N or C(R_{13}), X_{14} is N or C(R_{14}), X_{15} is N, C(R_{15}), or a carbon atom connected to $^*-(L_1)_{a1}{}^{*-}$, X_{16} is N, C(R_{16}), or a carbon atom connected to $^*-(L_1)_{a1}{}^{*-}$, X_{17} is N, C(R_{17}), or a carbon atom connected to $^*-(L_1)_{a1}{}^{*-}$, and X_{18} is N, C(R_{18}), or a carbon atom connected to $^*-(L_1)_{a1}{}^{*-}$, wherein one of X_{15} to X_{18} is connected to $^*-(L_1)_{a1}{}^{*-}$.

ring A₁ is selected from a C₅-C₆₀ carbocyclic group and a C₃-C₆₀ heterocyclic group comprising at least one heteroatom selected from O, S, and Si,

L_1 is selected from

a phenylene group, a pyridinylene group, a pyrimidinylene group, a pyrazinylene group, a pyridazinylene group, a triazinylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylylene group; and

a phenylene group, a pyridinylene group, a pyrimidinylene group, a pyrazinylene group, a pyridazinylene group, a triazinylene group, a fluorenylene group, a dibenzofuranylene group, and a dibenzothiophenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q₁₁)(Q₁₂)(Q₁₃),

L_2 is selected from

a phenylene group, a fluorenylene group, a dibenzofuran-
ylene group, and a dibenzothiophenylene group; and
a phenylene group, a fluorenylene group, a dibenzofuran-
ylene group, and a dibenzothiophenylene group, each
substituted with at least one selected from a deuterium.

—F, —Cl, —Br, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q_{11})(Q_{12})(Q_{13}),

a1 and a2 are each independently an integer selected from 0 to 5, wherein when a1 is 2 or greater, two or more groups L_1 are identical to or different from each other, and when a2 is 2 or greater, two or more groups L_2 are identical to or different from each other,

R_1 to R_8 , R_{11} to R_{18} , and R_{31} are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, a hydroxyl group, a cyano group (—CN), a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q_1)(Q_2)(Q_3),

b1 is an integer selected from 0 to 4,

c1 is an integer selected from 1 to 4,

at least one substituent of the substituted C_1 - C_{60} alkyl group, substituted C_2 - C_{60} alkenyl group, substituted C_2 - C_{60} alkynyl group, substituted C_1 - C_{60} alkoxy group, substituted C_3 - C_{10} cycloalkyl group, substituted C_1 - C_{10} heterocycloalkyl group, substituted C_3 - C_{10} cycloalkenyl group, substituted C_1 - C_{10} heterocycloalkenyl group, substituted C_6 - C_{60} aryl group, substituted C_6 - C_{60} aryloxy group, substituted C_6 - C_{60} arylthio group, substituted C_1 - C_{60} heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group is selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic

clic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q_{21})(Q_{22})(Q_{23}),

wherein Q_1 to Q_3 , Q_{11} to Q_{13} , and Q_{21} to Q_{23} are each independently selected from a hydrogen, a deuterium, a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group


in $*(L_1)_{a1}^*$, * and *' are each a binding site to a neighboring atom.

2. The condensed cyclic compound of claim 1, wherein ring A_1 is selected from a cyclopentane ring, a cyclohexane ring, a cyclopentene ring, a cyclohexene ring, a cycloheptene ring, a benzene ring, a pentalene ring, an indene ring, a naphthene ring, an azulene ring, a heptalene ring, an indacene ring, an acenaphthene ring, a fluorene ring, a spirobifluorene ring, a phenalene ring, a phenanthrene ring, an anthracene ring, a fluoranthene ring, a triphenylene ring, a pyrene ring, a chrysene ring, a naphthacene ring, a picene ring, a perylene ring, a pentaphene ring, a hexacene ring, a furane ring, a thiophene ring, a benzofurane ring, a benzothiophene ring, a dibenzofurane ring, and a dibenzothiophene ring.


3. The condensed cyclic compound of claim 1, wherein ring A_1 is selected from a benzene ring, a dibenzofurane ring, and a dibenzothiophene ring.

4. The condensed cyclic compound of claim 1, wherein L_1 is selected from groups represented by Formulae 3-1 to 3-56, and L_2 is selected from groups represented by Formulae 3-1, 3-15, 3-28, and 3-41 to 3-56:


Formula 3-1




Formula 3-2




Formula 3-3













Formula 3-4



Formula 3-5



-continued



Formula 3-6

Formula 3-7

Formula 3-8

Formula 3-9

Formula 3-10

Formula 3-11












Formula 3-12

Formula 3-13

Formula 3-14

Formula 3-15

-continued



Formula 3-16

Formula 3-17

Formula 3-18

Formula 3-19

Formula 3-20

Formula 3-21

Formula 3-22









Formula 3-23

Formula 3-24

Formula 3-25

Formula 3-26

-continued



Formula 3-27

Formula 3-28

Formula 3-29

Formula 3-30









Formula 3-31

Formula 3-32

Formula 3-33

Formula 3-34

-continued



Formula 3-35

Formula 3-36

Formula 3-37

Formula 3-38


Formula 3-39

Formula 3-40


Formula 3-41

Formula 3-42


-continued




Formula 3-43




Formula 3-44




Formula 3-45




Formula 3-46




Formula 3-47



Formula 3-48




Formula 3-49




Formula 3-50


-continued




Formula 3-51




Formula 3-52




Formula 3-53



Formula 3-54



Formula 3-55



Formula 3-56

wherein, in Formulae 3-1 to 3-56,

Y_1 is selected from O, S, and $C(Z_3)(Z_4)$,

Z_1 to Z_4 are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q_{11})(Q_{12})(Q_{13}),

wherein Q_{11} to Q_{13} are each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy

group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

d4 is an integer selected from 0 to 4,

d3 is an integer selected from 0 to 3,

d2 is an integer selected from 0 to 2, and

* and *' are each a binding site to a neighboring atom.

5. The condensed cyclic compound of claim 4, wherein

i) a1 is 0; or

ii) when a1 is not 0, at least one of groups L₁ is selected from groups represented by Formulae 3-15 to 3-56.


6. The condensed cyclic compound of claim 4, wherein

L₁ is selected from groups represented by Formulae 3-15, 3-28, 3-41, and 3-51,


L₂ is selected from groups represented by Formulae 3-1, 3-15, 3-28, 3-41, and 3-51, and

a1 and a2 are each independently 0, 1, or 2.


7. The condensed cyclic compound of claim 1, wherein a group represented by *-(L₁)_{a1}-*' is selected from groups represented by Formulae 4-1 to 4-39:




Formula 4-1




Formula 4-2




Formula 4-3



Formula 4-4




Formula 4-5




Formula 4-6


-continued




Formula 4-7




Formula 4-8




Formula 4-9




Formula 4-10




Formula 4-11



Formula 4-12




Formula 4-13




Formula 4-14

-continued


Formula 4-15




Formula 4-22




Formula 4-23




Formula 4-24




Formula 4-25




Formula 4-26




Formula 4-18




Formula 4-19



Formula 4-20




-continued




Formula 4-27

-continued




Formula 4-33


Formula 4-28




Formula 4-34




Formula 4-29




Formula 4-35




Formula 4-30




Formula 4-36




Formula 4-31



Formula 4-37




Formula 4-32




-continued

Formula 4-38



Formula 4-39



wherein, in Formulae 4-1 to 4-39,

X_{21} is N or C(Z_{21}), X_{22} is N or C(Z_{22}), X_{23} is N or C(Z_{23}), X_{24} is N or C(Z_{24}), X_{31} is N or C(Z_{31}), X_{32} is N or C(Z_{32}), X_{33} is N or C(Z_{33}), X_{34} is N or C(Z_{34}), X_{41} is N or C(Z_{41}), X_{42} is N or C(Z_{42}), X_{43} is N or C(Z_{43}), and X_{44} is N or C(Z_{44}), provided that at least one of X_{21} to X_{24} is not N, provided that at least one of X_{31} to X_{34} is not N, and provided that at least one of X_{41} to X_{44} is not N,

Z_{21} to Z_{24} , Z_{31} to Z_{34} , and Z_{41} to Z_{44} are each independently selected from a hydrogen, a deuterium, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-\text{Si}(Q_i)(Q_{12})(Q_{13})$,

wherein Q_{11} to Q_{13} are each independently a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, and

* and *¹ are each a binding site to a neighboring atom.

8. The condensed cyclic compound of claim 1, wherein R_1 to R_8 , R_{11} to R_{18} , and R_{31} are each independently selected from

a hydrogen, a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, and a C_1 - C_{10} alkoxy group;

a C_1 - C_{10} alkyl group and a C_1 - C_{10} alkoxy group, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a

hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-\text{Si}(Q_{21})(Q_{22})(Q_{23})$; and

$-\text{Si}(Q_1)(Q_2)(Q_3)$,

wherein Q_1 to Q_3 and Q_{21} to Q_{23} are each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group.

9. The condensed cyclic compound of claim 1, wherein R_1 to R_8 , R_{11} to R_{18} , and R_{31} are each independently selected from

a hydrogen, a deuterium, $-\text{F}$, a cyano group, a C_1 - C_{10} alkyl group, and a C_1 - C_{10} alkoxy group;

a C_1 - C_{10} alkyl group and a C_1 - C_{10} alkoxy group, each substituted with at least one selected from a deuterium, $-\text{F}$, and a cyano group;

a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;


a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, $-\text{F}$, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-\text{Si}(Q_{21})(Q_{22})(Q_{23})$; and

$-\text{Si}(Q_1)(Q_2)(Q_3)$,


Q_1 to Q_3 and Q_{21} to Q_{23} are each independently a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group.

10. The condensed cyclic compound of claim 1, wherein at least one of X_3 , X_6 , X_{13} , and X_{16} is C(CN).


11. The condensed cyclic compound of claim 1, wherein a group represented by




is selected from groups represented by Formulae 5-1 to 5-60:




Formula 5-1




Formula 5-2




Formula 5-3




Formula 5-4




Formula 5-5



Formula 5-6




Formula 5-7




Formula 5-8

-continued


Formula 5-9




Formula 5-10




Formula 5-11




Formula 5-12




Formula 5-13




Formula 5-14




Formula 5-15




Formula 5-16




Formula 5-17




-continued




Formula 5-18




Formula 5-19




Formula 5-20




Formula 5-21




Formula 5-22



Formula 5-23




Formula 5-24




Formula 5-25


-continued




Formula 5-26




Formula 5-27




Formula 5-28




Formula 5-29




Formula 5-30



Formula 5-31












Formula 5-32



Formula 5-33

-continued



Formula 5-34

Formula 5-35

Formula 5-36

Formula 5-37

Formula 5-38










Formula 5-39

Formula 5-40

Formula 5-41

Formula 5-42

-continued



Formula 5-43

Formula 5-44

Formula 5-45

Formula 5-46

Formula 5-47









Formula 5-48

Formula 5-49

Formula 5-50


Formula 5-51

-continued



-continued

Formula 5-60



Formula 5-52

Formula 5-53

wherein, in Formulae 5-1 to 5-60, * is a binding site to a neighboring atom.

12. The condensed cyclic compound of claim 1, represented by one of Formulae 1A to 1D:

Formula 5-54

Formula 5-55


Formula 5-56

Formula 5-57


Formula 5-58

Formula 5-59


Formula 1A



Formula 1B




Formula 1C




-continued


Formula 1D



wherein, in Formulae 1A to 1D,
 ring A_1 is independently selected from a benzene ring, a dibenzofurane ring, and a dibenzothiophene ring,
 L_1 is selected from groups represented by Formulae 3-15, 3-28, 3-41, and 3-51,
 L_2 is selected from groups represented by Formulae 3-1, 3-15, 3-28, 3-41, and 3-51,
 a_1 and a_2 are each independently selected from 0, 1, and 2,
 R_1 to R_8 , R_{11} to R_{18} , and R_{31} are each independently selected from
 a hydrogen, a deuterium, —F, a cyano group, a C_1 - C_{10} alkyl group, and a C_1 - C_{10} alkoxy group;
 a C_1 - C_{10} alkyl group and a C_1 - C_{10} alkoxy group, each substituted with at least one selected from a deuterium, —F, and a cyano group;
 a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;
 a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q_{21})(Q_{22})(Q_{23}); and
 —Si(Q_1)(Q_2)(Q_3),
 wherein Q_1 to Q_3 and Q_{21} to Q_{23} are each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,
 b_1 is 0 or 1, and
 c_1 is 1 or 2;




Formula 3-1




Formula 3-15

-continued


Formula 3-28




Formula 3-41




Formula 3-51



wherein, in Formulae 3-1, 3-15, 3-28, 3-41, and 3-51,
 Y_1 is selected from 0, S, and C(Z_3)(Z_4),
 Z_1 to Z_4 are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q_{11})(Q_{12})(Q_{13}),
 wherein Q_{11} to Q_{13} are each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,
 d_4 is an integer selected from 0 to 4,
 d_3 is an integer selected from 0 to 3, and
 * and *' are each a binding site to a neighboring atom.
13. The condensed cyclic compound of claim 12, wherein a group represented by









is selected from groups represented by Formulae 5-1 to 5-3, 5-31, 5-39, 5-47, and 5-55:




Formula 5-1

-continued



14. The condensed cyclic compound of claim 1, represented by one of Compounds 1 to 336:



Formula 5-2

Formula 5-3

Formula 5-31






Formula 5-39

Formula 5-47

Formula 5-55

1

-continued



2


3

4


5

6


-continued




7



8




9




10


-continued




11




12



13








14








15


-continued



-continued




-continued




26


-continued




29




27



30




28




31

-continued




32


-continued




35




33



36




34




37

-continued




38


-continued




41




39



42




40




43

-continued




44


-continued




47




45




48



46




49




50

-continued




51


-continued




56




52




57




53




58




54



59







55







60


-continued




-continued




-continued



69




70




71


-continued




72



73




74




75

-continued




76


-continued




80




77




81




78



82




79




83

-continued




84


-continued




87




85



88




86




89

-continued




90


-continued




93




91



94




92




95

-continued




96


-continued




100




97




101




98



102




99




103

-continued




104


-continued




108




105




109




106



110




107




111

-continued




112


-continued




116




113




117




114



118



115




119


-continued

-continued


120




123




121




124



122




-continued




125


-continued



127




126




128

121

-continued




129




130

-continued


131




132



133




-continued




134


-continued




137




135



138




136




139

-continued




140


-continued




143




141



144




142




145

-continued




146


-continued




150




147




151




148



152




149




153


-continued




154



155




156




157


-continued



158




159




160

-continued




161


-continued




164




162



165




163




166

-continued





167

-continued




170

168




171


172



169




173




-continued


-continued




174




177




175




178



176




179



176


-continued

180




-continued


183




181




184




182



185




-continued




186

-continued




189



187



188









190




191


-continued




-continued




201




202



203




204




205


-continued



206









207




208

-continued

-continued




-continued




215

-continued




219


216




220




217




221




218



222




-continued




223


-continued




227




224




228



225




226








229


-continued



-continued




-continued




236


-continued




239




237



240




238




241

-continued




242

-continued




243

246





244


247




245



248




-continued




249


-continued




252




250



253




251








254




-continued



-continued




-continued



-continued


261

264




262

265




263

266




-continued




267


-continued




271




268




272




269




273



270




274




275


-continued




276




277



278




279




280


-continued




281



282




283




284

-continued




285


-continued




288




286



289




287




290


-continued



291




292




293


-continued



294







295






296


-continued




-continued




-continued



-continued




-continued




313


-continued




317




314




318




315



319




316



320


-continued

321




-continued


325




322




326




323



327



324





-continued

-continued



331

328





332

329





333

330




-continued



-continued

336



15. An organic light-emitting device comprising:
a first electrode;
a second electrode; and
an organic layer disposed between the first electrode and the second electrode,
wherein the organic layer comprises an emission layer and at least one condensed cyclic compound represented by Formula 1 of claim 1.

16. The organic light-emitting device of claim 15, wherein the first electrode is an anode, the second electrode is a cathode,
the organic layer comprises a hole transport region disposed between the first electrode and the emission layer and an electron transport region disposed between the emission layer and the second electrode,
wherein the hole transport region comprises at least one selected from a hole injection layer, a hole transport layer, and an electron blocking layer, and
wherein the electron transport region comprises at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

17. The organic light-emitting device of claim 15, wherein the emission layer comprises the at least one condensed cyclic compound represented by Formula 1.

18. The organic light-emitting device of claim 15, wherein the emission layer comprises the at least one condensed cyclic compound represented by Formula 1, wherein the emission layer further comprises a phosphorescent dopant, and wherein an amount of the at least one condensed cyclic compound is larger than an amount of the phosphorescent dopant.

19. The organic light-emitting device of claim 17, wherein the emission layer emits blue light.

20. The organic light-emitting device of claim 15, wherein the emission layer comprises the condensed cyclic compound represented by Formula 1, and wherein the condensed cyclic compound represented by Formula 1 is a thermally activated delayed fluorescence emitter.

专利名称(译)	缩合环状化合物和包括其的有机发光器件		
公开(公告)号	US20160380210A1	公开(公告)日	2016-12-29
申请号	US15/145158	申请日	2016-05-03
[标]申请(专利权)人(译)	三星电子株式会社		
申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD. 三星SDI CO. , LTD.		
当前申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD. 三星SDI CO. , LTD.		
[标]发明人	KIM HYUNJUNG CHAE MIYOUNG KIM SANGMO JEON SOONOK CHUNG YEONSOOK JUNG YONGSIK HUH DALHO SON YOUNGMOK LEE NAMHEON		
发明人	KIM, HYUNJUNG CHAE, MIYOUNG KIM, SANGMO JEON, SOONOK CHUNG, YEONSOOK JUNG, YONGSIK HUH, DALHO SON, YOUNGMOK LEE, NAMHEON		
IPC分类号	H01L51/00 C09K11/02 C07D209/86 C09K11/06		
CPC分类号	H01L51/0072 C09K2211/1022 H01L51/009 H01L51/0085 H01L51/008 C09K11/02 C07D209/86 H01L51/5206 H01L51/5221 H01L51/5028 H01L51/5056 H01L51/5072 H01L51/5088 H01L51/5092 H01L51/5096 H01L51/5016 C09K2211/1007 C09K2211/1029 H01L51/5004 H01L2251/552 C09K2211/185 C09K2211/1044 C09K11/06 C07D209/88 C07D405/14 C07D409/14 C09K2211/1088 C09K2211/1092 H01L51/0073 H01L51/0074 H01L51/50 C07D403/10 H01L51/0061 H01L51/5012		
优先权	1020150089088 2015-06-23 KR 1020160039619 2016-03-31 KR		
其他公开文献	US10062852		
外部链接	Espacenet USPTO		

摘要(译)

由式1表示的耦合环状化合物：其中，在公式1中，组 R^1 和变量 R^2 与规范中描述的相同。

Formula 1

