



US 20170213985A1

(19) **United States**(12) **Patent Application Publication**
LEE et al.(10) **Pub. No.: US 2017/0213985 A1**(43) **Pub. Date: Jul. 27, 2017**(54) **ORGANIC OPTOELECTRONIC DEVICE
AND DISPLAY DEVICE****Publication Classification**(71) Applicant: **SAMSUNG SDI CO., LTD.**, Yongin-si,
Gyeonggi-do (KR)(72) Inventors: **Han-ILL LEE**, Suwon-si, Gyeonggi-do
(KR); **Chang-Woo KIM**, Suwon-si,
Gyeonggi-do (KR); **Dong-Wan RYU**,
Suwon-si, Gyeonggi-do (KR);
Young-Sung PARK, Suwon-si,
Gyeonggi-do (KR); **Chang-Ju SHIN**,
Suwon-si, Gyeonggi-do (KR); **Eun-Sun**
YU, Suwon-si, Gyeonggi-do (KR);
Sung-Hyun JUNG, Suwon-si,
Gyeonggi-do (KR); **Su-Jin HAN**,
Suwon-si, Gyeonggi-do (KR)(21) Appl. No.: **15/328,180**(22) PCT Filed: **Dec. 11, 2014**(86) PCT No.: **PCT/KR2014/012217**

§ 371 (c)(1),

(2) Date: **Jan. 23, 2017**(30) **Foreign Application Priority Data**


Aug. 13, 2014 (KR) 10-2014-0105353

(51) **Int. Cl.****H01L 51/00** (2006.01)**C07D 405/12** (2006.01)**C07D 209/86** (2006.01)**C09K 11/02** (2006.01)**C09K 11/06** (2006.01)(52) **U.S. Cl.**CPC **H01L 51/0072** (2013.01); **C09K 11/025**
(2013.01); **C09K 11/06** (2013.01); **C07D**
209/86 (2013.01); **H01L 51/0061** (2013.01);
H01L 51/006 (2013.01); **C07D 405/12**
(2013.01); **C09K 2211/1011** (2013.01); **H01L**
51/5064 (2013.01)


(57)

ABSTRACT

The present invention relates to an organic photoelectric device and a display device comprising the organic photoelectric device, the organic photoelectric device comprising: an anode; a cathode facing the anode; a light-emitting layer interposed between the anode and cathode; a hole transport layer interposed between the anode and the light-emitting layer; and an auxiliary hole transport layer interposed between the hole transport layer and the light-emitting layer, wherein the hole transport layer comprises a compound represented by Chemical formula I, and the auxiliary hole transport layer comprises a compound represented by Chemical formula II. Chemical formulas I and II are the same as set forth in the description.



【Figure 1】



ORGANIC OPTOELECTRONIC DEVICE AND DISPLAY DEVICE

TECHNICAL FIELD

[0001] An organic optoelectric device and a display device are disclosed.

BACKGROUND ART

[0002] An organic optoelectric device is a device that converts electrical energy into photoenergy, and vice versa. An organic optoelectric device may be classified as follows in accordance with its driving principles. One is a photoelectric diode where excitons are generated by photoenergy, separated into electrons and holes, and are transferred to different electrodes to generate electrical energy, and the other is a light emitting device where a voltage or a current is supplied to an electrode to generate photoenergy from electrical energy. Examples of the organic optoelectric device may be an organic photoelectric device, an organic light emitting diode, an organic solar cell, and an organic photo conductor drum. Of these, an organic light emitting diode (OLED) has recently drawn attention due to an increase in demand for flat panel displays. The organic light emitting diode converts electrical energy into light by applying current to an organic light emitting material and has a structure in which an organic layer is disposed between an anode and a cathode.

DISCLOSURE


Technical Problem

[0003] An embodiment provides an organic optoelectric device capable of realizing a long life-span and high efficiency characteristics.

[0004] Another embodiment provides a display device including the organic optoelectric device.

Technical Solution

[0005] According to one embodiment, an organic optoelectric device includes an anode and a cathode facing each other, a light-emitting layer disposed between the anode and cathode, a hole transport layer disposed between the anode and the light-emitting layer and an auxiliary hole transport layer disposed between the hole transport layer and the light-emitting layer, the hole transport layer includes a compound represented by Chemical Formula I and, the hole transport auxiliary layer includes a compound represented by Chemical Formula II.



[Chemical Formula I]

[0006] In Chemical Formula I,

[0007] R^1 to R^3 are independently a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, or a combination thereof,


[0008] R^4 to R^{10} are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C3 to C30 cycloalkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, a substituted or unsubstituted C6 to C30 arylamine group, a substituted or unsubstituted C1 to C30 alkoxy group, a substituted or unsubstituted C3 to C40 silyl group, a substituted or unsubstituted C3 to C40 silyloxy group, a substituted or unsubstituted C1 to C30 alkylthiol group, a substituted or unsubstituted C6 to C30 arylthiol group, a halogen, a halogen-containing group, a cyano group, a hydroxyl group, an amino group, a nitro group, or a combination thereof,

[0009] adjacent two of R^4 to R^{10} are fused to provide a ring, and

[0010] L^1 to L^3 are independently a single bond, a substituted or unsubstituted C1 to C30 alkylene group, a substituted or unsubstituted C3 to C30 cycloalkylene group, a substituted or unsubstituted C6 to C30 arylene group, a substituted or unsubstituted C2 to C30 heteroarylene group, a substituted or unsubstituted C6 to C30 aryleneamine group, a substituted or unsubstituted C1 to C30 alkoxylylene group, a substituted or unsubstituted C1 to C30 aryloxylylene group, a substituted or unsubstituted C2 to C30 alkenylene group, a substituted or unsubstituted C2 to C30 alkynylene group, or a combination thereof,

[0011] wherein "substituted" refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group,

[Chemical Formula II]



[0012] wherein, in Chemical Formula II,

[0013] R^{11} to R^{24} are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, or a combination thereof,

[0014] adjacent two of R^{11} to R^{17} and R^{18} to R^{24} are fused to provide a ring,

[0015] R^{25} and R^{26} are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group,

a substituted or unsubstituted C3 to C30 cycloalkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, a substituted or unsubstituted C6 to C30 arylamine group, a substituted or unsubstituted C1 to C30 alkoxy group, a substituted or unsubstituted C3 to C40 silyl group, a substituted or unsubstituted C1 to C30 alkylthiol group, a substituted or unsubstituted C6 to C30 arylthiol group, a halogen, a halogen-containing group, a cyano group, a hydroxyl group, an amino group, a nitro group, or a combination thereof, and

[0016] n is an integer ranging from 1 to 4,

[0017] wherein “substituted” refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group.

[0018] According to another embodiment, a display device including the organic optoelectric device is provided.

Advantageous Effects

[0019] An organic optoelectric device having a long life-span and high efficiency may be realized.

DESCRIPTION OF THE DRAWINGS

[0020] FIG. 1 is a schematic cross-sectional view showing an organic optoelectric device according to an embodiment.
[0021]

<Description of Symbols>	
10: anode	20: cathode
30: organic layer	31: hole transport layer
32: light-emitting layer	33: hole transport auxiliary layer
34: electron transport layer (ETL)	

MODE FOR INVENTION

[0022] Hereinafter, embodiments of the present invention are described in detail. However, these embodiments are exemplary, the present invention is not limited thereto and the present invention is defined by the scope of claims.

[0023] In the present specification, when a definition is not otherwise provided, “substituted” refers to one substituted with deuterium, a halogen, a hydroxy group, an amino group, a substituted or unsubstituted C1 to C30 amine group, a nitro group, a substituted or unsubstituted C1 to C40 silyl group, C1 to C30 alkyl group, C1 to C10 alkylsilyl group, C3 to C30 cycloalkyl group, C2 to C30 heterocycloalkyl group, C6 to C30 aryl group, C2 to C30 heteroaryl group, C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group such as a trifluoromethyl group, and the like, or a cyano group, instead of at least one hydrogen of a substituent or a compound.

[0024] In addition, two adjacent substituents of the substituted halogen, hydroxy group, amino group, substituted or unsubstituted C1 to C20 amine group, nitro group, substituted or unsubstituted C3 to C40 silyl group, C1 to C30 alkyl group, C1 to C10 alkylsilyl group, C3 to C30 cycloalkyl

group, C2 to C30 heterocycloalkyl group, C6 to C30 aryl group, C2 to C30 heteroaryl group, C1 to C20 alkoxy group, fluoro group, C1 to C10 trifluoroalkyl group such as trifluoromethyl group and the like, or cyano group may be fused with each other to form a ring. For example, the substituted C6 to C30 aryl group may be fused with another adjacent substituted C6 to C30 aryl group to form a substituted or unsubstituted fluorene ring.

[0025] In the present specification, when specific definition is not otherwise provided, “hetero” refers to one including at least one hetero atom selected from the group consisting of N, O, S, P, and Si, and remaining carbons in one functional group.

[0026] In the present specification, when a definition is not otherwise provided, “alkyl group” refers to an aliphatic hydrocarbon group. The alkyl group may be “a saturated alkyl group” without any double bond or triple bond.

[0027] The alkyl group may be a C1 to C30 alkyl group. More specifically, the alkyl group may be a C1 to C20 alkyl group or a C1 to C10 alkyl group. For example, a C1 to C4 alkyl group may have 1 to 4 carbon atoms in an alkyl chain which may be selected from methyl, ethyl, propyl, isopropyl, n-butyl, iso-butyl, sec-butyl, and t-butyl.

[0028] Specific examples of the alkyl group may be a methyl group, an ethyl group, a propyl group, an isopropyl group, a butyl group, an isobutyl group, a t-butyl group, a pentyl group, a hexyl group, a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and the like.

[0029] In the present specification, “aryl group” refers to a substituent including all element of the cycle having p-orbitals which form conjugation, and may be monocyclic, polycyclic or fused ring polycyclic (i.e., rings sharing adjacent pairs of carbon atoms) functional group.

[0030] In the present specification, “heterocyclic group” may include at least one hetero atom selected from N, O, S, P, and Si in a cyclic compound such as an aryl group, a cycloalkyl group, a fused ring thereof, or a combination thereof, and remaining carbons. When the heterocyclic group is a fused ring, the entire ring or each ring of the heterocyclic group may include one or more heteroatoms. Accordingly, the heterocyclic group is a general concept of a heteroaryl group.

[0031] More specifically, the substituted or unsubstituted C6 to C30 aryl group and/or the substituted or unsubstituted C2 to C30 heterocyclic group may be a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthracenyl group, a substituted or unsubstituted phenanthrylene group, a substituted or unsubstituted naphthacenyl group, a substituted or unsubstituted pyrenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted p-terphenyl group, a substituted or unsubstituted m-terphenyl group, a substituted or unsubstituted chrysenyl group, a substituted or unsubstituted triphenylenyl group, a substituted or unsubstituted perylenyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted indenyl group, a substituted or unsubstituted furanyl group, a substituted or unsubstituted thiophenyl group, a substituted or unsubstituted pyrrolyl group, a substituted or unsubstituted pyrazolyl group, a substituted or unsubstituted imidazolyl group, a substituted or unsubstituted triazolyl group, a substituted or unsubstituted oxazolyl group, a substituted or unsubstituted thiazolyl group, a substituted or unsubstituted

oxadiazolyl group, a substituted or unsubstituted thiadiazolyl group, a substituted or unsubstituted pyridyl group, a substituted or unsubstituted pyrimidinyl group, a substituted or unsubstituted pyrazinyl group, a substituted or unsubstituted triazinyl group, a substituted or unsubstituted benzofuranyl group, a substituted or unsubstituted benzothiophenyl group, a substituted or unsubstituted benzimidazolyl group, a substituted or unsubstituted indolyl group, a substituted or unsubstituted quinolyl group, a substituted or unsubstituted isoquinolyl group, a substituted or unsubstituted quinazolinyl group, a substituted or unsubstituted quinoxalinyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted benzoxazinyl group, a substituted or unsubstituted benzthiazinyl group, a substituted or unsubstituted acridinyl group, a substituted or unsubstituted phenazinyl group, a substituted or unsubstituted phenothiazinyl group, a substituted or unsubstituted phenoxazinyl group, a substituted or unsubstituted dibenzofuranyl group, a substituted or unsubstituted dibenzothiophenyl group, a substituted or unsubstituted carbazole group, a combination thereof, or a fused form of combinations thereof, but are not limited thereto.

[0032] In the present specification, a single bond refers to a direct bond not by carbon or a hetero atom except carbon, and specifically the meaning that L is a single bond means that a substituent linked to L directly bonds with a central core. That is, in the present specification, the single bond does not refer to methylene that is bonded via carbon.

[0033] In the specification, hole characteristics refer to an ability to donate an electron to form a hole when an electric field is applied and that a hole formed in the anode may be easily injected into the light-emitting layer, and a hole formed in a light-emitting layer may be easily transported into an anode and transported in the light-emitting layer due to conductive characteristics according to a highest occupied molecular orbital (HOMO) level.

[0034] In addition, electron characteristics refer to an ability to accept an electron when an electric field is applied and that an electron formed in a cathode may be easily injected into the light-emitting layer, and an electron formed in a light-emitting layer may be easily transported into a cathode and transported in the light-emitting layer due to conductive characteristics according to a lowest unoccupied molecular orbital (LUMO) level.

[0035] Hereinafter, an organic optoelectric device according to an embodiment is described.

[0036] The organic optoelectric device may be any device to convert electrical energy into photoenergy and vice versa without particular limitation, and may be, for example an organic photoelectric device, an organic light emitting diode, an organic solar cell, and an organic photo-conductor drum.

[0037] Herein, an organic light emitting diode as one example of an organic optoelectric device is described, but the present invention can be applied to other organic optoelectric devices in the same way.

[0038] In the drawings, the thickness of layers, films, panels, regions, etc., are exaggerated for clarity. Like reference numerals designate like elements throughout the specification. It will be understood that when an element such as a layer, film, region, or substrate is referred to as being "on" another element, it can be directly on the other element or intervening elements may also be present. In contrast, when

an element is referred to as being "directly on" another element, there are no intervening elements present.

[0039] FIG. 1 is a schematic cross-sectional view showing organic optoelectric devices according to one embodiment.

[0040] Referring to FIG. 1, an organic optoelectric device according to one embodiment includes an anode 10 and a cathode 20 facing each other and an organic layer 30 between the anode 10 and the cathode 20.


[0041] The anode 10 may be made of a conductor having a large work function to help hole injection, and may be for example metal, metal oxide and/or a conductive polymer. The anode 10 may be, for example a metal such as nickel, platinum, vanadium, chromium, copper, zinc, and gold or an alloy thereof; metal oxide such as zinc oxide, indium oxide, indium tin oxide (ITO), indium zinc oxide (IZO), and the like; a combination of metal and oxide such as ZnO and Al or SnO₂ and Sb; a conductive polymer such as poly(3-methylthiophene), poly(3,4-(ethylene-1,2-dioxy)thiophene) (PEDT), polypyrrole, and polyaniline, but is not limited thereto.

[0042] The cathode 20 may be made of a conductor having a small work function to help electron injection, and may be for example metal, metal oxide and/or a conductive polymer. The cathode 20 may be for example a metal or an alloy thereof such as magnesium, calcium, sodium, potassium, titanium, indium, yttrium, lithium, gadolinium, aluminum silver, tin, lead, cesium, barium, and the like; a multi-layer structure material such as LiF/Al, LiO₂/Al, LiF/Ca, LiF/Al and BaF₂/Ca, but is not limited thereto.

[0043] The organic layer 30 includes a hole transport layer 31, a light-emitting layer 32, and a hole transport auxiliary layer 33 between the hole transport layer 31 and the light-emitting layer 32.

[0044] The hole transport layer 31 facilitates hole transport from the anode 10 to the light-emitting layer 32 and the hole transport layer according to an embodiment includes a compound represented by Chemical Formula I.

[Chemical Formula I]



[0045] In Chemical Formula I,

[0046] R¹ to R³ are independently a substituted or unsubstituted C₆ to C₃₀ aryl group, a substituted or unsubstituted C₂ to C₃₀ heterocyclic group, or a combination thereof,

[0047] R⁴ to R¹⁰ are independently hydrogen, deuterium, a substituted or unsubstituted C₁ to C₃₀ alkyl group, a substituted or unsubstituted C₃ to C₃₀ cycloalkyl group, a substituted or unsubstituted C₆ to C₃₀ aryl group, a substituted or unsubstituted C₂ to C₃₀ heteroaryl group, a substituted or unsubstituted C₆ to C₃₀ arylamine group, a substituted or unsubstituted C₁ to C₃₀ alkoxy group, a substituted or unsubstituted C₃ to C₄₀ silyl group, a substituted or unsubstituted C₃ to C₄₀ silyloxy group, a sub-

stituted or unsubstituted C1 to C30 alkylthiol group, a substituted or unsubstituted C6 to C30 arylthiol group, a halogen, a halogen-containing group, a cyano group, a hydroxyl group, an amino group, a nitro group, or a combination thereof, and

[0048] adjacent two of R^4 to R^{10} are fused to provide a ring, and

[0049] L^1 to L^3 are independently a single bond, a substituted or unsubstituted C1 to C30 alkylene group, a substituted or unsubstituted C3 to C30 cycloalkylene group, a substituted or unsubstituted C6 to C30 arylene group, a substituted or unsubstituted C2 to C30 heteroarylene group, a substituted or unsubstituted C6 to C30 aryleneamine group, a substituted or unsubstituted C1 to C30 alkoxy group, a substituted or unsubstituted C1 to C30 aryloxy group, a substituted or unsubstituted C2 to C30 alkenylene group, a substituted or unsubstituted C2 to C30 alkynylene group, or a combination thereof,

[0050] wherein “substituted” refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group.


[0051] The compound represented by Chemical Formula I simultaneously includes a carbazole group and an amine group and thereby has a HOMO energy level adjusted in a range of -4.5 eV to -5.0 eV.

[0052] The compound having a HOMO energy level within the range may have excellent hole characteristics and thus efficiently transfer holes in a hole transport layer.

[0053] In addition, the compound represented by Chemical Formula II includes two carbazole groups and thus may have a HOMO energy level adjusted in a range of -4.9 eV to -5.5 eV.


[0054] The compound represented by Chemical Formula I may be represented by one of Chemical Formula I-1 to Chemical Formula I-5 in accordance with that a substituent of a carbazole group is present or not and a substituent of a carbazole is fused or not.

[Chemical Formula I-1]




-continued


[Chemical Formula I-2]




[Chemical Formula I-3]



[Chemical Formula I-4]



[Chemical Formula I-5]




[0055] In Chemical Formula I-1 to Chemical Formula I-5, R^1 to R^{10} and to L^3 are the same as defined as above, and


[0056] R^{27} and R^{28} are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, or a combination thereof,


[0057] wherein “substituted” refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro

[Group I]



-continued






[0059] In Group I, * is a linking point,


[0060] “substituted” refers to replacement of at least one hydrogen with deuterium, halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group.

[0061] In addition, the compound represented by Chemical Formula I may be represented by Chemical Formula I-6 or I-7 when the most specific L^3 selected from Group I is applied thereto.

[Chemical Formula I-6]



[Chemical Formula I-7]




[0062] R^1 to R^{10} , L^1 , and L^2 are the same as described above.

[0063] Specifically, the R^4 to R^{10} of Chemical Formula I may independently be hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, or a substituted or unsubstituted C6 to C30 aryl group.


[0064] As specific examples, R^1 to R^3 of Chemical Formula I may independently be a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, or a combination thereof, for example, the substituted or unsubstituted C6 to C30 aryl group may be a substituted or unsubstituted phenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted terphenyl group, a substituted or unsubstituted quaterphenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthracenyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted triphenylene group, combination thereof, or a fused form thereof, and the substituted or unsubstituted C2 to C30 heterocyclic group may be a substituted or unsubstituted carbazolyl group, a substituted or unsubstituted benzofuran group, a substituted or unsubstituted benzothiophenyl group, a substituted or unsubstituted dibenzofuran group, a substituted or unsubstituted dibenzothiophenyl group, or a combination thereof.

[0065] On the other hand, as more specific examples, the substituted or unsubstituted C6 to C30 aryl group and the substituted or unsubstituted C2 to C30 heterocyclic group may be selected from substituted or unsubstituted groups of Group II.

[Group II]



-continued




[0066] In Group II, * is a linking point,

[0067] wherein “substituted” refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group.







[0068] The compound represented by Chemical Formula I may be selected from compounds of Group III, but is not limited thereto.

[Group III]






-continued





-continued



-continued




-continued




-continued

17




-continued

20





21


18




19



22




23




-continued


24




25



26




27




-continued


28




29




30



31




-continued




32


33




34



35




-continued




36


37



38




39



-continued


40




41

-continued


44




45




42





46



43




47




-continued

48




-continued

51





52


49




50



53




54




-continued


55




56



57




58




-continued


59



60




61




-continued

62




-continued


65



63





66




67

64




-continued


68




69



70




71




-continued


72




73



74




75




-continued


76




77



78




79




-continued


80




81



82




83




-continued


84




85



86




87




-continued


88




89



90




91



-continued



92



93



-continued

96





94

97




95

98




-continued


99




10



101




102




-continued


103



104




105




-continued

106




-continued



109




107



108




111




112

-continued


113




114



115




116




-continued


117



118




119




-continued


120




121



122




123




-continued


124




125



126




127




-continued


128




129



130




131




-continued


132




133



134




135




-continued

-continued


136




139




137




140






138




141



-continued



[Chemical Formula II]



[0070] In Chemical Formula II,

[0071] R^{11} to R^{24} are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, or a combination thereof,

[0072] adjacent two of R^{11} to R^{17} and R^{18} to R^{24} are fused to provide a ring,

[0073] R^{25} and R^{26} are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C3 to C30 cycloalkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, a substituted or unsubstituted C6 to C30 arylamine group, a substituted or unsubstituted C1 to C30 alkoxy group, a substituted or unsubstituted C3 to C40 silyl group, a substituted or unsubstituted C1 to C30 alkylthiol group, a substituted or unsubstituted C6 to C30 arylthiol group, a halogen, a halogen-containing group, a cyano group, a hydroxyl group, an amino group, a nitro group, or a combination thereof, and

[0074] n is an integer ranging from 1 to 4,

[0075] wherein “substituted” refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group.

[0076] The compound represented by Chemical Formula II includes a linking group connected with one to four phenylenes and thus may have a flexible molecule structure compared with bicarbazole directly connected with no linking group, wherein this flexible molecule structure may effectively prevent stacking of the compound and thus improve thin film characteristics and resultantly increase process stability and simultaneously lower a deposition temperature.

[0077] However, the compound represented by Chemical Formula II has a HOMO energy level ranging from about -4.9 eV to -5.5 eV due to bicarbazole characteristics and thus may have deep energy compared with a known hole transport material.

[0078] The compound having the HOMO energy level may have remarkably deteriorated hole mobility compared with the known hole transport material, and accordingly when the compound represented by Chemical Formula II alone is used for a hole transport layer, holes are difficult to transfer from a hole injection layer (HIL).


[0079] Accordingly, the compound represented by Chemical Formula II for a hole transport auxiliary layer and the compound represented by Chemical Formula I for the hole

[0069] The hole transport auxiliary layer 33 may include a compound represented by Chemical Formula II.


transport layer may be used to supplement hole characteristics and thus realize an organic optoelectric device having high efficiency and a long life-span.

[0080] The compound represented by Chemical Formula II may be represented by one of Chemical Formulas II-1 to II-16 according to a kind of an intermediate linking group.


[Chemical Formula II-1]




[Chemical Formula II-2]




[Chemical Formula II-3]




[Chemical Formula II-4]




[Chemical Formula II-5]



[Chemical Formula II-6]




[Chemical Formula II-7]




-continued


[Chemical Formula II-8]




[Chemical Formula II-9]




[Chemical Formula II-10]



[Chemical Formula II-11]




[Chemical Formula II-12]




-continued

[Chemical Formula II-13]




[Chemical Formula II-14]




-continued

[Chemical Formula II-15]



[Chemical Formula II-16]



[0081] In Chemical Formula II-1 to Chemical Formula II-16, R^{11} to R^{26} are the same as described above.

[0082] The compounds represented by Chemical Formulas II-1 to II-16 includes a linking group connected with one to four phenylenes and thus has a flexible molecule structure, which may effectively prevent stacking of the compound and promote its deposition.

[0083] The R^{25} and R^{26} may independently be hydrogen, deuterium, a substituted or unsubstituted C6 to C30 aryl group, or a substituted or unsubstituted C2 to C30 heteroaryl group, and more specifically, the substituted or unsubstituted C6 to C30 aryl group may be a substituted or unsubstituted phenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted terphenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthracenyl group, a substituted or unsubstituted fluo-

renyl group, a substituted or unsubstituted triphenylene group, or a combination thereof, the substituted or unsubstituted C2 to C30 heteroaryl group, a substituted or unsubstituted pyridyl group, a substituted or unsubstituted pyrimidinyl group, a substituted or unsubstituted triazinyl group, or a combination thereof.

[0084] In addition, in the compound represented by Chemical Formula II, at least one hydrogen of R^{25} and R^{26} may be replaced or unreplaced by a phenyl group, a biphenyl group, a naphthyl group, a pyridyl group, a pyrimidinyl group, or a triazinyl group.







[0085] The R^{11} to R^{24} of Chemical Formula II may independently be hydrogen, deuterium, or a substituted or unsubstituted C6 to C30 aryl group.

[0086] Specifically, the substituted or unsubstituted C6 to C30 aryl group may be a substituted or unsubstituted phenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted o-terphenyl group, a substituted or unsubstituted p-terphenyl group, a substituted or unsubstituted m-terphenyl group, a substituted or unsubstituted

naphthyl group, or a combination thereof, but is not limited thereto.

[0087] The compound represented by Chemical Formula II may be, for example selected from compounds of Group IV, but is not limited thereto.


[Group IV]




-continued

7


8



9




10




-continued


11



12





13



-continued



14

15





16

17



18



19



-continued



20

21





22

23




24

25




-continued

26




27




-continued

28




29




-continued

30




31




-continued

32






33

34



35



36



-continued



37

38




39

40




41




-continued


42



43




44




-continued

45





46



-continued



47

48





49

50



51



52



-continued



53

54




55

56




57




-continued


58



59




60




-continued

61



62



63



-continued



64

65




66

67





68



-continued



69

70





71

72




73

74




-continued


75



76





77



-continued



78

79





80

81




82


83




-continued




84




85




86



87




88




89

-continued


90



91




92




-continued

93



94



95



-continued



96

97





98

99



100



101



-continued



102

103




104

105




106




-continued


107



108





109



-continued



110

111





112

113




114

115




-continued


116




117



118





119




-continued

120


121



122




123




-continued

124





125



-continued



126

127





128

129




130

131




-continued


132




133




134




135



136




137




-continued


138



139



140



[0088] As described above, the compound represented by Chemical Formula II which is advantageous for a deposition may be used for a hole transport auxiliary layer, while the compound represented by Chemical Formula I and having improved hole mobility is used for a hole transport layer, processibility and a life-span and efficiency of a device may be remarkably improved.

[0089] The compound represented by Chemical Formula I and the compound represented by Chemical Formula II may be applied in various combinations in each of the hole transport layer and the hole transport auxiliary layer.

[0090] The light-emitting layer **32** includes a host and a dopant.

[0091] The host is a matrix material having low self light emitting capability but high film forming capability and high light emitting capability.

[0092] The material used as a host may have electrons or holes injection property, a satisfactory film-formation, high heat resistance, a high exciton energy level, and excellent charge mobility, wherein a light emitting spectrum is overlapped with a dopant absorption spectrum, and a energy gap between Homo and Lumo should be wide.

[0093] A compound satisfying these properties may be an aromatic monocyclic compound, an aromatic condensed cyclic compound, a hetero monocyclic compound, a hetero condensed cyclic compound, a metal complex, a phi conjugated polymer compound, a sigma conjugated polymer compound, a metal complex, an amine derivative, a stilbene-based compound, a hydrazone-based compound, and the like.

[0094] In the present invention, known host materials may be used. For example, the host material may be selected from CBP (carbazole biphenyl), mCP (1,3-bis(carbazol-9-yl), 4,4'-bis(9-carbazol-yl)-2,2'-dimethyl-biphenyl (CDBP), 4,4',4"-tri(N-carbazolyl)triphenylamine (TCTA), 2,9-dimethyl-4,7-diphenyl-phenanthroline (BCP), 9,10-bis(4-(N-carbazolyl)phenyl)anthracene (BCPA), 3-(biphenyl-4-yl)-4-phenyl-5-(4-tert-butylphenyl)-1,2,4-triazole (TAZ), 1,1-bis(4-bis(4-methylphenyl)-aminophenyl)-cyclohexane (TAPC), tris-(8-hydroxyquinoline)aluminum (Alq₃), metal phthalocyanine, 4-biphenyloxolato aluminum(III)bis(2-methyl-8-quinolinato)4-phenylphenolate (BALq), N,N'-Bis(3-methylphenyl)-N,N'-diphenylbenzidine (TPD), 4,4'-bis{N-(1-naphthyl)-N-phenyl-amino}biphenyl (α -NPD), N-(4-(1E-2-(10-(4-(diphenylamino)styryl)anthracene-9-yl)vinyl)phenyl)-N-phenylbenzeneamine (BSA-2), 4,4'-bis(2,2'diphenylvinyl)-1,1'-biphenyl (DPVBi), 2-tert-butylphenyl-5-biphenyl-1,3,4-oxadiazole (PBD), poly(vinylcarbazole) (PVK) and derivatives thereof, carbazole substituted polyacetylenes (PAC), poly(p-phenylene vinylene) (PPV) and derivatives thereof, poly[2-methoxy-5-(2'-ethylhexyloxy)-1,4-phenylenevinylene-co-4,4'-bisphenylenevinylene] (MEH-BP-PPV), poly(thiophene) (PAT) and derivatives thereof, poly(9,9'-dialkylfluorene) (PDAF) and derivatives thereof, poly(p-phenylene) (PPP), and derivatives thereof, poly(1,4-naphthalene vinylene) (PNV), and derivatives thereof, polystyrene(PS) and derivatives thereof, polysilane and derivatives thereof, poly(arylenevinylene) (PAV) and derivatives thereof, but is not limited thereto.

[0095] The dopant is mixed with a host in a small amount to cause light emission, and may be generally a material such as a metal complex that emits light by multiple excitation into a triplet or more. The dopant may be, for example

an inorganic, organic, or organic/inorganic compound, and one or more kinds thereof may be used.

[0096] The dopant may be a red, green, or blue dopant, for example a phosphorescent dopant. The phosphorescent dopant may be an organic metal compound including Ir, Pt, Os, Ti, Zr, Hf, Eu, Tb, Tm, Fe, Co, Ni, Ru, Rh, Pd, or a combination thereof. The phosphorescent dopant may be, for example a compound represented by Chemical Formula Z, but is not limited thereto.

L₂MX

[Chemical Formula Z]

[0097] In Chemical Formula Z, M is a metal, and L and X are the same or different, and are a ligand to form a complex compound with M.

[0098] The M may be, for example Ir, Pt, Os, Ti, Zr, Hf, Eu, Tb, Tm, Fe, Co, Ni, Ru, Rh, Pd, or a combination thereof, and the L and X may be, for example a bidentate ligand.

[0099] The light-emitting layer **32** may include a material that emits red, green, and blue and white light, and for example, when the light-emitting layer **32** emits red light, it includes a host material of CBP (carbazole biphenyl) or mCP (1,3-bis(carbazol-9-yl), and a phosphorescent material including a dopant including one or more selected from PIQIr(acac) (bis(1-phenylisoquinoline)acetylacetonate iridium), PQIr(acac) (bis(1-phenylquinoline)acetylacetonate iridium), PQIr(tris(1-phenylquinoline)iridium) and PtOEP (octaethylporphyrin platinum), or a fluorescent material including PBD:Eu(DBM)₃ (Phen), or perylene, but is not limited thereto. When the light-emitting layer **32** emits green light, it includes a host material including CBP or mCP, and a phosphorescent material including a dopant including Ir(ppy)₃(fac tris(2-phenylpyridine)iridium), or a fluorescent material including Alq₃(tris(8-hydroxyquinolino)aluminum), but is not limited thereto. When the light-emitting layer **32** emits blue light, it includes a host material including CBP or mCP and a phosphorescent material including a dopant including (4,6-F₂ppy)₂Irpic. On the contrary, the light-emitting layer **32** may be made of a fluorescent material including any one selected from spiro-DPVBi, spiro-6P, distyryl benzene (DSB), distyryl arylene (DSA), a PFO-based polymer, and a PPV-based polymer, but is not limited thereto.

[0100] Particularly, when the hole transport layer **31** and the hole transport auxiliary layer **33** are used with a blue light emitting material, a driving voltage may be lowered and long life-span characteristics may be further maximized.

[0101] On the other hand, the hole transport auxiliary layer **33** may contact the hole transport layer **31** and the light-emitting layer **32**.

[0102] The organic layer **30** may further include an electron transport layer **34**. The electron transport layer **34** is a layer to help electron transfer from the cathode **20** and to the light-emitting layer **32**, and may be omitted as needed.

[0103] The organic layer **30** may further optionally include a hole injection layer (not shown) between the anode **10** and the hole transport layer **31** and/or an electron injection layer (not shown) between the cathode **20** and the electron transport layer **34**.

[0104] The organic light emitting diode may be applied to an organic light emitting display device.


BEST MODE

[0105] Hereinafter, the embodiments are illustrated in more detail with reference to examples. These examples, however, are not in any sense to be interpreted as limiting the scope of the invention.

Hole Transport Layer: Synthesis of Compounds Represent by Chemical Formula I

Synthesis Example 1: Synthesis of Intermediate I-1

[0106]




[0107] 9-phenyl-9H-carbazol-3-ylboronic acid (100 g, 348 mmol) was dissolved in 0.9 L of tetrahydrofuran (THF) under a nitrogen environment, 1-bromo-4-chlorobenzene (73.3 g, 383 mmol) and tetrakis(triphenylphosphine)palladium (4.02 g, 3.48 mmol) were added thereto, and the mixture was stirred. Potassium carbonate (128 g, 870 mmol) saturated in water was added thereto, and the obtained mixture was heated and refluxed at 80° C. for 8 hours. When the reaction was completed, water was added to the reaction solution, dichloromethane (DCM) was used for an extraction, and an extract therefrom was filtered after removing moisture with anhydrous MgSO_4 and then, concentrated under a reduced pressure. The obtained residue was separated and purified through flash column chromatography to obtain an intermediate I-1 (119 g, 97%).

[0108] HRMS (70 eV, EI+): m/z calcd for $\text{C}_{24}\text{H}_{16}\text{ClN}$: 353.0971, found: 353.

[0109] Elemental Analysis: C, 81%; H, 5%

Synthesis Example 2: Synthesis of Compound 4 of Chemical Formula I

[0110]



4

[0111] The intermediate I-1 (20 g, 56.5 mmol) was dissolved in 0.2 L of toluene under a nitrogen environment, dibenzyl-4-ylamine made by Shenzhen Gre-syn Chemical Technology Co., Ltd. (<http://www.gre-syn.com/>) (18.2 g, 56.5 mmol), bis(dibenzylideneacetone)palladium (0) (0.33 g, 0.57 mmol), tris-tert butylphosphine (0.58 g, 2.83 mmol), and sodium tert-butoxide (6.52 g, 67.8 mmol) were sequentially added thereto, and the mixture was heated and refluxed at 100° C. for 15 hours. When the reaction was completed, water was added to the reaction solution, dichloromethane



(DCM) was used for an extraction, and an extract therefrom was filtered after removing moisture with anhydrous MgSO_4 and then, concentrated under a reduced pressure. This obtained residue was separated and purified through flash column chromatography to obtain Compound 4 (32.5 g, 90%) of Chemical Formula I.

[0112] HRMS (70 eV, EI+): m/z calcd for $\text{C}_{48}\text{H}_{34}\text{N}_2$: 638.2722, found: 638.

[0113] Elemental Analysis: C, 90%; H, 5%

Synthesis Example 3: Synthesis of Compound 9 of Chemical Formula I

[0114]





[0115] The intermediate I-1 (20 g, 56.5 mmol) was dissolved in 0.2 L of toluene under a nitrogen environment, N-(biphenyl-4-yl)-9,9-dimethyl-9H-fluoren-2-amine made by Shenzhen Gre-syn Chemical Technology Co., Ltd. (<http://www.gre-syn.com/>) (20.4 g, 56.5 mmol), bis(dibenzylideneacetone)palladium (0) (0.33 g, 0.57 mmol), tris-tert butylphosphine (0.58 g, 2.83 mmol), and sodium tert-butoxide (6.52 g, 67.8 mmol) were sequentially added thereto, and the mixture was heated and refluxed at 100° C. for 13 hours. When the reaction was completed, water was added to the reaction solution, dichloromethane (DCM) was used for an extraction, and an extract therefrom was filtered after removing moisture with anhydrous MgSO_4 and then, concentrated under a reduced pressure. The obtained residue was separated and purified through flash column chromatography to obtain Compound 9 (33.8 g, 88%) of Chemical Formula I.


[0116] HRMS (70 eV, EI+): m/z calcd for $\text{C}_{48}\text{H}_{34}\text{N}_2$: 678.3045, found: 678.

[0117] Elemental Analysis: C, 90%; H, 6%

Synthesis Example 4: Synthesis of Compound 27 of Chemical Formula I

[0118]





[0119] The intermediate I-1 (20 g, 56.5 mmol) was dissolved in 0.2 L of toluene under a nitrogen environment, N-(4-(dibenzo[b,d]furan-4-yl)phenyl)biphenyl-4-amine made by Shenzhen Gre-syn Chemical Technology (<http://www.gre-syn.com/>) (23.2 g, 56.5 mmol), bis(dibenzylideneacetone)palladium (0) (0.33 g, 0.57 mmol), tris-tert butylphosphine (0.58 g, 2.83 mmol), and sodium tert-butoxide (6.52 g, 67.8 mmol) were sequentially added thereto, and the mixture was heated and refluxed at 100° C. for 18 hours. When the reaction was completed, water was added to the reaction solution, dichloromethane (DCM) was used for an extraction, and an extract therefrom was filtered after removing moisture with anhydrous MgSO_4 and then, concentrated under a reduced pressure. The obtained residue was separated and purified through flash column chromatography to obtain Compound 27 (37.5 g, 91%) of Chemical Formula I.



[0120] HRMS (70 eV, EI^+): m/z calcd for $\text{C}_{54}\text{H}_{36}\text{N}_2\text{O}$: 728.2828, found: 728.

[0121] Elemental Analysis: C, 89%; H, 5%

Hole Transport Auxiliary Layer: Synthesis of Compounds Represented by Chemical Formula II

Synthesis Example 5: Synthesis of Intermediate I-2

[0122]




[0123] The intermediate I-1 (90 g, 254 mmol) was dissolved in 0.8 L of dimethylformamide (DMF) under a nitrogen environment, bis(pinacolato)diboron (77.5 g, 305 mmol), (1,1'-bis(diphenylphosphine)ferrocene)dichloropalladium (II) (2.70 g, 2.54 mmol), and potassium acetate (74.8 g, 762 mmol) were added thereto, and the mixture was heated and refluxed at 150° C. for 20 hours. When the reaction was complete, water was added to the reaction solution, and the mixture was filtered and dried in a vacuum oven. The obtained residue was separated and purified through flash column chromatography to obtain an intermediate I-2 (75.8 g, 67%).

[0124] HRMS (70 eV, EI^+): m/z calcd for $\text{C}_{30}\text{H}_{28}\text{BNO}_2$: 445.2213, found: 445.


[0125] Elemental Analysis: C, 81%; H, 6%

Synthesis Example 6: Synthesis of Intermediate I-3

[0126]



-continued



I-3


[0127] 3-bromo-9-phenyl-9H-carbazole (100 g, 310 mmol) was dissolved in 0.8 L of tetrahydrofuran (THF) under a nitrogen environment, 3-chlorophenylboronic acid (53.4 g, 341 mmol) and tetrakis(triphenylphosphine)palladium (3.58 g, 3.10 mmol) were added thereto, and the mixture was stirred. Potassium carbonate (114 g, 775 mmol) saturated in water was added thereto, and the obtained mixture was heated and refluxed at 80° C. for 16 hours. When the reaction was completed, water was added to the reaction solution, dichloromethane (DCM) was used for an extraction, and an extract therefrom was filtered after removing moisture with anhydrous MgSO_4 and then, concentrated under a reduced pressure. The obtained residue was separated and purified through flash column chromatography to obtain an intermediate I-3 (91.0 g, 83%).

[0128] HRMS (70 eV, EI+): m/z calcd for $\text{C}_{24}\text{H}_{16}\text{ClN}$: 353.0971, found: 353.



[0129] Elemental Analysis: C, 81%; H, 5%

Synthesis Example 7: Synthesis of Intermediate I-4


[0130]



I-3



-continued



I-4


[0131] The intermediate I-3 (90 g, 254 mmol) was dissolved in 0.8 L of dimethylformamide (DMF) under a nitrogen environment, bis(pinacolato)diboron (77.5 g, 305 mmol), (1,1'-bis(diphenylphosphine)ferrocene)dichloropalladium (II) (2.70 g, 2.54 mmol), and potassium acetate (74.8 g, 762 mmol) were added thereto, and the mixture was heated and refluxed at 150° C. for 25 hours. When the reaction was complete, water was added to the reaction solution, and obtained mixture was filtered and dried in a vacuum oven. This obtained residue was separated and purified through flash column chromatography to obtain an intermediate I-4 (67.9 g, 60%).

[0132] HRMS (70 eV, EI+): m/z calcd for $\text{C}_{30}\text{H}_{28}\text{BNO}_2$: 445.2213, found: 445.

[0133] Elemental Analysis: C, 81%; H, 6%

Synthesis Example 8: Synthesis of Intermediate I-5

[0134]



I-5

[0135] 3-bromo-9H-carbazole (100 g, 406 mmol) was dissolved in 1.2 L of toluene under a nitrogen environment, 3-iodobiphenyl (137 g, 488 mmol), bis(dibenzylideneacetone)palladium (0) (2.33 g, 4.06 mmol), tris-tert butylphos-


phine (4.11 g, 20.3 mmol), and sodium tert-butoxide (46.8 g, 487 mmol) were sequentially added thereto, and the mixture was heated and refluxed at 100° C. for 10 hours. When the reaction was completed, water was added to the reaction solution, dichloromethane (DCM) was used for an extraction, and an extract therefrom was filtered after removing moisture with anhydrous MgSO_4 and then, concentrated under a reduced pressure. This obtained residue was separated and purified through flash column chromatography to obtain an intermediate I-5 (82.5 g, 51%).

[0136] HRMS (70 eV, EI+): m/z calcd for $\text{C}_{24}\text{H}_{16}\text{BrN}$: 397.0466, found: 397.

[0137] Elemental Analysis: C, 72%; H, 4%

Synthesis Example 9: Synthesis of Compound 1 of Chemical Formula II

[0138]



1


[0139] The intermediate I-2 (20 g, 44.9 mmol) was dissolved in 0.2 L of tetrahydrofuran (THF) under a nitrogen environment, 3-bromo-9-phenyl-9H-carbazole (14.5 g, 44.9 mmol) and tetrakis(triphenylphosphine)palladium (0.52 g, 0.45 mmol) were added thereto, and the mixture was stirred. Potassium carbonate (16.5 g, 112 mmol) saturated in water was added thereto, and the obtained mixture was heated and refluxed at 80° C. for 15 hours. When the reaction was completed, water was added to the reaction solution, dichloromethane (DCM) was used for an extraction, and an extract therefrom was filtered after removing moisture with anhydrous MgSO_4 and then, concentrated under a reduced pressure. The obtained residue was separated and purified through flash column chromatography to obtain Compound 1 (22.7 g, 90%) of Chemical Formula II.

[0140] HRMS (70 eV, EI+): m/z calcd for $\text{C}_{42}\text{H}_{28}\text{N}_2$: 560.2252, found: 560.

[0141] Elemental Analysis: C, 90%; H, 5%

Synthesis Example 10: Synthesis of Compound 2 of Chemical Formula II

[0142]



2

[0143] The intermediate I-4 (20 g, 44.9 mmol) was dissolved in 0.2 L of tetrahydrofuran (THF) under a nitrogen environment, 3-bromo-9-phenyl-9H-carbazole (14.5 g, 44.9 mmol) and tetrakis(triphenylphosphine)palladium (0.52 g, 0.45 mmol) were added thereto, and the mixture was stirred.


Potassium carbonate (16.5 g, 112 mmol) saturated in water was added thereto, and the obtained mixture was heated and refluxed at 80° C. for 17 hours. When the reaction was completed, water was added to the reaction solution, dichloromethane (DCM) was used for an extraction, and an extract therefrom was filtered after removing moisture with anhydrous MgSO_4 and then, concentrated under a reduced pressure. This obtained residue was separated and purified through flash column chromatography to obtain Compound 2 (21.4 g, 85%) of Chemical Formula II.

[0144] HRMS (70 eV, EI+): m/z calcd for $\text{C}_{42}\text{H}_{28}\text{N}_2$: 560.2252, found: 560.

[0145] Elemental Analysis: C, 90%; H, 5%

Synthesis Example 11: Synthesis of Compound II-33 of Chemical Formula II

[0146]



33


[0147] The intermediate I-2 (20 g, 44.9 mmol) was dissolved in 0.2 L of tetrahydrofuran (THF) under a nitrogen environment, the intermediate I-5 (17.9 g, 44.9 mmol) and tetrakis(triphenylphosphine)palladium (0.52 g, 0.45 mmol) were added thereto, and the mixture was stirred. Potassium carbonate (16.5 g, 112 mmol) saturated in water was added thereto, and the obtained mixture was heated and refluxed at 80° C. for 18 hours. When the reaction was completed, water was added to the reaction solution, dichloromethane (DCM) was used for an extraction, and an extract therefrom was filtered after removing moisture with anhydrous MgSO_4 and then, concentrated under a reduced pressure. The obtained residue was separated and purified through flash column chromatography to obtain Compound II-33 (24.6 g, 86%) of Chemical Formula II.

[0148] HRMS (70 eV, EI+): m/z calcd for $\text{C}_{48}\text{H}_{32}\text{N}_2$: 636.2565, found: 636.

[0149] Elemental Analysis: C, 91%; H, 5%

Synthesis Example 12: Synthesis of Compound 34 of Chemical Formula II

[0150]



34

[0151] The intermediate I-4 (20 g, 44.9 mmol) was dissolved in 0.2 L of tetrahydrofuran (THF) under a nitrogen


environment, the intermediate I-5 (17.9 g, 44.9 mmol) and tetrakis(triphenylphosphine)palladium (0.52 g, 0.45 mmol) were added thereto, and the mixture was stirred. Potassium carbonate (16.5 g, 112 mmol) saturated in water was added thereto, and the mixture was heated and refluxed at 80° C. for 18 hours. When the reaction was completed, water was added to the reaction solution, dichloromethane (DCM) was used for an extraction, and an extract therefrom was filtered after removing moisture with anhydrous MgSO_4 and then, concentrated under a reduced pressure. The obtained residue was separated and purified through flash column chromatography to obtain Compound 34 (25.7 g, 90%) of Chemical Formula II.

[0152] HRMS (70 eV, EI+): m/z calcd for $\text{C}_{42}\text{H}_{32}\text{N}_2$: 636.2565, found: 636.

[0153] Elemental Analysis: C, 91%; H, 5%

Synthesis Example 13: Synthesis of Compound HT-1 of Chemical Formula II

[0154]



[0155] 9-phenyl-9H-carbazol-3-ylboronic acid (20 g, 69.7 mmol) was dissolved in 0.2 L of tetrahydrofuran (THF), 3-bromo-9-phenyl-9H-carbazole (22.4 g, 69.7 mmol) and tetrakis(triphenylphosphine)palladium (0.81 g, 0.70 mmol) were added thereto, and the mixture was stirred. Potassium carbonate (25.7 g, 174 mmol) saturated in water was added

thereto, and the obtained mixture was heated and refluxed at 80° C. for 16 hours. When the reaction was completed, water was added to the reaction solution, dichloromethane (DCM) was used for an extraction, and an extract therefrom was filtered after removing moisture with anhydrous MgSO_4 and then, concentrated under a reduced pressure. The obtained residue was separated and purified through flash column chromatography to obtain Compound HT-1 (28.7 g, 85%) of Chemical Formula II.

[0156] HRMS (70 eV, EI+): m/z calcd for $\text{C}_{36}\text{H}_{24}\text{N}_2$: 484.1939, found: 484.

[0157] Elemental Analysis: C, 89%; H, 5%

(Energy Level Using Gaussian Tool)

[0158] An energy level of each material was measured in a B3LYP/6-31G** method by using a program Gaussian 09 with a super computer, GAIA (IBM power 6), and the results are shown in Table 1.

TABLE 1

Material	HOMO (eV)	LUMO (eV)
Compound I-4	-4.77	-0.87
Compound I-9	-4.70	-0.91
Compound I-27	-4.75	-1.10
Compound II-1	-5.04	-0.77
Compound II-2	-5.17	-0.73
Compound II-33	-5.04	-0.98
Compound II-34	-5.17	-0.97

[0159] According to the results, Compound II-1, Compounds II-2, II-33, and II-34 had a lower HOMO energy level than Compounds I-4, I-9, and I-27. Thereby, hole injection and flow are made more easily to realize a device having a lower driving voltage, high efficiency, and a long life-span.

(Manufacture of Organic Light Emitting Diode)

Example 1: Manufacture of Organic Light Emitting Diode (Blue Auxiliary Layer)

[0160] ITO (indium tin oxide) was coated to be 1500 Å thick on a glass substrate, and the coated glass was ultrasonic wave-washed with a distilled water. Subsequently, the glass substrate was ultrasonic wave-washed with a solvent such as isopropyl alcohol, acetone, methanol, and the like, moved to a plasma cleaner, cleaned by using oxygen plasma for 5 minutes, and then, moved to a vacuum depositor. This ITO transparent electrode was used as an anode, a 600 Å-thick hole injection layer was formed thereon by vacuum-depositing 4,4'-bis[N-[4-{N,N-bis(3-methylphenyl)amino}-phenyl]-N-phenylamino]biphenyl (DNTPD). Subsequently, Compound 4 of Chemical Formula I synthesized in Synthesis Example 2 was vacuum-deposited to form a hole transport layer having a 250 Å thickness. Compound 1 of Chemical Formula II synthesized in Synthesis Example 9 was vacuum-deposited to form an auxiliary layer having a 50 Å thickness of a hole transport layer. On the hole transport layer, a 250 Å-thick light-emitting layer was formed by vacuum-depositing 9,10-di-(2-naphthyl)anthracene (ADN) as a host and 3 wt % of 2,5,8,11-tetra(tert-butyl)perylene (TBPe) as a dopant. On the light-emitting layer, Alq3 was vacuum-deposited to form an electron transport layer having a thickness of 250 Å. A cathode was

formed by sequentially vacuum-depositing Liq to be 10 Å thick and Al to be 1000 Å thick on the electron transport layer to manufacture an organic light emitting diode.

[0161] The organic light emitting diode had a five-layered organic thin film structure and specifically, Al (1000 Å)/LiF (10 Å)/Alq3 (250 Å)/EML [ADN:TBPe=97:3] (250 Å)/hole transport auxiliary layer (50 Å)/hole transport layer (250 Å)/DNTPD (600 Å)/ITO (1500 Å).

Example 2

[0162] An organic light emitting diode was manufactured according to the same method as Example 1 except for using Compound 2 of Chemical Formula II synthesized in Synthesis Example 10 instead of Compound 1 synthesized in Synthesis Example 9 for the hole transport auxiliary layer.

Example 3

[0163] An organic light emitting diode was manufactured according to the same method as Example 1 except for using Compound 33 of Chemical Formula II synthesized in Synthesis Example 11 instead of Compound 1 synthesized in Synthesis Example 9 for the hole transport auxiliary layer.

Example 4

[0164] An organic light emitting diode was manufactured according to the same method as Example 1 except for using Compound 34 of Chemical Formula II synthesized in Synthesis Example 12 instead of Compound 1 synthesized in Synthesis Example 9 for the hole transport auxiliary layer.

Example 5

[0165] An organic light emitting diode was manufactured according to the same method as Example 3 except for using Compound 9 of Chemical Formula I synthesized in Synthesis Example 3 instead of Compound 4 synthesized in Synthesis Example 2 for the hole transport layer.

Example 6

[0166] An organic light emitting diode was manufactured according to the same method as Example 3 except for using Compound 27 of Chemical Formula I synthesized in Synthesis Example 4 instead of Compound 4 synthesized in Synthesis Example 2 for the hole transport layer.

Comparative Example 1

[0167] An organic light emitting diode was manufactured according to the same method as Example 1 except for using Compound HT-1 of Chemical Formula II synthesized in Synthesis Example 13 instead of Compound 1 synthesized in Synthesis Example 9 for the hole transport auxiliary layer.

Comparative Example 2

[0168] An organic light emitting diode was manufactured according to the same method as Comparative Example 1 except for using Compound 9 of Chemical Formula I synthesized in Synthesis Example 3 instead of Compound 4 synthesized in Synthesis Example 2 for the hole transport layer.

Comparative Example 3

[0169] An organic light emitting diode was manufactured according to the same method as Comparative Example 1 except for using Compound 27 of Chemical Formula I synthesized in Synthesis Example 4 instead of Compound 4 synthesized in Synthesis Example 2 for the hole transport layer.

Comparative Example 4

[0170] An organic light emitting diode was manufactured according to the same method as Example 1 except for using Compound 4 of Chemical Formula I synthesized in Synthesis Example 2 instead of Compound 1 of Chemical Formula II synthesized in Synthesis Example 9 for the hole transport auxiliary layer.

Comparative Example 5

[0171] An organic light emitting diode was manufactured according to the same method as Example 5 except for using Compound 9 of Chemical Formula I synthesized in Synthesis Example 3 instead of Compound 33 of Chemical Formula II synthesized in Synthesis Example 11 for the hole transport auxiliary layer.

Comparative Example 6

[0172] An organic light emitting diode was manufactured according to the same method as Example 6 except for using Compound 27 of Chemical Formula I synthesized in Synthesis Example 4 instead of Compound 33 of Chemical Formula II synthesized in Synthesis Example 11 for the hole transport auxiliary layer.

Comparative Example 7

[0173] An organic light emitting diode was manufactured according to the same method as Example 1 except for using Compound 1 of Chemical Formula II synthesized in Synthesis Example 9 instead of Compound 4 of Chemical Formula I synthesized in Synthesis Example 2 for the hole transport layer.

Comparative Example 8

[0174] An organic light emitting diode was manufactured according to the same method as Example 2 except for using Compound 2 of Chemical Formula II synthesized in Synthesis Example 10 instead of Compound 4 of Chemical Formula I synthesized in Synthesis Example 2 for the hole transport layer.

Comparative Example 9


[0175] An organic light emitting diode was manufactured according to the same method as Example 3 except for using Compound 33 of Chemical Formula II synthesized in Synthesis Example 11 instead of Compound 4 of Chemical Formula I synthesized in Synthesis Example 2 for the hole transport layer.

Comparative Example 10


[0176] An organic light emitting diode was manufactured according to the same method as Example 4 except for using Compound 34 of Chemical Formula II synthesized in Syn-

thesis Example 12 instead of Compound 4 of Chemical Formula I synthesized in Synthesis Example 2 for the hole transport layer.


[0177] DNTPD, ADN, NPB, and TBPe used to manufacture the organic light emitting diode have the following structures.




[DNTPD]



[ADN]



[NPB]



[TBPe]

(Performance Measurement of Organic Light Emitting Diode)

[0178] Current density and luminance changes depending on a voltage and luminous efficiency of each organic light emitting diode according to Examples 1 to 6 and Comparative Examples 1 to 10 were measured. The measurements were specifically performed in the following methods, and the results are shown in Table 2.

[0179] (1) Measurement of Current Density Change Depending on Voltage Change

[0180] Current values flowing in the unit devices of the obtained organic light emitting diodes were measured by using a current-voltage meter (Keithley 2400), while the voltage was increased from 0 V to 10 V, and the measured current value was divided by area to provide results.

[0181] (2) Measurement of Luminance Change Depending on Voltage Change

[0182] Luminance was measured by using a luminance meter (Minolta Cs-1000A), while the voltage of the organic light emitting diodes was increased from 0 V to 10 V.

[0183] (3) Measurement of Luminous Efficiency

[0184] Current efficiency (cd/A) at the same current density (10 mA/cm²) were calculated by using the luminance, current density, and voltage from the items (1) and (2).

[0185] (4) Measurement of Life-Span

[0186] A life-span was obtained by using 1000 cd/m² of initial luminance of an organic light emitting diode, measuring its luminance decrease as time goes, and measuring a time taken until the luminance decreased by 50% relative to the initial luminance.

TABLE 2

Devices	Compounds used in hole transport layer	Compound used in hole transport auxiliary layer	Voltage (V)	Color (EL color)	Efficiency (cd/A)	50% life-span (h) at 1000 cd/m ²
Example 1	Compound 4 of Chemical Formula I	Compound 1 of Chemical Formula II	6.3	Blue	7.1	1,400
Example 2	Compound 4 of Chemical Formula I	Compound 2 of Chemical Formula II	6.5	Blue	7.6	1,380
Example 3	Compound 4 of Chemical Formula I	Compound 33 of Chemical Formula II	6.4	Blue	7.3	1,490
Example 4	Compound 4 of Chemical Formula I	Compound 34 of Chemical Formula II	6.6	Blue	7.7	1,450
Example 5	Compound 9 of Chemical Formula I	Compound 33 of Chemical Formula II	6.2	Blue	7.5	1,500
Example 6	Compound 27 of Chemical Formula I	Compound 33 of Chemical Formula II	6.5	Blue	7.6	1,650
Comparative Example 1	Compound 4 of Chemical Formula I	HT-1	7.0	Blue	6.3	710
Comparative Example 2	Compound 9 of Chemical Formula I	HT-1	6.8	Blue	6.5	690
Comparative Example 3	Compound 27 of Chemical Formula I	HT-1	6.8	Blue	6.5	850
Comparative Example 4	Compound 4 of Chemical Formula I	Compound 4 of Chemical Formula I	6.6	Blue	5.7	1,340
Comparative Example 5	Compound 9 of Chemical Formula I	Compound 9 of Chemical Formula I	6.3	Blue	6.1	1,450
Comparative Example 6	Compound 27 of Chemical Formula I	Compound 27 of Chemical Formula I	6.5	Blue	6.0	1,500
Comparative Example 7	Compound 1 of Chemical Formula II	Compound 1 of Chemical Formula II	6.9	Blue	6.7	910
Comparative Example 8	Compound 2 of Chemical Formula II	Compound 2 of Chemical Formula II	7.1	Blue	7.1	900
Comparative Example 9	Compound 33 of Chemical Formula II	Compound 33 of Chemical Formula II	6.7	Blue	6.9	1,010
Comparative Example 10	Compound 34 of Chemical Formula II	Compound 34 of Chemical Formula II	6.9	Blue	7.2	980


[0187] Referring to the results of Table 2, Examples 1 to 6 realized a lower driving voltage, higher efficiency, and a longer life-span than Comparative Examples 1 to 10. Specifically, Comparative Examples 4, 5, and 6 using both a hole transport layer and a hole transport auxiliary layer only formed of Compound I realized a long life-span but greater than or equal to 20% lower efficiency than Examples 1 to 6.

[0188] Examples 1 to 6 realized relatively very high efficiency, considering that it is difficult to greater than or equal to 10% of increase efficiency of a blue fluorescent device. In addition, Comparative Examples 1, 2, and 3 using a hole transport auxiliary layer using bicarbazole having no phenyl linker among themselves realized high efficiency but a very low life-span. The reason is that the bicarbazole had an inherent problem of being rigid and not uniformly deposited, but Comparative Examples 7 to 10 used a hole transport layer and a hole transport auxiliary layer formed of a material having no above problem and thus realized a high life-span compared with Comparative Examples 1 to 3. Furthermore, this material (used in Comparative Examples 7 to 10) was used with Compound represented by Chemical Formula I having a high life-span and thus effectively realized a low driving voltage, high efficiency, and a long life-span like Examples 1 to 6.

[0189] Accordingly, an organic light emitting diode having a low voltage, high efficiency, high luminance, and a long life-span based on excellent hole injection and hole transfer capability may be provided.

[0190] While this invention has been described in connection with what is presently considered to be practical example embodiments, it is to be understood that the invention is not limited to the disclosed embodiments, but, on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the appended claims. Therefore, the aforementioned embodiments should be understood to be exemplary but not limiting the present invention in any way.

1. An organic optoelectric device, comprising
an anode and a cathode facing each other,
a light-emitting layer disposed between the anode and cathode,
a hole transport layer disposed between the anode and the light-emitting layer, and
an auxiliary hole transport layer disposed between the hole transport layer and the light-emitting layer,
wherein the hole transport layer includes a compound represented by Chemical Formula I, and
the hole transport auxiliary layer includes a compound represented by Chemical Formula II:




wherein, in Chemical Formula I,

R^1 to R^3 are independently a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, or a combination thereof,
 R^4 to R^{10} are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C3 to C30 cycloalkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, a substituted or unsubstituted C6 to C30 arylamine group, a substituted or unsubstituted C1 to C30 alkoxy group, a substituted or unsubstituted C3 to C40 silyl group, a substituted or unsubstituted C3 to C40 silyloxy group, a substituted or unsubstituted C1 to C30 alkylthiol group, a substituted or unsubstituted C6 to C30 arylthiol group, a halogen, a halogen-containing group, a cyano group, a hydroxyl group, an amino group, a nitro group, or a combination thereof,

adjacent two of R^4 to R^{10} are fused to provide a ring, and
 L^1 to L^3 are independently a single bond, a substituted or unsubstituted C1 to C30 alkylene group, a substituted or unsubstituted C3 to C30 cycloalkylene group, a substituted or unsubstituted C6 to C30 arylene group, a substituted or unsubstituted C2 to C30 heteroarylene group, a substituted or unsubstituted C2 to C30 alkenylene group, a substituted or unsubstituted C2 to C30 alkynylene group, or a combination thereof,

wherein "substituted" refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group,

[Chemical Formula II]



wherein, in Chemical Formula II,

R^{11} to R^{24} are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, or a combination thereof,

adjacent two of R^{11} to R^{17} and R^{18} to R^{24} are fused to provide a ring,

R^{25} and R^{26} are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C3 to C30 cycloalkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, a substituted or unsubstituted C6 to C30 arylamine group, a substituted or unsubstituted C1 to


C30 alkoxy group, a substituted or unsubstituted C3 to C40 silyl group, a substituted or unsubstituted C1 to C30 alkylthiol group, a substituted or unsubstituted C6 to C30 arylthiol group, a halogen, a halogen-containing group, a cyano group, a hydroxyl group, an amino group, a nitro group, or a combination thereof, and

n is an integer ranging from 1 to 4,


wherein “substituted” refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group.

2. The organic optoelectronic device of claim 1, wherein the compound represented by Chemical Formula I is represented by one of Chemical Formula I-1 to Chemical Formula I-5:


[Chemical Formula I-1]



[Chemical Formula I-2]




[Chemical Formula I-3]




-continued

[Chemical Formula I-4]



[Chemical Formula I-5]



wherein, in Chemical Formula I-1 to Chemical Formula I-5,

R¹ to R³ are independently a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, or a combination thereof,

R⁴ to R¹⁰ are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C3 to C30 cycloalkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, a substituted or unsubstituted C6 to C30 arylamine group, a substituted or unsubstituted C1 to C30 alkoxy group, a substituted or unsubstituted C3 to C40 silyl group, a substituted or unsubstituted C3 to C40 silyloxy group, a substituted or unsubstituted C1 to C30 alkylthiol group, a substituted or unsubstituted C6 to C30 arylthiol group, a halogen, a halogen-containing group, a cyano group, a hydroxyl group, an amino group, a nitro group, or a combination thereof,


L¹ to L³ are independently a single bond, a substituted or unsubstituted C1 to C30 alkylene group, a substituted or unsubstituted C3 to C30 cycloalkylene group, a substituted or unsubstituted C6 to C30 arylene group, a substituted or unsubstituted C2 to C30 heteroarylene group, a substituted or unsubstituted C6 to C30 aryleneamine group, a substituted or unsubstituted C1 to C30 alkoxy group, a substituted or unsubstituted C1 to C30 aryloxy group, a substituted or unsubstituted C2 to C30 alkenylene group, a substituted or unsubstituted C2 to C30 alkynylene group, or a combination thereof, and

R²⁷ and R²⁸ are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, or a combination thereof,


wherein “substituted” refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group.


3. The organic optoelectric device of claim 1, wherein the L¹ to L³ of Chemical Formula I are independently a single bond or selected from substituted or unsubstituted groups of Group I:

[Group I]



-continued






wherein, in Group I,

* is a linking point,

wherein "substituted" refers to replacement of at least one hydrogen by deuterium, a halogen, hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group.


4. The organic optoelectric device of claim 1, wherein the compound represented by Chemical Formula I is represented by Chemical Formula I-6 or Chemical Formula I-7:

[Chemical Formula I-6]



-continued

[Chemical Formula I-7]



R^1 to R^3 are independently a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heterocyclic group, or a combination thereof,

R^4 to R^{10} are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C3 to C30 cycloalkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, a substituted or unsubstituted C6 to C30 arylamine group, a substituted or unsubstituted C1 to C30 alkoxy group, a substituted or unsubstituted C3 to C40 silyl group, a substituted or unsubstituted C3 to C40 silyloxy group, a substituted or unsubstituted C1 to C30 alkylthiol group, a substituted or unsubstituted C6 to C30 arylthiol group, a halogen, a halogen-containing group, a cyano group, a hydroxyl group, an amino group, a nitro group, or a combination thereof,

adjacent two of R^4 to R^{10} are fused to provide a ring, and

L^1 and L^2 are independently a single bond, a substituted or unsubstituted C1 to C30 alkylene group, a substituted or unsubstituted C3 to C30 cycloalkylene group, a substituted or unsubstituted C6 to C30 arylene group, a substituted or unsubstituted C2 to C30 heteroarylene group, a substituted or unsubstituted C6 to C30 aryleneamine group, a substituted or unsubstituted C1 to C30 alkoxylylene group, a substituted or unsubstituted C1 to C30 aryloxylylene group, a substituted or unsubstituted C2 to C30 alkenylene group, a substituted or unsubstituted C2 to C30 alkynylene group, or a combination thereof,

wherein "substituted" refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group.

5. The organic optoelectric device of claim 1, wherein the R^4 to R^{10} of Chemical Formula I are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, or a substituted or unsubstituted C6 to C30 aryl group.

6. The organic optoelectric device of claim 1, wherein the R^1 to R^3 of Chemical Formula I are independently a substi-

tuted or unsubstituted C6 to C30 aryl group, or a substituted or unsubstituted C2 to C30 heterocyclic group,


the substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted terphenyl group, a substituted or unsubstituted quaterphenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthracenyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted spiro fluorenyl group, a substituted or unsubstituted triphenylene group, a combination thereof, or a fused form thereof, and

the substituted or unsubstituted C2 to C30 heterocyclic group is a substituted or unsubstituted carbazoyl group, a substituted or unsubstituted benzofuranyl group, a substituted or unsubstituted benzothiophenyl group, a substituted or unsubstituted dibenzofuranyl group, a substituted or unsubstituted dibenzothiophenyl group, or a combination thereof.


7. The organic optoelectric device of claim 1, wherein R¹ to R³ of Chemical Formula I are independently a substituted or unsubstituted C6 to C30 aryl group, or a substituted or unsubstituted C2 to C30 heterocyclic group, and

the substituted or unsubstituted C6 to C30 aryl group and the substituted or unsubstituted C2 to C30 heterocyclic group are selected from substituted or unsubstituted groups of Group II:


[Group II]



-continued



-continued




wherein, in Group II,

* is a linking point,


wherein “substituted” refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group.

8. The organic optoelectric device of claim 1, wherein the compound represented by Chemical Formula II is represented by one of Chemical Formula II-1 to Chemical Formula II-16:


[Chemical Formula II-1]



[Chemical Formula II-2]




[Chemical Formula II-3]




-continued


[Chemical Formula II-4]




[Chemical Formula II-5]



[Chemical Formula II-6]




[Chemical Formula II-7]




-continued


[Chemical Formula II-8]




[Chemical Formula II-9]



[Chemical Formula II-10]




[Chemical Formula II-11]




-continued


[Chemical Formula II-12]



[Chemical Formula II-13]




[Chemical Formula II-14]




-continued

[Chemical Formula II-15]



[Chemical Formula II-16]



wherein, in Chemical Formula II-1 to Chemical Formula II-16,

R¹¹ to R²⁴ are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, or a combination thereof,

adjacent two of R¹¹ to R¹⁷ and R¹⁸ to R²⁴ are fused to provide a ring, and

R²⁵ and R²⁶ are independently hydrogen, deuterium, a substituted or unsubstituted C1 to C30 alkyl group, a substituted or unsubstituted C3 to C30 cycloalkyl group, a substituted or unsubstituted C6 to C30 aryl group, a substituted or unsubstituted C2 to C30 heteroaryl group, a substituted or unsubstituted C6 to C30

arylamine group, a substituted or unsubstituted C1 to C30 alkoxy group, a substituted or unsubstituted C3 to C40 silyl group, a substituted or unsubstituted C1 to C30 alkylthiol group, a substituted or unsubstituted C6 to C30 arylthiol group, a halogen, a halogen-containing group, a cyano group, a hydroxyl group, an amino group, a nitro group, or a combination thereof,

wherein “substituted” refers to replacement of at least one hydrogen by deuterium, a halogen, a hydroxy group, an amino group, a C1 to C30 amine group, a nitro group, a C1 to C40 silyl group, a C1 to C30 alkyl group, a C1 to C10 alkylsilyl group, a C3 to C30 cycloalkyl group, a C2 to C30 heterocycloalkyl group, a C6 to C30 aryl group, a C2 to C30 heteroaryl group, a C1 to C20 alkoxy group, a fluoro group, a C1 to C10 trifluoroalkyl group, or a cyano group.

9. The organic optoelectric device of claim 1, wherein R^{25} and R^{26} of Chemical Formula II are independently hydrogen, deuterium, a substituted or unsubstituted C6 to C30 aryl group, or a substituted or unsubstituted C2 to C30 heteroaryl group.

10. The organic optoelectric device of claim 9, wherein the substituted or unsubstituted C6 to C30 aryl group is a substituted or unsubstituted phenyl group, a substituted or unsubstituted biphenyl group, a substituted or unsubstituted terphenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthracenyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted triphenylene group, or a combination thereof, and

the substituted or unsubstituted C2 to C30 heteroaryl group is a substituted or unsubstituted pyridyl group, a


substituted or unsubstituted pyrimidinyl group, a substituted or unsubstituted triazinyl group, or a combination thereof.

11. The organic optoelectric device of claim 9, wherein at least one hydrogen of the substituted or unsubstituted C6 to C30 aryl group and a substituted or unsubstituted C2 to C30 heteroaryl group is replaced or unreplaced by a phenyl group, a biphenyl group, a naphthyl group, a pyridyl group, a pyrimidinyl group, or a triazinyl group.

12. The organic optoelectric device of claim 1, wherein R^{11} to R^{24} of Chemical Formula II are independently hydrogen, deuterium, or a substituted or unsubstituted C6 to C30 aryl group.


13. The organic optoelectric device of claim 1, wherein the compound represented by Chemical Formula I is selected from compounds of Group III:

[Group III]




-continued


7




8




9




10



11




12




-continued


13




14




15




16




17




18



19




20



-continued


21

22




23

24








25

26



27



28



-continued



29

30





31

32





33

34




35

36




-continued


37




38




39




40




41




42




-continued




43




44




45




46




47



48











49



50



-continued



-continued



59

60





61

62



63



64



-continued



65

66





67

68





69

70




71

72




-continued


73




74




75




76




77




78



79




80




-continued


81




82




83




84




85




86



87




88




-continued

89




90


91




92





93



94











95




-continued
96

97




-continued


104




105




106




107




108




109




-continued
110




111




112




113




114




115



116




117




-continued


118




119




120




121




122




123











124




125




-continued




-continued
134


136




138



140




141




135


137




139




141




-continued
142



143




144




14. The organic optoelectric device of claim 1, wherein the compound represented by Chemical Formula II is one selected from compounds of Group IV:

[Group IV]

1





2





-continued
3

4





5

6




7

8




9




-continued


10



11




12





-continued

13



14



15



-continued



16

17





18

19



20



21



-continued



22

23




24

25




26




-continued

27




28




-continued

29




30




-continued

31





32



-continued



33

34





35

36




37

38




-continued
39


40



41




42




-continued


43



44




45




-continued


46



47




48




-continued

49


50




51




52




53





54



55




56




-continued


57



58




59




-continued

60





61



-continued



62

63





64

65




66

67





-continued

68





69

70




71

72




-continued


73




74



75




76




-continued

77



78



79



-continued



80

81





82

83





84

85



86



87




-continued

88


89



90




91




-continued

92





93



-continued



94

95





96

97



98



99



-continued



100

101





102

103




104

105




-continued


106



107




108





-continued

109



110



111



-continued



112

113




114

115




116





-continued

117





118

119




120

121




-continued


122



123




124





-continued

125




126

127




-continued


128




129




130




131



132



133





137

-continued



134

135




136

137




138




-continued

139



140



15. The organic optoelectric device of claim 1, wherein the hole transport auxiliary layer contacts the hole transport layer and the light-emitting layer respectively.

16. A display device comprising the organic optoelectric device of claim 1.

* * * * *

专利名称(译)	有机光电器件和显示器件		
公开(公告)号	US20170213985A1	公开(公告)日	2017-07-27
申请号	US15/328180	申请日	2014-12-11
申请(专利权)人(译)	三星SDI CO. , LTD.		
当前申请(专利权)人(译)	三星SDI CO. , LTD.		
[标]发明人	LEE HAN ILL KIM CHANG WOO RYU DONG WAN PARK YOUNG SUNG SHIN CHANG JU YU EUN SUN JUNG SUNG HYUN HAN SU JIN		
发明人	LEE, HAN-ILL KIM, CHANG-WOO RYU, DONG-WAN PARK, YOUNG-SUNG SHIN, CHANG-JU YU, EUN-SUN JUNG, SUNG-HYUN HAN, SU-JIN		
IPC分类号	H01L51/00 C07D405/12 C07D209/86 C09K11/02 C09K11/06		
CPC分类号	H01L51/0072 C09K11/025 C09K11/06 C07D209/86 H01L51/0061 H01L2251/552 C07D405/12 C09K2211/1011 H01L51/5064 H01L51/0052 H01L51/0073 H01L51/006 H01L51/0059 H01L51/0081 H01L51/0067 H01L51/5056 H05B33/14 Y10S428/917		
优先权	1020140105353 2014-08-13 KR		
其他公开文献	US10522766		
外部链接	Espacenet USPTO		

摘要(译)

本发明涉及有机光电子器件和包括该有机光电子器件的显示器件，该有机光电子器件包括：阳极;面向阳极的阴极;发光层介于阳极和阴极之间;空穴传输层介于阳极和发光层之间;在空穴传输层和发光层之间插入辅助空穴传输层，其中空穴传输层包含由化学式I表示的化合物，并且辅助空穴传输层包含由化学式II表示的化合物。化学式I和II与说明书中所述的相同。

