



(19) **United States**

(12) **Patent Application Publication**
CHO et al.

(10) **Pub. No.: US 2020/0044166 A1**
(43) **Pub. Date: Feb. 6, 2020**

(54) **ORGANOMETALLIC COMPOUND,
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME, AND DIAGNOSTIC
COMPOSITION INCLUDING THE
ORGANOMETALLIC COMPOUND**

(52) **U.S. Cl.**
CPC *H01L 51/0085* (2013.01); *H01L 51/5012*
(2013.01); *C09K 11/06* (2013.01); *C07F*
15/0033 (2013.01)


(71) Applicant: **Samsung Electronics Co., Ltd.,**
Suwon-si (KR)

(57) **ABSTRACT**

(72) Inventors: **Yongsuk CHO**, Hwaseong-si (KR);
Yoonhyun KWAK, Seoul (KR);
Jongwon CHOI, Yongin-si (KR); **Hyun**
KOO, Seongnam-si (KR); **Kyuhyun**
IM, Seongnam-si (KR); **Dmitry**
KRAVCHUK, Hwaseong-si (KR);
Seokhwan HONG, Seoul (KR)

An organometallic compound represented by Formula 1:

Formula 1



(21) Appl. No.: **16/527,093**

(22) Filed: **Jul. 31, 2019**



(30) **Foreign Application Priority Data**

Jul. 31, 2018 (KR) 10-2018-0089511
Jul. 29, 2019 (KR) 10-2019-0091699

Publication Classification

(51) **Int. Cl.**
H01L 51/00 (2006.01)
C07F 15/00 (2006.01)
C09K 11/06 (2006.01)


wherein, Formula 1, R₁ to R₁₀ and A₁ to A₇ are the same as described in the detailed description of the specification.



19

15

11



**ORGANOMETALLIC COMPOUND,
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME, AND DIAGNOSTIC
COMPOSITION INCLUDING THE
ORGANOMETALLIC COMPOUND**

CROSS-REFERENCE TO RELATED
APPLICATION

[0001] This application claims priority to Korean Patent Applications Nos. 10-2018-0089511, filed on Jul. 31, 2018, and 10-2019-0091699, filed on Jul. 29, 2019, in the Korean Intellectual Property Office, and all the benefits accruing therefrom under 35 U.S.C. § 119, the content of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

[0002] One or more embodiments relate to an organometallic compound, an organic light-emitting device including the same, and a diagnostic composition including the organometallic compound.

2. Description of the Related Art

[0003] Organic light-emitting devices (OLEDs) are self-emission devices, which have superior characteristics in terms of a viewing angle, response time, brightness, driving voltage, and response speed, and which produce full-color images.

[0004] In an example, an organic light-emitting device includes an anode, a cathode, and an organic layer disposed between the anode and the cathode, wherein the organic layer includes an emission layer. A hole transport region may be disposed between the anode and the emission layer, and an electron transport region may be disposed between the emission layer and the cathode. Holes provided from the anode may move toward the emission layer through the hole transport region, and electrons provided from the cathode may move toward the emission layer through the electron transport region. The holes and the electrons recombine in the emission layer to produce excitons. These excitons transit from an excited state to a ground state, thereby generating light.

[0005] Luminescent compounds may be used to monitor, sense, or detect a variety of biological materials including cells and proteins. An example of such luminescent compounds is a phosphorescent luminescent compound.

[0006] Various types of organic light emitting devices are known. However, there still remains a need in OLEDs having low driving voltage, high efficiency, high brightness, and long lifespan.


SUMMARY

[0007] Aspects of the present disclosure provide a novel organometallic compound, an organic light-emitting device including the same, and a diagnostic composition including the novel organometallic compound.

[0008] Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

[0009] An aspect of the present disclosure provides an organometallic compound represented by Formula 1:

Formula 1



[0010] In Formula 1,

[0011] R_1 to R_{10} and A_7 may each independently be hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-SF_5$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_7 - C_{60} arylalkyl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted C_2 - C_{60} heteroarylalkyl group, a substituted or unsubstituted mono-valent non-aromatic condensed polycyclic group, a substituted or unsubstituted mono-valent non-aromatic condensed heteropolycyclic group, $-N(Q_1)(Q_2)$, $-Si(Q_3)(Q_4)(Q_5)$, $-Ge(Q_3)(Q_4)(Q_5)$, $-B(Q_6)(Q_7)$, $-P(=O)(Q_8)(Q_9)$, or $-P(Q_8)(Q_9)$,

[0012] at least one of R_1 to R_{10} may each independently be a substituted or unsubstituted C_2 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_7 - C_{60} arylalkyl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60}

heteroarylthio group, a substituted or unsubstituted C₂-C₆₀ heteroarylalkyl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), —Ge(Q₃)(Q₄)(Q₅), —B(Q₆)(Q₇), —P(=O)(Q₈)(Q₉), or —P(Q₈)(Q₉),

[0013] A₁ to A₆ may each independently be a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₇-C₆₀ arylalkyl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted C₂-C₆₀ heteroarylalkyl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

[0014] two or more of R₁ to R₁₀ may optionally be linked to form a C₅-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₆₀ heterocyclic group unsubstituted or substituted at least one R_{1a},

[0015] two or more of A₁ to A₆ may optionally be linked to form a C₅-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₁₀ heterocyclic group unsubstituted or substituted with at least one R_{1a},

[0016] R_{1a} is understood by referring to the detailed description of R₇,

[0017] a substituent(s) of the substituted C₁-C₁₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₁₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₇-C₆₀ arylalkyl group, the substituted C₁-C₁₀ heteroaryl group, the substituted C₁-C₁₀ heteroaryloxy group, the substituted C₁-C₁₀ heteroarylthio group, the substituted C₂-C₆₀ heteroarylalkyl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may each independently be:

[0018] deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group;

[0019] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group, each substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl

group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), —Ge(Q₁₃)(Q₁₄)(Q₁₅), —B(Q₁₆)(Q₁₇), —P(=O)(Q₁₈)(Q₁₉), —P(Q₁₈)(Q₁₉), or any combination thereof;

[0020] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group;

[0021] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group, each substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), —Ge(Q₂₃)(Q₂₄)(Q₂₅), —B(Q₂₆)(Q₂₇), —P(=O)(Q₂₈)(Q₂₉), —P(Q₂₈)(Q₂₉), or any combination thereof;

[0022] —N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), —Ge(Q₃₃)(Q₃₄)(Q₃₅), —B(Q₃₆)(Q₃₇), —P(=O)(Q₃₈)(Q₃₉), or —P(Q₃₈)(Q₃₉); or

[0023] any combination thereof, and

[0024] Q₁ to Q₉, Q₁₁ to Q₁₉, Q₂₁ to Q₂₉, and Q₃₁ to Q₃₉ may each independently be hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; an amino group; an amidino group; a hydrazine group; a hydrazone group; a carboxylic acid group or a salt thereof; a sulfonic acid group or a salt thereof; a phosphoric acid group or a salt thereof; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; a C₁-C₆₀ alkoxy group; a C₃-C₁₀ cycloalkyl group; a C₁-C₁₀ heterocycloalkyl

group; a C₃-C₁₀ cycloalkenyl group; a C₁-C₁₀ heterocycloalkenyl group; a C₆-C₆₀ aryl group; a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₆-C₆₀ aryl group, or any combination thereof; a C₆-C₆₀ aryloxy group; a C₆-C₆₀ arylthio group; a C₇-C₆₀ arylalkyl group; a C₁-C₆₀ heteroaryl group; a C₁-C₆₀ heteroaryloxy group; a C₁-C₆₀ heteroarylthio group; a C₂-C₆₀ heteroarylalkyl group; a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

[0025] Another aspect of the present disclosure provides an organic light-emitting device including:

[0026] a first electrode,

[0027] a second electrode, and

[0028] an organic layer disposed between the first electrode and the second electrode,

[0029] wherein the organic layer includes an emission layer, and

[0030] wherein the organic layer includes at least one organometallic compound represented by Formula 1.

[0031] Another aspect of the present disclosure provides a diagnostic composition including at least one organometallic compound represented by Formula 1.

BRIEF DESCRIPTION OF THE DRAWING

[0032] These and/or other aspects will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with the FIGURE which is a schematic view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

[0033] Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the FIGURES, to explain aspects of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

[0034] Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the FIGURES, to explain aspects of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

[0035] It will be understood that when an element is referred to as being “on” another element, it can be directly in contact with the other element or intervening elements

may be present therebetween. In contrast, when an element is referred to as being “directly on” another element, there are no intervening elements present.

[0036] It will be understood that, although the terms first, second, third etc. may be used herein to describe various elements, components, regions, layers, and/or sections, these elements, components, regions, layers, and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer, or section from another element, component, region, layer, or section. Thus, a first element, component, region, layer, or section discussed below could be termed a second element, component, region, layer, or section without departing from the teachings of the present embodiments.

[0037] The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, the singular forms “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

[0038] The term “or” means “and/or.” It will be further understood that the terms “comprises” and/or “comprising,” or “includes” and/or “including” when used in this specification, specify the presence of stated features, regions, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, regions, integers, steps, operations, elements, components, and/or groups thereof.


[0039] Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this general inventive concept belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

[0040] Exemplary embodiments are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein should not be construed as limited to the particular shapes of regions as illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated may be rounded. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the precise shape of a region and are not intended to limit the scope of the present claims.

[0041] “About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” can mean within one or more standard deviations, or within $\pm 30\%$, 20%, 10%, 5% of the stated value.

[0042] An aspect of the present disclosure provides an organometallic compound represented by Formula 1 below:

Formula 1



[0043] In Formula 1,

[0044] R_1 to R_{10} and A_7 may each independently be hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-SF_5$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_7 - C_{60} arylalkyl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted C_2 - C_{60} heteroarylalkyl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-N(Q_1)(Q_2)$, $-Si(Q_3)(Q_4)(Q_5)$, $-Ge(Q_3)(Q_4)(Q_5)$, $-B(Q_6)(Q_7)$, $-P(=O)(Q_8)(Q_9)$, or $-P(Q_8)(Q_9)$,

[0045] at least one of R_1 to R_{10} (for example, at least one of R_1 to R_6) may each independently be a substituted or unsubstituted C_2 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_7 - C_{60} arylalkyl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy

group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted C_2 - C_{60} heteroarylalkyl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-N(Q_1)(Q_2)$, $-Si(Q_3)(Q_4)(Q_5)$, $-Ge(Q_3)(Q_4)(Q_5)$, $-B(Q_6)(Q_7)$, $-P(=O)(Q_8)(Q_9)$, or $-P(Q_8)(Q_9)$, and [0046] A_1 to A_6 may each independently be a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_7 - C_{60} arylalkyl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted C_2 - C_{60} heteroarylalkyl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

[0047] Q_1 to Q_9 are the same as described herein.

[0048] In an embodiment, Formula 1,

[0049] R_1 to R_{10} and A_7 may each independently be hydrogen, deuterium, a cyano group, a substituted or unsubstituted C_1 - C_{60} alkyl group, or a substituted or unsubstituted C_3 - C_{10} cycloalkyl group and/or

[0050] at least one of R_1 to R_{10} (for example, at least one of R_1 to R_6) may each independently be a substituted or unsubstituted C_2 - C_{60} alkyl group, or a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, and/or

[0051] A_1 to A_6 may each independently be a substituted or unsubstituted C_1 - C_{60} alkyl group or a substituted or unsubstituted C_3 - C_{10} cycloalkyl group.

[0052] In one or more embodiments, R_1 to R_{10} and A_7 in Formula 1 may each independently be:

[0053] hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, $-SF_5$, C_1 - C_{20} alkyl group, or a C_1 - C_{20} alkoxy group;

[0054] a C_1 - C_{20} alkyl group or a C_1 - C_{20} alkoxy group, each substituted with deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CF_3$, $-CF_2H$, $-CFH_2$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C_1 - C_{20} alkyl)phenyl group, a biphenyl group, a terphenyl

group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or any combination thereof;

[0055] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothio-phenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group, each unsubstituted or substituted with deuterium, —F, —Br, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, or any combination thereof;

[0056] —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), —B(Q₆)(Q₇), or —P(=O)(Q₈)(Q₉), or any combination thereof.

[0057] Q₁ to Q₉ are the same as described herein.

[0058] In one or more embodiments, R₁ to R₁₀ and A₇ in Formula 1 may each independently be:

[0059] hydrogen, deuterium, —F, a cyano group, a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a carbazolyl group, a fluorenyl group, a dibenzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, or —Si(Q₃)(Q₄)(Q₅);

[0060] a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, or a tert-decyl group, each substituted with deuterium, —F, a cyano group, or any combination thereof; or

[0061] a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a carbazolyl group, a fluorenyl group, a dibenzosilolyl group, a dibenzofuranyl group, or a dibenzothiophenyl group, each substituted with deuterium, —F, a cyano group, a C₁-C₁₀ alkyl group, or any combination thereof.

[0062] Q₃ to Q₅ are the same as described herein.

[0063] In one or more embodiments, at least one of R₁ to R₁₀ (for example, at least one of R₁ to R₆ in an embodiment, R₄) in Formula 1 may each independently be:

[0064] a C₂-C₂₀ alkyl group or a C₁-C₂₀ alkoxy group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof,

a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or any combination thereof;

[0065] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothio-phenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetra-zolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzo-carbazolyl group, a dibenzocarbazolyl group, an imida-zopyridinyl group, or an imidazopyrimidinyl group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothio-

phenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetra-zolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzo-carbazolyl group, a dibenzocarbazolyl group, an imida-zopyridinyl group, an imidazopyrimidinyl group, or any combination thereof;

[0066] —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), —B(Q₆)(Q₇), or —P(=O)(Q₈)(Q₉), or any combination thereof.

[0067] Q₁ to Q₆ are the same as described herein.

[0068] In one or more embodiments, at least one of R₁ to R₁₀ (for example, at least one of R₁ to R₆/in an embodiment, R₄) Formula 1 may each independently be:

[0069] an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a carbazolyl group, a fluorenyl group, a dibenzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, or —Si(Q₃)(Q₄)(Q₅);

[0070] an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, or a tert-decyl group, each substituted with deuterium, —F, a cyano group, or any combination thereof; or

[0071] a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a carbazolyl group, a fluorenyl group, a dibenzosilolyl group, a dibenzofuranyl group, or a dibenzo-thiophenyl group, each substituted with deuterium, —F, a cyano group, a C₁-C₁₀ alkyl group, or any combination thereof.

[0072] Q₃ to Q₅ are the same as described herein.

[0073] In one or more embodiments, A_1 to A_6 in Formula 1 may each independently be:

[0074] a C_1 - C_{20} alkyl group or a C_1 - C_{20} alkoxy group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, — CD_3 , — CD_2H , — CDH_2 , — CF_3 , — CF_2H , — CFH_2 , a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C_1 - C_{20} alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or any combination thereof; or

[0075] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C_1 - C_{20} alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, a tetrazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group, each unsubstituted or substituted with deuterium, —F, —Br, — CD_3 , — CD_2H , — CDH_2 , — CF_3 , — CF_2H , — CFH_2 , a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C_1 - C_{20} alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an

isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, or any combination thereof.

[0076] In one or more embodiments, A_1 to A_6 in Formula 1 may each independently be:

[0077] a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isoheptyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a carbazolyl group, a fluorenyl group, a dibenzosilolyl group, a dibenzofuranlyl group or a dibenzothiophenyl group;

[0078] a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isoheptyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, or a tert-decyl group, each substituted with deuterium, —F, a cyano group, or any combination thereof; or

[0079] a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a carbazolyl group, a fluorenyl group, a dibenzosilolyl group, a dibenzofuranlyl group, or a dibenzo-

thiophenyl group, each substituted with deuterium, —F, a cyano group, a C₁-C₁₀ alkyl group, or any combination thereof.

[0080] Q₃ to Q₅ are the same as described herein.

[0081] For example, Q₁ to Q₅ may each independently be:

[0082] —CH₃, —CD₃, —CD₂H, —CDH₂, —CH₂CH₃, —CH₂CD₃, —CH₂CD₂H, —CH₂CDH₂, —CHDCH₃, —CHDCD₂H, —CHDCDH₂, —CHDCD₃, —CD₂CD₃, —CD₂CD₂H, or —CD₂CDH₂, or

[0083] an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, a phenyl group, a biphenyl group, or a naphthyl group, each unsubstituted or substituted with deuterium, a C₁-C₁₀ alkyl group, a phenyl group, or any combination thereof,



[0084] but embodiments of the present disclosure are not limited thereto.

[0085] In one or more embodiments, in Formula 1,

[0086] R₁ to R₁₀ and A₇ may each independently be hydrogen, deuterium, —F, a cyano group, a nitro group, —SF₅, —CH₃, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a group represented by one of Formulae 9-1 to 9-66, a group represented by one of Formulae 9-1 to 9-66 in which at least one hydrogen is substituted with deuterium, a group represented by one of Formulae 10-1 to 10-249, a group represented by one of Formulae 10-1 to 10-249 in which at least one hydrogen is substituted with deuterium, —Si(Q₃)(Q₄)(Q₅), or —Ge(Q₃)(Q₄)(Q₅) (wherein Q₃ to Q₅ are the same as described herein), and/or

[0087] at least one of R₁ to R₁₀ (for example, at least one of R₁ to R₆) may each independently be a group represented by one of Formulae 9-1 to 9-66, a group represented by one of Formulae 9-1 to 9-66 in which at least one hydrogen is substituted with deuterium, a group represented by one of Formulae 10-1 to 10-249, a group represented by one of Formulae 10-1 to 10-249 in which at least one hydrogen is substituted with deuterium, —Si(Q₃)(Q₄)(Q₅), or —Ge(Q₃)(Q₄)(Q₅) (wherein Q₃ to Q₅ are the same as described herein), and/or

[0088] A₁ to A₆ may each independently be —CH₃, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a group represented by one of Formulae 9-1 to 9-66, a group represented by one of Formulae 9-1 to 9-66 in which at least one hydrogen is substituted with deuterium, a group represented by one of Formulae 10-1 to 10-249, or a group represented by one of Formulae 10-1 to 10-249 in which at least one hydrogen is substituted with deuterium, but embodiments of the present disclosure are not limited thereto:




9-1

9-2


9-3

9-4


-continued



9-5




9-6




9-7




9-8




9-9




9-10




9-11




9-12




9-13




9-14



9-15




9-16



9-17




9-18




9-19
















9-20



9-21




-continued




-continued

9-22



9-35

9-23



9-36

9-24




9-37

9-25




9-38

9-26



9-39

9-27




9-40

9-28




9-41

9-29




9-42

9-30




9-43

9-31




9-44

9-32



9-45










9-33



9-46


9-34

-continued




-continued

9-47




9-56

9-48




9-57

9-49




9-58

9-50




9-59

9-51




9-60

9-52




9-61

9-53




9-62

9-54




9-63

9-55














9-64




9-65

-continued




-continued


9-66




10-1




10-2




10-3




10-4




10-5




10-6




10-7




10-8



10-9



10-10



10-11

10-12

10-13

10-14

10-15

10-16

10-17

10-18











10-19

10-20

10-21


10-22

-continued




-continued

10-23




10-33

10-24




10-34

10-25




10-35

10-26




10-36

10-27




10-37

10-28




10-38

10-29




10-39

10-30




10-40

10-31




10-41

10-32












10-42




10-43

-continued




-continued

10-44




10-53

10-45




10-54

10-46




10-55

10-47



10-56


10-48



10-57


10-49

10-50



10-58

10-51













10-59

10-52




10-60

-continued




-continued


10-61



10-62




10-63




10-64

10-65




10-66

10-67



10-68

10-69



10-70

10-71

10-72











10-73

10-74


10-75

10-76


-continued




10-77



10-87




10-88



10-89


10-78

10-79




10-90

10-80




10-91

10-81




10-92

10-82




10-93

10-83




10-94

10-84




10-95

10-85




10-96

10-86













10-97




10-98

-continued




-continued

10-99




10-100

10-101




10-102

10-103




10-104

10-105





10-106

10-107



10-108



10-109

10-110

10-111








10-112

10-113

10-114


10-115

-continued




-continued

10-116




10-123

10-117




10-124

10-118




10-125

10-119




10-126

10-120




10-127

10-121




10-128

10-122




10-129


-continued




10-130




10-131




10-132




10-133



10-134




10-135




10-136


-continued




10-137




10-138




10-139




10-140



10-141












10-142




10-143

-continued




-continued

10-144




10-153

10-145




10-154

10-146




10-155

10-147




10-156

10-148




10-157

10-149




10-158

10-150




10-159

10-151




10-160

10-152




10-161




10-162

-continued




10-163

-continued




10-170

10-164




10-171




10-165

10-172




10-166

10-173




10-167

10-174




10-168

10-175







10-169

10-176















10-169

10-177




-continued




-continued

10-178




10-190

10-179




10-191

10-180




10-192

10-181




10-193

10-182




10-194

10-183




10-195

10-184




10-196

10-185




10-197

10-186




10-198

10-187



10-199


10-188




10-200

10-189


-continued




10-201




10-202




10-203




10-204



10-205




10-206




10-207


-continued




10-208




10-209




10-210




10-211



10-212




10-213




10-214


-continued




10-215




10-216




10-217




10-218



10-219




10-220




10-221


-continued




10-222




10-223




10-224




10-225




10-226



10-227




10-228




10-229


-continued



-continued



-continued









10-248

10-249

[0089] In Formulae 9-1 to 9-66 and 10-1 to 10-249, * indicates a binding site to a neighboring atom, Ph indicates a phenyl group, and TMS indicates a trimethylsilyl group.

[0090] The “group represented by one of Formulae 9-1 to 9-66 in which at least one hydrogen is substituted with deuterium” may be, for example, a group represented by one of Formulae 9-501 to 9-552:



9-501

9-502

9-503

9-504










9-505

9-506

9-507

9-508

-continued



9-509

9-510

9-511

9-512

9-513


9-514

9-515


9-516

9-517


-continued




9-518




9-519




9-520




9-521




9-522




9-523




9-524



9-525




9-526




9-527


-continued




9-528




9-529



9-530




9-531




9-532




9-533



9-534




9-535




9-536


-continued




9-537




9-538




9-539




9-540




9-541




9-542




9-543



9-544




9-545




9-546


-continued




9-547




9-548




9-549



9-550




9-551




9-552


[0091] The “group represented by one of Formulae 10-1 to 10-249 in which at least one hydrogen is substituted with deuterium” may be, for example, a group represented by one of Formulae 10-501 to 10-510:



10-501




10-502




10-503


-continued




10-504




10-505




10-506




10-507



10-508




10-509



10-510

[0092] In one or more embodiments, at least one of R_1 to R_{10} (for example, at least one of R_1 to R_6) in Formula 1 may be a group represented by Formula 2:



Formula 2

[0093] The number of carbon atoms included in Formula 2 may be 4 or more (for example, 4 to 20, 4 to 15 or 4 to 10).

[0094] R_{13} in Formula 2 may be hydrogen, deuterium, a C_1 - C_{20} alkyl group, deuterium-containing C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, or a deuterium-containing C_3 - C_{10} cycloalkyl group.

[0095] R_{14} and R_{15} in Formula 2 may each independently be a C_1 - C_{20} alkyl group, deuterium-containing C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, or a deuterium-containing C_3 - C_{10} cycloalkyl group.

[0096] * in Formula 2 indicates a binding site to a neighboring atom.

[0097] The terms “a deuterium-containing C_1 - C_{20} alkyl group” and “a deuterium-containing C_3 - C_{10} cycloalkyl group” as used herein each refer to a C_1 - C_{20} alkyl group substituted with at least one deuterium and a C_3 - C_{10} cycloalkyl group substituted with at least one deuterium, respectively. For example, a deuterium-containing methyl group may be $-CDH_2$, $-CD_2H$, and $-CD_3$.

[0098] Non-limiting examples of the “ C_1 - C_{20} alkyl group” include a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, and the like, but embodiments of the present disclosure are not limited thereto.

[0099] Non-limiting of the “ C_3 - C_{10} cycloalkyl group” include a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, and the like, but embodiments of the present disclosure are not limited thereto.

[0100] For example, R_{13} in Formula 2 may be hydrogen or deuterium.

[0101] in an embodiment, R_{13} in Formula 2 may be a C_1 - C_{20} alkyl group, a deuterium-containing C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, or a deuterium-containing C_3 - C_{10} cycloalkyl group.

[0102] In an embodiment, R_{14} and R_{15} in Formula 2 may be different from each other.

[0103] In one or more embodiments, in Formula 2,

[0104] R_{13} may be hydrogen, deuterium, $-CH_3$, $-CDH_2$, $-CD_2H$, or $-CD_3$, and

[0105] R_{14} and R_{15} may each independently be:

[0106] a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a

sec-decyl group, a tert-decyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, or a bicyclo[2.2.2]octyl group; or

[0107] a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isoheptyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, or a bicyclo[2.2.2]octyl group, each substituted with at least one deuterium,

[0108] but embodiments of the present disclosure are not limited thereto.

[0109] In one or more embodiments, in Formula 2,

[0110] R_{13} may be hydrogen, deuterium, $-\text{CH}_3$, $-\text{CDH}_2$, $-\text{CD}_2\text{H}$, or $-\text{CD}_3$,

[0111] R_{14} may be $-\text{CH}_3$, $-\text{CDH}_2$, $-\text{CD}_2\text{H}$, or $-\text{CD}_3$, and

[0112] R_{15} may be:

[0113] an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isoheptyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, or a bicyclo[2.2.2]octyl group; or

[0114] an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isoheptyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, or a bicyclo[2.2.2]octyl group, each substituted with at least one deuterium,

[0115] but embodiments of the present disclosure are not limited thereto.

[0116] In one or more embodiments, R_{14} and R_{15} in Formula 2 may each independently be $-\text{CH}_3$, $-\text{CDH}_2$,

$-\text{CD}_2\text{H}$, $-\text{CD}_3$, a group represented by one of Formulae 9-1 to 9-33, a group represented by one of Formulae 9-1 to 9-33 in which at least one hydrogen is substituted with deuterium, a group represented by one of Formulae 10-1 to 10-10, or a group represented by one of Formulae 10-1 to 10-10 in which at least one hydrogen is substituted with deuterium, but embodiments of the present disclosure are not limited thereto.

[0117] In one or more embodiments, a case where R_{13} to R_{15} in Formula 2 are all the same may be excluded.

[0118] In one or more embodiments, a case where R_{13} to R_{15} in Formula 2 are all methyl groups may be excluded.

[0119] In an embodiment, at least one of R_1 to R_6 in Formula 1 may each independently be a group represented by Formula 2.

[0120] For example, R_4 in Formula 1 may be a group represented by Formula 2.

[0121] In an embodiment, R_1 to R_3 , R_5 , and R_6 in Formula 1 may each be hydrogen, and R_4 may be a group represented by Formula 2.

[0122] In an embodiment, at least one of R_4 , R_7 , and R_9 in Formula 1 may not be each hydrogen.

[0123] In one or more embodiments, each of R_7 and R_9 in Formula 1 may not be hydrogen.

[0124] In one or more embodiments, in Formula 1, each of R_7 and R_9 may not be hydrogen, and each of R_8 and R_{10} may not be hydrogen.

[0125] In one or more embodiments, none of R_4 , R_7 , and R_9 in Formula 1 may be hydrogen.

[0126] In one or more embodiments, each of R_7 and R_9 in Formula 1 may not be hydrogen, and R_7 and R_9 may be identical to each other.

[0127] In one or more embodiments, each of R_7 and R_9 in Formula 1 may not be hydrogen, and R_7 and R_9 may be different from each other.

[0128] In one or more embodiments, in Formula 1, each of R_7 and R_9 may not be hydrogen, R_7 and R_9 may be different from each other, and the number of carbon atoms included in R_7 may be greater than that of carbon atoms included in R_9 .

[0129] In one or more embodiments, R_7 and R_9 in Formula 1 may each independently be a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, or a substituted or unsubstituted C_6 - C_{60} aryl group.

[0130] In one or more embodiments, at least one of R_7 and R_9 in Formula 1 may each independently be a substituted or unsubstituted C_2 - C_{60} alkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, or a substituted or unsubstituted C_6 - C_{60} aryl group.

[0131] In one or more embodiments, at least one of A_1 to A_6 in Formula 1 may each independently be a substituted or unsubstituted C_2 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_7 - C_{60} arylalkyl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted

or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted C₂-C₆₀ heteroarylalkyl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

[0132] For example, at least one of A₁ to A₆ in Formula 1 may each independently be:

[0133] an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an iso-hexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a carbazolyl group, a fluorenyl group, a dibenzosilolyl group, a dibenzofuranyl group, or a dibenzothiophenyl group;

[0134] an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an iso-hexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, or a tert-decyl group, each substituted with deuterium, —F, a cyano group, any combination thereof; or

[0135] a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a carbazolyl group, a fluorenyl group, a dibenzosilolyl group, a dibenzofuranyl group, or a dibenzothiophenyl group, each substituted with deuterium, —F, a cyano group, a C₁-C₁₀ alkyl group, any combination thereof.

[0136] Q₃ to Q₅ are the same as described herein.

[0137] In an embodiment, at least one of A₁ to A₆ in Formula 1 may each independently be a group represented by one of Formulae 9-1 to 9-66, a group represented by one of Formulae 9-1 to 9-66 in which at least one hydrogen is substituted with deuterium, a group represented by one of Formulae 10-1 to 10-249, or a group represented by one of

Formulae 10-1 to 10-249 in which at least one hydrogen is substituted with deuterium, but embodiments of the present disclosure are not limited thereto.

[0138] In one or more embodiments, A₇ may not be hydrogen.

[0139] In one or more embodiments, in Formula 1, a group represented by *—C(A₁)(A₂)(A₃) and a group represented by *—C(A₄)(A₅)(A₆) may be identical to each other, and * indicates a binding site to a neighboring atom.

[0140] In one or more embodiments, in Formula 1 a group represented by *—C(A₁)(A₂)(A₃) and a group represented by *—C(A₄)(A₅)(A₆) may be different from each other, and * indicates a binding site to a neighboring atom.

[0141] In one or more embodiments, in Formula 1,

[0142] A₁ and A₂ may be identical to each other, and A₁ and A₃ may be different from each other; and/or

[0143] A₄ and A₅ may be identical to each other, and A₄ and A₆ may be different from each other.

[0144] In Formula 1, two or more of R₁ to R₁₀ may optionally be linked to form a C₅-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{1a}, and two or more of A₁ to A₆ may optionally be linked to form a C₅-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{1a}. Here, R_{1a} is the same as defined in connection with R₇.


[0145] For example, a C₅-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} and a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{1a} may each independently be a cyclopentane group, a cyclohexane group, a cycloheptane group, a cyclooctane group, an adamantane group, a norbornane group, a norbornene group, a cyclopentene group, a cyclohexene group, a cycloheptene group, a bicyclo[1.1.1]pentane group, a bicyclo[2.1.1]hexane group, a bicyclo[2.2.1]heptane group, a bicyclo[2.2.2]octane group, a benzene group, a naphthalene group, a fluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an isoindole group, an indole group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a cinnoline group, a carbazole group, a phenanthroline group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a tetrazine group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, a dibenzocarbazole group, an imidazopyridine group, or an imidazopyrimidine group, each unsubstituted or substituted with at least one R_{1a}, but embodiments of the present disclosure are not limited thereto.

[0146] In an embodiment, two or more of A₁ to A₃ (for example, all of A₁ to A₃) in Formula 1 may be linked to form a C₅-C₆₀ carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C₁-C₆₀ heterocyclic group unsubstituted or substituted with at least one R_{1a}, and/or two or more of A₄ to A₆ (for example, all of A₄ to A₆) in Formula 1 may be


linked to form a C_5 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{1a} .

[0147] In one or more embodiments, in Formula 1, at least one of a group represented by $*-C(A_1)(A_2)(A_3)$ and a group represented by $*-(A_4)(A_5)(A_6)$ may each independently be a cyclopentane group, a cyclohexane group, a cycloheptane group, a cyclooctane group, an adamantane group, a norbornane group, a norbornene group, a cyclopentene group, a cyclohexene group, a cycloheptene group, a bicyclo[1.1.1]pentane group, a bicyclo[2.1.1]hexane group, a bicyclo[2.2.1]heptane group, a bicyclo[2.2.2]octane group, a benzene group, a naphthalene group, a fluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an isoindole group, an indole group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a cinnoline group, a carbazole group, a phenanthroline group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a tetrazine group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, a dibenzocarbazole group, an imidazopyridine group, or an imidazopyrimidine group, each unsubstituted or substituted with at least one R_{1a} , but embodiments of the present disclosure are not limited thereto.

[0148] For example, the organometallic compound represented by Formula 1 may be one of Compounds 1 to 6, but embodiments of the present disclosure are not limited thereto:



-continued



[0149] At least one of R_1 to R_{10} in Formula 1 may each independently be a substituted or unsubstituted C_2 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted

or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₇-C₆₀ arylalkyl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted C₂-C₆₀ heteroarylalkyl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), —Ge(Q₃)(Q₄)(Q₅), —B(Q₆)(Q₇), —P(=O)(Q₈)(Q₉), or —P(Q₈)(Q₉). For example, at least one of R₁ to R₁₀ (for example, at least one of R₁ to R₆) in Formula 1 may not be hydrogen nor a methyl group, but may be a substituent described above. In this regard, the organometallic compound represented by Formula 1 may have an increased electron-donating effect so that a wavelength of the light emitted by the organometallic compound may be shifted to a relatively short wavelength side. Accordingly, the non-radiative transition of the organometallic compound may decrease while the photoluminescence quantum yield (PLQY) of the organometallic compound may increase. As a result, an electronic device, for example, an organic light-emitting device, including the organometallic compound may have increased external quantum efficiency (EQE), and the full width at half maximum (FWHM) of the electroluminescence (EL) spectrum peak of such an organic light-emitting device may be reduced.

[0150] In one or more embodiments, A₁ to A₆ in Formula 1 may each independently be a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₇-C₆₀ arylalkyl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted C₂-C₆₀ heteroarylalkyl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group. For example, each of A₁ to A₆ in Formula 1 may not be hydrogen, but may include at least one carbon.

[0151] Although not limited to a particular theory, an α -proton has chemical reactivity that is about 10⁵ greater than that of a β -proton. That is, the α -proton may cause a side reaction due to production of intermediates in various forms during synthesis and/or storage of a compound. However, each A₁ to A₆ in Formula 1 as described above may not include the α -proton, and in this regard, the organometallic compound represented by Formula 1 may have a stable

chemical structure with minimal occurrence of a side reaction before/after synthesis, and at the same time, an intermolecular interaction of the organometallic compound may be minimized during the operation of an electronic device (for example, an organic light-emitting device) including the organometallic compound. Thus, an electronic device, for example, an organic light-emitting device, including the organometallic compound represented by Formula 1 may have improved luminescence efficiency and lifespan characteristics.

[0152] A highest occupied molecular orbital (HOMO) energy level, a lowest unoccupied molecular orbital (LUMO) energy level, a singlet (S₁) energy level, and a triplet (T₁) energy level of some compounds of the organometallic compound represented by Formula 1 are evaluated by a density functional theory (DFT) of Gaussian program with molecular structure optimization based on B3LYP, and results are shown in Table 1.

TABLE 1

Compound No.	HOMO (eV)	LUMO (eV)	T ₁ (eV)
1	-4.554	-1.672	1.974
2	-4.542	-1.659	2.008
3	-4.543	-1.660	1.975
4	-4.504	-1.644	1.978
5	-4.543	-1.658	1.977
6	-4.567	-1.672	1.990

[0153] Referring to Table 1, it is confirmed that the organometallic compound represented by Formula 1 has such electrical characteristics that are suitable for use as a dopant for in an electronic device, for example, for an organic light-emitting device.

[0154] Synthesis methods of the organometallic compound represented by Formula 1 may be recognizable by one of ordinary skill in the art by referring to Synthesis Examples provided below.

[0155] Therefore, the organometallic compound represented by Formula 1 may be suitable for use as a dopant in an organic layer of an organic light-emitting device, for example, in an emission layer of the organic layer. Another aspect of the present disclosure provides an organic light-emitting device including: a first electrode, a second electrode, and an organic layer disposed between the first electrode and the second electrode and including an emission layer, wherein the organic layer includes at least one organometallic compound represented by Formula 1.

[0156] The organic light-emitting device may have, due to the inclusion of an organic layer including the organometallic compound represented by Formula 1, an improved driving voltage, an improved external quantum efficiency, an improved low roll-off ratio, and an improved long lifespan.

[0157] The organometallic compound represented by Formula 1 may be used between a pair of electrodes of an organic light-emitting device. For example, the organometallic compound represented by Formula 1 may be included in the emission layer. In this regard, the organometallic compound may act as a dopant, and the emission layer may

further include a host (that is, an amount of the organometallic compound represented by Formula 1 is smaller than an amount of the host). The emission layer may emit red light having a maximum emission wavelength in a range of, for example, about 550 nanometers (nm) or more (for example, about 550 nm or more and about 900 nm or less).

[0158] The expression “(an organic layer) includes at least one organometallic compound” as used herein may include an embodiment in which “(an organic layer) includes identical organometallic compounds represented by Formula 1” and an embodiment in which “(an organic layer) includes two or more different organometallic compounds represented by Formula 1”.

[0159] For example, the organic layer may include, as the organometallic compound, only Compound 1. In this regard, Compound 1 may be included only in the emission layer of the organic light-emitting device. In one or more embodiments, the organic layer may include, as the organometallic compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may be included in an identical layer (for example, Compound 1 and Compound 2 all may exist in an emission layer).

[0160] The first electrode may be an anode, which is a hole injection electrode, and the second electrode may be a cathode, which is an electron injection electrode; or the first electrode may be a cathode, which is an electron injection electrode, and the second electrode may be an anode, which is a hole injection electrode.

[0161] For example, the organic light-emitting device, the first electrode is an anode, and the second electrode is a cathode, and the organic layer further includes a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode, and the hole transport region includes a hole injection layer, a hole transport layer, an electron blocking layer, or any combination thereof, and the electron transport region includes a hole blocking layer, an electron transport layer, an electron injection layer, or any combination thereof.

[0162] The term “organic layer” as used herein refers to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of an organic light-emitting device. The “organic layer” may include, in addition to an organic compound, an organometallic complex including metal.

[0163] The FIGURE is a schematic cross-sectional view of an organic light-emitting device **10** according to an embodiment. Hereinafter, the structure of an organic light-emitting device according to an embodiment and a method of manufacturing an organic light-emitting device according to an embodiment will be described in connection with the FIGURE. The organic light-emitting device **10** includes a first electrode **11**, an organic layer **15**, and a second electrode **19**, which are sequentially stacked.

[0164] A substrate may be additionally disposed under the first electrode **11** or above the second electrode **19**. For use as the substrate, any substrate that is used in general organic light-emitting devices may be used, and the substrate may be

a glass substrate or a transparent plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

[0165] The first electrode **11** may be formed by depositing or sputtering a material for forming the first electrode **11** on the substrate. The first electrode **11** may be an anode. The material for forming the first electrode **11** may be a material with a high work function to facilitate hole injection. The first electrode **11** may be a reflective electrode, a semi-reflective electrode, or a transmissive electrode. The material for forming the first electrode may be, for example, indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), and zinc oxide (ZnO). In one or more embodiments, the material for forming the first electrode **11** may be metal, such as magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag).

[0166] The first electrode **11** may have a single-layered structure or a multi-layered structure including two or more layers. For example, the first electrode **11** may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode **11** is not limited thereto.

[0167] The organic layer **15** is disposed on the first electrode **11**.

[0168] The organic layer **15** may include a hole transport region, an emission layer, and an electron transport region.

[0169] The hole transport region may be disposed between the first electrode **11** and the emission layer.

[0170] The hole transport region may include a hole injection layer, a hole transport layer, an electron blocking layer, a buffer layer, or any combination thereof.

[0171] The hole transport region may include only either a hole injection layer or a hole transport layer. In one or more embodiments, the hole transport region may have a hole injection layer/hole transport layer structure or a hole injection layer/hole transport layer/electron blocking layer structure, which are sequentially stacked in this stated order from the first electrode **11**.

[0172] When the hole transport region includes a hole injection layer, the hole injection layer may be formed on the first electrode **11** by using one or more suitable methods, for example, vacuum deposition, spin coating, casting, and/or Langmuir-Blodgett (LB) deposition.


[0173] When a hole injection layer is formed by vacuum deposition, the deposition conditions may vary according to a material that is used to form the hole injection layer, and the structure and thermal characteristics of the hole injection layer. For example, the deposition conditions may include a deposition temperature of about 100° C. to about 500° C., a vacuum pressure of about 10⁻⁸ to about 10⁻³ torr, and a deposition rate of about 0 Angstroms per second (Å/sec) to about 100 Å/sec. However, the deposition conditions are not limited thereto, but embodiments of the present disclosure are not limited thereto.

[0174] When the hole injection layer is formed using spin coating, coating conditions may vary according to the material used to form the hole injection layer, and the structure


and thermal properties of the hole injection layer. For example, a coating speed may be from about 2,000 revolutions per minute (rpm) to about 5,000 rpm, and a temperature at which a heat treatment is performed to remove a solvent after coating may be from about 80° C. to about 200° C. However, the coating conditions are not limited thereto.

[0175] Conditions for forming a hole transport layer and an electron blocking layer may be understood by referring to conditions for forming the hole injection layer.


[0176] The hole transport region may include m-MT-DATA, TDATA, 2-TNATA, NPB, β -NPB, TPD, spiro-TPD, spiro-NPB, methylated-NPB, TAPC, HMTPD, 4,4',4''-tris (N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzene sulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrene sulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrene sulfonate) (PANI/PSS), a compound represented by Formula 201 below, a compound represented by Formula 202 below, or any combination thereof:




m-MT-DATA





TDATA




2-TNATA




NPB

 β -NPB


TPD




Spiro-TPD




Spiro-NPB




methylated NPB




TAPC



HMTPD



Formula 202



[0177] Ar₁₀₁ to Ar₁₀₂ in Formula 201 may each independently be a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, or a pentacenylene group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, or any combination thereof.

[0178] xa and xb in Formula 201 may each independently be an integer from 0 to 5, or may be 0, 1 or 2. For example, xa may be 1 and xb may be 0, but xa and xb are not limited thereto.

[0179] R_{101} to R_{108} , R_{111} to R_{119} , and R_{121} to R_{124} in Formulae 201 and 202 may each independently be:

[0180] hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group (for example, a methyl group, an ethyl group, a propyl group, a butyl group, pentyl group, a hexyl group, and the like), or a C_1 - C_{10} alkoxy group (for example, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, and the like);

[0181] a C_1 - C_{10} alkyl group or a C_1 - C_{10} alkoxy group, each substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, or any combination thereof; or

[0182] a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, or a pyrenyl group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, or any combination thereof,

[0183] but embodiments of the present disclosure are not limited thereto.


[0184] R_{109} in Formula 201 may be a phenyl group, a naphthyl group, an anthracenyl group, or a pyridinyl group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyridinyl group, or any combination thereof.

[0185] In an embodiment, the compound represented by Formula 201 may be represented by Formula 201A, but embodiments of the present disclosure are not limited thereto:


[0186] Detailed descriptions of R_{101} , R_{111} , R_{112} , and R_{109} in Formula 201A are the same as described provided herein.

[0187] For example, the compound represented by Formula 201 and the compound represented by Formula 202 may each include one of Compounds HT1 to HT20 or any combination thereof, but embodiments of the present disclosure are not limited thereto:


HT1



HT2




Formula 201A




-continued

HT3




-continued


HT5



HT4




HT6




-continued

HT7





-continued

HT9




HT10

HT8




-continued

HT11




-continued


HT14




HT15




HT12




HT16




HT13



HT17



-continued




[0188] A thickness of the hole transport region may be from about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes at least one of a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, for example about 100 Å to about 1,500 Å. While not wishing to be bound by theory, it is understood that when the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

[0189] The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-

generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

[0190] The charge-generation material may be, for example, a p-dopant. The p-dopant may be a quinone derivative, a metal oxide, a cyano group-containing compound, or any combination thereof, but embodiments of the present disclosure are not limited thereto. Non-limiting examples of the p-dopant are a quinone derivative, such as tetracyanoquinonedimethane (TCNQ) or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonedimethane (F4-TCNQ); a metal oxide, such as a tungsten oxide or a molybdenum oxide; and a cyano group-containing compound, such as Compound HT-D1 below, but are not limited thereto:



[0191] The hole transport region may include a buffer layer.






[0192] Also, the buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, and thus, efficiency of a formed organic light-emitting device may be improved.

[0193] Meanwhile, when the hole transport region includes an electron blocking layer, a material for the electron blocking layer may be materials for the hole transport region described above, materials for a host to be explained later, or any combination thereof. However, the material for the electron blocking layer is not limited thereto. For example, when the hole transport region includes an electron blocking layer, a material for the electron blocking layer may be mCP, which will be explained later.



[0194] Then, an emission layer may be formed on the hole transport region by vacuum deposition, spin coating, casting, LB deposition, or the like. When the emission layer is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied in forming the hole injection layer although the deposition or coating conditions may vary according to a compound that is used to form the emission layer.

[0195] The emission layer may include a host and a dopant, and the dopant may include the organometallic compound represented by Formula 1.


[0196] The host may include TPBi, TBADN, ADN (also referred to as “DNA”), CBP, CDBP, TCP, mCP, Compounds H50, Compound H51, Compound H52, or any combination thereof:




-continued




H50



H51



H52



[0197] When the organic light-emitting device is a full-color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and/or a blue emission layer. In one or more embodiments, due to a stacked structure including a red emission

layer, a green emission layer, and/or a blue emission layer, the emission layer may emit white light.

[0198] When the emission layer includes a host and a dopant, an amount of the dopant may be in a range of about 0.01 parts by weight to about 15 parts by weight based on 100 parts by weight of the host, but embodiments of the present disclosure are not limited thereto.

[0199] A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. While not wishing to be bound by theory, it is understood that when the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.


[0200] Then, an electron transport region may be disposed on the emission layer.

[0201] The electron transport region may include a hole blocking layer, an electron transport layer, an electron injection layer, or any combination thereof.


[0202] For example, the electron transport region may have a hole blocking layer/electron transport layer/electron injection layer structure or an electron transport layer/electron injection layer structure, but the structure of the electron transport region is not limited thereto. The electron transport layer may have a single-layered structure or a multi-layered structure including two or more different materials.

[0203] Conditions for forming the hole blocking layer, the electron transport layer, and the electron injection layer which constitute the electron transport region may be understood by referring to the conditions for forming the hole injection layer.

[0204] When the electron transport region includes a hole blocking layer, the hole blocking layer may include, for example, BCP, BPhen, BAiq, or any combination thereof, but embodiments of the present disclosure are not limited thereto:






BCP




Bphen

[0205] A thickness of the hole blocking layer may be from about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. While not wishing to be bound by theory, it is understood that when the thickness of the hole blocking layer is within these ranges, the hole blocking layer may have excellent hole blocking characteristics without a substantial increase in driving voltage.

[0206] The electron transport layer may include BOP, BPhen, Alq₃, BAiq, TAZ, NTAZ, or any combination thereof:









TAZ




NTAZ

[0207] In one or more embodiments, the electron transport layer may include at least one of ET1 to ET25, but are not limited thereto:







-continued



-continued




-continued




-continued

ET14





-continued

ET17





ET18

ET15




ET19

ET16




-continued

ET20





-continued

ET23





ET21

ET24



ET22


ET25



[0208] A thickness of the electron transport layer may be from about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. While not wishing to be bound by theory, it is understood that when the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.

[0209] Also, the electron transport layer may further include, in addition to the materials described above, a metal-containing material.

[0210] The metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (LiQ), Compound ET-D2, or combination thereof:



[0211] The electron transport region may include an electron injection layer that promotes flow of electrons from the second electrode **19** therein.

[0212] The electron injection layer may include LiF, NaCl, CsF, Li₂O, BaO, or any combination thereof.

[0213] A thickness of the electron injection layer may be from about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. While not wishing to be bound by theory, it is understood that when a thickness of the electron injection layer is within these ranges, satisfactory electron injection characteristics may be obtained without substantial increase in driving voltage.

[0214] The second electrode **19** is disposed on the organic layer **15**. The second electrode **19** may be a cathode. A material for forming the second electrode **19** may be a metal, an alloy, an electrically conductive compound, or a combination thereof, which have a relatively low work function. For example, lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be formed as the material for forming the second electrode **19**. To manufacture a top-emission type light-emitting device, a transmissive electrode formed using ITO or IZO may be used as the second electrode **19**.

[0215] Hereinbefore, the organic light-emitting device according to an embodiment has been described in connection with the FIGURE.

[0216] Another aspect of the present disclosure provides a diagnostic composition including at least one of the organometallic compound represented by Formula 1.

[0217] The organometallic compound represented by Formula 1 provides high luminescent efficiency. Accordingly, a diagnostic composition including the organometallic compound may have high diagnostic efficiency.

[0218] The diagnostic composition may be used in various applications including a diagnosis kit, a diagnosis reagent, a biosensor, and a biomarker.

[0219] The term “C₁-C₆₀ alkyl group” as used herein refers to a linear or branched saturated aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms, and examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an isoamyl group, and a hexyl group. The term “C₁-C₆₀ alkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

[0220] The term “C₁-C₆₀ alkoxy group” as used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group), and examples thereof include a methoxy group, an ethoxy group, and an iso-propyloxy group.

[0221] The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon double bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkenylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

[0222] The term “C₂-C₆₀ alkynyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon triple bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethynyl group, and a propynyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

[0223] The term “C₃-C₁₀ cycloalkyl group” as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and non-limiting examples thereof include a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, and a bicyclo[2.2.2]octyl group. The term “C₃-C₁₀ cycloalkylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

[0224] The term “C₁-C₁₀ heterocycloalkyl group” as used herein refers to a monovalent saturated monocyclic group having at least one heteroatom selected from N, O, P, Si and S as a ring-forming atom and 1 to 10 carbon atoms, and non-limiting examples thereof include a tetrahydrofuranlyl group and a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkyl group.

[0225] The term “C₃-C₁₀ cycloalkenyl group” as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atom, at least one carbon-carbon double bond in its ring, and no aromaticity, and a non-limiting example thereof includes a cycloheptenyl group. The term “C₃-C₁₀ cycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

[0226] The term “C₁-C₁₀ heterocycloalkenyl group” as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, P, Si, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least

one double bond in its ring. Non-limiting examples of the C₁-C₁₀ heterocycloalkenyl group include a 2,3-dihydrofuran-yl group and a 2,3-dihydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkenyl group.

[0227] The term “C₆-C₆₀ aryl group” as used herein refers to a monovalent group having a monovalent carbocyclic aromatic system having 6 to 60 carbon atoms, and the term “C₆-C₆₀ arylene group” as used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Non-limiting examples of the C₆-C₆₀ aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

[0228] The term “C₁-C₆₀ heteroaryl group” as used herein refers to a monovalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, P, Si, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. The term “C₁-C₆₀ heteroarylene group” as used herein refers to a divalent group having a heterocyclic aromatic system that has at least one heteroatom selected from N, O, P, Si, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. Non-limiting examples of the C₁-C₆₀ heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the rings may be fused to each other.

[0229] The term “C₆-C₆₀ aryloxy group” as used herein indicates —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), the term “C₆-C₆₀ arylthio group” as used herein indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group), and the term “C₇-C₆₀ arylalkyl group” as used herein indicates —A₁₀₄A₁₀₅ (wherein A₁₀₅ is the C₆-C₅₉ aryl group and A₁₀₄ is the C₁-C₅₃ alkylene group).

[0230] The term “C₁-C₆₀ heteroaryloxy group” as used herein refers to —OA₁₀₆ (wherein A₁₀₆ is the C₂-C₆₀ heteroaryl group), the term “C₁-C₆₀ heteroarylthio group” as used herein indicates —SA₁₀₇ (wherein A₁₀₇ is the C₁-C₆₀ heteroaryl group), and the term “C₂-C₆₀ heteroarylalkyl group” as used herein refers to —A₁₀₈A₁₀₉ (A₁₀₉ is a C₁-C₅₉ heteroaryl group, and A₁₀₈ is a C₁-C₅₉ alkylene group).

[0231] The term “monovalent non-aromatic condensed polycyclic group” as used herein refers to a monovalent group (for example, having 8 to 60 carbon atoms) having two or more rings condensed to each other, only carbon atoms as ring-forming atoms, and no aromaticity in its entire molecular structure. A non-limiting example of the monovalent non-aromatic condensed polycyclic group includes a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

[0232] The term “monovalent non-aromatic condensed heteropolycyclic group” as used herein refers to a monovalent group (for example, having 2 to 60 carbon atoms) having two or more rings condensed to each other, a heteroatom selected from N, O, P, Si, and S, other than carbon atoms, as a ring-forming atom, and no aromaticity in its entire molecular structure. A non-limiting example of the

monovalent non-aromatic condensed heteropolycyclic group includes a carbazolyl group. The term “divalent non-aromatic condensed heteropolycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0233] The term “C₅-C₆₀ carbocyclic group” as used herein refers to a saturated or unsaturated cyclic group having, as a ring-forming atom, 5 to 60 carbon atoms only. The C₅-C₆₀ carbocyclic group may be a monocyclic group or a polycyclic group.

[0234] The term “C₁-C₆₀ heterocyclic group” as used herein refers to a saturated or unsaturated cyclic group having, as a ring-forming atom, at least one heteroatom selected from N, O, Si, P, and S other than 1 to 60 carbon atoms. The C₁-C₆₀ heterocyclic group may be a monocyclic group or a polycyclic group.

[0235] A substituent(s) of the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₇-C₆₀ arylalkyl group, the substituted C₁-C₆₀ heteroaryl group, the substituted C₁-C₆₀ heteroaryloxy group, the substituted C₁-C₆₀ heteroarylthio group, the substituted C₂-C₆₀ heteroarylalkyl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may each independently be:

[0236] deuterium, —F, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group;

[0237] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group, each substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), —Ge(Q₁₃)(Q₁₄)(Q₁₅), —B(Q₁₆)(Q₁₇), —P(=O)(Q₁₈)(Q₁₉), —P(Q₁₈)(Q₁₉), or any combination thereof;

[0238] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy

group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group;

[0239] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group, each substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), —Ge(Q₂₃)(Q₂₄)(Q₂₅), —B(Q₂₆)(Q₂₇), —P(=O)(Q₂₈)(Q₂₉), —P(Q₂₈)(Q₂₉), or any combination thereof;

[0240] —N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), —Ge(Q₃₃)(Q₃₄)(Q₃₅), —B(Q₃₆)(Q₃₇), —P(=O)(Q₃₈)(Q₃₉), or —P(Q₃₈)(Q₃₉), or

[0241] any combination thereof.


[0242] In the present specification, Q₁ to Q₉, Q₁₁ to Q₁₉, Q₂₁ to Q₂₉, and Q₃₁ to Q₃₉ may each independently be hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; an amino group; an amidino group; a hydrazine group; a hydrazone group; a carboxylic acid group or a salt thereof; a sulfonic acid group or a salt thereof; a phosphoric acid group or a salt thereof; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₉ alkynyl group; a C₁-C₆₀ alkoxy group; a C₃-C₁₀ cycloalkyl group; a C₁-C₁₀ heterocycloalkyl group; a C₃-C₁₀ cycloalkenyl group; a C₁-C₁₀ heterocycloalkenyl group; a C₆-C₆₉ aryl group; a C₆-C₆₉ aryl group substituted with a C₁-C₆₀ alkyl group, a C₆-C₆₉ aryl group, or any combination thereof; a C₆-C₆₉ aryloxy group; a C₆-C₆₉ arylthio group; a C₇-C₆₉ arylalkyl group; a C₁-C₆₀ heteroaryl group; a C₁-C₆₀ heteroaryloxy group; a C₁-C₆₀ heteroarylthio group; a C₂-C₆₀ heteroarylalkyl group; a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

[0243] Hereinafter, a compound and an organic light-emitting device according to embodiments are described in detail with reference to Synthesis Example and Examples. However, the organic light-emitting device is not limited thereto. The wording “B was used instead of A” used in describing Synthesis Examples means that an amount of A used was identical to an amount of B used, in terms of a molar equivalent.

EXAMPLES

Synthesis Example 1: Synthesis of Compound 2

[0244]



[0245] Synthesis of Intermediate 2-L1

[0246] 1-bromo-6-(sec-butyl)isoquinoline (5.48 grams (g), 20.76 millimoles, mmol), (3,5-dimethylphenyl)boronic acid (4.67 g, 31.14 mmol), Pd(PPh₃)₄ (1.92 g, 1.66 mmol), and K₂CO₃ (7.17 g, 51.90 mmol), tetrahydrofuran (THF) (60 milliliters, mL), and distilled water (30 mL) were mixed together, and the mixed solution was stirred under reflux for 18 hours. Then, the reaction temperature was lowered to room temperature, and the reaction mixture was extracted by using methylene chloride (MC). The organic layer was dried

by using anhydrous magnesium sulfate (MgSO_4) to remove moisture, and filtered. The filtrate was decompressed, and the residue was purified by using column chromatography under conditions of EA:Hexane=1:10, thereby obtaining 5.60 g (93%) of Intermediate 2-L1.

[0247] MALDI-TOFMS (m/z): $\text{C}_{21}\text{H}_{23}\text{N}$ (M+) 289.

[0248] Synthesis of Intermediate 2-L2

[0249] Intermediate 2-L1 (5.58 g, 19.3 mmol), iridium chloride (3.02 g, 8.58 mmol), ethoxyethanol (45 mL), and distilled water (15 mL) were mixed together, and the mixed solution was stirred under reflux for 24 hours. The reaction temperature was lowered to room temperature, and a solid produced therefrom was separated by filtration. A filtrate was thoroughly washed by using water/methanol/hexane in the stated order, and a solid obtained therefrom was dried in a vacuum oven, thereby obtaining 3.9 g (57%) of Intermediate 2-L2.


[0250] Synthesis of Compound 2

[0251] Intermediate 2-L2 (1.56 g, 0.97 mmol), 3,3,7,7-tetramethylnonane-4,6-dione (2.06 g, 9.69 mmol), Na_2CO_3 (1.02 g, 9.69 mmol), and ethoxyethanol (20 mL) were mixed together, and the mixed solution was stirred for 24 hours. The mixture obtained therefrom was filtered, and the filtered solid was thoroughly washed by using ethanol and hexane, and purified by using column chromatography under conditions of dichloromethane:n-hexane=1:1 (v/v), thereby obtaining 1.40 g (74%) of Compound 2.

[0252] HRMS(MALDI) calcd for $\text{C}_{55}\text{H}_{67}\text{IrN}_2\text{O}_2$: m/z 980.37. Found: 980.39.

Synthesis Example 2: Synthesis of Compound 1

[0253]




[0254] Compound 1 (74%) was obtained in the same manner as in the synthesis of Compound 2 of Synthesis Example 1, except that 2,2,6,6-tetramethylheptane-3,5-dione (9.69 mmol) was used instead of 3,3,7,7-tetramethylnonane-4,6-dione.

[0255] HRMS(MALDI) calcd for $\text{C}_{53}\text{H}_{63}\text{IrN}_2\text{O}_2$: m/z 952.37. Found: 952.39.

Synthesis Example 3: Synthesis of Compound 3

[0256]



[0257] Compound 3 (74%) was obtained in the same manner as in the synthesis of Compound 2 of Synthesis Example 1, except that 3,7-diethyl-3,7-dimethylnonane-4,6-dione (9.69 mmol) was used instead of 3,3,7,7-tetramethylnonane-4,6-dione.

[0258] HRMS(MALDI) calcd for $\text{C}_{57}\text{H}_{71}\text{IrN}_2\text{O}_2$: m/z 1008.37. Found: 1008.39.

Evaluation Example 1: Evaluation of HOMO and LUMO Energy Levels

[0259] According to the methods shown in Table 2, HOMO and LUMO energy levels of Compounds 1 to 3 were evaluated. The results are shown in Table 3.

TABLE 2

HOMO energy level evaluation method	Cyclic voltammetry (CV) (electrolyte: 0.1M Bu ₄ NClO ₄ /solvent: CH ₂ Cl ₂ /electrode: 3-electrode system (working electrode: GC, reference electrode: Ag/AgCl, auxiliary electrode: Pt)) was used to obtain a voltage (V)-current (A) graph for each compound. Then, a HOMO energy level of each compound was calculated from a reduction onset of the graph.
LUMO energy level evaluation method	Each compound was diluted in CHCl ₃ at a concentration of 1 × 10 ⁻⁵ M, and a Shimadzu UV-350 spectrometer was used to measure UB absorption spectra at room temperature. Then, a LUMO energy level was calculated by using an optical band gap (E _g) from the edge of the UV absorption spectrum.

TABLE 3

Compound No.	HOMO (eV)	LUMO (eV)
1	-5.071	-2.410
2	-5.060	-2.401
3	-5.060	-2.401

[0260] Referring to Table 3, it was confirmed that Compounds 1 to 3 had suitable electrical characteristics for use as materials for organic light-emitting devices.

Evaluation Example 2: Evaluation of Photoluminescence Quantum Yield (PLQY)

[0261] PMMA solution in CH₂Cl₂ was mixed with 5 percent by weight (weight %) of a mixture including CBP and Compound 2 (wherein an amount of Compound 2 was 10 parts by weight of 100 parts by weight of the mixture). The resulting product was spin-coated on a quartz substrate, and the substrate was heat-treated in an oven at a temperature of 80° C., and then, cooled to room temperature, thereby preparing a film.

[0262] A PLQY in film of Compound 2 was evaluated by using a Hamamatsu Photonics absolute PL quantum yield measurement system using a xenon light source, equipped with a monochromator, a photonic multichannel analyzer, and an integrating sphere, and utilizing a PLQY measurement software (Hamamatsu Photonics, Ltd., Shizuoka, Japan). The same process was repeated with respect to Compounds 1, 3, and C, and the results are shown in Table 4.

TABLE 4

Compound No.	Compound 1	Compound 2	Compound 3	Compound C
PLQY	0.837	0.905	0.917	0.734




TABLE 4-continued

Compound No.	Compound 1	Compound 2	Compound 3	Compound C
2				
3				
C				

[0263] Referring to Table 4, it was confirmed that Compounds 1 to 3 each had a greater PLQY in film than Compound C.

Evaluation Example 3: Measurement of Decay Time

[0264] A quartz substrate washed with chloroform and pure water was prepared first, and predetermined materials shown in Table 5 were vacuum-(co)-deposited on the quartz substrate at a vacuum degree of 10⁻⁷ torr, thereby preparing Films 1 to 3, each having a thickness of 50 nm.

TABLE 5

Film No.	Compound used in film preparation
Film 1	CBP:Compound 1 (at a weight ratio of 9:1)
Film 2	CBP:Compound 2 (at a weight ratio of 9:1)
Film 3	CBP:Compound 3 (at a weight ratio of 9:1)

[0265] Subsequently, a PL spectrum of Film 1 prepared as described above was evaluated at room temperature by using FluoTime 300 which is a TRPL measurement system manufactured by PicoQuant Company and a PLS340 (excitation wavelength=340 nm, spectral width=20 nm) which is a pumping source manufactured by PicoQuant Company. Then, a wavelength of the main peak of the spectrum was determined, and the number of photons emitted at the wavelength of the main film upon a photon pulse (pulse width=500 picoseconds) applied on each film by the PLS340 was measured based on the Time-Correlated Single Photon Counting (TCSPC). This measurement was repeated to obtain a TRPL curve with sufficient fitting. Two or more exponential decay functions were fitted to the obtained results to obtain $T_{decay}(E_x)$, i.e., decay time, of Film 1, and the results are shown in Table 6. The functions used for the fitting is shown in Equation 1 below, and the greatest value among T_{decay} values obtained from each exponential decay function used in the fitting was indicates as $T_{decay}(E_x)$. Here, during the measurement time equal to the measurement time used to obtain the TRPL curve, the same measurement was repeated one more time in a dark state (i.e., a state where a pumping signal incident on the predetermined film was blocked) to obtain a baseline curve or a background signal curve to be used as a baseline for the fitting. The same process was repeated for Films 2 and 3, and the results are shown in Table 6.

$$f(t) = \sum_{i=1}^n A_i \exp(-t/T_{decay,i}) \quad \text{Equation 1}$$

TABLE 6

Film No.	Decay time (μ s)
Film 1 (Compound 1)	0.950
Film 2 (Compound 2)	0.995
Film 3 (Compound 3)	0.993

[0266] Referring to Table 6, it was confirmed that Compounds 1 to 3 each had excellent decay time.


Example 1


[0267] As an anode, a glass substrate on which ITO/Ag/ITO was formed to a thickness of 70 Å/1,000 Å/70 Å was cut to a size of 50 mm×50 mm×0.5 mm, sonicated with isopropyl alcohol and pure water each for 5 minutes, and then, cleaned by exposure to ultraviolet rays and ozone for 30 minutes. Then, the anode was provided to a vacuum deposition apparatus.

[0268] 2-TNATA was vacuum-deposited on the anode to form a hole injection layer having a thickness of 600 Å, and 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (hereinafter, referred to as NPB) was vacuum-deposited on the hole injection layer to form a hole transport layer having a thickness of 1,350 Å.

[0269] Next, CBP (as a host) and Compound 1 (as a dopant) were co-deposited at a weight ratio of 98:2 on the hole transport layer to form an emission layer having a thickness of 400 Å.

[0270] Then, BCP was vacuum-deposited on the emission layer to form a hole blocking layer having a thickness of 50 Å, and Alq₃ was vacuum-deposited on the hole blocking layer to form an electron transport layer having a thickness of 350 Å. LiF was vacuum-deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Mg and Ag were co-deposited at a weight ratio of 90:10 on the electron injection layer to form a cathode having a thickness of 120 Å, thereby completing the manufacture of an organic light-emitting device:





Examples 2 and 3 and Comparative Examples A to C

[0271] Organic light-emitting devices were manufactured in the same manner as in Example 1, except that compounds listed in Table 7 below were each used as a dopant instead of Compound 1 in forming an emission layer.

Evaluation Example 4: Evaluation of Characteristics of Organic Light-Emitting Device

[0272] The driving voltage, current density, maximum external quantum efficiency (Max EQE), roll-off ratio, emission peak wavelength of EL spectrum, FWHM of EL spectrum, emission color, color coordinates (CIE_x), and/or lifespan (T₉₇) of the organic light-emitting devices manufactured according to Examples 1 to 3 and Comparative Examples A to C were evaluated, and the results are shown in Table 7. Here, as a device used for the evaluation, a current-voltage meter (Keithley 2400) and a luminance meter (Minolta Cs-1000A) were used. The lifespan (T₉₇) (at 3,500 nit) was obtained by evaluating time (hours, hr) that lapsed when luminance was 97% of initial luminance (100%). The roll-off ratio was calculated according to Equation 20 below:

$$\text{Roll off ratio} = \left\{ 1 - \frac{\text{efficiency (at 3,500 nit)}}{\text{maximum luminance efficiency}} \right\} \times 100\% \quad \text{Equation 20}$$

TABLE 7

Compound No.	No. of dopant in emission layer	Driving voltage (V)	Current density (mA/cm ²)	Max EQE (%)	Roll-off Ratio (%)	Emission peak		Emission color	Color coordinate (CIE _x)	LT ₉₇ (hr)
						wavelength (nm)	FWHM (nm)			
Example 1	1	5.20	5.71	28.0	15	626	54	Red	0.684	252
Example 2	2	5.16	6.40	28.2	15	625	51	Red	0.677	280
Example 3	3	5.11	6.46	28.6	14	624	49	Red	0.674	306
Comparative Example A	A	5.22	8.01	24.1	19	—	60	Red	0.683	200
Comparative Example B	B	5.32	6.98	25.6	16	624	55	Red	0.675	210
Comparative Example C	C	5.42	7.11	24.1	19	634	60	Red	0.683	210








TABLE 7-continued

Compound	No. of dopant in emission layer	Driving voltage (V)	Current density (mA/cm ²)	Max EQE (%)	Roll-off Ratio (%)	Emission peak wavelength (nm)	FWHM (nm)	Emission color	Color coordinate (CIE _x)	LT ₉₇ (hr)
3										
A										
B										
C										

[0273] Referring to Table 7, it was confirmed that the organic light-emitting devices manufactured according to Examples 1 to 3 emitted red light having excellent color purity, and also had an improved driving voltage, an improved external quantum efficiency, an improved roll-off ratio, and an improved lifespan, as compared with the organic light-emitting devices manufactured according to Comparative Examples A to C.

[0274] According to the one or more embodiments, the organometallic compound has excellent electric characteristics and stability, and thus, an electronic device, for example, an organic light-emitting device, including the organometallic compound may have a low driving voltage, good external quantum efficiency, a low roll-off ratio, and a long lifespan. In addition, since the organometallic com-

pound has excellent phosphorescence characteristics, a diagnostic composition including the organometallic compound may be provided with a high diagnosis efficiency.


[0275] It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

[0276] While one or more embodiments have been described with reference to the FIGURES, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present disclosure as defined by the following claims.

What is claimed is:

1. An organometallic compound represented by Formula 1:

Formula 1



wherein, in Formula 1,

R_1 to R_{10} and A_7 are each independently hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-SF_5$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_7 - C_{60} arylalkyl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted C_2 - C_{60} heteroarylalkyl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-N(Q_1)(Q_2)$, $-Si(Q_3)(Q_4)(Q_5)$, $-Ge(Q_3)(Q_4)(Q_5)$, $-B(Q_6)(Q_7)$, $-P(=O)(Q_8)(Q_9)$, or $-P(Q_8)(Q_9)$,

each of at least one of R_1 to R_{10} is independently a substituted or unsubstituted C_2 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted

C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_7 - C_{60} arylalkyl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted C_2 - C_{60} heteroarylalkyl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-N(Q_1)(Q_2)$, $-Si(Q_3)(Q_4)(Q_5)$, $-Ge(Q_3)(Q_4)(Q_5)$, $-B(Q_6)(Q_7)$, $-P(=O)(Q_8)(Q_9)$, or $-P(Q_8)(Q_9)$,

A_1 to A_6 are each independently a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_7 - C_{60} arylalkyl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryloxy group, a substituted or unsubstituted C_1 - C_{60} heteroarylthio group, a substituted or unsubstituted C_2 - C_{60} heteroarylalkyl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, or a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

two or more of R_1 to R_{10} are optionally linked to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{1a} ,

two or more of A_1 to A_6 are optionally linked to form a C_3 - C_{60} carbocyclic group unsubstituted or substituted with at least one R_{1a} or a C_1 - C_{60} heterocyclic group unsubstituted or substituted with at least one R_{1a} ,

R_{1a} is the same as defined in connection with R_7 ,

a substituent(s) of the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_1 - C_{60} alkoxy group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_1 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_6 - C_{60} aryloxy group, the substituted C_6 - C_{60} arylthio group, the substituted C_7 - C_{60} arylalkyl group, the substituted C_1 - C_{60} heteroaryl group, the substituted C_1 - C_{60} heteroaryloxy group, the substituted C_1 - C_{60} heteroarylthio group, the substituted C_2 - C_{60} heteroarylalkyl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is each independently:

deuterium, $-F$, $-Cl$, $-Br$, $-I$, $-CD_3$, $-CD_2H$, $-CDH_2$, $-CF_3$, $-CF_2H$, $-CFH_2$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group,

- a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or a C₁-C₆₀ alkoxy group;
- a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, or C₁-C₆₀ alkoxy group, each substituted with deuterium, —F, —Br, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), —Ge(Q₁₃)(Q₁₄)(Q₁₅), —B(Q₁₆)(Q₁₇), —P(=O)(Q₁₈)(Q₁₉), —P(Q₁₈)(Q₁₉), or any combination thereof;
- a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group;
- a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group, each substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₇-C₆₀ arylalkyl group, a C₁-C₆₀ heteroaryl group, a C₁-C₆₀ heteroaryloxy group, a C₁-C₆₀ heteroarylthio group, a C₂-C₆₀ heteroarylalkyl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), —Ge(Q₂₃)(Q₂₄)(Q₂₅), —B(Q₂₆)(Q₂₇), —P(=O)(Q₂₈)(Q₂₉), —P(Q₂₈)(Q₂₉), or any combination thereof;
- N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), —Ge(Q₃₃)(Q₃₄)(Q₃₅), —B(Q₃₆)(Q₃₇), —P(=O)(Q₃₈)(Q₃₉), —P(Q₃₈)(Q₃₉), or any combination thereof; or any combination thereof, and
- Q₁ to Q₉, Q₁₁ to Q₁₉, Q₂₁ to Q₂₉, and Q₃₁ to Q₃₉ are each independently hydrogen; deuterium; —F; —Cl; —Br; —I; a hydroxyl group; a cyano group; a nitro group; an amino group; an amidino group; a hydrazine group; a hydrazone group; a carboxylic acid group or a salt thereof; a sulfonic acid group or a salt thereof; a phosphoric acid group or a salt thereof; a C₁-C₆₀ alkyl group; a C₂-C₆₀ alkenyl group; a C₂-C₆₀ alkynyl group; a C₁-C₆₀ alkoxy group; a C₃-C₁₀ cycloalkyl group; a C₁-C₁₀ heterocycloalkyl group; a C₃-C₁₀ cycloalkenyl group; a heterocycloalkenyl group; a C₆-C₆₀ aryl group; a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₆-C₆₀ aryl group or any combination thereof; a C₆-C₆₀ aryloxy group; a C₆-C₆₀ arylthio group; a C₇-C₆₀ arylalkyl group; a C₁-C₆₀ heteroaryl group; a C₁-C₆₀ heteroaryloxy group; a C₁-C₆₀ heteroarylthio group; a C₂-C₆₀ heteroarylalkyl group; a monovalent non-aromatic condensed polycyclic group; or a monovalent non-aromatic condensed heteropolycyclic group.
2. The organometallic compound of claim 1, wherein R₁ to R₁₀ and A₇ are each independently: hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, —SF₅, a C₁-C₂₀ alkyl group, or a C₁-C₂₀ alkoxy group;
- a C₁-C₂₀ alkyl group or a C₁-C₂₀ alkoxy group, each substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or a combination thereof;
- a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group,

an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranly group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranly group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group, each unsubstituted or substituted with deuterium, —F, —Br, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cycloctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranly group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranly group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, or any combination thereof;

—N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), —B(Q₆)(Q₇), or —P(=O)(Q₈)(Q₉); or

any combination thereof,

each of at least one of R₁ to R₁₀ is independently:

a C₂-C₂₀ alkyl group or a C₁-C₂₀ alkoxy group, each unsubstituted or substituted with deuterium, —F, —Cl, —Br, —I, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a

cyclohexyl group, a cycloheptyl group, a cycloctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or any combination thereof;

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cycloctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranly group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranly group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group, each unsubstituted or substituted with deuterium, —F, —Br, —CD₃, —CD₂H, —CDH₂, —CF₃, —CF₂H, —CFH₂, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cycloctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C₁-C₂₀ alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazoliny group, a cinnolinyl group, a carbazolyl

group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, or any combination thereof;

$-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{Si}(\text{Q}_3)(\text{Q}_4)(\text{Q}_5)$, $-\text{B}(\text{Q}_6)(\text{Q}_7)$, or $-\text{P}(=\text{O})(\text{Q}_8)(\text{Q}_9)$; or

any combination thereof, and

Q_1 to Q_9 are each independently:

$-\text{CH}_3$, $-\text{CD}_3$, $-\text{CD}_2\text{H}$, $-\text{CDH}_2$, $-\text{CH}_2\text{CH}_3$, $-\text{CH}_2\text{CD}_3$, $-\text{CH}_2\text{CD}_2\text{H}$, $-\text{CH}_2\text{CDH}_2$, $-\text{CHDCCH}_3$, $-\text{CHDCD}_2\text{H}$, $-\text{CHDCDH}_2$, $-\text{CHDCD}_3$, $-\text{CD}_2\text{CD}_3$, $-\text{CD}_2\text{CD}_2\text{H}$, or $-\text{CD}_2\text{CDH}_2$; or

an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, a phenyl group, a biphenyl group, or a naphthyl group, each unsubstituted or substituted with deuterium, a C_1 - C_{10} alkyl group, a phenyl group, or any combination thereof.

3. The organometallic compound of claim 1, wherein

A_1 to A_6 are each independently:


a C_1 - C_{20} alkyl group or a C_1 - C_{20} alkoxy group, each unsubstituted or substituted with deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, $-\text{CD}_3$, $-\text{CD}_2\text{H}$, $-\text{CDH}_2$, $-\text{CF}_3$, $-\text{CF}_2\text{H}$, $-\text{CFH}_2$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C_1 - C_{20} alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, or any combination thereof; or

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C_1 - C_{20} alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, or any combination thereof.

group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group, each unsubstituted or substituted with deuterium, $-\text{F}$, $-\text{Br}$, $-\text{CD}_3$, $-\text{CD}_2\text{H}$, $-\text{CDH}_2$, $-\text{CF}_3$, $-\text{CF}_2\text{H}$, $-\text{CFH}_2$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, a bicyclo[2.2.2]octyl group, a phenyl group, a (C_1 - C_{20} alkyl)phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, or any combination thereof.

4. The organometallic compound of claim 1, wherein

each of at least one of R_1 to R_{10} is independently a group represented by Formula 2:



Formula 2

wherein, the number of carbon atoms in Formula 2 is 4 or more,

R_{13} in Formula 2 is hydrogen, deuterium, a C_1 - C_{20} alkyl group, deuterium-containing C_1 - C_{20} alkyl group, a C_3 - C_{10} cycloalkyl group, or a deuterium-containing C_3 - C_{10} cycloalkyl group,

R_{14} and R_{15} in Formula 2 are each independently a C_1 - C_{20} alkyl group, a deuterium-containing C_1 - C_{20} alkyl

group, a C₃-C₁₀ cycloalkyl group, or a deuterium-containing C₃-C₁₀ cycloalkyl group, and

* indicates a binding site to a neighboring atom.

5. The organometallic compound of claim 4, wherein R_{1,3} in Formula 2 is hydrogen or deuterium.

6. The organometallic compound of claim 4, wherein R_{1,4} and R_{1,5} in Formula 2 are different from each other.

7. The organometallic compound of claim 4, wherein in Formula 2,

R_{1,3} is hydrogen, deuterium, —CH₃, —CDH₂, —CD₂H, or —CD₃,

R_{1,4} and R_{1,5} are each independently:

a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isohexyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, or a bicyclo[2.2.2]octyl group; or

a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, a sec-butyl group, an isobutyl group, a tert-butyl group, an n-pentyl group, a tert-pentyl group, a neopentyl group, an isopentyl group, a sec-pentyl group, a 3-pentyl group, a sec-isopentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isohexyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decyl group, an isodecyl group, a sec-decyl group, a tert-decyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a bicyclo[1.1.1]pentyl group, a bicyclo[2.1.1]hexyl group, a bicyclo[2.2.1]heptyl group, or a bicyclo[2.2.2]octyl group, each substituted with at least one deuterium.

8. The organometallic compound of claim 4, wherein R₄ in Formula 1 is a group represented by Formula 2.

9. The organometallic compound of claim 1, wherein R₄, R₇, and R₉ in Formula 1 are each not hydrogen.

10. The organometallic compound of claim 1, wherein R₇ and R₉ in Formula 1 are each not hydrogen and identical to each other.


11. The organometallic compound of claim 1, wherein each of at least one of A₁ to A₆ is independently a substituted or unsubstituted C₂-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted heterocycloalkenyl



group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₇-C₆₀ arylalkyl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryloxy group, a substituted or unsubstituted C₁-C₆₀ heteroarylthio group, a substituted or unsubstituted C₂-C₆₀ heteroarylalkyl group, a substituted or unsubstituted mono-valent non-aromatic condensed polycyclic group, or a substituted or unsubstituted mono-valent non-aromatic condensed heteropolycyclic group.

12. The organometallic compound of claim 1, wherein A₇ is not hydrogen.

13. The organometallic compound of claim 1, wherein in Formula 1, each of at least one of a group represented by *—C(A₁)(A₂)(A₃) and a group represented by *(A₄)(A₅)(A₆) is independently a cyclopentane group, a cyclohexane group, a cycloheptane group, a cyclooctane group, an adamantane group, a norbornane group, a norbornene group, a cyclopentene group, a cyclohexene group, a cycloheptene group, a bicyclo[1.1.1]pentane group, a bicyclo[2.1.1]hexane group, a bicyclo[2.2.1]heptane group, a bicyclo[2.2.2]octane group, a benzene group, a naphthalene group, a fluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an isoindole group, an indole group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a cinnoline group, a carbazole group, a phenanthroline group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a tetrazine group, a dibenzofuran group, a dibenzothiophene group, a benzocarbazole group, a dibenzocarbazole group, an imidazopyridine group, or an imidazopyrimidine group, each unsubstituted or substituted with at least one R_{1,a}.

14. The organometallic compound of claim 1, wherein the organometallic compound is one of Compounds 1 to 6:





- 15.** An organic light-emitting device comprising:
 a first electrode;
 a second electrode; and
 an organic layer disposed between the first electrode and the second electrode and comprising an emission layer, wherein the organic layer comprises at least one organometallic compound of claim 1.
- 16.** The organic light-emitting device of claim 15, wherein the first electrode is an anode, the second electrode is a cathode, the organic layer further comprises a hole transport disposed between the first electrode and the emission layer and an electron transport region disposed between the emission layer and the second electrode, the hole transport region comprises a hole injection layer, a hole transport layer, an electron blocking layer, a buffer layer, or any combination thereof, and the electron transport region comprises a hole blocking layer, an electron transport layer, an electron injection layer, or any combination thereof.
- 17.** The organic light-emitting device of claim 15, wherein the emission layer comprises the at least one organometallic compound.
- 18.** The organic light-emitting device of claim 17, wherein the emission layer emits red light.
- 19.** The organic light-emitting device of claim 17, wherein the emission layer further comprises a host, and an amount of the host in the emission layer is greater than that of the organometallic compound in the emission layer.
- 20.** A diagnostic composition comprising at least one organometallic compound of claim 1.

* * * * *

专利名称(译)	有机金属化合物，包括该有机金属化合物的有机发光器件以及包括该有机金属化合物的诊断组合物		
公开(公告)号	US20200044166A1	公开(公告)日	2020-02-06
申请号	US16/527093	申请日	2019-07-31
[标]申请(专利权)人(译)	三星电子株式会社		
申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD.		
当前申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD.		
[标]发明人	CHO YONGSUK KWAK YOONHYUN CHOI JONGWON KOO HYUN IM KYUHYUN KRAVCHUK DMITRY HONG SEOKHWAN		
发明人	CHO, YONGSUK KWAK, YOONHYUN CHOI, JONGWON KOO, HYUN IM, KYUHYUN KRAVCHUK, DMITRY HONG, SEOKHWAN		
IPC分类号	H01L51/00 C07F15/00 C09K11/06		
CPC分类号	C09K2211/1029 H01L51/5056 C09K11/06 H01L51/5092 H01L2251/552 C09K2211/185 H01L51/5016 H01L51/5096 H01L51/5072 H01L51/0085 H01L51/5012 H01L51/5088 C07F15/0033 A61P35/00		
优先权	1020180089511 2018-07-31 KR 1020190091699 2019-07-29 KR		
外部链接	Espacenet USPTO		

摘要(译)

式1表示的有机金属化合物：其中，式1，R1至R10和A1至A7与在说明书的详细描述中描述的相同。

