



US009741969B2

(12) **United States Patent**
Cheng et al.

(10) **Patent No.:** **US 9,741,969 B2**
(45) **Date of Patent:** **Aug. 22, 2017**

(54) **CARRIER GENERATION MATERIAL AND ORGANIC LIGHT-EMITTING DIODE**

(71) Applicant: **NATIONAL TSING HUA UNIVERSITY**, Hsinchu (TW)

(72) Inventors: **Chien-Hong Cheng**, Hsin-Chu (TW);
Wei-Ting Hsieh, Hsinchu (TW);
Chen-Hsun Hung, Hsinchu (TW);
Min-Jie Huang, Hsinchu (TW);
Cheng-Chang Lai, Hsinchu (TW);
Chuang-Yi Liao, Hsinchu (TW)

(73) Assignee: **National Tsing Hua University**, Hsinchu (TW)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 150 days.

(21) Appl. No.: **14/860,559**

(22) Filed: **Sep. 21, 2015**

(65) **Prior Publication Data**

US 2017/0062771 A1 Mar. 2, 2017

(30) **Foreign Application Priority Data**

Aug. 24, 2015 (TW) 104127446 A

(51) **Int. Cl.**

H01L 51/54 (2006.01)

H01L 51/52 (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC **H01L 51/5278** (2013.01); **C07D 241/42** (2013.01); **C07D 241/44** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC H01L 51/0032; H01L 51/005; H01L 51/0072; H01L 51/0071; H01L 51/50;

(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

495,625 A 4/1893 Cotton
4,446,217 A 5/1984 Takasu et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CN 1347572 A 5/2002
CN 1376758 A 10/2002

(Continued)

OTHER PUBLICATIONS




Smith et al. J. Am. Chem. Soc. 1939, 61, 2619-2624. Year of publication: 1939.*

(Continued)

Primary Examiner — Andrew K Bohaty

(57) **ABSTRACT**

A carrier generation material is provided, which has a chemical structure of:



wherein R¹ is hydrogen or alkyl group; each of R² is independently hydrogen, halogen, —CN, —CF₃, —NO₂, or alkyl group; each of R³ is independently hydrogen, halogen, —CN, —CF₃, —NO₂, or alkyl group; R⁴ is hydrogen, halogen, —CN, —CF₃, —NO₂, or alkyl group; R⁵ is hydrogen, halogen, —CN, —CF₃, —NO₂, or alkyl group; R⁶ is =O, =NH, or malononitrile group, and R⁷ is hydrogen, halogen, —CN, —CF₃, —NO₂, or alkyl group.

4 Claims, 1 Drawing Sheet

- (51) **Int. Cl.**
C07D 241/46 (2006.01)
C07D 241/44 (2006.01)
C07D 487/04 (2006.01)
C07D 241/42 (2006.01)
H01L 51/00 (2006.01)
- (52) **U.S. Cl.**
CPC **C07D 241/46** (2013.01); **C07D 487/04** (2013.01); **H01L 51/0072** (2013.01)
- (58) **Field of Classification Search**
CPC . H01L 51/5278; C07D 241/42; C07D 241/44; C07D 241/46; C07D 487/00; C07D 487/02; C07D 487/04; C07D 487/10
USPC 428/690, 691, 411.4, 336, 917; 427/58, 427/66; 313/500–512; 257/40, 88–104, 257/E51.001–E51.052; 252/301.16–301.35
- 2007/0222374 A1 9/2007 Egawa et al.
2007/0228938 A1 * 10/2007 Hatwar H01L 27/3213 313/504
2008/0079354 A1 4/2008 Egawa et al.
2008/0091012 A1 4/2008 Egawa et al.
2008/0193797 A1 8/2008 Heil et al.
2011/0180791 A1 7/2011 Pan et al.
2011/0284835 A1 11/2011 Osaka et al.
2011/0297925 A1 12/2011 Breuning
2012/0097899 A1 4/2012 Parham et al.
2012/0243909 A1 9/2012 Tomari et al.
2012/0256172 A1 * 10/2012 Ito C07D 493/04 257/40
2012/0302751 A1 11/2012 Nomura et al.
2012/0313506 A1 12/2012 Egawa et al.
2013/0049577 A1 2/2013 Kadoma et al.
2013/0053558 A1 2/2013 Pflumm et al.
2013/0306959 A1 11/2013 Ikeda et al.
2014/0001451 A1 1/2014 Mizuki et al.
2014/0228566 A1 8/2014 Egawa et al.

See application file for complete search history.

FOREIGN PATENT DOCUMENTS

(56) **References Cited**

U.S. PATENT DOCUMENTS


- 5,077,142 A * 12/1991 Sakon C09K 11/06 313/504
5,248,579 A 9/1993 Terrell et al.
5,306,587 A 4/1994 Terrell et al.
5,585,213 A 12/1996 Tamano et al.
7,875,879 B2 1/2011 Suzuki et al.
7,911,135 B2 3/2011 Sakata et al.
7,927,720 B2 4/2011 Nomura et al.
7,931,974 B2 4/2011 Egawa et al.
7,951,470 B2 5/2011 Tokuda et al.
7,993,761 B2 8/2011 Osaka et al.
8,008,489 B2 8/2011 Egawa et al.
8,119,259 B2 2/2012 Kadoma et al.
8,178,216 B2 5/2012 Nomura et al.
8,203,262 B2 6/2012 Seo et al.
8,216,696 B2 7/2012 Kawakami et al.
8,252,433 B2 8/2012 Egawa et al.
8,313,845 B2 11/2012 Nomura et al.
8,314,101 B2 11/2012 Kadoma et al.
8,362,472 B2 1/2013 Suzuki et al.
8,471,017 B2 6/2013 Egawa et al.
8,507,901 B2 8/2013 Pan
8,703,305 B2 4/2014 Egawa et al.
8,815,412 B2 8/2014 Kadoma et al.
8,927,117 B2 1/2015 Buesing et al.
2005/0089789 A1 4/2005 Zhu

- CN 1487937 A 4/2004
CN 1554726 A 12/2004
CN 1585152 A 2/2005
CN 1634927 A 7/2005
CN 1725455 A 1/2006
CN 1828963 A 9/2006
CN 102150086 A 8/2011
CN 102762630 A 10/2012
CN 103403906 A 11/2013
CN 104205391 A 12/2014
JP 09003342 A * 1/1997
TW 200526759 8/2005
TW 200824498 6/2008
TW 201144313 12/2011
TW 201244211 11/2012
TW 201315729 4/2013
TW 201345896 11/2013
TW 1425074 2/2014
TW 1435889 5/2014
TW 201428083 7/2014
TW 1461506 11/2014

OTHER PUBLICATIONS

Machine translation of JP09-003342. Date of publication: Jan. 7, 1997.*

* cited by examiner



1

CARRIER GENERATION MATERIAL AND ORGANIC LIGHT-EMITTING DIODE

CROSS REFERENCE TO RELATED APPLICATIONS

This Application claims priority of Taiwan Patent Application No. 104127446, filed on Aug. 24, 2015, the entirety of which is incorporated by reference herein.

BACKGROUND

Technical Field

The disclosure relates to an organic light-emitting diode, and in particular it relates to the composition of a carrier generation layer thereof.

Description of the Related Art

Compared to inorganic compounds, organic compounds are more varied in terms of their material system. Organic materials with any function can be synthesized through the appropriate molecular designs. The films of organic compounds have extremely high flexibility and excellent processability. In recent years, functional organic materials with the above advantages have attracted attention among those in the photonics and electronics industries.

Because organic compounds are inherently free of carriers, they normally have excellent insulative properties. In the electronics field, these organic compounds generally served as insulators, being used in insulation materials, protection materials, encapsulation materials, etc. However, a mechanism wherein a large current flows through organic materials was initially developed in the electronics field. For example, organic films with a total thickness of about 100 nm can be disposed between electrodes. Organic hole transport layers and organic electron transport layers are stacked to constitute a stack of the organic films, and a light-emitting material (phosphorescent material) may serve as an electron-hole combination layer in the stack. By applying a voltage to a device, the electrons and holes can be combined in the light-emitting layer to emit light. As such, the device is a so-called organic light-emitting diode (OLED).

Some related art provides the concept of a carrier generation layer to improve the luminescent efficiency of the OLED, in which an anode, a first electroluminescent layer, a carrier generation layer, a second electroluminescent layer, and a cathode are sequentially stacked. Note that the electroluminescent layer (EL layer) means an organic compound layer, and it may emit light by injecting carriers. In addition, the carrier generation layer is a floating electrode without a connection to an outer circuit.

When a voltage V is applied through the anode and the cathode of the OLED, the carrier generation layer may produce electrons and holes, wherein the electrons are injected into the first EL layer and the holes are injected into the second EL layer. Compared to an OLED with only one EL layer, the OLED with two EL layers may emit double the amount of luminescence using the same current (but using double or higher voltage).


The OLED with the carrier generation layer may enhance the current efficiency and lower the current density several-fold by stacking a plurality of EL layers. Theoretically, the device lifetime should be elongated by the enhanced current efficiency due to lowered current density. However, the selection of the carrier generation material is rare, due to late development. Accordingly, a novel carrier generation material

2

is called for to increase the enablement of the carrier generation material in the OLED.

BRIEF SUMMARY

One embodiment of the disclosure provides a carrier generation material, having a chemical structure of:



wherein R^1 is hydrogen or alkyl group; each of R^2 is independently hydrogen, halogen, $-\text{CN}$, $-\text{CF}_3$, $-\text{NO}_2$, or alkyl group; each of R^3 is independently hydrogen, halogen, $-\text{CN}$, $-\text{CF}_3$, $-\text{NO}_2$, or alkyl group; R^4 is hydrogen, halogen, $-\text{CN}$, $-\text{CF}_3$, $-\text{NO}_2$, or alkyl group; R^5 is hydrogen, halogen, $-\text{CN}$, $-\text{CF}_3$, $-\text{NO}_2$, or alkyl group; R^6 is $=\text{O}$, $=\text{NH}$, or malononitrile group; and R^7 is hydrogen, halogen, $-\text{CN}$, $-\text{CF}_3$, $-\text{NO}_2$, or alkyl group.

3

One embodiment of the disclosure provides an organic light-emitting diode, comprising: an anode; a cathode; a carrier generation material layer, including the described carrier generation material, disposed between the anode and the cathode; a first light-emitting layer disposed between the anode and the carrier generation material layer; and a second light-emitting layer, disposed between the cathode and the carrier generation material layer.

A detailed description is given in the following embodiments with reference to the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS


The disclosure can be more fully understood by reading the subsequent detailed description and examples with references made to the accompanying drawings, wherein:

The FIGURE shows an organic light-emitting diode in one embodiment of the disclosure.

DETAILED DESCRIPTION


The following description is of the best-contemplated mode of carrying out the disclosure. This description is made for the purpose of illustrating the general principles of the disclosure and should not be taken in a limiting sense. The scope of the disclosure is best determined by reference to the appended claims.

In one embodiment, a carrier generation material has a chemical structure of Formula 1. In Formula 1, R^1 is hydrogen or alkyl group. Each of R^2 is independently hydrogen, halogen, $-\text{CN}$, $-\text{CF}_3$, $-\text{NO}_2$, or alkyl group. Each of R^3 is independently hydrogen, halogen, $-\text{CN}$, $-\text{CF}_3$, $-\text{NO}_2$, or alkyl group.




(Formula 1)

The carrier generation material of Formula 1 can be synthesized as described below. First, a compound should be pre-synthesized as shown in Formula 2. In Formula 2, R^1 can be varied by selecting commercially available raw materials or processing general chemical reactions, and the related description is omitted here for simplifying the description.




(Formula 2)

4




Subsequently, the product in Formula 2 is reacted with an alkyne compound, as shown in Formula 3. In Formula 3, R^2 can be varied by selecting commercially available raw materials or processing general chemical reactions, and the related description is omitted here for simplifying the description.

(Formula 3)




The product in Formula 3 is then reacted with a diamine compound to form a compound of Formula 1, as shown in Formula 4. In Formula 4, R^3 can be varied by selecting commercially available raw materials or processing general chemical reactions, and the related description is omitted here for simplifying the description.

(Formula 4)



5

-continued




5

10

15

In one embodiment, the carrier generation material has a chemical structure of Formula 5. In Formula 5, R^1 is hydrogen or alkyl group. Each of R^2 is independently hydrogen, halogen, $-\text{CN}$, $-\text{CF}_3$, $-\text{NO}_2$, or alkyl group. R^3 is hydrogen, halogen, $-\text{CN}$, $-\text{CF}_3$, $-\text{NO}_2$, or alkyl group.


(Formula 5)



25

The carrier generation material of Formula 5 can be synthesized as below. The product in Formula 3 is reacted with a diamine compound to form the compound of Formula 5, as shown in Formula 6. In Formula 6, R^4 can be varied by selecting commercially available raw materials or processing general chemical reactions, and the related description is omitted here for simplifying the description.

(Formula 6)



40

45

50


55

60

65


6

-continued



In one embodiment, the carrier generation material has a chemical structure of Formula 7. In Formula 7, R^5 is hydrogen, halogen, $-\text{CN}$, $-\text{CF}_3$, $-\text{NO}_2$, or alkyl group.

(Formula 7)



The carrier generation material of Formula 7 can be synthesized as below. An ethanedione compound and a tetramine compound are reacted to form the product of Formula 7, as shown in Formula 7. In Formula 8, R^5 can be varied by selecting commercially available raw materials or processing general chemical reactions, and the related description is omitted here for simplifying the description.


(Formula 8)

50

55

60


65




sodium acetate
n-butanol, 120° C.

7




-continued



In one embodiment, the carrier generation material has a chemical structure of Formula 9. In Formula 9, R^6 is $=O$, $=NH$, or malononitrile group. R^7 is hydrogen, halogen, $-CN$, $-CF_3$, $-NO_2$, or alkyl group.






The carrier generation material of Formula 9 can be synthesized as below. First, 2,3-dichloro-1,4-naphthoquinone is reacted with phthalimide salt, as shown in Formula 10.






Subsequently, the product in Formula 10 is reacted with hydrazine monohydrate, as shown in Formula 11.

8

(Formula 11)




Subsequently, the product in Formula 11 is reacted with an ethanedione compound amine compound, as shown in Formula 12. In Formula 12, R^7 can be varied by selecting commercially available raw materials or processing general chemical reactions, and the related description is omitted here for simplifying the description.



Alternatively, the product in Formula 12 can be reacted with malononitrile, as shown in Formula 13. Both of the products in Formulae 12 and 13 belong to the compound of Formula 9, and the difference therebetween is R^6 being $=O$ or malononitrile group.

9



The above carrier generation materials can be applied in OLEDs. As shown in the FIGURE, the OLED **100** may include an anode **11**, a cathode **19**, and a carrier generation material layer **15** disposed therebetween. The OLED **100** also includes a first light-emitting layer **13** disposed between the anode **11** and the carrier generation material layer **15**, and a second light-emitting layer **17** disposed between the cathode **19** and the carrier generation material layer **15**.

In one embodiment, the anode **11** has a thickness of about 15 nm. The anode **11** can be a transparent conductive material such as indium tin oxide (ITO), indium zinc oxide (IZO), aluminum zinc oxide (AZO), cadmium tin oxide (CTO), tin oxide (SnO₂), zinc oxide (ZnO), or the like. The cathode **19** may have a thickness of 75 nm to 100 nm. The cathode can be composed of composition of magnesium aluminum alloy, magnesium silver alloy, magnesium indium alloy, aluminum lithium alloy, or aluminum. The first light-emitting layer **13** may have a thickness of 120 nm to 140 nm. The first light-emitting layer can be composed of N,N'-diphenyl-1-naphthaleny-1,1'-biphenyl-4,4'-diamine, 4,4',4''-Tris(carbazol-9-yl)-triphenylamine, 9,9-(1,3-phenylene)bis-9H-carbazole, tris(2-phenylpyridine)iridium, tris[1-phenylisoquinoline-C2,N]iridium(III) (Ir(piq)3), bis[2-(4,6-difluorophenyl)pyridinato-C2,N](picolinato)iridium(III), 1,3,5-tris(1-phenyl-1H-benzimidazol-2-yl)benzene, 3,3'-[3-(3-Pyridinyl)phenyl][1,1':3',1''-terphenyl]-3,3'-diyl] bispyridine, co-evaporated lithium fluoride and electron transport layer, or aluminum. The second light-emitting layer **17** may have a thickness of 120 nm to 140 nm. The second light-emitting layer can be composed of N,N'-diphenyl-1-naphthaleny-1,1'-biphenyl-4,4'-diamine, 4,4',4''-Tris(carbazol-9-yl)-triphenylamine, 9,9-(1,3-phenylene)bis-9H-carbazole, tris(2-phenylpyridine)iridium, Ir(piq)3, bis[2-(4,6-difluorophenyl)pyridinato-C2,N](picolinato)iridium(III), 1,3,5-tris(1-phenyl-1H-benzimidazol-2-yl)benzene, or 3,3'-[3-(3-Pyridinyl)phenyl][1,1':3',1''-terphenyl]-3,3'-diyl] bispyridine. The carrier generation material layer **15** may have a thickness of 1 nm to 5 nm. The carrier generation material layer **15** can be composed of the compound of Formula 1, Formula 5, Formula 7, or Formula 9.

10

The OLED **100** may further include other common layered materials such as an electron injection layer, a hole injection layer, an electron transport layer, a hole transport layer, a hole block layer, other functional layer, or a combination thereof if necessary. Alternatively, the OLED **100** may include a plurality of carrier generation layer, and the number of the light-emitting layers is the number of the carrier generation layer add one (+1), wherein at least one of the carrier generation layer is composed of the compound of Formula 1, Formula 5, Formula 7, or Formula 9.


Below, exemplary embodiments will be described in detail with reference to the accompanying drawings so as to be easily realized by a person having ordinary knowledge in the art. The inventive concept may be embodied in various forms without being limited to the exemplary embodiments set forth herein. Descriptions of well-known parts are omitted for clarity, and like reference numerals refer to like elements throughout.

EXAMPLES

Example 1

SeO₂ (8 g, 72 mmol) and water (1 g, 55 mol) were put into a two neck bottle (100 mL). 40 mL of 1,4-dioxane was then added into the bottle, and the mixture was heated to reflux for dissolving the SeO₂. 4-methylacetophenon (5.37 g, 40 mmol, and commercially available from Alfa Aesar) was then added into the bottle to react for 6 hours. The reaction result was filtered and washed by ethyl acetate to collect filtrate, and the organic solvent of the filtrate was removed by a rotary evaporator. The concentrated substance was re-crystallized by hot water to obtain 5.88 g of white solid (yield=88%). For details relating to the above reaction, refer to P. Wang, W.-J. Tao, X.-L. Sun, S. Liao, Y. Tang, *J. Am. Chem. Soc.*, 2013, 135, 16849-16852. The above reaction is shown in Formula 14. The spectra of the product in Formula 14 are listed below: ¹H NMR (400 MHz, CDCl₃): δ 9.65 (s, 1H), 8.09 (d, J=8.4 Hz, 2H), 7.31 (d, J=8.0 Hz, 2H), 2.43 (s, 3H).

(Formula 14)




The product in Formula 14 (33.3 mg, 0.2 mmol), diphenylacetylene (42.8 mg, 0.24 mmol), and molecular sieves were put in a high-pressure tube. 0.5 mL of 1,2-dichloro ethane was added into the tube. Iron trichloride (97.4 mg, 0.6 mmol) was added into and dissolved by 1.5 mL of 1,2-dichloro ethane under nitrogen, and then added into the tube. The tube was vacuumed and purged by nitrogen, and the mixture in the tube was then reacted at room temperature for 1 hour. The reaction result was neutralized by 1 mL of water, and then filtered and washed by ethyl acetate to collect

11

filtrate. The organic solvent of the filtrate was removed by a rotary evaporator. The concentrated substance was purified by chromatography with an eluent of ethyl acetate and n-hexane (v/v=1/4), thereby obtaining 39 mg of a red solid (yield=60%). The above reaction is shown in Formula 15. The spectra of the product in Formula 15 are listed below: ¹H NMR (400 MHz, CDCl₃): δ 8.00 (s, 1H), 7.30-7.24 (m, 4H), 7.12-7.06 (m, 5H), 6.95-6.89 (m, 3H), 2.40 (s, 3H); ¹³C NMR (100 MHz, CDCl₃): δ 180.6 (CO), 179.3 (CO), 152.9 (C), 140.9 (C), 137.5 (C), 135.9 (CH), 135.7 (C), 134.1 (C), 133.5 (C), 130.9 (C), 130.8 (CH), 130.3 (2 CH), 130.2 (CH), 129.0 (2 CH), 128.1 (2 CH), 128.1 (CH), 127.4 (2 CH), 127.2 (CH), 21.0 (CH₃).

(Formula 15)




Example 2

The product of Formula 15 (324.4 mg, 1 mmol) and o-phenylenediamine (108.2 mg, 1 mmol) were put in a round-bottom bottle (100 mL). 40 mL toluene was then added into the bottle, and a Dean-Stark device was set on the bottle. The mixture in the bottle was refluxed and reacted under nitrogen. The organic solvent of the reaction result was removed by rotary evaporator, and the concentrated substance was dissolved by a small amount of ethyl acetate. The ethyl acetate solution was mixed with n-hexane for re-crystallization, thereby obtaining 361 mg of a pale yellow solid (yield=91%). The above reaction is shown in Formula 16. The spectra of the product in Formula 16 are listed below: ¹H NMR (400 MHz, CDCl₃): δ 9.38 (s, 1H), 8.38 (d, J=8.4 Hz, 1H), 8.13 (d, J=8.4 Hz, 1H), 7.83 (t, J=8.4 Hz, 1H), 7.75 (t, J=8.4 Hz, 1H), 7.52-7.47 (m, 2H), 7.33-7.22 (m, 10H), 2.70 (s, 3H); ¹³C NMR (100 MHz, CDCl₃): δ 143.4 (C), 142.7 (2C), 141.8 (C), 141.3 (C), 138.6 (C), 137.7 (C), 137.7 (C), 136.4 (C), 131.7 (2 CH), 131.5 (C), 131.0 (CH), 130.8 (C), 130.7 (2 CH), 130.0 (CH), 129.7 (CH), 129.3 (CH), 129.2 (CH), 127.7 (2 CH), 127.7 (CH), 127.0 (2 CH), 126.9 (CH), 126.3 (CH), 125.1 (CH), 21.7 (CH₃).

12

(Formula 16)



The product in Formula 16 was dissolved in dichloromethane to prepare a solution with a concentration of 10⁻⁵M. The UV absorption spectrum and the photoluminescence spectrum of the solution were measured, and the cross value of the spectra was divided 1241 to obtain the E_g of the product in Formula 16 (2.7 eV).


The ultraviolet photoelectron spectrum (UPS) of the product in Formula 16 was measured to obtain the HOMO value of the product in Formula 16 (-7.5 eV). For details concerning the method of calculating the HOMO value from the UPS, refer to *Adv. Funct. Mater.*, 2012, 22, 600-608 and *J. Mater. Chem. C*, 2014, 2, 1982-1989. The LUMO value (-4.8 eV) can be obtained by subtracting the E_g from the HOMO value.

Example 3


4,4'-dibromobenzil (2 g, 5.4 mmol, and commercially available from Alfa Aesar) was put in a high-pressure tube. Copper (I) cyanide (1.07 g, 12 mmol) was then added into the tube. The tube was then vacuumed and introduced by nitrogen. 30 mL of DMF was then added into the tube, and the mixture in the tube was heated to 160° C. and stirred for 20 hours. The reaction result was extracted by supersaturated saline and ethyl ether to collect an organic phase. The organic phase was dehydrated by magnesium sulfate, and then concentrated by a rotary evaporator. The concentrated substance was purified by chromatography with an eluent of dichloromethane and n-hexane (v/v=5/1), thereby obtaining 0.8 g of a yellow solid (yield=40%). The above reaction is shown in Formula 17. The spectra of the product in Formula

13

17 are listed below: ^1H NMR (400 MHz, CDCl_3): δ 8.09 (d, $J=8$ Hz, 4H), 7.83 (d, $J=8$ Hz, 4H). ^{13}C NMR (100 MHz, CDCl_3 , δ): 190.8, 135.3, 132.9, 130.4, 118.4, 117.4.



1,2,4,5-Benzenetetramine tetrahydrochloride (0.5 g, 1.76 mmol, and commercially available from Alfa Aesar) and the product in Formula 17 (1 g, 3.85 mmol) were put into a reaction bottle. Sodium acetate (0.576 g, 7.02 mmol) and n-butanol (50 mL) were added into the bottle. The mixture in the bottle was heated to 120°C to react for 20 hours. A yellow precipitate was formed in a solution of the reaction result, and the yellow precipitate was then collected by filtering. The filtered cake was washed by n-hexane and ethyl ether, and then purified by thermal sublimation to obtain 0.8 g of a bright yellow powder (yield=25%). The above reaction is shown in Formula 18. The spectra of the product in Formula 18 are listed below: ^1H NMR (400 MHz, CDCl_3): δ 9.08 (s, 2H), 7.72 (s, 16H). HRMS (EI, m/z): calcd. for $\text{C}_{38}\text{H}_{18}\text{N}_8$: 586.1654, Found: 586.1649 (M^+).




The product in Formula 18 had an E_g of 2.8 eV, a HOMO value of -7.2 eV, and a LUMO value of -4.4 eV, which were

14

measured and calculated by methods that were similar to those of Example 2.


Example 4

2,3-Dichloro-1,4-naphthoquinone (4.54 g, 20 mmol, and commercially available from Alfa Aesar) and potassium phthalimide (15.54 g, 84 mmol) were put in a reaction bottle. 100 mL of acetonitrile was then added into the bottle, and the mixture in the bottle was heated to 85 to react for 3 hours. A yellow precipitate was formed in a solution of the reaction result, and the yellow precipitate was then collected by filtering. The filtered cake was washed by water and methanol to obtain yellow powder (yield=97%). The above reaction is shown in Formula 19. The spectra of the product in Formula 19 are listed below: ^1H NMR (400 MHz, CDCl_3): δ 8.21 (m, 2H), 7.86 (m, 4H), 7.83 (m, 2H), 7.75 (m, 4H).





The product in Formula 19 (2.24 g, 5 mmol) was put in a reaction bottle. 20 mL of hydrazine hydrate and 150 mL of water were added into the reaction bottle, and the mixture in the bottle was heated to 70°C to react for 3 hours. A purple precipitate was formed in a solution of the reaction result, and the purple precipitate was then collected by filtering. The filtered cake was washed by water and ethyl ether to obtain purple solid (yield=70%). The above reaction is shown in Formula 20. The spectra of the product in Formula 20 are listed below: ^1H NMR (400 MHz, CDCl_3): δ 8.21 (m, 2H), 7.86 (m, 4H), 7.83 (m, 2H), 7.75 (m, 4H).


15



(Formula 20)




The product in Formula 20 (0.1 g, 0.5 mmol) and the product in Formula 17 (0.138 g, 0.53 mmol) were put in a high-pressure tube. Acetic acid was added into the bottle, and the mixture in the bottle was heated to 75° C. to react for 20 hours. A yellow precipitate was formed in a solution of the reaction result, and the yellow precipitate was then collected by filtering. The filtered cake was washed by water and ethyl ether, and then purified by thermal sublimation to obtain 0.15 g of yellow powder (yield=35%). The above reaction is shown in Formula 21. The spectra of the product in Formula 21 are listed below: ¹H NMR (400 MHz, CDCl₃): δ 8.45 (m, 2H), 7.93 (m, 2H), 7.71 (dd, J=8.4, 18 Hz, 8H). ¹³C NMR (100 MHz, CDCl₃, δ): 180.5, 154.9, 142.7, 140.5, 135.4, 133.1, 132.6, 130.7, 128.1, 117.8, 114.4. HRMS (EL m/z): cald. for C₂₆H₁₂N₄O₂: 412.0960, found: 412.0961 (M⁺).




+

acetic acid



16

-continued




The product in Formula 21 had an Eg of 3.4 eV, a HOMO value of -7.5 eV, and a LUMO value of -4.1 eV, which were measured and calculated by methods that were similar to those of Example 2.

Example 5

The product in Formula 21 (0.15 g, 0.24 mmol) was put into a reaction bottle. The bottle was vacuumed and purged by nitrogen. Anhydrous dichloromethane (5 mL) and malonitrile (0.063 mL) were then added into the bottle. Anhydrous titanium tetrachloride (0.22 mL) was then added into the bottle in ice bath, and anhydrous pyridine (0.66 mL) was then slowly injected into the bottle. The mixture in the bottle was then stirred for 15 minutes and the ice bath was removed. The mixture was then left at room temperature to react at room temperature for 24 hours. The reaction result was neutralized by dilute hydrochloric acid, and the neutralized substance was extracted by dichloromethane to collect an organic phase. The organic phase was dehydrated by magnesium sulfate and then concentrated by a rotary evaporator. The concentrated substance was purified by chromatography with an eluent of dichloromethane, thereby obtaining a yellow solid. The yellow solid was further purified by thermal sublimation to obtain 0.035 g of dark green powder (yield=24.3%). The above reaction is shown in Formula 22. The spectra of the product in Formula 22 are listed below: ¹H NMR (400 MHz, CDCl₃): δ 8.57 (m, 2H), 7.88 (m, 2H), 7.76 (dd, J=8.8, 42 Hz, 8H). HRMS (EI, m/z): cald. for C₃₂H₁₂N₈: 508.1185, found: 508.1187 (M⁺).

(Formula 22)

(Formula 21)




17

The product in Formula 22 had an E_g of 3.0 eV, a HOMO value of -7.2 eV, and a LUMO value of -4.2 eV, which were measured and calculated by methods that were similar to those of Example 2.

While the disclosure has been described by way of example and in terms of the preferred embodiments, it is to be understood that the disclosure is not limited to the disclosed embodiments. On the contrary, it is intended to cover various modifications and similar arrangements (as would be apparent to those skilled in the art). Therefore, the scope of the appended claims should be accorded the broadest interpretation so as to encompass all such modifications and similar arrangements.

What is claimed is:

1. A carrier generation material, having a chemical structure of:



2. An organic light-emitting diode, comprising:
an anode;
a cathode;


18

a carrier generation material layer, including the carrier generation material as claimed in claim 1, disposed between the anode and the cathode;

a first light-emitting layer disposed between the anode and the carrier generation material layer; and

a second light-emitting layer, disposed between the cathode and the carrier generation material layer.

3. A carrier generation material, having a chemical structure of:



4. An organic light-emitting diode, comprising:
an anode;
a cathode;

a carrier generation material layer, including the carrier generation material as claimed in claim 3, disposed between the anode and the cathode;

a first light-emitting layer disposed between the anode and the carrier generation material layer; and

a second light-emitting layer, disposed between the cathode and the carrier generation material layer.

* * * * *

专利名称(译)	载流子发生材料和有机发光二极管		
公开(公告)号	US9741969	公开(公告)日	2017-08-22
申请号	US14/860559	申请日	2015-09-21
[标]申请(专利权)人(译)	国立清华大学		
申请(专利权)人(译)	清大		
当前申请(专利权)人(译)	清大		
[标]发明人	CHENG CHIEN HONG HSIEH WEI TING HUNG CHEN HSUN HUANG MIN JIE LAI CHENG CHANG LIAO CHUANG YI		
发明人	CHENG, CHIEN-HONG HSIEH, WEI-TING HUNG, CHEN-HSUN HUANG, MIN-JIE LAI, CHENG-CHANG LIAO, CHUANG-YI		
IPC分类号	H01L51/54 H01L51/00 C07D241/42 C07D487/04 H01L51/52 C07D241/46 C07D241/44		
CPC分类号	H01L51/5278 C07D241/42 C07D241/44 C07D241/46 C07D487/04 H01L51/0072 H01L51/0051		
优先权	104127446 2015-08-24 TW		
其他公开文献	US20170062771A1		
外部链接	Espacenet USPTO		

摘要(译)

提供一种载体生成材料，其化学结构为：其中R¹、R²各自独立地为氢，卤素，-CN，-CF₃，-NO₂或烷基；R³各自独立地为氢，卤素，-CN，-CF₃，-NO₂或烷基；R⁴、R⁵各自独立地为氢，卤素，-CN，-CF₃，-NO₂或烷基；R⁶是=O，=NH或丙二腈基团，R⁷是氢，卤素，-CN，-CF₃，-NO₂或烷基。

