



US010040794B2

(12) **United States Patent**
Hwang et al.(10) **Patent No.: US 10,040,794 B2**(45) **Date of Patent: Aug. 7, 2018**(54) **CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**(71) Applicants: **Samsung Electronics Co., Ltd.**,
Suwon-si, Gyeonggi-do (KR); **Samsung SDI Co., Ltd.**, Yongin-si, Gyeonggi-do (KR)(72) Inventors: **Kyuyoung Hwang**, Ansan-si (KR);
Ohyun Kwon, Yongin-si (KR);
Sangmo Kim, Hwaseong-si (KR);
Joohee Seo, Uiwang-si (KR); **Seungjae Lee**, Uiwang-si (KR); **Byoungki Choi**,
Hwaseong-si (KR); **Hyeonho Choi**,
Seoul (KR)(73) Assignees: **SAMSUNG ELECTRONICS CO., LTD.**, Gyeonggi-Do (KR); **SAMSUNG SDI CO., LTD.**, Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 424 days.

(21) Appl. No.: **14/661,619**(22) Filed: **Mar. 18, 2015**(65) **Prior Publication Data**

US 2015/0325799 A1 Nov. 12, 2015

(30) **Foreign Application Priority Data**

May 7, 2014 (KR) 10-2014-0054432

(51) **Int. Cl.****H01L 51/00** (2006.01)
C07D 471/14 (2006.01)
H01L 51/50 (2006.01)
C07D 471/04 (2006.01)
C07D 471/22 (2006.01)
C07D 491/147 (2006.01)
C07D 491/22 (2006.01)
C07D 495/14 (2006.01)
C07D 519/00 (2006.01)
C07F 7/08 (2006.01)(52) **U.S. Cl.**CPC **C07D 471/14** (2013.01); **C07D 471/04** (2013.01); **C07D 471/22** (2013.01); **C07D 491/147** (2013.01); **C07D 491/22** (2013.01); **C07D 495/14** (2013.01); **C07D 519/00** (2013.01); **C07F 7/0816** (2013.01); **H01L 51/0067** (2013.01); **H01L 51/0072** (2013.01); **H01L 51/5012** (2013.01); **H01L 51/5016** (2013.01); **H01L 51/5056** (2013.01); **H01L 51/5072** (2013.01); **H01L 51/5088** (2013.01); **H01L 51/5092** (2013.01); **H01L 51/5096** (2013.01)(58) **Field of Classification Search**CPC H01L 51/0072
See application file for complete search history.(56) **References Cited**

U.S. PATENT DOCUMENTS

8,748,015 B2 6/2014 Morishita et al.
2010/0032658 A1 2/2010 Lee et al.
2012/0273770 A1 11/2012 Sunagawa et al.

FOREIGN PATENT DOCUMENTS

JP 2008214307 B2 9/2008
JP 2013042045 A 2/2013
KR 1020100007780 A 1/2010
KR 1020100137198 A 12/2010
KR 1020120079037 A 7/2012
KR 1020120119942 A 11/2012
KR 10 2013 0073700 * 7/2013
KR 10-1313505 B1 9/2013
KR 101313505 B1 10/2013
KR 10-1456521 B1 10/2014
WO 2012090462 A1 7/2012

OTHER PUBLICATIONS

Lussem et al. "Bright prospects for organic-LED lighting" (SPIE Newsroom Dec. 28, 2009) <http://spie.org/newsroom/2522-bright-prospects-for-organic-led-lighting>.*

KR 10 2013 0073700 machine translation (2013).*

Ghorbani-Vaghei (Tetrahedron Letters, 53 (2012) 4751-4753).*


* cited by examiner

Primary Examiner — Kuo Liang Peng

(74) Attorney, Agent, or Firm — Cantor Colburn LLP


(57) **ABSTRACT**

A condensed cyclic compound represented by Formulae 1A or 1B:



wherein in Formulae 1A and 1B, groups, rings, substituents, and variables are defined in the detailed description.

FIG. 1



1

CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

This application claims priority to Korean Patent Application No. 10-2014-0054432, filed on May 7, 2014, in the Korean Intellectual Property Office, and all the benefits accruing therefrom under 35 U.S.C. § 119, the content of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

The present disclosure relates to condensed cyclic compounds and organic light-emitting devices including the same.

2

produce excitons. These excitons change from an excited state to a ground state, thereby generating light.



Various types of organic light emitting devices are known. However, there still remains a need in OLEDs having low driving voltage, high efficiency, high brightness, and long lifespan.

SUMMARY

One or more embodiments relate to a novel condensed cyclic compound and an organic light-emitting device including the same.

Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

An aspect provides a condensed cyclic compound represented by Formulae 1A or 1B:



2. Description of the Related Art

Organic light emitting devices (OLEDs) are self-emission devices that have wide viewing angles, high contrast ratios, and short response times. In addition, the OLEDs exhibit excellent brightness, driving voltage, and response speed characteristics, and produce full-color images.

A typical organic light-emitting device includes an anode, a cathode, and an organic layer that is disposed between the anode and the cathode and includes an emission layer. A hole transport region may be disposed between the anode and the emission layer, and an electron transport region may be disposed between the emission layer and the cathode. Holes provided from the anode may move toward the emission layer through the hole transport region, and electrons provided from the cathode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, are recombined in the emission layer to

wherein in the formulae,

Ring A₁ in Formulae 1A and 1B is represented by Formula 1C;

Ring B₁ in Formulae 1A and 1B is a C₆-C₂₀ aromatic ring; X₂₁ is selected from N-[(L₂₁)_{a21}-(R₂₁)_{b21}], S, O, S(=O), S(=O)₂, C(R₂₂)(R₂₃), and Si(R₂₂)(R₂₃);

X₁₁ is N or C-[(L₁₁)_{a11}-(R₁₁)_{b11}];

X₁₂ is N or C-[(L₁₂)_{a12}-(R₁₂)_{b12}];

X₁₃ is N or C-[(L₁₃)_{a13}-(R₁₃)_{b13}];

X₁₄ is N or C-[(L₁₄)_{a14}-(R₁₄)_{b14}];

provided that at least one selected from X₁₁ to X₁₄ is N;

L₁ to L₃, L₁₁ to L₁₄, and L₂₁ may be each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₂-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group,

and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

a1 to a3, a11 to a14, and a21 may be each independently an integer selected from 0 to 5;

R₁ to R₃, R₁₁ to R₁₄, and R₂₁ to R₂₃ may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₂-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), and —B(Q₆)(Q₇);

b1 to b3, b11 to b14, and b21 may be each independently an integer selected from 1 to 5;

c1 and c2 are each independently an integer selected from 1 to 4;

at least one of substituents of the substituted C₃-C₁₀ cycloalkylene group, the substituted C₂-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₂-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₂-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₂-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₂-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl

group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅) and —B(Q₂₆)(Q₂₇); and

—N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), and —B(Q₃₆)(Q₃₇),

wherein Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₇ are each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

Another aspect provides an organic light-emitting device including:

a first electrode;

a second electrode;

and an organic layer disposed between the first electrode and the second electrode,

wherein the organic layer includes an emission layer, and further includes at least one condensed cyclic compound represented by Formula 1.

The condensed cyclic compound may be included in the emission layer, the emission layer may further include a dopant, and the condensed cyclic compound included in the emission layer may act as a host.

BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other aspects will become apparent and more readily appreciated from the following description of

the embodiments, taken in conjunction with FIG. 1 which is a schematic view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the FIGURES, to explain aspects of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. The term “or” means “and/or.” Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

It will be understood that when an element is referred to as being “on” another element, it can be directly in contact with the other element or intervening elements may be present therebetween. In contrast, when an element is referred to as being “directly on” another element, there are no intervening elements present.

It will be understood that, although the terms first, second, third etc. may be used herein to describe various elements, components, regions, layers, and/or sections, these elements, components, regions, layers, and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer, or section from another element, component, region, layer, or section. Thus, a first element, component, region, layer, or section discussed below could be termed a second element, component, region, layer, or section without departing from the teachings of the present embodiments.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, the singular forms “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

It will be further understood that the terms “comprises” and/or “comprising,” or “includes” and/or “including” when used in this specification, specify the presence of stated features, regions, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, regions, integers, steps, operations, elements, components, and/or groups thereof.

Spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature’s


relationship to another element(s) or feature(s) as illustrated in the FIGURES. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the FIGURES. For example, if the device in the FIGURES is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the exemplary term “below” can encompass both an orientation of above and below. The device may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein interpreted accordingly.

“About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” can mean within one or more standard deviations, or within $\pm 30\%$, 20% , 10% , 5% of the stated value.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.


Exemplary embodiments are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein should not be construed as limited to the particular shapes of regions as illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated may be rounded. Thus, the regions illustrated in the FIGURES are schematic in nature and their shapes are not intended to illustrate the precise shape of a region and are not intended to limit the scope of the present claims.

A condensed cyclic compound according to an embodiment is represented by Formulae 1A or 1B below:



-continued

Formula 1B



Ring A₁ in Formulae 1A and 1B is represented by Formula 1C as follows.



Formula 1C

Ring A₁ in Formulae 1A and 1B is a ring that shares a carbon atom with adjacent two 6-membered rings fused thereto.

Ring B₁ in Formulae 1A and 1B is a C₆-C₂₀ aromatic ring. The ring B₁ is a ring that shares a carbon atom with adjacent ring A₁ and that is fused to the ring A₁.

For example, the ring B₁ may be a benzene, a naphthalene, an anthracene, or a pyrene.

According to an embodiment, the ring B₁ may be a benzene or a naphthalene.

X₂₁ in Formula 1C is selected from N-[(L₂₁)_{a21}-(R₂₁)_{b21}], S, O, S(=O), S(=O)₂, C(R₂₂)(R₂₃), and Si(R₂₂)(R₂₃). For example, X₂₁ in Formula 1C may be selected from N-[(L₂₁)_{a21}-(R₂₁)_{b21}], S, O, and Si(R₂₂)(R₂₃), but is not limited thereto. L₂₁, a₂₁, R₂₁ to R₂₃, and b₂₁ may be understood by referring to descriptions to be presented herein.

X₁₁ in Formulae 1A and 1B is N or C-[(L₁₁)_{a11}-(R₁₁)_{b11}],

X₁₂ is N or C-[(L₁₂)_{a12}-(R₁₂)_{b12}],

X₁₃ is N or C-[(L₁₃)_{a13}-(R₁₃)_{b13}],

X₁₄ is N or C-[(L₁₄)_{a14}-(R₁₄)_{b14}],

provided that at least one selected from X₁₁ to X₁₄ is N.

For example, at least one selected from R₁₂ and R₁₃ in Formulae 1A and 1B may each be nitrogen (N). L₁₁ to L₁₄, a₁₁ to a₁₄, R₁₁ to R₁₄, and b₁₁ to b₁₄ may be understood by referring to descriptions to be presented herein.

L₁ to L₃, L₁₁ to L₁₄, and L₂₁ may be each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₂-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

For example, L₁ to L₃, L₁₁ to L₁₄, and L₂₁ in Formulae 1A and 1B may be each independently selected from

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylenylene group, a fluorenylene group, a spiro-fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a

naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pyrrolylene group, an imidazolylene group, a pyrazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylenylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzooxazolylene group, a benzoimidazolylene group, a furanylenylene group, a benzofuranylenylene group, a thiophenylene group, a benzothiophenylene group, a thiazolylene group, an isothiazolylene group, a benzothiazolylene group, an isoxazolylene group, an oxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylenylene group, a dibenzothiophenylene group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinylene group, and an imidazopyridinylene group; and


a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylenylene group, a fluorenylene group, a spiro-fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pyrrolylene group, an imidazolylene group, a pyrazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylenylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzooxazolylene group, a benzoimidazolylene group, a furanylenylene group, a benzofuranylenylene group, a thiophenylene group, a benzothiophenylene group, a thiazolylene group, an isothiazolylene group, a benzothiazolylene group, an isoxazolylene group, an oxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylenylene group, a dibenzothiophenylene group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinylene group, and an imidazopyridinylene group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt

9


thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a quinoxalinyl group, a carbazolyl group, a phenyl group-substituted carbazolyl group, a phenanthrolyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a phenyl group-substituted benzocarbazolyl group, a phenyl group-substituted dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, and $-\text{Si}(\text{Q}_{33})(\text{Q}_{34})(\text{Q}_{35})$,

wherein Q_{33} to Q_{35} may be each independently a hydrogen, a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, or an imidazopyridinyl group, but they are not limited thereto.


For example, L_1 to L_3 , L_{11} to L_{14} , and L_{21} in Formulae 1A and 1B may be each independently selected from Formulae 2-1 to 2-34.




Formula 2-1



Formula 2-2



Formula 2-3




Formula 2-4


10

-continued


Formula 2-5




Formula 2-6




Formula 2-7




Formula 2-8




Formula 2-9




Formula 2-10




Formula 2-11




Formula 2-12




Formula 2-13



Formula 2-14














Formula 2-15



11


-continued

**12**

-continued


Formula 2-16

5




Formula 2-17

10



Formula 2-18

15




Formula 2-19

20

Formula 2-20

25




Formula 2-21

30

Formula 2-22


35



Formula 2-23

40

45




Formula 2-24

50


Formula 2-25

55



Formula 2-26

60



Formula 2-27

Formula 2-28

Formula 2-29

Formula 2-30

Formula 2-31

Formula 2-32

Formula 2-33









Formula 2-34

wherein in Formulae 2-1 to 2-34,








Y₁ may be O, S, S(=O), S(=O)₂, C(Z₃)(Z₄), N(Z₅), or Si(Z₆)(Z₇);

15

-continued

**16**

-continued



Formula 3-13

5

Formula 3-14

10

15

20

Formula 3-15

25

Formula 3-16

30

Formula 3-17

35

40

Formula 3-18

45

50

Formula 3-19

55

Formula 3-20

60

65

Formula 3-21

Formula 3-22

Formula 3-23

Formula 3-24







Formula 3-25

Formula 3-26

Formula 3-27

17

-continued

**18**

-continued

Formula 3-28

5

10

Formula 3-29

15

20

Formula 3-30

25

30

Formula 3-31

35

40

Formula 3-32

45

50

Formula 3-33

Formula 3-34

Formula 3-35

Formula 3-36

Formula 3-37

Formula 3-38

Formula 3-39

55 a1 in Formula 1 indicates the number of groups L_1 , and may be 0, 1, 2, 3, 4, or 5, for example, 0, 1, or 2, or for example, 0 or 1. When a1 is 0, $-(L_1)_{a1}-$ is a single bond. When a1 is 2 or more, groups L_1 may be identical or different. a2, a3, a11, a12, a13, and a14 may be understood by referring to the description provided in connection with a1.

60 R_1 to R_3 , R_{11} to R_{14} , and R_{21} to R_{23} in Formulae 1A, 1B, and 1C may be each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a

19

phosphoric acid or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_2 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-N(Q_1)(Q_2)$, $-Si(Q_3)(Q_4)(Q_5)$, and $-B(Q_6)(Q_7)$. Q_1 to Q_7 may be understood by referring to descriptions to be provided herein.


For example, R_1 to R_3 , R_{11} to R_{14} , and R_{21} to R_{23} may be each independently selected from

a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;


a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, and a phosphoric acid or a salt thereof;

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolylene group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzofuroypyridinyl group, a benzothiophenopyridinyl group, a benzofuroypyrimidinyl group, a benzothiophenopyrimidinyl group, a group represented by


20



a group represented by




and a group represented by




a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolylene group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzofuroypyridinyl group, a benzothiophenopyridinyl group, a benzofuroypyrimidinyl group, a benzothiophenopyrimidinyl group, a group represented by


21



a group represented by



and a group represented by



each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₂-C₂₀ alkenyl group, a C₂-C₂₀ alkynyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a phenyl group substituted with another phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a quinoxalinyl group, a carbazolyl group, a phenyl group-substituted carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a phenyl group-substituted benzocarbazolyl group, a phenyl group-substituted dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, and —Si(Q₃)(Q₄)(Q₅); and

—Si(Q₃)(Q₄)(Q₅),

wherein Q₃ to Q₅ and Q₃₃ to Q₃₅ may be each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl

22

group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, or an imidazopyridinyl group.

According to an embodiment, R₁ to R₃, R₁₁ to R₁₄, and R₂₁ to R₂₃ are each independently selected from


a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, and a phosphoric acid or a salt thereof;


one of Formulae 4-1 to 4-49; and

—Si(Q₃)(Q₄)(Q₅);


Formula 4-1




Formula 4-2




Formula 4-3




Formula 4-4



Formula 4-5















Formula 4-6



23


-continued

**24**

-continued


Formula 4-7

5




Formula 4-8

10




Formula 4-9

15




Formula 4-10

20




Formula 4-11

25




Formula 4-12

30




Formula 4-13

35




Formula 4-14

40




Formula 4-15

45



Formula 4-16

50




Formula 4-17

55

Formula 4-18

60



65

Formula 4-19

Formula 4-20

Formula 4-21

Formula 4-22

Formula 4-23

Formula 4-24

Formula 4-25

Formula 4-26








Formula 4-27

Formula 4-28










Formula 4-29

25

-continued

**26**

-continued



Formula 4-30

5

Formula 4-31

10

Formula 4-32

20

Formula 4-33

30

Formula 4-34

35

Formula 4-35

45

Formula 4-36

60

65

Formula 4-37

Formula 4-38

Formula 4-39

Formula 4-40

Formula 4-41

Formula 4-42


Formula 4-43

Formula 4-44


Formula 4-45

27


-continued




Formula 4-46



Formula 4-47



Formula 4-48



Formula 4-49

wherein in Formulae 4-1 to 4-49,

Y_{31} is O, S, $C(Z_{33})(Z_{34})$, $N(Z_{35})$, or $Si(Z_{36})(Z_{37})$;

Z_{31} to Z_{37} are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a phenyl group substituted with another phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a quinoxalinyl group, a carbazolyl group, a phenyl group-substituted carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a phenyl group-substituted benzocarbazolyl group, a phenyl group-substituted dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, and —Si(Q_{33})(Q_{34})(Q_{35});

Q_3 to Q_5 and Q_{33} to Q_{35} may be each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a ben-

28

zocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, or an imidazopyridinyl group;

e1 may be an integer of 1 to 5;

e2 may be an integer of 1 to 7;

e3 may be an integer of 1 to 3;

e4 may be an integer of 1 to 4;

e5 may be an integer of 1 or 2;

e6 may be an integer of 1 to 6, and


* indicates a binding site to a neighboring atom.

In some embodiments, R_1 to R_3 , R_{11} to R_{14} , and R_{21} to R_{23} are each independently selected from


a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, and a phosphoric acid or a salt thereof; and


one of from Formulae 5-1 to 5-77, but they are not limited thereto:




Formula 5-1




Formula 5-2



Formula 5-3











Formula 5-4



Formula 5-5

29


-continued

**30**

-continued

Formula 5-6


5



10


Formula 5-7

15




Formula 5-8

20




25

30



Formula 5-9


35



40


Formula 5-10

45



Formula 5-11

50




Formula 5-12

55

Formula 5-13

60

65



Formula 5-14

Formula 5-15

Formula 5-16

Formula 5-17

Formula 5-18









Formula 5-19

Formula 5-20









Formula 5-21

31

-continued

**32**

-continued



Formula 5-22

5

Formula 5-30

Formula 5-23

10

Formula 5-31

Formula 5-24

25

Formula 5-32

Formula 5-25

35

Formula 5-33

Formula 5-26

45

Formula 5-34

Formula 5-27

50

Formula 5-35

Formula 5-28

55

Formula 5-36

Formula 5-29









60

Formula 5-37

65

33


-continued

**34**

-continued


Formula 5-38

5




Formula 5-39

10




Formula 5-40

15




Formula 5-41

20



Formula 5-42


30



Formula 5-43

35


40



Formula 5-44

45


50



Formula 5-45

55

60



65

Formula 5-46

Formula 5-47

Formula 5-48

Formula 5-49

Formula 5-50







Formula 5-51

Formula 5-52

Formula 5-53

35


-continued

**36**

-continued

Formula 5-54


5



10

Formula 5-55


15



20

Formula 5-56


25



30

Formula 5-57


35



40

Formula 5-58


45



50


Formula 5-59

55



60

65



Formula 5-60

Formula 5-61

Formula 5-62

Formula 5-63








Formula 5-64

Formula 5-65

Formula 5-66

37

-continued




38

-continued

Formula 5-67


5



10

Formula 5-68

15




20

Formula 5-69

25

Formula 5-70


30



35

Formula 5-71

40



45

Formula 5-72

50

55

Formula 5-73

60

According to an embodiment, R_1 , R_2 , R_{11} to R_{14} , R_{22} , and R_{23} are each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a phenanthrenyl group, a fluorenyl group, a chrysenyl group, a carbazolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, and a quinoxalinyl group.

For example, R_1 , R_2 , R_{11} to R_{14} , R_{22} , and R_{23} may be each independently selected from a hydrogen, a C_1 - C_{20} alkyl group, a phenyl group, and a naphthyl group, but they are not limited thereto.

In some embodiments, R_3 and R_{21} may be each independently selected from a substituted or unsubstituted C_6 - C_{30} aryl group, a substituted or unsubstituted C_2 - C_{30} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

Formula 5-74


Formula 5-75

Formula 5-76


Formula 5-77

39


R₃ and R₂₁ may be each independently selected from a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perilenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthridinyl group, a quinoxalinyl group, a quinazolinyl group, a cynolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isooxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzofuro-pyridinyl group, a benzothiophenopyridinyl group, a benzofuopyrimidinyl group, a benzothiophenopyrimidinyl group, a group represented by



a group represented by



and a group represented by




and


a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an

40


indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzofuopyrimidinyl group, a benzothiophenopyridinyl group, a benzofuopyrimidinyl group, a benzothiophenopyrimidinyl group, a group represented by



a group represented by



and a group represented by



each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₂-C₂₀ alkenyl group, a

41

C₂-C₂₀ alkynyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a phenyl group substituted with another phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a quinoxalinyl group, a carbazolyl group, a phenyl group-substituted carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a phenyl group-substituted benzocarbazolyl group, a phenyl group-substituted dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, and —Si(Q₃₃)(Q₃₄)(Q₃₅);

wherein Q₃₃ to Q₃₅ may be each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, or an imidazopyridinyl group, but they are not limited thereto.

For example, R₃ and R₂₁ may be each independently represented by one of Formulae 4-1 to 4-49 (for example, one of Formulae 5-1 to 5-77), but they are not limited thereto.

In some embodiments, R₃ may be selected from a substituted or unsubstituted C₂-C₃₀ heteroaryl group and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, each group containing at least one nitrogen as a ring-forming atom.

For example, R₃ may be any one selected from Formulae 4-7 to 4-25 and 4-32 to 4-49, but is not limited thereto.

In some embodiments, R₃ may be any one selected from Formulae 5-27 to 5-77, but is not limited thereto.


b1 in Formulae 1A and 1B indicates the number of groups R₁, and may be an integer of 1 to 5. For example, b1 may be 1 or 2. When b1 is 2 or more, groups R₁ may be identical or different. b2, b3, b11 to b14, and b21 may be understood by referring to the description presented in connection with b1. For example, b1 to b3, b11 to b41, and b21 may be 1 or 2, but are not limited thereto.

c1 in Formulae 1A and 1B indicates the number of groups —[(L₁)_{a1}—(R₁)_{b1}], and may be selected from an integer of 1 to 4. For example, c1 may be 1 or 2. When c1 is 2 or more, two or more —[(L₁)_{a1}—(R₁)_{b1}] are identical or different. For example, c1 and c2 may be 1 or 2, but are not limited thereto.


According to an embodiment, the condensed cyclic compound may be represented by one selected from Formulae 1A-1 to 1A-16 and 1B-1 to 1B-3 below:

42


Formula 1A-1




Formula 1A-2




Formula 1A-3



Formula 1A-4




Formula 1A-5



43


-continued

Formula 1A-6

**44**


-continued

Formula 1A-11




Formula 1A-12


Formula 1A-7





Formula 1A-8




Formula 1A-9




Formula 1A-10




Formula 1A-13




Formula 1A-14



Formula 1A-15




Formula 1A-16




45

-continued


Formula 1B-1



Formula 1B-2




Formula 1B-3




Ring A_1 , L_1 to L_3 , a_1 to a_3 , R_1 to R_3 , R_{11} to R_{14} , b_1 to b_3 , c_1 , and c_2 in Formulae 1A-1 to 1A-16 and 1B-1 to 1B-3 (a_1 and a_2 are all 0 and b_1 and b_2 are all 1) may be understood by referring to the description presented herein.

In some embodiments, the condensed cyclic compound may be represented by one selected from Formulae 1A(1)-1 to 1A(1)-16, but is not limited thereto:

Formula 1A(1)-1




Formula 1A(1)-2


**46**

-continued


Formula 1A(1)-3




Formula 1A(1)-4




Formula 1A(1)-5




Formula 1A(1)-6



Formula 1A(1)-7




Formula 1A(1)-8




47

-continued


Formula 1A(1)-9




Formula 1A(1)-10




Formula 1A(1)-11



Formula 1A(1)-12




Formula 1A(1)-13




48

-continued


Formula 1A(1)-14



Formula 1A(1)-15




Formula 1A(1)-16






X_{21} , L_1 to L_3 , a_1 to a_3 , R_1 to R_3 , R_{11} to R_{14} , b_1 to b_3 , c_1 , and c_2 in Formulae 1A(1)-1 to 1A(1)-16 (a_1 and a_2 are all 0 and b_1 and b_2 are all 1) may be understood by referring to the description presented herein.

For example, the condensed cyclic compound may be one of Compounds 1 to 200 below, but is not limited thereto:



49

-continued



50

-continued

2


5

5

10

15

20



3


25

6

30

35

40



4

45


50

7

55


60

65




51

-continued






52

-continued







53

-continued








54

-continued



55

-continued

**56**

-continued

22

5

10

15

23

20

25

30

24

35

40

45

25

50

55

26

60

65






27

28

29





30

31



57

-continued



32

5

10

33

15

20

25

30

34

35

40

45

35

50





55

60

65

58

-continued



36

37





38

39

40

59

-continued



60

-continued

41

5

10

15

20

42

25

30

35

43

40

45

50

44

55

60





65

45

46





47

48






61

-continued



62

-continued



49

5

10

15

50

20

25

51 35

40

45

50

52

55

60

65





53

54

55

63

-continued

**64**

-continued

56

5

10

15

57 20

25

30

35

58

40

45

50

59

55

60





65

60

61





62

63



65

-continued



66

-continued

64

68

5

10

15

65

20

25

30

66

35

40

45





50

67

55






60

65



67

-continued

**68**

-continued

72

5

10

15

73

20

25

30

74

35

40

75

45

50






76

55

60

65

77



78





79

80

81

69

-continued

**70**

-continued

82

5

10

83

15

20

25

84

30

35

40

45





85

50

55

60

65



86




87

88

89

71

-continued



72

-continued

90

5

10

15

20

91

25

30

35

40

92





45

50

55

60

65



93





94

95

96

73

-continued

**74**

-continued

97

5

10

15

98

20

25

30

99

35

40

45

100

50

55




60

65

101




102

103







75

-continued




**76**

-continued



77

-continued

**78**

-continued

111


5

10

15

20

114



112

25


30

35

40

45

115



116


113

50

55





60

65



79

-continued

**80**

-continued

117

121

5

10

15

118

20

25

30

119

35

40

45




120

50

55


60

65



81

-continued




124

5

10

15

20




125 25

30

35

40

45



126

50


55

60


65

82


-continued



127







128



129

83

-continued

**84**

-continued

130

5

10

15

20

131

25

30

132

35

40

45

133


50

55


60

65


134




135



136







137




85

-continued

**86**

-continued



138

142

5

10

15

139

20

25

30

140

35

40

45

141

50

55


60

65

143





144

145








87

-continued


**88**

-continued



89


-continued



155

5


10



156 15

20

25




157 30

35

40

45



158 50


55

60


65

90


-continued




159




160



161







162







163

91

-continued





**92**

-continued







93

-continued





**94**

-continued







95

-continued


**96**

-continued



97

-continued



98

-continued

188

191

5

10

15

20

25

189

30

35

40

45

190

50






192

193

55





60

65



99


-continued

**100**

-continued

194

198



195

20

196


35

40

45

197

50



199

200

In the condensed cyclic compound represented by Formulae 1A or 1B, at least one selected from X_{11} to X_{14} is necessarily N. Accordingly, HOMO and LUMO energy levels of the condensed cyclic compound represented by Formulae 1A or 1B may be adjusted according to the structure of a device, and according to the number and location of N in X_{11} to X_{14} in Formulae 1A and 1B, S_1 energy level and T_1 energy level of the condensed cyclic compound may be easily adjustable. A condensed cyclic compound as described above may be used in a different capacity as, for example, a red host, a green host, or a blue host.

The highest occupied molecular orbital (HOMO), the lowest unoccupied molecular orbital (LUMO), a singlet (S_1)

energy level, and a triplet (T1) energy level of Compounds 1, 25, 26, 37, 39, 101 to 104, 113, 114, 132, 133, 134, 146, 148, 156 to 158, 170, 171 and 172 were evaluated by using Gaussian program DFT method (structural optimization was performed at B3LYP, 6-31G(d,p) level), and evaluation results are shown in Table 1 below.

TABLE 1

Compound No.	HOMO (eV)	LUMO (eV)	S1 energy level (eV)	T1 energy level (eV)
Compound 1	-5.085	-0.981	3.414	2.737
Compound 25	-5.433	-1.247	3.376	2.709
Compound 26	-5.350	-1.344	3.471	2.620
Compound 37	-5.452	-1.184	3.482	2.771
Compound 39	-5.320	-1.241	3.548	2.695
Compound 101	-5.118	-1.931	2.738	2.606
Compound 102	-5.200	-2.043	2.715	2.521
Compound 103	-5.020	-1.844	2.867	2.727
Compound 104	-5.087	-2.085	2.614	2.599
Compound 113	-5.487	-1.730	3.266	2.847
Compound 114	-5.316	-1.718	3.086	2.663
Compound 132	-5.545	-2.142	2.956	2.552
Compound 133	-5.358	-1.893	3.145	2.711
Compound 134	-5.420	-2.148	2.865	2.707
Compound 146	-5.574	-1.834	3.188	2.581
Compound 148	-5.370	-1.873	3.041	2.621
Compound 156	-5.570	-2.128	2.978	2.605
Compound 157	-5.375	-1.889	3.159	2.772
Compound 158	-5.442	-2.146	2.881	2.766
Compound 170	-5.540	-1.825	3.194	2.644
Compound 171	-5.262	-1.697	3.208	2.689
Compound 172	-5.342	-1.864	3.024	2.696

From the data listed in Table 1, it was determined that Compounds 1, 25, 26, 37, 39, 101 to 104, 113, 114, 132, 133, 134, 146, 148, 156 to 158, 170, 171, and 172 have electric characteristics suitable for use as a material for an organic light-emitting device.

The preparation of condensed cyclic compounds represented by Formula 1A or 1B may be apparent to one of ordinary skill in the art by referring to Synthesis Examples to be explained below.

The condensed cyclic compound represented by Formula 1A or 1B is suitable for use in an organic layer of an organic light-emitting device, for example, for use as a host in an emission layer of the organic layer. Thus, another aspect provides an organic light-emitting device that includes:

- a first electrode;
 - a second electrode; and
 - an organic layer that is disposed between the first electrode and the second electrode,
- wherein the organic layer includes an emission layer and at least one of the condensed cyclic compound represented by Formula 1A or 1B.

The organic light-emitting device may have, due to the inclusion of an organic layer including the condensed cyclic compound represented by Formula 1A or 1B, low driving voltage, high efficiency, high brightness, and long lifespan.

The condensed cyclic compound of Formula 1A or 1B may be used between a pair of electrodes of an organic light-emitting device. For example, the condensed cyclic compound may be included in at least one selected from an emission layer, a hole transport region (including, for example, at least one of a hole injection layer, a hole transport layer, and an electron blocking layer) that is disposed between the first electrode and the emission layer, and an electron transport region (including, for example, at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer) that is

disposed between the emission layer and the second electrode. For example, the condensed cyclic compound represented by Formula 1A or 1B may be included in the emission layer. In this regard, the emission layer may further include a dopant, and the condensed cyclic compound included in the emission layer may act as a host. The emission layer may be a green emission layer emitting green light, and the dopant may be a phosphorescent dopant.

The expression “(an organic layer) includes at least one condensed cyclic compound” used herein may include a case in which “(an organic layer) includes one condensed cyclic compound of Formulae 1A or 1B and a case in which (an organic layer) includes two or more different condensed cyclic compounds of Formulae 1A or 1B.

For example, the organic layer may include, as the condensed cyclic compound, only Compound 1. In this regard, Compound 1 may be situated in an emission layer of the organic light-emitting device. In another embodiment, the organic layer may include, as the condensed cyclic compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may be situated in either an identical layer (for example, Compound 1 and Compound 2 all may be situated in an emission layer), or different layers.

For example, in the organic light-emitting device, the first electrode may be an anode, the second electrode may be a cathode, and the organic layer may include

- i) a hole transport region that is disposed between the first electrode and the emission layer, wherein the hole transport region may include at least one of a hole injection layer, a hole transport layer, and an electron blocking layer, and
- ii) an electron transport region that is disposed between the emission layer and the second electrode, wherein the electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

The term “organic layer” as used herein refers to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of an organic light-emitting device. The “organic layer” may include, in addition to an organic compound, an organometallic complex including metal.

FIG. 1 is a schematic view of an organic light-emitting device 10 according to an embodiment. Hereinafter, the structure of an organic light-emitting device according to an embodiment and a method of manufacturing an organic light-emitting device according to an embodiment will be described in connection with FIG. 1. The organic light-emitting device 10 includes a first electrode 11, an organic layer 15, and a second electrode 19, which are sequentially stacked.

In FIG. 1, a substrate may be additionally disposed under the first electrode 11 or above the second electrode 19. For use as the substrate, any substrate that is used in general organic light-emitting devices may be used, and the substrate may be a glass substrate or transparent plastic substrate, each with excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water repellency.

The first electrode 11 may be formed by depositing or sputtering a material for forming the first electrode on the substrate. The first electrode 11 may be an anode. The material for the first electrode 11 may be selected from materials with a high work function to make holes be easily injected. The first electrode 13 may be a reflective electrode or a transmissive electrode. The material for the first electrode 11 may be an indium tin oxide (ITO), indium zinc

103

oxide (IZO), tin oxide (SnO_2), or zinc oxide (ZnO). According to another embodiment, the material for the first electrode **11** may be metal, such as magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag). ⁵

The first electrode **11** may have a single-layer structure or a multi-layer structure including two or more layers.

An organic layer **15** may be disposed on the first electrode **11**. ¹⁰

The organic layer **15** may include a hole transport region, an emission layer, and an electron transport region.

The hole transport region may be disposed between the first electrode **11** and the emission layer. ¹⁵

The hole transport region may include at least one of a hole injection layer, a hole transport layer, an electron blocking layer, and a buffer layer.

The hole transport region may include only either a hole injection layer or a hole transport layer. According to another embodiment, the hole transport region may have a structure of hole injection layer/hole transport layer or hole injection layer/hole transport layer/electron blocking layer, which are sequentially stacked in this stated order from the first electrode **11**. ²⁰

When the hole transport region includes a hole injection layer (HIL), the hole injection layer may be formed on the first electrode **11** by using any one of various methods, for example, vacuum deposition, spin coating, casting, or Langmuir-Blodgett (LB) deposition. ²⁵

When a hole injection layer is formed by vacuum deposition, the deposition conditions may vary according to a material that is used to form the hole injection layer, and the structure and thermal characteristics of the hole injection layer. For example, the deposition conditions may include a deposition temperature of about 100 to about 500° C., a vacuum pressure of about 10^{-8} to about 10^{-3} torr, and a deposition rate of about 0.01 to about 100 Angstroms per second ($\text{\AA}/\text{sec}$). However, the deposition conditions are not limited thereto. ³⁰


When the hole injection layer is formed using spin coating, coating conditions may vary according to the material used to form the hole injection layer, and the structure and thermal properties of the hole injection layer. For example, a coating speed may be from about 2,000 revolutions per minute (rpm) to about 5,000 rpm, and a temperature at which a heat treatment is performed to remove a solvent after coating may be from about 80° C. to about 200° C. However, the coating conditions are not limited thereto. ³⁵

Conditions for a hole transport layer and an electron blocking layer may be understood by referring to conditions for forming the hole injection layer. ⁴⁰


The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB, β -NPB, TPD, Spiro-TPD, Spiro-NPB, α -NPB, TAPC, HMTDP, 4,4',4"-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201 below, and a compound represented by Formula 202 below: ⁴⁵

104


m-MTDATA



TDATA








2-TNATA







105

-continued

**106**


-continued



107

-continued

Formula 202



Ar₁₀₁ to Ar₁₀₂ in Formula 201 may be each independently selected from

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthene group, a triphenylenylene group, a pyrenylene group, a chrysenylenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, and a pentacenylene group; and

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthene group, a triphenylenylene group, a pyrenylene group, a chrysenylenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, and a pentacenylene group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

xa and xb in Formula 201 may be each independently selected from an integer of 0 to 5, or 0, 1 or 2. For example, xa may be 1 and xb may be 0, but xa and xb are not limited thereto.

R₁₀₁ to R₁₀₈, R₁₁₁ to R₁₁₉, and R₁₂₁ to R₁₂₄ in Formulae 201 and 202 may be each independently selected from

a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group (for example, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, and so on), and a C₁-C₁₀ alkoxy group (for example, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, and so on);

a C₁-C₁ alkyl group and a C₁-C₁₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, and a phosphoric acid or a salt thereof;

a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, and a pyrenyl group; and

a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, and a pyrenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I,

108

a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, or a C₁-C₁₀ alkoxy group, but they are not limited thereto.


R₁₀₉ in Formula 201 may be selected from

a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group; and

a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group.

According to an embodiment, the compound represented by Formula 201 may be represented by Formula 201A below, but is not limited thereto:


Formula 201A



R₁₀₁, R₁₁₁, R₁₁₂, and R₁₀₉ in Formula 201A may be understood by referring to the description provided herein.

For example, the compound represented by Formula 201, and the compound represented by Formula 202 may include compounds HT1 to HT20 illustrated below, but are not limited thereto.


HT1



109

-continued

HT2



5

10

15

20


25

30

35

40

HT3



45

50

55


60

65

110

-continued

HT4



5

10

15

20


25

30

35

40

HT5



45

50

55


60

65

111

-continued

HT6



112

-continued

HT8

5

10

15

20

25

30

35

40

HT7




45

50

55

60


65



113


-continued

HT10


**114**

-continued

HT12





HT13




HT14

HT11




HT15



115


-continued



HT16


116

-continued




HT20

HT17




20

HT18



40

HT19



55


60

65

A thickness of the hole transport region may be in a range of about 100 Angstrom (Å) to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes both a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, for example about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.


The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

The charge-generation material may be, for example, a p-dopant. The p-dopant may be one of a quinone derivative, a metal oxide, and a cyano group-containing compound, but is not limited thereto. Non-limiting examples of the p-dopant are a quinone derivative, such as tetracyanoquinonedi-methane (TCNQ) or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonedi-methane (F4-TCNQ); a metal oxide, such as a tungsten oxide or a molybdenum oxide; and a cyano group-containing compound, such as Compound HT-D1 below, but are not limited thereto.



Compound HT-D1

117





The hole transport region may include a buffer layer.

Also, the buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, and thus, efficiency of a formed organic light-emitting device may be improved.

Then, an emission layer (EML) may be formed on the hole transport region by vacuum deposition, spin coating, casting, LB deposition, or the like. When the emission layer is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied to form the hole injection layer although the deposition or coating conditions may vary according to the material that is used to form the emission layer.

The emission layer may include a host and a dopant. The host may include at least one condensed cyclic compound represented by Formulae 1A or 1B.

The host may further include, in addition to the condensed cyclic compound represented by Formula 1, at least one of TPBi, TBADN, AND (also referred to as "DNA"), CBP, CDBP, and TCP.



118

-continued

5

10

ADN

15

20

CBP

25

30

CDBP

35

40

45

TCP

When the organic light-emitting device is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and a blue emission layer. According to another embodiment, due to a stack structure including a red emission layer, a green emission layer, and/or a blue emission layer, the emission layer may emit white light. A host in the red emission layer, the green emission layer, and the blue emission layer may include the condensed cyclic compound represented by Formula 1. According to an embodiment, the host in the green emission layer may include the condensed cyclic compound represented by Formulae 1A or 1B.


A dopant in the emission layer may be a fluorescent dopant that emits light according to a fluorescent emission mechanism or a phosphorescent dopant that emits light according to a phosphorescent emission mechanism.

According to an embodiment, the emission layer may include a host including the condensed cyclic compound represented by one of Formulae 1A or 1B and a phosphorescent dopant. The phosphorescent dopant may include an

119

organometallic complex including a transition metal (for example, iridium (Ir), platinum (Pt), osmium (Os), or rhodium (Rh)).

The phosphorescent dopant may include an organometallic complex represented by Formula 81 below:



wherein in Formula 81,

M may be selected from iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm);

Y_1 to Y_4 are each independently selected from carbon (C) or nitrogen (N);

Y_1 and Y_2 are linked via a single bond or a double bond, and Y_3 and Y_4 are linked via a single bond or a double bond;

CY_1 and CY_2 are each independently selected from a benzene, a naphthalene, a fluorene, a spiro-fluorene, an indene, a pyrrole, a thiophene, a furan, an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isooxazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, a quinoline, an isoquinoline, a benzoquinoline, a quinoxaline, a quinazoline, a carbazole, a benzoimidazole, a benzofuran, a benzothiophene, an isobenzothiophene, a benzooxazole, an isobenzooxazole, a triazole, a tetrazole, an oxadiazole, a triazine, a dibenzofuran, and a dibenzothiophene, and CY_1 and CY_2 are optionally linked to each other through a single bond or an organic linking group;

R_{81} to R_{82} may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_2 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q_1)(Q_2), —Si(Q_3)(Q_4)(Q_5), and —B(Q_6)(Q_7);

a_{81} and a_{82} are each independently selected from an integer of 1 to 5;

n_{81} is selected from an integer of 0 to 4;

n_{82} is 1, 2, or 3; and


120

L_{81} is selected from a monovalent organic ligand, a divalent organic ligand, and a trivalent organic ligand.

The phosphorescent dopant may include at least one of Compounds PD 1 to PD74 below, but is not limited thereto:

5


PD1



10

15


PD2



20

25

PD3




30

35

40


PD4



45

50

PD5








55

60

65

121

-continued

**122**

-continued

PD6

5

10

PD7

15

20

25

PD8

30

35

PD9

40

45






50

PD10

55

60

65



PD11

PD12






PD13

PD14

PD15

123

-continued

**124**

-continued

PD16

5

10

PD17

15

20

PD18

25

30

35

PD19

40

45


PD20

50

55


60

65




PD21


PD22




PD23




PD24



PD25









PD26



125


-continued

**126**

-continued

PD27


5



10

PD28


15



20

PD29

25



30


PD30

35

40

PD31


45



50

PD32

55



60

65

PD33

PD34






PD35

PD36

PD37

127

-continued

**128**

-continued

PD38

5

10

PD39 15

20

25

PD40 30

35

PD41 40

45






50

PD42

55

60

65



PD43

PD44







PD45

PD46

PD47

129

-continued

**130**

-continued

PD48

5

10

PD49

15

20

PD50

25

30

PD51

35

40

PD52

45






50

55

PD53

60

65



PD54

PD55






PD56

PD57

PD58

131

-continued

**132**

-continued

PD59

5

10

PD60

15

20

PD61

25

30

35

PD62

40

45






50

PD63

55

60

65



PD64

PD65






PD66

PD67

PD68

133

-continued

**134**

-continued

PD69

PD74

5

10

PD70

15

20

According to another embodiment, the phosphorescent dopant may include PtOEP or Compound PhGD illustrated below:


25

PD71

30

35

40




PtOEP

PD72

45

50



PhGD

PD73


60

65


The fluorescent dopant may include at least one selected from DPVBi, D PAVBi, TBPe, DCM, DCJTb, Coumarin 6, and C545T.

135


136



DPVBi




DPAVB




TBPe


DCM



DCJT



Coumarin 6



C545T

137

When the emission layer includes a host and a dopant, an amount of the dopant may be in a range of about 0.01 to about 15 parts by weight based on 100 parts by weight of the host, but is not limited thereto.

A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.


Then, an electron transport region may be disposed on the emission layer.

The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.


For example, the electron transport region may have a structure of electron transport layer, hole blocking layer/electron transport layer/electron injection layer or electron transport layer/electron injection layer, but is not limited thereto. The electron transport layer may have a single-layered structure or a multi-layer structure including two or more different materials.

Conditions for forming the hole blocking layer, the electron transport layer, and the electron injection layer which constitute the electron transport region may be understood by referring to the conditions for forming the hole injection layer.

When the electron transport layer includes a hole blocking layer, the hole blocking layer may include, for example, at least one of BCP and Bphen, but may also include other materials.



BCP





Bphen


A thickness of the hole blocking layer may be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thickness of the hole blocking layer is within these ranges, the hole blocking layer may have excellent hole blocking characteristics without a substantial increase in driving voltage.

The electron transport layer may further include, in addition to the organometallic compound represented by Formula 1, at least one selected from BCP, Bphen, Alq₃, Balq, TAZ, and NTAZ.


138

Alq₃

BAIq




TAZ




NTAZ

According to another embodiment, the electron transport layer may include at least one of ET1 and ET2, but are not limited thereto:

139



ET1




ET2

A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.


Also, the electron transport layer may further include, in addition to the materials described above, a metal-containing material.

The metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2.



ET-D1

140



ET-D2

The electron transport region may include an electron injection layer (EIL) that allows electrons to be easily provided from a second electrode 19.

The electron injection layer may include at least one selected from, LiF, NaCl, CsF, Li₂O, BaO, and LiQ.

A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

The second electrode 19 is disposed on the organic layer 15. The second electrode 19 may be a cathode. A material for forming the second electrode 19 may be metal, an alloy, an electrically conductive compound, and a combination thereof, which have a relatively low work function. For example, lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be used as the material for forming the second electrode 19. To manufacture a top emission type light-emitting device, a transmissive electrode formed using ITO or IZO may be used as the second electrode 19.

Hereinbefore, the organic light-emitting device has been described with reference to FIG. 1, but is not limited thereto.

A C₁-C₆₀ alkyl group used herein refers to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms. Detailed examples thereof are a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. A C₁-C₆₀ alkenylene group used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

A C₁-C₆₀ alkoxy group used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group). Detailed examples thereof are a methoxy group, an ethoxy group, and an isopropoxy group.

A C₂-C₆₀ alkenyl group used herein refers to a hydrocarbon group formed by substituting at least one carbon double bond in the middle or at the terminal of the C₂-C₆₀ alkyl group. Detailed examples thereof are an ethenyl group, a propenyl group, and a butenyl group. A C₂-C₆₀ alkenylene group used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

A C₂-C₆₀ alkynyl group used herein refers to a hydrocarbon group formed by substituting at least one carbon triple bond in the middle or at the terminal of the C₂-C₆₀ alkyl group. Detailed examples thereof are an ethynyl group, and a propynyl group. A C₂-C₆₀ alkynylene group used herein refers to a divalent group having the same structure as the C₂-C₂ alkynyl group.

A C₃-C₁₀ cycloalkyl group used herein refers to a monovalent hydrocarbon monocyclic group having 3 to 10 carbon atoms. Detailed examples thereof are a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. A C₃-C₁₀ cycloalkylene group used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

A C₂-C₁₀ heterocycloalkyl group used herein refers to a monovalent monocyclic group having at least one hetero atom selected from N, O, P, and S as a ring-forming atom and 2 to 10 carbon atoms. Detailed examples thereof are a tetrahydrofuran group and a tetrahydrothiophenyl group. A C₂-C₁₀ heterocycloalkylene group used herein refers to a divalent group having the same structure as the C₂-C₁₀ heterocycloalkyl group.

A C₃-C₁₀ cycloalkenyl group used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one double bond in the ring thereof and does not have aromaticity. Detailed examples thereof are a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. A C₃-C₁₀ cycloalkenylene group used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

A C₂-C₁₀ heterocycloalkenyl group used herein refers to a monovalent monocyclic group that has at least one hetero atom selected from N, O, P, and S as a ring-forming atom, 2 to 10 carbon atoms, and at least one double bond in its ring. Detailed examples of the C₂-C₁₀ heterocycloalkenyl group are a 2,3-dihydrofuran group and a 2,3-dihydrothiophenyl group. A C₂-C₁₀ heterocycloalkenylene group used herein refers to a divalent group having the same structure as the C₂-C₁₀ heterocycloalkenyl group.

A C₆-C₆₀ aryl group used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C₆-C₆₀ arylene group used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Detailed examples of the C₆-C₆₀ aryl group are a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

A C₂-C₆₀ heteroaryl group used herein refers to a monovalent group having a carbocyclic aromatic system that has at least one hetero atom selected from N, O, P, and S as a ring-forming atom, and 2 to 60 carbon atoms. A C₂-C₆₀ heteroarylene group used herein refers to a divalent group having a carbocyclic aromatic system that has at least one hetero atom selected from N, O, P, and S as a ring-forming atom, and 2 to 60 carbon atoms. Examples of the C₂-C₆₀ heteroaryl group are a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₂-C₂ heteroaryl group and the C₂-C₂ heteroarylene group each include two or more rings, the rings may be fused to each other.

A C₆-C₆₀ aryloxy group used herein indicates —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and a C₆-C₆₀ arylthio group indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

A monovalent non-aromatic condensed polycyclic group used herein refers to a monovalent group that has two or more rings condensed to each other, only carbon atoms (for example, the number of carbon atoms may be in a range of 8 to 60) as ring forming atoms, wherein the molecular structure as a whole is non-aromatic in the entire molecular

condensed polycyclic group is a fluorenyl group. A divalent non-aromatic condensed polycyclic group used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

A monovalent non-aromatic condensed heteropolycyclic group used herein refers to a monovalent group that has two or more rings condensed to each other, has a heteroatom selected from N, O, P, and S, other than carbon atoms (for example, the number of carbon atoms may be in a range of 2 to 60), as ring forming atoms, wherein the molecular structure as a whole is non-aromatic in the entire molecular structure. An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. A divalent non-aromatic condensed heteropolycyclic group used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

At least one of substituents of the substituted C₃-C₁₀ cycloalkylene group, the substituted C₂-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₂-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₂-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₂-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₂-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

cloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅) and —B(Q₂₆)(Q₂₇); and

—N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), and —B(Q₃₆)(Q₃₇), wherein

Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₇ may be each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazine group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

For example, at least one of substituents of the substituted C₃-C₁₀ cyclo alkylene group, the substituted C₂-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₂-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₂-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cyclo alkyl group, the substituted C₂-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₂-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazine group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentalenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoidolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isooxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perilenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoidolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isooxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoidolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isooxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, and an imidazopyridinyl group;

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoidolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isooxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, and an imidazopyridinyl group;

145

group, an isothiazolyl group, a benzothiazolyl group, an isooxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, and an imidazopyridinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spirofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoioxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isooxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and —N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), and —B(Q₃₆)(Q₃₇), wherein

Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇ and Q₃₁ to Q₃₇ may be each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spirofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoioxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a


146

benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isooxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group or an imidazopyridinyl group.

Hereinafter, a compound and an organic light-emitting device according to embodiments are described in detail with reference to Synthesis Example and Examples. However, the organic light-emitting device is not limited thereto. The wording “B was used instead of A” used in describing Synthesis Examples means that a molar equivalent of A was identical to a molar equivalent of B.

EXAMPLE

Synthesis Example 1: Synthesis of Compound 103




147

15 g (39.12 mmol) of Intermediate A, 18.18 g (46.94 mol) of Intermediate B, 1.075 g (1.17 mmol) of $\text{Pd}_2(\text{dba})_3$ (tris (dibenzylideneacetone)dipalladium(0)), 1.716 g (3.52 mmol) of $\text{P}(\text{t-Bu})_3$ (tri-tert-butylphosphine), and 4.887 g (50.86 mmol) of $\text{NaO}(\text{t-Bu})$ were placed in a flask, and then, 200 mL of xylene was added thereto, and in a nitrogen atmosphere, the resultant mixture was refluxed for 18 hours while stirring. The result was slowly added to 800 mL of methanol to produce a solid, which was then dried in vacuum. Then, the solid was dissolved in 200 mL of monochlorobenzene and recrystallized, followed by filtration and vacuum-drying, thereby obtaining 18.31 g (yield 68%) of Compound 103.

$^1\text{H-NMR}$ (300 MHz, CDCl_3): 9.35 (s, 1H); 9.08 (d, 1H); 8.99 (t, 1H); 8.24 (m, 4H); 8.20 (d, 1H); 8.08 (d, 1H); 8.04 (s, 1H); 7.98 (d, 1H); 8.86 (t, 1H); 7.69 (d, 1H); 7.62 (t, 2H); 7.57 (m, 3H); 7.49 (m, 6H); 7.38 (m, 4H); 7.28 (m, 3H).

Synthesis Example 2: Synthesis of Compound 104



148

15 g (39.12 mmol) of Intermediate A, 18.23 g (46.94 mol) of Intermediate C, 1.075 g (1.17 mmol) of $\text{Pd}_2(\text{dba})_3$ (tris (dibenzylideneacetone)dipalladium(0)), 1.716 g (3.52 mmol) of $\text{P}(\text{t-Bu})_3$ (tri-tert-butylphosphine), and 4.887 g (50.86 mmol) of $\text{NaO}(\text{t-Bu})$ were placed in a flask, and then, 200 mL of xylene was added thereto, and in a nitrogen atmosphere, the resultant mixture was refluxed for 18 hours while stirring. The result was slowly added to 800 mL of methanol to produce a solid, which was then dried in vacuum. Then, the solid was dissolved in 200 mL of monochlorobenzene and recrystallized, followed by filtration and vacuum-drying, thereby obtaining 16.10 g (yield 60%) of Compound 104.

HRMS calcd for $\text{C}_{48}\text{H}_{30}\text{N}_6$: m/z 690.2532. Found: 690.2533.

Evaluation Example 1: Thermal Characteristics Evaluation on Compounds 103 and 104

Thermal analysis was performed on Compounds 103 and 104 by using thermo gravimetric analysis (TGA) and differential scanning calorimetry (DSC) (N_2 atmosphere, temperature range: from room temperature to 800° C. (10° C./min)-TGA, from room temperature to 450° C.-DSC, Pan Type: Pt Pan in disposable Al Pan(TGA), and disposable Al pan(DSC)), and results thereof are shown in Table 2.

TABLE 2

Compound No.	Td5	Tg	Tm	Ts
Compound 103	479	168.40	n/a	n/a
Compound 104	470	165.21	n/a	n/a

Referring to Table 2, it was confirmed that Compounds 103 and 104 have excellent thermal stability.

Example 1

An ITO glass substrate was cut to a size of 50 mm×50 mm×0.5 mm, sonicated in acetone isopropyl alcohol and pure water, each for 15 minutes, and then, washed by exposure to UV ozone for 30 minutes.

Then, m-MTDATA was deposited on an ITO electrode (anode) of the glass substrate at a deposition speed of 1 Å/sec to form a hole injection layer having a thickness of 600 Å, and then, α -NPD was deposited on the hole injection layer at a deposition speed of 1 Å/sec to form a hole transport layer having a thickness of 300 Å. $\text{Ir}(\text{ppy})_3$ (dopant) and Compound 103 (host) were co-deposited on the hole transport layer at a deposition speed 0.1 Å/sec and a deposition speed of 1 Å/sec, respectively, to form an emission layer having a thickness of 400 Å.

BALq was deposited on the emission layer at a deposition speed of 1 Å/sec to form a hole blocking layer having a thickness of 50 Å, and Alq_3 was deposited on the hole blocking layer to form an electron transport layer having a thickness of 300 Å, and then, LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and then, Al was vacuum deposited on the electron injection layer to form a second electrode (cathode) having a thickness of 1,200 Å, thereby completing manufacturing of an organic light-emitting device having a structure of ITO/m-MTDATA (600 Å)/ α -NPD (300 Å)/Compound 103+10% ($\text{Ir}(\text{ppy})_3$) (400 Å)/ BALq (50 Å)/ Alq_3 (300 Å)/ LiF (10 Å)/ Al (1,200 Å).

149

Example 2

An organic light-emitting device having the structure of ITO/m-MTDATA (600 Å)/α-NPD (300 Å)/Compound 104+ 10% (Ir(ppy)₃) (400 Å)/Balq (50 Å)/Alq₃ (300 Å)/LiF (10 Å)/Al (1,200 Å) was manufactured in the same manner as in Example 1, except that in forming an emission layer, Compound 104 was used instead of Compound 103.

Comparative Example 1

An organic light-emitting device having the structure of ITO/m-MTDATA (600 Å)/α-NPD (300 Å)/CBP+10% (Ir(ppy)₃) (400 Å)/Balq (50 Å)/Alq₃ (300 Å)/LiF (10 Å)/Al (1,200 Å) was manufactured in the same manner as in Example 1, except that in forming an emission layer, CBP was used instead of Compound 103.

Evaluation Example 2: Evaluation on Characteristics of an Organic Light-Emitting Device

Characteristics of the organic light-emitting devices manufactured according to Examples 1 to 2 and Comparative Example 1 were evaluated according to the following methods, and results thereof are shown in Table 3.

(1) Change in Current Density According to Voltage

Regarding the manufactured organic light-emitting devices, a current flowing in a unit device was measured by using a current-voltage meter while a voltage was raised from -5 Volts (V) to 10 V, and the measured current value was divided by an area.

(2) Change in Brightness According to Voltage

Regarding the manufactured organic light-emitting devices, brightness was measured by using Minolta Cs-1000A while a voltage was raised from -5 V to 10 V.

(3) Luminescence Efficiency

Current efficiency (candelas per ampere, cd/A) was measured at the same current density (10 milliamperes per square centimeter, mA/cm²) by using brightness, current density, and voltage measured according to (1) and (2).

TABLE 3

Brightness (1,000 cd/m ²)	Host	Dopant	Driving Voltage Voltage (V)	Current efficiency (cd/A)	Power Efficiency (lm/W)
Example 1	Compound 103	Ir(ppy) ₃	5.8	31.5	17.1
Example 2	Compound 104	Ir(ppy) ₃	5.3	33.0	19.6
Comparative Example 1	CBP	Ir(ppy) ₃	6.5	29.0	14.0

Referring to Table 3, it was confirmed that the organic light-emitting devices manufactured according to Examples 1 and 2 have lower driving voltage, higher efficiency, and higher brightness than the organic light-emitting devices manufactured according to Comparative Example 1.

The condensed cyclic compound according to embodiments has excellent electric characteristics and thermal stability. Accordingly, an organic light-emitting device including the condensed cyclic compound may have a low driving voltage, high efficiency, high brightness, and a long lifespan.

It should be understood that the exemplary embodiments described therein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of



150

features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

While one or more embodiments have been described with reference to the FIGURES, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present disclosure as defined by the following claims.

What is claimed is:

1. A condensed cyclic compound represented by Formulae 1A or 1B:



wherein in Formulae 1A and 1B,

Ring A₁ in Formulae 1A and 1B is represented by Formula 1C;

Ring B₁ in Formulae 1A and 1B is a C₆-C₂₀ aromatic ring; X₂₁ is selected from N-[(L₂₁)_{a21}-(R₂₁)_{b21}], S, O, S(=O), S(=O)₂, C(R₂₂)(R₂₃), and Si(R₂₂)(R₂₃);

X₁₁ is N or C-[(L₁₁)_{a11}-(R₁₁)_{b11}];

X₁₂ is N or C-[(L₁₂)_{a12}-(R₁₂)_{b12}];

X₁₃ is N or C-[(L₁₃)_{a13}-(R₁₃)_{b13}];

X₁₄ is N or C-[(L₁₄)_{a14}-(R₁₄)_{b14}]; provided that

at least one selected from X₁₁ to X₁₄ is N;

L₁ to L₃, L₁₁ to L₁₄, and L₂₁ are each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₂-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

a₁ to a₃, a₁₁ to a₁₄, and a₂₁ are each independently an integer selected from 0 to 5;

R₁ to R₃, R₁₁ to R₁₄, and R₂₁ to R₂₃ are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a substituted or

151

unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₂-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), and —B(Q₆)(Q₇), provided that, when Formula 1C is a part of Formula 1B, at least one of R₂₂ and R₂₃ in Formula 1C is not hydrogen;

b1 to b3, b11 to b14, and b21 are each independently an integer selected from 1 to 5;

c1 and c2 are each independently an integer selected from 1 to 4;

at least one of substituents of the substituted C₃-C₁₀ cycloalkylene group, the substituted C₂-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₂-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₂-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₂-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₂-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

152

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅) and —B(Q₂₆)(Q₂₇); and —N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), and —B(Q₃₆)(Q₃₇),

wherein Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₇ are each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₂-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

2. The condensed cyclic compound of claim 1, wherein Ring B₁ in Formulae 1A and 1B is a benzene or a naphthalene.

3. The condensed cyclic compound of claim 1, wherein L₁ to L₃, L₁₁ to L₁₄, and L₂₁ are each independently selected from

a phenylene group, a pentalenylene group, an indenylene group, a naphthalenylene group, an azulenenylene group, a heptalenylene group, an indacenylene group, an acenaphthalenylene group, a fluorenenylene group, a spiro-fluorenenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pyrrolylene group, an imidazolylene group, a pyrazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene

153

group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylenegroup, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzooxazolylenegroup, a benzoimidazolylenegroup, a furanylenegroup, a benzofuranylenegroup, a thiophenylene group, a benzothiophenylene group, a thiazolylenegroup, an isothiazolylenegroup, a benzothiazolylenegroup, an isoxazolylenegroup, an oxazolylenegroup, a triazolylenegroup, a tetrazolylenegroup, a oxadiazolylenegroup, a triazinylene group, a dibenzofuranylenegroup, a dibenzothiophenylene group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinylene group, and an imidazopyridinylene group; and


a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylenegroup, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylenegroup, a spiro-fluorenylenegroup, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenegroup, a picenylene group, a perylenylene group, a pentaphenylenegroup, a hexacenylene group, a pyrrolylenegroup, an imidazolylenegroup, a pyrazolylenegroup, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylenegroup, an indolylenegroup, an indazolylenegroup, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylenegroup, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzooxazolylenegroup, a benzoimidazolylenegroup, a furanylenegroup, a benzofuranylenegroup, a thiophenylene group, a benzothiophenylene group, a thiazolylenegroup, an isothiazolylenegroup, a benzothiazolylenegroup, an isoxazolylenegroup, an oxazolylenegroup, a triazolylenegroup, a tetrazolylenegroup, a oxadiazolylenegroup, a triazinylene group, a dibenzofuranylenegroup, a dibenzothiophenylene group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinylene group, and an imidazopyridinylene group, each substituted with at least one of a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a phenyl group substituted with another phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a quinoxalinyl group, a carbazolyl group, a phenyl group-substituted carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a phenyl group-substituted

154


benzocarbazolyl group, a phenyl group-substituted dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, and —Si(Q₃)(Q₃₄)(Q₃₅), wherein Q₃₃ to Q₃₅ are each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, or an imidazopyridinyl group.

4. The condensed cyclic compound of claim 1, wherein L₁ to L₃, L₁₁ to L₁₄, and L₂₁ are each independently selected from Formulae 2-1 to 2-34:


Formula 2-1




Formula 2-2




Formula 2-3




Formula 2-4



Formula 2-5














Formula 2-6



155

-continued



Formula 2-7

5

Formula 2-8

10

Formula 2-9

20

Formula 2-10

25

Formula 2-11

30

Formula 2-12

35

Formula 2-13

40

Formula 2-14

45

Formula 2-15

50

Formula 2-16

55











Formula 2-17

60

65

156

-continued



Formula 2-18

Formula 2-19

Formula 2-20

Formula 2-21

Formula 2-22

Formula 2-23

Formula 2-24


Formula 2-25

Formula 2-26

Formula 2-27

157

-continued



wherein in Formulae 2-1 to 2-34,

Y_1 is O, S, $S(=O)$, $S(=O)_2$, $C(Z_3)(Z_4)$, $N(Z_5)$, or $Si(Z_6)(Z_7)$;

Z_1 to Z_7 are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a phenyl group substituted with another phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group,

158

Formula 2-28

5

Formula 2-29

10

Formula 2-30

15

Formula 2-31

25

Formula 2-32

30

Formula 2-33

40

Formula 2-34

45

50

55

a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a quinoxalinyl group, a carbazolyl group, a phenyl group-substituted carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a phenyl group-substituted benzocarbazolyl group, a phenyl group-substituted dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, and $-Si(Q_{33})(Q_{34})(Q_{35})$;

wherein Q_{33} to Q_{35} are each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, or an imidazopyridinyl group;

d_1 is an integer of 1 to 4;

d_2 is an integer of 1 to 3;

d_3 is an integer of 1 to 6;

d_4 is an integer of 1 to 8;


d_5 is an integer of 1 or 2;

d_6 is an integer of 1 to 5; and


* and *' indicates a binding site to a neighboring atom.

5. The condensed cyclic compound of claim 1, wherein L_1 to L_3 , L_{11} to L_{14} , and L_{21} are each independently selected from Formulae 3-1 to 3-39:


Formula 3-1




Formula 3-2




Formula 3-3



Formula 3-4











Formula 3-5



159

-continued



160

-continued

Formula 3-6

5

Formula 3-7

10

Formula 3-8

15

Formula 3-9

25

Formula 3-10

30

Formula 3-11

40









Formula 3-12

55

Formula 3-13

60

65



Formula 3-14

Formula 3-15

Formula 3-16

Formula 3-17

Formula 3-18







Formula 3-19

Formula 3-20

Formula 3-21

161


-continued

**162**

-continued

Formula 3-22


5



10

Formula 3-23


15



20

Formula 3-24


25



30

Formula 3-25

35




40

45

Formula 3-26


50



55

Formula 3-27

60



65

Formula 3-28

Formula 3-29

Formula 3-30







Formula 3-31

Formula 3-32

Formula 3-33

163

-continued



6. The condensed cyclic compound of claim 1, wherein a₁ to a₃, all to a₁₄, and a₁₂ are each independently 0, 1, or 2.

7. The condensed cyclic compound of claim 1, wherein R₁ to R₃, R₁₁ to R₁₄, and R₂₁ to R₂₃ are each independently selected from


a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from a deuterium,


164

—F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, and a phosphoric acid or a salt thereof;


a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnoliny group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolylene group, a triazinyl group, a dibenzofuran group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzofuopyrimidinyl group, a benzothiophenopyrimidinyl group, a group represented by



a group represented by




and a group represented by




165


a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolylene group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzofuropyridinyl group, a benzothiophenopyridinyl group, a benzofuropyrimidinyl group, a benzothiophenopyrimidinyl group, a group represented by



a group represented by



and a group represented by



each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a

166

nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_2 - C_{20} alkenyl group, a C_2 - C_{20} alkynyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a phenyl group substituted with another phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a quinoxalinyl group, a carbazolyl group, a phenyl group-substituted carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a phenyl group-substituted benzocarbazolyl group, a phenyl group-substituted dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, and $-\text{Si}(\text{Q}_{33})(\text{Q}_{34})(\text{Q}_{35})$; and

$-\text{Si}(\text{Q}_3)(\text{Q}_4)(\text{Q}_5)$,

wherein Q_3 to Q_5 and Q_{33} to Q_{35} are each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, or an imidazopyridinyl group,

provided that, when Formula 1C is a part of Formula 1B, at least one of R_{22} and R_{23} in Formula 1C is not hydrogen.

8. The condensed cyclic compound of claim 1, wherein R_1 to R_3 , R_{11} to R_{14} , and R_{21} to R_{23} are each independently selected from


a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, and a phosphoric acid or a salt thereof; and

one of Formulae 4-1 to 4-49; and











$-\text{Si}(\text{Q}_3)(\text{Q}_4)(\text{Q}_5)$:

Formula 4-1



167


-continued

**168**

-continued


Formula 4-2

5




Formula 4-3

10




Formula 4-4

15



20

Formula 4-5




25

30


Formula 4-6

35




Formula 4-7

40




Formula 4-8

45




Formula 4-9

50




Formula 4-10

55




60

Formula 4-11



65



Formula 4-12

Formula 4-13

Formula 4-14

Formula 4-15

Formula 4-16

Formula 4-17

Formula 4-18

Formula 4-19

Formula 4-20










Formula 4-21

Formula 4-22

Formula 4-23

169

-continued



170

-continued

Formula 4-24

5

Formula 4-25

10

Formula 4-26

15

20

Formula 4-27

25

Formula 4-28

30

Formula 4-29

40

Formula 4-30

45

50








Formula 4-31

55

Formula 4-32

60

65



Formula 4-33

Formula 4-34

Formula 4-35

Formula 4-36


Formula 4-37

Formula 4-38

Formula 4-39

171

-continued



172

wherein in Formulae 4-1 to 4-49,

Y₃₁ is O, S, C(Z₃₃)(Z₃₄), N(Z₃₅), or Si(Z₃₆)(Z₃₇);

Z₃₁ to Z₃₇ are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a phenyl group substituted with another phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a quinoxalinyl group, a carbazolyl group, a phenyl group-substituted carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a phenyl group-substituted benzocarbazolyl group, a phenyl group-substituted dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, and —Si(Q₃₃)(Q₃₄)(Q₃₅);

Q₃ to Q₅ and Q₃₃ to Q₃₅ are each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, or an imidazopyridinyl group, provided that, when Formula 1C is a part of Formula 1B, at least one of R₂₂ and R₂₃ in Formula 1C is not hydrogen;

e1 is an integer of 1 to 5;
e2 is an integer of 1 to 7;
e3 is an integer of 1 to 3;
e4 is an integer of 1 to 4;
e5 is an integer of 1 or 2;
e6 is an integer of 1 to 6; and








* indicates a binding site to a neighboring atom.

9. The condensed cyclic compound of claim 1, wherein R₁ to R₃, R₁₁ to R₁₄, and R₂₁ to R₂₃ are each independently selected from

a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;
a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid

173

or a salt thereof, a sulfonic acid or a salt thereof, and a phosphoric acid or a salt thereof; and
any one of Formulae 5-1 to 5-77:

**174**

-continued

Formula 5-8

5

Formula 5-1

10

Formula 5-2

15

Formula 5-3

20

Formula 5-4

25

30

35

Formula 5-5

40

45

Formula 5-6










50

55

Formula 5-7

60

65



Formula 5-9

Formula 5-10

Formula 5-11

Formula 5-12

Formula 5-13








Formula 5-14

Formula 5-15

Formula 5-16

175

-continued



176

-continued

Formula 5-17

5

Formula 5-18

10

Formula 5-19

15

Formula 5-20

25

Formula 5-21

35

Formula 5-22










45

Formula 5-23

55

60

65



Formula 5-24

Formula 5-25

Formula 5-26

Formula 5-27

Formula 5-28

Formula 5-29









Formula 5-30

Formula 5-31

Formula 5-32

177


-continued

**178**

-continued


Formula 5-33

5



Formula 5-34


10



15

Formula 5-35


20



25

Formula 5-36


30



35

Formula 5-37


40



45


Formula 5-38

50



Formula 5-39


55



60

Formula 5-40

65



Formula 5-41

Formula 5-42

Formula 5-43

Formula 5-44

Formula 5-45








Formula 5-46

Formula 5-47








Formula 5-48

179

-continued

**180**

-continued



Formula 5-49

5

Formula 5-50

10

15

Formula 5-51

20

25

Formula 5-52

30

Formula 5-53

35

40

Formula 5-54

45

50

55

Formula 5-55

60

65

Formula 5-56

Formula 5-57

Formula 5-58

Formula 5-59








Formula 5-60

Formula 5-61








Formula 5-62

181

-continued

**182**

-continued



Formula 5-63

5

Formula 5-64

10

15

Formula 5-65

20

25

Formula 5-66

30

35

Formula 5-67

40

45

Formula 5-68

50

55

Formula 5-69

60

65

Formula 5-70

Formula 5-71

Formula 5-72

Formula 5-73


Formula 5-74

Formula 5-75

Formula 5-76

183

-continued



Formula 5-77

provided that, when Formula 1C is a part of Formula 1B, at least one of R_{22} and R_{23} in Formula 1C is not hydrogen.

10. The condensed cyclic compound of claim 1, wherein R_1 , R_2 , R_{11} to R_{14} , R_{22} , and R_{23} are each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a phenanthrenyl group, a fluorenyl group, a chrysenyl group, a carbazolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, and a quinoxalinyl group,

provided that, when Formula 1C is a part of Formula 1B, at least one of R_{22} and R_{23} in Formula 1C is not hydrogen.


11. The condensed cyclic compound of claim 1, wherein R_3 and R_{21} are each independently selected from a substituted or unsubstituted C_6 - C_{30} aryl group, a substituted or unsubstituted C_2 - C_{30} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

12. The condensed cyclic compound of claim 1, wherein R_3 is a substituted or unsubstituted C_2 - C_{30} heteroaryl group or a substituted or unsubstituted monovalent non-aromatic hetero-condensed polycyclic group, each group containing at least one nitrogen atom as a ring-forming atom.


13. The condensed cyclic compound of claim 1, wherein R_3 and R_{21} are each independently selected from a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perilenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthridinyl group, a quinoxalinyl group, a quinazolinyl group, a cynolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoaxazolyl group, a benzoimidazolyl group, a furanyl group, a

184


benzofuranyl group, a thiophenyl group, a benzothio-phenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isooxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a group represented by



a group represented by




and a group represented by




and a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoaxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothio-phenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an

185


oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolylene group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a benzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzofuopyrimidinyl group, a benzothiophenopyridinyl group, a benzofuopyrimidinyl group, a benzothiophenopyrimidinyl group, a group represented by



a group represented by



and a group represented by



each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₂-C₂₀ alkenyl group, a C₂-C₂₀ alkynyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a phenyl group substituted with another phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a quinoxalinyl group, a carbazolyl group, a phenyl group-substituted carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a benzocarbazolyl group, a phenyl group-substituted benzocarbazolyl group, a phenyl group-substituted dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, and —Si(Q₃₃)(Q₃₄)(Q₃₅);


wherein Q₃₃ to Q₃₅ are each independently a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a

186


cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a benzocarbazolyl group, an imidazopyrimidinyl group, or an imidazopyridinyl group.

14. The condensed cyclic compound of claim 1, wherein the condensed cyclic compound is represented by one of Formulae 1A-1 to 1A-16 and 1B-1 to 1B-3:


Formula 1A-1




Formula 1A-2



Formula 1A-3




Formula 1A-4




187

-continued


Formula 1A-5




Formula 1A-6




Formula 1A-7



Formula 1A-8




Formula 1A-9




188

-continued


Formula 1A-10




Formula 1A-11




Formula 1A-12




Formula 1A-13



Formula 1A-14




Formula 1A-15




189

-continued


Formula 1A-16




Formula 1B-1



Formula 1B-2



Formula 1B-3




and

in Formulae 1A-1 to 1A-16 and 1B-1 to 1B-3, definitions of Ring A₁, L₁ to L₃, a₁ to a₃, R₁ to R₃, R₁₁ to R₁₄, b₁ to b₃, c₁, and c₂ are the same as in claim 1.


15. The condensed cyclic compound of claim 1, wherein the condensed cyclic compound is represented by one of Formulae 1A(1)-1 to 1A(1)-16:

Formula 1A(1)-1


**190**

-continued


Formula 1A(1)-2




Formula 1A(1)-3




Formula 1A(1)-4




Formula 1A(1)-5



Formula 1A(1)-6




Formula 1A(1)-7



191

-continued

Formula 1A(1)-8




5

10

15


Formula 1A(1)-9



20

25

Formula 1A(1)-10




30

35

40


Formula 1A(1)-11



45

50

Formula 1A(1)-12




60

65


192

-continued


Formula 1A(1)-13




Formula 1A(1)-14



Formula 1A(1)-15



Formula 1A(1)-16




definitions of X_{21} , L_1 to L_3 , $a1$ to $a3$, R_1 to R_3 , R_{11} to R_{14} , $b1$ to $b3$, and $c1$ and $c2$ in Formulae 1A(1)-1 to 1A(1)-16 are the same as in claim 1.

16. The condensed cyclic compound of claim 15, wherein R_3 is selected from


a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perilenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl

193


group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthridinyl group, a quinoxalinyl group, a quinazolinyl group, a cynolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isooxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a group represented by



a group represented by



and a group represented by




and


a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl

194


group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolylene group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzofuropyridinyl group, a benzothiophenopyridinyl group, a benzofuropyrimidinyl group, a benzothiophenopyrimidinyl group, a group represented by



a group represented by



and a group represented by





each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₂-C₂₀ alkenyl group, a C₂-C₂₀ alkynyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a phenyl group substituted with another phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a quinoxalinyl group, a carbazolyl group, a phenyl group-substituted carbazolyl group, a phenanthrolinyl

195

group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a phenyl group-substituted benzocarbazolyl group, a phenyl group-substituted dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, and $-\text{Si}(\text{Q}_{33})(\text{Q}_{34})(\text{Q}_{35})$;




wherein Q_{33} to Q_{35} are each independently a hydrogen, a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, a pyrenyl group, a phenanthrenyl group, a triphenylenyl group, a pyrenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, or an imidazopyridinyl group.

17. The condensed cyclic compound of claim 1, wherein the condensed cyclic compound is one of Compounds 1 to 200:






196




-continued



197
-continued



198
-continued






9

10

11

199

-continued

**200**

-continued

12

15

5

10

15

20

25

13

30

35

40

45

14




50

17

55





60

65



201

-continued



202

-continued

18

22

5

10

15

20

25

30

35

40

45






21

50

55






60

65



203

-continued

**204**

-continued

27

5

10

28

15

20

29

25

30

35

30

45

50

31

60





65

32

33






34

35







205

-continued



206

-continued



36

5

10

15

37

20

25

38

30

35

40

39

45

50

55

40

60

65

41





42

43





44

207

-continued




**208**

-continued







209

-continued





**210**

-continued



211

-continued

**212**

-continued

60

5

10

61 15

20

25

62 30

35

40

45


63 50

55


60

65


64




65



66







67



213

-continued

**214**

-continued

68

72

5

10

69

15

20

25

70

30

35

40

45






71

50

55






60

65



215

-continued

**216**

-continued

77

5

10

78 15

20

25

79

30

35

80 40

45

50


81

55


60

65


82




83



84







85






217

-continued





**218**

-continued







219

-continued




**220**

-continued



221

-continued

**222**

-continued

101

5

10

15

20

102

25

30

35

40

103 45


50

55


60

65


104



105







106



223

-continued

**224**

-continued

107

111

5

10

15

108

20

25

112

30

109

35

40

45

50




110

113

55


60

65



225

-continued



114

5

10

15

20

115

25

30

35

40

45



116

50


55

60


65

**226**


-continued




117



118




119



120

227

-continued



121

228


-continued

5


10

15

20



124




122 25


30

35

40



125




123

50

55

60




65



126

229

-continued

**230**

-continued

127

130

5

10

15

20

128

25

30

35

40

45

129

50

131


132

133

55





60

65







231

-continued





**232**

-continued







233

-continued






**234**

-continued







235

-continued


**236**

-continued




237

-continued





**238**

-continued







239

-continued





**240**

-continued







241

-continued





**242**

-continued






243

-continued




**244**

-continued







245

-continued



**246**

-continued




247

-continued

**248**

-continued

**18.** An organic light-emitting device comprising:

a first electrode;

a second electrode; and

an organic layer disposed between the first electrode and the second electrode,

wherein the organic layer comprises an emission layer, and further comprises at least one of the condensed cyclic compound of claim 1.

19. The organic light-emitting device of claim 18, wherein the first electrode is an anode, the second electrode is a cathode, and the organic layer comprises

i) a hole transport region disposed between the first electrode and the emission layer, wherein the hole transport region comprises at least one selected from a hole injection layer, a hole transport layer, and an electron blocking layer, and

ii) an electron transport region disposed between the emission layer and the second electrode, wherein the electron transport region comprises at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

20. The organic light-emitting device of claim 18, wherein the emission layer comprises at least one condensed cyclic compound of claim 1.

* * * * *

专利名称(译)	缩合环状化合物和包括其的有机发光器件		
公开(公告)号	US10040794	公开(公告)日	2018-08-07
申请号	US14/661619	申请日	2015-03-18
[标]申请(专利权)人(译)	三星电子株式会社		
申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD. 三星SDI CO. , LTD		
当前申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD. 三星SDI CO. , LTD.		
[标]发明人	HWANG KYUYOUNG KWON OHYUN KIM SANGMO SEO JOOHEE LEE SEUNGJAE CHOI BYOUNGKI CHOI HYEONHO		
发明人	HWANG, KYUYOUNG KWON, OHYUN KIM, SANGMO SEO, JOOHEE LEE, SEUNGJAE CHOI, BYOUNGKI CHOI, HYEONHO		
IPC分类号	H01L51/00 C07D471/14 H01L51/50 C07D471/04 C07D471/22 C07F7/08 C07D491/22 C07D495/14 C07D519/00 C07D491/147		
CPC分类号	C07D471/14 C07D471/22 C07D491/147 C07D491/22 C07D495/14 C07D519/00 C07F7/0816 H01L51/ /0067 H01L51/0072 H01L51/5012 C07D471/04 H01L51/5096 H01L51/5016 H01L51/5056 H01L51/ /5072 H01L51/5088 H01L51/5092 C09B1/00 C09B3/14 C09B23/148 C09B47/00 C09B57/00 C09B57/ /008 C09B57/02 C09B57/10		
代理机构(译)	康托科尔伯恩LLP		
审查员(译)	彭, 阔亮		
优先权	1020140054432 2014-05-07 KR		
其他公开文献	US20150325799A1		

摘要(译)

由式1A或1B表示的稠合环状化合物：其中在公式1A和1中B，组，环，取代基和变量在详细描述中定义。

