



US009123903B2

(12) **United States Patent**
Lin et al.

(10) **Patent No.:** **US 9,123,903 B2**
(45) **Date of Patent:** ***Sep. 1, 2015**

(54) **DIBENZOTHIOPHENE-CONTAINING MATERIALS IN PHOSPHORESCENT LIGHT EMITTING DIODES**

(71) Applicant: **Universal Display Corporation**, Ewing, NJ (US)

(72) Inventors: **Chun Lin**, Yardley, PA (US); **Alexey Dyatkin**, Ambler, PA (US); **Zeinab Elshenawy**, Holland, PA (US); **Walter Yeager**, Yardley, PA (US)

(73) Assignee: **Universal Display Corporation**, Ewing, NJ (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 161 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **14/026,868**

(22) Filed: **Sep. 13, 2013**

(65) **Prior Publication Data**

US 2014/0008643 A1 Jan. 9, 2014

Related U.S. Application Data

(62) Division of application No. 13/186,204, filed on Jul. 19, 2011, now Pat. No. 8,580,402, which is a division of application No. 12/208,907, filed on Sep. 11, 2008, now Pat. No. 8,007,927.

(60) Provisional application No. 61/017,480, filed on Dec. 28, 2007.

(51) **Int. Cl.**
H01L 51/54 (2006.01)
H01L 51/00 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **H01L 51/0085** (2013.01); **C07D 209/86**

(2013.01); **C07D 235/18** (2013.01); **C07D 235/20** (2013.01); **C07D 333/76** (2013.01); **C07D 405/14** (2013.01); **C07D 409/10** (2013.01); **C07D 409/14** (2013.01); **C07D 413/10** (2013.01); **C07D 471/04** (2013.01);
(Continued)

(58) **Field of Classification Search**
None

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,769,292 A 9/1988 Tang et al.
5,061,569 A 10/1991 VanSlyke et al.
(Continued)

FOREIGN PATENT DOCUMENTS

EP 0650955 5/1995
EP 1725079 11/2006
(Continued)

OTHER PUBLICATIONS

Xu, et al., "Facile synthesis of novel monodisperse linear 3,9-linked oligocarbazoles," *Tetrahedron Letters* 46 (2005) p. 6883-6886.
(Continued)


Primary Examiner — Gregory Clark

(74) *Attorney, Agent, or Firm* — Duane Morris LLP

(57) **ABSTRACT**

An organic light emitting device that includes an anode, a cathode, an enhancement layer, and an emissive layer that includes homoleptic iridium complexes containing phenyl-imidazole ligands, which include at least one fused substituent. The enhancement layer also includes a new dibenzothiophene and dibenzofuran-containing compound that is useful as a material in an enhancement layer.

6 Claims, 14 Drawing Sheets



- (51) **Int. Cl.**
C07D 209/86 (2006.01)
C07D 235/18 (2006.01)
C07D 235/20 (2006.01)
C07D 333/76 (2006.01)
C07D 405/14 (2006.01)
C07D 409/10 (2006.01)
C07D 409/14 (2006.01)
C07D 413/10 (2006.01)
C07D 471/04 (2006.01)
C07D 487/04 (2006.01)
C07F 5/02 (2006.01)
C07F 7/08 (2006.01)
- (52) **U.S. Cl.**
 CPC *C07D 487/04* (2013.01); *C07F 5/027*
 (2013.01); *C07F 7/0814* (2013.01); *H01L*
51/0071 (2013.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,247,190 A 9/1993 Friend et al.
 5,703,436 A 12/1997 Forrest et al.
 5,707,745 A 1/1998 Forrest et al.
 5,834,893 A 11/1998 Bulovic et al.
 5,844,363 A 12/1998 Gu et al.
 6,013,982 A 1/2000 Thompson et al.
 6,087,196 A 7/2000 Sturm et al.
 6,091,195 A 7/2000 Forrest et al.
 6,097,147 A 8/2000 Baldo et al.
 6,294,398 B1 9/2001 Kim et al.
 6,303,238 B1 10/2001 Thompson et al.
 6,337,102 B1 1/2002 Forrest et al.
 6,468,819 B1 10/2002 Kim et al.
 6,528,187 B1 3/2003 Okada
 6,687,266 B1 2/2004 Ma et al.
 6,835,469 B2 12/2004 Kwong et al.
 6,921,915 B2 7/2005 Takiguchi et al.
 7,087,321 B2 8/2006 Kwong et al.
 7,090,928 B2 8/2006 Thompson et al.
 7,154,114 B2 12/2006 Brooks et al.
 7,250,226 B2 7/2007 Tokito et al.
 7,279,704 B2 10/2007 Walters et al.
 7,329,722 B2 2/2008 Vaitkeviciene et al.
 7,332,232 B2 2/2008 Ma et al.
 7,338,722 B2 3/2008 Thompson et al.
 7,393,599 B2 7/2008 Thompson et al.
 7,396,598 B2 7/2008 Takeuchi et al.
 7,431,968 B1 10/2008 Stein et al.
 7,445,855 B2 11/2008 Mackenzie et al.
 7,504,769 B2 3/2009 Rado et al.
 7,534,505 B2 5/2009 Lin et al.
 7,651,791 B2 1/2010 Nakano et al.
 7,989,644 B2 8/2011 Tanabe et al.
 8,007,927 B2 8/2011 Lin et al.
 8,221,905 B2 7/2012 Lin et al.
 8,367,850 B2 2/2013 Ma et al.
 2002/0034656 A1 3/2002 Thompson et al.
 2002/0134984 A1 9/2002 Igarashi
 2002/0158242 A1 10/2002 Son et al.
 2003/0138657 A1 7/2003 Li et al.
 2003/0151042 A1 8/2003 Hueschen
 2003/0152802 A1 8/2003 Tsuboyama et al.
 2003/0175553 A1 9/2003 Thompson et al.
 2003/0230980 A1 12/2003 Forrest et al.
 2004/0036077 A1 2/2004 Ise
 2004/0137267 A1 7/2004 Igarashi et al.
 2004/0137268 A1 7/2004 Igarashi et al.
 2004/0174116 A1 9/2004 Lu et al.
 2005/0025993 A1 2/2005 Thompson et al.
 2005/0112407 A1 5/2005 Ogasawara et al.
 2005/0238919 A1 10/2005 Ogasawara
 2005/0244673 A1 11/2005 Satoh et al.
 2005/0260441 A1 11/2005 Thompson et al.

2005/0260449 A1 11/2005 Walters et al.
 2006/0008670 A1 1/2006 Lin et al.
 2006/0202194 A1 9/2006 Jeong et al.
 2006/0240279 A1 10/2006 Adamovich et al.
 2006/0251923 A1 11/2006 Lin et al.
 2006/0263635 A1 11/2006 Ise
 2006/0280965 A1 12/2006 Kwong et al.
 2007/0075631 A1 4/2007 Tung et al.
 2007/0190359 A1 8/2007 Knowles et al.
 2007/0224446 A1 9/2007 Nakano et al.
 2007/0278938 A1 12/2007 Yabunouchi et al.
 2008/0015355 A1 1/2008 Schafer et al.
 2008/0018221 A1 1/2008 Egen et al.
 2008/0106190 A1 5/2008 Yabunouchi et al.
 2008/0124572 A1 5/2008 Mizuki et al.
 2008/0220265 A1 9/2008 Xia et al.
 2008/0297033 A1 12/2008 Knowles et al.
 2009/0008605 A1 1/2009 Kawamura et al.
 2009/0009065 A1 1/2009 Nishimura et al.
 2009/0017330 A1 1/2009 Iwakuma et al.
 2009/0030202 A1 1/2009 Iwakuma et al.
 2009/0039776 A1 2/2009 Yamada et al.
 2009/0045730 A1 2/2009 Nishimura et al.
 2009/0045731 A1 2/2009 Nishimura et al.
 2009/0101870 A1 4/2009 Prakash et al.
 2009/0108737 A1 4/2009 Kwong et al.
 2009/0115316 A1 5/2009 Zheng et al.
 2009/0153034 A1 6/2009 Lin et al.
 2009/0165846 A1 7/2009 Johannes et al.
 2009/0167162 A1 7/2009 Lin et al.
 2009/0179554 A1 7/2009 Kuma et al.
 2011/0057559 A1 3/2011 Xia et al.
 2011/0084599 A1 4/2011 Brooks et al.
 2011/0278552 A1 11/2011 Numata
 2013/0020565 A1 1/2013 Numata
 2013/0175510 A1 7/2013 Ma et al.

FOREIGN PATENT DOCUMENTS

EP 2034538 3/2009
 JP 62283341 12/1987
 JP 07-053950 2/1995
 JP 200511610 1/2005
 JP 2007123392 5/2007
 JP 2007126403 5/2007
 JP 2007254297 10/2007
 JP 2008074939 4/2008
 JP 2008078362 4/2008
 WO 2001039234 5/2001
 WO 2002002714 1/2002
 WO 200215645 2/2002
 WO 2003040257 5/2003
 WO 2003060956 7/2003
 WO 2004093207 10/2004
 WO 2004107822 12/2004
 WO 2005014551 2/2005
 WO 2005019373 3/2005
 WO 2005030900 4/2005
 WO 2005089025 9/2005
 WO 2005123873 12/2005
 WO 2006009024 1/2006
 WO 2006056418 6/2006
 WO 2006072002 7/2006
 WO 2006082742 8/2006
 WO 2007/029798 9/2006
 WO 2006098120 9/2006
 WO 2006100298 9/2006
 WO 2006103874 10/2006
 WO 2006114966 11/2006
 WO 2006/12880 12/2006
 WO 2006132173 12/2006
 WO 2007002683 1/2007
 WO 2007004380 1/2007
 WO 2007/069569 6/2007
 WO 2007063754 6/2007
 WO 2007063796 6/2007
 WO 2007/077810 7/2007
 WO 2007/238500 9/2007
 WO 2008056746 5/2008

(56)

References Cited

FOREIGN PATENT DOCUMENTS

WO	2008101842	8/2008
WO	2008132085	11/2008
WO	2009000673	12/2008
WO	2009/008099	1/2009
WO	2009/008100	1/2009
WO	2009003898	1/2009
WO	2009008311	1/2009
WO	2009018009	2/2009
WO	2009/030981	3/2009
WO	2009050290	4/2009
WO	2009/060742	5/2009
WO	2009021126	5/2009
WO	2009062578	5/2009
WO	2009063833	5/2009
WO	2009066778	5/2009
WO	2009066779	5/2009
WO	2009086028	7/2009
WO	2009100991	8/2009

OTHER PUBLICATIONS

Tsai, et al., "3-(9-Carbazolyl)carbazoles and 3,6-Di(9-carbazolyl)carbazoles as effective host materials for efficient blue organic electrophosphorescence" *Adv. Mater.* 2007, 19, 862-866.

Adachi, Chihaya et al., "Organic Electroluminescent Device Having a Hole Conductor as an Emitting Layer," *Appl. Phys. Lett.*, 55(15): 1489-1491 (1989).

Adachi, Chihaya et al., *Appl. Phys.*, "Neary 100% Internal Phosphorescence Efficiency in an Organic Light Emitting Device," *J. Appl. Phys.*, 90(10): 5048-5051 (2001).

Adachi, Chihaya et al., "High-Efficiency Red Electrophosphorescence Devices," *Appl. Phys. Lett.*, 78(11):1622-1624.

Aonuma, Masaki et al., "Material Design of Hole Transport Materials Capable of Thick-Film Formation in Organic Light Emitting Diodes," *Appl. Phys. Lett.*, 90:183503-1-183503-3.

Baldo et al., Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices, *Nature*, vol. 395, 151-154, (1998).

Baldo et al., Very high-efficiency green organic light-emitting devices based on electrophosphorescence, *Appl. Phys. Lett.*, vol. 75, No. 3, 4-6 (1999).

Gao, Zhigang et al., "Bright-Blue Electroluminescence From a Silyl-Substituted ter-(phenylene-vinylene) derivative," *Appl. Phys. Lett.*, 74(6): 865-867 (1999).

Guo, Tzung-Fang et al., "Highly Efficient Electrophosphorescent Polymer Light-Emitting Devices," *Organic Electronics*, 115-20 (2000).

Hamada, Yuji et al., "High Luminance in Organic Electroluminescent Devices with Bis(10-hydroxybenzo[h]quinolinato)" *Chem. Lett.*, 905-906 (1993).

Holmes, R.J. et al., "Blue Organic Electrophosphorescence Using Exothermic Host-Guest Energy Transfer," *Appl. Phys. Lett.*, 82(15):2422-2424 (2003).

Hu, Nan-Xing et al., "Novel High Tg Hole-Transport Molecules Based on Indolo[3,2-b]carbazoles for Organic Light-Emitting Devices," *Synthetic Metals*, 111-112:421-424 (2000).

Huang, Jinsona et al., "Highly Efficient Red-Emission Polymer Phosphorescent Light-Emitting Diodes Based on Two Novel Tris(1-phenylisoquinolinato-C2,N)iridium(III) Derivatives," *Adv. Mater.*, 19:739-743 (2007).

Huang, Wei-Sheng et al., "Highly Phosphorescent Bis-Cyclometalated Iridium Complexes Containing Benzoimidazole-Based Ligands," *Chem. Mater.*, 16(12):2480-2488 (2004).

Hung, L.S. et al., "Anode Modification in Organic Light-Emitting Diodes by Low-Frequency Plasma Polymerization of CHF₃," *Appl. Phys. Lett.*, 78(5):673-675 (2001).

Kai, Masarnichi and Tokito, Shizuo, "Highly Efficient Phosphorescence From Organic Light-Emitting Devices with an Exciton-Block Layer," *Appl. Phys. Lett.*, 79(2):156-158 (2001).

Ikeda, Hisao et al., "P-185 Low-Drive-Voltage OLEDs with a Buffer Layer Having Molybdenum Oxide," *SID Symposium Digest*, 37 923-926 (2006).

Inada, Hiroshi and Shirota, Yasuhiko, "1,3,5-Tris[4-(diphenylamino)phenyl]benzene and its Methylsubstituted Derivatives as a Novel Class of Amorphous Molecular Materials," *J. Mater. Chem.*, 3(3):319-320 (1993).

Kanno, Hiroshi et al., "Highly Efficient and Stable Red Phosphorescent Organic Light-Emitting Device Using bis[2-(2-benzothiazoyl)phenolato]zinc(II) as host material," *Appl. Phys. Lett.*, 90:123509-1-123509-3 (2007).

Kido J. Junji et al., 1,2,4-Triazole Derivative as an Electron Transport Layer in Organic Electroluminescent Devices, *Jpn. J. Appl. Phys.*, 32:L917-L920 (1993).

Kuwabara, Yoshiyuki et al., "Thermally Stable Multilayered Organic Electroluminescent Devices Using Novel Starburst Molecules, 4,4',4"-Tri(N-carbazolyl)triphenylamine (TCTA) and 4,4',4"-Tris(3-methylphenylphenyl-amino) triphenylamine (m-MTDATA), as Hole-Transport Materials," *Adv. Mater.*, 6(9):677-679 (1994).

Kwong, Raymond C. et al., "High Operational Stability of Electrophosphorescent Devices," *Appl. Phys. Lett.*, 81(1) 162-164 (2002).

Lamansky, Sergey et al., "Synthesis and Characterization of Phosphorescent Cyclometalated Iridium Complexes," *Inorg. Chem.*, 40(7):1704-1711 (2001).

Lee, Chang-Lyoul et al., "Polymer Phosphorescent Light-Emitting Devices Doped with Tris(2-phenylpyridine) Iridium as a Triplet Emitter," *Appl. Phys. Lett.*, 77(15):2280-2282 (2000).

Lo, Shih-Chun et al., "Blue Phosphorescence from Iridium(III) Complexes at Room Temperature," *Chem. Mater.*, 18 (21):5119-5129 (2006).

Ma, Yuguang et al., "Triplet Luminescent Dinuclear-Gold(I) Complex-Based Light-Emitting Diodes with Low Turn-On voltage," *Appl. Phys. Lett.*, 74(10):1361-1363 (1999).

Mi, Bao-Xiu et al., "Thermally Stable Hole-Transporting Material for Organic Light-Emitting Diode an Isoindole Derivative," *Chem. Mater.*, 15(16):3148-3151 (2003).

Nishida, Jun-ichi et al., "Preparation, Characterization, and Electroluminescence Characteristics of α -Diimine-type Platinum(II) Complexes with Perfluorinated Phenyl Groups as Ligands," *Chem. Lett.*, 34(4): 592-593 (2005).

Niu, Yu-Hua et al., "Highly Efficient Electrophosphorescent Devices with Saturated Red Emission from a Neutral Osmium Complex," *Chem. Mater.*, 17(13):3532-3536 (2005).

Noda, Tetsuya and Shirota, Yasuhiko, "5,5'-Bis(dimesitylboryl)-2,2'-bithiophene and 5,5"-Bis(dimesitylboryl)-2,2'5',2"-terthiophene as a Novel Family of Electron-Transporting Amorphous Molecular Materials," *J. Am. Chem. Soc.*, 120 (37):9714-9715 (1998).

Okumoto, Kenji et al., "Green Fluorescent Organic Light-Emitting Device with External Quantum Efficiency of Nearly 10%," *Appl. Phys. Lett.*, 89:063504-1-063504-3 (2006).

Palilis, Leonidas C., "High Efficiency Molecular Organic Light-Emitting Diodes Based on Silole Derivatives and Their Exciplexes," *Organic Electronics*, 4:113-121 (2003).

Paulose, Betty Marie Jennifer S. et al., "First Examples of Alkenyl Pyridines as Organic Ligands for Phosphorescent Iridium Complexes," *Adv. Mater.*, 16(22):2003-2007 (2004).

Ranjan, Sudhir et al., "Realizing Green Phosphorescent Light-Emitting Materials from Rhenium(I) Pyrazolato Diimine Complexes," *Inorg. Chem.*, 42(4):1248-1255 (2003).

Sakamoto Youichi, "Synthesis, Characterization, and Electron-Transport Property of Perfluorinated Phenylene Dendimers," *J. Am. Chem. Soc.*, 122(8):1832-1833 (2000).

Salbeck, J. et al., "Low (1997) Molecular Organic Glasses for Blue Electroluminescence," *Synthetic Metals*, 91209-215 (1997).

Shirota, Yasuhiko et al., "Starburst Molecules Based on p-Electron Systems as Materials for Organic Electroluminescent Devices," *Journal of Luminescence*, 72-74:985-991 (1997).

(56)

References Cited

OTHER PUBLICATIONS

Sotoyama, Wataru et al., "Efficient Organic Light-Emitting Diodes with Phosphorescent Platinum Complexes Containing NCN-Coordinating Tridentate Ligand," *Appl. Phys. Lett.*, 86:153505-1-15350-3 (2005).

Sun, Yiru and Forrest, Stephen R., "High-Efficiency White Organic Light Emitting Devices with Three Separate Phosphorescent Emission Layers," *Appl. Phys. Lett.*, 91:263503-1-263503-3 (2007).

T. Östergård et al., "Langmuir-Blodgett Light-Emitting Diodes of Poly(3-Hexylthiophene) Electro-Optical Characteristics Related to Structure," *Synthetic Metals*, 87:171-177 (1997).

Takizawa, Shin-ya et al., "Phosphorescent Iridium Complexes Based on 2-Phenylimidazo[1,2- α]pyridine Ligands Tuning of Emission Color toward the Blue Region and Application to Polymer Light-Emitting Devices," *Inorg. Chem.*, 46(10):4308-4319 (2007).

Tang, C.W. and VanSlyke, S.A., "Organic Electroluminescent Diodes," *Appl. Phys. Lett.*, 51(12):913-915 (1987).

Tung, Yung-Liang et al., "Organic Light-Emitting Diodes Based on Charge-Neutral Ru II Phosphorescent Emitters," *Adv. Mater.*, 17(8):1059-1064 (2005).

Van Slyke, S. A. et al., "Organic Electroluminescent Devices with Improved Stability," *Appl. Phys. Lett.*, 69 (15):2160-2162 (1996).

Wang, Y. et al., "Highly Efficient Electroluminescent Materials Based on Fluorinated Organometallic Iridium Compounds," *Appl. Phys. Lett.*, 79(4):449-451 (2001).

Wong, Keith Man-Chung et al., A Novel Class of Phosphorescent Gold(III) Alkynyl-Based Organic Light-Emitting Devices with Tunable Colour, *Chem. Commun.*, 2906-2908 (2005).

Wong, Wai-Yeung, "Multifunctional Iridium Complexes Based on Carbazole Modules as Highly Efficient Electrophosphors," *Angew. Chem. Int. Ed.*, 45:7800-7803 (2006).




FIGURE 1




FIGURE 2




FIGURE 3




FIGURE 4




FIGURE 5




FIGURE 6




FIGURE 7




FIGURE 8




FIGURE 9




FIGURE 10




FIGURE 11




FIGURE 12




FIGURE 13




FIGURE 14

1

DIBENZOTHIOPHENE-CONTAINING MATERIALS IN PHOSPHORESCENT LIGHT EMITTING DIODES

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a divisional of U.S. application Ser. No. 13/186,204, filed Jul. 19, 2011, which is a divisional of U.S. application Ser. No. 12/208,907, filed Sep. 11, 2008, which issued as U.S. Pat. No. 8,007,927 on Aug. 30, 2011, which claims priority to U.S. Provisional Application Ser. No. 61/017,480, filed Dec. 28, 2007, the disclosures of which are herein expressly incorporated by reference in their entirety. This application is also related to International Application No. PCT/IB2007/004687, filed Dec. 28, 2007.

PARTIES TO A JOINT RESEARCH AGREEMENT

The claimed invention was made by, on behalf of, and/or in connection with one or more of the following parties to a joint university corporation research agreement: Regents of the University of Michigan, Princeton University, The University of Southern California, and the Universal Display Corporation. The agreement was in effect on and before the date the claimed invention was made, and the claimed invention was made as a result of activities undertaken within the scope of the agreement.

FIELD OF THE INVENTION

The present invention is directed to organic light emitting devices (OLEDs). More specifically, the present invention relates to phosphorescent light emitting materials and devices that may have improved device lifetime.

BACKGROUND


Opto-electronic devices that make use of organic materials are becoming increasingly desirable for a number of reasons. Many of the materials used to make such devices are relatively inexpensive, so organic opto-electronic devices have the potential for cost advantages over inorganic devices. In addition, the inherent properties of organic materials, such as their flexibility, may make them well suited for particular applications such as fabrication on a flexible substrate. Examples of organic opto-electronic devices include organic light emitting devices (OLEDs), organic phototransistors, organic photovoltaic cells, and organic photodetectors. For OLEDs, the organic materials may have performance advantages over conventional materials. For example, the wavelength at which an organic emissive layer emits light may generally be readily tuned with appropriate dopants.

OLEDs make use of thin organic films that emit light when voltage is applied across the device. OLEDs are becoming an increasingly interesting technology for use in applications such as flat panel displays, illumination, and backlighting. Several OLED materials and configurations are described in U.S. Pat. Nos. 5,844,363, 6,303,238, and 5,707,745, which are incorporated herein by reference in their entirety.

One application for phosphorescent emissive molecules is a full color display. Industry standards for such a display call for pixels adapted to emit particular colors, referred to as "saturated" colors. In particular, these standards call for saturated red, green, and blue pixels. Color may be measured using CIE coordinates, which are well known to the art.

2

One example of a green emissive molecule is tris(2-phenylpyridine) iridium, denoted Ir(ppy)₃, which has the structure of Formula I:



In this, and later figures herein, we depict the dative bond from nitrogen to metal (here, Ir) as a straight line.

As used herein, the term "organic" includes polymeric materials as well as small molecule organic materials that may be used to fabricate organic opto-electronic devices. "Small molecule" refers to any organic material that is not a polymer, and "small molecules" may actually be quite large. Small molecules may include repeat units in some circumstances. For example, using a long chain alkyl group as a substituent does not remove a molecule from the "small molecule" class. Small molecules may also be incorporated into polymers, for example as a pendent group on a polymer backbone or as a part of the backbone. Small molecules may also serve as the core moiety of a dendrimer, which consists of a series of chemical shells built on the core moiety. The core moiety of a dendrimer may be a fluorescent or phosphorescent small molecule emitter. A dendrimer may be a "small molecule," and it is believed that all dendrimers currently used in the field of OLEDs are small molecules.

As used herein, "top" means furthest away from the substrate, while "bottom" means closest to the substrate. Where a first layer is described as "disposed over" a second layer, the first layer is disposed further away from substrate. There may be other layers between the first and second layer, unless it is specified that the first layer is "in contact with" the second layer. For example, a cathode may be described as "disposed over" an anode, even though there are various organic layers in between.

As used herein, "solution processible" means capable of being dissolved, dispersed, or transported in and/or deposited from a liquid medium, either in solution or suspension form.

A ligand may be referred to as "photoactive" when it is believed that the ligand directly contributes to the photoactive properties of an emissive material. A ligand may be referred to as "ancillary" when it is believed that the ligand does not contribute to the photoactive properties of an emissive material, although an ancillary ligand may alter the properties of a photoactive ligand.

As used herein, and as would be generally understood by one skilled in the art, a first "Highest Occupied Molecular Orbital" (HOMO) or "Lowest Unoccupied Molecular Orbital" (LUMO) energy level is "greater than" or "higher than" a second HOMO or LUMO energy level if the first energy level is closer to the vacuum energy level. Since ionization potentials (IP) are measured as a negative energy relative to a vacuum level, a higher HOMO energy level corresponds to an IP having a smaller absolute value (an IP that is less negative). Similarly, a higher LUMO energy level corresponds to an electron affinity (EA) having a smaller absolute value (an EA that is less negative). On a conventional energy level diagram, with the vacuum level at the top, the

3




LUMO energy level of a material is higher than the HOMO energy level of the same material. A “higher” HOMO or LUMO energy level appears closer to the top of such a diagram than a “lower” HOMO or LUMO energy level.

As used herein, and as would be generally understood by one skilled in the art, a first work function is “greater than” or “higher than” a second work function if the first work function has a higher absolute value. Because work functions are generally measured as negative numbers relative to vacuum level, this means that a “higher” work function is more negative. On a conventional energy level diagram, with the vacuum level at the top, a “higher” work function is illustrated as further away from the vacuum level in the downward direction. Thus, the definitions of HOMO and LUMO energy levels follow a different convention than work functions.

More details on OLEDs, and the definitions described above, can be found in U.S. Pat. No. 7,279,704, which is incorporated herein by reference in its entirety.

SUMMARY OF THE INVENTION


A new type of materials is provided. The new class of materials has a dibenzothiophene-containing compound selected from the group consisting of:




4

-continued


Compound 4G




Compound 5G



Compound 6G




Compound 7G



5

-continued


Compound 8G




6

-continued


Compound 12G




Compound 9G




Compound 10G




Compound 11G



Compound 2G



Compound 3G



where each of R_1 through R_6 are independently selected from the group consisting of any aryl and alkyl substituents and H, and where each of R_1 through R_6 may represent multiple substitutions. In one aspect, all of R_1 through R_6 are H.


An organic light emitting device is also provided. The device has an anode, a cathode, an and an organic layer disposed between the anode and the cathode. The organic layer further comprises a material containing a compound from the group consisting of Compound 1G through 12G, as described above, with or without substituents. Preferably the organic layer is an emissive layer having a host and an emissive dopant, and the compound is the host. The compound may also preferably be used as a material in an enhancement layer.

New materials are provided. The materials have a dibenzothiophene-containing and/or dibenzofuran-containing compound selected from the group consisting of:


7

-continued


Compound 4G




Compound 5G



Compound 6G




Compound 7G


**8**

-continued


Compound 8G




Compound 9G



Compound 10G




Compound 11G




9


-continued




Compound 12G




Compound 13G



Compound 14G




Compound 15G




Compound 16G

10


-continued




Compound 17G



Compound 18G




Compound 19G



Compound 20G

11

-continued




Compound 21G

5

10

15


Compound 22G



20

25

Compound 23G




30

35

40


Compound 24G



45

50

Compound 25G




55

60

65


12

-continued




Compound 26G


Compound 27G




Compound 28G



Compound 29G




Compound 30G




13


-continued




Compound 31G



Compound 32G




Compound 33G



Compound 34G

14

-continued



Compound 35G

where each of R_1 through R_8 are independently selected from the group consisting of any aryl and alkyl substituents and H, and where each of R_1 through R_8 may represent multiple substitutions. In one aspect, all of R_1 through R_8 are H.

An organic light emitting device is also provided. The device has an anode, a cathode, and an organic layer disposed between the anode and the cathode. The organic layer further comprises a material containing a compound from the group consisting of Compound 2G through 35G, as described above, with or without substituents. Preferably the organic layer is an emissive layer having a host and an emissive dopant, and the compound is the host. The compound may also preferably be used as a material in an enhancement layer.

A consumer product is also provided. The product contains a device that has an anode, a cathode, and an organic layer disposed between the anode and the cathode, where the organic layer further comprises a material containing a compound from the group consisting of Compounds 2G through 35G, as described above, with or without substituents.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 shows an organic light emitting device.

FIG. 2 shows an inverted organic light emitting device that does not have a separate electron transport layer.

FIG. 3 shows an organic light emitting device including compounds disclosed herein.

FIG. 4 shows a plot of normalized luminescence versus time for the device of FIG. 3.

FIG. 5 shows a plot of external quantum efficiency versus luminance for the device of FIG. 3.

FIG. 6 shows a plot of power efficacy versus luminance for the device of FIG. 3.

FIG. 7 shows a plot of luminance versus voltage for the device of FIG. 3.

FIG. 8 shows a plot of EL intensity versus wavelength for the device of FIG. 3.

FIG. 9 shows an organic light emitting device including compounds disclosed herein.

FIG. 10 shows a plot of external quantum efficiency versus luminance for the device of FIG. 9.

FIG. 11 shows a plot of power efficacy versus luminance for the device of FIG. 9.

FIG. 12 shows a plot of luminance versus voltage for the device of FIG. 9.

FIG. 13 shows a plot of EL intensity versus wavelength for the device of FIG. 9.

FIG. 14 shows a dibenzothiophene-containing compound.

DETAILED DESCRIPTION

Generally, an OLED comprises at least one organic layer disposed between and electrically connected to an anode and a cathode. When a current is applied, the anode injects holes and the cathode injects electrons into the organic layer(s). The injected holes and electrons each migrate toward the oppositely charged electrode. When an electron and hole localize on the same molecule, an "exciton," which is a localized electron-hole pair having an excited energy state, is formed. Light is emitted when the exciton relaxes via a photoemissive mechanism. In some cases, the exciton may be localized on an excimer or an exciplex. Non-radiative mechanisms, such as thermal relaxation, may also occur, but are generally considered undesirable.

The initial OLEDs used emissive molecules that emitted light from their singlet states ("fluorescence") as disclosed, for example, in U.S. Pat. No. 4,769,292, which is incorporated by reference in its entirety. Fluorescent emission generally occurs in a time frame of less than 10 nanoseconds.

More recently, OLEDs having emissive materials that emit light from triplet states ("phosphorescence") have been demonstrated. Baldo et al., "Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices," *Nature*, vol. 395, 151-154, 1998; ("Baldo-I") and Baldo et al., "Very high-efficiency green organic light-emitting devices based on electrophosphorescence," *Appl. Phys. Lett.*, vol. 75, No. 3, 4-6 (1999) ("Baldo-II"), which are incorporated by reference in their entireties. Phosphorescence is described in more detail in U.S. Pat. No. 7,279,704 at cols. 5-6, which are incorporated by reference.

FIG. 1 shows an organic light emitting device 100. The figures are not necessarily drawn to scale. Device 100 may include a substrate 110, an anode 115, a hole injection layer 120 (HIL), a hole transport layer 125 (HTL), an electron blocking layer 130, an emissive layer 135, a hole blocking layer 140, an electron transport layer 145, an electron injection layer 150, a protective layer 155, and a cathode 160. Cathode 160 is a compound cathode having a first conductive layer 162 and a second conductive layer 164. Device 100 may be fabricated by depositing the layers described, in order. The properties and functions of these various layers, as well as example materials, are described in more detail in U.S. Pat. No. 7,279,704 at cols. 6-10, which are incorporated by reference.

More examples for each of these layers are available. For example, a flexible and transparent substrate-anode combination is disclosed in U.S. Pat. No. 5,844,363, which is incorporated by reference in its entirety. An example of a p-doped hole transport layer is m-MTDATA doped with F.sub.4-TCNQ at a molar ratio of 50:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. Examples of emissive and host materials are disclosed in U.S. Pat. No. 6,303,238 to Thompson et al., which is incorporated by reference in its entirety. An example of an n-doped electron transport layer is BPhen doped with Li at a molar ratio of 1:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. U.S. Pat. Nos. 5,703,436 and 5,707,745, which are incorporated by reference in their entireties, disclose examples of cathodes including compound cathodes having a thin layer of metal such as Mg:Ag with an overlying transparent, electrically-

conductive, sputter-deposited ITO layer. The theory and use of blocking layers is described in more detail in U.S. Pat. No. 6,097,147 and U.S. Patent Application Publication No. 2003/0230980, which are incorporated by reference in their entireties. Examples of injection layers are provided in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety. A description of protective layers may be found in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety. An "enhancement layer" occupies the same position in a device as a blocking layer described above, and may have blocking functionality or other functionality that improves device performance.

FIG. 2 shows an inverted OLED 200. The device includes a substrate 210, a cathode 215, an emissive layer 220, a hole transport layer 225, and an anode 230. Device 200 may be fabricated by depositing the layers described, in order. Because the most common OLED configuration has a cathode disposed over the anode, and device 200 has cathode 215 disposed under anode 230, device 200 may be referred to as an "inverted" OLED. Materials similar to those described with respect to device 100 may be used in the corresponding layers of device 200. FIG. 2 provides one example of how some layers may be omitted from the structure of device 100.

The simple layered structure illustrated in FIGS. 1 and 2 is provided by way of non-limiting example, and it is understood that embodiments of the invention may be used in connection with a wide variety of other structures. The specific materials and structures described are exemplary in nature, and other materials and structures may be used. Functional OLEDs may be achieved by combining the various layers described in different ways, or layers may be omitted entirely, based on design, performance, and cost factors. Other layers not specifically described may also be included. Materials other than those specifically described may be used. Although many of the examples provided herein describe various layers as comprising a single material, it is understood that combinations of materials, such as a mixture of host and dopant, or more generally a mixture, may be used. Also, the layers may have various sublayers. The names given to the various layers herein are not intended to be strictly limiting. For example, in device 200, hole transport layer 225 transports holes and injects holes into emissive layer 220, and may be described as a hole transport layer or a hole injection layer. In one embodiment, an OLED may be described as having an "organic layer" disposed between a cathode and an anode. This organic layer may comprise a single layer, or may further comprise multiple layers of different organic materials as described, for example, with respect to FIGS. 1 and 2.

Structures and materials not specifically described may also be used, such as OLEDs comprised of polymeric materials (PLEDs) such as disclosed in U.S. Pat. No. 5,247,190 to Friend et al., which is incorporated by reference in its entirety. By way of further example, OLEDs having a single organic layer may be used. OLEDs may be stacked, for example as described in U.S. Pat. No. 5,707,745 to Forrest et al, which is incorporated by reference in its entirety. The OLED structure may deviate from the simple layered structure illustrated in FIGS. 1 and 2. For example, the substrate may include an angled reflective surface to improve out-coupling, such as a mesa structure as described in U.S. Pat. No. 6,091,195 to Forrest et al., and/or a pit structure as described in U.S. Pat. No. 5,834,893 to Bulovic et al., which are incorporated by reference in their entireties.

Unless otherwise specified, any of the layers of the various embodiments may be deposited by any suitable method. For the organic layers, preferred methods include thermal evapo-

17

ration, ink-jet, such as described in U.S. Pat. Nos. 6,013,982 and 6,087,196, which are incorporated by reference in their entireties, organic vapor phase deposition (OVPD), such as described in U.S. Pat. No. 6,337,102 to Forrest et al., which is incorporated by reference in its entirety, and deposition by organic vapor jet printing (OVJP), such as described in U.S. patent application Ser. No. 10/233,470, which is incorporated by reference in its entirety. Other suitable deposition methods include spin coating and other solution based processes. Solution based processes are preferably carried out in nitrogen or an inert atmosphere. For the other layers, preferred methods include thermal evaporation. Preferred patterning methods include deposition through a mask, cold welding such as described in U.S. Pat. Nos. 6,294,398 and 6,468,819, which are incorporated by reference in their entireties, and patterning associated with some of the deposition methods such as ink-jet and OVJD. Other methods may also be used. The materials to be deposited may be modified to make them compatible with a particular deposition method. For example, substituents such as alkyl and aryl groups, branched or unbranched, and preferably containing at least 3 carbons, may be used in small molecules to enhance their ability to undergo solution processing. Substituents having 20 carbons or more may be used, and 3-20 carbons is a preferred range. Materials with asymmetric structures may have better solution processibility than those having symmetric structures, because asymmetric materials may have a lower tendency to recrystallize. Dendrimer substituents may be used to enhance the ability of small molecules to undergo solution processing.

Devices fabricated in accordance with embodiments of the invention may be incorporated into a wide variety of consumer products, including flat panel displays, computer monitors, televisions, billboards, lights for interior or exterior illumination and/or signaling, heads up displays, fully transparent displays, flexible displays, laser printers, telephones, cell phones, personal digital assistants (PDAs), laptop computers, digital cameras, camcorders, viewfinders, micro-displays, vehicles, a large area wall, theater or stadium screen, or a sign. Various control mechanisms may be used to control devices fabricated in accordance with the present invention, including passive matrix and active matrix. Many of the devices are intended for use in a temperature range comfortable to humans, such as 18 degrees C. to 30 degrees C., and more preferably at room temperature (20-25 degrees C.).

The materials and structures described herein may have applications in devices other than OLEDs. For example, other optoelectronic devices such as organic solar cells and organic photodetectors may employ the materials and structures. More generally, organic devices, such as organic transistors, may employ the materials and structures.

The terms halo, halogen, alkyl, cycloalkyl, alkenyl, alkynyl, arylkyl, heterocyclic group, aryl, aromatic group, and heteroaryl are known to the art, and are defined in U.S. Pat. No. 7,279,704 at cols. 31-32, which are incorporated herein by reference.


Dibenzo[b,d]thiophene (also referred to herein as "dibenzothiophene")-containing materials are provided, which can be used in the PHOLED devices fabricated by both vapor deposition or solution processing, giving long lifetime stable devices with low voltage. The materials may be used as a stable host in PHOLED devices, or in other layers, such as an enhancement layer.

Compounds are provided comprising dibenzothiophene and/or dibenzofuran. Dibenzothiophenes and dibenzofurans may be used as hole and/or electron transporting organic conductors, they usually exhibit more reversible electrochemical reduction in solution than some common organic

18




groups, such as biphenyl. The triplet energies of dibenzothiophenes and dibenzofurans are relatively high. Therefore, a compound containing dibenzothiophene and/or dibenzofuran may be advantageously used as a host or a material for an enhancement layer in PHOLED devices. For example, the triplet energy of dibenzothiophene is high enough for use in a blue or green PHOLED device. Dibenzothiophene and/or dibenzofuran-containing compounds may provide improved device stability while maintaining good device efficiency.

Dibenzothiophene-containing materials may have the following general structure:



Each of R_1 and R_2 may be independently selected from the group consisting of any alkyl, alkoxy, amino, alkenyl, alkynyl, arylkyl, aryl, heteroaryl, and hydrogen, and where R_1 and R_2 may represent multiple substitutions.


Particular dibenzothiophene compounds are provided, which may be advantageously used in OLEDs, having the following structures:




19

-continued


Compound 4G




Compound 5G



Compound 6G




Compound 7G


**20**

-continued


Compound 8G




Compound 9G



Compound 10G




Compound 11G



21


-continued




Compound 12G

Each of R_1 through R_6 are independently selected from the group consisting of any alkyl, alkoxy, amino, alkenyl, alkynyl, arylkyl, aryl, heteroaryl, and hydrogen, and where each of R_1 through R_6 may represent multiple substitutions.


Additionally, particular dibenzothiophene-containing compounds, which may be advantageously used in OLEDs, are provided:




Compound 1



Compound 2




Compound 3




Compound 4

22


-continued




Compound 5



Compound 6




Compound 7



Compound 8

23


-continued



Compound 9

24


Compound 2G



15

Compound 3G


Compound 10



30

Compound 4G


Compound 11




45

Compound 5G

Compound 12



65




Dibenzothiophene-containing and/or dibenzofuran-containing compounds are provided, which may be advantageously used in OLEDs, having the following structures:


25

-continued


Compound 6G




Compound 7G



Compound 8G




Compound 9G


**26**

-continued


Compound 10G




Compound 11G




Compound 12G



Compound 13G







Compound 14G








27

-continued






**28**

-continued



29


-continued




30

-continued


Compound 24G




Compound 25G



Compound 26G



Compound 27G



Compound 28G

Compound 29G

Compound 30G


Compound 31G

Compound 32G


31

-continued


Compound 33G



Compound 34G



Compound 35G




Each of R_1 through R_8 are independently selected from the group consisting of any alkyl, alkoxy, amino, alkenyl, alkynyl, aryl, heteroaryl, and hydrogen, and where each of R_1 through R_8 may represent multiple substitutions.


Additionally, dibenzothiophene-containing and/or dibenzofuran-containing compounds are provided, which may be advantageously used in OLEDs, are provided:

32


Compound 2




Compound 3




Compound 4



Compound 5




Compound 6




33

-continued


Compound 7




Compound 8




Compound 9



Compound 10




Compound 11


**34**

-continued


Compound 12




Compound 13




Compound 14



Compound 15




Compound 16



35

-continued

Compound 17



5


10

15

20


Compound 18

25



Compound 19

40




45

50

Compound 20

55




65


36

-continued


Compound 21




Compound 22




Compound 23



Compound 24




Compound 25



37

-continued




Compound 26

5

10

15


Compound 27



20

25

Compound 28




30

35

40

45

Compound 29



50


55

60

65


38

-continued




Compound 30

Compound 31






Compound 32



39

-continued

**40**

As used herein, the following compounds have the following structures:

Compound 33

5

H1

10

15

20

Compound 34

25

30

35

40



Compound 35

50


55

60


65




P1



P2







P3



P4

41


-continued



42

-continued

NPD



Particular host-dopant combinations for the emissive layer of an OLED are also provided which may lead to devices having particularly good properties. Specifically, devices having an emissive layer using H1 as the host and P1, P2, or P7 as an emissive dopant are demonstrated to have particularly good properties. Such devices may be particularly favorable when the emissive layer includes two organic layers, a first organic layer including H1 doped with P1, and a second organic layer including H1 doped with P2, as illustrated in FIG. 3.

Similarly, devices having an emissive layer using Compound 1 as the host and P3, P4 and/or P5 as dopants may lead to devices having particularly good properties. Specifically, devices having an emissive layer using Compound 1 as the host and P3 as an emissive dopant, and/or an emissive layer with multiple dopants using Compound 1 as the host and P4 and P5 as dopants, where P5 is the primary emissive dopant in the layer. Such devices may be particularly favorable when the emissive layer includes two organic layers, a first organic layer including Compound 1 doped with P3, and a second organic layer including Compound 1 doped with P4 and P5, as illustrated in FIG. 9.

Devices having an emissive layer using Compound 23 as the host and P1 as the dopant may also lead to devices having particularly good properties.

Additionally, a consumer product comprising a device having an anode, a cathode, and an organic layer, disposed between the anode and the cathode. The organic layer further comprises a material containing a compound selected from the group consisting of Compound 2G-35G where R_1 through R_8 are independently selected from the group consisting of any alkyl, alkoxy, amino, alkenyl, alkynyl, arylkyl, aryl, heteroaryl and hydrogen, and where each of R_1 through R_8 may represent multiple substitutions.

The materials described herein as useful for a particular layer in an organic light emitting device may be used in combination with a wide variety of other materials present in the device. For example, emissive dopants disclosed herein may be used in conjunction with a wide variety of hosts, transport layers, blocking layers, injection layers, electrodes and other layers that may be present. The materials described or referred to below are non-limiting examples of materials that may be useful in combination with the compounds disclosed herein, and one of skill in the art can readily consult the literature to identify other materials that may be useful in combination.

In addition to and/or in combination with the materials disclosed herein, many hole injection materials, hole transporting materials, host materials, dopant materials, exciton/hole blocking layer materials, electron transporting and electron injecting materials may be used in an OLED. Non-limiting examples of the materials that may be used in an OLED in combination with materials disclosed herein are listed in Table 1 below. Table 1 lists non-limiting classes of materials, non-limiting examples of compounds for each class, and references that disclose the materials.

TABLE 1





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Hole injection materials		
Phthalocyanine and porphyrin compounds		Appl. Phys. Lett. 69, 2160 (1996)
Starburst triarylamines		J. Lumin. 72-74, 985 (1997)
CF _x Fluoro-hydrocarbon polymer	$\text{---}[\text{CH}_x\text{F}_y]_n\text{---}$	Appl. Phys. Lett. 78, 673 (2001)
Conducting polymers (e.g., PEDOT:PSS, polyaniline, polythiophene)		Synth. Met. 87, 171 (1997)
Arylamine complexed with metal oxides such as molybdenum and tungsten oxides		SID Symposium Digest, 37, 923 (2006)
Hole transporting materials		

TABLE 1-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Triarylamines (e.g., TPD, α -NPD)		Appl. Phys. Lett. 51, 913 (1987)
		U.S. Pat. No. 5,061,569
		EP650955
		J. Mater. Chem. 3, 319 (1993)

TABLE 1-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		Appl. Phys. Lett. 90, 183503 (2007)
		Appl. Phys. Lett. 90, 183503 (2007)
Triarylamine on spirofluorene core		Synth. Met. 91, 209 (1997)
Arylamine carbazole compounds		Adv. Mater. 6, 677 (1994)

TABLE 1-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Indolocarbazoles		Synth. Met. 111, 421 (2000)
Isoindole compounds		Chem. Mater. 15, 3148 (2003)
Phosphorescent OLED host materials Red hosts	  	Appl. Phys. Lett. 78, 1622 (2001)
Metal 8-hydroxyquinolates (e.g. Alq ₃ , BAlq)		Nature 395, 151 (1998)
		US20060202194

TABLE 1-continued







MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Metal phenoxy-benzothiazole compounds		WO2005014551
		Appl. Phys. Lett. 90, 123509 (2007)
Conjugated oligomers and polymers (e.g., polyfluorene)		Org. Electron. 1, 15 (2000)
Green hosts	Arylcarbazoles	Appl. Phys. Lett. 78, 1622 (2001)
		US2003175553
		WO2001039234
		

TABLE 1-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Aryltriphenylene compounds		US20060280965
		US20060280965
Polymers (e.g., PVK)		Appl. Phys. Lett. 77, 2280 (2000)
Spirofluorene compounds		WO2004093207
Metal phenoxy- benzoxazole compounds		WO05089025

TABLE 1-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO06132173
		JP200511610
Spirofluorene-carbazole compounds		JP2007254297
		JP2007254297
Indolocabazoles		WO07063796

TABLE 1-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5-member ring electron deficient heterocycles (e.g., triazole, oxadiazole)		WO07063754
		J. Appl. Phys. 90, 5048 (2001)
		WO04107822
Metal phenoxy- pyridine compounds		WO05030900
Blue hosts	Arylcarbazoles	Appl. Phys. Lett, 82, 2422 (2003)
		US20070190359

TABLE 1-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Dibenzo-thiophene-carbazole compounds		WO2006114966
Phosphorescent dopants Red dopants		
Heavy metal porphyrins (e.g., PtOEP)		Nature 395, 151 (1998)
Iridium (III) organometallic complexes		Appl. Phys. Lett. 78, 1622 (2001)
		US06835469
		US06835469

TABLE 1-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US20060202194
		US20060202914
		US07087321
		US07087321
	 H_{17}C_8	Adv. Mater. 19, 739 (2007)

TABLE 1-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Platinum (II) organometallic complexes		WO2003040257
Osmium (III) complexes		Chem. Mater. 17, 3532 (2005)
Ruthenium (II) complexes		Adv. Mater. 17, 1059 (2005)
Green dopants		
Iridium (III) organometallic complexes	 and its derivatives	Inorg. Chem. 40, 1704 (2001)
		US2002034656

TABLE 1-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US06687266
		Chem. Mater. 16, 2480 (2004)
		US2007190359
		US 2006008670 JP2007123392
		Adv. Mater. 16, 2003 (2004)

TABLE 1-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		Angew. Chem. Int. Ed. 2006, 45, 7800
Pt (II) organometallic complexes		Appl. Phys. Lett. 86, 153505 (2005)
		Appl. Phys. Lett. 86, 153505 (2005)
		Chem. Lett. 34, 592 (2005)

TABLE 1-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Gold complexes		Chem. Commun. 2906 (2005)
Rhenium (III) complexes		Inorg. Chem. 42, 1248 (2003)
Blue dopants		WO2002002714
Iridium (III) organometallic		WO2006009024
Iridium (III) organometallic		US2006251923

TABLE 1-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO05123873
		WO05123873
		WO07004380
		WO06082742
Osmium (II) complexes		US2005260449

TABLE 1-continued







MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		Organometallics 23, 3745 (2004)
Gold complexes		Appl. Phys. Lett. 74, 1361 (1999)
Platinum (II) complexes		WO06098120, WO06103874
Exciton/hole blocking layer materials		
Bathocuprine compounds (e.g., BCP, BPhen)		Appl. Phys. Lett. 75, 4 (1999)
		Appl. Phys. Lett. 79, 449 (2001)
Metal 8-hydroxy-quinolates (e.g., BAlq)		Appl. Phys. Lett. 81, 162 (2002)

TABLE 1-continued




MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5-member ring electron deficient heterocycles such as triazole, oxadiazole, imidazole, benzoimidazole		Appl. Phys. Lett. 81, 162 (2002)
Triphenylene compounds		US20050025993
Fluorinated aromatic compounds		Appl. Phys. Lett. 79, 156 (2001)
Electron transporting materials		

TABLE 1-continued












MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Anthracene-benzimidazole compounds		WO03060956
Anthracene-benzothiazole compounds		Appl. Phys. Lett. 89, 063504 (2006)
Metal 8-hydroxy-quinolates (e.g., Alq ₃)		Appl. Phys. Lett. 51, 913 (1987)
Metal hydroxy-benzoquinolates		Chem. Lett. 5, 905 (1993)
Bathocuprine compounds such as BCP, BPhen, etc		Appl. Phys. Lett. 91, 263503 (2007)
		Appl. Phys. Lett. 79, 449 (2001)


TABLE 1-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5-member ring electron deficient heterocycles (e.g., triazole, oxadiazole, imidazole, benzimidazole)		Appl. Phys. Lett. 74, 865 (1999)
		Appl. Phys. Lett. 55, 1489 (1989)
		Jpn. J. Apply. Phys. 32, L917 (1993)
Silole compounds		Org. Electron. 4, 113 (2003)
Arylborane compounds		J. Am. Chem. Soc. 120, 9714 (1998)
Fluorinated aromatic compounds		J. Am. Chem. Soc. 122, 1832 (2000)

Compound Examples

Some of the dibenzothiophene-containing compounds were synthesized, as follows:


Compound 1



Step 1. 3,3'-dihydroxybiphenyl (9.3 g, 50 mmol) was dissolved in 100 mL of CH_2Cl_2 , followed by the addition of pyridine (15.8 g, 200 mmol). To this solution at -15°C ., Ti_2O (42.3 g, 150 mmol) was added dropwise. The mixture was continued to stir at room temperature for 5 h. The organic phase was separated and washed with brine once. The crude product was further purified by a silica column. 3,3'-ditriflatebiphenyl was obtained as pale white solid (21.3 g).


Step 2. To a 500 mL round flask was added 3,3'-ditriflatebiphenyl (2.7 g, 6 mmol), 4-dibenzothiopheneboronic acid (4.1 g, 18 mmol), $\text{Pd}_2(\text{dba})_3$ (0.2 g, 0.2 mmol), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (0.3 g, 0.8 mmol), potassium phosphate tribasic (5.1 g, 24 mmol), and 150 mL of toluene. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, the mixture was purified by a silica gel column. Yield was 2.6 g.

Compound 2




To a 500 mL round flask was added 2,2'-ditriflatebiphenyl (2.7 g, 6 mmol), 4-dibenzothiopheneboronic acid (4.1 g, 18 mmol), $\text{Pd}_2(\text{dba})_3$ (0.2 g, 0.2 mmol), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (0.3 g, 0.8 mmol), potassium phosphate tribasic (5.1 g, 24 mmol), and 150 mL of toluene. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, the mixture was purified by a silica gel column. Yield was 2.5 g.

Compound 3




To a 500 mL round flask was added 4,6-diiododibenzothiophene (4.2 g, 9.6 mmol), 4-dibenzothiopheneboronic acid (5.3 g, 23.1 mmol), $\text{Pd}_2(\text{dba})_3$ (0.2 g, 0.2 mmol), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (0.3 g, 0.8 mmol), potassium phosphate tribasic (7.4 g, 35 mmol), and 150 mL of toluene. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, the mixture was purified by a silica gel column. Yield was 2.4 g.

Compound 4



To a 500 mL round flask was added 4,6-diiododibenzothiophene (3.9 g, 8.9 mmol), carbazole (3.3 g, 19.6 mmol), $\text{Pd}_2(\text{dba})_3$ (0.2 g, 0.2 mmol), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (0.3 g, 0.8 mmol), sodium t-butoxide (5.8 g, 60 mmol), and 200 mL of xylene. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, the mixture was purified by a silica gel column. Yield was 2.2 g.

Compound 5




Step 1. 2,6-Dibromo-1,3,5-trimethylbenzene (8.34 g, 30 mmol) was dissolved in 50 mL of CHCl_3 and suspended with 1.0 g of iron powder in 200 mL round-bottom flask. Bromine

85

(2.00 ml, 31 mmol) was added dropwise at room temperature and reaction mixture was heated to reflux for 3 hours, cooled down to room temperature and stirred overnight. Solution was decanted, washed with NaOH 10% aq., filtered and evaporated. The solid residue was crystallized from chloroform, providing 7.00 g of yellow solid (2,4,6-tribromo-1,3,5-trimethylbenzene).


Step 2. The 1 L round-bottom flask equipped with magnetic stirrer and reflux condenser was charged with 2,4,6-tribromo-1,3,5-trimethylbenzene (3.4 g, 9.5 mmol), 4-dibenzothiopheneboronic acid (8.7 g, 38 mmol), $\text{Pd}_2(\text{OAc})_2$ (0.16 g, 0.7 mmol), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (0.46 g, 1.1 mmol), potassium phosphate tribasic (53 g, 250 mmol), 1.2 ml of water and 700 mL of toluene. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, the mixture was purified by a silica gel column. Yield was 5.2 g.

Compound 6



To a 500 mL round flask was added cyanuric chloride (1.5 g, 8.0 mmol), 4-dibenzothiopheneboronic acid (6.8 g, 30 mmol), $\text{Pd}_2(\text{dba})_3$ (0.2 g, 0.2 mmol), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (0.3 g, 0.8 mmol), potassium phosphate tribasic (8.5 g, 40 mmol), and 250 mL of toluene. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, the mixture was filtered. The product was further purified by recrystallization from EtOAc. Yield was 3.0 g.


Compound 7



2,8-Dibromobenzothiophene (2.5 g, 7.3 mmol) in 150 mL of THF was treated with n-BuLi (1.6 M in hexane, 10 mL, 16 mmol) at -78°C . for 1 h. Dimesitylboron fluoride (5.0 g, 16.8 mmol) in 40 mL of ether was added dropwise. After the mixture was stirred for another 1 h, the mixture was slowly warmed up to room temperature and continued to stir overnight. The product was purified by a silica gel column. Yield was 2.8 g.


86

Compound 8




4-Dibenzothiopheneboronic acid (5.0 g) was suspended in 300 mL of xylene and performed the Dean-Stark extraction for 5 h. After cooling down, the solid was collected, washed with EtOAc and hexane, and sublimed at 320°C . twice. Yield was 3.6 g.

Compound 9



To a 500 mL round flask lithium amide (0.2 g, 10 mmol), 4-iododibenzothiophene (9.9 g, 32 mmol), $\text{Pd}_2(\text{dba})_3$ (0.2 g, 0.2 mmol), 2-dicyclohexylphosphino-2',4',6'-triisopropylbiphenyl (0.4 g, 0.8 mmol), sodium t-butoxide (2.9 g, 30 mmol), and 200 mL of toluene were added. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, the mixture was purified by a silica gel column. Yield was 4.0 g.


Compound 10



The 500 mL round flask was charged with 2,3-dibromobenzo[b]thiophene (5.0 g, 17.1 mmol), 4-dibenzothiopheneboronic acid (10.0 g, 43.8 mmol), $\text{Pd}_2(\text{PPh}_3)_4$ (0.8 g, 0.7 mmol), potassium carbonate (14.2 g, 103 mmol) in

87


30 ml water followed by 200 ml of toluene. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, separation of aqueous phase and evaporation the mixture was purified by a silica gel column (hexane/ethyl acetate 4/1 mixture), providing target compound as solidified colorless oil (4.6 g).



Compound 11

Step 1. Dibenzothiophene (9.21 g, 50 mmol) was dissolved in 100 ml of dry THF and solution was cooled to -50°C . n-BuLi (1.6 molar solution in hexanes, 40 ml, 64 mmol) was added dropwise. The reaction mixture was warmed to room temperature, stirred for 4 hours and cooled to -30°C . Dibenzofluorenone (9.0 g, 50 mmol) in 70 ml THF was added dropwise, reaction mixture was allowed to warm to room temperature and stirred overnight. The reaction mixture was diluted with ethyl acetate (75 ml), washed with brine 3 times, dried over MgSO_4 , filtered and evaporated. The solid residue was purified by column chromatography on silica (hexane/ethyl acetate 7/3) providing 12.0 g of 9-(dibenzo[b,d]thiophen-4-yl)-9H-fluoren-9-ol as white solid.

Step 2. 9-(Dibenzo[b,d]thiophen-4-yl)-9H-fluoren-9-ol (product from the Step 1, 3.64 g, 10 mmol) were dissolved in 100 ml of dry toluene. Twenty drops of 10% solution of P_2O_5 in $\text{CH}_3\text{SO}_3\text{H}$ were added at room temperature, and reaction mixture was stirred for 5 hours. The solution was decanted from solid residue, filtered through silica plug and evaporated. The solid residue was subjected to column chromatography (silica, hexane/ethyl acetate 4/1) providing 4.0 g of white solid.



Compound 12

Step 1. The 200 ml round-bottom flask equipped with reflux condenser and magnetic stirrer was charged with carbazole (14.75 g, 88 mmol), 3-iodobromobenzene (25.0 g, 88 mmol), $\text{Pd}_2(\text{dba})_3$ (0.8 g, 0.85 mmol) and dppf (1,1'-bis(diphenylphosphino)ferrocene, 0.98 g, 1.8 mmol), sodium t-butoxide (25 g, 265 mmol) and 100 ml of dry xylene.

88

Reaction mixture was refluxed under N_2 atmosphere for 48 hours, cooled down to room temperature and evaporated. The solid residue was subjected to column chromatography on silica (eluent—hexane/ethyl acetate 9/1) providing 11.7 g of 9-(3-bromophenyl)-9H-carbazole as white solid.

Step 2. 9-(3-Bromophenyl)-9H-carbazole (11.7 g, 36 mmol), Bis(pinacolato)diboron (13.85 g, 54 mmol), potassium acetate (7.00 g, 71 mmol), 1,1'-bis(diphenylphosphino)ferrocene[dichloropalladium (II) (0.6 g) were dissolved in 100 ml of dry dioxane and refluxed under N_2 atmosphere overnight. Then reaction mixture was cooled down to room temperature, diluted with ethyl acetate, washed with brine, dried over magnesium sulfate, and evaporated. The solid residue was subjected to column chromatography on silica (eluent hexane/ethyl acetate 5/1), providing 8.00 g of 9-(3-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)phenyl)-9H-carbazole as yellow solid. Analytically pure material may be prepared by crystallization from hexane, otherwise product was used without additional purification.


Step 3. 2-Bromoanisole (5.61 g, 30 mmol) and 4-dibenzothiopheneboronic acid (6.84 g, 30 mmol), $\text{Pd}_2(\text{PPh}_3)_4$ (1.00 g, 0.8 mmol) were dissolved in 100 ml of toluene. Saturated solution of sodium carbonate (12.5 g in water) was added, and reaction mixture was heated to reflux under N_2 atmosphere overnight. Then reaction mixture was cooled down to room temperature, separated organic phase and evaporated toluene. The solid residue was subjected to column chromatography on silica (eluent—hexane/ethyl acetate 4/1) providing 4-(2-methoxyphenyl)dibenzo[b,d]thiophene as 6.6 g of colorless solidified oil.

Step 4. 4-(2-Methoxyphenyl)dibenzo[b,d]thiophene (6.6 g, 23 mmol) and pyridinium hydrochloride (27 g, 230 mmol) were mixed together, placed in the 100 ml round bottom flask and heated to reflux for 45 min. Reaction mixture was cooled to 60°C , diluted with 100 ml water and extracted with ethyl acetate. The organic phase was separated, dried over magnesium sulfate, filtered and evaporated. The residue was subjected to column chromatography on silica (eluent hexane/ethyl acetate 5/1), providing 4.00 g of 2-(dibenzo[b,d]thiophen-4-yl)phenol as clear solidified oil.


Step 5. 2-(Dibenzo[b,d]thiophen-4-yl)phenol (3.9 g, 14 mmol) was dissolved in 80 ml of dry dichloromethane, containing 5 ml of dry pyridine, and solution was cooled in the ice bath. The triflic anhydride (5 ml, 28 mmol) was added dropwise, the reaction mixture was stirred overnight at room temperature, washed with water and evaporated. The residue was purified by column chromatography on silica (eluent hexane/ethyl acetate 9/1), providing 4.2 g of clear colorless solidified oil.

Step 6. The 200 ml round bottom flask with reflux condenser and magnetic stirrer was charged with triflate from Step 5 (4.1 g, 10 mmol) and boronic ester from Step 2 (3.7 g, 10 mmol) followed by tribasic potassium phosphate (6.36 g, 30 mmol), palladium acetate (0.67 g, 0.3 mmol), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (0.8 g, 0.6 mmol), 200 ml of toluene and 6 ml of water. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, the mixture was purified by a silica gel column with eluent hexane/ethyl acetate 4/1, providing 2.8 g of target compound as white solid.

89




To a 500 mL round flask carbazole (3.7 g, 22 mmol), 2,8-dibromobenzothiophene (3.4 g, 10 mmol), Pd(OAc)₂ (0.1 g, 0.5 mmol), tri-*t*-butylphosphine (1 M in toluene, 1.5 mL, 1.5 mmol), sodium *t*-butoxide (6.3 g, 66 mmol), and 200 mL of xylene were added. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, the mixture was purified by a silica gel column. Yield was 4.7 g.



Compound 13

To a 500 mL round flask 4-iododibenzothiophene (6.2 g, 20 mmol), carbazole (4.0 g, 24 mmol), Pd₂(dba)₃ (0.9 g, 1.0 mmol), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (1.6 g, 4.0 mmol), sodium *t*-butoxide (5.8 g, 60 mmol), and 200 mL of xylene were added. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, the mixture was purified by a silica gel column. Yield was 2.4 g.




Compound 14

m-Carborane (5.0 g, 35 mmol) in 200 mL of dry DME was treated with *n*-BuLi (1.6 M in hexane, 48 mL, 76 mmol) at 0° C. for 30 min under nitrogen. After the mixture was warm up to room temperature, CuCl (9.5 g, 96 mmol) was added. The mixture continued to stir for 1 h, and 30 mL of dry pyridine, 4-iododibenzothiophene (22.6 g, 73 mmol) were added. The resulting mixture was refluxed for 60 h. After cooling, the mixture was purified by a silica gel column. Yield was 1.8 g.

90

H1

Compound 15




Step 1. Dibenzothiophene (27 g, 147 mmol) in 400 mL of THF was treated slowly with *n*-BuLi (1.6 M in hexane, 100 mL, 160 mmol) at -50° C. The resulting mixture was slowly warmed up to room temperature and continued to stir for 5 h. The solution was cooled back to -78° C., DMF (61 mL) in 100 mL of THF was added slowly. The mixture continued to stir for another 2 h at this temperature and then warmed up to room temperature. The product was extracted with EtOAc and further purified by a silica gel column. Yield of 4-dibenzothiophenealdehyde was 21 g.

Step 2. To a 300 mL of THF solution of 2,8-dibromodibenzothiophene (3.4 g, 10 mmol) at -78° C. was added slowly by *n*-BuLi (1.6 M in hexane, 13.8 mL, 22 mmol). After stirred for 1 h at this temperature, the mixture was treated slowly with a 100 mL of THF solution of 4-dibenzothiophenealdehyde (4.2 g, 20 mmol). The solution was then allowed to warm up to room temperature. The product was extracted with EtOAc and further purified by a silica gel column. Yield of dicarbinol intermediate was 4.2 g.


Step 3. To a 50 mL of CH₂Cl₂ solution of above dicarbinol intermediate (4.5 g, 7.4 mmol) and CF₃COOH (60 mL) was added portionwise of solid powder of sodium borohydride (2.8 g, 74 mmol). The mixture was stirred under nitrogen overnight. The solvents was removed by rotovap, and the solid was washed with water then with NaHCO₃ solution. The crude product was further purified by a silica gel column. Yield of final product was 2.4 g.

Compound 16




Dibenzothiophene (14 g, 76 mmol) in 200 mL of THF was treated slowly with *n*-BuLi (1.6 M in hexane, 50 mL, 80 mmol) at -50° C. The resulting mixture was slowly warmed up to room temperature and continued to stir for 5 h. The solution was cooled back to -78° C., SiCl₄ (2.0 g, 12 mmol) was added slowly. The mixture continued to stir for another 2 h at this temperature and 12 h at room temperature. The product was extracted with EtOAc and further purified by a silica gel column. Yield was 3.5 g.


91



To a 500 mL round flask 3,6-di(9-carbazolyl)carbazole (3.0 g, 6 mmol, prepared similarly as described above for 3-(9-carbazolyl)carbazole), 2-bromobenzothiophene (2.1 g, 7.8 mmol), CuI (0.4 g, 2.0 mmol), trans-1,2-Diaminocyclohexane (0.4 g, 3.6 mmol), potassium phosphate tribasic (3.2 g, 15 mmol), and 250 mL of toluene were added. The reaction was heated to reflux and stirred under a nitrogen atmosphere for 24 hours. After cooling, the mixture was purified by a silica gel column. Yield was 3.1 g.



92








The 300 mL round bottom flask, equipped with magnetic stirrer and refluxed condenser, was charged with carbazole (7.1 g, 42.5 mmol), 3-iodobromobenzene (25.00 g, 88 mmol), Pd₂(dba)₃ (800 mg, 1 mol %), dppf (1',1'-bis(diphenylphosphino)ferrocene (975 mg, 2 mol %), sodium t-butoxide (6.3 g) and m-xylene (100 ml). The reaction mixture was heated to reflux and stirred under nitrogen atmosphere for 48 hours. Then reaction was cooled down to room temperature, filtered through silica plug and evaporated. The residue was subjected to column chromatography on silica gel, eluent gradient mixture hexane-hexane/ethyl acetate mixture 9:1, providing 7.00 g of 9-(3-bromo-phenyl)-9H-carbazole as white solid, structure was confirmed by NMR and GCMS spectroscopy.

7.00 g of 9-(3-bromo-phenyl)-9H-carbazole (21.7 mmol), bis-pinacolatodiborane (8.3 g, 32.7 mmol), potassium acetate (4.30 g) and (1,1'-bis(diphenylphosphino)-ferrocene)dichloropalladium (II) (500 mg) were dissolved in 100 ml of dioxane and refluxed under nitrogen for 24 hours. After evaporation the residue was subjected to column chromatography on silica gel (eluent hexane/ethyl acetate 9/1 mixture), providing pure 9-[3-(4,4,5,5-tetramethyl-[1,3,2]dioxaborolan-2-yl)-phenyl]-9H-carbazole as white solid (11.8 g).

The 300 mL round bottom flask, equipped with magnetic stirrer and refluxed condenser, was charged with 2,8-dibromo-dibenzothiophene (3.42 g, 10 mmol), 9-[3-(4,4,5,5-tetramethyl-[1,3,2]dioxaborolan-2-yl)-phenyl]-9H-carbazole (11.7 g, 30 mmol), palladium (II) acetate (64 mg), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (234 mg), potassium phosphate tribasic anhydrous (53.0 g), 700 ml of toluene and 2 ml of water. The reaction mixture was heated to reflux and stirred under nitrogen atmosphere for 24 hours. Then reaction was cooled down to room temperature, filtered through silica plug and evaporated. The residue was washed with hexane, ethanol, water, ethanol and hexane, then was crystallized from toluene. Sublimation (255° C. at 10⁻⁵ mm Hg) provided pure material (white solid, 2.0 g, structure confirmed by NMR).

93



Compound 19



94

2,6-Dimethoxyaniline (5.5 g, 0.036 mol), 2,2'-dibromobiphenyl (13.45 g, 0.043 mol), sodium tert-butoxide (8.58 g, 0.089 mol) and $\text{Pd}_2(\text{dba})_3$ (1.15 g, 13 mmol) were charged into a 500 mL 3-neck flask with 300 mL of anhydrous toluene.

This flask was evacuated and back filled with N_2 (this procedure was repeated a total of 3 times). Lastly, (9.6 mL, 96 mmol) $\text{P}(\text{t-Bu})_3$ 1.0 M in toluene was syringed into the reaction vessel through a septum. The reaction mixture was heated at reflux for 18 h. Heating was then discontinued. The reaction mixture was diluted with 200 mL of water. The toluene layer was separated. The aqueous was extracted 1x200 mL toluene. The toluene extracts were combined, were dried over magnesium sulfate then were filtered and concentrated under vacuum. Silica gel chromatography of the crude product. Solvent system used was 20-35% methylene chloride/hexanes.


9-(2,6-Dimethoxyphenyl)-9H-carbazole (10.00 g) and pyridinium hydrochloride (50.0 g) were placed in the 250 mL round-bottom flask, equipped with magnetic stirrer and immersed in the pre-heated oil bath (230° C., 45 min). The reaction mixture was cooled down to room temperature, diluted with 400 mL water and extracted with ethyl acetate (3x150 mL). Organic fractions were combined, dried over sodium sulfate anhydrous, filtered and evaporated, providing 5.5 g of pure 2-carbazol-9-yl-benzene-1,3-diol. 2-Carbazol-9-yl-benzene-1,3-diol (5.5 g, 20 mmol) and pyridine (6.0 mL) were dissolved in 50 mL DCM (anhydrous) and cooled in the ice bath. Solution of triflic anhydride (6.0 mL) in 20 mL DCM was added dropwise upon intensive stirring, reaction mixture was warmed up to room temperature and stirred overnight. The reaction mixture was washed with water, dried over sodium sulfate, filtered and evaporated, providing crude triflate. Pure material (white solid, 6.0 g) was obtained by column chromatography on silica gel (eluent hexane/ethyl acetate 1/1 mixture).

Bis-triflate (3.13 g, 5.8 mmol), 4-dibenzothiopheneboronic acid (3.30 g, 14.5 mmol), $\text{Pd}_2(\text{dba})_3$ (212 mg, 2 mol %), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (190 mg, 4 mol %), potassium phosphate tribasic monohydrate (8.00 g), 100 mL of toluene and 1 mL of water were refluxed in the round-bottom flask under nitrogen atmosphere for 24 hours, filtered hot through silica plug and evaporated. The residue was washed with hexane, ethanol, water, ethanol and hexane, then crystallized from toluene, providing pure material (4.1 g).



95

-continued



2,6-Dimethoxyphenol (15.4 g, 0.1 mol) and 15 ml of pyridine were dissolved in 150 ml DCM and solution was cooled in the ice bath. Triflic anhydride was added dropwise upon vigorous stirring, reaction mixture was allowed to warm up to room temperature, washed with water and evaporated. Kugelrohr distillation (200° C., 2 mm Hg) provided 25 g of solidified clear oil.

2,6-Dimethoxytriflate (8.58 g, 30 mmol), 4-dibenzothiopheneboronic acid (6.84 g, 30 mmol), potassium phos-

96


phate tribasic monohydrate (20.7 g), palladium (II) acetate (672 mg), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (700 mg) and 150 ml of toluene and 3 ml of water were heated to reflux and stirred under nitrogen atmosphere for 24 hours.

Hot reaction mixture was filtered through silica plug and evaporated, the residue was subjected to column chromatography on silica (eluent hexane/ethyl acetate 4/1 mixture), providing 4-(2,6-dimethoxyphenyl)-dibenzothiophene (9.00 g, prism crystals from ethyl acetate).

4-(2,6-Dimethoxyphenyl)-dibenzothiophene (9.00 g) and pyridinium hydrochloride (20 g) were placed in the 100 mL round-bottom flask, equipped with a magnetic stirrer. The flask was immersed in the pre-heated oil bath (220° C., 1 hour), cooled down to room temperature and dissolved in 200 ml of water. The solution was extracted with ethyl acetate (4x50 mL), organic fractions were combined, dried over sodium sulfate, filtered and evaporated, providing 2-(dibenzo[b,d]thiophen-4-yl)benzene-1,3-diol (7.2 g, white solid).


2-(Dibenzo[b,d]thiophen-4-yl)benzene-1,3-diol (7.2 g) was dissolved in 150 mL of dry DCM, containing 15 mL of pyridine. Solution was cooled in the ice bath, then triflic anhydride (18 mL in 25 mL of DCM) was added dropwise. Reaction was allowed to warm up to room temperature and washed with 10% sodium bicarbonate solution in water. DCM was evaporated, and the residue was subjected to column chromatography, providing 14.5 g of bis-triflate.

Triflate (5.56 g, 10 mmol), 4-dibenzothiopheneboronic acid (5.35 g, 25 mmol), palladium (II) acetate (44 mg), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (161 mg) and potassium phosphate tribasic trihydrate (7.00 g) were suspended in 100 ml of toluene and refluxed under nitrogen atmosphere for 24 hours. Hot reaction mixture was filtered and evaporated, the residue was crystallized from toluene twice. Sublimation (245° C., 10⁻⁵ mm Hg) provided 5.0 g of target compound.



97

-continued




The 300 ml round-bottom flask equipped with reflux condenser and magnetic stirrer was charged with 2,6-dimethoxybiphenyl triflate (10.00 g, 35 mmol), phenyl boronic acid (4.25 g, 35 mmol), potassium phosphate tribasic monohydrate (24.1 g), palladium (II) acetate (156 mg, 2 mol %), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (573 mg, 4 mol %), toluene (100 ml) and water (2 ml). The reaction mixture was refluxed overnight, filtered through silica plug and evaporated. The residue was subjected to column chromatography on silica gel (eluent hexane/ethyl acetate 4/1 mixture), providing dimethoxybiphenyl as white solid (5.00 g).

2,6-Dimethoxybiphenyl (5.00 g) and 15 g of pyridinium hydrochloride were placed in the round-bottom flask and immersed in the oil bath (210° C., 1.5 hours). Then the reaction was cooled down to room temperature, diluted with 200 ml of water and extracted with ethyl acetate (4×50 ml). Organic fractions were combined, dried over sodium sulfate and evaporated. The residue was subjected to column chromatography on silica gel (eluent hexane/ethyl acetate 1/1 mixture), providing 3.3 of biphenyl-2,6-diol as yellow solid.

Biphenyl-2,6-diol (7.2 g, 39 mmol) was dissolved in DCM (100 ml) and pyridine (10 ml). The solution was cooled in the ice bath, and triflic anhydride (27.3 g) was added dropwise upon vigorous stirring. The reaction mixture was allowed to warm up to room temperature, was washed with water, dried and evaporated. The residue was subjected to column chromatography on silica gel (eluent hexane/ethyl acetate 4/1 mixture), providing 8.00 g of pure triflate.


The triflate (7.4 g, 16.4 mmol), 4-dibenzothiophene boronic acid (11.2 g, 49 mmol), potassium phosphate tribasic monohydrate (22.7 g), palladium (II) acetate (70 mg), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (270 mg) and 100 ml of toluene were refluxed overnight under nitrogen atmosphere. The hot solution was filtered through silica plug and evaporated. The residue was crystallized hexane/ethyl acetate, providing target product as white solid (5.01 g). The material was additionally purified by sublimation (220° C., 10⁻⁵ mm Hg).


98



The 300 ml round-bottom flask equipped with reflux condenser and magnetic stirrer was charged with 2-bromoaniline (8.00 g, 46.5 mmol), 4-dibenzothiopheneboronic acid (10.5 g, 46.5 mmol), potassium carbonate (20 g, saturated solution in water), tetrakis(triphenylphosphine)palladium (0) (500 mg) and 100 ml of toluene. The reaction mixture was refluxed overnight under nitrogen atmosphere, filtered through silica plug and evaporated. Product was purified by column chromatography on silica gel, eluent hexane/ethyl acetate 4/1 mixture, providing 2-(dibenzo[b,d]thiophen-4-yl)aniline (10.1 g) as yellow oil.

2-(Dibenzo[b,d]thiophen-4-yl)aniline (10.1 g, 36.4 mmol), 2,2'-dibromobiphenyl (12.0 g, 38.5 mmol), sodium tert-butoxide (7.00 g, 72.9 mmol), and Pd₂(dba)₃ (330 mg) were charged into a 500 mL 3-neck flask with 300 mL of anhydrous toluene. This flask was evacuated and back filled with N₂ (this procedure was repeated a total of 3 times). Lastly, (5 mL, 96 mmol) P(t-Bu)₃ 1.0 M in toluene was syringed into the reaction vessel through a septum. The reaction mixture was heated at reflux for 18 h. Heating was then discontinued. The reaction mixture was diluted with 200 mL of water. The toluene layer was separated. The aqueous was extracted 1×200 mL toluene. The toluene extracts were combined, were dried over magnesium sulfate then were filtered and concentrated under vacuum. Crude material was washed with hexane and crystallized from toluene-DCM. The material was additionally purified by sublimation (190° C., 10⁻⁵ mm Hg), providing 6.23 g of pure crystalline material.





The 300 mL round-bottom flask equipped with magnetic stirrer and reflux condenser was charged with 2,6-dibromopyridine (2.20 g, 9.2 mmol), 4-dibenzothiopheneboronic acid (4.62 g, 20 mmol), Pd₂(dba)₃ (180 mg), S-phos (220 mg), potassium triphosphate (6.00 g) and 100 mL of anhydrous toluene. The flask was filled with nitrogen, and solution was stirred under reflux overnight. Then hot reaction mixture was filtered through silica plug, silica was washed with hot toluene. Organic fractions were combined and evaporated. The residue was subjected to column chromatography on silica gel (eluent hexane/ethyl acetate 4/1 mixture), providing target compound as white solid (3.01 g). Material was additionally purified by sublimation (225° C. at 10⁻⁵ mm Hg) and used for device fabrication.

100

compound as the ETL2 and 400 or 450 Å of tris-8-hydroxyquinoline aluminum (Alq₃) as the ETL1.

Comparative Example 1 was fabricated similarly to the Device Examples except that CBP was used as the host.

The materials for the Emissive Layer, and the materials and thicknesses for ETL 2 and ETL1, of Device Examples 1-8 are provided in Table 2. The devices were tested, and the results measured are provided in Table 3. Compound is abbreviated using the term Cmpd.

TABLE 2

Device Example	Host	Dopant wt %	ETL2 (Å)	ETL1 (Å)	ITO thickness (Å)
Comparative 1	CBP	P1 10%	HPT (50)	Alq ₃ (450)	1200
1	Cmpd 1	P1 10%	Cmpd 1 (100)	Alq ₃ (400)	1200
2	Cmpd 1	P6 10%	Cmpd 1 (100)	Alq ₃ (400)	1200
3	Cmpd 1	P1 10%	HPT (50)	Alq ₃ (450)	1200
4	Cmpd 1	P6 10%	HPT (50)	Alq ₃ (450)	1200
5	Cmpd 2	P1 9%	HPT (50)	Alq ₃ (400)	800
6	Cmpd 3	P1 9%	HPT (50)	Alq ₃ (400)	800
7	Cmpd 4	P1 9%	HPT (50)	Alq ₃ (400)	1200
8	Cmpd 5	P1 9%	HPT (50)	Alq ₃ (400)	1200

TABLE 3

Device Example	CIE		Emission		At L = 1000 cd/m ²				At J = 40 mA/cm ²	
					LE	EQE	PE		L ₀	LT _{80%}
	X	Y	(nm)	(nm)	V (V)	(cd/A)	(%)	(lm/W)	(cd/m ²)	(hr)
Comparative 1	0.346	0.613	522	75	6.2	57.0	16	28.9	13,304	105
1	0.337	0.619	523	73	7.4	48.2	13	20.5	13,611	325
2	0.328	0.620	520	73	7.4	36.8	10	15.6	12,284	340
3	0.338	0.618	524	73	6.3	60.3	17	30.1	13,683	300
4	0.328	0.621	520	73	6.4	52	14.4	25.5	14,014	187
5	0.336	0.623	524	72	5.9	53.8	15	28.7	16389	18
6	0.349	0.614	528	73	6.1	45.5	12	23.2	15672	28
7	0.355	0.609	528	74	6.8	39.6	11	18.3	13403	98
8	0.353	0.613	528	72	6.3	49.5	14	24.7	15442	5.5

Device Examples

All example devices were fabricated by high vacuum (<10⁻⁷ Torr) thermal evaporation. The anode electrode is ~800 Å, 1200 Å or 2000 Å of indium tin oxide (ITO), or 800 Å Sapphire/IZO. The cathode consists of 10 Å of LiF followed by 1000 Å of Al. All devices are encapsulated with a glass lid sealed with an epoxy resin in a nitrogen glove box (<1 ppm of H₂O and O₂) immediately after fabrication, and a moisture getter was incorporated inside the package.

The organic stack of Device Examples 1-8 consisted of sequentially, from the ITO surface (1200 Å), 100 Å of P1 as the hole injection layer (HIL), 300 Å of 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (α-NPD) as the hole transporting layer (HTL), 300 Å of the invention compound doped with 10 or 15 wt % of an Ir phosphorescent compound as the emissive layer (EML), 50 Å or 100 Å of HPT or the invention

From Device Examples 1-8, it can be seen that the Invention Compounds as hosts in green phosphorescent OLEDs give high device efficiency (LE>35 cd/A at 1000 cd/m²), indicating dibenzothiophene as a chromophore has triplet energy high enough for efficient green electrophosphorescence. Most notably is the high stability of the device incorporating Compounds 1 as the host. Device Example 3 and Comparative Example 1 are only different in the host. Device Example 3 uses Compound 1 as the host whereas Comparative Example 1 uses the commonly used host CBP. The lifetime, T_{80%} (defined as the time required for the initial luminance, L₀, to decay to 80% of its value, at a constant current density of 40 mA/cm² at room temperature) are 300 hours and 105 hours respectively, with Device Example 3 having a

101

slightly higher L_{10} . This translates to almost a 3 fold improvement in the device stability. The invention compounds may function well as the enhancement layer (ETL2). Device Example 1 and Device Example 3 both have Compound 1 as the host, but Compound 1 and 2,3,6,7,10,11-hexaphenyltriphenylene (HPT) as the enhancement layer respectively. They have $T_{0.8}$ of 325 and 300 hours respectively with similar L_{10} (~ 13600 cd/m²), indicating the good performance of the invention compound as the enhancement layer.

The data suggest that arylbenzothiophenes, particularly biphenyl substituted dibenzothiophenes, are excellent hosts and enhancement layer for phosphorescent OLEDs, providing as least the same efficiency and multiple times of improvement in stability compared to the commonly used CBP as the host.

A number of devices were fabricated having two different doped emissive layers, where the devices do not include a hole transport layer using a material such as NPD. Table 4 shows the structures for these devices. Table 5 shows mea-

102

sured experimental results for these devices. In general, the devices had an ITO anode, a hole injection layer of LG101TM (purchased from LG Chemical, Korea), and an emissive layer having a first organic layer and a second organic layer with an interface in between. Some of the devices had an enhancement layer (ETL2). All of the devices had an electron transport layer (ETL1) of LG201, available from the same source as LG101. Devices 9-16 have first and second organic layers with the same non-emissive materials, and different phosphorescent materials, where the first organic layer additionally includes a lower energy emissive material. All of devices 9-16 include emissive layers having a first and second organic layer with an interface in between. In all of these devices, the concentration of phosphorescent material is higher in the first (closer to anode) organic layer. The materials and thicknesses for Device Examples 9-16 are provided in Table 4. The devices were tested, and the results measured are provided in Table 5. Compound is abbreviated using the term Cmpd. All percentages are wt % unless otherwise noted.

TABLE 4

Device	Anode	HIL	EML1	EML2	ETL2	ETL1
9	ITO [1200 Å]	LG101 [100 Å]	Cmpd 1: P4 (30%):P5 (0.5%) [300 Å]	Cmpd 1: P3 (18%) [250 Å]	none	LG201 [300 Å]
10	ITO [1200 Å]	LG101 [100 Å]	Cmpd 1: P4 (30%):P5 (0.5%) [300 Å]	Cmpd 1: P3 (12%) [250 Å]	none	LG201 [300 Å]
11	ITO [1200 Å]	LG101 [100 Å]	Cmpd 1: P4 (30%):P5 (0.5%) [300 Å]	Cmpd 1: P3 (24%) [250 Å]	none	LG201 [300 Å]
12	ITO [1200 Å]	LG101 [100 Å]	Cmpd 1: P4 (30%):P5 (0.5%) [300 Å]	Cmpd 1: P3 (24%) [250 Å]	Cmpd 1 [50 Å]	LG201 [300 Å]
13	ITO [1200 Å]	LG101 [100 Å]	Cmpd 1: P4 (30%):P5 (0.5%) [300 Å]	Cmpd 1: P3 (18%) [250 Å]	Cmpd 1 [50 Å]	LG201 [300 Å]
14	ITO [1200 Å]	LG101 [100 Å]	Cmpd 1: P4 (30%):P5 (0.5%) [300 Å]	Cmpd 1: P3 (12%) [250 Å]	Cmpd 1 [50 Å]	LG201 [300 Å]
15	ITO [1200 Å]	LG101 [200 Å]	Cmpd 1: P4 (30%):P5 (0.5%) [200 Å]	Cmpd 1: P3 (18%) [250 Å]	Cmpd 1 [50 Å]	LG201 [300 Å]
16	ITO [1200 Å]	LG101 [100 Å]	Cmpd 1: P4 (30%):P5 (0.5%) [200 Å]	Cmpd 1: P3 (18%) [250 Å]	Cmpd 1 [50 Å]	LG201 [300 Å]

TABLE 5

Device	At 1,000 cd/m ²							
	V	LE	EQE	PE	At 10 mA/cm ²		At L_{10} = 1,000 cd/m ²	
	(V)	(cd/A)	(%)	(lm/W)	CIE x	CIE y	LT _{70%} (hr)	LT _{60%} (hr)
9	6.1	23.7	10.9	12.3	0.467	0.457	Not measured	Not measured
10	6.2	31.7	15.1	16.1	0.500	0.445	35,500	100,000
11	6.2	14.9	6.9	7.5	0.467	0.457	Not measured	Not measured
12	6.1	29.5	13.5	15.2	0.456	0.460	78,000	140,000
13	6.3	32.4	15.3	16.1	0.437	0.451	90,000	230,000
14	7.0	33.2	16.3	15.0	0.505	0.439	88,000	180,000
15	6.4	29.0	13.9	14.3	0.472	0.449	Not measured	Not measured
16	6.2	29.4	14.2	14.9	0.467	0.448	Not measured	Not measured

From Device Examples 9, 10 and 11, it can be seen that the efficiency of the device decreased with increasing concentration of P3, and the device CIE red-shifted with decreasing P3 concentration. Device Examples 9-11 differ only in the concentration of the emissive compound P3 (i.e., devices contain varying concentrations of P3) as all of Device Examples 9-11 contained Inventive Compound 1 as the host, and were without a blocking layer between the EML and the LG201.

From Device Examples 12, 13, and 14, it can be seen that the efficiency of the device decreased with increasing concentration of P3, the device CIE red-shifted with decreasing P3 concentration, and device operating voltage increased with decreasing concentration of P3. Devices 12-14 differ only in the concentration of the emissive compounds P3, as all of devices 12-14 contained the inventive Compound 1 as the host and the blocking layer situated between the EML and ETL. Notably, Compound 1 is an efficient electron transport and blocking layer material, because the efficiency of each of Devices 12, 13, and 14 was shown to exceed that of Devices 9, 10, and 11. Also, the electron stability of Compound 1 was found to be significant, because Devices 12-14 demonstrated an $LT_{60\%}$ stability that exceeded 100,000 hrs from 1,000 cd/m^2 initial luminance.

From Device Examples 15 and 16, it can be seen that the devices show variation in device characteristics (e.g., CIE, efficiency) when the injection layer LG101 thickness is varied (e.g., 200 Å versus 100 Å).

The organic stack of Device Examples 17-20 consisted of sequentially, from the ITO surface, 100 Å of P1 as the hole injection layer (HIL), 300 Å of NPD as the hole transport layer (HTL), 300 Å of the invention compound doped with 10 wt % or 15 wt % of P1, an Ir phosphorescent compound, as the emissive layer (EML), 50 Å or 100 Å of HPT or the invention compound as enhancement layer (ETL2), an electron transport layer (ETL1) of Alq_3 having a thickness identified in Table 5, and a LiF/Al cathode. In particular, the BL and ETL have a sum total of 500 Å. Thus, the general device structure for the devices of Table 5 was: ITO(1200 Å)/P1 (100 Å)/NPD (300 Å)/Host: P1 x % (300 Å)/ETL2 (50 Å or 100 Å)/ Alq_3 (400 Å or 450 Å)/LiF(10 Å)/Al(1000 Å).

TABLE 6

Device example	Host Cmpd.	Dopant x %	ETL2 (Å)	ETL1 (Å)	At 1000 cd/m^2				At 40 mA/cm^2			
					CIE		V (V)	L.E. (cd/A)	EQE (%)	PE (lm/W)	L_0 (cd/m^2)	$LT_{80\%}$ (hr)
					X	Y						
17	23	P1 10%	23 (100 Å)	Alq_3 (400 Å)	0.355	0.605	7.1	42.2	11.7	18.66	13,580	160
18	23	P1 15%	23 (100 Å)	Alq_3 (450 Å)	0.353	0.609	6.8	42.1	11.6	19.44	14,521	155
19	23	P1 1%	HPT (50 Å)	Alq_3 (450 Å)	0.355	0.607	6.8	46.9	13	21.66	14,728	94
20	23	P1 15%	HPT (50 Å)	Alq_3 (400 Å)	0.352	0.611	6.6	44.9	12.3	21.36	15,070	63

The data in Table 6 describes the performance of Devices Examples 17-20. The voltage, luminous efficiency, external quantum efficiency and power efficiency data were measured at 1000 cd/m^2 (display level brightness). The lifetime was measured at accelerated conditions: 40 ma/cm^2 DC. The initial device luminance (L_0) at life-test conditions (40 mA/cm^2) is also shown in Table 5. Compound 23 was used as a host for the green phosphorescent emitter P1. Two different dopant concentrations (10% or 15%) and two different ETL1 layers (Alq_3 of 400 Å or 450 Å) were varied in the devices and tested experimentally. The data show no significant difference in the device performance due to dopant concentration variation.

However, there was a difference in the device performance due to variation in the ETL1 layer. In devices having HPT as the ETL1 layer, the device efficiency was slightly higher due to stronger BL properties of HPT. However, the lifetime of the devices with Compound 23 as the ETL1 was longer. The data suggests that Compound 23 can be used as an efficient host for green phosphorescent emitter and as a ETL1 in the device. The stability of devices having Compound 23 as the ETL1 layer in the devices is higher than the stability of devices having a similar overall structure except with HPT as the ETL1 layer.

The organic stack of Device Examples 21-24 consisted of sequentially, from the anode surface, 100 Å of P1 or LG101 as the hole injection layer (HIL), 300 Å of NPD as the hole transport layer (HTL) or no HTL, 300 Å of the invention compound doped with 9 wt %, 15 wt % or 20 wt % of P2 or P7 Ir phosphorescent compounds as the emissive layer (EML), 50 Å, 150 Å or 250 Å of H1 as the enhancement layer (ETL2), and 200 Å, 300 Å or 400 Å of Alq_3 as the electron transport layer (ETL1). The materials and thicknesses of Device Examples 21-24 are provided in Table 7. The devices were tested, and the corresponding results measured are provided in Table 8.

TABLE 7

De-vice	Anode	HIL	HTL	EML	ETL2	ETL1
21	ITO [800 Å]	LG101 [100 Å]	none	H1:P2 15% [600 Å]	H1 [250 Å]	Alq_3 [200 Å]
22	ITO [2000 Å]	LG101 [100 Å]	NPD [300 Å]	H1:P2 9% [300 Å]	H1 [50 Å]	Alq_3 [400 Å]
23	ITO [800 Å]	P1 [100 Å]	NPD [300 Å]	H1:P7 9% [300 Å]	H1 [50 Å]	Alq_3 [400 Å]
24	Sapphire/ IZO[800 Å]	LG101 [100 Å]	none	H1:P7 20% [300 Å]	H1 [150 Å]	Alq_3 [300 Å]

TABLE 8

Device	At 1000 cd/m^2				At L_0 =		
	V	LE	EQE	PE	At 10 mA/cm^2		1000 cd/m^2
	(V)	(cd/A)	(%)	(lm/W)	CIE x	CIE y	$LT_{80\%}$ (hr)
21	12.9	10.0	5.3	2.4	0.160	0.285	352
22	7.6	10.9	6.6	4.5	0.155	0.234	77
23	9.0	12.1	6.0	4.2	0.162	0.317	151
24	7.1	8.9	5.5	4.0	0.145	0.232	205

105

From Devices 21, 22, 23, and 24 it can be seen that the devices demonstrate differences between device structures having an emissive layer containing H1 and an emissive compound P2 or P7. Device Example 21 did not have an HTL, and used a thick EML to enhance device operational stability. The measured CIE coordinates of Device Example 21 were not blue saturated, so the structures of Device Examples 22, 23, and 24 used a 30 nm EML. Device Example 22 also incorporated a 200 nm ITO layer to saturate the device blue CIE. Device Example 23 was a standard blue PHOLED that was not optimized for operational stability. Device Example 24 was a blue PHOLED using the same emissive compound P7 as used in Device Example 23. However, Device Example 24 had several features that enabled longevity such as no NPDP, sapphire heat sink substrate, a thick blocking layer, and high emitter concentration. Hence, the $LT_{80\%}$ of Device Example 24 exceeded the $LT_{80\%}$ of Device Example 23, and Device Example 24 had improved blue CIE compared to Device Example 23.

FIG. 3 shows an organic light emitting device having only a layer with a high hole conductivity between an emissive layer and the anode, an enhancement layer of the same material used as a non-emissive host in the emissive layer, and an emissive layer having first and second organic layers with different concentrations of phosphorescent material and non-emissive materials, where the concentration of phosphorescent material in the second organic layer is variable. The device of FIG. 3 includes a 10 nm thick hole injection layer of LG101, a 30 nm thick first organic emissive layer of H1 doped with 30 wt % P2, a 30 nm thick second organic emissive layer of H1 doped with X wt % P2, a 25 nm thick enhancement layer of H1, a 20 nm thick electron transport layer of Alq_3 , and a LiF/Al cathode. X varies from 10 wt % to 18 wt % in the devices fabricated, with devices at X=10, 14 and 18 wt % as indicated in the legends for FIG. 4.

FIG. 4 shows a plot of normalized luminescence versus time for the device of FIG. 3.

FIG. 5 shows a plot of external quantum efficiency versus luminance for the device of FIG. 3.

FIG. 6 shows a plot of power efficacy versus luminance for the device of FIG. 3.

FIG. 7 shows a plot of luminance versus voltage for the device of FIG. 3.

FIG. 8 shows a plot of EL intensity versus wavelength for the device of FIG. 3.

FIG. 9 shows an organic light emitting device having only a layer with a high hole conductivity between an emissive layer and the anode, an enhancement layer of the same material used as a non-emissive host in the emissive layer, and an emissive layer having first and second organic layers with different phosphorescent materials in the first and second organic layers, where the concentration of phosphorescent material in the second organic emissive layer is variable. The device of FIG. 9 includes a 10 nm thick hole injection layer of LG101, a 30 nm thick first organic emissive layer of H1 doped

106

with 30 wt % P1, a 30 nm thick second organic emissive layer of H1 doped with X wt % P2, a 25 nm thick enhancement layer of H1, a 20 nm thick electron transport layer of Alq_3 , and a LiF/Al cathode. X varies from 10 wt % to 18 wt % in the devices fabricated, with devices at X=10, 14 and 18 wt % as indicated in the legends for FIG. 4. The device of FIG. 9 is very similar to that of FIG. 3, with the difference being that the device of FIG. 9 uses different emissive phosphorescent material in the first and second organic emissive layers, while the device of FIG. 3 uses the same phosphorescent material in both layers. The concentrations of the phosphorescent materials are the same in the device of FIG. 3 compared to the device of FIG. 9.

FIG. 10 shows a plot of external quantum efficiency versus luminance for the device of FIG. 9.

FIG. 11 shows a plot of power efficacy versus luminance for the device of FIG. 9.

FIG. 12 shows a plot of luminance versus voltage for the device of FIG. 9.

FIG. 13 shows a plot of EL intensity versus wavelength for the device of FIG. 9.


The device of FIG. 9 may be compared to the device of FIG. 3. In terms of device architecture, the devices are similar except in the emissive layer, where the device of FIG. 9 has an emissive layer doped with phosphorescent emitter P1 and another emissive layer doped phosphorescent emitter P2, whereas the device of FIG. 3 has only phosphorescent emitter P2. Both devices have a step in dopant concentration, and similar concentrations even in the layers where the actual dopant is different. Several points can be understood from comparing these two device architectures. First, the device of FIG. 9 exhibits a broad emission spectra that is a combination of emission from both P1 and P2. As a result, it can be inferred that the device of FIG. 3 is emitting from both the layer doped with 30% P2 and the layer doped with a lesser concentration of P2. Comparing FIG. 5 to FIG. 10, it can be seen that the device of FIG. 9 has better charge balance than the device of FIG. 3, as evidenced by a relatively flat external quantum efficiency over three orders of magnitude for the device of FIG. 9 as compared to two orders of magnitude for the device of FIG. 3.

It is understood that the various embodiments described herein are by way of example only, and are not intended to limit the scope of the invention. For example, many of the materials and structures described herein may be substituted with other materials and structures without deviating from the spirit of the invention. The present invention as claimed may therefore include variations from the particular examples and preferred embodiments described herein, as will be apparent to one of skill in the art. It is understood that various theories as to why the invention works are not intended to be limiting.


107

The invention claimed is:

1. An organic light emitting device, comprising:
an anode;
a cathode;
an emissive layer; and
an enhancement layer, wherein



is in the enhancement layer;
wherein the emissive layer comprises an emissive dopant
selected from the group consisting of:




wherein R_1 , R_2 , and R_3 are independently selected from the
group consisting of any alkyl, alkoxy, amino, alkenyl,
alkynyl, aryl, heteroaryl, and hydrogen,
wherein (a) R_1 and R_3 form a fused ring that is, optionally,
further substituted, (b) R_2 and R_3 form a fused ring that
is, optionally, further substituted, or (c) both.


2. The device of claim 1, wherein R_2 and R_3 form a fused
ring that is, optionally, further substituted.

108

3. The device of claim 2, wherein the emissive dopant
comprises:



4. The device of claim 2, wherein the emissive dopant
comprises:



5. The device of claim 1, wherein the emissive layer com-
prises H1 as a host.

6. The device of claim 1, wherein the enhancement layer is
a hole blocking layer.

* * * * *

专利名称(译)	磷光发光二极管中含二苯并噻吩的材料		
公开(公告)号	US9123903	公开(公告)日	2015-09-01
申请号	US14/026868	申请日	2013-09-13
[标]申请(专利权)人(译)	环球展览公司		
申请(专利权)人(译)	通用显示器公司		
当前申请(专利权)人(译)	通用显示器公司		
[标]发明人	LIN CHUN DYATKIN ALEXEY ELSHENAWY ZEINAB YEAGER WALTER		
发明人	LIN, CHUN DYATKIN, ALEXEY ELSHENAWY, ZEINAB YEAGER, WALTER		
IPC分类号	H01L51/54 C07D409/10 C07D409/14 C07D413/10 C07D471/04 C07D487/04 C07F5/02 C07F7/08 C07D405/14 H01L51/00 C07D209/86 C07D235/18 C07D235/20 C07D333/76		
CPC分类号	H01L51/0085 C07D209/86 C07D235/18 C07D235/20 C07D333/76 C07D405/14 C07D409/10 C07D409/14 C07D413/10 C07D471/04 C07D487/04 C07F5/027 C07F7/0814 H01L51/0071 H01L51/0074 C09K11/025 C09K11/06 C09K2211/1007 C09K2211/1029 C09K2211/1044 C09K2211/185 H01L51/0067 H01L51/0072 H01L51/5016		
代理机构(译)	DUANE MORRIS LLP		
审查员(译)	CLARK , GREGORY		
优先权	61/017480 2007-12-28 US		
其他公开文献	US20140008643A1		
外部链接	Espacenet USPTO		

摘要(译)

一种有机发光器件，包括阳极，阴极，增强层和发光层，所述发光层包括含有苯基-咪唑配体的均配型铱配合物，所述配体包括至少一个稠合取代基。增强层还包括新的二苯并噻吩和含二苯并呋喃的化合物，其可用作增强层中的材料。

