



US01052277B2

(12) **United States Patent**  
**Ushikubo et al.**

(10) **Patent No.:** **US 10,522,777 B2**  
(45) **Date of Patent:** **Dec. 31, 2019**

(54) **DISPLAY DEVICE WITH CAP LAYER**

USPC ..... 257/40, 98; 438/29  
See application file for complete search history.

(71) Applicant: **Japan Display Inc.**, Tokyo (JP)

(72) Inventors: **Takahiro Ushikubo**, Tokyo (JP);  
**Norihisa Maeda**, Tokyo (JP)

(73) Assignee: **Japan Display Inc.**, Tokyo (JP)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **15/730,162**

(22) Filed: **Oct. 11, 2017**

(65) **Prior Publication Data**

US 2018/0123068 A1 May 3, 2018

(30) **Foreign Application Priority Data**

Oct. 27, 2016 (JP) ..... 2016-210298

(51) **Int. Cl.**

**H01L 51/50** (2006.01)  
**H01L 27/32** (2006.01)  
**H01L 51/52** (2006.01)  
**H01L 51/00** (2006.01)  
**H01L 29/08** (2006.01)  
**H01L 35/24** (2006.01)

(52) **U.S. Cl.**

CPC ..... **H01L 51/504** (2013.01); **H01L 27/3244** (2013.01); **H01L 51/5064** (2013.01); **H01L 51/5092** (2013.01); **H01L 51/5253** (2013.01); **H01L 51/5265** (2013.01)

(58) **Field of Classification Search**

CPC ..... H01L 51/5265; H01L 27/3211; H01L 27/3244; H01L 51/504; H01L 51/5064; H01L 51/5092; H01L 51/5076; H01L 27/3246

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,608,991 B2 10/2009 Abe et al.  
2006/0103929 A1\* 5/2006 Morisawa ..... G02B 5/22 359/452  
2016/0043154 A1\* 2/2016 Choi ..... H01L 27/3258 257/40  
2016/0104868 A1\* 4/2016 Kang ..... H01L 51/5275 257/40  
2016/0133880 A1\* 5/2016 Lee ..... H01L 51/5281 257/40

(Continued)

FOREIGN PATENT DOCUMENTS

JP 2006-173092 A 6/2006  
JP 2008-218081 A 9/2008  
JP 2012-038555 A 2/2012

*Primary Examiner* — Nduka E Ojeh


(74) *Attorney, Agent, or Firm* — Michael Best & Friedrich LLP

(57) **ABSTRACT**

Provided is a display device having a first pixel and a second pixel adjacent to the first pixel. The first pixel includes a first pixel electrode, a first EL layer over the first pixel electrode, and a second electrode over the first EL layer. The second pixel includes a second pixel electrode, a second EL layer over the second pixel electrode, and the second electrode over the second EL layer. The display device further possesses a first cap layer over the second electrode, a second cap layer over the first cap layer and overlapping with the first EL layer, and a third cap layer covering the second cap layer, overlapping with the first EL layer and the second EL layer, and in contact with the first cap layer in a region overlapping with the second EL layer.

**20 Claims, 15 Drawing Sheets**

100



(56)

**References Cited**

## U.S. PATENT DOCUMENTS

|              |      |         |             |              |
|--------------|------|---------|-------------|--------------|
| 2016/0155979 | A1 * | 6/2016  | Yim .....   | H01L 51/5275 |
|              |      |         |             | 257/40       |
| 2016/0197308 | A1 * | 7/2016  | Jeong ..... | H01L 51/5275 |
|              |      |         |             | 257/40       |
| 2016/0240589 | A1 * | 8/2016  | Jeong ..... | H01L 27/322  |
| 2016/0276421 | A1 * | 9/2016  | Lee .....   | H01L 27/3272 |
| 2017/0104036 | A1 * | 4/2017  | Maeda ..... | H01L 27/3211 |
| 2017/0330923 | A1 * | 11/2017 | Chung ..... | H01L 27/124  |
| 2018/0053918 | A1 * | 2/2018  | Woo .....   | H01L 51/5284 |
| 2018/0182823 | A1 * | 6/2018  | Ito .....   | H01L 51/5256 |

\* cited by examiner

FIG. 1







FIG. 3






FIG. 5

200




FIG. 6

300




FIG. 7




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 9A




FIG. 9B




FIG. 9C




FIG. 10A




FIG. 10B




FIG. 11A




FIG. 11B




FIG. 12A




FIG. 12B




FIG. 13




FIG. 14





FIG. 15



1

**DISPLAY DEVICE WITH CAP LAYER****CROSS REFERENCE TO RELATED APPLICATIONS**

This application is based on and claims the benefit of priority from the prior Japanese Patent Application No. 2016-210298, filed on Oct. 27, 2016, the entire contents of which are incorporated herein by reference.

**FIELD**

An embodiment of the present invention relates to a light-emitting element, a display device including the light-emitting element, and a manufacturing method of the display device.

**BACKGROUND**

An organic EL (Electroluminescence) display device is represented as an example of a display device. An organic EL display device has an organic light-emitting element (hereinafter, referred to as a light-emitting element) in each of a plurality of pixels formed over a substrate. A light-emitting element has a layer (hereinafter, referred to as an organic layer or an EL layer) including an organic compound between a pair of electrodes (cathode and anode) and is operated by supplying current between the pair of electrodes. A color provided by a light-emitting element is mainly determined by a light-emitting material in an EL layer, and light emission with a variety of colors can be obtained by appropriately selecting a light-emitting material. Arrangement of a plurality of light-emitting elements giving different colors on a substrate makes it possible to reproduce a full-color image.

An emission color and emission intensity of a light-emitting element can be also controlled by utilizing a light-interference effect in and outside the light-emitting element. For example, in Japanese patent application publications No. 2012-38555, 2008-218081, and 2006-173092, light-emission generated in an EL layer is resonated and amplified between a pair of electrodes and the light extracted from the EL layer is further resonated and amplified in an optical adjustment layer in contact with one of the pair of electrodes, by which the emission color is adjusted and the emission intensity is controlled.

**SUMMARY**

An embodiment of the present invention is a display device having a first pixel and a second pixel adjacent to the first pixel. The first pixel includes a first pixel electrode, a first EL layer over the first pixel electrode, and a second electrode over the first EL layer. The second pixel includes a second pixel electrode, a second EL layer over the second pixel electrode, and the second electrode over the second EL layer. The display device further possesses a first cap layer over the second electrode, a second cap layer over the first cap layer and overlapping with the first EL layer, and a third cap layer covering the second cap layer, overlapping with the first EL layer and the second EL layer, and in contact with the first cap layer in a region overlapping with the second EL layer.

An embodiment of the present invention is a display device having a first pixel, a second pixel adjacent to the first pixel, and a third pixel adjacent to the second pixel. The first pixel includes a first pixel electrode, a first EL layer over the

2

first pixel electrode, and a second electrode over the first EL layer. The second pixel includes a second pixel electrode, a second EL layer over the second pixel electrode, and the second electrode over the second EL layer. The third pixel includes a third pixel electrode, a third EL layer over the third pixel electrode, and the second electrode over the third EL layer. The display device further possesses a first cap layer over the second electrode, a second cap layer over the first cap layer and overlapping with the first EL layer, and a third cap layer covering the second cap layer, overlapping with the first EL layer, the second EL layer, and the third EL layer, and in contact with the first cap layer in a region overlapping with the third EL layer.

**BRIEF DESCRIPTION OF DRAWINGS**

FIG. 1 is a schematic perspective view of a display device according to an embodiment of the present invention;

FIG. 2 is a schematic cross-sectional view of a display device according to an embodiment of the present invention;

FIG. 3 is a diagram showing the dependence of a light-interference effect on an optical film thickness;

FIG. 4A to FIG. 4C are diagrams showing emission behavior of a display device according to an embodiment of the present invention;

FIG. 5 is a schematic cross-sectional view of a display device according to an embodiment of the present invention;

FIG. 6 is a schematic cross-sectional view of a display device according to an embodiment of the present invention;

FIG. 7 is a schematic cross-sectional view of a display device according to an embodiment of the present invention;

FIG. 8A to FIG. 8C are schematic cross-sectional views for explaining a manufacturing method of a display device according to an embodiment of the present invention;

FIG. 9A to FIG. 9C are schematic cross-sectional views for explaining a manufacturing method of a display device according to an embodiment of the present invention;

FIG. 10A and FIG. 10B are schematic cross-sectional views for explaining a manufacturing method of a display device according to an embodiment of the present invention;

FIG. 11A and FIG. 11B are schematic cross-sectional views for explaining a manufacturing method of a display device according to an embodiment of the present invention;

FIG. 12A and FIG. 12B are schematic cross-sectional views for explaining a manufacturing method of a display device according to an embodiment of the present invention;

FIG. 13 is a schematic cross-sectional view for explaining a manufacturing method of a display device according to an embodiment of the present invention;

FIG. 14 is a schematic cross-sectional view for explaining a manufacturing method of a display device according to an embodiment of the present invention; and

FIG. 15 is a schematic cross-sectional view for explaining a manufacturing method of a display device according to an embodiment of the present invention.

**DESCRIPTION OF EMBODIMENTS**

Hereinafter, the embodiments of the present invention are explained with reference to the drawings. The invention can be implemented in a variety of different modes within its concept and should not be interpreted only within the disclosure of the embodiments exemplified below.

The drawings may be illustrated so that the width, thickness, shape, and the like are illustrated more schematically compared with those of the actual modes to provide a clearer explanation. However, they are only an example, and do not

limit the interpretation of the invention. In the specification and the drawings, the same reference number is provided to an element that is the same as that which appears in preceding drawings, and a detailed explanation may be omitted as appropriate.

In the present invention, when a plurality of films is formed by performing etching or light irradiation on one film, the plurality of films may have functions or rules different from each other. However, the plurality of films originates from a film formed as the same layer in the same process and has the same layer structure and the same material. Therefore, the plurality of films is defined as films existing in the same layer.

In the specification and the scope of the claims, unless specifically stated, when a state is expressed where a structure is arranged "over" another structure, such an expression includes both a case where the substrate is arranged immediately above the "other structure" to be in contact with the "other structure" and a case where the structure is arranged over the "other structure" with an additional structure therebetween.

### First Embodiment

#### 1. Outline Structure

A schematic perspective view of a display device 100 according to an embodiment of the present invention is shown in FIG. 1. The display device 100 has, over one surface (top surface) of a substrate 110, a plurality of pixels 102 arranged in a row direction and a column direction, a display region 104 structured by the plurality of pixels 102, scanning-line driver circuits 106, and a data-line driver circuit 108. A variety of signals for driving the pixels 102 is input from an external circuit (not shown) to the scanning-line driver circuits 106 and the data-line driver circuit 108 through a connector such as a flexible printed circuit (FPC) connected to terminals 114 disposed over the substrate. Each pixel 102 is controlled on the basis of these signals so that an image is reproduced on the display region 104.

One or both of the scanning-line driver circuits 106 and the data-line driver circuit 108 may not be necessarily formed over the substrate 110 directly, and driver circuits formed over a substrate (e.g., semiconductor substrate) different from the substrate 110 may be arranged over the substrate 110 or the connector and each pixel 102 may be controlled by these driver circuits. In FIG. 1, an example is illustrated where the display region 104 and the scanning-line driver circuits 106 formed over the substrate 110 are covered by an opposing substrate 112, while the data-line driver circuit 108 prepared over another substrate is mounted over the substrate 110.

#### 2. Light-Emitting Element

A schematic cross-sectional view of the display device 100 is shown in FIG. 2. In this cross-sectional view, three pixels 102a, 102b, and 102c of the plurality of pixels 102 of the display device 100 are illustrated. The pixel 102b is adjacent to and sandwiched by the pixel 102a and the pixel 102c. The substrate 110 for supporting the pixels 102 and a variety of circuits for driving the pixels 102 are omitted in FIG. 2.

A light-emitting element 120 is provided to each pixel 102. Each light-emitting element 120 possesses a first electrode (hereinafter, referred to as a pixel electrode) 122, a second electrode (also called a common electrode) 124, and an EL layer 130 sandwiched therebetween. Here, the pixels 102a, 102b, and 102c have pixel electrodes 122a, 122b, and 122c, respectively. The pixel electrodes 122a, 122b, and

122c are electrically separated from one another and independently applied with a potential on the basis of the signals from the data-line driver circuit 108.

Edge portions of the pixel electrodes 122a, 122b, and 122c are covered by a partition wall 116, and depressions and projections caused by a thickness of the pixel electrodes 122 are relieved by the partition wall 116. The partition wall 116 is an insulating film formed over the display region 104 so as to expose the pixel electrodes 122. Therefore, the partition wall 116 can be regarded as one insulating film having a plurality of opening portions, and each opening portion overlaps with the respective pixel electrode 122.

The second electrode 124 is disposed over the plurality of pixels 102a, 102b, and 102c. Therefore, the second electrode 124 is shared by the plurality of pixels 102a, 102b, and 102c and supplies a common potential to the plurality of light-emitting elements 120.

The pixel electrode 120 and the second electrode 124 are configured so that one of them transmits visible light and the other reflects visible light. One of the pixel electrode 120 and the second electrode 124 functions as an anode, and the other serves as a cathode. In the present embodiment, an example is explained in which the pixel electrode 122 serves as an anode reflecting visible light and the second electrode 124 functions as a semi-transparent and semi-reflective cathode partly transmitting and partly reflecting visible light. In this case, the pixel electrode 122 can be formed by using a metal having a high reflectance, such as silver and aluminum, or an alloy thereof. Alternatively, a film of a conductive oxide with a light-transmitting property may be formed over a film including the metal or the alloy. Indium-tin oxide (ITO), indium-zinc oxide (IZO), and the like are exemplified as a conductive oxide. As the second electrode 124, it is possible to use a metal thin film including a metal such as aluminum, magnesium, and silver or an alloy thereof and having a thickness which allows visible light to transmit therethrough. Alternatively, a conductive oxide with a light-transmitting property, such as ITO and IZO, may be used. When the metal thin film is employed as the second electrode 124, a conductive oxide with a light-transmitting property may be stacked over the metal thin film.

A structure of the EL layer 130 may be arbitrarily determined, and the EL layer 130 may be structured with a plurality of layers having different functions. The EL layer 130 of the light-emitting element 120 shown in FIG. 2 has a hole-injection layer 132, a hole-transporting layer 134, an emission layer 136, an electron-transporting layer 138, and an electron-injection layer 140. Each layer may have a single-layer structure or may be formed with stacked layers of different materials. Alternatively, the EL layer 130 may not include all of these layers and may further contain a layer with another function. For example, the EL layer 130 may include a hole-blocking layer, an electron-blocking layer, an exciton-blocking layer, and the like. Alternatively, one layer may have functions of two layers.

A potential difference is provided between the pixel electrode 122 and the second electrode 124, by which holes and electrons are injected to the EL layer 130 from the former and latter, respectively. Holes are transported to the emission layer 136 through the hole-injection layer 132 and the hole-transporting layer 134. Electrons are transported to the emission layer 136 through the electron-injection layer 140 and the electron-transporting layer 138. Holes and electrons are recombined in the emission layer 136, giving an excited state of a light-emitting material included in the emission layer 136. When the excited state is relaxed to a ground state, light with a wavelength corresponding to an

energy difference between the excited state and the ground state is released and observed as the light emission from the light-emitting element **120**.

Hence, a region of the pixel electrode **122** exposed from the opening portion of the partition wall **116** contributes to the injection of holes and is an emission region of each light-emitting element **120**. In other words, the emission region of each light-emitting element **120** matches the opening portion of the partition wall **116**.

For the hole-injection layer **132**, a compound to which holes are readily injected, that is, a compound readily oxidized (i.e., electron-donating compound) can be used. In other words, a compound whose level of the highest occupied molecular orbital (HOMO) is shallow can be used. For example, an aromatic amine such as a benzidine derivative and a triarylamine, a carbazole derivative, a thiophene derivative, a phthalocyanine derivative such as copper phthalocyanine, and the like can be used. Alternatively, a polymer material such as a polythiophene derivative or a polyaniline derivative may be used.

Poly(3,4-ethylenedioxydithiophene)/poly(styrenesulfonic acid) is represented as an example. Alternatively, a mixture of an electron-donating compound such as the aforementioned aromatic amine, carbazole derivative, or aromatic hydrocarbon with an electron acceptor may be used. As an electron acceptor, a transition-metal oxide such as vanadium oxide and molybdenum oxide, a nitrogen-containing heteroaromatic compound, an aromatic compound having a strong electron-withdrawing group such as a cyano group, and the like are represented.

The hole-transporting layer **134** has a function to transport holes injected to the hole-injection layer **132** to the emission layer **136**, and a material the same as or similar to the material usable in the hole-injection layer **132** can be used. For example, it is possible to use a material having a deeper HOMO level than that of the hole-injection layer **132** and having a difference in HOMO level from the hole-injection layer **132** by approximately 0.5 eV or less.

The emission layer **136** may be formed with a single compound or have the so-called host-guest type structure. In the case of the host-guest type structure, a stillbene derivative, a condensed aromatic compound such as an anthracene derivative, a carbazole derivative, a metal complex including a ligand having a benzoquinolinol as a basic skeleton, an aromatic amine, a nitrogen-containing heteroaromatic compound such as a phenanthroline derivative, and the like can be used as a host material, for example. A fluorescent material such as a coumarin derivative, a pyran derivative, a quinacridone derivative, a tetracene derivative, a pyrene derivative, and an anthracene derivative, or a phosphorescent material such as an iridium-based orthometal complex can be used as a guest. When the emission layer **136** is configured with a single compound, the aforementioned host material can be used.

The electron-transporting layer **138** has a function to transport electrons injected from the second electrode **124** through the electron-injection layer **140** to the emission layer **136**. For the electron-transporting layer **138**, a compound readily reduced (i.e., electron-accepting compound) can be used. In other words, a compound whose level of the lowest unoccupied molecular orbital (LUMO) is deep can be used. For example, a metal complex including a ligand having a benzoquinolinol as a basic skeleton, such as tris(8-quinolinolato)aluminum and tris(4-methyl-8-quinolinolato)aluminum, a metal complex including a ligand having an oxathiazole or thiazole as a basic skeleton, and the like are represented. In addition to these metal complexes, a

compound with an electron-deficient heteroaromatic ring, such as an oxadiazole derivative, a thiazole derivative, a triazole derivative, and a phenanthroline derivative, can be used.

For the electron-injection layer **140**, a compound which promotes electron injection to the electron-transporting layer **138** from the second electrode **124** can be used. For example, a mixture of a compound usable in the electron-transporting layer **138** with an electron-donating material such as lithium or magnesium can be used. Alternatively, an inorganic compound such as lithium fluoride and calcium fluoride may be used.

Each layer included in the EL layer **130** may be formed by applying a wet-type film-forming method such as an ink-jet method, a spin-coating method, and a printing method or a dry-type film-forming method such as an evaporation method.

In FIG. 2, the layers other than the emission layer **136** of the EL layer **130**, that is, the hole-injection layer **132**, the hole-transporting layer **134**, the electron-transporting layer **138**, and the electron-injection layer **140** are continuously formed through the pixels **102a**, **102b**, and **102c** and shared by the pixels **102a**, **102b**, and **102c**. On the other hand, the emission layer **136** is formed pixel-by-pixel in the pixels **102a**, **102b**, and **102c**. The use of such a structure allows the pixels **102a**, **102b**, and **102c** to have the emission layers (**136a**, **136b**, and **136c**) having light-emitting materials different from one another, by which emission colors different from one another can be produced. For example, when the emission layers **136a**, **136b**, and **136c** include light-emitting materials respectively giving blue, green, and red emissions, full-color display can be achieved by extracting three primary colors from the pixels **102a**, **102b**, and **102c**. In the example shown in FIG. 2, the emission layers **136a**, **136b**, and **136c** are not in contact with one another, and the hole-transporting layer **134** and the electron-transporting layer **138** are in contact with each other over the partition wall **116**. However, the emission layers **136a**, **136b**, and **136c** may be formed so as to overlap with one another over the partition wall **116**.

The layers other than the emission layer **136** may have different structures or the same structure between the pixels **102a**, **102b**, and **102c**. For example, as shown in FIG. 2, the display device **100** may be configured so that a thickness of the hole-transporting layer **134** is different between the pixels **102a**, **102b**, and **102c**. Alternatively, although not shown, a thickness or a stacking structure of the hole-injection layer **132** and the electron-transporting layer **138** may be different between the pixels.

### 3. Resonance in Light-Emitting Element

As described above, the EL layers **130** may have different structures between the pixels **102a**, **102b**, and **102c**. Thus, an appropriate resonance structure can be provided to each light-emitting element **120** by controlling a thickness of the EL layer **130**. This resonance structure is also called a microcavity. The light-emission from the EL layer **130** is reflected by the pixel electrode **122**, and simultaneously partly passes through and is partly reflected by the second electrode **124**. The light reflected by the second electrode **124** is reflected again by the pixel electrode **122**. The reflected light interferes with each other between the pixel electrode **122** and the second electrode **124**, and is then extracted through the second electrode **124**.

In this case, light with a wavelength consistent with an optical distance of the light-emitting element **120** is amplified while repeating the reflection, whereas light with a wavelength inconsistent with the optical distance is attenu-

ated. For example, in the case of the light directed perpendicularly to the pixel electrode **122**, the optical distance depends on a distance between a reflection surface of the pixel electrode **122** and a reflection surface of the second electrode **124**. When the former is a top surface of the pixel electrode **122** and the latter is a bottom surface of the second electrode **124**, the optical distance corresponds to  $L$  shown in FIG. 2, and  $L$  is a summation of a product of a refractive index by a thickness of each layer of the EL layer **130** because the interference takes place in the EL layer **130**. When an odd multiple of one fourth of  $\lambda$  ( $\lambda/4$ ) is the same as or close to the optical distance  $L$  where  $\lambda$  is a wavelength of the light, the light having this wavelength  $\lambda$  is consistent with the optical distance  $L$  and amplified. On the other hand, when an integral multiple of one second of  $\lambda$  ( $\lambda/2$ ), that is, an integral multiple of a half wavelength is the same as or close to the optical distance  $L$ , the light having this wavelength  $\lambda$  is inconsistent with the optical distance  $L$  and attenuated. Accordingly, when the light emitted from the emission layer **136** is centered at a wavelength  $\lambda$  (e.g., in the case where an emission peak wavelength is  $\lambda$ ), the thickness of the EL layer **130** is controlled so that the optical distance  $L$  is an odd multiple of  $\lambda/4$ , by which a full-width half-maximum of the emitted light is decreased, color purity is improved, and luminance in a front direction of the light-emitting element **120** is increased.

Hence, the structure of each of the EL layers **130** is adjusted in each of the pixels **102a**, **102b**, and **102c** so as to be consistent with the emission wavelengths of the emission layers **136a**, **136b**, and **136c**, which enables an improvement of color purity of the emitted light and an increase of luminance. For example, as shown in FIG. 2, the optical distance can be adjusted by varying the thickness of the hole-transporting layer **134** between the pixels **102**. The display device **100** having the light-emitting element **120** with high color purity of emitted light and increased intensity of front luminance can be obtained by this method.

#### 4. Optical Adjustment Layer

The display device **100** may further possess an optical adjustment layer **150** over the second electrode **124**. The optical adjustment layer **150** has a first cap layer **152**, a second cap layer **154** over the first cap layer **152**, and a third cap layer **156** over the second cap layer **154**. The first cap layer **152** may be formed so as to be in contact with the second electrode **124**. The third cap layer **156** covers the first cap layer **152** and the second cap layer **154**.

Here, the second cap layer **154** is provided so as to overlap with a part of the plurality of pixels **102**. In other words, a part of the pixels **102** does not overlap with the second cap layer **154**. For example, as shown in FIG. 2, the second cap layer **154** overlaps with the EL layer **130** of the pixel **102a** or the emission region thereof, but does not overlap with the EL layers **130** of the pixels **102b** and **102c** nor the emission regions thereof. Therefore, the first cap layer **152** is spaced from the third cap layer **156** with the second cap layer **154** sandwiched therebetween over the emission region in the pixel **102a**. On the other hand, the first cap layer **152** and the third cap layer **156** may be in contact with each other in the emission regions of the pixels **102b** and **102c**.

The color provided by the pixel **102** (exemplified by the pixel **102a** in the present embodiment) whose emission region is covered by the second cap layer **154** may be different from the colors provided by the pixels **102** (exemplified by the pixels **102b** and **102c** in the present embodiment) whose emission regions are not covered by the second cap layer **154**. For example, the emission color of the emission layer **136a** of the pixel **102a** may be different from

those of the emission layers **136b** and **136c** of the pixels **102b** and **102c**. The emission wavelength of the emission layer **136a** may be longer than those of the emission layers **136b** and **136c**. In other words, an emission peak wavelength of the emission layer **136a** may be longer than those of the emission layers **136b** and **136c**. For example, the display device **100** may be configured so that the emission layer **136a** provides red emission while the emission layers **136b** and **136c** provide green and blue emissions.

A refractive index and a thickness of the first cap layer **152** can be selected so that both or one of the light emissions of the light-emitting elements **120** of the pixels **102b** and **102c** is amplified between a top surface and a bottom surface of the first cap layer **152**. That is, the refractive index and the thickness of the first cap layer **152** can be selected so that a product (hereinafter, referred to as an optical film thickness) of the refractive index by the thickness is an odd multiple of one fourth of both or one of the emission wavelengths (e.g., emission peak wavelengths) of the light-emitting elements **120** of the pixels **102b** and **102c**.

For example, the film thickness of the first cap layer **152** is equal to or more than 10 nm and equal to or less than 200 nm. It is preferred that the film thickness of the first cap layer **152** be selected according to individual cases because the optimal value thereof depends on a material of the first cap layer **152**, a material and a film thickness of the third cap layer **156**, an optical film thickness of the EL layer **130**, an emission wavelength of a light-emitting material, and objective color purity of the emission.

The first cap layer **152** may have a high transmissivity and a high refractive index in a visual region. For example, the first cap layer **152** may have a refractive index of 1.7 or 2 or more.

On the other hand, the third cap layer **156** may include a material with a refractive index smaller than that of the first cap layer **152**. With this structure, it is possible to increase reflectance at an interface between the first cap layer **152** and the third cap layer **156** for the light directed from the first cap layer **152** to the third cap layer **156**. As a result, a micro-cavity can be formed between the top surface and the bottom surface of the first cap layer **152** to amplify the light in the pixels **102b** and **102c**.

For example, the film thickness of the third cap layer **156** is equal to or more than 10 nm and equal to or less than 200 nm. It is preferred that the film thickness of the third cap layer **156** be selected according to individual cases because the optimal value thereof depends on a material and a film thickness of the first cap layer **152**, a material of the third cap layer **156**, an optical film thickness of the EL layer **130**, an emission wavelength of a light-emitting material, and objective color purity of the emission.

As a material with a high refractive index, a polymer material with a high refractive index is represented. As a polymer material with a high refractive index, a polymer material including sulfur, halogen, or phosphorus is given, for example. As a polymer including sulfur, a polymer having a substituent such as a thioether, a sulfone, and a thiophene in a main chain or side chain is represented. As a polymer material including phosphorus, a polymer including a phosphorous acid group or a phosphoric acid group in a side chain, a polyphosphazene, and the like are represented. As a polymer material including halogen, a polymer material having bromine or iodine as a substituent. The aforementioned polymer material may be intermolecularly or intramolecularly cross-linked.

An inorganic material may be also used as a material having a high refractive index, and titanium oxide, zirco-

niun oxide, chromium oxide, aluminum oxide, indium oxide, ITO, IZO, lead sulfide, zinc sulfide, silicon nitride, and the like are exemplified. Alternatively, a simple substrate of a Group 14 element such as amorphous silicon may be used.

A mixture of the inorganic material and a polymer material may be used. In this case, the aforementioned polymer may be utilized.

As a material with a low refractive index, a polymer material including fluorine is exemplified. As a polymer material including fluorine, polytetrafluoroethylene, poly(vinylidene fluoride), a polymer having these structures as a basic skeleton, a poly(vinyl ether), a polyimide, a poly(methacrylic ester), a poly(acrylic ester), a polysiloxane having fluorine in a side chain, and the like are given. These polymers may be intermolecularly or intramolecularly cross-linked.

As an inorganic compound with a low refractive index, a metal fluoride such as lithium fluoride, magnesium fluoride, and calcium fluoride, silicon oxide including boron oxide or phosphorus oxide, and the like are represented.

The second cap layer **154** is arranged between the first cap layer **152** and the third cap layer **156** and is preferred to have a film thickness of 2  $\mu\text{m}$  or more which is a sufficient film thickness to inhibit the light-interference effect. As demonstrated by the calculation result of FIG. 3, it has been known that the light intensity after the interference depends on a gap (optical film thickness) of the microcavity, and the interference effect decreases as the gap becomes larger to eventually inhibit observation of the interference effect. Furthermore, since a film located over the second cap layer **154**, e.g., the third cap layer **156**, is arranged to extend over the second cap layer **154**, there is a possibility that the third cap layer **156** or a film located over the third cap layer **156** is disconnected due to a step caused by the films located thereunder. Thus, it is preferred that the second cap layer **154** does not have an unnecessarily large film thickness. For example, the film thickness of the second cap layer **154** is preferred to be equal to or less than 10  $\mu\text{m}$ .

A refractive index of the second cap layer **154** may be the same as or less than that of the first cap layer **152**. This configuration reduces reflectance at an interface between the first cap layer **152** and the second cap layer **154** for the light directed from the first cap layer **152** to the second cap layer **154** and prevents the resonance in the first cap layer **152**. In other words, the light directed from the first cap layer **152** to the second cap layer **154** can be effectively introduced into the second cap layer **154**.

More specifically, the second cap layer **154** may contain the material usable in the first cap layer **152**. Alternatively, the second cap layer **154** may include a polymer material or an inorganic material having the same or substantially the same refraction index as the first cap layer **152**. The polymer material may be a thermoplastic resin or a resin which is crosslinked and cured by heating or light irradiation. As a resin, an acrylic resin, an epoxy resin, a resin having a polyimide, a polyamide, a polyester, a polycarbonate, or a polysiloxane as a basic skeleton, and the like are represented. The use of the aforementioned materials and the selection of the film thickness of the second cap layer **154** from the aforementioned range prevents the resonance in the first cap layer **152** and the second cap layer **154**, by which the light radiated from the light-emitting element **120** can be supplied outside while maintaining the spectrum shape and the intensity thereof.

## 5. Control of Emission by Optical Adjustment Layer

The use of the optical adjustment layer **150** with the aforementioned structure allows production of the display device **100** with excellent color purity and high efficiency. For example, when the pixels **102a**, **102b**, and **102c** have the red-, green-, and blue-emissive emission layers **136a**, **136b**, and **136c**, respectively, the emission layers **136a**, **136b**, and **136c** give emission spectra (**142a**, **142b**, and **142c**) in a red region (e.g., 610 nm to 750 nm), a green region (e.g., 500 nm to 600 nm), and a blue region (e.g., 400 nm to 480 nm), respectively, as shown in FIG. 4A. The emission peak wavelengths are also located in the aforementioned regions, respectively.

As described above, the optical adjustment in each light-emitting element **120** allows each spectrum to be narrowed and emission luminance in the front direction of the display device **100** to be increased. For example, as shown in FIG. 4B, the full-width half-maximum and intensity of the spectra **142a**, **142b**, and **142c** are decreased and the intensity thereof is increased. As a result, the light-emitting elements **120a**, **120b**, and **120c** provide the light emission with the spectra **144a**, **144b**, and **144c**, respectively. Note that the optical adjustment in each light-emitting element **120** is arbitrarily conducted.

Here, as shown in FIG. 2, when the emission regions of the pixels **102b** and **102c** are not covered by the second cap layer **154**, the light emission of the light-emitting elements **120** in the pixels **102b** and **102c** can be further optically adjusted with the first cap layer **152**. Accordingly, as demonstrated by the middle and right diagrams of FIG. 4C, the emission spectra of the light-emitting elements **120b** and **120c** are further narrowed, and the intensity thereof is increased (spectra **146b** and **146c**).

Current efficiency is generally the lowest in a light-emitting element giving blue color. Additionally, since a phosphorescent material giving blue emission with high color purity is extremely limited, a light-emitting element giving blue color exhibits the lowest quantum efficiency. Therefore, an optical adjustment layer arranged outside a light-emitting element is usually designed so that blue light is amplified in order to reinforce the low efficiency. In this case, an optical film thickness of the optical adjustment layer will be 120 nm, 360 nm, 600 nm, or the like if a wavelength of light to be amplified is 480 nm. However, red light (e.g., 720 nm) is attenuated when the optical film thickness of the optical adjustment layer is 360 nm, and intensity thereof is significantly decreased. Thus, when the optical adjustment layer is designed so that light emission with a short wavelength is amplified, light emission with a long wavelength may be significantly reduced. Therefore, the first cap layer **152** is not always capable of amplifying the light emission from the light-emitting element **120** in the pixel **120a** covered by the second cap layer **154**. Additionally, when the second cap layer **154** is not provided in the pixel **102a**, the light emission is attenuated, and the spectrum thereof becomes broad, resulting in a tendency to decrease the intensity (spectrum **145a**).

However, in the display device **100**, the second cap layer **154** is disposed over the light-emitting element **120a** giving the light emission with a long wavelength so that the resonance is inhibited in the first cap layer **152** and the second cap layer **154**. Hence, it is possible to extract the light emission from the light-emitting element **120a** while maintaining the spectrum shape and the intensity thereof (spectrum **146a**). Accordingly, the color purity of the light radiated by the light-emitting element **120a** is maintained, and the efficiency does not decrease.

## 11

Therefore, application of the present embodiment allows each pixel **102** to provide light emission with excellent color purity and high efficiency. As a result, a display device capable of displaying an image with high display quality can be provided.

## 6. Other Structures

As shown in FIG. 2, the display device **100** may further have a sealing film (hereinafter, referred to as a passivation film) **160** over the optical adjustment layer **150**. The passivation film **160** has a function to prevent impurities such as water and oxygen from entering the light-emitting element **120** from outside, thereby improving reliability of the light-emitting element **120**. The structure of the passivation film **160** can be arbitrarily determined, and the passivation film **160** may have a three-layer structure as shown in FIG. 2, for example. In this case, the passivation film **160** may have a first layer **162**, a second layer **164**, and a third layer **166**. The first layer **162** and the third layer **166** may include an inorganic compound, and the second layer **164** may contain an organic compound, for example. Silicon nitride and silicon oxide can be used for the first layer **162** and the third layer **166**, for example. The second layer **164** can be formed at a thickness so that depressions and projections caused by the partition wall **116** and the like are absorbed and a flat surface is provided.

The opposing substrate **112** may be provided over the passivation film **160** via a filler **170**. Thus, the filler **170** also functions as an adhesive. The display device **100** including the light-emitting element **120** is physically protected by the opposing substrate **112**. Although not illustrated, the opposing substrate **112** may be provided with a color filter, a light-shielding film, an overcoat protecting the color filter and the light-shielding film, and the like. The opposing substrate **112** may be a flexible resin film or a circularly polarizing plate.

## Second Embodiment

In the present embodiment, a display device **200** having a structure different from that of the display device **100** is explained. Explanation of the structures the same as those of the First Embodiment may be omitted.

A schematic cross-sectional view of the display device **200** is shown in FIG. 5. Three pixels **102a**, **102b**, and **102c** are illustrated in FIG. 5. The pixel **102b** is adjacent to the pixels **102a** and **102c** and sandwiched therebetween. The pixels **102a**, **102b**, and **102c** may have the emission layers **136a**, **136b**, and **136c** giving emission colors different from one another. As shown in FIG. 5, the display device **200** is different from the display device **100** in that the EL layers **130** or their emission regions of two pixels with different emission colors (pixels **102a** and **102b** in FIG. 5) are covered by the first cap layer **152**, the second cap layer **154**, and the third cap layer **156** and that the first cap layer **152** and the third cap layer **156** are in contact with each other over the EL layer **130** or its emission region of the pixel (pixel **102c** in FIG. 5) giving an emission color different from those of the pixels **102a** and **102b**. In this case, the pixels **102a** and **102b** whose emission regions are covered by the first cap layer **152**, the second cap layer **154**, and the third cap layer **156** may be adjacent to each other as shown in FIG. 5.

For example, when the first cap layer **152** is able to amplify the light emission from the light-emitting element **120** of one pixel **102c** but unable to amplify the light emission from the light-emitting elements **120** of the other two pixels **102a** and **102b**, the use of the structure of the

## 12

display device **200** makes it possible to prevent a decrease in color purity and intensity of the light emission from the pixels **102a** and **102b**. As a result, the light emission with excellent color purity is efficiently attained from each pixel **102**, and a display device capable of displaying an image with high display quality can be provided.

## Third Embodiment

In the present embodiment, a display device **300** having a structure different from those of the display devices **100** and **200** is explained. Explanation of the structures the same as those of the First and Second Embodiments may be omitted.

A schematic cross-sectional view of the display device **300** is shown in FIG. 6. The display device **300** is different from the display devices **100** and **200** in the vertical relationship between the first cap layer **152** and the second cap layer **154**. Specifically, the optical adjustment layer **150** of the display device **300** possesses the second cap layer **154** over the second electrode **124**, the first cap layer **152** over the second cap layer **154**, and the third cap layer **156** over the first cap layer **152**. Similar to the display device **100**, the second cap layer **154** overlaps with the EL layers **130** or their emission regions of a part of the pixels **102** (pixel **102a** in FIG. 6) but does not overlap with the EL layers **130** or their emission regions of another part of the pixels **102** (pixels **102b** and **102c** in FIG. 6). Therefore, the first cap layer **152** and the second electrode **124** are not in contact with each other over the emission region in the pixel in which the EL layer **130** or its emission region overlaps with the second cap layer **154**. Moreover, the first cap layer **152** is spaced from the third cap layer **156** with the second cap layer **154** therebetween. On the other hand, the first cap layer **152** and the third cap layer **156** are in contact with each other over the emission regions of all of the pixels **102**.

As described above, the second cap layer **154** may contain a material whose refractive index is the same as or close to that of the first cap layer **152**. Therefore, the reflection at the interface between the second cap layer **154** and the first cap layer **152** is suppressed. As a result, the light interference is inhibited in the first cap layer **152** over the pixel **102a** in which the emission region overlaps with the second cap layer **154**, and the spectrum shape and intensity of the light emission from the light-emitting element **120** are substantially maintained. On the other hand, in the pixels **102b** and **102c** in which the emission regions do not overlap with the second cap layer **154**, the light emission is amplified in the first cap layer **152**, leading to an improvement of the color purity and intensity. Hence, the light emission with excellent color purity is efficiently attained from each pixel **102**, and a display device capable of displaying an image with high display quality can be provided.

## Fourth Embodiment

In the present embodiment, a manufacturing method of the display device **100** according to the present invention is explained. Explanation of the structures the same as those of the First to Third Embodiments may be omitted.

FIG. 7 shows a schematic cross-sectional view of the display device **100** including three continuously arranged pixels **102a**, **102b**, and **102c**. Here, an example is demonstrated where the emission region of the pixel **102b** overlaps with the second cap layer **154**, and the first cap layer **152** and the third cap layer **156** are in contact with each other over the emission regions of the pixels **102a** and **102c**.

The pixels **102** including the plurality of pixels **102a**, **102b**, and **102c** each possess, over the substrate **110**, elements such as a transistor **224**, the light-emitting element **120** electrically connected to the transistor **224**, and a supplementary capacitor **248** through a base film **210**. FIG. 7 shows an example in which one transistor **224** and one supplementary capacitor **248** are disposed in each pixel **102**. However, each pixel **102** may have a plurality of transistors and a plurality of capacitor elements. The structure of the light-emitting element **120** is the same as that described in the First Embodiment. Hereinafter, a manufacturing method of the display device **100** is explained with reference to the schematic cross-sectional views thereof.

#### 1. Transistor

First, as shown in FIG. 8A, the base film **210** is formed over the substrate **110**. The substrate **110** has a function to support semiconductor elements included in the display region **104**, such as the transistor **224**, the light-emitting element **120**, and the like. Therefore, a material having heat resistance to a process temperature of a variety of elements formed thereover and chemical stability to chemicals used in the process may be used for the substrate **110**. Specifically, the substrate **110** may include glass, quartz, plastics, a metal, ceramics, and the like.

When flexibility is provided to the display device **100**, a base material is formed over the substrate **110**. In this case, the substrate **110** may be called a supporting substrate. The base material is an insulating film with flexibility and may include a material selected from a polymer material exemplified by a polyimide, a polyamide, a polyester, and a polycarbonate. The base material can be formed by applying a wet-type film-forming method such as a printing method, an ink-jet method, a spin-coating method, and a dip-coating method or a lamination method.

The base film **210** is a film having a function to prevent impurities such as an alkaline metal from diffusing to the transistor **224** and the like from the substrate **110** (and the base material) and may include an inorganic insulator such as silicon nitride, silicon oxide, silicon nitride oxide, and silicon oxynitride. The base film **210** can be formed to have a single-layer or stacked-layer structure by applying a chemical vapor deposition method (CVD method), a sputtering method, or the like. When an impurity concentration in the substrate **110** is low, the base film **210** may not be provided or may be formed to cover a part of the substrate **110**.

Next, a semiconductor film **212** is formed (FIG. 8A). The semiconductor film **212** may contain Group 14 elements such as silicon. Alternatively, the semiconductor film **212** may include an oxide semiconductor. As an oxide semiconductor, Group 13 elements such as indium and gallium are represented. For example, a mixed oxide of indium and gallium (IGO) may be used. When an oxide semiconductor is used, the semiconductor film **212** may further contain a Group 12 element, and a mixed oxide of indium, gallium, and zinc (IGZO) is exemplified. Crystallinity of the semiconductor film **212** is not limited, and the semiconductor film **212** may include a crystal state of a single crystalline, polycrystalline, microcrystalline, or amorphous state.

When the semiconductor film **212** includes silicon, the semiconductor film **212** may be prepared with a CVD method by using silane gas and the like as a raw material. A heat treatment or application of light such as a laser may be performed on amorphous silicon obtained to conduct crystallization. When the semiconductor film **212** includes an oxide semiconductor, the semiconductor film **212** can be formed by utilizing a sputtering method or the like.

Next, a gate insulating film **214** is prepared so as to cover the semiconductor film **212** (FIG. 8A). The gate insulating film **214** can also be prepared with an inorganic compound containing silicon, such as silicon oxide and silicon nitride, by using the same method as the base film **210**. The gate insulating film **214** may have a single-layer structure or a stacked-layer structure.

Next, a gate electrode **216** is formed over the gate insulating film **214** with a sputtering method or a CVD method (FIG. 8B). The gate electrode **216** may be formed with a metal such as titanium, aluminum, copper, molybdenum, tungsten, tantalum or an alloy thereof so as to have a single-layer or stacked-layer structure. For example, a structure in which a highly conductive metal such as aluminum and copper is sandwiched by a metal with a relatively high melting point, such as titanium, tungsten, and molybdenum, can be employed.

Next, an interlayer film **218** is formed over the gate electrode **216** (FIG. 8B). The interlayer film **218** may have a single-layer or stacked layer structure, may include an inorganic insulator such as silicon nitride, silicon oxide, silicon nitride oxide, and silicon oxynitride, and may be prepared with the same method as that of the base film **210**. When the interlayer film **218** has a stacked structure, a layer including an inorganic compound may be stacked after forming a layer including an organic compound, for example. After that, doping may be conducted on the semiconductor film **212** to form source/drain regions.

Next, etching is performed on the interlayer film **218** and the gate insulating film **214** to form openings **220** reaching the semiconductor film **212** (FIG. 8C). The openings **220** can be prepared, for example, by conducting plasma etching in a gas including a fluorine-containing hydrocarbon.

Next, a metal film is formed to cover the openings **220** and processed with etching to form source/drain electrodes **222** (FIG. 9A). Similar to the gate electrode **216**, the metal film may include a metal such as titanium, aluminum, copper, molybdenum, and tantalum or an alloy thereof and may have a single-layer or stacked layer structure. The metal film can be formed with a method similar to that of the gate electrode **216**. Through the aforementioned processes, the transistor **224** is fabricated. In the present embodiment, the transistor **224** is illustrated as a top-gate type transistor. However, there is no limitation to the structure of the transistor **224**, and the transistor **224** may be a bottom-gate type transistor, a multi-gate type transistor having a plurality of gate electrodes **216**, or a dual-gate type transistor having a structure in which the semiconductor film **212** is sandwiched by two gate electrodes **216**. Moreover, there is no limitation to a vertical relationship between the source/drain electrodes **222** and the semiconductor film **212**.

#### 2. Supplementary Capacitor and Light-Emitting Element

Next, a leveling film **230** is formed so as to cover the transistor **224** (FIG. 9A). The leveling film **230** has a function to absorb depressions, projections, and inclinations caused by the transistor **224** and the like and provide a flat surface. The leveling film **230** can be prepared with an organic insulator. As an organic insulator, a polymer material such as an epoxy resin, an acrylic resin, a polyimide, a polyamide, a polyester, a polycarbonate, and a polysiloxane is represented. The leveling film **230** can be formed with the aforementioned wet-type film-forming method and the like.

After that, etching is performed on the leveling film **230** to form an opening **232** exposing one of the source/drain electrodes **222** (FIG. 9B). After that, a connection electrode **234** is prepared so as to cover this opening **232** and be in contact with one of the source/drain electrodes **222** of the

transistor **224** (FIG. 9C). The connection electrode **234** may be formed by using a conductive oxide transmitting visible light, such as indium-tin oxide (ITO) and indium-zinc oxide (IZO), with a sputtering method or the like. Note that formation of the connection electrode **234** is optional. Deterioration of a surface of the source/drain electrode **222** can be avoided in the following processes by forming the connection electrode **234**, by which generation of contact resistance between the source/drain electrode **222** and the pixel electrode **122** can be suppressed.

Next, a metal film is formed over the leveling film **230** and processed with etching to form one of electrodes **240** of the supplementary capacitor **248** (FIG. 10A). Similar to the conductive film used for the formation of the source/drain electrodes **222**, the metal film used here may have a single layer structure or a stacked layer structure, and a three-layer structure of molybdenum/aluminum/molybdenum may be employed, for example.

Next, an insulating film **242** is formed over the leveling film **230** and the electrode **240** (FIG. 10A). The insulating film **242** not only functions as a protection film for the transistor **224** but also serves as a dielectric in the supplementary capacitor **248**. Therefore, it is preferred to use a material with relatively high permittivity. For example, the insulating film **242** can be formed with silicon nitride, silicon nitride oxide, silicon oxynitride, or the like by applying a CVD method or a sputtering method. Openings **244** and **246** are provided in the insulating film **242** (FIG. 10A). The former is provided for electrical connection between the pixel electrode **122** formed later and the connection electrode **234**. The latter is an opening to abstract, through the partition wall **116**, water and gas eliminated from the leveling film **230** in a heating process and the like performed after the formation of the partition wall **116**.

Next, as shown in FIG. 10B, the pixel electrode **122** is prepared so as to cover the opening **244**. The supplementary capacitor **248** is formed by the pixel electrode **122**, the insulating film **242**, and the electrode **240**. A potential of the gate electrode **216** of the transistor **224** can be maintained for a longer time by forming the supplementary capacitor **248**.

The structure of the pixel electrode **122** is the same as that described in the First Embodiment, and the pixel electrode **122** can be formed by using a sputtering method, a CVD method, or the like.

Next, the partition wall **116** is formed so as to cover the edge portion of the pixel electrode **122** (FIG. 10B). The formation of the partition wall **116** allows steps caused by the pixel electrode **122** and the like to be absorbed and the pixel electrodes **122** of the adjacent pixels **102** to be electrically insulated from each other. The partition wall **116** may be prepared with a wet-type film-forming method by using an epoxy resin, an acrylic resin, or the like.

Next, the EL layer **130** and the second electrode **124** of the light-emitting element **120** are formed so as to cover the pixel electrode **122** and the partition wall **116**. The structures of these elements are the same as those described in the First Embodiment. Specifically, the hole-injection layer **132** is first formed to cover the pixel electrode **122** and the partition wall **116**, and then the hole-transporting layer **134** is prepared over the hole-injection layer **132** (FIG. 11A). As described above, the hole-injection layer **132** and the hole-transporting layer **134** each may have a single-layer structure or a stacked-layer structure. For example, when the thickness of the hole-transporting layer **134** is changed in every pixel **102** as shown in FIG. 2, the hole-transporting layer **134** in which a plurality of compounds is stacked may

be provided in the pixel **102a** having the hole-transporting layer **134** with a large thickness, while the hole-transporting layer **134** may have a single-layer structure in the pixel **102b** or **102c** having the hole-transporting layer **134** with a small thickness.

Next, the emission layer **136** is formed over the hole-transporting layer **134** (FIG. 11B). In the present embodiment, the emission layers **136a**, **136b**, and **136c** which are different in structure or include different materials between the continuously arranged pixels **102a**, **102b**, and **102c** are fabricated. In this case, materials to be included in the respective emission layers **136a**, **136b**, and **136c** are respectively deposited in the pixels **102a**, **102b**, and **102c** by using metal masks. Alternatively, the emission layers **136a**, **136b**, and **136c** may be formed with an ink-jet method.

The electron-transporting layer **138** and the electron-injection layer **140** are successively formed over the emission layer **136**, and the second electrode **124** is formed over the electron-injection layer **140** (FIG. 12A). Each layer structuring the EL layer **130** may be formed by applying a wet-type film-forming method or a dry-type film-forming method such as an evaporation method. The second electrode **124** is also prepared by using a sputtering method or an evaporation method. Through these processes, the supplementary capacitor **248** and the light-emitting element **120** are fabricated.

### 3. Optical Adjustment Layer

Next, the optical adjustment layer **150** is formed over the second electrode **124**. Specifically, the first cap layer **152**, the second cap layer **154**, and the third cap layer **156** are successively formed (FIG. 12B, FIG. 13, and FIG. 14). These layers may be formed with a wet-type film-forming method or a dry-type film-forming method. Alternatively, an epitaxial growth method or an atomic layer deposition (ALD) method may be applied. The first cap layer **152** and the third cap layer **156** may be formed over all the pixels **102**. On the other hand, the second cap layer **154** is selectively formed over the pixels **102** (here, pixel **102b**) in which the optical adjustment is not performed on the light extracted from the light-emitting elements **120**. The thickness of the second cap layer **154** is larger than those of the first cap layer **152** and the third cap layer **156**. Therefore, application of an ink-jet method, a printing method, or the like allows the efficient formation of the second cap layer **154**.

### 4. Passivation Film and Other Structures

After forming the optical adjustment layer **150**, the passivation film **160** is prepared. Specifically, as shown in FIG. 15, the first layer **162** is first formed over the optical adjustment layer **150**. The first layer **162** may include an inorganic material such as silicon nitride, silicon oxide, silicon nitride oxide, and silicon oxynitride and may be prepared with a method similar to that of the base film **210**.

Next, the second layer **164** is formed. The second layer **164** may contain an organic resin including an acrylic resin, a polysiloxane, a polyimide, a polyester, and the like. As shown in FIG. 15, the second layer **164** may be formed at a thickness so that depressions and projections caused by the partition wall **116** are absorbed and a flat surface is provided. The second layer **164** may be formed by a wet-type film-forming method such as an ink-jet method. Alternatively, the second layer **164** may be prepared by atomizing or vaporizing oligomers serving as a raw material of the aforementioned polymer material at a reduced pressure, spraying the first layer **162** with the oligomers, and then polymerizing the oligomers.

After that, the third layer **166** is formed. The third layer **166** may have the same structure as the first layer **162** and

can be formed with the same method as that of the first layer 162. Through these processes, the passivation film 160 is fabricated.

After that, the opposing substrate 112 is fixed through the filler 170 (FIG. 7). The filler 170 may contain a polymer material such as a polyester, an epoxy resin, and an acrylic resin and may be formed by applying a printing method, a lamination method or the like. A desiccant may be included in the filler 170. The opposing substrate 112 may include the same material as the substrate 110. When flexibility is provided to the display device 100, a polymer material such as a polyolefin and a polyimide can be applied for the opposing substrate 112 in addition to the aforementioned polymer materials. In this case, the base material is formed over the substrate 110 as described above, and then the elements such as the transistor 224 and the light-emitting element 120 are fabricated thereover. After that, an interface between the substrate 110 and the base material is irradiated with light such as a laser to reduce adhesion between the substrate 110 and the base material, and then the substrate 110 is physically peeled off, leading to the formation of the flexible display device 100.

Although not shown, a polarizing plate (circularly polarizing plate) may be formed without using the opposing substrate 112. Alternatively, a polarizing plate may be arranged over or under the opposing substrate 112.

The aforementioned modes described as the embodiments of the present invention can be implemented by appropriately combining with each other as long as no contradiction is caused. Furthermore, any mode which is realized by persons ordinarily skilled in the art through the appropriate addition, deletion, or design change of elements or through the addition, deletion, or condition change of a process is included in the scope of the present invention as long as they possess the concept of the present invention.

In the specification, although the cases of the organic EL display device are exemplified, the embodiments can be applied to any kind of display devices of the flat panel type such as other self-emission type display devices, liquid crystal display devices, and electronic paper type display device having electrophoretic elements and the like. In addition, it is apparent that the size of the display device is not limited, and the embodiment can be applied to display devices having any size from medium to large.

It is properly understood that another effect different from that provided by the modes of the aforementioned embodiments is achieved by the present invention if the effect is obvious from the description in the specification or readily conceived by persons ordinarily skilled in the art.

What is claimed is:

1. A display device comprising: a first pixel including:

a first pixel electrode;

a first electroluminescent (EL) layer over the first pixel electrode; and a second electrode over the first EL layer; a second pixel adjacent to the first pixel, the second pixel including: a second pixel electrode;

a second EL layer over the second pixel electrode; and the second electrode over the second EL layer; a first cap layer over the second electrode, the first cap layer including a polymer material or an inorganic material containing an element selected from Group 14 elements;

a second cap layer over the first cap layer and overlapping with the first EL layer; and a third cap layer covering the second cap layer, overlapping with the first EL layer

and the second EL layer, and in direct contact with the first cap layer in a region overlapping with the second EL layer, wherein

a thickness of the second cap layer is larger than a thickness of the third cap layer in an area overlapping with the first EL layer.

2. The display device according to claim 1, wherein a thickness of the second cap layer is equal to or more than 2  $\mu\text{m}$  and equal to or less than 10  $\mu\text{m}$ .

3. The display device according to claim 1, wherein the second cap layer includes a resin.

4. The display device according to claim 1,

wherein the third cap layer is spaced apart from the first cap layer with the second cap layer sandwiched therebetween over an emission region of the first pixel.

5. The display device according to claim 1, wherein an emission peak wavelength of the first EL layer is different from an emission peak wavelength of the second EL layer.

6. The display device according to claim 1, wherein an emission peak wavelength of the first EL layer is longer than an emission peak wavelength of the second EL layer.

7. The display device according to claim 1, wherein a refractive index of the second cap layer is equal to or less than a refractive index of the first cap layer.

8. The display device according to claim 1,

wherein a sealing film covering a plurality of pixels including the first pixel and the second pixel is arranged over the third cap layer,

the thickness of the second cap layer is larger than a thickness of the sealing film in the area, and the sealing film includes silicon nitride or silicon oxide.

9. The display device according to claim 8,

wherein the third cap layer includes fluorine, and the sealing film includes:

an inorganic film in direct contact with the third cap layer; and

an organic film on an opposite side of the inorganic film from the third cap layer and in direct contact with the inorganic film.

10. A display device comprising: a first pixel comprising: a first pixel electrode;

a first electroluminescent (EL) layer over the first pixel electrode; and a second electrode over the first EL layer; a second pixel adjacent to the first pixel, the second pixel including: a second pixel electrode;

a second EL layer over the second pixel electrode; and the second electrode over the second EL layer; a third pixel adjacent to the second pixel, the third pixel including: a third pixel electrode;

a third EL layer over the third pixel electrode; and the second electrode over the third EL layer;

a first cap layer over the second electrode, the first cap layer including a polymer material or an inorganic material containing an element selected from Group 14 elements;

a second cap layer over the first cap layer and overlapping with the first EL layer without overlapping with the second EL layer and the third EL layer; and

a third cap layer covering the second cap layer, overlapping with the first EL layer, the second EL layer, and the third EL layer, and in direct contact with the first cap layer in a region overlapping with the third EL layer, wherein

a thickness of the second cap layer is larger than a thickness of the third cap layer in an area overlapping with the first EL layer, and

## 19

the first EL layer, the second EL layer, and the third EL layer emit lights with colors different from one another.

11. The display device according to claim 10, wherein a thickness of the second cap layer is equal to or more than 2  $\mu\text{m}$  and equal to or less than 10  $\mu\text{m}$ .

12. The display device according to claim 10, wherein the second cap layer includes a resin.

13. The display device according to claim 10, wherein the third cap layer is spaced apart from the first cap layer with the second cap layer sandwiched therebetween over an emission region of the first pixel.

14. The display device according to claim 13, wherein the third cap layer is in contact with the first cap layer over an emission region of the second pixel.

15. The display device according to claim 13, wherein the second cap layer overlaps with the second EL layer.

16. The display device according to claim 15, wherein the third cap layer is spaced apart from the first cap layer with the second cap layer sandwiched therebetween over the emission region of the second pixel.

17. The display device according to claim 10, wherein an emission peak wavelength of the first EL layer is different

## 20

from an emission peak wavelength of the second EL layer and an emission peak wavelength of the third EL layer.

18. The display device according to claim 10, wherein an emission peak wavelength of the first EL layer is longer than an emission peak wavelength of the second EL layer and an emission peak wavelength of the third EL layer.

19. The display device according to claim 18, wherein the emission peak wavelength of the second EL layer is longer than the emission peak wavelength of the third EL layer.

20. The display device according to claim 10, wherein a sealing film covering a plurality of pixels including the first pixel and the second pixel is arranged over the third cap layer,

the third cap layer includes fluorine,

the thickness of the second cap layer is larger than a thickness of the sealing film in the area, and

the sealing film includes:

an inorganic film in direct contact with the third cap layer; and

an organic film on an opposite side of the inorganic film from the third cap layer and in direct contact with the inorganic film.

\* \* \* \* \*

|                |                                                                        |         |            |
|----------------|------------------------------------------------------------------------|---------|------------|
| 专利名称(译)        | 带盖层的显示装置                                                               |         |            |
| 公开(公告)号        | <a href="#">US10522777</a>                                             | 公开(公告)日 | 2019-12-31 |
| 申请号            | US15/730162                                                            | 申请日     | 2017-10-11 |
| [标]申请(专利权)人(译) | 株式会社日本显示器                                                              |         |            |
| 申请(专利权)人(译)    | 日本展示INC.                                                               |         |            |
| 当前申请(专利权)人(译)  | 日本展示INC.                                                               |         |            |
| [标]发明人         | USHIKUBO TAKAHIRO<br>MAEDA NORIHISA                                    |         |            |
| 发明人            | USHIKUBO, TAKAHIRO<br>MAEDA, NORIHISA                                  |         |            |
| IPC分类号         | H01L51/50 H01L35/24 H01L51/00 H01L29/08 H01L51/52 H01L27/32            |         |            |
| CPC分类号         | H01L51/5265 H01L51/5092 H01L51/504 H01L51/5253 H01L51/5064 H01L27/3244 |         |            |
| 优先权            | 2016210298 2016-10-27 JP                                               |         |            |
| 其他公开文献         | US20180123068A1                                                        |         |            |
| 外部链接           | <a href="#">Espacenet</a>                                              |         |            |

# 摘要(译)

提供一种具有第一像素和与第一像素相邻的第二像素的显示装置。第一像素包括第一像素电极，在第一像素电极上方的第一EL层和在第一EL层上方的第二电极。第二像素包括第二像素电极，在第二像素电极上方的第二EL层和在第二EL层上方的第二电极。该显示装置还具有在第二电极上方的第一盖层，在第一盖层上方且与第一EL层重叠的第二盖层，以及覆盖第二盖层的第三盖层，其与第一EL层和第一EL层重叠。第二EL层，并在与第二EL层重叠的区域中与第一盖层接触。

