



US 20190074448A1

(19) **United States**(12) **Patent Application Publication**
Lim et al.(10) **Pub. No.: US 2019/0074448 A1**(43) **Pub. Date: Mar. 7, 2019**(54) **A PLURALITY OF HOST MATERIALS AND
ORGANIC ELECTROLUMINESCENT
DEVICE COMPRISING THE SAME**(71) Applicant: **Rohm and Haas Electronic Materials
Korea Ltd.**(72) Inventors: **Young-Mook Lim, Yongin (KR);
Bitnari Kim, Suwon (KR)**(73) Assignees: **Rohm and Haas Electronic Materials
Korea Ltd., Cheonan (KR); Rohm and
Haas Electronic Materials Korea
Ltd., Cheonan (KR)**(21) Appl. No.: **15/774,288**(22) PCT Filed: **Nov. 1, 2016**(86) PCT No.: **PCT/KR2016/012455**

§ 371 (c)(1),

(2) Date: **May 8, 2018**(30) **Foreign Application Priority Data**

Nov. 17, 2015 (KR) 10-2015-0161209

Sep. 20, 2016 (KR) 10-2016-0120026

Publication Classification(51) **Int. Cl.****H01L 51/00** (2006.01)**C07D 495/04** (2006.01)**C07D 491/048** (2006.01)**C07D 403/10** (2006.01)**C07D 209/86** (2006.01)**C07D 209/08** (2006.01)(52) **U.S. Cl.**CPC **H01L 51/0072** (2013.01); **H01L 51/0067**
(2013.01); **H01L 51/0059** (2013.01); **C07D**
495/04 (2013.01); **H01L 51/5016** (2013.01);
C07D 403/10 (2013.01); **C07D 209/86**
(2013.01); **C07D 209/08** (2013.01); **C07D**
491/048 (2013.01)

(57)

ABSTRACT

The present disclosure relates to a host material and an organic electroluminescent device comprising the same. By using a specific combination of two or more host compounds according to the present disclosure, the organic electroluminescent device of the present disclosure has luminous efficiency at least equivalent to or higher than conventional devices and has lifespan better than conventional devices.

A PLURALITY OF HOST MATERIALS AND ORGANIC ELECTROLUMINESCENT DEVICE COMPRISING THE SAME

TECHNICAL FIELD

[0001] The present disclosure relates to a plurality of host materials and an organic electroluminescent device comprising the same.

BACKGROUND ART

[0002] An electroluminescent (EL) device is a self-light-emitting device which has advantages in that it provides a wider viewing angle, a greater contrast ratio, and a faster response time. An organic EL device was first developed by Eastman Kodak, by using small aromatic diamine molecules and aluminum complexes as materials to form a light-emitting layer [Appl. Phys. Lett. 51, 913, 1987].

[0003] The organic EL device (OLED) converts electric energy into light when electricity is applied to an organic light-emitting material(s). Generally, the organic EL device has a structure comprising an anode, a cathode, and an organic layer disposed between the anode and the cathode. The organic layer of the organic EL device comprises a hole injection layer, a hole transport layer, an electron blocking layer, a light-emitting layer (comprising a host material and a dopant material), an electron buffering layer, a hole blocking layer, an electron transport layer, an electron injection layer, etc. Depending on its function, materials for forming the organic layer can be classified as a hole injection material, a hole transport material, an electron blocking material, a light-emitting material, an electron buffering material, a hole blocking material, an electron transport material, an electron injection material, etc. When a voltage is applied to the organic EL device, holes and electrons are injected from an anode and a cathode, respectively, to the light-emitting layer. Excitons having high energy are formed by recombinations between the holes and the electrons, the energy puts the organic light-emitting compound in an excited state, and the decay of the excited state results in a relaxation of the energy level into a ground state, accompanied by light-emission.

[0004] The most important factor determining luminous efficiency in the organic EL device is light-emitting materials. The light-emitting material needs to have high quantum efficiency, high electron mobility, and high hole mobility. Furthermore, the light-emitting layer formed by the light-emitting material needs to be uniform and stable. Depending on the colors visualized by light-emission, the light-emitting materials can be classified as a blue-, green-, or red-emitting material, and can additionally include a yellow- or orange-emitting material. Furthermore, the light-emitting material can be classified according to its function, as a host material and a dopant material. Recently, the development of an OLED providing high efficiency and a long lifespan is urgent. In particular, considering EL requirements for a middle or large-sized OLED panel, materials showing better performance than conventional ones must be urgently developed. In order to achieve the development, a host material which plays a role as a solvent in a solid state and transfers energy, should have high purity, and an appropriate molecular weight for being deposited under a vacuum. In addition, a host material should have high glass transition temperature and high thermal decomposition temperature to

ensure thermal stability; high electrochemical stability to have a long lifespan; ease of preparation for amorphous thin film; and good adhesion to materials of adjacent layers. Furthermore, a host material should not move to an adjacent layer.

[0005] The light-emitting material can be prepared by combining a host with a dopant to improve color purity, luminous efficiency, and stability. Generally, a device showing good EL performances comprises a light-emitting layer prepared by combining a host with a dopant. The host material greatly influences the efficiency and lifespan of the EL device when using a host/dopant system, and thus its selection is important.

[0006] Korean Patent Application Laying-Open No. 10-2014-0096203 discloses an organic electroluminescent device using indole derivatives and biscarbazole compounds as a plurality of host materials. However, it does not specifically disclose an organic electroluminescent device comprising a compound having a structure wherein benzo-carbazole and triazinyl are connected via a pyridine linker, as a host material.


DISCLOSURE OF THE INVENTION

Problems to be Solved

[0007] The objective of the present disclosure is to provide an organic electroluminescent device that has luminous efficiency at least equivalent to or higher than conventional devices and has lifespan longer than conventional devices.

Solution to Problems

[0008] As a result of an earnest study for solving the above-described problems, the present inventors found that the above objective can be achieved by a host material that comprises one or more first host compounds and one or more second host compounds wherein the first host compound is represented by the following formula 1 and the second host compound is represented by the following formula 2.



(1)

[0009] wherein

[0010] L_1 represents a single bond or a substituted or unsubstituted (C6-C30)arylene,

[0011] A represents hydrogen, a substituted or unsubstituted phenyl, a substituted or unsubstituted naphthyl, a substituted or unsubstituted fluorenyl, a substituted or unsubstituted dibenzothiophenyl, or a substituted or unsubstituted dibenzofuranyl,

[0012] Ar_1 , Ar_2 and Ar_3 , each independently, represent a substituted or unsubstituted (C6-C30)aryl(ene), or a substituted or unsubstituted 3- to 30-membered heteroaryl(ene); or


Ar₂ and Ar₃ may be linked to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring, whose carbon atom(s) may be replaced with at least one heteroatom selected from the group consisting of nitrogen, oxygen, and sulfur,

[0013] R₁ represents deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted 3- to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted di(C1-C30)alkyl(C6-C30)arylsilyl, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino; or R₁ may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring,

[0014] wherein the heteroaryl(ene) contains one or more heteroatoms selected from the group consisting of B, N, O, S, Si, and P,

[0015] a represents an integer of 0 to 4,

[0016] and when a is an integer of 2 or more, each of R₁ may be the same or different;



[0017] wherein

[0018] Ar₄ and Ar₅, each independently, represent a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted (C3-C30)cycloalkyl, or a substituted or unsubstituted 3- to 30-membered heteroaryl,

[0019] R₃ and R₄, each independently, represent deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted 3- to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted di(C1-C30)alkyl(C6-C30)arylsilyl, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino,

[0020] wherein the heteroaryl contains one or more heteroatoms selected from the group consisting of B, N, O, S, Si, and P, and

[0021] c represents an integer of 0 to 4; d represents an integer of 0 to 6; and when c or d is an integer of 2 or more, each of R₃ or R₄ may be the same or different.

Effects of the Invention

[0022] The present disclosure provides an organic electroluminescent device that has luminous efficiency at least equivalent to or higher than conventional devices and has lifespan longer than conventional devices. Furthermore, a display system or a lighting system using the organic electroluminescent device of the present disclosure can be produced.

EMBODIMENTS OF THE INVENTION

[0023] Hereinafter, the present disclosure will be described in detail. However, the following description is intended to explain the invention, and is not meant in any way to restrict the scope of the invention.

[0024] The host materials that comprise organic electroluminescent compounds represented by formula 1 above and represented by formula 2 above will be described in detail.

[0025] In formula 1, L₁ may represent a single bond or a substituted or unsubstituted (C6-C30)arylene, preferably a single bond or a substituted or unsubstituted (C6-C25)arylene, more preferably a single bond or a substituted or unsubstituted (C6-C18)arylene, and may include a single bond, an unsubstituted phenylene, an unsubstituted naphthylene, and an unsubstituted biphenylene.

[0026] In formula 1, A may represent hydrogen, a substituted or unsubstituted phenyl, a substituted or unsubstituted naphthyl, a substituted or unsubstituted fluorenyl, a substituted or unsubstituted dibenzothiophenyl, or a substituted or unsubstituted dibenzofuranyl, preferably hydrogen, an unsubstituted phenyl, a fluorenyl substituted with one or more methyl, an unsubstituted naphthyl, an unsubstituted dibenzothiophenyl, or an unsubstituted dibenzofuranyl; and the substituted fluorenyl may be a fluorenyl substituted with dimethyl.

[0027] In formula 1, Ar₁ to Ar₃, each independently, may represent a substituted or unsubstituted (C6-C30)aryl(ene), or a substituted or unsubstituted 3 to 30-membered heteroaryl(ene); Ar₂ and Ar₃ may be linked to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring, whose carbon atom(s) may be replaced with at least one heteroatom selected from the group consisting of nitrogen, oxygen, and sulfur; preferably, Ar₁ to Ar₃, each independently, may represent a substituted or unsubstituted (C6-C25)aryl(ene); Ar₂ and Ar₃ may be linked to form a substituted or unsubstituted 5 to 25-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring, whose carbon atom(s) may be replaced with at least one heteroatom selected from the group consisting of nitrogen, oxygen, and sulfur; more preferably, Ar₁ to Ar₃, each independently, may represent a substituted or unsubstituted (C6-C20)aryl(ene); Ar₂ and Ar₃ may be linked to form a substituted or unsubstituted 5 to 20-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring, whose carbon

atom(s) may be replaced with nitrogen. For example, Ar₁ and Ar₂ may be a phenyl substituted or unsubstituted with naphthyl or phenanthrenyl, an unsubstituted biphenyl, an unsubstituted terphenyl, a fluorenyl substituted with dimethyl, or a benzofluorenyl substituted with dimethyl; Ar₃ may represent an unsubstituted phenylene, an unsubstituted naphthylene, or a fluorenylene substituted with dimethyl; and Ar₂ and Ar₃ may be linked to form an unsubstituted carbazole.

[0028] In formula 1, R₁ may represent deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted 3 to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted di(C1-C30)alkyl(C6-C30)arylsilyl, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino; or R₁ may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring; preferably, R₁ may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 5 to 25-membered, mono- or polycyclic aromatic ring; more preferably, R₁ may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 5 to 18-membered, mono- or polycyclic, aromatic ring; specifically, the aromatic ring formed by linking the adjacent substituents may be selected from the group consisting of a benzene, an indole, an indene, a benzofuran and a bezothiophene, substituted or unsubstituted with a (C1-C10)alkyl or a (C6-C15)aryl; for example, the adjacent substituents may be linked to form an unsubstituted benzene, an indene substituted with dimethyl, an unsubstituted benzofuran or an unsubstituted bezothiophene.

[0029] In formula 1, a represents an integer of 0 to 4, preferably an integer of 0 to 2; and when a is an integer of 2 or more, each of R₁ may be the same or different.

[0030] In formula 2, Ar₄ and Ar₅, each independently, may represent a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted (C3-C30)cycloalkyl, or a substituted or unsubstituted 3- to 30-membered heteroaryl; preferably, each independently, may represent a substituted or unsubstituted (C6-C25)aryl; more preferably, each independently, may represent an unsubstituted (C6-C18)aryl, such as, an unsubstituted phenyl, an unsubstituted naphthyl, or an unsubstituted biphenyl.




[0031] In formula 2, R₃ and R₄, each independently, may represent deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted 3- to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted

di(C1-C30)alkyl(C6-C30)arylsilyl, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino; preferably, each independently, may represent a substituted or unsubstituted (C6-C25)aryl; or more preferably, each independently, may represent an unsubstituted (C6-C20)aryl, such as an unsubstituted phenyl, or an unsubstituted terphenyl.


[0032] In formula 2, c may represent an integer of 0 to 4; d may represent an integer of 0 to 6; preferably, c and d, each independently, may represent 0 or 2; more preferably, c and d, each independently, may represent 0 or 1. When each of c or d represents an integer of 2 or more, each of R₃ or R₄ may be the same or different.

[0033] In formulae 1 and 2, the heteroaryl contains one or more heteroatoms selected from the group consisting of B, N, O, S, Si, and P; preferably, one or more heteroatoms selected from the group consisting of N, O, and S.


[0034] The compound of formula 1 of the present disclosure may be represented by any one of the following formulae 3 to 7:



-continued



(6)



(7)

[0035] In formulae 3 to 7, Ar_1 to Ar_3 , each independently, may represent a substituted or unsubstituted (C6-C30)aryl(ene), or a substituted or unsubstituted 3 to 30-membered heteroaryl(ene); preferably, a substituted or unsubstituted (C6-C25)aryl(ene); more preferably a substituted or unsubstituted (C6-C20)aryl(ene); for example, Ar_1 and Ar_2 , each independently, may represent a phenyl substituted or unsubstituted with naphthyl or phenanthrenyl, an unsubstituted biphenyl, an unsubstituted terphenyl, a fluorenyl substituted with dimethyl, or a benzofluorenyl substituted with dimethyl; and Ar_3 may represent an unsubstituted phenylene, an unsubstituted naphthylene, or a fluorenylene substituted with dimethyl.

[0036] In formulae 4 and 6, X may represent S, O or CR₇R₈, preferably S or O.

[0037] In formulae 3 to 6, R_2 and R_5 to R_8 , each independently, may represent deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted 3- to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted di(C1-C30)alkyl(C6-C30)arylsilyl, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino; or R_2 and R_5 to R_8 , each independently, may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, ali-


cyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring, whose carbon atom(s) may be replaced with at least one heteroatom selected from the group consisting of nitrogen, oxygen, and sulfur; or preferably, R_2 and R_5 to R_8 , each independently, may represent a substituted or unsubstituted (C1-C20)alkyl; or R_2 and R_5 to R_8 , each independently, may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 5 to 25-membered, mono- or polycyclic, aromatic ring, whose carbon atom(s) may be replaced with at least one heteroatom selected from the group consisting of nitrogen, oxygen, and sulfur; or more preferably, R_2 and R_5 to R_8 , each independently, may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 5 to 18-membered, mono- or polycyclic, aromatic ring; for example, the adjacent substituents may be linked to form an unsubstituted benzene ring, or an indene ring substituted with dimethyl.

[0038] In formulae 3 to 7, the heteroaryl contains one or more heteroatoms selected from the group consisting of B, N, O, S, Si, and P; preferably, one or more heteroatoms selected from the group consisting of N, O, and S.


[0039] In formulae 3 to 7, b and f, each independently, may represent an integer of 0 to 4, and e may represent an integer of 0 to 2; when each of b or f represents an integer of 2 or more, or when e represents an integer of 2, each of R_2 , R_5 , or R_6 may be the same or different. Preferably, b and f, each independently, may represent an integer of 0 to 2, and e may represent an integer of 0.

[0040] In formulae 3 to 7, L_1 , R_1 , and a are as defined in formula 1 above.

[0041] The compound of formula 3 of the present disclosure may be represented by any one of the following formulae 8 to 10, and the compound of formula 4 of the present disclosure may be represented by the following formula 11:




(8)




(9)

-continued



(10)



(11)


[0042] In formulae 8 to 11, R_9 to R_{14} , each independently, may represent deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted 3- to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted di(C1-C30)alkyl(C6-C30)arylsilyl, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino; R_9 to R_{14} , each independently, may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic ring, or a combination of the alicyclic ring and the aromatic ring, whose carbon atom(s) may be replaced with at least one heteroatom selected from the group consisting of nitrogen, oxygen, and sulfur; preferably, R_9 to R_{14} , each independently, may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 5 to 25-membered, mono- or polycyclic, aromatic ring, whose carbon atom(s) may be replaced with at least one heteroatom selected from the group consisting of nitrogen, oxygen, and sulfur; or more preferably, R_9 to R_{14} , each independently, may be linked to an adjacent substituent(s) to form an unsubstituted 5 to 18-membered, mono- or polycyclic, aromatic ring; for example, R_9 to R_{14} , each independently, may be linked to an adjacent substituent(s) to form an unsubstituted benzene ring.

[0043] In formulae 8 to 11, the heteroaryl contains one or more heteroatoms selected from the group consisting of B, N, O, S, Si, and P; preferably, one or more heteroatoms selected from the group consisting of N, O, and S.


[0044] In formulae 8 to 11, g and h, each independently, may represent an integer of 0 to 6; i and k, each independently, may represent an integer of 0 to 4; j and m, each independently, may represent an integer of 0 to 7; when each of g, h, i, j, k or m represents an integer of 2 or more, each of R_9 , R_{10} , R_{11} , R_{12} , R_{13} , or R_{14} may be the same or different. Preferably, g, h, i, and k, each independently, may represent 0, and, j and m, each independently, may represent 0 or 2.

[0045] In formulae 8 to 11, L_1 , R_1 , R_2 , R_5 , R_6 , Ar_1 to Ar_3 , a, b, e, and f are as defined in formulae 3 to 7.

[0046] According to one embodiment of the present disclosure, the compound of formula 2 of the present disclosure may be represented by any one of the following formulae 12 to 16:




(12)



(13)

-continued



[0047] In formulae 12 to 16, R₃, R₄, Ar₄, Ar₅, c, and d are as defined in formula 2.


[0048] Herein, “(C1-C30)alkyl” indicates a linear or branched alkyl having 1 to 30, preferably 1 to 20, and more preferably 1 to 10 carbon atoms, and includes methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, tert-butyl, etc. “(C2-C30) alkenyl” indicates a linear or branched alkenyl having

2 to 30, preferably 2 to 20, and more preferably 2 to 10 carbon atoms and includes vinyl, 1-propenyl, 2-propenyl, 1-butenyl, 2-butenyl, 3-butenyl, 2-methylbut-2-enyl, etc. “(C2-C30)alkynyl” indicates a linear or branched alkynyl having 2 to 30, preferably 2 to 20, and more preferably 2 to 10 carbon atoms and includes ethynyl, 1-propynyl, 2-propynyl, 1-butyne, 2-butyne, 3-butyne, 1-methylpent-2-ynyl, etc. Herein, “(C3-C30)cycloalkyl” indicates a mono- or polycyclic hydrocarbon having 3 to 30, preferably 3 to 20, more preferably 3 to 7 ring backbone carbon atoms. The cycloalkyl includes cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, etc. Herein, “3 to 7-membered heterocycloalkyl” indicates a cycloalkyl having 3 to 7, preferably 5 to 7 ring backbone atoms including at least one heteroatom selected from B, N, O, S, Si, and P; preferably O, S, and N, and includes tetrahydrofuran, pyrrolidine, thiolan, tetrahydropyran, etc. Herein, “(C6-C30)aryl(ene)” indicates a monocyclic ring-type or fused ring-type radical derived from aromatic hydrocarbon having 6 to 30, preferably 6 to 20 ring backbone carbon atoms wherein the (C6-C30)aryl (ene) may be partially saturated. The aryl includes phenyl, biphenyl, terphenyl, naphthyl, binaphthyl, phenylnaphthyl, naphthylphenyl, fluorenyl, phenylfluorenyl, benzofluorenyl, dibenzofluorenyl, phenanthrenyl, phenylphenanthrenyl, anthracenyl, indenyl, triphenylenyl, pyrenyl, tetracenyl, perylenyl, chrysenyl, naphthacenyl, fluoranthenyl, etc. Herein, “3 to 30-membered heteroaryl(ene)” indicates an aryl group having 3 to 30 ring backbone atoms including at least one, preferably 1 to 4, heteroatoms selected from the group consisting of B, N, O, S, Si, and P; may be a monocyclic ring, or a fused ring condensed with at least one benzene ring; may be partially saturated; may be one formed by linking at least one heteroaryl or aryl group to a heteroaryl group via a single bond(s); and includes a monocyclic ring-type heteroaryl such as furyl, thiophenyl, pyrrolyl, imidazolyl, pyrazolyl, thiazolyl, thiadiazolyl, isothiazolyl, isoxazolyl, oxazolyl, oxadiazolyl, triazinyl, tetrazinyl, triazolyl, tetrazolyl, furazanyl, pyridyl, pyrazinyl, pyrimidinyl, pyridazinyl, etc., and a fused ring-type heteroaryl such as benzofuranyl, benzothiophenyl, isobenzofuranyl, dibenzofuranyl, dibenzothiophenyl, benzoimidazolyl, benzothiazolyl, benzoisothiazolyl, benzoisoxazolyl, benzoxazolyl, isoindolyl, indolyl, benzoindolyl, indazolyl, benzothiadiazolyl, quinolyl, isoquinolyl, cinnolyl, quinazolinyl, quinoxalyl, naphthyridyl, carbazoyl, phenoxazinyl, phenanthridinyl, benzodioxolyl, etc. Further, “halogen” includes F, Cl, Br, and I.


[0049] Furthermore, herein, “substituted” in the expression, “substituted or unsubstituted,” means that a hydrogen atom in a certain functional group is replaced with another atom or group, i.e. a substituent. The substituents of the substituted aryl(ene), the substituted heteroaryl(ene), the substituted alkyl, the substituted alkenyl, the substituted alkynyl, the substituted cycloalkyl, the substituted trialkylsilyl, the substituted triarylsilyl, the substituted dialkylaryl-silyl, the substituted mono- or di-arylamino, the substituted phenyl, the substituted naphthyl, the substituted fluorenyl, the substituted dibenzothiophenyl, the substituted dibenzofuranyl, and the substituted, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring in L₁, A, Ar₁ to Ar₅, and R₁ to R₁₄ of formulae 1 to 11 of the present disclosure, each independently, are at least one selected from the group consisting of deuterium, a halogen; a cyano; a carboxy; a nitro; a

hydroxyl; a (C1-C30)alkyl; a halo(C1-C30)alkyl; a (C2-C30)alkenyl; a (C2-C30)alkynyl; a (C1-C30)alkoxy; a (C1-C30)alkylthio; a (C3-C30)cycloalkyl; a 3- to 7-membered heterocycloalkyl; a (C6-C30)aryloxy; a (C6-C30)arylthio; a 3- to 30-membered heteroaryl unsubstituted or substituted with a (C6-C30)aryl or di(C6-C30)arylamino; a (C6-C30)aryl unsubstituted or substituted with a cyano, a 3- to 30-membered heteroaryl or a tri(C6-C30)arylsilyl; a tri(C1-C30)alkylsilyl; a tri(C6-C30)arylsilyl; a di(C1-C30)alkyl (C6-C30)arylsilyl; a (C1-C30)alkyldi(C6-C30)arylsilyl; an amino; a mono- or di-(C1-C30)alkylamino; a mono- or di-(C6-C30)arylamino; a (C1-C30)alkyl(C6-C30)arylamino; a (C1-C30)alkylcarbonyl; a (C1-C30)alkoxycarbonyl; a (C6-C30)arylcarbonyl; a di(C6-C30)arylboronyl; a di(C1-C30)alkylboronyl; a (C1-C30)alkyl(C6-C30)arylboronyl; a (C6-C30)aryl(C1-C30)alkyl; and a (C1-C30)alkyl (C6-C30)aryl; and preferably, each independently, are at least one selected from the group consisting of a (C1-C20)alkyl, and an unsubstituted (C6-C25)aryl; more preferably, each independently, are at least one selected from the group consisting of a (C1-C10)alkyl, and an unsubstituted (C6-C18)aryl; and the substituent may include methyl, an unsubstituted naphthyl or an unsubstituted phenanthrenyl.


[0050] The first host compound of formula 1 of the present disclosure includes the following, but is not limited thereto:




H1-1




H1-2




H1-3



H1-4



H1-5




H1-6

-continued


-continued

H1-7




-continued


H1-10




H1-8




H1-11




H1-9



H1-12




-continued




H1-13

-continued




H1-15


H1-14



H1-16




-continued




H1-17

-continued




H1-19


H1-20



H1-18




H1-21




-continued


H1-22



H1-23




H1-24




-continued


H1-25



H1-26




-continued




H1-27

-continued




H1-29


H1-28



H1-30




-continued




H1-31

-continued




H1-33


H1-34



H1-32




H1-35




-continued

H1-36




-continued


H1-39




H1-37




H1-40



H1-38




H1-41




-continued

H1-42




-continued


H1-45




H1-43




H1-46



H1-44




H1-47




-continued

H1-48




-continued




H1-53

-continued




H1-55

H1-54




H1-56




-continued

H1-57




-continued


H1-60




H1-61




H1-58




H1-59



H1-62




-continued




H1-63

-continued




H1-66


H1-64




H1-65



H1-67




H1-68




-continued

H1-69




H1-70




H1-71

-continued


H1-72



H1-73




H1-74




-continued

H1-75




-continued


H1-77



H1-76




H1-78




-continued

H1-79




-continued


H1-81




H1-80



H1-82




-continued




H1-83


-continued




H1-85



H1-84




H1-86



H1-87


-continued

H1-88





-continued

H1-91




H1-92


H1-89



H1-90




H1-93




-continued

H1-94




-continued

H2-3




[0051] The second host compound of formula 2 above of the present disclosure includes the following, but is not limited thereto:


H2-1




H2-4



H2-2




H2-5




-continued

H2-6




-continued


H2-8




H2-9




H2-7



H2-10




-continued




H2-11


-continued




H2-14




H2-12



H2-15




H2-13



H2-16


-continued

H2-17





-continued

H2-29




H2-30


H2-18



H2-28




H2-31




-continued


H2-32



H2-33




H2-34




-continued


H2-35




H2-36



H2-37




-continued




H2-38


-continued




H2-41




H2-39



H2-42




H2-40




H2-43

-continued




H2-44

-continued




H2-47


H2-45




H2-48



H2-46




H2-49




-continued


H2-50



H2-51




H2-52




-continued


H2-53



H2-54




H2-55




-continued

H2-56




-continued


H2-59




H2-57




H2-60



H2-58




H2-61




-continued

H2-62




-continued


H2-65




H2-63




H2-66



H2-64




H2-67




-continued

H2-68



H2-69



[0052] The compound of formula 1 and the compound of formula 2 of the present disclosure can be prepared by a synthetic method known to one skilled in the art, e.g., bromination, Suzuki reaction, Buchwald-Hartwig reaction, Ullmann reaction, etc.

[0053] According to another embodiment of the present disclosure, a combination comprising the compound of formula 1 and the compound of formula 2 is provided. The combination above may be a combination that is comprised in a light-emitting layer of an organic electroluminescent device. In the combination of the present disclosure, the weight ratio in the light-emitting layer between the compound of formula 1 and the compound of formula 2 is in the range of 1:99 to 99:1, and preferably 30:70 to 70:30 in view of driving voltage, luminous efficiency, and lifespan.



[0054] The organic electroluminescent device of the present disclosure comprises an anode, a cathode, and one or more light-emitting layers disposed between the anode and cathode, wherein the light-emitting layers comprise a dopant and a host; the host comprises two or more host compounds; and a first host compound of the host compounds is repre-


sented by the formula 1 above; and a second host compound is represented by formula 2 above.

[0055] The light-emitting layer indicates a layer or plural layers consisting of two or more stacked layers, from which light is emitted. It is preferable that a doping amount of the dopant compound is less than 20 wt % based on the total amount of the host compound and the dopant compound. In the organic electroluminescent device of the present disclosure, the weight ratio in the light-emitting layer between the first host material and the second host material is in the range of 1:99 to 99:1, and preferably 30:70 to 70:30 in view of driving voltage, luminous efficiency, and lifespan.

[0056] The dopant for the organic electroluminescent device of the present disclosure is preferably one or more phosphorescent dopant compounds. The phosphorescent dopant compound for the organic electroluminescent device of the present disclosure is not limited, but may be preferably selected from metallated complex compounds of iridium (Ir), osmium (Os), copper (Cu) or platinum (Pt), more preferably selected from ortho-metallated complex compounds of iridium (Ir), osmium (Os), copper (Cu) or platinum (Pt), and even more preferably ortho-metallated iridium complex compounds.

[0057] The phosphorescent dopant may be preferably selected from the compound of the following formulae 101 to 103:






an integer of 2 or more, each of R_{100} may be the same or different; and e represents an integer of 1 to 3.




[0061] Specifically, the phosphorescent dopant includes the following:

[0058] wherein L is selected from the following structures:




[0059] R_{100} represents hydrogen, or a substituted or unsubstituted (C1-C30)alkyl;

[0060] R_{101} to R_{109} and R_{111} to R_{123} , each independently, represent hydrogen, deuterium, a halogen, a (C1-C30)alkyl substituted or unsubstituted with a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkoxy, a substituted or unsubstituted (C3-C30)cycloalkyl, or a substituted or unsubstituted (C6-C30)aryl; R_{120} to R_{123} , each independently, may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring, for example, a quinoline; R_{124} to R_{127} , each independently, represent hydrogen, deuterium, a halogen, a substituted or unsubstituted (C1-C30)alkyl, or a substituted or unsubstituted (C6-C30)aryl; when R_{124} to R_{127} , each independently, are an aryl, R_{124} to R_{127} , each independently, may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic or (hetero) aromatic ring, or a combination of the alicyclic ring and the (hetero)aromatic ring, for example, a fluorene, a dibenzothiophene, a dibenzofuran; R_{201} to R_{211} , each independently, represent hydrogen, deuterium, a halogen, or a (C1-C30)alkyl substituted or unsubstituted with a halogen; R_{208} to R_{211} , each independently, may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic, aromatic, or heteroaromatic ring, or a combination of the alicyclic ring, the aromatic ring, and the heteroaromatic ring, for example, a fluorene, a dibenzothiophene, a dibenzofuran; r and s , each independently, represent an integer of 1 to 3; when r or s is




-continued





D-4

-continued





D-8

D-5





D-9

D-6




D-10

D-7




D-11

-continued




D-12

-continued




D-16


D-13




D-17




D-14




D-18




D-15



D-19




-continued




D-20

-continued




D-24


D-21




D-25




D-22




D-26




D-23




D-27




-continued




D-28



D-29




D-30




D-31


-continued




D-32




D-33



D-34




D-35




D-36

-continued




D-37


-continued




D-41




D-38




D-42




D-39



D-43




D-40




D-44

-continued




D-45


-continued




D-49




D-46




D-50




D-47



D-51




D-48




D-52

-continued




D-53


-continued




D-57




D-54




D-58




D-55



D-59




D-56



D-60

-continued



D-61


D-62

D-63

D-64

D-65

-continued




D-66

D-67

D-68


D-69

-continued




D-70


-continued




D-74




D-71




D-75




D-72



D-76




D-73




D-77

-continued




D-78


-continued




D-82




D-79




D-83




D-80




D-84



D-81




D-85




D-86

-continued




D-87

-continued




D-91


D-92




D-88




D-93




D-89




D-94




D-90



D-95




-continued




D-96


-continued




D-100




D-97




D-101




D-98



D-102




D-99




D-103

-continued




D-104


-continued




D-108




D-105




D-109




D-106



D-110




D-107




D-111

-continued




D-112


-continued



D-116





D-113





D-117

D-114




D-118

D-115




D-119

-continued




D-120


-continued




D-124




D-121




D-125




D-122



D-123




D-126




D-127

-continued




D-128


-continued




D-132




D-129




D-133




D-130



D-134




D-131




D-135

-continued




D-136


D-137




D-138



D-139




-continued




D-140


D-141




D-142



D-143



-continued



selected from the group consisting of arylamine-based compounds and styrylarylamine-based compounds in the organic layer.

[0063] In the organic electroluminescent device of the present disclosure, the organic layer may further comprise at least one metal selected from the group consisting of metals of Group 1, metals of Group 2, transition metals of the 4th period, transition metals of the 5th period, lanthanides and organic metals of the d-transition elements of the Periodic Table, or at least one complex compound comprising the metal.

[0064] In the organic electroluminescent device of the present disclosure, preferably, at least one layer (hereinafter, "a surface layer") may be placed on an inner surface(s) of one or both electrode(s), selected from a chalcogenide layer, a metal halide layer and a metal oxide layer. Specifically, a chalcogenide (includes oxides) layer of silicon or aluminum is preferably placed on an anode surface of an electroluminescent medium layer, and a metal halide layer or a metal oxide layer is preferably placed on a cathode surface of an electroluminescent medium layer. Such a surface layer provides operation stability for the organic electroluminescent device. Preferably, the chalcogenide includes SiO_x ($1 \leq x \leq 2$), AlO_x ($1 \leq x \leq 1.5$), SiON , SiAlON , etc.; the metal halide includes LiF , MgF_2 , CaF_2 , a rare earth metal fluoride, etc.; and the metal oxide includes Cs_2O , Li_2O , MgO , SrO , BaO , CaO , etc.

[0065] In the organic electroluminescent device of the present disclosure, a hole injection layer, a hole transport layer, a hole auxiliary layer, an auxiliary light-emitting layer, or an electron blocking layer, or a combination thereof may be disposed between the anode and the light-emitting layer. The hole injection layer may be composed of two or more layers in order to lower an energy barrier for injecting holes from the anode to a hole transport layer or an electron blocking layer (or a voltage for injecting a hole). Each of the layers may comprise two or more compounds. The hole transport layer or electron blocking layer may be composed of two or more layers. Wherein the hole auxiliary layer or the auxiliary light-emitting layer is disposed between the hole transport layer and the light-emitting layer, and modulates hole mobility. The hole auxiliary layer or the auxiliary light-emitting layer has the effects to provide improved efficiency and lifespan of the organic electroluminescent device.

[0066] An electron buffering layer, a hole blocking layer, an electron transport layer, an electron injection layer, or a combination thereof may be disposed between the light-emitting layer and the cathode. The electron buffering layer may be composed of two or more layers in order to control the electron injection and improve characteristics of interface between the light-emitting layer and the electron injection layer. Each of the layers may comprise two or more compounds. The hole blocking layer or electron transport layer may be composed of two or more layers, and each of the layers may comprise two or more compounds.

[0067] In the organic electroluminescent device of the present disclosure, a mixed region of an electron transport compound and a reductive dopant, or a mixed region of a hole transport compound and an oxidative dopant may be placed on at least one surface of a pair of electrodes. In this case, the electron transport compound is reduced to an anion, and thus it becomes easier to inject and transport electrons from the mixed region to an electroluminescent

[0062] The organic electroluminescent device of the present disclosure may further comprise at least one compound

medium. Furthermore, the hole transport compound is oxidized to a cation, and thus it becomes easier to inject and transport holes from the mixed region to the electroluminescent medium. Preferably, the oxidative dopant includes various Lewis acids and acceptor compounds, and the reductive dopant includes alkali metals, alkali metal compounds, alkaline earth metals, rare-earth metals, and mixtures thereof. A reductive dopant layer may be employed as a charge generating layer to prepare an electroluminescent device having two or more light-emitting layers and emitting white light.

[0068] In order to form each layer of the organic electroluminescent device of the present disclosure, any of dry film-forming methods such as vacuum evaporation, sputtering, plasma, and ion plating methods, or wet film-forming methods such as spin coating, dip coating, and flow coating methods can be used. A co-evaporation or a mixture-evaporation is used for forming a film of the first host material and a film of the second host material. The co-evaporation indicates a process for two or more materials to be deposited as a mixture, by introducing each of the two or more materials into respective crucible cells, and applying electric current to the cells for each of the materials to be evaporated. Herein, a mixture-evaporation indicates a process for two or more materials to be deposited as a mixture, by mixing the two or more materials in one crucible cell before the deposition, and applying electric current to the cell for the mixture to be evaporated.


[0069] When using a wet film-forming method, a thin film can be formed by dissolving or diffusing materials forming each layer into any suitable solvent such as ethanol, chloroform, tetrahydrofuran, dioxane, etc. The solvent can be any solvent where the materials forming each layer can be dissolved or diffused, and where there are no problems in film-formation capability.

[0070] A display system or a lighting system using the organic electroluminescent device of the present disclosure can be produced.


[0071] Hereinafter, for a more in-depth understanding of the present disclosure, the luminescent properties of the organic electroluminescent device comprising the host compound of the present disclosure will be explained.

[0072] Hereinafter, the organic electroluminescent compound of the present disclosure, the preparation method and the physical properties of the compound, and the luminescent properties of the organic electroluminescent device comprising the compound will be explained in detail with reference to the following examples.

[EXAMPLE 1] PREPARATION OF COMPOUND H2-2



[0073]



[0074] 1) Preparation of Compound 1-1

[0075] After introducing a compound 7H-benzo[c]carbazole (30 g, 138.1 mmol), 5-bromo-2-iodopyridine (58.8 g, 207.1 mmol), CuI (12.5 g, 65.4 mmol), K_3PO_4 (73 g, 345.2 mmol), ethylene diamine (8.3 g, 138.1 mmol), and toluene (600 mL) into a flask, the mixture was stirred under reflux at 120° C. for 4 hours. After completion of the reaction, the mixture was extracted with ethyl acetate and purified with water, and the obtained organic layer was concentrated under reduced pressure. The organic layer was subjected to silica

gel column chromatography (methylene chloride(MC): hexane(Hex)) to obtain compound 1-1 (16 g, yield: 31%).

[0076] 2) Preparation of Compound 1-2

[0077] After introducing compound 1-1 (16 g, 42.86 mmol), pinacolatodiboron (13.1 g, 51.44 mmol), $\text{PdCl}_2(\text{PPh}_3)_2$ (3 g, 4.3 mmol), potassium acetate (KOAc) (10.5 g, 107 mmol), and 1,4-dioxane (200 mL) into a flask, the mixture was stirred under reflux at 120° C. for 2 hours. After completion of the reaction, the mixture was extracted with ethyl acetate and purified water, and the obtained organic layer was dried under reduced pressure. The organic layer was subjected to silica gel column chromatography (MC: Hex) to obtain compound 1-2 (11 g, yield: 61%).




[0078] 3) Preparation of Compound H2-2

[0079] After introducing compound 1-2 (11 g, 26.17 mmol), 2-chloro-4-(naphthalen-2-yl)-6-phenyl-1,3,5-triazine (8.3 g, 26.17 mmol), Na_2CO_3 (6.9 g, 65.42 mmol), $\text{Pd}(\text{PPh}_3)_4$ (1.5 g, 1.3 mmol), tetrahydrofuran (THF) (100 mL), and purified water (30 mL) into a flask, the mixture was stirred under reflux at 120° C. for 4 hours. After completion of the reaction, the mixture was extracted with ethyl acetate and purified water, and the obtained organic layer was concentrated under reduced pressure. The organic layer was subjected to silica gel column chromatography (MC:Hex) to obtain compound H2-2 (6.54 g, yield: 43.1%).

[Device Examples 1 to 4] OLED Comprising a First Host Compound and a Second Host Compound of the Present Disclosure as a Host

[0080] An OLED was produced using the organic electroluminescent compound of the present disclosure as follows. A transparent electrode indium tin oxide (ITO) thin film (10 Ω/sq) on a glass substrate for an OLED (Geomatec) was subjected to an ultrasonic washing with acetone, ethanol, and distilled water sequentially, and was then stored in isopropanol. The ITO substrate was then mounted on a substrate holder of a vacuum vapor depositing apparatus. HI-1 was introduced into a cell of said vacuum vapor depositing apparatus, and then the pressure in the chamber of said apparatus was controlled to 10^{-6} torr. Thereafter, an electric current was applied to the cell to evaporate the above introduced material, thereby forming a first hole injection layer having a thickness of 80 nm on the ITO substrate. HI-2 was then introduced into another cell of said vacuum vapor depositing apparatus, and evaporated by applying electric current to the cell, thereby forming a second hole injection layer having a thickness of 5 nm on the first hole injection layer. HT-1 was introduced into one cell of the vacuum vapor depositing apparatus, and evaporated by applying electric current to the cell, thereby forming a first hole transport layer having a thickness of 10 nm on the second hole injection layer. HT-3 was introduced into another cell of the vacuum vapor depositing apparatus, and evaporated by applying electric current to the cell, thereby forming a second hole transport layer having a thickness of 60 nm on the first hole transport layer. After forming the hole injection layer and the hole transport layer, a light-emitting layer was deposited thereon as follows. A first host material and a second host material shown in Table 1 below were introduced, as host materials, into a cell of the vacuum vapor depositing apparatus, and compound D-71 was introduced, as a dopant, into another cell. The two host compounds were then evaporated at the same rate of 1:1, so that the dopant was deposited in a doping amount of 3 wt % based on the

total amount of the host and dopant to form a light-emitting layer having a thickness of 40 nm on the second hole transport layer. Compounds ET-1 and EI-1 were then introduced into another two cells of the vacuum vapor depositing apparatus, respectively, and evaporated at the same rate of 1:1, thereby forming an electron transport layer having a thickness of 30 nm on the light-emitting layer. After depositing compound EI-1 as an electron injection layer having a thickness of 2 nm on the electron transport layer, an Al cathode having a thickness of 80 nm was then deposited by another vacuum vapor deposition apparatus on the electron injection layer to produce an OLED. Evaluation results of the devices produced in Device Examples 1 to 4 are shown in Table 1 below.



-continued

HT-3





TABLE 1-continued

Device Example No.	The 1 st Host	The 2 nd Host	Driving Voltage (V)	Efficiency (cd/A)	The Emission Color	T98 Life- span (hr)
Device Example 2	H1-81	H2-2	3.8	27.8	Red	153
Device Example 3	H1-92	H2-2	3.5	27.7	Red	56
Device Example 4	H1-14	H2-2	3.4	29.1	Red	62

ET-1



EI-1







TABLE 1

Device Example No.	The 1 st Host	The 2 nd Host	Driving Voltage (V)	Efficiency (cd/A)	The Emission Color	T98 Life- span (hr)
Device Example 1	H1-7	H2-2	3.4	29.3	Red	76



H1-7


D-71




H1-81

TABLE 1-continued


Device Example No.	The 1 st Host	The 2 nd Host	Driving Voltage (V)	Efficiency (cd/A)	The Emission Color	T98 Life- span (hr)
-----------------------	-----------------------------	-----------------------------	---------------------------	----------------------	--------------------------	------------------------------



H1-92



H1-14




H2-2

[Device Examples 5 to 8] OLED Comprising a First Host Compound and a Second Host Compound of the Present Disclosure as a Host

[0081] In Device Examples 5 to 8, OLEDs were produced in the same manner as in Device Examples 1 to 4, except that a first hole injection layer having a thickness of 90 nm was formed, the doping amount of the dopant was 2 wt %, an electron transport layer having a thickness of 35 nm was deposited, and the first host was changed as shown in Table 2 below. Evaluation results of the devices produced in Device Examples 5 to 8 are shown in Table 2 below.

TABLE 2


Device Example No.	The 1 st Host	The 2 nd Host	Driving Voltage (V)	Efficiency (cd/A)	The Emission Color	T98 Life- span (hr)
Device Example 5	H1-80	H2-2	3.5	28.7	Red	100
Device Example 6	H1-90	H2-2	3.6	30.3	Red	85
Device Example 7	H1-93	H2-2	3.5	29.9	Red	82
Device Example 8	H1-91	H2-2	3.6	30.0	Red	64




H1-80

TABLE 2-continued


Device Example No.	The 1 st Host	The 2 nd Host	Driving Voltage (V)	Efficiency (cd/A)	The Emission Color	T98 Life-span (hr)
--------------------	--------------------------	--------------------------	---------------------	-------------------	--------------------	--------------------



H1-90




H1-91



H1-93

TABLE 2-continued

Device Example No.	The 1 st Host	The 2 nd Host	Driving Voltage (V)	Efficiency (cd/A)	The Emission Color	T98 Life-span (hr)
--------------------	--------------------------	--------------------------	---------------------	-------------------	--------------------	--------------------



H2-2

[Comparative Device Example 1] OLED
Comprising a Conventional Organic
Electroluminescent Compound

[0082] An OLED was produced in the same manner as in Device Examples 1 to 4, except that the first host shown in Table 3 below was employed as a host for a light-emitting layer and the second host was not employed.

TABLE 3

Device Example No.	The 1 st Host	The 2 nd Host	Driving Voltage (V)	Efficiency (cd/A)	The Emission Color	T98 Life-span (hr)
Comparative Device Example 1	H1-92	—	8.1	13.6	Red	X

*X indicates that lifespan of a device was too short to be measured.

[Comparative Device Example 2] OLED
Comprising a Conventional Organic
Electroluminescent Compound

[0083] An OLED was produced in the same manner as in Device Examples 1 to 4, except that the second host shown in Table 4 below was employed as a host for a light-emitting layer and the first host was not employed.

TABLE 4


Device Example No.	The 1 st Host	The 2 nd Host	Driving Voltage (V)	Efficiency (cd/A)	The Emission Color	T98 Life-span (hr)
Comparative Device Example 2	—	H2-2	3.3	24.9	Red	7

[Comparative Device Example 3] OLED
Comprising a Conventional Organic
Electroluminescent Compound

[0084] An OLED was produced in the same manner as in Device Examples 1 to 4, except that the first host and the second host shown in Table 5 below were employed as a host for a light-emitting layer.

TABLE 5


Device Example No.	The 1 st Host	The 2 nd Host	Driving Voltage (V)	Efficiency (cd/A)	The Emission Color	T98 Life-span (hr)
Comparative Device Example 3	H1-7	Compound A	3.5	31.1	Red	40



Compound A

[0085] By using a specific combination of two or more host compounds according to the present disclosure, the organic electroluminescent device of the present disclosure has luminous efficiency at least equivalent to or higher than conventional devices and has lifespan longer than conventional devices.

1. A host material that comprises one or more first host compounds and one or more second host compounds wherein the first host compound is represented by the following formula 1 and the second host compound is represented by the following formula 2:



wherein

L_1 represents a single bond or a substituted or unsubstituted (C6-C30)arylene,


A represents hydrogen, a substituted or unsubstituted phenyl, a substituted or unsubstituted naphthyl, a substituted or unsubstituted fluorenyl, a substituted or unsubstituted dibenzothiophenyl, or a substituted or unsubstituted dibenzofuranyl,

Ar_1 , Ar_2 , and Ar_3 , each independently, represent a substituted or unsubstituted (C6-C30)aryl(ene), or a substituted or unsubstituted 3- to 30-membered heteroaryl(ene); or Ar_2 and Ar_3 may be linked to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring, whose carbon atom(s) may be replaced with at least one heteroatom selected from the group consisting of nitrogen, oxygen, and sulfur,

R_1 represents deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted 3- to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted di(C1-C30)alkyl(C6-C30)arylsilyl, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino; or R_1 may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring, wherein the heteroaryl(ene) contains one or more heteroatoms selected from the group consisting of B, N, O, S, Si, and P,

a represents an integer of 0 to 4,

and when a is an integer of 2 or more, each of R_1 may be the same or different;



wherein




Ar_4 and Ar_5 , each independently, represent a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted (C3-C30)cycloalkyl, or a substituted or unsubstituted 3- to 30-membered heteroaryl,

R_3 and R_4 , each independently, represent deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted 3- to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted di(C1-C30)alkyl(C6-C30)arylsilyl, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino,



wherein the heteroaryl contains one or more heteroatoms selected from the group consisting of B, N, O, S, Si, and P, and

c represents an integer of 0 to 4; d represents an integer of 0 to 6; and when c or d is an integer of 2 or more, each of R_3 or R_4 may be the same or different.

2. The host material according to claim 1, wherein formula 1 is represented by any one of the following formulae 3 to 7:



-continued



wherein

Ar_1 , Ar_2 , and Ar_3 , each independently, represent a substituted or unsubstituted (C6-C30)aryl(ene), or a substituted or unsubstituted 3 to 30-membered heteroaryl(ene);




X represents S, O or CR_7R_8 ;

R_2 and R_5 to R_8 , each independently, represent deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted 3- to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted di(C1-C30)alkyl(C6-C30)arylsilyl, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino; or R_2 and R_5 to R_8 , each independently, are linked to an adjacent substituent(s) to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring, whose carbon atom(s) may be replaced with at least one heteroatom selected from the group consisting of nitrogen, oxygen, and sulfur;

b and f, each independently, represent an integer of 0 to 4, and e represents an integer of 0 to 2; when each of b or f represents an integer of 2 or more, or when e represents an integer of 2, each of R_2 , R_5 , or R_6 may be the same or different; and

L_1 , R_1 , and a are as defined in claim 1.

3. The host material according to claim 2, wherein formula 3 is represented by any one of the following formulae 8 to 10:



wherein

R_9 to R_{12} , each independently, represent deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted 3- to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted di(C1-C30)alkyl(C6-C30)arylsilyl, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino; or R_9 to R_{12} , each independently, may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring,


whose carbon atom(s) may be replaced with at least one heteroatom selected from the group consisting of nitrogen, oxygen, and sulfur;

the heteroaryl contains one or more heteroatoms selected from the group consisting of B, N, O, S, Si, and P;

g and h , each independently, represent an integer of 0 to 6; i represents an integer of 0 to 4; j represents an integer of 0 to 7; when each of g , h , i or j represents an integer of 2 or more, each of R_9 , R_{10} , R_{11} or R_{12} may be the same or different; and

L_1 , R_1 , R_2 , Ar_1 , Ar_2 , Ar_3 , a , and b are as defined in claim 2.

4. The host material according to claim 2, wherein formula 4 is represented by the following formula 11:



wherein

R_{13} and R_{14} , each independently, represent deuterium, a halogen, a cyano, a substituted or unsubstituted (C1-C30)alkyl, a substituted or unsubstituted (C2-C30)alkenyl, a substituted or unsubstituted (C2-C30)alkynyl, a substituted or unsubstituted (C3-C30)cycloalkyl, a substituted or unsubstituted (C6-C30)aryl, a substituted or unsubstituted 3- to 30-membered heteroaryl, a substituted or unsubstituted tri(C1-C30)alkylsilyl, a substituted or unsubstituted tri(C6-C30)arylsilyl, a substituted or unsubstituted di(C1-C30)alkyl(C6-C30)arylsilyl, or a substituted or unsubstituted mono- or di-(C6-C30)arylamino; or R_{13} and R_{14} , each independently, may be linked to an adjacent substituent(s) to form a substituted or unsubstituted 3 to 30-membered, mono- or polycyclic, alicyclic or aromatic ring, or a combination of the alicyclic ring and the aromatic ring, whose carbon atom(s) may be replaced with at least one heteroatom selected from the group consisting of nitrogen, oxygen, and sulfur;





the heteroaryl contains one or more heteroatoms selected from the group consisting of B, N, O, S, Si, and P;

k represents an integer of 0 to 4, and m represents an integer of 0 to 7; when each of k or m represents an integer of 2 or more, each of R_{13} or R_{14} may be the same or different; and

L_1 , R_1 , R_5 , R_6 , Ar_1 , Ar_3 , a , e , and f are as defined in claim 2.



5. The host material according to claim 1, wherein formula 2 is represented by any one of the following formulae 12 to 16:

-continued




wherein Ar₄, Ar₅, R₃, R₄, c, and d are as defined in claim 1.

6. The host material according to claim 1, wherein the first host compound of formula 1 is selected from the group consisting of:




-continued




H1-2


-continued




H1-6




H1-3




H1-4



H1-7




H1-5



H1-8


-continued

H1-9





-continued

H1-12





H1-13

H1-10




H1-14

H1-11




-continued




H1-15

-continued




H1-18

H1-16



H1-19


H1-17



H1-20


-continued

H1-21




-continued


H1-24




H1-22




H1-23



H1-25




-continued




H1-26


-continued



H1-28




H1-27




H1-29

-continued




H1-30

-continued




H1-32


H1-33



H1-31




H1-34




-continued

H1-35




-continued


H1-38




H1-36




H1-39



H1-37




H1-40




-continued

H1-41





-continued

H1-44





H1-45

H1-42




H1-46

H1-43




-continued

H1-47




-continued

H1-50





H1-51


H1-48




H1-49



H1-52



-continued




H1-53

H1-54

H1-55

-continued




H1-56

H1-57


-continued

H1-58




-continued


H1-61




H1-59




H1-62



H1-60




H1-63




-continued

H1-64




-continued


H1-67




H1-68




H1-65




H1-66



H1-69




-continued




H1-70

-continued


H1-72




H1-73




H1-71



H1-74




-continued




H1-75


-continued



H1-77




H1-76



H1-78


-continued

H1-79




-continued


H1-81




H1-80



H1-82




-continued




H1-83


-continued




H1-85



H1-84




H1-86




H1-87

-continued


H1-88



H1-89




H1-90




-continued


H1-91



H1-92




H1-93




-continued

H1-94




-continued

H2-3




7. The host material according to claim 1, wherein the second host compound of formula 2 is selected from the group consisting of:


H2-1




H2-4



H2-2




H2-5




-continued

H2-6




-continued


H2-9




H2-7




H2-10




H2-8



H2-11




-continued



H2-12



-continued



H2-15



H2-16

H2-13




H2-14

H2-17




-continued

H2-18




-continued


H2-21




H2-19




H2-22



H2-20




H2-23




-continued


H2-24



H2-25




H2-26




-continued


H2-27




H2-28



H2-29




-continued




H2-30


-continued




H2-33




H2-31



H2-34




H2-32




H2-35

-continued




H2-36


-continued




H2-39




H2-37



H2-40




H2-38




H2-41

-continued


H2-42



H2-43




H2-44




-continued


H2-45




H2-46



H2-47




-continued




H2-48

-continued





H2-51

H2-49




H2-50




H2-52

H2-53




-continued

H2-54




-continued


H2-57



H2-55





H2-58




H2-59

H2-56




-continued

H2-60




-continued


H2-63




H2-64




H2-61



H2-62




H2-65




-continued

H2-66





-continued

H2-68



H2-69

H2-67



8. An organic electroluminescent device comprising an anode, a cathode, and at least one light-emitting layer disposed between the anode and cathode, wherein the light-emitting layer comprises a host and a dopant, and the host comprises the host material according to claim 1.

* * * * *

专利名称(译)	多种主体材料和包含其的有机电致发光器件		
公开(公告)号	US20190074448A1	公开(公告)日	2019-03-07
申请号	US15/774288	申请日	2016-11-01
[标]申请(专利权)人(译)	罗门哈斯电子材料有限公司		
申请(专利权)人(译)	罗门哈斯电子材料KOREA LTD.		
当前申请(专利权)人(译)	罗门哈斯电子材料KOREA LTD.		
[标]发明人	LIM YOUNG MOOK KIM BITNARI		
发明人	LIM, YOUNG-MOOK KIM, BITNARI		
IPC分类号	H01L51/00 C07D495/04 C07D491/048 C07D403/10 C07D209/86 C07D209/08		
CPC分类号	H01L51/0072 H01L51/0067 H01L51/0059 C07D495/04 C07D491/048 C07D403/10 C07D209/86 C07D209/08 H01L51/5016 H01L2251/5384		
优先权	1020150161209 2015-11-17 KR 1020160120026 2016-09-20 KR		
其他公开文献	US10454044		
外部链接	Espacenet USPTO		

摘要(译)

本发明涉及主体材料和包含该主体材料的有机电致发光器件。通过使用根据本发明的两种或更多种主体化合物的特定组合，本发明的有机电致发光器件具有至少等于或高于常规器件的发光效率并且具有比常规器件更好的寿命。

