



US008872170B2

(12) **United States Patent**
Su et al.

(10) **Patent No.:** **US 8,872,170 B2**
(45) **Date of Patent:** **Oct. 28, 2014**

(54) **IMAGE DISPLAY SYSTEM**

(71) Applicant: **InnoLux Corporation**, Miao-Li County (TW)

(72) Inventors: **Hsin-Yuan Su**, Miao-Li County (TW);
Chun-kai Li, Miao-Li County (TW);
Hsiang-Lun Hsu, Miao-Li County (TW)

(73) Assignee: **Innolux Corporation**, Miao-Li County (TW)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **13/804,712**

(22) Filed: **Mar. 14, 2013**

(65) **Prior Publication Data**

US 2013/0277648 A1 Oct. 24, 2013

(30) **Foreign Application Priority Data**

Apr. 19, 2012 (TW) 101113902 A

(51) **Int. Cl.**
H01L 51/50 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 51/5012** (2013.01)
USPC **257/40; 257/98; 257/E51.018**

(58) **Field of Classification Search**

USPC 257/40, 98, E51.018; 438/26
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,674,636 A * 10/1997 Dodabalapur et al. 428/690
6,831,409 B2 * 12/2004 Yamada 313/506
7,208,863 B2 * 4/2007 Strip 313/112
2011/0150019 A1 * 6/2011 Leatherdale et al. 372/45.01
2011/0303905 A1 * 12/2011 Gather et al. 257/40

* cited by examiner

Primary Examiner — Roy Potter


(74) *Attorney, Agent, or Firm* — McClure, Qualey & Rodack, LLP

(57) **ABSTRACT**

An image display system employing an organic electroluminescent device is provided. The organic electroluminescent device includes a substrate; a first electrode formed on the substrate; a first emitting layer formed on the first electrode, wherein the first emitting layer emits a first color of light, and a second color of light; a second electrode formed on the first emitting layer, wherein the second color of light emitted by the first emitting layer generates a first standing wave within the organic electroluminescent device, and the first emitting layer is disposed at an antinode of the first standing wave, such that the intensity of the second color of light is enhanced, and the second color of light is mixed with the first color of light to produce a white emission.

18 Claims, 7 Drawing Sheets

100






FIG. 1




FIG. 2




FIG. 3




FIG. 4


200

FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9

300




FIG. 10

1

IMAGE DISPLAY SYSTEM

CROSS REFERENCE TO RELATED APPLICATIONS

This application is based upon and claims the benefit of priority from the prior Taiwan Patent Application No. 101113902, filed on Apr. 19, 2012, the entire contents of which are incorporated herein by reference.

BACKGROUND

1. Technical Field

The present invention relates to an image display system, and in particular relates to an image display system having an organic electroluminescent device.

2. Description of the Related Art

Recently, with the development and wide application of electronic products, such as mobile phones, and notebook computers, there have been increasing demands for flat display elements which consume less power and occupy less space. Organic electroluminescent diodes are popular for use in flat panel displays as they are self-emitting and highly luminous, provide wide viewing angles, have a fast response speed, and a simple fabrication process.

An organic electroluminescent diode is an LED that uses an organic layer as the active layer. In recent years, organic electroluminescent diodes have been gradually applied in flat panel displays. One trend in organic electroluminescent diode technology is to achieve high luminescent efficiency and long operating lifetimes.

Several methods have been employed to achieve full color emission in organic electroluminescent devices. In general, there is a major tendency to fabricate full color organic electroluminescent devices by a method of RGB emitting layers or a color changing method. Among these methods, the so-called "color changing method" indicates that white organic electroluminescent diodes are formed respectively on corresponding red, green and blue color filters, and then driven by bias voltages to emit red, green and blue respectively.

In the direct full-color display technique, there is a tendency to fabricate full color organic electroluminescent devices by a method of RGB emitting layers. The so-called method of RGB emitting layers indicates that red, green and blue color arrays are formed, and then driven by bias voltages to emit red, green and blue, respectively. The individual aging rates of RGB organic electroluminescent materials, however, are different and lead to color deterioration of the organic electroluminescent device after a period of time.

Accordingly, a full-color organic electroluminescent device with a color filter has been developed to solve the problems caused by the above full-color organic electroluminescent devices. In particular, white light emitted from a white organic light emitting diode is converted to RGB by passing through the RGB color filters. Nevertheless, since the RGB emission spectrum of the white organic electroluminescent device does not precisely correspond to the RGB transmission spectrum of RGB color filters, the spectral FWHM (full width at half maximum) of the filtered RGB luminescence is enlarged and reduced, such that color saturation (NTSC ratio) of the full-color display employing the white organic electroluminescent device and RGB color filters is reduced, limiting the color range thereof.

Therefore, it is necessary to develop a simple and efficient manufacturing method and structure for a full-color organic electroluminescent device.

2

SUMMARY

An exemplary embodiment of the invention provides an image display system including an organic electroluminescent device. The organic electroluminescent device includes: a substrate; a first electrode formed on the substrate; a first emitting layer formed on the first electrode, wherein the first emitting layer emits a first color of light, and a second color of light; a second electrode formed on the first emitting layer, wherein the second color of light emitted by the first emitting layer generates a first standing wave within the organic electroluminescent device, and the first emitting layer is disposed at an antinode of the first standing wave, such that the intensity of the second color of light is enhanced, and the second color of light is mixed with the first color of light to produce a white emission.

Another exemplary embodiment of the invention provides an image display system including an organic electroluminescent device. The organic electroluminescent device includes a substrate; a first electrode formed on the substrate; a first hole injection layer, a first hole transport layer, a first emitting layer, a first spacer layer, a second emitting layer, a second spacer layer, a third emitting layer, a first electron transport layer, and a first electron injection layer sequentially formed on the first electrode, wherein the first emitting layer, the second emitting layer, and the third emitting layer are formed by the same material, and each emitting layer emits a first color, a second color, and a third color of light; a second electrode formed on the first electron injection layer, wherein the second color of light emitted by each emitting layer generates a first standing wave within the organic electroluminescent device, and the third color emitted of light by each emitting layer generates a second standing wave within the organic electroluminescent device, such that the intensities of the second color of light and the third color of light are enhanced, and the second color of light and the third color of light are mixed with the first color of light to produce a white emission.

A detailed description is given in the following embodiments with reference to the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

The disclosure can be more fully understood by reading the subsequent detailed description and examples with references made to the accompanying drawings, wherein:

FIG. 1 is a schematic cross section of an organic electroluminescent device according to an embodiment of the present invention;

FIG. 2 is an electroluminescent photograph of a blue organic electroluminescent material employed by the electroluminescent device of FIG. 1;

FIG. 3 is an electroluminescent photograph of the organic electroluminescent devices having the first hole injection layer with various thicknesses;

FIG. 4 shows a CIE coordination comparison diagram of the organic electroluminescent devices having the first hole injection layer with different thicknesses;

FIG. 5 is a schematic cross section of an organic electroluminescent device according to another embodiment of the present invention;

FIG. 6 is an electroluminescent photograph of the first emitting layer of the organic electroluminescent device as shown in FIG. 5;

FIG. 7 is an electroluminescent photograph of the second emitting layer of the organic electroluminescent device as shown in FIG. 5;

FIG. 8 is an electroluminescent photograph of the third emitting layer of the organic electroluminescent device as shown in FIG. 5;

FIG. 9 is an electroluminescent photograph of the organic electroluminescent device as shown in FIG. 5; and

FIG. 10 schematically shows an image display system including the organic electroluminescent devices of the invention.

DETAILED DESCRIPTION

Embodiments of the invention provide an organic electroluminescent device and an image display system employing the same. Due to the microcavity effect, the organic electroluminescent device of the invention can produce a white emission with emitting layers with the same material.

The following description is of the best-contemplated mode of carrying out the invention. This description is made for the purpose of illustrating the general principles of the invention and should not be taken in a limiting sense. The scope of the invention is best determined by reference to the appended claims.

As shown in FIG. 1, an organic electroluminescent device **100** according to an embodiment of the invention is provided. The organic electroluminescent device **100** includes a substrate **10**, wherein the substrate **10** can be a quartz substrate, a glass substrate, a ceramic substrate, or a plastic substrate. Further, the substrate **10** can be a substrate including a required element (such as a thin film transistor). The accompanying drawings illustrate the substrate **10** as a plain rectangle in order to simplify illustration.

A first electrode **12** (serving as an anode) is formed on the substrate **10**, wherein the first electrode **12** can be a reflective electrode having a reflectivity of about 50-100% (such as about 90%). The reflective electrode can be an opaque metal layer which is relatively thick (such as Al, Cu, Mo, Ti, Pt, Ir, Ni, Cr, Ag, Au, W, or alloys thereof). Next, still as shown in FIG. 1, a first carrier injection/transport layer **14**, a first emitting layer **16**, and a second carrier injection/transport layer **18** are sequentially formed on the first electrode **12**. Finally, a second electrode **20** (serving as a cathode) is formed on second carrier injection/transport layer **18**. The first carrier injection/transport layer **14** can be a hole injection/transport layer, including a first hole injection layer **14A**, and a first hole transport layer **14B**. The second carrier injection/transport layer **18** can be an electron injection/transport layer, including a first electron transport layer **18A**, and a first electron injection layer **18B**. The first hole injection layer **14A**, the first a hole transport layer **14B**, the first electron transport layer **18A**, and the first electron injection layer **18B** of the invention can be organic semiconductor materials (such as an organic small molecule material, or polymer material) or organic-metallic materials, and can be formed by thermal vacuum evaporation, physical vapor deposition, chemical vapor deposition (organic small molecule material), spin coating, ink-jet printing, or screen printing (polymer material) methods. Further, the thicknesses of the first hole injection layer **14A**, the first a hole transport layer **14B**, the first electron transport layer **18A**, and the first electron injection layer **18B** are not limited and can be optionally modified by a person of ordinary skill in the field.

The second electrode **20** can be a semi-transparent electrode, wherein the light absorbance of the second electrode **20** is less than 25% (such as less than 10%). The second electrode **20** can be a semi-transparent metal layer which is relatively thin (such as Al, Cu, Mo, Ti, Pt, Ir, Ni, Cr, Ag, Au, W, or alloys thereof), or a semi-transparent layer including metal and

transparent conductive materials (such as indium tin oxide (ITO), indium zinc oxide (IZO), aluminum zinc oxide (AZO), or zinc oxide (ZnO)). Herein, in order to force the organic electroluminescent device **100** to produce a white emission by microcavity effect, suitable materials of the first emitting layer **16** can be an organic electroluminescent material having a larger full width at half maximum. In an embodiment, the organic electroluminescent material can have a full width at half maximum (FWHM) of more than 90 nm. Namely, the organic electroluminescent material of the first emitting layer should have a broadband wavelength range of the visible light. For example, the first emitting layer **16** can be a green organic electroluminescent material having a full width at half maximum (FWHM) more than 90 nm, or a blue organic electroluminescent material having a full width at half maximum of more than 90 nm, such as TPB (1,1,4,4-tetraphenylbutadiene), DSA-Ph(p-bis[p-N,N-diphenyl-amino-styryl]benzene), TAZ (1,2,4-triazole derivative), DSA (istyrylarylene derivatives), or BCzVB (1,4-bis[2-(3-N-ethyl-carbazoryl)vinyl]benzene. Further, the wave-length of the first emitting layer can be adjusted by doping a dopant. The dose of the dopant is not limited and can be optionally modified by a person of ordinary skill in the field. The organic electroluminescent material of the emitting layer can be fluorescent or phosphorescent materials. The method for forming the emitting layer can be by thermal vacuum evaporation, physical vapor deposition, chemical vapor deposition (organic small molecule material), spin coating, ink-jet printing, or screen printing methods.

FIG. 2 is an electroluminescent photograph of a blue organic electroluminescent material. As show in FIG. 2, the blue organic electroluminescent material has a major luminous intensity at 440-500 nm (i.e. the first color of light B of the blue organic electroluminescent material is blue), and the blue organic electroluminescent material also has a minor luminous intensity at 520-630 nm (i.e. the second color of light Y of the blue organic electroluminescent material is yellow). Since the second color (yellow) of light Y of the blue organic electroluminescent material has a lower luminous intensity than the first color (blue) of light B, the second color (yellow) of light Y emitted by an organic electroluminescent device employing the blue organic electroluminescent material is enhanced by microcavity effect, in order to mix the first color (blue) of light B and the second color (yellow) of light Y to produce white emission. Accordingly, due to the reflective electrode **12** and the semi-transparent electrode **20**, the second color (yellow) of light Y emitted by the first emitting layer **16** generates a standing wave within the organic electroluminescent device **100**. Further, in order to enhance the emitting layer **16** of the second color of light Y, the first emitting layer **16** has to be disposed at an antinode of the standing wave.

When the first emitting layer **16** is disposed at a location near to the antinode of the standing wave with the organic electroluminescent device **100**, the luminous intensity of the second color of light Y can be enhanced by microcavity effect according to the Fabry-Perot equation. It should be noted that, the thickness of the first carrier injection/transport layer **14** (such as hole injection/transport layer), and the second carrier injection/transport layer **18** (such as electron injection/transport layer) can be optionally adjusted in order to force the location of the first emitting layer **16** to be near to the antinode of the standing wave. However, the recombination region of the electrons and holes would also be moved when adjusting the thickness of the carrier injection/transport layer. In order to maintain the recombination region of the electrons and holes within the first emitting layer **16**, the thickness of the

first hole transport layer **14B**, the thickness of the first emitting layer thickness, the thickness of first electron transport layer **18A**, and thickness of first electron injection layer **18B** are fixed, and only the thickness of the first hole injection layer **14A** (with a relatively high hole mobility) is adjusted. For example, the thickness of the first hole transport layer **14B** can be of between 50-200 Å (such as 100 Å), the thickness of the first emitting layer thickness can be of between 100-400 Å (such as 250 Å), the thickness of the first electron transport layer **18A** and the electron injection layer **18B** can be of between 300-700 Å (the thickness of the first electron transport layer **18A** can be 200 Å, and the thickness of the first electron injection layer **18B** can be 100 Å).

FIG. 3 is an electroluminescent photograph of the organic electroluminescent devices **100** with various thicknesses of the first hole injection layer **14A**. When the first hole injection layer **14A** has a thickness of 250 Å, the relative luminous intensity of the second color of light Y of the organic electroluminescent device **100** is less than 0.2, and the organic electroluminescent device **100** has a blue emission. As shown in FIG. 4, the CIE coordination of the organic electroluminescent device **100** (with the first hole injection layer **14A** having a thickness of 250 Å) is close to the CIE coordination of a blue light. When the first hole injection layer **14A** has a thickness of 450 Å, the relative luminous intensity of the second color of light Y of the organic electroluminescent device **100** is increased to 0.6, as shown in FIG. 3. Meanwhile, the CIE coordination of the organic electroluminescent device **100** (with the first hole injection layer **14A** having a thickness of 450 Å) is close to the CIE coordination of a green light (as shown in FIG. 4), since the first emitting layer **16** is more close to the antinode of the antinode of the second color of light Y.

When the first hole injection layer **14A** has a thickness of 650 Å, the relative luminous intensity of the second color of light Y (with a wavelength of 520-630 nm) of the organic electroluminescent device **100** is increased to about 0.7, as shown in FIG. 3. Meanwhile, the CIE coordination of the organic electroluminescent device **100** (with the first hole injection layer **14A** having a thickness of 650 Å) is close to the CIE coordination (0.33, 0.33) of a white light (as shown in FIG. 4), since the first emitting layer **16** is substantially disposed at the antinode (separated by a vertical distance about 750 Å from a top surface **13** of the first electrode **12** and calculated via Fabry-Perot equation) of the second color of light Y.

Herein, when the thickness of the first hole injection layer **14A** is increased to over 650 Å, the blue color of light B of the organic electroluminescent device **100** is increased gradually. Since the first emitting layer **16** is positioned away from the antinode gradually, the organic electroluminescent device **100** produces a white emission again until the first emitting layer **16** is close to the next antinode of the standing wave (separated by a vertical distance of about 1870 Å from a top surface **13** of the first electrode **12** and calculated via the Fabry-Perot equation).

Accordingly, the thickness of the first carrier injection/transport layer **14** (including the first hole injection **14A** and first a hole transport layer **14B**) can be from 650 to 850 Å, or from 1750 to 1950 Å, thereby causing the organic electroluminescent device **100** with a blue emitting layer to produce a white emission.

As shown in FIG. 5, an organic electroluminescent device **200** according to another embodiment of the invention is provided. Particularly, the organic electroluminescent device **200** includes three identical emitting layers in order to produce a white emission. The organic electroluminescent

device **200** includes a substrate **110**, and a first electrode **112** (serving as an anode) formed on substrate **110**. Next, a first carrier injection/transport layer **114** (such as a hole injection/transport layer including a first hole injection layer **114A**, and a first a hole transport layer **114B**), a first emitting layer **116**, a first spacer layer **118**, a second emitting layer **120**, a second spacer layer **122**, a third emitting layer **124**, and a second carrier injection/transport layer **126** (such as an electron injection/transport layer including a first electron transport layer **126A** and a first hole injection layer **126B**) are sequentially formed on first electrode **112**. Finally, a second electrode **128** (serving as a cathode) is formed on second carrier injection/transport layer **126**. Particularly, the substrate, the first electrode, the carrier injection/transport layer, and the second electrode have the same definitions as described above. The first spacer layer **118**, for example, can include a second electron transport layer **118A**, a second electron injection layer **118B**, a connecting layer **118C**, and a second hole transport layer **118D**. The second spacer layer **122** can be a third hole transport layer, wherein the connecting layer **118C** can be an n-type or p-type connecting layer, such as Alq:Li/MoO₃.

It should be noted that, in this embodiment, the first emitting layer **116**, the second emitting layer **120**, and the third emitting layer **124** are formed by the same material, thereby reducing the process complexity of the organic electroluminescent device **200**.

In order to force the organic electroluminescent device **200** to produce a white emission by microcavity effect, suitable materials of the first emitting layer **116**, the second emitting layer **120**, and the third emitting layer **124** can be an organic electroluminescent material having a larger full width at half maximum. Namely, the organic electroluminescent material can have a full width at half maximum (FWHM) of more than 90 nm. In an embodiment, the organic electroluminescent material of the first emitting layer **116**, the second emitting layer **120**, and the third emitting layer **124** should have a broadband wavelength range of the visible light (including red, green, and blue color).

For example, the first emitting layer **116**, the second emitting layer **120**, and the third emitting layer **124** can be a green organic electroluminescent material having a full width at half maximum of more than 90 nm, such as Alq₃ (8-Hydroxyquinoline aluminum salt), and fac-tris(2-phenyl pyridine) iridium (Ir(ppy)₃). Further, the wave-length of the first emitting layer can be adjusted by doping a dopant. The dose of the dopant is not limited and can be optionally modified by a person of ordinary skill in the field. Moreover, the first emitting layer **116**, the second emitting layer **120**, and the third emitting layer **124** can be fluorescent or phosphorescent material. The method for forming the emitting layer can be thermal vacuum evaporation, physical vapor deposition, chemical vapor deposition (organic small molecule material), spin coating, ink-jet printing, or screen printing methods.

In this embodiment, since the first emitting layer **116**, the second emitting layer **120**, and the third emitting layer **124** is a green organic electroluminescent material having a full width at half maximum, the luminous intensity of the blue color of light and the red color of light of the organic electroluminescent device **200** should be enhanced in order to force the organic electroluminescent device **200** to produce a white emission.

For example, in this embodiment, the first electrode **112** serves as a reflective electrode, and the second electrode **128** serves as a semi-transparent electrode, thereby they form a microcavity. The blue color of light and the red color of light generate, respectively, a blue light standing wave and a red

light standing wave. The second emitting layer **120** and the third emitting layer **124** are disposed respectively at the antinode of the blue light standing wave and the red light standing wave, such that the blue light and the red light within the organic electroluminescent device **200** perform a constructive interference and the green light within the organic electroluminescent device **200** performs a destructive interference. Therefore, the luminous intensity of the blue light and the red light is enhanced, and the luminous intensity of the green light is reduced, resulting in the organic electroluminescent device **200** to produce a white emission.

In this embodiment, the locations of the antinode of the blue light standing wave and the red light standing wave are measured according to the Fabry-Perot equation. The second emitting layer **120** and third emitting layer **124** are disposed to be close to the antinodes of the blue light standing wave and the red light standing wave, respectively.

For example, the thickness of the first carrier injection/transport layer **114** (including the first hole injection layer **114A** and the first a hole transport layer **114B**) is controlled to be between about 1200-1600 Å, such that the first emitting layer **116** is separated by a vertical distance of about 1200-1600 Å (such as 1400 Å) from a top surface **113** of the first electrode **112**. Therefore, the first emitting layer **116** has a major luminous intensity at 550 nm (a green emission) and a minor luminous intensity at 480 nm (a blue emission), as shown in FIG. 6. The thickness of the first carrier injection/transport layer **114** (including the first hole injection layer **114A** and the first a hole transport layer **114B**), the first emitting layer **116**, and first spacer layer **118** is controlled to be between about 2300-2550 Å, such that the second emitting layer **120** is disposed at the antinode of the red light standing wave and separated by a vertical distance about 2300-2550 Å (such as 2480 Å) from a top surface **113** of the first electrode **112**. Therefore, since the luminous intensity of the red light is increased and the luminous intensity of the green light is reduced, the second emitting layer **120** has a major luminous intensity at 580-650 nm (a red emission), as shown in FIG. 7;

The thickness of the first carrier injection/transport layer **114** (including the first hole injection layer **114A** and the first a hole transport layer **114B**), the first emitting layer **116**, the first spacer layer **118**, the second emitting layer **120**, and the second spacer layer **122** are controlled to be between about 2650-2950 Å, such that the third emitting layer **124** is disposed at the antinode of the blue light standing wave and separated by a vertical distance about 2650-2950 Å (such as 2762 Å) from a top surface **113** of the first electrode **112**. Therefore, since the luminous intensity of the blue light is increased and the luminous intensity of the green light is reduced, the third emitting layer **124** has a major luminous intensity at 440-500 nm (a blue emission), as shown in FIG. 8.

Accordingly, since the first emitting layer **116**, the second emitting layer **120**, and the third emitting layer **124** emit a green emission, a red emission, and a blue emission respectively, the organic electroluminescent device **200** produces a white emission after mixing the green emission as shown in FIG. 9, the red emission, and the blue emission. Therefore, the invention provides a white color organic electroluminescent device by merely employing a single organic electroluminescent material.

As shown in FIG. 10, the image display system **300** including the organic electroluminescent device **100** (or **200**) according to an embodiment of the invention is shown. The image display system **300** can be an electric device such as notebook computer, mobile phone, digital camera, personal data assistant (PDA), desktop computer, television, car display, or portable DVD player. The image display system **300**

of the invention includes the organic electroluminescent device **100** (or **200**) and an input unit **150** coupled to the organic electroluminescent device **100** (or **200**). The input unit **150** is operative to provide input to the organic electroluminescent device **100** (or **200**), such that the organic electroluminescent device **100** (or **200**) displays images.

While the disclosure has been described by way of example and in terms of the preferred embodiments, it is to be understood that the disclosure is not limited to the disclosed embodiments. To the contrary, it is intended to cover various modifications and similar arrangements (as would be apparent to those skilled in the art). Therefore, the scope of the appended claims should be accorded the broadest interpretation so as to encompass all such modifications and similar arrangements.

What is claimed is:

1. An image display system, comprising:

an organic electroluminescent device, comprising:

a substrate;

a first electrode formed on the substrate;

a first emitting layer formed on the first electrode, wherein the first emitting layer emits a first color of light, and a second color of light;

a first hole injection layer and a first a hole transport layer disposed between the first electrode and the first emitting layer, wherein the thickness of the first hole injection layer and the first a hole transport layer is of between 650-850 Å, or 1750-1950 Å;

a second electrode formed on the first emitting layer, wherein the second color of light emitted by the first emitting layer generates a first standing wave within the organic electroluminescent device, and the first emitting layer is disposed at an antinode of the first standing wave, such that the intensity of the second color of light is enhanced, and the second color of light is mixed with the first color of light to produce a white emission.

2. The image display system as claimed in claim 1, wherein the first emitting layer has a full width at half maximum of more than 90 nm.

3. The image display system as claimed in claim 1, wherein the first color of light is blue, and the second color of light is yellow.

4. The image display system as claimed in claim 1, further comprising a first electron transport layer, and a first electron injection layer disposed between the first emitting layer and the second electrode.

5. The image display system as claimed in claim 1, wherein the first electrode is a reflective electrode.

6. The image display system as claimed in claim 1, wherein the second electrode is a semi-transparent electrode.

7. The image display system as claimed in claim 6, wherein the semi-transparent electrode has a light absorbance of less than 25%.

8. The image display system as claimed in claim 1, further comprising a first spacer layer, a second emitting layer, a second spacer layer, a third emitting layer, a first electron transport layer, and a first electron injection layer disposed between the first emitting layer and the second electrode, wherein the first spacer layer, the second emitting layer, the second spacer layer, the third emitting layer, the first electron transport layer, and the first electron injection layer are sequentially formed on the first emitting layer.

9. The image display system as claimed in claim 8, wherein the first emitting layer, the second emitting layer, and the third emitting layer are formed by the same material, and each emitting layer emits the first color of light, the second color of light, and a third color of light simultaneously.

9

10. The image display system as claimed in claim 9, wherein the third color of light emitted by each emitting layer generates a second standing wave within the organic electroluminescent device, and the second emitting layer, or the third emitting layer is disposed at an antinode of the second standing wave. 5

11. The image display system as claimed in claim 8, wherein the full widths at half maximum of the first emitting layer, the second emitting layer, and the third emitting layer are larger than 90 nm. 10

12. The image display system as claimed in claim 9, wherein the first color of light is green, the second color of light is blue, and the third color of light is red.

13. The image display system as claimed in claim 8, wherein the first spacer layer comprises a second electron transport layer, a second electron injection layer, a connecting layer, and a second hole transport layer. 15

14. The image display system as claimed in claim 8, wherein the second spacer layer comprises a third hole transport layer. 20

15. An image display system, comprising:
an organic electroluminescent device, comprising:
a substrate;
a first electrode formed on the substrate;

a first hole injection layer, a first a hole transport layer, a first emitting layer, a first spacer layer, a second emitting layer, a second spacer layer, a third emitting layer, a first electron transport layer, and a first electron injection layer sequentially formed on the first electrode, wherein the first emitting layer, the second emitting layer, and the third emitting layer are formed by the same material, and 25 30

10

each emitting layer emits a first color, a second color, and a third color of light; and

a second electrode formed on the first electron injection layer, wherein the second color of light emitted by each emitting layer generates a first standing wave within the organic electroluminescent device, and the third color of light emitted by each emitting layer generates a second standing wave within the organic electroluminescent device, such that the intensities of the second color of light and the third color of light are enhanced, and the second color of light and the third color of light are mixed with the first color of light to produce a white emission.

16. The image display system as claimed in claim 15, wherein the full widths at half maximum the first emitting layer, the second emitting layer, and the third emitting layer are larger than 90 nm.

17. The image display system as claimed in claim 15, wherein the first color is green, the second color is blue, and the third color of light is red.

18. The image display system as claimed in claim 15, wherein the thickness of the first hole injection layer, and the first a hole transport layer is of between 1200-1600 Å, the thickness of the first hole injection layer, the first a hole transport layer, the first emitting layer, and the first spacer layer is of between 2300-2550 Å, and the thickness of the first hole injection layer, the first a hole transport layer, the first emitting layer, the first spacer layer, the second emitting layer, and the second spacer layer is of between 2650-2950 Å.

* * * * *

专利名称(译)	图像显示系统		
公开(公告)号	US8872170	公开(公告)日	2014-10-28
申请号	US13/804712	申请日	2013-03-14
[标]申请(专利权)人(译)	群创光电股份有限公司		
申请(专利权)人(译)	群创光电		
当前申请(专利权)人(译)	群创光电		
[标]发明人	SU HSIN YUAN LI CHUN KAI HSU HSIANG LUN		
发明人	SU, HSIN-YUAN LI, CHUN-KAI HSU, HSIANG-LUN		
IPC分类号	H01L51/50		
CPC分类号	H01L51/5265 H01L51/5044 H01L51/5036 H01L51/5012 H01L2251/558		
审查员(译)	波特, ROY		
优先权	101113902 2012-04-19 TW		
其他公开文献	US20130277648A1		
外部链接	Espacenet USPTO		

摘要(译)

提供了一种采用有机电致发光器件的图像显示系统。所述有机电致发光器件包括基板；在基板上形成的第一电极；第一发射层，形成在第一电极上，其中第一发射层发射第一颜色的光和第二颜色的光；第二电极，形成在第一发射层上，其中由第一发射层发射的第二色光在有机电致发光器件内产生第一驻波，并且第一发射层设置在第一驻波的波腹处，例如第二种光的强度得到增强，并且第二种光与第一种光混合以产生白色发射。

100

