





US 20140163233A1

(19) **United States**(12) **Patent Application Publication**
Balaganesan et al.(10) **Pub. No.: US 2014/0163233 A1**(43) **Pub. Date: Jun. 12, 2014**(54) **ELECTRON TRANSPORTING COMPOUNDS
AND ORGANIC ELECTROLUMINESCENT
DEVICES USING THE SAME**(57) **ABSTRACT**(71) Applicant: **E-RAY OPTOELECTRONICS
TECHONOLGY CO., LTD.,**
Chung-Li 320 (TW)(72) Inventors: **Banumathy Balaganesan**, Chung-Li
320 (TW); **Heh-Lung Huang**, Chung-Li
320 (TW); **Po-Wei Hsu**, Chung-Li 320
(TW); **Kun-Feng Chiang**, Chung-Li 320
(TW)(73) Assignee: **E-RAY OPTOELECTRONICS
TECHONOLGY CO., LTD.,**
Chung-Li 320 (TW)(21) Appl. No.: **14/098,719**(22) Filed: **Dec. 6, 2013****Related U.S. Application Data**(60) Provisional application No. 61/734,552, filed on Dec.
7, 2012.**Publication Classification**(51) **Int. Cl.**
H01L 51/00 (2006.01)(52) **U.S. Cl.**
CPC **H01L 51/0055** (2013.01); **H01L 51/0074**
(2013.01); **H01L 51/0058** (2013.01); **H01L**
51/0067 (2013.01)USPC **546/256**; 549/43; 549/42

The present invention discloses a novel compound of Formula 1, and an organic electroluminescent device using the same. In Formula 1, X and Y independently represents an aromatic or a hetero aromatic hydrocarbon having a carbon number of from 5 to 10. Ar₁ to Ar₇ each independently represents an unsubstituted or substituted aromatic hydrocarbon having a carbon number of from 4 to C12, or an unsubstituted or substituted condensed polycyclic aromatic hydrocarbon having a carbon number of from 4 to 12; Ar₁ to Ar₇ can form an annulated or fused aromatic ring system with the adjacent aromatic hydrocarbons. When the compound of Formula I is used in the device, high luminous efficiency, longer lifetime and low driving voltage can be achieved.

Formula I






FIG. 1




FIG. 2






FIG. 3








FIG. 6




FIG. 7




FIG. 8

ELECTRON TRANSPORTING COMPOUNDS AND ORGANIC ELECTROLUMINESCENT DEVICES USING THE SAME

BACKGROUND OF THE INVENTION

[0001] 1. Field of the Invention

[0002] The present invention relates to compounds comprising benzothiophene moieties linked to a fluoranthene molecular skeleton and electroluminescent devices using the same, and more particularly, to a compound comprising a substituted or unsubstituted dibenzothiophene linked directly to substituted or unsubstituted benzofluoranthene and an electroluminescent device using the same.

[0003] 2. Description of Related Art

[0004] There has been an increasing interest in developing novel organic materials that cater to organic light emitting device (OLED) applications. Such devices are commercially attractive because they offer the cost-advantageous fabrication of high density pixelated displays exhibiting brilliant luminance with long life times, high efficiency, low driving voltages and wide color range.

[0005] A typical OLED comprises at least one organic emissive layer sandwiched between an anode and a cathode. When a current is applied, the anode injects holes and the cathode injects electrons into the organic layer(s). The injected holes and electrons each migrate toward the oppositely charged electrode. When an electron and hole localize on the same molecule, an "exciton", which is a localized electron-hole pair having an excited energy state, is formed. Light is emitted when the exciton relaxes through a photo-emissive mechanism. To improve the charge transport capabilities and also the luminous efficiency of such devices, additional layers around the emissive layer, such as an electron transport layer and/or a hole transport layer, or an electron blocking and/or hole blocking layer(s) have been incorporated. Doping the host material with another material (i.e., guest) has been well demonstrated in literature to enhance the device performance and to tune the chromaticity. Several OLED materials and device configurations are described in U.S. Pat. Nos. 4,769,292, 5,844,363, and 5,707,745, which are incorporated herein by reference in their entirety.

[0006] The reason for manufacturing an organic EL display with a multi-layered thin film structure includes stabilization of the interfaces between the electrodes and the organic layers. In addition, in organic materials, the mobility of electrons and holes significantly differ, and thus, if appropriate hole transportation and electron transportation layers are used, holes and electrons can be efficiently transferred to the luminescent layer. Also, if the density of the holes and electrons are balanced in the emitting layer, luminous efficiency can be increased. The proper combination of organic layers described above can enhance the device efficiency and lifetime. However, it has been very difficult to find an organic material that satisfies all the requirements for use in practical display applications.

[0007] Tris(8-hydroxyquinoline)aluminum (Alq₃) is one of the widely used electron transporting material; however, it has an intense green emission and devices using the same exhibits higher driving voltages. Therefore, it is crucial to find an electron transporting molecule that has excellent properties compared to the conventional material in all practical aspects, such as high efficiency, reduced driving voltage and operational stability.

[0008] Organic small molecules having imidazole groups, oxazole groups and thiazole groups have been frequently reported as materials for electron injection and transportation layers, as described in the literature Chem. Mater. 2004, No. 16, p. 4556.

[0009] U.S. Pat. No. 5,645,948 and U.S. Pat. No. 5,766,779 discloses a representative material, 1,3,5-tris(1-phenyl-1H-benzimidazol-2-yl)benzene (TPBI), for electron transportation having blue emission. TPBI has three N-phenyl benzimidazole groups, in 1,3,5-substitution sites of benzene and functions both as an electron transporting and an emitting material. However, TPBI has lower operational stability.

[0010] U.S. Pat. No. 6,878,469 discloses a compound, wherein the 2-phenyl benzimidazolyl group is linked to the C-2, C-6 positions of anthracene framework. US20080125593, KR20100007143 discloses electron transporting materials comprising imidazopyridyl or benzimidazolyl groups in its molecular skeleton, exhibiting low driving voltage and high efficiency. However, these materials also lack operational stability.

[0011] Fluoranthene derivatives are well known in the art as being useful as light emitting compounds, have been disclosed in JP2002069044, JP2005320286, US20070243411, WO2008059713, WO2011052186. U.S. Pat. No. 7,879,465 and U.S. Pat. No. 8,076,009 disclose the use of annulated fluoranthene in the electron injection and electron transport layers. However, these devices do not have all desired EL characteristics in terms of high luminance, operational stability and reduced driving voltage.


[0012] Dibenzothiophenes (DBT) are classified as chalcogenophenes and are cheap and commercial available, which has been reported to be one of the most abundant compounds in gas oil. DBT has a high ionization potential (IP) and a large band gap, which does not show have intense absorptions in the visible region. Its co-planarity is favorable for intermolecular interaction. KR20110085784 discloses benzodithiophenes used in the light emitting devices. US 20120187381 discloses the use of azadibenzo moieties linked to anthracene as electron transporting materials, and they still need to improve in terms of stability and driving voltage.

[0013] Accordingly, there remains a need to develop a compound for use in an organic light emitting device that can overcome the above drawbacks.

SUMMARY OF THE INVENTION

[0014] An object of the present invention is to provide a compound for use in an electron transport layer or a light emitting layer of an organic light emitting device to provide the device with high luminous efficiency, longer lifetime and low driving voltage, and an electroluminescent device using the same.

[0015] The present invention provides a benzothiophene linked to a fluoranthene molecular skeleton having the following Formula (I):



Formula I


[0016] wherein X and Y independently represents an aromatic or a hetero aromatic hydrocarbon having a carbon number of from 5 to 10, and

[0017] Ar₁ to Ar₇ each independently represents an unsubstituted or substituted aromatic hydrocarbon having a carbon number of from 4 to 12, or an unsubstituted or substituted condensed polycyclic aromatic hydrocarbon having a carbon number of from 4 to 12; Ar₁ to Ar₇ can form an annulated or fused aromatic ring system with the adjacent aromatic hydrocarbons.


[0018] In one embodiment, the compound has a formula selected from the group consisting of Formula (II) to Formula (XIII):

-continued


Formula VI




Formula II




Formula III




Formula IV




Formula V




Formula VII



Formula VIII




Formula IX




-continued


Formula X




Formula XI



Formula XII



Formula XIII



wherein X and Y independently represents an aromatic or a hetero aromatic hydrocarbon having a carbon number of from

5 to 10, and R_1 to R_7 are independently selected from the group consisting of hydrogen, deuterium, alkyl, alkoxy, amino, silyl, cyano, aryl, and heteroaryl.

[0019] In one embodiment, X and Y are selected from the group consisting of phenyl, 2-tolyl, 3-tolyl, 4-tolyl, 4-pyridyl, 1-naphthyl, and 2-naphthyl.

[0020] The present invention further provides a process for producing a compound represented by a formula selected from the group consisting of Formulae (II) to (XIII).

[0021] In one embodiment, the compound represented by a formula selected from the group consisting of Formulae (II) to (XIII) is capable of being made into an amorphous thin film for organic electroluminescent devices, by means of a vacuum deposition method or a spin coating method.

[0022] The present invention further provides an organic electroluminescent device that utilizes a compound represented by a formula selected from the group consisting of Formulae (II) to (XIII).

[0023] In one embodiment, the compound is used in an electron transport layer or an electron injection layer as a single material or in combination with an n-type dopant material.

[0024] In another embodiment, the compound is used in one selected from the group consisting of a light emitting layer, a hole block layer and an electron block layer.

[0025] In a further embodiment, the compound is used in a light emitting layer used in combination with a fluorescent or a phosphorescent emitter.

[0026] In one embodiment, the organic electroluminescent device is one of a fluorescent organic electroluminescent device and a phosphorescent organic electroluminescent device.

[0027] Organic electroluminescent devices of the present invention exhibit a longer lifetime and better thermal stability with high efficiency and low driving voltage. In addition, by using the organic compounds of the present invention, it becomes possible to provide an organic electroluminescent device which can emit white light.

BRIEF DESCRIPTION OF THE DRAWINGS

[0028] The objects, spirits, and advantages of the preferred embodiments of the present invention will be readily understood by the accompanying drawings and the detailed descriptions, wherein:

[0029] FIG. 1 is a cross-sectional view illustrating an organic light emitting according to an embodiment of the present invention;

[0030] FIG. 2 is a cross-sectional view illustrating an organic light emitting device according to another embodiment of the present invention;

[0031] FIG. 3 is a cross-sectional view illustrating an organic light emitting device according to yet another embodiment of the present invention;

[0032] FIG. 4 shows the ^1H -NMR spectrum of Compound A1;

[0033] FIG. 5 shows the ^1H -NMR spectrum of Compound A2;

[0034] FIG. 6 shows the ^1H -NMR spectrum of Compound A5;

[0035] FIG. 7 shows the electroluminescent spectrum of an organic electroluminescent device according to the present invention; and

[0036] FIG. 8 shows the plot of luminance against current density of the organic electroluminescent device according to the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0037] The detailed description of the present invention is illustrated by the following specific examples. Persons skilled in the art can conceive the other advantages and effects of the present invention based on the disclosure contained in the specification of the present invention.


[0038] A compound for an organic electroluminescent device according to this invention is represented general Formula (I). Preferably, the compound of Formula (I) is one of compounds represented by Formula (II) to (XIII).

[0039] In the Formula (II) to (XIII), X and Y represents an aromatic or a hetero aromatic hydrocarbon having carbons from C5 to C10; X and Y may be the same or different; X and Y may be selected from a group consisting of phenyl, tolyl, pyridyl, naphthyl. R1 to R7 are independently selected from the group consisting of hydrogen, deuterium, alkyl, alkoxy, amino, silyl, cyano, aryl, heteroaryl.


[0040] Preferable examples of the compounds represented by the aforementioned Formula (II) to (XIII) are shown below (A1-A24; B1-B24; C1-C24; D1-D24; E1-E24; F1-F24; G1-G24; H1-H24) but not limited to.

-continued

A3




A4





A5


A1




A2



A6




-continued




A7


-continued




A10




A8



A11




A9



A12


-continued

A13




-continued


A16




A14




A17




A18



A15




A19




-continued


A20




A21



A22




A23




-continued


A24



B1



B2





-continued


-continued

B6


B3




B4




B7



B5




B8




-continued

B9




-continued


B12




B10



B13




B11




-continued

B14




-continued


B17




B15




B18



B16




B19




-continued

-continued


B20




B23




B21




B24



B22




C1




-continued


-continued




C2




C5




C3



C6




C4




C7


-continued




-continued




C9



C12








C10



-continued



-continued




-continued

-continued


C21




C19




C22



C20




C23




-continued

-continued

C24





D3





D4

D1




D5

D2




-continued




D6


-continued




D9




D7



D10








D8



D11


-continued

-continued




-continued


D17




D18



D19




D20




-continued


D21



D22




D23




-continued

D24




-continued


E4




E5




E1




E6




E2




E7



E3




-continued




E8


-continued




E11



E9



E10




E12


-continued

-continued


E13




E15




E14



E16



E17





-continued

-continued



E18

E22





E19

E23





E20

E24




E21

F1




-continued


F2




F3



F4




F5




-continued


F6



F7




F8




-continued

-continued


F9




F12




F10




F13




F11




-continued




-continued




F18




F15




F19



F16




F20




-continued


F21




F22



F23




F24




-continued


G1




G2



G3









G4







-continued

-continued




-continued






-continued




-continued



-continued




-continued




G22


-continued




H2




G23




H3



G24




H1



H4


-continued

H5




-continued


H8




H6




H9



H7



H10





-continued

-continued



H14

H11





H15

H12




H16


H13




-continued




H17



H18




H19




H20


-continued



H21




H22




H23

-continued

H24



-continued




A2

[0041] Various arylated fluorene derivatives may be prepared by following similar literature procedures given in Journal of the American Chemical Society 1949, vol. 71 (6), p. 1917; Journal of Nanoscience and Nanotechnology 2008, 8(9), p. 4787.

[0042] Various dibenzothiophene derivatives may be prepared by following the procedures given in the literature cited elsewhere.

[0043] One of the typical synthetic schemes to synthesize one of the exemplary Compounds A2 is given below:



[0044] The compound represented by formula (I) as previously described may be included in an organic layer of an organic electroluminescent device (EL), according to one embodiment of the present invention. Therefore the organic electroluminescent device of the present invention has at least one organic layer disposed between an anode and a cathode piled one upon another on a substrate, wherein the organic layer comprises a compound represented by the formula (I) as described earlier. As described herein, the organic layer may be an emitting layer, a hole block layer, an electron transport layer, an electron injection layer or a hole transport layer. The organic layer including the compound represented by the formula (I) may preferably be included in the electron transport/injection layer, and in combination with electrically injecting dopants (n/p type).

[0045] Electrically conducting (i.e., n/p type) dopants to be used in the electron transport layer are preferably organic alkali/alkaline metal complexes, oxides, halides, carbonates, phosphates of alkali/alkaline group metals containing at least one metal selected from lithium and cesium. Such organic metal complexes are known in the aforementioned patent documents and elsewhere and a suitable complex can be selected from them and used in this invention.

[0046] The content of the aforementioned electrically injecting dopant in the electron transport/electron injection layer is preferably in the range of 25 wt % to 75 wt %.

[0047] Further, the compound represented by any of formula (I) may be included in the layer between emitting layer and electron transport layer. The emitting layer may include fluorescent and phosphorescent dopants and their corresponding fluorescent and phosphorescent host emitters, respectively.

[0048] Furthermore, the compounds represented by any of formulae (I) to (XIII) may be used in an electron injecting/transporting layer or hole blocking layer and/or electron blocking layer.

[0049] The structure of the organic electroluminescent device of this invention will be explained with reference to the drawing, but not limited thereto.

[0050] FIG. 1 is a schematic view showing an organic light emitting device according to an embodiment of the present

invention. An organic light emitting device 100 includes a substrate 110, an anode 120, a hole injection layer 130, a hole transport layer 140, an emissive layer 150, an electron transport layer 160, an electron injection layer 170, and a cathode 180. The organic light emitting device 100 may be fabricated by depositing the layers described in order. FIG. 2 a schematic view showing an organic light emitting device according to another embodiment of the present invention, which is similar to that of FIG. 1. However, in the organic light emitting device of FIG. 2, an exciton 245 is interposed between a hole transport layer 240 and a light emitting layer 250. FIG. 3, which is schematic view showing an organic light emitting device according to yet another embodiment of the present invention, is also similar to FIG. 1, except for an exciton block layer 355 interposed between a light emitting layer 350 and an electron transport layer 360.

[0051] Materials used in hole injection layer, hole transport layer, electron blocking layer, hole blocking layer, light emitting layer, electron injecting layer may those conventionally used. For example, an electron-transporting material for forming the electron-transporting layer differs from that for forming the light emitting layer, and has hole-transporting properties, so as to facilitate hole mobility in the electron-transporting layer, and to prevent accumulation due to the difference in ionization potential between the light emitting layer and the electron-transporting layer.

[0052] In addition, U.S. Pat. No. 5,844,363 discloses a flexible and transparent substrate-anode combination. An example of a p-doped hole transport layer is m-MTDATA doped with F₄-TCNQ at a molar ratio of 50:1, as disclosed in US Patent Application Publication No. 20030230980. An example of an n-doped electron transport layer is BPhen doped with Li at a molar ratio of 1:1, as disclosed in US Patent Application Publication No. 20030230980. U.S. Pat. Nos. 5,703,436 and 5,707,745 disclose examples of cathodes including compound cathodes having a thin layer of metal such as Mg:Ag with an overlying transparent, electrically-conductive, sputter-deposited ITO layer. The theory and use of blocking layers is described in U.S. Pat. No. 6,097,147 and US Patent Application Publication No. 20030230980, which are incorporated by reference in their entireties. Examples of injection layers are provided in US Patent Application Publication No. 20040174116. A description of protective layers may be found in US Patent Application Publication No. 20040174116.

[0053] Structures and materials not specifically described may also be used, such as OLEDs comprised of polymeric materials (PLED) such as disclosed in U.S. Pat. No. 5,247,190. Further, OLEDs having a single organic layer may be used. OLEDs may be stacked as described in U.S. Pat. No. 5,707,745.

[0054] Unless otherwise specified, any of the layers of the various embodiments may be deposited by any suitable method. For the organic layers, preferred methods include thermal evaporation, ink-jet, such as described in U.S. Pat. Nos. 6,013,982 and 6,087,196, organic vapor phase deposition (OVPD), such as described in U.S. Pat. No. 6,337,102, and deposition by organic vapor jet printing (OVJP), such as described in U.S. patent application Ser. No. 10/233,470. Other suitable deposition methods include spin coating and other solution-based processes. Solution-based processes are preferably carried out in nitrogen or an inert atmosphere. For the other layers, preferred methods include thermal evaporation. Preferred patterning methods include deposition

through a mask, cold welding such as described in U.S. Pat. Nos. 6,294,398 and 6,468,819, and patterning associated with deposition methods such as ink-jet and OVJD. Certainly, other methods may be used. The materials to be deposited may be modified to make them compatible with a particular deposition method.

[0055] An organic electroluminescent device of this invention is applicable to a single device, a device with its structure arranged in array, or a device having the anode and the cathode arranged in an X-Y matrix. The present invention significantly improves luminous efficiency and driving stability of an organic electroluminescent device over the conventional devices, when used in combination of phosphorescent dopants in the light emitting layer, and furthermore the organic electroluminescent device of the present invention can perform better when applied to full-color or multicolor panels.

EXAMPLES

[0056] This invention will be described in more detail below with reference to the examples; however, it will not be limited to these examples.

Synthesis Example 1

Synthesis of Compound A1

[0057] 3-bromo-7,12-diphenylbenzo[k]fluoranthene (6 g) and 4-dibenzothiophenyl boronic acid (3.2 g) were stirred together in 30 ml of toluene. 0.06 g of tetrakis(triphenylphosphine)palladium, 6.0 g of potassium carbonate and 15 ml of aqueous ethanol were added thereto, and refluxed under nitrogen for 6 h. The reaction was quenched with water, and the toluene layer was removed and passed through a celite column.

[0058] The organic layers were combined and then evaporated in a rotary evaporator under vacuum to yield compound A1 as a light yellow solid.

[0059] Compound A1 showed a melting point of 307° C. and a glass transition temperature of 176° C.

[0060] The major UV absorption peaks of Compound A1 were 313 nm, 394 nm, and 417 nm.

[0061] The photoluminescence spectrum of Compound A1 showed an emission at 435 nm.

[0062] ¹H-NMR spectrum of Compound A1 is shown in FIG. 4

[0063] ¹H NMR (CDCl₃, δ): 8.21 (dd, 1H) -8.20 (dd, 1H); 7.72-7.57 (m, 14H); 7.56-7.54 (m, 3H); 7.48 (d, 1H); 7.45-7.41 (m, 3H); 7.27-7.23 (m, 1H); 6.74 (d, 1H); 6.65 (d, 1H).

Synthesis Example 2

Synthesis of Compound A2

[0064] 2-bromo-dibenzo[b,d]thiophene (10 g), phenylboronic acid (5.1 g) tetrakis(triphenylphosphine)palladium (2.2 g) and potassium carbonate (18.38 g) were refluxed in a mixture of toluene (110 mL), ethanol (20 mL) and water (90 mL) overnight. The reaction was quenched with water and the toluene layer was removed and passed through a celite column and the toluene layer was evaporated in a rotary evaporator to yield 5.2 g 2-phenyl-dibenzo[b,d]thiophene. 2-phenyldibenzo[b,d]thiophene (5.2 g) was dissolved in anhydrous tetrahydrofuran (50 mL) under nitrogen atmosphere, and the solution was then cooled to -78° C. 20.0 mL of n-butyl

lithium (1.6 M solution) was added dropwise into the reaction mixture, and continuously stirred to equilibrate to room temperature. The reaction mixture was then cool to -60°C ., and trimethylborate (5.67 mL) was added and the reaction was allowed to stir overnight. The reaction was then quenched with 20% aqueous hydrochloric acid, and extracted the organic layer with ethyl acetate; ethyl acetate layer was then washed thoroughly with water and dried over anhydrous sodium sulfate, and was evaporated to dryness to yield 4.2 g of 8-phenyldibenzo[b,d]thiophene-4-boronic acid.

[0065] 3-bromo-7,12-diphenylbenzo[k]fluoranthene, (4.63 g), prepared by procedures known in the art, and 8-phenyldibenzo[b,d]thiophene-4-boronic acid (3.5 g) were stirred together in 50 mL of toluene. 0.553 g of tetrakis(triphenylphosphine)palladium, 4.62 g of potassium carbonate, and 50 mL of aqueous ethanol were added thereto, and refluxed under nitrogen. The reaction was monitored by thin layer chromatography for 6 h. The reaction was quenched with water and the toluene layer was further extracted with water and was passed through a silica gel column chromatography. The organic layers were combined and then evaporated in a rotary evaporator under vacuum to yield 3.5 g of Compound A2 as a yellow-white solid.

[0066] Compound A2 did not show any observable melting point. Compound A2 showed a uv-vis absorption peaks at 395, 417 nm, and its photoluminescence in tetrahydrofuran showed an emission peak at 440 nm.

[0067] ^1H -NMR of compound A2 is shown in FIG. 5.

[0068] ^1H NMR (CDCl_3 , δ): 8.45-8.39 (m, 1H); 8.25 (dd, 1H); 7.83-7.56 (m, 17H); 7.51-7.36 (m, 8H); 7.27-7.24 (m, 1H); 6.73 (d, 1H); 6.63 (d, 1H).

Synthesis Example 3

Synthesis of compound A5

[0069] 2,8-dibromo-dibenzo[b,d]thiophene (14 g), phenylboronic acid (11.0 g) tetrakis(triphenylphosphine)palladium (3.8 g) and potassium carbonate (20 g) were refluxed together in a mixture of toluene (110 mL), ethanol (20 mL) and water (90 mL) overnight. The reaction was quenched with water and the toluene layer was removed and passed through a celite column and the toluene layer was evaporated in a rotary evaporator to yield 6.0 g 2,8-diphenyl-dibenzo[b,d]thiophene.

[0070] 2,8-diphenyldibenzo[b,d]thiophene (6.0) was dissolved in anhydrous tetrahydrofuran (80 mL) under nitrogen atmosphere and the solution was then cooled to -78°C . 20.0 mL of n-butyl lithium (1.6 M solution) was added dropwise into the reaction mixture and continuously stirred to equilibrate to room temperature. The reaction mixture was then cool to -60°C . and trimethylborate (5.67 mL) was added and the reaction was allowed to stir overnight. The reaction was then quenched with 20% aqueous hydrochloric acid, and extracted the organic layer with ethyl acetate; ethyl acetate layer was then washed thoroughly with water and dried over anhydrous sodium sulfate, and was evaporated to dryness to yield 4.5 g of 2,8-diphenyldibenzo[b,d]thiophene-4-boronic acid.

[0071] 3-bromo-7,12-diphenylbenzo[k]fluoranthene, (3.8 g), prepared by procedures known in the art, and 2,8-diphenyldibenzo[b,d]thiophene-4-boronic acid (3.5 g) were stirred together in 50 mL of toluene. 0.5 g of tetrakis(triphenylphosphine)palladium, 3.8 g of potassium carbonate, and 50 mL of aqueous ethanol were added thereto, and refluxed under nitro-

gen. The reaction was monitored by thin layer chromatography for 6 h. The reaction was quenched with water and the toluene layer was further extracted with water and was passed through a silica gel column chromatography. The organic layers were combined and then evaporated in a rotary evaporator under vacuum to yield 3.0 g of Compound A5 as a yellow solid.

[0072] Compound A5 showed a glass transition temperature of 194°C . Compound A5 showed a uv-vis absorption peaks at 397, 419 nm, and its photoluminescence in tetrahydrofuran showed an emission peak at 446 nm.

[0073] ^1H -NMR of compound A5 is shown in FIG. 6.

[0074] ^1H NMR (CDCl_3 , δ): 8.46-8.42 (m, 2H); 7.807.56 (m, 20H); 7.51-7.36 (m, 9H); 7.29-7.24 (m, 1H); 6.74 (d, 1H); 6.63 (d, 1H).

Device Example 1

Fabrication of Organic Electroluminescent Device

[0075] Prior to use, the substrate was degreased with solvents and cleaned in a UV ozone before it was loaded into the evaporation system. The substrate was then transferred into a vacuum deposition chamber for deposition of all other layers on top of the substrate. By evaporation from a heated boat under a vacuum of approximately 10^{-6} Torr, the following layers were deposited in the following sequence, as shown in FIG. 2:

[0076] a) a hole injecting layer, 30 nm thick, HAT-CN,

[0077] b) a hole transporting layer, 110 nm thick, N,N'-di-1-naphthyl-N,N'-diphenyl-4,4'-diaminobiphenyl (NPB);


[0078] c) a light emitting layer, 30 nm thick, comprising BH doped with 3% BD by volume; (BH and BD from E-ray optoelectronics Tech Co. Ltd, Taiwan)


[0079] e) an electron transport layer, 15 nm thick, including compound A1;

[0080] f) an electron injection layer, 1 nm thick, LiF; and

[0081] g) a cathode: approximately 150 nm thick, including Compound A1.

Device structure may be denoted as: ITO/HAT-CN (30 nm)/NPB (110 nm)/BH-3% BD (30 nm)/Compound A1 (15 nm)/LiF (1 nm)/Al (150 nm).





[0082] After the deposition of these layers, the device was transferred from the deposition chamber into a dry box for encapsulation, and were subsequently encapsulated using an UV-curable epoxy and a glass lid containing a moisture getter. The organic EL has an emission area of 3 mm². The organic EL device thus obtained was connected to an outside power

source, and upon application of direct current voltage, emission of light with the characteristics shown in Table 2 was confirmed.

[0083] The EL characteristics of all the fabricated devices were evaluated using a constant current source (KEITHLEY 2400 Source Meter, made by Keithley Instruments, Inc., Cleveland, Ohio) and a photometer (PHOTO RESEARCH SpectraScan PR 650, made by Photo Research, Inc., Chatsworth, Calif.) at room temperature.

[0084] Operational lifetime (or stability) of the devices were tested at the room temperature and at various initial luminance depending on the color of the emitting layer, by driving a constant current through the devices. The color was reported using Commission Internationale de l'Eclairage (CIE) coordinates.

Device Example 2

Fabrication of Organic EL Device

[0085] Organic fluorescent EL device was fabricated similar to the layer structure as example 1, except that a n-dopant of Lithium quinoate, Liq, is used with the compound A1 in the ratio of 1:1, in the electron transport layer. The device structure may be denoted as: ITO/HAT-CN (30 nm)/NPB (110 nm)/BH-3% BD (30 nm)/Liq doped Compound A1 (15 nm)/LiF (1 nm)/Al (150 nm).

Comparative Example 1

Fabrication of Organic EL Device

[0086] Organic EL device was fabricated similar to the layer structure as example 1, except that Alq₃ was used in place of Compound A1 in the electron transport layer. The device structure may be denoted as: ITO/HAT-CN (30 nm)/NPB (110 nm)/BH-3% BD (30 nm)/Alq₃ (15 nm)/LiF (1 nm)/Al (150 nm).

[0087] The peak wavelength of the emitted light, maximum luminance efficiency, driving voltage, and power efficiency of the organic EL devices fabricated in the examples are shown in Table 2. EL spectra of the device examples 1-2 are shown in FIG. 7, and a plot of voltage versus luminance is shown in FIG. 8.

TABLE 2

	Driving voltage (V)	Peak Wavelength (nm)	Max. luminance efficiency (cd/A) @ 10 mA/cm ²	T ₅₀ @L ₀ = 1000 nits
Device Example 1	7.31	468	8.77	990
Device Example 2	3.37	468	10.31	11339
Comparative Example 1	5.53	468	9.90	5637


INDUSTRIAL APPLICABILITY

[0088] As described above in detail, the organic EL device in which the material for the EL device of the present invention is used is extremely practical because it has high luminous efficiency, high thermal stability, sufficiently low driving voltage and long lifetime. Therefore, the organic EL device of this invention is applicable to flat panel displays,

mobile phone displays, light sources utilizing the characteristics of planar light emitters, sign-boards and has a high technical value.

[0089] Although the invention has been disclosed and illustrated with reference to particular embodiments, the principles involved are susceptible for use in numerous other embodiments that will be apparent to persons skilled in the art. This invention is, therefore, to be limited only as indicated by the scope of the appended claims.

1. A compound of formula (I):




Formula I

wherein X and Y independently represents an aromatic or a hetero aromatic hydrocarbon having a carbon number of from 5 to 10, and


Ar₁ to Ar₇ each independently represents an unsubstituted or substituted aromatic hydrocarbon having a carbon number of from 4 to 12, or an unsubstituted or substituted condensed polycyclic aromatic hydrocarbon having a carbon number of from 4 to 12, or Ar₁ to Ar₇ optionally form an annulated or fused aromatic ring system with the adjacent aromatic hydrocarbons.

2. The compound of claim 1, which is a compound of a formula selected from the group consisting of Formula (II) to Formula (XIII):




Formula II


Formula III



-continued




Formula IV




Formula V


Formula VI



Formula VII




Formula VIII




-continued


Formula IX




Formula X



Formula XI




Formula XII



-continued

Formula XIII



wherein X and Y independently represents an aromatic or a hetero aromatic hydrocarbon having a carbon number of from 5 to 10, and R₁ to R₇ are independently selected from the group consisting of hydrogen, deuterium, alkyl, alkoxy, amino, silyl, cyano, aryl, and heteroaryl.

3. The compound of claim 1, wherein X and Y are selected from the group consisting of phenyl, 2-tolyl, 3-tolyl, 4-tolyl, 4-pyridyl, 1-naphthyl, and 2-naphthyl.

4. A process for producing a compound represented by a formula selected from the group consisting of Formulae (II) to (XIII).

5. The process of claim 4, wherein the compound is adapted to be made into an amorphous thin film for organic electroluminescent devices, by means of a vacuum deposition method or a spin coating method.

6. An organic electroluminescent device that utilizes a compound represented by a formula selected from the group consisting of Formulae (II) to (XIII).

7. The organic electroluminescent device of claim 6, wherein the compound is adapted to be a material in an electron transport layer or an electron injection layer as a single material or in combination with an n-type dopant material.

8. The organic electroluminescent device of claim 6, wherein the compound is adapted to be a material in one selected from the group consisting of a light emitting layer, a hole block layer and an electron block layer.

9. The organic electroluminescent device of claim 6, wherein the compound is adapted to be a material in a light emitting layer used in combination with a fluorescent or a phosphorescent emitter.

10. The organic electroluminescent device of claim 6, which is one of a fluorescent organic electroluminescent device and a phosphorescent organic electroluminescent device.

* * * * *

专利名称(译)	电子传输化合物和使用其的有机电致发光器件		
公开(公告)号	US20140163233A1	公开(公告)日	2014-06-12
申请号	US14/098719	申请日	2013-12-06
申请(专利权)人(译)	E光光电屠春风CO., LTD.		
当前申请(专利权)人(译)	E光光电屠春风CO., LTD.		
[标]发明人	BALAGANESAN BANUMATHY HUANG HEH LUNG HSU PO WEI CHIANG KUN FENG		
发明人	BALAGANESAN, BANUMATHY HUANG, HEH-LUNG HSU, PO-WEI CHIANG, KUN-FENG		
IPC分类号	H01L51/00		
CPC分类号	H01L51/0055 H01L51/0074 H01L51/0067 H01L51/0058 H01L51/5072		
优先权	61/734552 2012-12-07 US		
其他公开文献	US9153787		
外部链接	Espacenet USPTO		

摘要(译)

本发明公开了一种新的式1化合物，以及使用该化合物的有机电致发光器件。在式1中，X和Y独立地表示碳数为5至10的芳族或杂芳族烃。Ar1至Ar7各自独立地表示碳原子数为4至C12的未取代或取代的芳族烃，或碳原子数为4-12的未取代或取代的稠多环芳烃；Ar1至Ar7可与相邻的芳烃形成稠合或耦合的芳环系统。当式I化合物用于该器件时，可以实现高发光效率，更长寿命和低驱动电压。

