





US 20150001521A1

(19) **United States**(12) **Patent Application Publication**
HUANG et al.(10) **Pub. No.: US 2015/0001521 A1**(43) **Pub. Date: Jan. 1, 2015**(54) **ORGANIC COMPOUND AND ORGANIC
ELECTROLUMINESCENT DEVICE
EMPLOYING THE SAME**(71) Applicants: **INDUSTRIAL TECHNOLOGY
RESEARCH INSTITUTE**, Hsinchu
(TW); **NATIONAL TSING HUA
UNIVERSITY**, Hsinchu (TW)(72) Inventors: **Heh-Lung HUANG**, New Taipei City
(TW); **Cheng-An WU**, New Taipei City
(TW); **Chien-Hong CHENG**, Hsin-Chu
City (TW)(73) Assignees: **NATIONAL TSING HUA
UNIVERSITY**, Hsinchu (TW);
**INDUSTRIAL TECHNOLOGY
RESEARCH INSTITUTE**, Hsinchu
(TW)(21) Appl. No.: **14/490,232**(22) Filed: **Sep. 18, 2014****Related U.S. Application Data**(63) Continuation-in-part of application No. 13/243,552,
filed on Sep. 23, 2011.(30) **Foreign Application Priority Data**

Aug. 5, 2011 (TW) 100127919

Publication Classification(51) **Int. Cl.**
H01L 51/00 (2006.01)(52) **U.S. Cl.**
CPC **H01L 51/0067** (2013.01); **H01L 51/0072**
(2013.01); **H01L 51/5024** (2013.01)USPC **257/40**; 548/266.4(57) **ABSTRACT**Organic compounds and organic electroluminescence
devices employing the same are provided. The organic com-
pound has a chemical structure represented below:wherein, R^1 are independently a hydrogen, or C_{1-8} alkyl;
and R^2 is a hydrogen, hydroxy, or C_{1-8} alkoxy. The
organic compounds have a high triplet energy (tE_g) gap
and apt to transmit the energy to a guest emitter.**10**




FIG. 1

ORGANIC COMPOUND AND ORGANIC ELECTROLUMINESCENT DEVICE EMPLOYING THE SAME

CROSS REFERENCE TO RELATED APPLICATIONS

[0001] This application is a Continuation-In-Part of pending U.S. patent application Ser. No. 13/243,552, filed Sep. 23, 2011 and entitled “Organic compound and organic electroluminescent device employing the same”, which claims priority of Taiwan Patent Application No. 100127919, filed on Aug. 5, 2011.

BACKGROUND

[0002] 1. Field

[0003] The disclosure relates to an organic compound and organic electroluminescence device employing the same and, more particularly, to an organic compound serving as a host material and a phosphorescent organic electroluminescence device employing the same.

[0004] 2. Description of the Related Art

[0005] Recently, with the development and wide application of electronic products, such as mobile phones, PDAs, and notebook computers, there has been increasing demand of flat display elements which consume less electric power and occupy less space. Organic electroluminescent devices are self-emitting and highly luminous, with wider viewing angles, faster response speeds, and simpler fabrication methods, making them an industry display of choice.

[0006] Generally, an organic electroluminescent device was composed of a light-emission layer sandwiched between a pair of electrodes. When an electric field was applied to the electrodes, the cathode injects electrons into the light-emission layer and the anode injects holes into the light-emission layer. When the electrons recombination with the holes in the light-emission layer, excitons were formed. Recombination of the electron and hole results in light emission.

[0007] Depending on the spin states of the hole and electron, the exciton which results from the hole and electron recombination can have either a triplet or singlet spin state. Luminescence from a singlet exciton results in fluorescence whereas luminescence from a triplet exciton results in phosphorescence. The emissive efficiency of phosphorescence is three times that of fluorescence. Therefore, it is crucial to develop highly efficient phosphorescent materials, in order to increase the emissive efficiency of the OLED.


[0008] In application of organic electroluminescent devices, phosphorescent guest materials have to be used in combination with host materials which has an energy gap matched therewith, thereby achieving optimal electroluminescent performance and quantum yield. Particularly, since blue and green host materials require larger differences of energy gap between the host and guest materials for electroluminescence, the host materials used in an phosphorescent OLED should have a shorter conjugated system. Further, in order to keep the key characteristics of the organic compound used in OLEDs (i.e. thermal-stability), the host material should also have larger molecular weight, resulting in difficulties for chemical structure designs.

[0009] Since conventional, commercially available phosphorescent host materials or phosphorescent host materials disclosed in prior art references merely have the moieties of carbazole or silyl benzene derivatives, the phosphorescent

host materials exhibit inferior thermal stability, resulting in devices made therefrom to have low current density and high operating voltage.

BRIEF SUMMARY

[0010] An exemplary embodiment of an organic compound has a Formula (I), of:



[0011] Formula (I)

[0012] wherein, R^1 are independently a hydrogen, or C_{1-8} alkyl; and R^2 is a hydrogen, hydroxyl, or C_{1-8} alkoxy.

[0013] In another exemplary embodiment of the disclosure, an organic electroluminescence device is provided. The device includes: a pair of electrodes; and an electroluminescent element disposed between the pair of electrodes, wherein the electroluminescent element includes the aforementioned organic compound.

[0014] Yet another exemplary embodiment of the disclosure provides an organic electroluminescence device including an emission layer which includes a host material and a phosphorescent dopant. Particularly, the host material includes the aforementioned organic compound and the emission layer emits blue or green light under a bias voltage.

[0015] A detailed description is given in the following embodiments with reference to the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0016] The disclosure can be more fully understood by reading the subsequent detailed description and examples with references made to the accompanying drawings, wherein:

[0017] FIG. 1 shows a cross section of an organic electroluminescent device disclosed by an embodiment of the disclosure.

DETAILED DESCRIPTION


[0018] The following description is of the best-contemplated mode of carrying out the disclosure. This description is made for the purpose of illustrating the general principles of the disclosure and should not be taken in a limiting sense. The scope of the disclosure is best determined by reference to the appended claims.

[0019] Organic Compound

[0020] The disclosure provides organic compounds having a high triplet energy (tE_g) gap and apt to transmit the energy to a guest emitter. Therefore, the organic compounds of the

disclosure are suitable as host material of blue or green phosphorescent organic electroluminescent devices, thereby increasing the efficiency thereof.


[0021] The disclosure provides an organic compound having a Formula (I), of:



[0022] Formula (I)


[0023] wherein, R^1 are independently a hydrogen, or C_{1-8} alkyl; and R^2 is a hydrogen, hydroxyl, or C_{1-8} alkoxy.

[0024] In the structure of Formula (I), the moieties



means that R^1 can be located at any one of the four substitutable positions of the benzene ring and the R^1 are independent. For example, R^1 can be each independently a methyl group, ethyl group, propyl group, isopropyl group, butyl group, tert-butyl group, pentyl group, or hexyl group. Further, R^2 can be methoxy group, ethoxy group, propoxy group, isopropoxy group, butoxy group, isobutoxy group, pentyloxy group, or hexyloxy group.

[0025] The organic compounds of Formula (I) of the disclosure have a high triplet energy (tE_g) gap and are apt to transmit the energy to a guest emitter. Further, in comparison with the conventional compound (represented by



wherein Ar^1 and Ar^2 are phenyl or pyridine group, and R^{11} and R^{12} are hydrogen, alkyl group, hydroxyl group, or aryl



group), since the organic compounds of Formula (I) of the disclosure have a triazole moiety bound to the benzene at the meta-position relative to a carbazole moiety resulting in a shorter conjugated system, the organic compounds of the disclosure are suitable for serving as a blue or green host material for a phosphorescent organic electroluminescent device. Moreover, the organic compounds of Formula (I) of the disclosure, in comparison with the conventional compound, are not apt to be crystallized after formation of a film by evaporation.

[0026] The organic compounds of the disclosure include the following compounds shown in Table 1. In addition, the contraction thereof are also named and shown in Table 1.

TABLE 1

Ex-ample	Structures	Contraction
1		m-TAZCz
2		m-TAZtCz
3		m-TAZDCz

TABLE 1-continued


Ex- ample	Structures	Contraction
4		m-TAZDtCz
5		m-TAZDCz-nH

[0027] In order to clearly illustrate the method for preparing organic compounds of the disclosure, the preparation of compounds disclosed in Examples 1-5 are described in detail as below.


Example 1

Preparation of Compound m-TAZCz


[0028] First, compound (1) (benzoyl chloride, 71.42 mmole, 10 g) was added into a 250 ml bottle and dissolved into THF (100 ml). Next, N_2H_4 (32.46 mmol, 1.62 g) was injected into the bottle at 0° C. After reacting for 4 hrs, a compound (2) was obtained with a yield of 92%. The synthesis pathway was as follows:




-continued




[0029] Next, compound (2) (41.66 mmol 10 g), and PCl_5 (91.51 mmol 18.76 g) were added into a 250 ml bottle and dissolved into toluene (100 mL). Next, after heating to 120° C. for 3 hrs, the result was purified by column chromatography, obtaining compound (3) with a yield of 90%. The synthesis pathway was as follows:



[0030] Next, compound (3) (18.11 mmol 5 g), 3-bromoaniline (21.73 mmol, 3.69 g), and N,N -dimethylaniline (25 mL) were added into a 100 ml bottle. Next, after heating to 130° C. for 12 hrs, the result was purified by column chromatography, obtaining compound (4) with a yield of 50%. The synthesis pathway was as follows:



[0031] Next, compound (4) (8 mmol, 3 g), carbazole (9.6 mmol, 1.61 g) and K_2CO_3 (40 mmol, 5.52 g) were added into a 50 ml bottle and dissolved into DMSO (30 ml). The mixture was heated to 180° C. for 36 hrs. After cooling, the result was purified by washing with water, and compound m-TAZCz was obtained. The synthesis pathway was as follows:



[0032] The physical measurements of the compound m-TAZCz are listed below:

[0033] 1H -NMR (400 MHz, $CDCl_3$, δ): 8.07 (m, 4H), 7.72-7.21 (m, 20H), 6.85 (m, 4H).

[0034] ^{13}C -NMR (100 MHz, $CDCl_3$, δ): 154.70, 139.98, 139.38, 136.38, 131.22, 129.92, 129.17, 128.77, 127.42, 126.73, 126.15, 125.93, 123.68, 120.60, 120.44, 109.10.


[0035] HRMS (EI) Calcd for $C_{32}H_{22}N_4$ (M^+): 462.1844. Found: 462.1844.

[0036] Elemental analysis: C, 83.09; H, 4.79; N, 12.11. Found: C, 83.33; H, 4.69; N, 12.22.

Example 2

Preparation of Compound m-TAZtCz

[0037] Compound (4) (13.33 mmol, 5 g), compound (5) (3,6-di-tert-butyl-9H-carbazole, 16 mmol, 4.46 g) and K_2CO_3 (66.66 mmol, 9.2 g) were added into a 50 ml bottle and dissolved into DMSO (30 ml). The mixture was heated to 180° C. for 36 hrs. After cooling, the result was purified by washing with water, and compound m-TAZtCz was obtained. The synthesis pathway was as follows:



[0038] The physical measurements of the compound m-TAZtCz are listed below:

[0039] 1H -NMR (400 MHz, $CDCl_3$, δ): 8.07 (s, 2H), 7.71-7.16 (m, 16H), 6.84 (d, $J=8$, 2H), 1.44 (s, 18H).

[0040] ^{13}C -NMR (100 MHz, $CDCl_3$, δ): 143.69, 138.28, 131.21, 130.06, 129.12, 128.80, 125.38, 123.76, 116.43, 108.58, 34.69, 31.89.




[0041] HRMS (EI) Calcd for $C_{40}H_{38}N_4$ (M^+): 574.3096. Found: 574.3100.

[0042] Elemental analysis: C, 83.59; H, 6.66; N, 9.75. Found: C, 83.69; H, 6.74; N, 9.78.



Example 3

Preparation of Compound m-TAZDCz


[0043] First, compound (3) (36.22 mmol, 10 g), compound (6) (3,5-difluorobenzenamine, 39.85 mmol, 5.14 g), and N,N-dimethyl aniline (30 mL) were added into a 250 ml bottle. Next, the mixture was heated to 135° C. for 12 hrs. After reaction, a compound (7) was obtained with a yield of 50%. The synthesis pathway was as follows:



[0044] Next, compound (7) (15.01 mmol, 5 g), carbazole (33.03 mmol, 5.54 g) and K_2CO_3 (75.05 mmol, 10.35 g) were added into a 50 ml bottle and dissolved into DMSO (30 ml). The mixture was heated to 180° C. for 36 hrs. After cooling, the result was purified by washing with water, and compound m-TAZDCz was obtained with a yield of 82%. The synthesis pathway was as follows:



-continued



[0045] The physical measurements of the compound m-TAZDCz are listed below:

[0046] $^1\text{H-NMR}$ (400 MHz, CDCl_3 , δ): 8.07 (d, $J=8 \text{ Hz}$, 4H), 7.97 (s, 1H), 7.68-7.55 (m, 11H), 7.34 (s, 2H), 7.29-7.23 (m, 7H), 6.92 (m, 4H).


[0047] $^{13}\text{C-NMR}$ (100 MHz, CDCl_3 , δ): 154.55, 140.64, 139.66, 130.17, 129.57, 129.15, 126.59, 126.35, 124.00, 123.87, 123.56, 120.99, 120.57, 109.14.


[0048] HRMS (EI) Calcd for $\text{C}_{44}\text{H}_{29}\text{N}_5$ (M^+): 627.2523. Found: 627.2428. Elemental analysis: C, 84.19; H, 4.66; N, 11.16. Found: C, 84.06; H, 4.69; N, 11.15.

Example 4

Preparation of Compound m-TAZDtCz

[0049] Compound (7) (15.01 mmol, 5 g), compound (5) (3,6-di-tert-butyl-9H-carbazole, 33.03 mmol, 9.22 g), and K_2CO_3 (75.07 mmol, 10.36 g) were added into a 50 ml bottle and dissolved into DMSO (30 ml). The mixture was heated to 180° C. for 36 hrs. After cooling, the result was purified by washing with water, and compound m-TAZDtCz. The synthesis pathway was as follows:





[0050] The physical measurements of the compound m-TAZDtCz are listed below:

[0051] $^1\text{H-NMR}$ (400 MHz, CDCl_3 , δ): 8.10 (s, 4H), 8.09 (s, 1H), 7.66-7.28 (m, 16H), 6.89 (m, 4H), 1.47 (s, 36H).

[0052] $^{13}\text{C-NMR}$ (100 MHz, CDCl_3 , δ): 154.71, 144.04, 141.07, 138.02, 137.21, 130.03, 129.49, 129.08, 126.88, 123.97, 123.88, 123.14, 122.58, 116.55, 108.68, 34.71, 31.88.



[0053] HRMS (FAB) Calcd for $\text{C}_{60}\text{H}_{61}\text{N}_5$ (M^+): 851.4927. Found: 851.4928.

[0054] Elemental analysis: C, 84.57; H, 7.22; N, 8.22. Found: C, 84.70; H, 7.60; N, 8.29.


Example 5

Preparation of Compound m-TAZDCz-nH


[0055] Compound (3) (36.23 mmol, 10 g), compound (8) (4-amino-2,6-difluorophenol, 43.47 mmol, 6.30 g), and N,N-dimethyl aniline were added into a 100 ml reaction bottle. Next, the mixture was heated to 135° C. for 12 hrs. After reaction, a compound (9) was obtained with a yield of 50%. The synthesis pathway was as follows:



[0056] Compound (9) (14.32 mmol, 5 g), carbazole (31.51 mmol, 5.29 g), and K_2CO_3 (71.6 mmol 9.8 g) were added into a 50 ml bottle and dissolved into DMSO (30 ml). The mixture was heated to 180° C. for 36 hrs. After cooling, the result was purified by washing with water, and compound (10) was obtained with a yield of 35%. The synthesis pathway was as follows:



[0057] Next, compound (X) (3.1 mmol, 2 g), 1-Bromohexane (3.73 mmol, 0.61 g), and KOH (4.04 mmol, 0.22 g) were added into a 100 ml bottle and dissolved into ethanol (30 ml). The mixture was heated to reflux for 3 hrs. After purification, compound m-TAZDCz-nH was obtained with a yield of 98%. The synthesis pathway was as follows:



[0058] The physical measurements of the compound m-TAZDCz-nH are listed below:

[0059] $^1\text{H-NMR}$ (400 MHz, CDCl_3 , δ): 8.06 (d, $J=8$ Hz, 2H), 7.87 (d, 1H), 7.52-7.20 (m, 11H), 6.93 (d, $J=8$ Hz, 1H), 6.68 (d, $J=8$ Hz, 2H), 3.93 (t, $J_1=4$ Hz, $J_2=12$ Hz, 2H), 1.42 (m, 2H), 1.03-0.98 (m, 6H), 0.73-0.70 (t, $J_1=8$ Hz, $J_2=12$ Hz).

[0060] $^{13}\text{C-NMR}$ (100 MHz, CDCl_3 , δ): 155.73, 154.73, 140.55, 129.69, 128.98, 128.58, 128.09, 127.04, 127.06, 126.80, 125.58, 123.29, 120.03, 119.82, 114.11, 109.73, 68.91, 31.06, 28.53, 25.16, 22.20, 13.75.

[0061] Properties of Organic Compounds

[0062] The glass transition temperature (T_g), melting point (T_m), decomposition temperature (T_d), band gap (E_g), triplet energy gap (E_T), and HOMO (highest occupied molecular orbital) and LUMO (lowest unoccupied molecular orbital) energy gap of compounds m-TAZCz, m-TAZtCz, m-TAZDCz, and m-TAZDtCz were measured and are shown in Table 2.

TABLE 2

	m-TAZCz	m-TAZtCz	m-TAZDCz	m-TAZDtCz
T_g	—	120.6° C.	159° C.	—
T_m	312.4° C.	288.7° C.	301.06° C.	—
T_d	358° C.	367° C.	432° C.	421° C.
(5%)				
LUMO (eV)	2.31	1.92	2.03	2.13
HOMO (eV)	5.99	5.54	5.6	5.68
E_T (eV)	3.0	2.99	3.01	2.97
E_g (eV)	3.68	3.62	3.57	3.54

[0063] As shown in Table 2, since the compounds m-TAZCz, m-TAZtCz, and m-TAZDCz have decomposition temperatures (T_d) of more than 350° C. (m-TAZDCz has a decomposition temperatures (T_d) of more than 430° C. especially), and glass transition temperatures (T_g) of more than 120° C., the compounds of the disclosure exhibits excellent thermal stability. The compounds also have suitable LUMO and HOMO energy gaps, thereby substantially matching a normal electron transfer layer.

[0064] Organic Electroluminescent Device

[0065] FIG. 1 shows an embodiment of an organic electroluminescent device 10. The electroluminescent device 100 includes a substrate 12, a bottom electrode 14, an electroluminescent element 16, and a top electrode 18, as shown in FIG. 1. The organic electroluminescent device can be top-emission, bottom-emission, or dual-emission devices.

[0066] The substrate 12 can be a glass plastic, or semiconductor substrate. Suitable materials for the bottom and top electrodes can be Ca, Ag, Mg, Al, Li, In, Au, Ni, W, Pt, Cu, indium tin oxide (ITO), indium zinc oxide (IZO), aluminum zinc oxide (AZO), or zinc oxide (ZnO), formed by sputtering, electron beam evaporation, thermal evaporation, or chemical vapor deposition. Further, at least one of the bottom and top electrodes 14 and 18 is transparent.

[0067] The electroluminescent element 16 at least includes an emission layer, and can further include a hole injection layer, a hole transport layer, an electron transport layer, and an electron injection layer. In an embodiment of the disclosure, at least one layer of the electroluminescent element 16 includes the aforementioned organic compound.

[0068] According to an embodiment of the disclosure, the organic electroluminescent device can be a phosphorescent organic electroluminescent device, and the phosphorescent organic electroluminescent device can include an emission layer including a host material and a phosphorescent dopant, wherein the host material includes the aforementioned organic compounds.

[0069] In order to clearly disclose the organic electroluminescent devices of the disclosure, the following examples (using m-TAZCz, m-TAZDCz (prepared from Example 1 and Example 3) as host materials and blue or green phosphorescent dopant) are intended to illustrate the disclosure more fully without limiting their scope, since numerous modifications and variations will be apparent to those skilled in this art.

Example 6

Green Organic Electroluminescent Device

[0070] A glass substrate with an indium tin oxide (ITO) film of 100 nm was provided and then washed with a cleaning

agent, acetone, and isopropanol with ultrasonic agitation. After drying with nitrogen flow, the ITO film was subjected to a UV/ozone treatment. Next, TAPC (1,1-bis(di-4-tolylaminophenyl)cyclohexane, with a thickness of 40 nm), m-TAZCz doped with Ir(ppy)₃ (tris(2-phenylpyridine)iridium) (the ratio between m-TAZCz and Ir(ppy)₃ was 100:15, with a thickness of 30 nm), BPhen (4,7-diphenyl-1,10-phenanthroline, with a thickness of 30 nm), LiF (with a thickness of 0.5 nm), and Al (with a thickness of 110 nm) were subsequently formed on the ITO film at 10⁻⁶ Pa, obtaining the electroluminescent device (1). The materials and layers formed therefrom are described in the following.

[0071] ITO (100 nm)/TAPC (40 nm)/15% Ir(ppy)₃:m-TAZCz (30 nm)/BPhen (30 nm)/LiF (0.5 nm)/Al (110 nm).

[0072] The optical property of the electroluminescent device (1), as described in Example 6, was measured by a PR650 (purchased from Photo Research Inc.) and a Minolta TS110. The results are shown below:

[0073] Optimal efficiency: 31.9 cd/A, and 22.7 lm/W;

[0074] Emissive efficiency: 31.8 cd/A, and 22.2 lm/W (@1000 cd/m²);

[0075] CIE coordinations: (0.30, 0.63).

Example 7

Blue Organic Electroluminescent Device

[0076] A glass substrate with an indium tin oxide (ITO) film of 100 nm was provided and then washed with a cleaning agent, acetone, and isopropanol with ultrasonic agitation. After drying with nitrogen flow, the ITO film was subjected to a UV/ozone treatment. Next, NPB (N,N'-di(naphthalene-1-yl)-N,N'-diphenyl-benzidine, with a thickness of 50 nm), TAPC (1,1-bis(di-4-tolylaminophenyl)cyclohexane, with a thickness of 15 nm), m-TAZCz doped with Firpic (Iridium-bis(4,6-difluorophenyl-pyridinato-N,C₂)-picolinate) (the ratio between m-TAZCz and Ir(ppy)₃ was 100:11, with a thickness of 40 nm), m-TPhOXD (Bis(2-tert-butyl-1,3,4-oxadiazole-5-diyl) 3,3'-m-terphenyl, with a thickness of 12.5 nm), BPhen (4,7-diphenyl-1,10-phenanthroline), with a thickness of 12.5 nm), LiF (with a thickness of 1 nm), and Al (with a thickness of 100 nm) were subsequently formed on the ITO film at 10⁻⁶ Pa, obtaining the electroluminescent device (2). The materials and layers formed therefrom are described in the following.

[0077] ITO (100 nm)/NPB (50 nm)/TAPC (15 nm)/m-TAZCz: Firpic 11% (40 nm)/m-TPhOXD (12.5 nm)/BPhen (12.5 nm)/LiF (1 nm)/Al (100 nm)

[0078] The optical property of the electroluminescent device (2), as described in Example 7, was measured by a PR650 (purchased from Photo Research Inc.) and a Minolta TS110. The results are shown below:

[0079] Optimal efficiency: 21.43 cd/A, 11.99 lm/W;

[0080] Emissive efficiency: 20 cd/A, 7.2 lm/W (@1000 cd/m²);

[0081] CIE coordinations: (0.16, 0.35).

Example 8

Green Organic Electroluminescent Device

[0082] A glass substrate with an indium tin oxide (ITO) film of 100 nm was provided and then washed with a cleaning agent, acetone, and isopropanol with ultrasonic agitation. After drying with nitrogen flow, the ITO film was subjected to a UV/ozone treatment. Next, NPNPB (N,N'-di-phenyl-N,N'-di-[4-(N,N'-diphenyl-amino)phenyl]benzidine, with a thickness of 60 nm), NPB (N,N'-di(naphthalene-1-yl)-N,N'-diphenyl-benzidine, with a thickness of 10 nm), TCTA (4,4',4'-tri(N-carbazolyl)triphenylamine with a thickness of 10 nm), m-TAZDCz doped with Ir(ppy)₃ (the ratio between m-TAZCz and Ir(ppy)₃ was 100:11, with a thickness of 30 nm), TAZ (3-phenyl-4-(1-naphthyl)-5-phenyl-1,2,4-triazole, with a thickness of 10 nm), BALq (aluminium (III) bis(2-methyl-8-quinolinato)-4-phenylphenolate, with a thickness of 10 nm), LiF (lithium fluoride, with a thickness of 1 nm), and Al (with a thickness of 100 nm) were subsequently formed on the ITO film at 10⁻⁶ Pa, obtaining the electroluminescent device (3). The materials and layers formed therefrom are described in the following.

[0083] ITO (100 nm)/NPNPB (60 nm)/NPB (10 nm)/m-TAZDCz:Ir(ppy)₃ (30 nm)/TAZ (10 nm)/BALq (10 nm)/LiF (1 nm)/Al (100 nm).

[0084] NPB (50 nm)/TAPC (15 nm)/m-TAZCz:Firpic 11% (40 nm)/m-TPhOXD (12.5 nm)/BPhen (12.5 nm)/LiF (1 nm)/Al (100 nm)

[0085] The optical property of the electroluminescent device (3), as described in Example 8, was measured by a PR650 (purchased from Photo Research Inc.) and a Minolta TS110. The results are shown below:

[0086] Optimal efficiency: 93.3 cd/A, 73.3 lm/W;

[0087] Emissive efficiency: 88 cd/A, 48 lm/W (@1000 cd/m²);

[0088] CIE coordinations: (0.27, 0.65).


[0089] Device Lifetime: 1014 hr @ 500 cd/m²

[0090] The organic electroluminescent device employing the organic compounds of Formula (I) can have an emissive efficiency of 7 lm/W for emitting blue light (or 48 lm/w for emitting green light) at a brightness of 1000 cd/m². The green color device lifetime reached to 1014 hours at 500 cd/m². Accordingly, the organic compounds of Formula (I) of the disclosure have a high triplet energy (tE_g) gap and are apt to transmit energy to a guest emitter. The organic compounds of Formula (I) of the disclosure have a triazole moiety bound to the benzene at the meta-position relative to a carbazole moiety resulting in a shorter conjugated system. Therefore, the organic compounds of Formula (I) of the disclosure are suitable as host material of blue or green phosphorescent organic electroluminescent devices, thereby increasing efficiency thereof.

[0091] While the disclosure has been described by way of example and in terms of the preferred embodiments, it is to be understood that the disclosure is not limited to the disclosed embodiments. To the contrary, it is intended to cover various modifications and similar arrangements (as would be apparent to those skilled in the art). Therefore, the scope of the appended claims should be accorded the broadest interpretation so as to encompass all such modifications and similar arrangements.

What is claimed is:

1. An organic compound having a Formula (I), of:




Formula (I)

wherein R^1 are independently a hydrogen, or C_{1-8} alkyl; and R^2 is a hydrogen, hydroxyl, or C_{1-8} alkoxy.

2. The organic compound as claimed in claim 1, wherein R^1 are independently a methyl group, ethyl group, propyl group, isopropyl group, butyl group, tert-butyl group, pentyl group, or hexyl group.

3. The organic compound as claimed in claim 1, wherein R^2 is a methoxy group, ethoxy group, propoxy group, isopropoxy group, butoxy group, isobutoxy group, pentyloxy group, or hexyloxy group.

4. The organic compound as claimed in claim 1, wherein the organic compound is



5. An organic electroluminescence device, comprising:
a pair of electrodes; and

an electroluminescent element disposed between the pair of electrodes, wherein the electroluminescent element comprises the organic compound as claimed in claim 1.

6. An organic electroluminescence device, comprising:
a pair of electrodes; and

an electroluminescent element disposed between the pair of electrodes, wherein the electroluminescent element comprises an emission layer comprising a host material and a phosphorescent dopant, and the host material comprises the organic compound as claimed in claim 1.

7. The organic electroluminescent device as claimed in claim 6, wherein the emission layer emits blue or green light under a bias voltage.

* * * * *

专利名称(译)	有机化合物和使用其的有机电致发光器件		
公开(公告)号	US20150001521A1	公开(公告)日	2015-01-01
申请号	US14/490232	申请日	2014-09-18
[标]申请(专利权)人(译)	财团法人工业技术研究院 国立清华大学		
申请(专利权)人(译)	工业技术研究院 清大		
当前申请(专利权)人(译)	工业技术研究院 清大		
[标]发明人	HUANG HEH LUNG WU CHENG AN CHENG CHIEN HONG		
发明人	HUANG, HEH-LUNG WU, CHENG-AN CHENG, CHIEN-HONG		
IPC分类号	H01L51/00		
CPC分类号	H01L51/0067 H01L51/5024 H01L51/0072 C07D403/14 H01L51/0081 H01L51/0085 H01L51/5016 H01L2251/308		
优先权	100127919 2011-08-05 TW		
其他公开文献	US9178164		
外部链接	Espacenet USPTO		

摘要(译)

提供了有机化合物和使用其的有机电致发光器件。有机化合物具有如下化学结构：其中，R₁独立地为氢，或C₁₋₈烷基；R₂和R₃是氢，羟基或C₁₋₈-/-烷基。有机化合物具有较高的三重态能量（tE_g）间隙，易于将能量传递给客体发射体。

