



US 20190044075A1

(19) **United States**

(12) **Patent Application Publication**
LIN et al.

(10) **Pub. No.: US 2019/0044075 A1**

(43) **Pub. Date: Feb. 7, 2019**

(54) **ORGANIC ELECTROLUMINESCENT
MATERIALS AND DEVICES**

H01L 51/50 (2006.01)

C07D 233/54 (2006.01)

C09K 11/06 (2006.01)

(71) Applicant: **UNIVERSAL DISPLAY
CORPORATION**, Ewing, NJ (US)

C07D 401/12 (2006.01)

C07D 213/69 (2006.01)

(72) Inventors: **Chun LIN**, Yardley, PA (US);
Chuanjun XIA, Lawrenceville, NJ
(US); **Jui-Yi TSAI**, Newtown, PA (US)

C07F 15/00 (2006.01)

C07F 7/08 (2006.01)

C07D 235/04 (2006.01)

(73) Assignee: **UNIVERSAL DISPLAY
CORPORATION**, Ewing, NJ (US)

(52) **U.S. Cl.**

CPC *H01L 51/0087* (2013.01); *C07D 209/82*

(2013.01); *C07D 235/04* (2013.01); *C07D*

233/54 (2013.01); *H01L 51/5016* (2013.01);

C09K 2211/1044 (2013.01); *C09K 2211/1007*

(2013.01); *C09K 11/06* (2013.01); *C07D*

401/12 (2013.01); *C07D 213/69* (2013.01);

C07F 15/0086 (2013.01); *C07F 7/0814*

(2013.01); *C09K 2211/185* (2013.01); *C09K*

2211/1029 (2013.01); *C07F 15/0093*

(2013.01); *H01L 51/5012* (2013.01)

(21) Appl. No.: **16/154,864**

(22) Filed: **Oct. 9, 2018**

Related U.S. Application Data

(62) Division of application No. 14/565,576, filed on Dec.
10, 2014, now Pat. No. 10,135,008.

(60) Provisional application No. 61/924,340, filed on Jan.
7, 2014.

Publication Classification

(51) **Int. Cl.**


H01L 51/00 (2006.01)

C07D 209/82 (2006.01)

(57)

ABSTRACT

A novel method for forming a metal-carbene bond is dis-
closed.






FIG. 1





FIG. 2



FORMULA I

FIG. 3




FIG. 4

ORGANIC ELECTROLUMINESCENT MATERIALS AND DEVICES

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application is a divisional of U.S. patent application Ser. No. 14/565,576, filed on Dec. 10, 2014, which claims priority under 35 U.S.C. § 119(e) to U.S. Provisional Application Ser. No. 61/924,340, filed Jan. 7, 2014, the disclosures of which are herein expressly incorporated by reference in their entirety.

PARTIES TO A JOINT RESEARCH AGREEMENT

[0002] The claimed invention was made by, on behalf of, and/or in connection with one or more of the following parties to a joint university corporation research agreement: The Regents of the University of Michigan, Princeton University, University of Southern California, and Universal Display Corporation. The agreement was in effect on and before the date the claimed invention was made, and the claimed invention was made as a result of activities undertaken within the scope of the agreement.

FIELD OF THE INVENTION

[0003] The present invention relates to compounds for use as phosphorescent emitters and devices, such as organic light emitting diodes, including the same.


BACKGROUND

[0004] Opto-electronic devices that make use of organic materials are becoming increasingly desirable for a number of reasons. Many of the materials used to make such devices are relatively inexpensive, so organic opto-electronic devices have the potential for cost advantages over inorganic devices. In addition, the inherent properties of organic materials, such as their flexibility, may make them well suited for particular applications such as fabrication on a flexible substrate. Examples of organic opto-electronic devices include organic light emitting devices (OLEDs), organic phototransistors, organic photovoltaic cells, and organic photodetectors. For OLEDs, the organic materials may have performance advantages over conventional materials. For example, the wavelength at which an organic emissive layer emits light may generally be readily tuned with appropriate dopants.

[0005] OLEDs make use of thin organic films that emit light when voltage is applied across the device. OLEDs are becoming an increasingly interesting technology for use in applications such as flat panel displays, illumination, and backlighting. Several OLED materials and configurations are described in U.S. Pat. Nos. 5,844,363, 6,303,238, and 5,707,745, which are incorporated herein by reference in their entirety.

[0006] One application for phosphorescent emissive molecules is a full color display. Industry standards for such a display call for pixels adapted to emit particular colors, referred to as “saturated” colors. In particular, these standards call for saturated red, green, and blue pixels. Color may be measured using CIE coordinates, which are well known to the art.

[0007] One example of a green emissive molecule is tris(2-phenylpyridine) iridium, denoted Ir(ppy)₃, which has the following structure:



[0008] In this, and later figures herein, we depict the dative bond from nitrogen to metal (here, Ir) as a straight line.

[0009] As used herein, the term “organic” includes polymeric materials as well as small molecule organic materials that may be used to fabricate organic opto-electronic devices. “Small molecule” refers to any organic material that is not a polymer, and “small molecules” may actually be quite large. Small molecules may include repeat units in some circumstances. For example, using a long chain alkyl group as a substituent does not remove a molecule from the “small molecule” class. Small molecules may also be incorporated into polymers, for example as a pendent group on a polymer backbone or as a part of the backbone. Small molecules may also serve as the core moiety of a dendrimer, which consists of a series of chemical shells built on the core moiety. The core moiety of a dendrimer may be a fluorescent or phosphorescent small molecule emitter. A dendrimer may be a “small molecule,” and it is believed that all dendrimers currently used in the field of OLEDs are small molecules.

[0010] As used herein, “top” means furthest away from the substrate, while “bottom” means closest to the substrate. Where a first layer is described as “disposed over” a second layer, the first layer is disposed further away from substrate. There may be other layers between the first and second layer, unless it is specified that the first layer is “in contact with” the second layer. For example, a cathode may be described as “disposed over” an anode, even though there are various organic layers in between.

[0011] As used herein, “solution processible” means capable of being dissolved, dispersed, or transported in and/or deposited from a liquid medium, either in solution or suspension form.

[0012] A ligand may be referred to as “photoactive” when it is believed that the ligand directly contributes to the photoactive properties of an emissive material. A ligand may be referred to as “ancillary” when it is believed that the ligand does not contribute to the photoactive properties of an emissive material, although an ancillary ligand may alter the properties of a photoactive ligand.

[0013] As used herein, and as would be generally understood by one skilled in the art, a first “Highest Occupied Molecular Orbital” (HOMO) or “Lowest Unoccupied Molecular Orbital” (LUMO) energy level is “greater than” or “higher than” a second HOMO or LUMO energy level if the first energy level is closer to the vacuum energy level. Since ionization potentials (IP) are measured as a negative energy relative to a vacuum level, a higher HOMO energy level corresponds to an IP having a smaller absolute value (an IP that is less negative). Similarly, a higher LUMO


energy level corresponds to an electron affinity (EA) having a smaller absolute value (an EA that is less negative). On a conventional energy level diagram, with the vacuum level at the top, the LUMO energy level of a material is higher than the HOMO energy level of the same material. A “higher” HOMO or LUMO energy level appears closer to the top of such a diagram than a “lower” HOMO or LUMO energy level.

[0014] As used herein, and as would be generally understood by one skilled in the art, a first work function is “greater than” or “higher than” a second work function if the first work function has a higher absolute value. Because work functions are generally measured as negative numbers relative to vacuum level, this means that a “higher” work function is more negative. On a conventional energy level diagram, with the vacuum level at the top, a “higher” work function is illustrated as further away from the vacuum level in the downward direction. Thus, the definitions of HOMO and LUMO energy levels follow a different convention than work functions.

[0015] More details on OLEDs, and the definitions described above, can be found in U.S. Pat. No. 7,279,704, which is incorporated herein by reference in its entirety.

SUMMARY OF THE INVENTION

[0016] According to an embodiment, a compound having a Pt tetradentate structure, having the formula:



is disclosed, wherein rings A, B, C, and D each independently represent a 5-membered or 6-membered carbocyclic or heterocyclic ring;

[0017] wherein R^A , R^B , R^C , and R^D each independently represent mono, di, tri, or tetra-substitution, or no substitution;

[0018] wherein L^1 , L^2 , and L^3 are each independently selected from the group consisting of a direct bond, BR, NR, PR, O, S, Se, C=O, S=O, SO₂, CRR', SiRR', GeRR', and combinations thereof;

[0019] wherein when n is 1, L^4 is selected from the group consisting of a direct bond, BR, NR, PR, O, S, Se, C=O, S=O, SO₂, CRR', SiRR', GeRR', and combinations thereof;

[0020] when n is 0, L^4 is not present;

[0021] wherein R^A , R^B , R^C , R^D , R, and R' are each independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, aryl-alkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof;

[0022] wherein any adjacent R^A , R^B , R^C , R^D , R, and R' are optionally joined to form a ring;

[0023] wherein X^1 , X^2 , X^3 , and X^4 each independently selected from the group consisting of carbon and nitrogen;

[0024] wherein one of Q^1 , Q^2 , Q^3 , and Q^4 is oxygen, the remaining three of Q^1 , Q^2 , Q^3 , and Q^4 each represents a direct bond so that Pt directly bonds to three of X^1 , X^2 , X^3 , and X^4 ; and

[0025] wherein when L^1 , L^2 , L^3 , or L^4 represents a direct bond, the direct bond is not a C—C bond.

[0026] According to another embodiment, a device comprising one or more organic light emitting devices is also provided. At least one of the one or more organic light emitting devices comprises an anode, a cathode, and an organic layer, disposed between the anode and the cathode, wherein the organic layer includes a compound having Formula I as defined herein including all of its variations.

[0027] According to yet another embodiment, a formulation comprising a compound having Formula I as defined herein including all of its variations, is provided.

[0028] According to another embodiment, a novel method for forming a metal-carbene bond is disclosed.

[0029] The novel Pt tetradentate complexes having Pt—O bond disclosed herein are useful as emitters in phosphorescent OLEDs.

BRIEF DESCRIPTION OF THE DRAWINGS

[0030] FIG. 1 shows an organic light emitting device.

[0031] FIG. 2 shows an inverted organic light emitting device that does not have a separate electron transport layer.

[0032] FIG. 3 shows Formula I as disclosed herein.

[0033] FIG. 4 shows the solution photoluminescence spectrum of Compound 99 in 2-methyl-tetrahydrofuran at room temperature.

DETAILED DESCRIPTION

[0034] Generally, an OLED comprises at least one organic layer disposed between and electrically connected to an anode and a cathode. When a current is applied, the anode injects holes and the cathode injects electrons into the organic layer(s). The injected holes and electrons each migrate toward the oppositely charged electrode. When an electron and hole localize on the same molecule, an “exciton,” which is a localized electron-hole pair having an excited energy state, is formed. Light is emitted when the exciton relaxes via a photoemissive mechanism. In some cases, the exciton may be localized on an excimer or an exciplex. Non-radiative mechanisms, such as thermal relaxation, may also occur, but are generally considered undesirable.

[0035] The initial OLEDs used emissive molecules that emitted light from their singlet states (“fluorescence”) as disclosed, for example, in U.S. Pat. No. 4,769,292, which is incorporated by reference in its entirety. Fluorescent emission generally occurs in a time frame of less than 10 nanoseconds.

[0036] More recently, OLEDs having emissive materials that emit light from triplet states (“phosphorescence”) have been demonstrated. Baldo et al., “Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices,” *Nature*, vol. 395, 151-154, 1998; (“Baldo-I”) and Baldo et al., “Very high-efficiency green organic light-emitting devices based on electrophosphorescence,” *Appl.*

Phys. Lett., vol. 75, No. 3, 4-6 (1999) ("Baldo-II"), which are incorporated by reference in their entirety. Phosphorescence is described in more detail in U.S. Pat. No. 7,279,704 at cols. 5-6, which are incorporated by reference.

[0037] FIG. 1 shows an organic light emitting device **100**. The figures are not necessarily drawn to scale. Device **100** may include a substrate **110**, an anode **115**, a hole injection layer **120**, a hole transport layer **125**, an electron blocking layer **130**, an emissive layer **135**, a hole blocking layer **140**, an electron transport layer **145**, an electron injection layer **150**, a protective layer **155**, a cathode **160**, and a barrier layer **170**. Cathode **160** is a compound cathode having a first conductive layer **162** and a second conductive layer **164**. Device **100** may be fabricated by depositing the layers described, in order. The properties and functions of these various layers, as well as example materials, are described in more detail in U.S. Pat. No. 7,279,704 at cols. 6-10, which are incorporated by reference.

[0038] More examples for each of these layers are available. For example, a flexible and transparent substrate-anode combination is disclosed in U.S. Pat. No. 5,844,363, which is incorporated by reference in its entirety. An example of a p-doped hole transport layer is m-MTDATA doped with F₄-TCNQ at a molar ratio of 50:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. Examples of emissive and host materials are disclosed in U.S. Pat. No. 6,303,238 to Thompson et al., which is incorporated by reference in its entirety. An example of an n-doped electron transport layer is BPhen doped with Li at a molar ratio of 1:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. U.S. Pat. Nos. 5,703,436 and 5,707,745, which are incorporated by reference in their entirety, disclose examples of cathodes including compound cathodes having a thin layer of metal such as Mg:Ag with an overlying transparent, electrically-conductive, sputter-deposited ITO layer. The theory and use of blocking layers is described in more detail in U.S. Pat. No. 6,097,147 and U.S. Patent Application Publication No. 2003/0230980, which are incorporated by reference in their entirety. Examples of injection layers are provided in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety. A description of protective layers may be found in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety.

[0039] FIG. 2 shows an inverted OLED **200**. The device includes a substrate **210**, a cathode **215**, an emissive layer **220**, a hole transport layer **225**, and an anode **230**. Device **200** may be fabricated by depositing the layers described, in order. Because the most common OLED configuration has a cathode disposed over the anode, and device **200** has cathode **215** disposed under anode **230**, device **200** may be referred to as an "inverted" OLED. Materials similar to those described with respect to device **100** may be used in the corresponding layers of device **200**. FIG. 2 provides one example of how some layers may be omitted from the structure of device **100**.

[0040] The simple layered structure illustrated in FIGS. 1 and 2 is provided by way of non-limiting example, and it is understood that embodiments of the invention may be used in connection with a wide variety of other structures. The specific materials and structures described are exemplary in nature, and other materials and structures may be used.

Functional OLEDs may be achieved by combining the various layers described in different ways, or layers may be omitted entirely, based on design, performance, and cost factors. Other layers not specifically described may also be included. Materials other than those specifically described may be used. Although many of the examples provided herein describe various layers as comprising a single material, it is understood that combinations of materials, such as a mixture of host and dopant, or more generally a mixture, may be used. Also, the layers may have various sublayers. The names given to the various layers herein are not intended to be strictly limiting. For example, in device **200**, hole transport layer **225** transports holes and injects holes into emissive layer **220**, and may be described as a hole transport layer or a hole injection layer. In one embodiment, an OLED may be described as having an "organic layer" disposed between a cathode and an anode. This organic layer may comprise a single layer, or may further comprise multiple layers of different organic materials as described, for example, with respect to FIGS. 1 and 2.

[0041] Structures and materials not specifically described may also be used, such as OLEDs comprised of polymeric materials (PLEDs) such as disclosed in U.S. Pat. No. 5,247,190 to Friend et al., which is incorporated by reference in its entirety. By way of further example, OLEDs having a single organic layer may be used. OLEDs may be stacked, for example as described in U.S. Pat. No. 5,707,745 to Forrest et al, which is incorporated by reference in its entirety. The OLED structure may deviate from the simple layered structure illustrated in FIGS. 1 and 2. For example, the substrate may include an angled reflective surface to improve out-coupling, such as a mesa structure as described in U.S. Pat. No. 6,091,195 to Forrest et al., and/or a pit structure as described in U.S. Pat. No. 5,834,893 to Bulovic et al., which are incorporated by reference in their entirety.

[0042] Unless otherwise specified, any of the layers of the various embodiments may be deposited by any suitable method. For the organic layers, preferred methods include thermal evaporation, ink-jet, such as described in U.S. Pat. Nos. 6,013,982 and 6,087,196, which are incorporated by reference in their entirety, organic vapor phase deposition (OVPD), such as described in U.S. Pat. No. 6,337,102 to Forrest et al., which is incorporated by reference in its entirety, and deposition by organic vapor jet printing (OVJP), such as described in U.S. Pat. No. 7,431,968, which is incorporated by reference in its entirety. Other suitable deposition methods include spin coating and other solution based processes. Solution based processes are preferably carried out in nitrogen or an inert atmosphere. For the other layers, preferred methods include thermal evaporation. Preferred patterning methods include deposition through a mask, cold welding such as described in U.S. Pat. Nos. 6,294,398 and 6,468,819, which are incorporated by reference in their entirety, and patterning associated with some of the deposition methods such as ink jet and OVJD. Other methods may also be used. The materials to be deposited may be modified to make them compatible with a particular deposition method. For example, substituents such as alkyl and aryl groups, branched or unbranched, and preferably containing at least 3 carbons, may be used in small molecules to enhance their ability to undergo solution processing. Substituents having 20 carbons or more may be used, and 3-20 carbons is a preferred range. Materials with asymmetric structures may have better solution processability.

than those having symmetric structures, because asymmetric materials may have a lower tendency to recrystallize. Dendrimer substituents may be used to enhance the ability of small molecules to undergo solution processing.

[0043] Devices fabricated in accordance with embodiments of the present invention may further optionally comprise a barrier layer. One purpose of the barrier layer is to protect the electrodes and organic layers from damaging exposure to harmful species in the environment including moisture, vapor and/or gases, etc. The barrier layer may be deposited over, under or next to a substrate, an electrode, or over any other parts of a device including an edge. The barrier layer may comprise a single layer, or multiple layers. The barrier layer may be formed by various known chemical vapor deposition techniques and may include compositions having a single phase as well as compositions having multiple phases. Any suitable material or combination of materials may be used for the barrier layer. The barrier layer may incorporate an inorganic or an organic compound or both. The preferred barrier layer comprises a mixture of a polymeric material and a non-polymeric material as described in U.S. Pat. No. 7,968,146, PCT Pat. Application Nos. PCT/US2007/023098 and PCT/US2009/042829, which are herein incorporated by reference in their entireties. To be considered a "mixture", the aforesaid polymeric and non-polymeric materials comprising the barrier layer should be deposited under the same reaction conditions and/or at the same time. The weight ratio of polymeric to non-polymeric material may be in the range of 95:5 to 5:95. The polymeric material and the non-polymeric material may be created from the same precursor material. In one example, the mixture of a polymeric material and a non-polymeric material consists essentially of polymeric silicon and inorganic silicon.

[0044] Devices fabricated in accordance with embodiments of the invention can be incorporated into a wide variety of electronic component modules (or units) that can be incorporated into a variety of electronic products or intermediate components. Examples of such electronic products or intermediate components include display screens, lighting devices such as discrete light source devices or lighting panels, etc. that can be utilized by the end-user product manufacturers. Such electronic component modules can optionally include the driving electronics and/or power source(s). Devices fabricated in accordance with embodiments of the invention can be incorporated into a wide variety of consumer products that have one or more of the electronic component modules (or units) incorporated therein. Such consumer products would include any kind of products that include one or more light source(s) and/or one or more of some type of visual displays. Some examples of such consumer products include flat panel displays, computer monitors, medical monitors, televisions, billboards, lights for interior or exterior illumination and/or signaling, heads-up displays, fully or partially transparent displays, flexible displays, laser printers, telephones, cell phones, tablets, phablets, personal digital assistants (PDAs), laptop computers, digital cameras, camcorders, viewfinders, micro-displays, 3-D displays, vehicles, a large area wall, theater or stadium screen, or a sign. Various control mechanisms may be used to control devices fabricated in accordance with the present invention, including passive matrix and active matrix. Many of the devices are intended for use in a temperature range comfortable to humans, such as 18 degrees C. to 30 degrees C., and more preferably at room temperature (20-25 degrees C.), but could be used outside this temperature range, for example, from -40 degree C. to +80 degree C.

[0045] The materials and structures described herein may have applications in devices other than OLEDs. For example, other optoelectronic devices such as organic solar cells and organic photodetectors may employ the materials and structures. More generally, organic devices, such as organic transistors, may employ the materials and structures.

[0046] The term "halo," "halogen," or "halide" as used herein includes fluorine, chlorine, bromine, and iodine.

[0047] The term "alkyl" as used herein contemplates both straight and branched chain alkyl radicals. Preferred alkyl groups are those containing from one to fifteen carbon atoms and includes methyl, ethyl, propyl, isopropyl, butyl, isobutyl, tert-butyl, and the like. Additionally, the alkyl group may be optionally substituted.

[0048] The term "cycloalkyl" as used herein contemplates cyclic alkyl radicals. Preferred cycloalkyl groups are those containing 3 to 7 carbon atoms and includes cyclopropyl, cyclopentyl, cyclohexyl, and the like. Additionally, the cycloalkyl group may be optionally substituted.

[0049] The term "alkenyl" as used herein contemplates both straight and branched chain alkene radicals. Preferred alkenyl groups are those containing two to fifteen carbon atoms. Additionally, the alkenyl group may be optionally substituted.

[0050] The term "alkynyl" as used herein contemplates both straight and branched chain alkyne radicals. Preferred alkynyl groups are those containing two to fifteen carbon atoms. Additionally, the alkynyl group may be optionally substituted.

[0051] The terms "aralkyl" or "arylalkyl" as used herein are used interchangeably and contemplate an alkyl group that has as a substituent an aromatic group. Additionally, the aralkyl group may be optionally substituted.

[0052] The term "heterocyclic group" as used herein contemplates aromatic and non-aromatic cyclic radicals. Hetero-aromatic cyclic radicals also means heteroaryl. Preferred hetero-non-aromatic cyclic groups are those containing 3 or 7 ring atoms which includes at least one hetero atom, and includes cyclic amines such as morpholino, piperidino, pyrrolidino, and the like, and cyclic ethers, such as tetrahydropyran, tetrahydropyran, and the like. Additionally, the heterocyclic group may be optionally substituted.

[0053] The term "aryl" or "aromatic group" as used herein contemplates single-ring groups and polycyclic ring systems. The polycyclic rings may have two or more rings in which two carbons are common to two adjoining rings (the rings are "fused") wherein at least one of the rings is aromatic, e.g., the other rings can be cycloalkyls, cycloalkenyls, aryl, heterocycles, and/or heteroaryls. Additionally, the aryl group may be optionally substituted.

[0054] The term "heteroaryl" as used herein contemplates single-ring hetero-aromatic groups that may include from one to three heteroatoms, for example, pyrrole, furan, thiophene, imidazole, oxazole, thiazole, triazole, pyrazole, pyridine, pyrazine and pyrimidine, and the like. The term heteroaryl also includes polycyclic hetero-aromatic systems having two or more rings in which two atoms are common to two adjoining rings (the rings are "fused") wherein at least one of the rings is a heteroaryl, e.g., the other rings can be cycloalkyls, cycloalkenyls, aryl, heterocycles, and/or heteroaryls. Additionally, the heteroaryl group may be optionally substituted.

[0055] The alkyl, cycloalkyl, alkenyl, alkynyl, aralkyl, heterocyclic group, aryl, and heteroaryl may be optionally substituted with one or more substituents selected from the group consisting of hydrogen, deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, cyclic amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acid,

ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.


[0056] As used herein, “substituted” indicates that a substituent other than H is bonded to the relevant position, such as carbon. Thus, for example, where R^1 is mono-substituted, then one R^1 must be other than H. Similarly, where R^1 is di-substituted, then two of R^1 must be other than H. Similarly, where R^1 is unsubstituted, R^1 is hydrogen for all available positions.

[0057] The “aza” designation in the fragments described herein, i.e. aza-dibenzofuran, aza-dibenzothiophene, etc. means that one or more of the C—H groups in the respective fragment can be replaced by a nitrogen atom, for example, and without any limitation, azatriphenylene encompasses both dibenzofuran and dibenzothiophene. One of ordinary skill in the art can readily envision other nitrogen analogs of the aza-derivatives described above, and all such analogs are intended to be encompassed by the terms as set forth herein.

[0058] It is to be understood that when a molecular fragment is described as being a substituent or otherwise attached to another moiety, its name may be written as if it were a fragment (e.g. phenyl, phenylene, naphthyl, dibenzofuryl) or as if it were the whole molecule (e.g. benzene, naphthalene, dibenzofuran). As used herein, these different ways of designating a substituent or attached fragment are considered to be equivalent.

[0059] Tetradentate platinum complexes can be used as emitters in phosphorescent OLEDs. These complexes have a single ligand that has four coordination sites, enabling versatile materials design. The known tetradentate platinum complexes such as tetradentate platinum complex coordinating to a ligand with two neutral nitrogen donors, one anionic carbon donor and one anionic oxygen donor (Advanced Functional Materials, 2013, 23, 5168 and Chemistry a European Journal, 2013, 19, 69) have shown high PLQY and high EQE in OLED devices. However, because of the conjugation and low triplet energy of the ligands, only green and longer wavelength emission can be achieved. In the present disclosure, the inventors have formulated tetradentate platinum complexes with high triplet energy ligands. These novel complexes comprise a Pt—O bond.

[0060] According to an aspect of the present disclosure, a compound having a Pt tetradentate structure having the formula:



is disclosed. In Formula I, rings A, B, C, and D each independently represent a 5-membered or 6-membered carbocyclic or heterocyclic ring; wherein R^4 , R^5 , R^6 , and R^7 each independently represent mono, di, tri, or tetra-substitution, or no substitution; wherein L^1 , L^2 , and L^3 are each independently selected from the group consisting of a direct

bond, BR, NR, PR, O, S, Se, C=O, S=O, SO₂, CRR', SiRR', GeRR', and combinations thereof; wherein when n is 1, L^4 is selected from the group consisting of a direct bond, BR, NR, PR, O, S, Se, C=O, S=O, SO₂, CRR', SiRR', GeRR', and combinations thereof; when n is 0, L^4 is not present; wherein R^4 , R^5 , R^6 , R^7 , R, and R' are each independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, aryl-alkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof;

[0061] wherein any adjacent R^4 , R^5 , R^6 , R^7 , R, and R' are optionally joined to form a ring; wherein X^1 , X^2 , X^3 , and X^4 each independently selected from the group consisting of carbon and nitrogen;

[0062] wherein one of Q^1 , Q^2 , Q^3 , and Q^4 is oxygen, the remaining three of Q^1 , Q^2 , Q^3 , and Q^4 each represents a direct bond so that Pt directly bonds to three of X^1 , X^2 , X^3 , and X^4 ; and

[0063] wherein when L^1 , L^2 , L^3 , or L^4 represents a direct bond, the direct bond is not a C—C bond.

[0064] In one embodiment of the compound, wherein two of X^1 , X^2 , X^3 , and X^4 that directly bond to Pt are carbon thus forming Pt—C bonds, and one of X^1 , X^2 , X^3 , and X^4 that directly bond to Pt is nitrogen. In another embodiment, wherein the two Pt—C bonds are in cis configuration.

[0065] In one embodiment of the compound, L^1 , L^2 , and L^3 are each independently selected from the group consisting of a direct bond, NR, O, CRR', SiRR', and combinations thereof; and wherein when n is 1, L^4 is selected from the group consisting of a direct bond, NR, O, CRR', SiRR', and combinations thereof.

[0066] In another embodiment of the compound, R and R' are each independently selected from the group consisting of hydrogen, deuterium, methyl, ethyl, propyl, 1-methylethyl, butyl, 1-methylpropyl, 2-methylpropyl, pentyl, 1-methylbutyl, 2-methylbutyl, 3-methylbutyl, 1,1-dimethylpropyl, 1,2-dimethylpropyl, 2,2-dimethylpropyl, cyclopentyl, cyclohexyl, phenyl, and combinations thereof.

[0067] In one embodiment, the compound has a neutral charge.

[0068] In one embodiment, the compound has at least one Pt-carbene bond.

[0069] In one embodiment of the compound, n is 0. In another embodiment of the compound, n is 1.





[0070] In one embodiment of the compound, one of the rings A, B, C, and D is phenyl when said ring is bonded to one of the Q^1 , Q^2 , Q^3 and Q^4 that is oxygen.

[0071] In one embodiment of the compound, the rings A, B, C, and D are each independently selected from the group consisting of phenyl, pyridine, and imidazole.




[0072] In one embodiment of the compound, when L^1 , L^2 , L^3 , or L^4 represents a direct bond, the direct bond is a C—N bond.

[0073] In one embodiment of the compound, at least one of L^1 , L^2 , L^3 , and L^4 is not a direct bond.


[0074] In another embodiment of the compound, the compound is selected from the group consisting of:



-continued




[0075] In another embodiment of the compound, the compound is selected from the group consisting of:




Compound 1


-continued




Compound 2




Compound 3



Compound 4




Compound 5




Compound 6


-continued




Compound 7




Compound 8



Compound 9




Compound 10




Compound 11

-continued




Compound 12


-continued




Compound 18




Compound 14




Compound 19




Compound 15




Compound 20




Compound 16



Compound 21




Compound 17




Compound 22

-continued




Compound 23


-continued




Compound 28




Compound 24




Compound 29




Compound 25




Compound 30




Compound 26



Compound 31




Compound 27




Compound 32

-continued




Compound 33


-continued




Compound 38




Compound 34




Compound 39




Compound 35




Compound 40




Compound 36



Compound 41




Compound 37




Compound 42


-continued




Compound 43



Compound 44




Compound 45




Compound 46


-continued




Compound 47



Compound 48




Compound 49



Compound 50


-continued

Compound 51




-continued


Compound 55




Compound 52




Compound 56




Compound 53




Compound 57



Compound 54




Compound 58




-continued


Compound 59




Compound 60



Compound 61




Compound 62




-continued


Compound 63




Compound 64




Compound 65




Compound 66




Compound 67




-continued




Compound 68




Compound 69



Compound 70




Compound 71




Compound 72


-continued




Compound 73




Compound 74



Compound 75




Compound 76




Compound 77

-continued




Compound 78


-continued




Compound 83




Compound 79




Compound 84




Compound 80




Compound 85



Compound 81




Compound 86




Compound 82


-continued




Compound 87



Compound 88




Compound 89




Compound 90


-continued




Compound 91



Compound 92




Compound 93




Compound 94


-continued




Compound 95



Compound 96




Compound 97




Compound 98


-continued




Compound 99



Compound 100




Compound 101




Compound 102


-continued




Compound 103



Compound 104




Compound 105




Compound 106


-continued



Compound 107




Compound 108




Compound 109

-continued




Compound 110


-continued




Compound 113




Compound 111



Compound 114




Compound 112




Compound 115

-continued




Compound 116


-continued




Compound 119




Compound 117




Compound 120



Compound 121




Compound 118




Compound 122


-continued




Compound 123



Compound 124




Compound 125




Compound 126


-continued




Compound 127



Compound 128




Compound 129




Compound 130

-continued




Compound 131


-continued




Compound 134




Compound 132



Compound 135



Compound 133




Compound 136


and

-continued

Compound 137



[0076] According to another aspect of the present disclosure, a device comprising one or more organic light emitting devices incorporating the compound disclosed herein is provided. At least one of the one or more organic light emitting devices comprise: an anode; a cathode; and an organic layer, disposed between the anode and the cathode, comprising a compound having a Pt tetradentate structure, having the formula:



Formula I

[0077] wherein rings A, B, C, and D each independently represent a 5-membered or 6-membered carbocyclic or heterocyclic ring;

[0078] wherein R^A , R^B , R^C , and R^D each independently represent mono, di, tri, or tetra-substitution, or no substitution;

[0079] wherein L^1 , L^2 , and L^3 are each independently selected from the group consisting of a direct bond, BR, NR, PR, O, S, Se, C=O, S=O, SO₂, CRR', SiRR', GeRR', and combinations thereof;

[0080] wherein when n is 1, L^4 is selected from the group consisting of a direct bond, BR, NR, PR, O, S, Se, C=O, S=O, SO₂, CRR', SiRR', GeRR', and combinations thereof;

[0081] when n is 0, L^4 is not present;

[0082] wherein R^A , R^B , R^C , R^D , R, and R' are each independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, aryl-alkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof;

[0083] wherein any adjacent R^A , R^B , R^C , R^D , R, and R' are optionally joined to form a ring;

[0084] wherein X^1 , X^2 , X^3 , and X^4 are each independently selected from the group consisting of carbon and nitrogen;

[0085] wherein one of Q^1 , Q^2 , Q^3 , and Q^4 is oxygen, the remaining three of Q^1 , Q^2 , Q^3 , and Q^4 each represent a direct bond so that Pt directly bonds to three of X^1 , X^2 , X^3 , and X^4 ; and

[0086] wherein when L^1 , L^2 , L^3 , or L^4 represents a direct bond, the direct bond is not a C—C bond.

[0087] In one embodiment of the device, the device is selected from the group consisting of a consumer product, an electronic component module, an organic light-emitting device, and a lighting panel.

[0088] In another embodiment of the device, the organic layer is an emissive layer and the compound is an emissive dopant or a non-emissive dopant.

[0089] In another embodiment of the device, the organic layer further comprises a host, wherein the host comprises a triphenylene containing benzo-fused thiophene or benzo-fused furan;


[0090] wherein any substituent in the host is an unfused substituent independently selected from the group consisting of C_mH_{2m+1} , OC_mH_{2m+1} , OAr_1 , $N(C_mH_{2m+1})_2$, $N(Ar_1)(Ar_2)$, $CH=CH-C_mH_{2m+1}$, $C\equiv CC_mH_{2m+1}$, Ar_1 , Ar_1-Ar_2 , $C_mH_{2m}-Ar_1$, or no substitution;

[0091] wherein m is from 1 to 10; and


[0092] wherein Ar_1 and Ar_2 are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof.

[0093] In some embodiments of the device, the organic layer further comprises a host, wherein the host comprises at least one chemical group selected from the group consisting of triphenylene, carbazole, dibenzothiophene, dibenzofuran, dibenzoselenophene, azatriphenylene, azacarbazole, aza-dibenzothiophene, aza-dibenzofuran, and aza-dibenzoselenophene.


[0094] In one embodiment of the device, the host is selected from the group consisting of:




-continued






-continued



-continued



-continued





and combinations thereof.

[0095] In one embodiment of the device, the host comprises a metal complex.


[0096] According to another aspect of the present disclosure, a formulation comprising a compound having a Pt tetradentate structure, having Formula I as described herein including all variations thereof is disclosed.

[0097] According to another aspect of the present disclosure, a novel method for forming a metal-carbene bond is disclosed. The method is exemplified by the following scheme for synthesis of Compound 99:





[0098] A 35 ml microwave reaction vessel was charged with a ligand



(1 g, 1.367 mmol); K_2PtCl_4 (0.567 g, 1.367 mmol); sodium acetate (1.121 g, 13.67 mmol) and acetic acid (20 ml) forming a reaction mixture. The reaction mixture was heated in a microwave reactor (CEM brand; discovery model) to 160° C. for 10.5 hours. The reaction mixture was neutralized with aqueous ammonium and extracted by dichloromethane. The organic portion was combined and evaporated to dryness. The residue was subjected to column chromatography (SiO_2 , Et_3N pretreated, 100% dichloromethane) to yield the desired product (0.7 g, 79%).

[0099] The method comprises: mixing a metal precursor with a carbene salt, a weak base salt, and a solvent to form a reaction mixture; and heating the reaction mixture, wherein the weak base salt has pK_a greater than 4.

[0100] N-heterocyclic carbenes (NHC) are one of the most promising new classes of ligands in the design of transition metal complexes. The general synthetic procedure is to carry out the deprotection of an imidazole salt followed by coordination of the resulting free carbene to the metal. However; this method usually requires cryogenic condition due to the short shelf life of the free carbene in ambient temperature. In this disclosure; we develop a methodology in which free carbene is not involved in the process. Therefore, cryogenic condition is not necessary and conventional heating process can be applied. This novel methodology shall be more practical in industrial setting environment. Furthermore, conventional carbene ligation is generally carried out in a basic or neutral condition due to high sensitivity of the free carbene toward acid. In the novel method of the present

disclosure, since the free carbene is not involved in the process, the choice of the solvent is not restricted to a basic or neutral solvent. In fact, solvents with weak acidity can be used in the present method.

[0101] In one embodiment of the method, the metal precursor is a second or third row transition metal. In one embodiment, the metal precursor is selected from the group consisting of Ir, Rh, Re, Ru, Os, Pt, and Pd. In another embodiment, the metal precursor is a halide salt. In another embodiment, the metal precursor is selected from the group consisting of K_2PtCl_4 , Na_2PtCl_4 , PtCl_2 , $\text{PtCl}_2(\text{DMSO})_2$, $\text{Pt}(\text{COD})\text{Cl}_2$, $\text{IrCl}_3 \cdot x\text{H}_2\text{O}$, $\text{Na}_2\text{IrCl}_6 \cdot x\text{H}_2\text{O}$, $(\text{NH}_4)_2\text{IrCl}_6$, $\text{K}_3\text{IrCl}_6 \cdot x\text{H}_2\text{O}$, Na_2IrBr_6 , $[(\text{COD})\text{IrCl}]_2$, $\text{OsCl}_3 \cdot x\text{H}_2\text{O}$, $(\text{NH}_4)_2\text{OsCl}_6$, Na_2OsCl_6 , and $\text{OsCl}_2(\text{DMSO})_2$.

[0102] In one embodiment of the method, the carbene salt is a carbon carbene salt. In another embodiment, the carbene salt is a N-heterocyclic carbene salt. In some embodiments, the carbene salt comprises a tetradentate ligand. In another embodiment, the carbene salt is a carbene halide salt.

[0103] In one embodiment of the method, the weak base salt is selected from the group consisting of: sodium acetate, potassium acetate, sodium butyrate, potassium butyrate, sodium propionate, and potassium propionate.

[0104] In one embodiment of the method, the solvent is the corresponding weak acid of the weak base salt. In some embodiments, the solvent is selected from the group consisting of acetic acid, propanoic acid, pivalic acid, and butyric acid.

[0105] In one embodiment of the method, the heating step is carried out in a microwave reactor.

[0106] In some embodiments of the method, the reaction mixture has a free carbene concentration of less than 10% of the carbene salt concentration. In one embodiment, the reaction mixture has a free carbene concentration of less than 1% of the carbene salt concentration. In one embodiment, the reaction mixture has a free carbene concentration of less than 0.1% of the carbene salt concentration.

[0107] In some embodiments of the method, the method produces a metal-carbene complex having a yield of at least 50%. In one embodiment, the method produces a metal-carbene complex having a yield of at least 70%.

[0108] In yet another aspect of the present disclosure, a formulation comprising a compound of Formula I as defined herein including all of their variations, is provided. The formulation can include one or more components selected from the group consisting of a solvent, a host, a hole injection material, hole transport material, and an electron transport layer material, disclosed herein.


Combination with Other Materials

[0109] The materials described herein as useful for a particular layer in an organic light emitting device may be used in combination with a wide variety of other materials present in the device. For example, emissive dopants disclosed herein may be used in conjunction with a wide variety of hosts, transport layers, blocking layers, injection layers, electrodes and other layers that may be present. The materials described or referred to below are non-limiting examples of materials that may be useful in combination with the compounds disclosed herein, and one of skill in the art can readily consult the literature to identify other materials that may be useful in combination.

HIL/HTL:

[0110] A hole injecting/transporting material to be used in the present invention is not particularly limited, and any compound may be used as long as the compound is typically used as a hole injecting/transporting material. Examples of the material include, but are not limited to: a phthalocyanine or porphyrin derivative; an aromatic amine derivative; an indolocarbazole derivative; a polymer containing fluorohydrocarbon; a polymer with conductivity dopants; a conducting polymer, such as PEDOT/PSS; a self-assembly monomer derived from compounds such as phosphonic acid and silane derivatives; a metal oxide derivative, such as MoO_3 ; a p-type semiconducting organic compound, such as 1,4,5,8,9,12-Hexaazatriphenylenehexacarbonitrile; a metal complex, and a cross-linkable compound.


[0111] Examples of aromatic amine derivatives used in HIL or HTL include, but are not limited to the following general structures:



[0112] Each of Ar^1 to Ar^9 is selected from the group consisting of aromatic hydrocarbon cyclic compounds such as benzene, biphenyl, triphenyl, triphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene; the group consisting of aromatic heterocyclic compounds such as dibenzothio-phenene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyridine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benzisoxazole, benzothiazole, quinoline, isoquinoline, cinnoline, quinazoline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzofurapyridine, furodipyridine, benzothienopyridine, thienodipyridine, benzoselenophenopyridine, and selenophenodipyridine; and the group consisting of 2 to 10 cyclic structural units which are groups of the same type or different types selected from the aromatic hydrocarbon cyclic group and the aromatic heterocyclic group and are bonded to each other directly or via at least one of oxygen


atom, nitrogen atom, sulfur atom, silicon atom, phosphorus atom, boron atom, chain structural unit and the aliphatic cyclic group. Wherein each Ar is further substituted by a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

[0113] In one aspect, Ar^1 to Ar^9 is independently selected from the group consisting of:



wherein k is an integer from 1 to 20; X^{101} to X^{108} is C (including CH) or N; Z^{101} is NAr^1 , O, or S; Ar^1 has the same group defined above.

[0114] Examples of metal complexes used in HIL or HTL include, but are not limited to the following general formula:




wherein Met is a metal, which can have an atomic weight greater than 40; $(\text{Y}^{101}-\text{Y}^{102})$ is a bidentate ligand, Y^{101} and Y^{102} are independently selected from C, N, O, P, and S; L^{101} is an ancillary ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal; and $k'+k''$ is the maximum number of ligands that may be attached to the metal.

[0115] In one aspect, $(\text{Y}^{101}-\text{Y}^{102})$ is a 2-phenylpyridine derivative. In another aspect, $(\text{Y}^{101}-\text{Y}^{102})$ is a carbene ligand. In another aspect, Met is selected from Ir, Pt, Os, and Zn. In a further aspect, the metal complex has a smallest oxidation potential in solution vs. Fc^+/Fc couple less than about 0.6 V.


Host:

[0116] The light emitting layer of the organic EL device of the present invention preferably contains at least a metal

[0117] Examples of metal complexes used as host are preferred to have the following general formula:




[0118] In one aspect, the metal complexes are:




[10120] Examples of organic compounds used as host are selected from the group consisting of aromatic hydrocarbon cyclic compounds such as benzene, biphenyl, triphenyl, triphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene; the group consisting of aromatic heterocyclic compounds such as dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyridine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benzisoxazole, benzothiazole, quinoline, isoquinoline, cinnoline, quinoxaline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzo-furopyridine, furodipyridine, benzothienopyridine, thienodipyridine, benzoselenophenopyridine, and selenophenodipyridine; and the group consisting of 2 to 10 cyclic structural units which are groups of the same type or different types selected from the aromatic hydrocarbon cyclic group and the aromatic heterocyclic group and are bonded to each other directly or via at least one of oxygen atom, nitrogen atom, sulfur atom, silicon atom, phosphorus atom, boron atom, chain structural unit and the aliphatic cyclic group. Wherein each group is further substituted by a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl,

[0121] In one aspect, the host compound contains at least one of the following groups in the molecule:



-continued



wherein R^{101} to R^{107} is independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof; when it is aryl or heteroaryl, it has the similar definition as Ar's mentioned above. k is an integer from 0 to 20 or 1 to 20; k'' is an integer from 0 to 20. X^{101} to X^{108} is selected from C (including CH) or N.


Z^{101} and Z^{102} is selected from NR^{101} , O, or S.

HBL:

[0122] A hole blocking layer (HBL) may be used to reduce the number of holes and/or excitons that leave the emissive layer. The presence of such a blocking layer in a device may result in substantially higher efficiencies as compared to a similar device lacking a blocking layer. Also, a blocking layer may be used to confine emission to a desired region of an OLED.

[0123] In one aspect, compound used in HBL contains the same molecule or the same functional groups used as host described above.

[0124] In another aspect, compound used in HBL contains at least one of the following groups in the molecule:





wherein k is an integer from 1 to 20; L^{101} is an another ligand, k' is an integer from 1 to 3.





ETL:

[0125] Electron transport layer (ETL) may include a material capable of transporting electrons. Electron transport layer may be intrinsic (undoped), or doped. Doping may be used to enhance conductivity. Examples of the ETL material are not particularly limited, and any metal complexes or organic compounds may be used as long as they are typically used to transport electrons.

[0126] In one aspect, compound used in ETL contains at least one of the following groups in the molecule:







-continued



wherein R^{101} is selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, aryl-alkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof, when it is aryl or heteroaryl, it has the similar definition as Ar 's mentioned above. Ar^1 to Ar^3 has the similar definition as Ar 's mentioned above. k is an integer from 1 to 20. X^{101} to X^{108} is selected from C (including CH) or N.

[0127] In another aspect, the metal complexes used in ETL include, but are not limited to the following general formula:



wherein (O—N) or (N—N) is a bidentate ligand, having metal coordinated to atoms O, N or N, N; L^{101} is another ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal.


[0128] In any above-mentioned compounds used in each layer of the OLED device, the hydrogen atoms can be partially or fully deuterated. Thus, any specifically listed substituent, such as, without limitation, methyl, phenyl, pyridyl, etc. encompasses undeuterated, partially deuterated, and fully deuterated versions thereof. Similarly, classes of substituents such as, without limitation, alkyl, aryl, cycloalkyl, heteroaryl, etc. also encompass undeuterated, partially deuterated, and fully deuterated versions thereof.

[0129] In addition to and/or in combination with the materials disclosed herein, many hole injection materials, hole transporting materials, host materials, dopant materials, exciton/hole blocking layer materials, electron transporting and electron injecting materials may be used in an OLED. Non-limiting examples of the materials that may be used in an OLED in combination with materials disclosed herein are listed in Table A below. Table A lists non-limiting classes of materials, non-limiting examples of compounds for each class, and references that disclose the materials.

TABLE A

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Hole injection materials		

Phthalocyanine
and porphyrin
compounds



Appl. Phys. Lett.
69, 2160 (1996)

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Starburst triarylaminines		J. Lumin. 72-74, 985 (1997)
CF _x Fluoro-hydrocarbon polymer	$\text{-(CH}_2\text{F}_y\text{)-}_n$	Appl. Phys. Lett. 78, 673 (2001)
Conducting polymers (e.g., PEDOT:PSS, polyaniline, polythiophene)		Synth. Met. 87, 171 (1997) WO2007002683
Phosphonic acid and silane SAMs		US20030162053
Triarylamine or polythiophene polymers with conductivity dopants	 and	EP1725079A1

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		
		
Organic compounds with conductive inorganic compounds, such as molybdenum and tungsten oxides	 $+ \text{MoO}_x$	US20050123751 SID Symposium Digest, 37, 923 (2006) WO2009018009
n-type semiconducting organic complexes		US20020158242

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Metal organometallic complexes		US20060240279
Cross-linkable compounds		US20080220265
Polythiophene based polymers and copolymers		WO 2011075644 EP2350216
Hole transporting materials		
Triarylamines (e.g., TPD, □-NPD)		Appl. Phys. Lett. 51, 913 (1987)

TABLE A-continued




MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		U.S. Pat. No. 5,061,569
		EP650955
		J. Mater. Chem. 3, 319 (1993)

TABLE A-continued




MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		Appl. Phys. Lett. 90, 183503 (2007)
		Appl. Phys. Lett. 90, 183503 (2007)
Triarylamine on spirofluorene core		Synth. Met. 91, 209 (1997)

TABLE A-continued




MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Arylamine carbazole compounds		Adv. Mater. 6, 677 (1994), US20080124572
Triarylamine with (di)benzothio- phene/(di)benzofuran		US20070278938, US20080106190 US20110163302
Indolocarbazoles		Synth. Met. 111, 421 (2000)

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Isoindole compounds		Chem. Mater. 15, 3148 (2003)
Metal carbene complexes		US20080018221
Phosphorescent OLED host materials Red hosts		
Arylcarbazoles		Appl. Phys. Lett. 78, 1622 (2001)
Metal 8-hydroxyquinolates (e.g., Alq ₃ , BALq)		Nature 395, 151 (1998)
		US20060202194

TABLE A-continued







MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO2005014551
		WO2006072002
Metal phenoxybenzothiazole compounds		Appl. Phys. Lett. 90, 123509 (2007)
Conjugated oligomers and polymers (e.g., polyfluorene)		Org. Electron. 1, 15 (2000)
Aromatic fused rings		WO2009066779, WO2009066778, WO2009063833, US20090045731, US20090045730, WO2009008311, US20090008605, US20090009065
Zinc complexes		WO2010056066

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Chrysene based compounds		WO2011086863
Green hosts		
Arylcarbazoles		Appl. Phys. Lett. 78, 1622 (2001)
		US20030175553
		WO2001039234
Aryltriphenylene compounds		US20060280965

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Poly-fused heteroaryl compounds		US20060280965
		WO2009021126
		US20090309488 US20090302743 US20100012931
Donor acceptor type molecules		WO2008056746
		WO2010107244

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Aza-carbazole/DBT/ DBF		JP2008074939
		US20100187984
Polymers (e.g., PVK)		Appl. Phys. Lett. 77, 2280 (2000)
Spirofluorene compounds		WO2004093207
Metal phenoxybenzoxazole compounds		WO2005089025

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO2006132173
		JP200511610
Spirofluorene-carbazole compounds		JP2007254297
		JP2007254297
Indolocarbazoles		WO2007063796

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO2007063754
5-member ring electron deficient heterocycles (e.g., triazole, oxadiazole)	 	J. Appl. Phys. 90, 5048 (2001) WO2004107822
Tetraphenylene complexes		US20050112407
Metal phenoxypyridine compounds		WO2005030900

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Metal coordination complexes (e.g., Zn, Al with N [*] N ligands)		US20040137268, US20040137267
Blue hosts		
Arylcarbazoles		Appl. Phys. Lett, 82, 2422 (2003)
		US20070190359
Dibenzothiophene/ Dibenzofuran- carbazole compounds		WO2006114966, US20090167162
		US20090167162

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO2009086028
		US20090030202, US20090017330
		US20100084966
Silicon aryl compounds		US20050238919
		WO2009003898

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Silicon/Germanium aryl compounds	 <chem>c1ccc(cc1)[Si](c2ccccc2)(c3ccccc3)c4cc5ccccc5s4</chem>	EP2034538A
Aryl benzoyl ester	 <chem>c1ccccc1C(=O)Oc2ccc(cc2)C(C)(C)c3ccc(cc3)Oc4ccccc4C(=O)c5ccccc5</chem>	WO2006100298
Carbazole linked by non-conjugated groups	 <chem>c1ccc2c(c1)c3ccccc3n2-c4ccc(cc4)C(C)(C)c5ccc(cc5)n6c7ccccc7c8ccccc68</chem>	US20040115476
Aza-carbazoles	 <chem>c1ccc2c(c1)c3ccncc3n2-c4ccc(cc4)C(C)(C)c5ccc(cc5)n6c7ccncc7c8ccccc68</chem>	US20060121308

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
High triplet metal organometallic complex		U.S. Pat. No. 7,154,114
	Phosphorescent dopants Red dopants	
Heavy metal porphyrins (e.g., PtOEP)		Nature 395, 151 (1998)
Iridium(III) organometallic complexes		Appl. Phys. Lett. 78, 1622 (2001)
		US20030072964

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US20030072964
		US20060202194
		US20060202194
		US20070087321

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US20080261076 US20100090591
		US20070087321
		Adv. Mater. 19, 739 (2007)
		WO2009100991

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO2008101842
		U.S. Pat. No. 7,232,618
Platinum(II) organometallic complexes		WO2003040257
		US20070103060

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Osmium(III) complexes		Chem. Mater. 17, 3532 (2005)
Ruthenium(II) complexes		Adv. Mater. 17, 1059 (2005)
Rhenium (I), (II), and (III) complexes		US20050244673
Green dopants		
Iridium(III) organometallic complexes	 and its derivatives 	Inorg. Chem. 40, 1704 (2001) US20020034656

TABLE A-continued




MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		U.S. Pat. No. 7,332,232
		US20090108737
		WO2010028151

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		EP1841834B
		US20060127696
		US20090039776
		U.S. Pat. No. 6,921,915
		US20100244004

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		U.S. Pat. No. 6,687,266
		Chem. Mater. 16, 2480 (2004)
		US20070190359
		US 20060008670 JP2007123392
		WO2010086089, WO2011044988

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		Adv. Mater. 16, 2003 (2004)
		Angew. Chem. Int. Ed. 2006, 45, 7800
		WO2009050290
		US20090165846
		US20080015355

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US20010015432
		US20100295032
Monomer for polymeric metal organometallic compounds		U.S. Pat. No. 7,250,226, U.S. Pat. No. 7,396,598
Pt(II) organometallic complexes, including polydentate ligands		Appl. Phys. Lett. 86, 153505 (2005)
		Appl. Phys. Lett. 86, 153505 (2005)

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		Chem. Lett. 34, 592 (2005)
		WO2002015645
		US20060263635
		US20060182992 US20070103060

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Cu complexes		WO2009000673
		US20070111026
Gold complexes		Chem. Commun. 2906 (2005)
Rhenium(III) complexes		Inorg. Chem. 42, 1248 (2003)

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Osmium(II) complexes		U.S. Pat. No. 7,279,704
Deuterated organometallic complexes		US20030138657
Organometallic complexes with two or more metal centers		US20030152802
		U.S. Pat. No. 7,090,928

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Blue dopants		
Iridium(III) organometallic complexes		WO2002002714
		WO2006009024
		US20060251923 US20110057559 US20110204333
		U.S. Pat. No. 7,393,599, WO2006056418, US20050260441, WO2005019373
		U.S. Pat. No. 7,534,505

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO2011051404
		U.S. Pat. No. 7,445,855
		US20070190359, US20080297033 US20100148663
		U.S. Pat. No. 7,338,722
		US20020134984

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		Angew. Chem. Int. Ed. 47, 4542 (2008)
		Chem. Mater. 18, 5119 (2006)
		Inorg. Chem. 46, 4308 (2007)
		WO2005123873
		WO2005123873

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO2007004380
		WO2006082742
Osmium(II) complexes		U.S. Pat. No. 7,279,704
		Organometallics 23, 3745 (2004)
Gold complexes		Appl. Phys. Lett. 74, 1361 (1999)

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Platinum(II) complexes		WO2006098120, WO2006103874
Pt tetradentate complexes with at least one metal-carbene bond		U.S. Pat. No. 7,655,323
Exciton/hole blocking layer materials		
Bathocuprine compounds (e.g., BCP, BPhen)		Appl. Phys. Lett. 75, 4 (1999)
		Appl. Phys. Lett. 79, 449 (2001)
Metal 8-hydroxyquinolates (e.g., BAlq)		Appl. Phys. Lett. 81, 162 (2002)

TABLE A-continued




MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5-member ring electron deficient heterocycles such as triazole, oxadiazole, imidazole, benzimidazole		Appl. Phys. Lett. 81, 162 (2002)
Triphenylene compounds		US20050025993
Fluorinated aromatic compounds		Appl. Phys. Lett. 79, 156 (2001)

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Phenothiazine-S-oxide		WO2008132085
Silylated five-membered nitrogen, oxygen, sulfur or phosphorus dibenzoheterocycles		WO2010079051
Aza-carbazoles		US20060121308
Electron transporting materials		
Anthracene-benzoimidazole compounds		WO2003060956

TABLE A-continued







MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US20090179554
Aza triphenylene derivatives		US20090115316
Anthracene-benzothiazole compounds		Appl. Phys. Lett. 89, 063504 (2006)
Metal 8-hydroxyquinolates (e.g., Alq ₃ , Zr _q ₄)		Appl. Phys. Lett. 51, 913 (1987) U.S. Pat. No. 7,230,107
Metal hydroxybenzoquinolates		Chem. Lett. 5, 905 (1993)
Bathocuprine compounds such as BCP, BPhen, etc		Appl. Phys. Lett. 91, 263503 (2007)

TABLE A-continued











MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		Appl. Phys. Lett. 79, 449 (2001)
5-member ring electron deficient heterocycles (e.g., triazole, oxadiazole, imidazole, benzimidazole)		Appl. Phys. Lett. 74, 865 (1999)
		Appl. Phys. Lett. 55, 1489 (1989)
		Jpn. J. Apply. Phys. 32, L917 (1993)
Silole compounds		Org. Electron. 4, 113 (2003)


TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Arylborane compounds		J. Am. Chem. Soc. 120, 9714 (1998)
Fluorinated aromatic compounds		J. Am. Chem. Soc. 122, 1832 (2000)
Fullerene (e.g., C60)		US20090101870
Triazine complexes		US20040036077
Zn (N^N) complexes		U.S. Pat. No. 6,528,187

EXPERIMENTAL


[0130] Synthesis of Compound 99

Synthesis of 2-methoxy-N-(2-nitrophenyl)aniline

[0131]

A three neck 500 ml round bottom flask was charged with 1-bromo-2-nitrobenzene (10 g, 49.5 mmol); 2-methoxyaniline (5.58 ml, 49.5 mmol); Cs_2CO_3 (47.4 g, 146 mmol); (oxybis(2,1-phenylene))bis(diphenylphosphine) (1.920 g, 3.56 mmol); Pd_2dba_3 (1.088 g, 1.188 mmol), and toluene (250 ml). The reaction mixture was refluxed for 17 hours. The reaction was then filtered through a pad of Celite®. The organic layer was combined and subjected to column chromatography (SiO_2 , 5% THF in heptane) to yield 2-methoxy-N-(2-nitrophenyl)aniline (11.55 g, 96%).


Synthesis of
N1-(2-methoxyphenyl)benzene-1,2-diamine

[0132]

A 500 ml hydrogenation bottle was charged with 2-methoxy-N-(2-nitrophenyl)aniline (11.55 g, 47.3 mmol); 10% pd/c (0.75 g) and EtOH (200 ml). The reaction was shaken under 50 psi of H_2 for 4 hours. The reaction mixture was filtered through a pad of Celite®. The organic portion

was subjected to column chromatography (SiO_2 , 10% THF in heptane) to yield N1-(2-methoxyphenyl)benzene-1,2-diamine (8.67 g, 86%).



Synthesis of N1-(2-methoxyphenyl)-N2-(9-(pyridin-2-yl)-9H-carbazol-2-yl)benzene-1,2-diamine

[0133]

A 500 ml three neck round bottom flask was charged with 2-bromo-9-(pyridin-2-yl)-9H-carbazole (10.24 g, 31.7 mmol); N1-(2-methoxyphenyl)benzene-1,2-diamine (6.79 g, 31.7 mmol); Pd_2dba_3 (0.870 g, 0.951 mmol); dicyclohexyl (2',6'-dimethoxy-[1,1'-biphenyl]-2-yl)phosphine (S-Phos) (1.561 g, 3.80 mmol); sodium t-butoxide (5.12 g, 53.2 mmol) and 150 ml of anhydrous toluene. The reaction was heated to reflux for 17 hours. The reaction mixture was then diluted with saturated ammonium chloride solution and extracted with ethyl acetate. The organic portion was combined and evaporated to dryness. The residue was subjected to column chromatography (SiO_2 , 20% THF in heptane) to yield N1-(2-methoxyphenyl)-N2-(9-(pyridin-2-yl)-9H-carbazol-2-yl)benzene-1,2-diamine (12.24 g, 85%).


Synthesis of 3-(2-methoxyphenyl)-1-(9-(pyridin-2-yl)-9H-carbazol-2-yl)-1H-benzo[d]imidazol-3-ium chloride

[0134]




A 500 ml round bottom flask was charged with N1-(2-methoxyphenyl)-N2-(9-(pyridin-2-yl)-9H-carbazol-2-yl) benzene-1,2-diamine (12.24 g, 26.8 mmol), triethylorthoformate (150 ml); 4 ml of concentrated HCl and 10 drops of formic acid. The reaction was reflux for 6 hours. The reaction mixture was filtered and yield 3-(2-methoxyphenyl)-1-(9-(pyridin-2-yl)-9H-carbazol-2-yl)-1H-benzo[d]imidazol-3-ium chloride. (12 g, 89%).

[0135] Synthesis of Ligand for Compound 99




-continued



A 35 ml microwave reactor vessel was charged with 3-(2-methoxyphenyl)-1-(9-(pyridin-2-yl)-9H-carbazol-2-yl)-1H-benzo[d]imidazol-3-ium chloride (3 g, 5.96 mmol) and 12 ml of solution (HBr:HOAc=1:1 by volume). The reaction mixture was subjected to microwave reactor (CEM brand; discovery model) and heated to 140° C. for 1.5 hours. The reaction mixture was filtered and the precipitation was washed with acetone to yield the desired ligand. (3.8 g, 88%).

[0136] Synthesis of Compound 99





A 35 ml microwave reaction vessel was charged with ligand (1 g, 1.367 mmol), K₂PtCl₄ (0.567 g, 1.367 mmol), sodium acetate (1.121 g, 13.67 mmol), and acetic acid (20 ml). The reaction mixture was subjected to microwave reactor (CEM brand; discovery model) and heated to 160° C. for 10.5 hours. The reaction mixture was neutralized with aqueous ammonium and extracted by dichloromethane. The organic portion was combined and evaporated to dryness. The

residue was subjected to column chromatography (SiO_2 , triethylamine pretreated, 100% dichloromethane) to yield Compound 99 (0.7 g, 79%).

[0137] Photophysics of Compound 99

FIG. 4 shows the solution photoluminescence spectrum of Compound 99 in 2-methyl-tetrahydrofuran at room temperature. Compound 99 has a Peak maximum of 502 nm which is suitable for being a green dopant in OLED display. Furthermore, the half width of the peak maximum is only 30 nm; which has an excellent color purity for OLED application. The very narrow linewidth might be attributed to a very rigid ligand structure. In other words, the geometry does not change much between the excited state and ground state. The redox property is listed in the following Table 1 to compare with IrPPY; a standard green emitter for OLEDs. Compound 99 has a shallower HOMO and a deeper LUMO than IrPPY. As a result, Compound 99 has a smaller electrochemical band gap than IrPPY and more saturated green color. In general, a smaller electrochemical band gap can be beneficial for OLEDs since it tends to have better stability toward charges.

TABLE 1

HOMO/LUMO comparison via Cyclic Voltammetry data				
	Oxidation potential	Reduction Potential	Gap(ev)	T1
	0.2 V	-2.33 V	2.53	502 nm
Compound 99				
	0.3 V	-2.7 V	3	510 nm
IrPPY				

The reduction potentials are based on values measured from differential pulsed voltammetry and are reported relative to a ferrocene/ferrocenium redox couple used as an internal reference (0.45V vs SCE). The following condition was applied for electrochemical measurement: Anhydrous DMF was used as the solvent under inert atmosphere and 0.1M tetra(n-butyl)ammonium hexafluorophosphate was used as the supporting electrolyte; a glassy carbon rod was used as the working electrode; a platinum wire was used as the counter electrode; and a silver wire was used as the reference electrode.

[0138] It is understood that the various embodiments described herein are by way of example only, and are not intended to limit the scope of the invention. For example, many of the materials and structures described herein may be substituted with other materials and structures without deviating from the spirit of the invention. The present invention as claimed may therefore include variations from the particular examples and preferred embodiments described herein, as will be apparent to one of skill in the art. It is understood that various theories as to why the invention works are not intended to be limiting.

What is claimed is:

1. A method for forming a metal-carbene bond, the method comprising:

mixing a metal precursor with a carbene salt, a weak base salt, and a solvent to form a reaction mixture; and heating the reaction mixture, wherein the weak base salt has pKa greater than 4, whereby the reaction mixture comprises a metal-carbene complex.

2. The method of claim 1, wherein the metal precursor is a second or third row transition metal.

3. The method of claim 1, wherein the metal precursor is selected from the group consisting of Ir, Rh, Re, Ru, Os, Pt, and Pd.

4. The method of claim 1, wherein the metal precursor is a halide salt.

5. The method of claim 1, wherein the metal precursor is selected from the group consisting of K_2PtCl_4 , Na_2PtCl_4 , PtCl_2 , $\text{PtCl}_2(\text{DMSO})_2$, $\text{Pt}(\text{COD})\text{Cl}_2$, $\text{IrCl}_3 \cdot x\text{H}_2\text{O}$, $\text{Na}_2\text{IrCl}_6 \cdot x\text{H}_2\text{O}$, $(\text{NH}_4)_2\text{IrCl}_6$, $\text{K}_3\text{IrCl}_6 \cdot x\text{H}_2\text{O}$, Na_2IrBr_6 , $[(\text{COD})\text{IrCl}]_2$, $\text{OsCl}_3 \cdot x\text{H}_2\text{O}$, $(\text{NH}_4)_2\text{OsCl}_6$, Na_2OsCl_6 , and $\text{OsCl}_2(\text{DMSO})_2$.

6. The method of claim 1, wherein the carbene salt is a carbon carbene salt.

7. The method of claim 1, wherein the carbene salt is a N-heterocyclic carbene salt.

8. The method of claim 1, wherein the carbene salt comprises a tetradentate ligand.

9. The method of claim 1, wherein the carbene salt is a carbene halide salt.

10. The method of claim 1, wherein the weak base salt is selected from the group consisting of: sodium acetate, potassium acetate, sodium butyrate, potassium butyrate, sodium propionate, and potassium propionate.

11. The method of claim 1, wherein the solvent is the corresponding weak acid of the weak base salt.

12. The method of claim 1, wherein the solvent is selected from the group consisting of acetic acid, propanoic acid, pivalic acid, and butyric acid.

13. The method of claim 1, wherein the heating step is carried out in a microwave reactor.

14. The method of claim 1, wherein the reaction mixture has a carbene salt concentration and a free carbene concentration and the free carbene concentration is less than 10% of the carbene salt concentration.

15. The method of claim 1, wherein the reaction mixture has a carbene salt concentration and a free carbene concentration and the free carbene concentration is less than 1% of the carbene salt concentration.

16. The method of claim 1, wherein the reaction mixture has a carbene salt concentration and a free carbene concentration and the free carbene concentration is less than 0.1% of the carbene salt concentration.

17. The method of claim 1, wherein the method produces a metal-carbene complex having a yield of at least 50%.

18. The method of claim 1, wherein the method produces a metal-carbene complex having a yield of at least 70%.

* * * * *

专利名称(译)	有机电致发光材料和器件		
公开(公告)号	US20190044075A1	公开(公告)日	2019-02-07
申请号	US16/154864	申请日	2018-10-09
[标]申请(专利权)人(译)	环球展览公司		
申请(专利权)人(译)	通用显示器公司		
当前申请(专利权)人(译)	通用显示器公司		
[标]发明人	LIN CHUN XIA CHUANJUN TSAI JUI YI		
发明人	LIN, CHUN XIA, CHUANJUN TSAI, JUI-YI		
IPC分类号	H01L51/00 C07D209/82 H01L51/50 C07D233/54 C09K11/06 C07D401/12 C07D213/69 C07F15/00 C07F7/08 C07D235/04		
CPC分类号	C07D209/82 H01L51/5012 C07D233/54 H01L51/5016 C09K2211/1044 C09K2211/1007 C09K11/06 C07D401/12 C07D213/69 H01L51/0087 C07F15/0086 C07F7/0814 C09K2211/185 C09K2211/1029 C07F15/0093 C07D235/04		
优先权	61/924340 2014-01-07 US		
外部链接	Espacenet USPTO		

摘要(译)

公开了一种形成金属 - 卡宾键的新方法。

