



US010141287B2

(12) **United States Patent**
Zou et al.

(10) **Patent No.:** **US 10,141,287 B2**
(45) **Date of Patent:** **Nov. 27, 2018**

(54) **TRANSFERRING METHOD,
MANUFACTURING METHOD, DEVICE AND
ELECTRONIC APPARATUS OF MICRO-LED**

(71) Applicant: **Goertek, Inc.**, Weifang, Shandong (CN)

(72) Inventors: **Quanbo Zou**, Weifang (CN); **Zhe Wang**, Weifang (CN)

(73) Assignee: **GOERTEK, INC.**, Weifang, Shandong (CN)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **15/531,194**

(22) PCT Filed: **Jul. 14, 2015**

(86) PCT No.: **PCT/CN2015/083990**

§ 371 (c)(1),

(2) Date: **May 26, 2017**

(87) PCT Pub. No.: **WO2017/008254**

PCT Pub. Date: **Jan. 19, 2017**

(65) **Prior Publication Data**

US 2017/0330867 A1 Nov. 16, 2017

(51) **Int. Cl.**

H01L 25/075 (2006.01)

H01L 33/00 (2010.01)

(Continued)

(52) **U.S. Cl.**

CPC **H01L 25/0753** (2013.01); **H01L 33/0079** (2013.01); **H01L 33/0095** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC H01L 33/0095; H01L 33/52; H01L 2933/005; H01L 2933/0066

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,333,860 B1 12/2012 Bibl et al.

8,426,227 B1 4/2013 Bibl et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CN 101859728 A 10/2010

KR 10-2012-0006859 A 1/2012

WO 2013154181 A1 10/2013

Primary Examiner — Jay C Chang


Assistant Examiner — Mikka Liu

(74) *Attorney, Agent, or Firm* — Hultquist, PLLC; Steven J. Hultquist

(57) **ABSTRACT**

The present invention discloses a transferring method, a manufacturing method, a device and an electronic apparatus of micro-LED. The method for transferring micro-LED comprises: forming micro-LEDs on a laser-transparent original substrate, wherein the micro-LEDs are lateral micro-LEDs whose P electrodes and N electrodes are located on one side; bringing the P electrodes and N electrodes of the lateral micro-LEDs into contact with pads preset on a receiving substrate; and irradiating the original substrate with laser from the original substrate side to lift-off the lateral micro-LEDs from the original substrate. A technical effect of using lateral micro-LEDs lies in that the processing for N metal electrode after the micro-LED transfer can be omitted.

10 Claims, 15 Drawing Sheets



- (51) **Int. Cl.**
H01L 33/52 (2010.01)
H01L 33/62 (2010.01)
H01L 33/20 (2010.01)
- (52) **U.S. Cl.**
 CPC *H01L 33/52* (2013.01); *H01L 33/62*
 (2013.01); *H01L 33/20* (2013.01); *H01L*
2224/16225 (2013.01); *H01L 2224/83192*
 (2013.01); *H01L 2933/005* (2013.01); *H01L*
2933/0066 (2013.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,470,621 B2	6/2013	Kuo et al.	
2010/0015744 A1 *	1/2010	Kazinzci	H01H 1/0036 438/52
2012/0244683 A1	9/2012	Akagi	
2012/0280374 A1	11/2012	Choi et al.	
2015/0228622 A1 *	8/2015	Koyanagi	H01L 23/49838 257/777
2015/0340346 A1 *	11/2015	Chu	H01L 25/0753 257/89

* cited by examiner




FIG. 1




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F




FIG. 2G




FIG. 3




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 4D




FIG. 4E




FIG. 4F




FIG. 4G




FIG. 4H




FIG. 4I




FIG. 4J




FIG. 4K




FIG. 4L




FIG. 5




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 6D




FIG. 6E




FIG. 6F




FIG. 7A




FIG. 7B




FIG. 7C




FIG. 7D




FIG. 7E




FIG. 7F




FIG. 7G




FIG. 7H




FIG. 7I




FIG. 7J




FIG. 7K




FIG. 7L

FIG. 9




FIG. 10

1

TRANSFERRING METHOD, MANUFACTURING METHOD, DEVICE AND ELECTRONIC APPARATUS OF MICRO-LED

CROSS-REFERENCE TO RELATED APPLICATION

This application is a U.S. national phase under the provisions of 35 U.S.C. § 371 of International Patent Application No. PCT/CN2015/083990 filed Jul. 14, 2015. The disclosure of such international patent application is hereby incorporated herein by reference in its entirety, for all purposes.

FIELD OF THE INVENTION

The present invention relates to Micro-Light Emitting Diode (micro LED) array for display, and in particular, to a method for transferring micro-LED, a method for manufacturing a micro-LED device, a micro-LED device and an electronic apparatus containing a micro-LED device.

BACKGROUND OF THE INVENTION

The micro-LED technology refers to the LED array of small size integrated on a substrate with high density. Currently, the micro-LED technology is starting development, and it is expected in the industry that a high-quality micro-LED product comes into the market. High-quality micro-LED will have a deep affection on the conventional display products such as LCD/OLED that have already been put into the market.

In the process of manufacturing micro-LEDs, micro-LEDs are first formed on a donor wafer, and then the micro-LEDs are transferred to a receiving substrate. The receiving substrate is a display screen, for example.

One difficulty during manufacturing a micro-LED lies in how to transfer a micro-LED from a donor wafer to a receiving substrate. In the prior art, the transfer is generally performed by means of electrostatic pick-up. A transfer head array will be needed during the electrostatic pick-up. The structure of the transfer head array is relatively complicated, and the stability thereof shall be considered. An extra cost shall be paid for manufacturing a transfer head array. A phase change shall be made before pick-up with the transfer head array. In addition, during manufacturing with a transfer head array, limitations apply to the thermo budget of a micro-LED for phase change, which is generally lower than 350° C., or more specifically, lower than 200° C.; otherwise, the performance of the micro-LED will be degraded. It generally requires two transfers during the manufacturing with transfer head array, i.e., the transfer from a donor wafer to a carrier wafer and the transfer from the carrier wafer to a receiving substrate.

U.S. Pat. No. 8,333,860B1 discloses an array of transfer heads for transferring micro devices, in which a voltage is applied to the electrode in the transfer head to pick-up a micro device. This patent is fully incorporated hereby as reference herein.

U.S. Pat. No. 8,426,227B1 discloses a method of forming a micro light emitting diode array, in which a micro-LED array is transferred to a receiving substrate by using a transfer head array. This patent is fully incorporated hereby as reference herein.

SUMMARY OF THE INVENTION

One object of this invention is to provide a new technical solution for transferring a micro-LED.

2

According to an embodiment of the present invention, there is provided a method for transferring micro-LED, comprising: forming micro-LEDs on a laser-transparent original substrate, wherein the micro-LEDs are lateral micro-LEDs whose P electrodes and N electrodes are located on one side; bringing the P electrodes and N electrodes of the lateral micro-LEDs into contact with pads preset on a receiving substrate; and irradiating the original substrate with laser from the original substrate side to lift-off the lateral micro-LEDs from the original substrate.

Preferably, the method further comprises: providing an anisotropic conductive layer on a receiving substrate. Preferably, the P electrodes and N electrodes of the lateral micro-LEDs are brought into contact with pads preset on a receiving substrate via the anisotropic conductive layer. Preferably, the method further comprises: processing the anisotropic conductive layer, to electrically connect the P electrodes and N electrodes of the lateral micro-LEDs with the pads on the receiving substrate.

Preferably, the anisotropic conductive layer is at least one of an anisotropic conductive film, an anisotropic conductive paste and an anisotropic conductive tape.

Preferably, the P electrodes and N electrodes of the lateral micro-LEDs are brought into contact with pads preset on a receiving substrate by means of an action of gravity.

Preferably, the P electrodes and N electrodes of the lateral micro-LEDs are brought into contact with pads preset on a receiving substrate by means of an action of electrostatic force.

Preferably, the electrostatic force is applied by applying voltage to the pads.

Preferably, the lateral micro-LEDs contain magnetic substance, and the P electrodes and N electrodes of the lateral micro-LEDs are brought into contact with pads preset on a receiving substrate by means of an action of electromagnetic force.

Preferably, the P electrodes and N electrodes of the lateral micro-LEDs include solder bumps, and the method further comprises: bonding the solder bumps with the pads.

According to another embodiment of the present invention, there is provided a method for manufacturing a micro-LED device, comprising transferring lateral micro-LEDs to a receiving substrate by using the method according to the present invention.

According to another embodiment of the present invention, there is provided a micro-LED device, which is manufactured by using the method according to the present invention.

According to another embodiment of the present invention, there is provided an electronic apparatus, containing a micro-LED device according to the present invention.

In addition, it should be understood by a person skilled in the art that, although a lot of problems exist in the prior art, the solution of each embodiment or each claim could just improve in one or several aspects, and it is not necessary for it to solve all the technical problems listed in the Background of the Invention or in the prior art. It should be understood by a person skilled in the art that content which is not mentioned in a claim should not be regarded as a limitation to said claim.

Further features of the present invention and advantages thereof will become apparent from the following detailed description of exemplary embodiments according to the present invention with reference to the attached drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are incorporated in and constitute a part of the specification, illustrate embodi-

ments of the invention and, together with the description thereof, serve to explain the principles of the invention.

FIG. 1 shows a flow chart of an illustrative embodiment of the method according to the present invention.

FIG. 2A to 2G shows an example for transferring a micro-LED according to the present invention.

FIG. 3 shows a flow chart of another illustrative embodiment of the method according to the present invention.

FIGS. 4A to 4L show another example for transferring a micro-LED according to the present invention.

FIG. 5 shows a flow chart of still another illustrative embodiment of the method according to the present invention.

FIGS. 6A to 6F show an example for transferring red micro-LEDs according to the present invention.

FIGS. 7A to 7L show still another example for transferring a micro-LED according to the present invention.

FIG. 8 shows still an example for transferring a lateral micro-LED according to the present invention.

FIG. 9 shows still another example for transferring a lateral micro-LED according to the present invention.

FIG. 10 shows a flow chart of still another illustrative embodiment of the method according to the present invention.

DETAILED DESCRIPTION OF THE EMBODIMENTS

Various exemplary embodiments of the present invention will now be described in detail with reference to the drawings. It should be noted that the relative arrangement of the components and steps, the numerical expressions, and numerical values set forth in these embodiments do not limit the scope of the present invention unless it is specifically stated otherwise.

The following description of at least one exemplary embodiment is merely illustrative in nature and is in no way intended to limit the invention, its application, or uses.

Techniques, methods and apparatus as known by one of ordinary skill in the relevant art may not be discussed in detail but are intended to be part of the specification where appropriate.

In all of the examples illustrated and discussed herein, any specific values should be interpreted to be illustrative only and non-limiting. Thus, other examples of the exemplary embodiments could have different values.

Notice that similar reference numerals and letters refer to similar items in the following figures, and thus once an item is defined in one figure, it is possible that it need not be further discussed for following figures.

Embodiments and examples of the present invention will be described below with reference to the drawings.

FIG. 1 shows a flow chart of an illustrative embodiment of the method for transfer micro-LED according to the present invention.

As shown in FIG. 1, at step S1100, a micro-LED is formed on a laser-transparent original substrate.

The laser-transparent original substrate can be a sapphire substrate, SiC substrate and so on, for example. The micro-LED can be used for being mounted on a display screen panel.

It should be understood by a person skilled in the art that one micro-LED could be formed on the original substrate, or a plurality of micro-LED could be formed on the original substrate. For example, a plurality of micro-LEDs can be formed on the laser-transparent original substrate. The plurality of micro-LEDs can form an array.

In an example, in a case where a plurality of micro-LEDs are formed on the laser-transparent original substrate, the original substrate can be singulated or divided into multiple pieces for more flexible transferring.

At step S1200, the micro-LED is brought into contact with a pad preset on a receiving substrate.

For example, the receiving substrate is a display screen panel.

For example, the pad can be set for red pixel array, yellow pixel array or blue pixel array.

In an example, in a case where a plurality of micro-LED are formed, at least one micro-LED of the plurality of micro-LEDs can be brought into contact with at least one pad preset on the receiving substrate. The at least one micro-LED could be one, several or all of the plurality of micro-LEDs. It should be understood by a person skilled in the art that, although it is just described here that at least one micro-LED, which is expected to be lifted-off, is in contact with a pad, a remaining micro-LED of the plurality of micro-LEDs can also be in contact with a pad.

For example, in the step of contact (S1200), the micro-LED can be brought into contact with the pad preset on the receiving substrate via a liquid thin film. For example, the liquid thin film can include flux. Herein, the lift-off of a micro-LED will be easy through the surface tension force of the liquid thin film (flux), and the successful rate is high.

At step S1300, the original substrate is irradiated with laser from the original substrate side to lift-off the micro-LED from the original substrate.

In an example, in a case where at least one micro-LED is in contact with pad, at least one area on the original substrate can be irradiated with laser from the original substrate side to lift-off the at least one micro-LED from the original substrate. For example, a technician can select the at least one area. For example, the at least one area corresponds to the at least micro-LED, respectively. The at least one area can be just partial area on the original substrate, or can be the whole area.

In another example, the original substrate can be offset for transferring additional micro-LEDs.

In another example, after the transferring using the original substrate, an additional laser-transparent backup substrate can be used to cope with a situation in which micro-LEDs are missing at some points on the display screen panel. For example, a micro-LED can be formed on an additional laser-transparent backup substrate; the micro-LED on the backup substrate is brought into contact with a pad preset on a receiving substrate; and the backup substrate is irradiated with laser from the backup substrate side to lift-off the micro-LED from the backup substrate. In such a way, the quality of a display screen can further be improved.

An array of micro-LEDs can be formed on the receiving substrate after the transferring of micro-LEDs to the receiving substrate.

After the transferring of micro-LEDs to the receiving substrate, the present invention can further include subsequent steps.

For example, the lifted-off micro-LEDs can be reflow-soldered on the receiving substrate. A negative electrode can be deposited on the micro-LEDs. The reflow-soldering can be performed after micro-LEDs of each color are transferred. Alternatively, the reflow-soldering can be performed after micro-LEDs of all colors are transferred.

In addition, the soldered micro-LED can be filled with polymer. For example, a confocal dielectric deposition can be used instead of polymer filling.

In another embodiment, the present invention further includes a method for manufacturing a micro-LED device. The manufacturing method comprises transferring a micro-LED to a receiving substrate by using the method for transferring a micro-LED according to the present invention.

In another embodiment, the present invention further includes a micro-LED device, such as a display screen device. The micro-LED device can be manufactured by using the method for manufacturing a micro-LED device according to the present invention.

In comparison with the prior art, under the similar conditions, the micro-LED manufactured by using the solution of the present invention is relatively simple and reliable while maintaining a high quality, and the through put thereof is relatively high with low cost.

In another embodiment, the present invention further includes an electronic apparatus. The electronic apparatus contains a micro-LED device according to the present invention. For example, the electronic apparatus can be a mobile phone, a pad computer and so on.

In the solution of the present invention, a micro-LED is formed directly on the original substrate and it is transferred to a receiving substrate by means of laser lift-off. The solution of this invention has not been conceived by the prior art.

In addition, the micro-LED can be selectively transferred through the present invention.

In addition, in the solution of the present invention, the transfer can be performed only once while two transfers are needed in the prior art.

In addition, in comparison with the prior art, the solution of the present invention is relatively efficient, the cost is relatively low and product performance degrade due to an extra thermal budget will not occur.

In addition, in comparison with the prior art using a pick-up head, the present invention does not need a complicated pick-up system, and thus the cost of product manufactured using the present invention will relatively low and reliable.

In addition, since it does not need the temporary bonding in the prior art between the micro-LED and the intermediate carrier substrate, the cost can be further decreased by this invention.

Since it is not necessary to consider the phase change of bonding layer considered in the prior art using pick-up head, the manufacturing method of the present invention can have a relatively high through put and the extra thermal load limitation will be less. Consequently, under the similar conditions, the manufactured micro-LED will have a higher performance.

An example for transferring a micro-LED according to the present invention will be described below with reference to FIGS. 2A to 2G.

As shown in FIG. 2A, micro-LEDs 2 are formed on a laser-transparent original substrate 1 such as sapphire substrate. The micro-LEDs 2 have a vertical micro-LED structure, for example. The micro-LEDs 2 contains, for example, a n-doped GaN layer, a multiple quantum well structure, a p-doped GaN layer, a p metal electrode, a bump, and so on.

As shown in FIG. 2A, the plurality of micro-LEDs 2 can be singulated.

As shown in FIG. 2B, the original substrate 1 is flipped over, and is aligned with a receiving substrate 4 with liquid thin film (for example, containing flux) 5. The micro bumps on the micro-LEDs are in contact with the flux. Pads 3 are preset on the receiving substrate 4. For example, the pads 3

include pad 3r for receiving red micro-LED, pad 3b for receiving blue micro-LED and pad 3g for receiving green micro-LED.

As shown in FIG. 2C, partial areas 7 on the original substrate are selectively irradiated with laser 7, to lift off the selected micro-LEDs 2a, 2b of the plurality of formed micro-LEDs from the original substrate.

As shown in FIG. 2D, the original substrate 1 is lifted up. Because of the function of the surface tension force of the liquid thin film, the selected micro-LEDs 2a, 2b are lifted-off easily, while the other micro-LEDs are remained on the original substrate 1.

Then, the original substrate is moved and the operations of FIGS. 2C to 2D are repeated, so that a plurality of micro-LEDs are transferred to the receiving substrate.

As shown in FIG. 2E, the plurality of micro-LEDs are transferred to the receiving substrate 4.

As shown in FIG. 2F, for example, the plurality of micro-LEDs are soldered onto the receiving substrate through reflow soldering. Then, the flux is cleaned.

As shown in FIG. 2G, the receiving substrate is filled with polymer 8 and is sealed. Then, n-metal electrode 9 is deposited, for example, using ITO material.

FIG. 3 shows a flow chart of another illustrative embodiment of the method for transferring a micro-LED according to the present invention.

As shown in FIG. 3, at step S2100, micro-LEDs are formed on a laser-transparent original substrate.

At step S2200, an anisotropic conductive layer is provided on a receiving substrate.

For example, the anisotropic conductive layer is at least one of an anisotropic conductive film (ACF), an anisotropic conductive paste (ACP) and an anisotropic conductive tape (ACT).

At step S2300, the micro-LEDs are brought into contact with the anisotropic conductive layer on the receiving substrate. For example, the micro-LEDs are adhered to the anisotropic conductive layer on the receiving substrate. At this step, the micro-LEDs can be aligned with the receiving substrate in advance, for example.

At step S2400, the original substrate is irradiated with laser from the original substrate side to lift-off the micro-LEDs from the original substrate.

For example, the above steps can be performed with respect to red micro-LEDs, green micro-LEDs and blue micro-LEDs, respectively. Since the transfer with respect to the three micro-LEDs can be regarded as a simple repeat of the above steps, they are not repeated here. As long as each of the above steps is performed in a solution, the solution will be covered by this invention.

At step S2500, the anisotropic conductive layer is processed to electrically connect the micro-LEDs (its electrodes) with the pads on the receiving substrate.

In an example, pressure can be applied on the anisotropic conductive layer from the micro-LED side by using an auxiliary substrate. For example, the temperature of processing the anisotropic conductive layer can be between 150° C. and 200° C. For example, the applied pressure is between 1 MPa and 4 MPa. For example, the time period of applying pressure is between 10 second and 30 second.

In an example, the auxiliary substrate can be a flat rigid substrate. The inventors of the present application have found that the possible displacement of the micro-LEDs can be reduced by using a rigid substrate. This point has not noticed by a person skilled in the art.

For example, the surface of the auxiliary substrate can be coated with temporary bonding polymer. In this situation,

the step **S2500** can further comprises: bonding the auxiliary substrate with the anisotropic conductive layer via the temporary bonding polymer; and after applying pressure, de-bonding the auxiliary substrate via the temporary bonding polymer, to remove the auxiliary substrate. The advantage of temporarily bonding the auxiliary substrate with the anisotropic conductive layer lies in that, the positions of the micro-LEDs can be relatively fixed, and the displacement of micro-LEDs during processing the anisotropic conductive layer is reduced.

After the above processes, normal subsequent processes can be done on the micro-LEDs. For example, the subsequent processes include: etching the temporary bonding polymer, to expose the epitaxial layers of the micro-LEDs; forming N-metal electrodes on the epitaxial layers of the micro-LEDs; and performing encapsulation on the N-metal electrodes.

For example, the receiving substrate can be a display substrate. Leads and pads can be set on the receiving substrate in advance, to be electronically connected with the micro-LEDs.

In this embodiment, the micro-LEDs and the receiving substrate are connected through an anisotropic conductive layer. This approach of processing is relatively simple and is more suitable for production in large bulk.

In another embodiment, the present invention further provides a method for manufacturing a micro-LED device. The manufacturing method comprises transferring micro-LEDs to a receiving substrate by using the method according to the present invention. For example, the receiving substrate is a display screen or display substrate. The micro-LED device is a display device, for example.

In another embodiment, the present invention further provides a micro-LED device, such as a display device. The micro-LED device can be manufactured by using the method for manufacturing a micro-LED device according to the present invention. In the micro-LED device according to the embodiment, the micro-LEDs come into electronic contact with the pads on the receiving substrate via the anisotropic conductive layer, which is different from the micro-LED device in the prior art.

In another embodiment, the present invention further provides an electronic apparatus. The electronic apparatus contains a micro-LED device according to the embodiment. For example, the electronic apparatus can be a mobile phone, a pad and so on.

FIG. 4A to 4L shows another example for transferring a micro-LED according to the present invention.

As shown in FIG. 4A, an original substrate **201** such as a sapphire substrate has red micro-LEDs **202** thereon. The receiving substrate **204** such as display substrate has an anisotropic conductive film (ACF) **203** thereon. The receiving substrate **204** has signal leads **205** and pads **205'** for connecting micro-LEDs.

As shown in FIG. 4B, the original substrate **201** (red micro-LED **202**) is brought into contact with the anisotropic conductive film **203** with a light force. For example, the red micro-LEDs **202** to be transferred can be aligned with the pads on the receiving substrate **204**. The original substrate **201** is irradiated with laser **206**, to selectively lift-off red micro-LEDs.

FIG. 4C shows lifted-off red micro-LEDs **202r**.

FIG. 4D shows an original substrate **207** and the green micro-LEDs **208** thereof. The green micro-LEDs to be lifted-off are aligned with the pads on the receiving substrate **204**.

FIG. 4E shows the situation in which the green micro-LEDs **208** are in contact with the anisotropic conductive film **203** with a light force. At least one green micro-LED is selectively lifted-off by using laser **209**.

FIG. 4F shows lifted-off red micro-LEDs **202r** and green micro-LEDs **208g**.

FIG. 4G shows an original substrate **210** and the blue micro-LEDs **211** thereof. The blue micro-LEDs to be lifted-off are aligned with the pads on the receiving substrate **204**.

FIG. 4H shows the situation in which the blue micro-LEDs **211** are in contact with the anisotropic conductive film **203** with a light force. At least one blue micro-LED is selectively lifted-off by using laser **212**.

FIG. 4I shows lifted-off red micro-LEDs **202r**, green micro-LEDs **208g** and blue micro-LEDs **211b**.

After the transfer of micro-LEDs in the three colors, an inspection and repair can be performed with respect to any defect.

FIG. 4J shows an auxiliary substrate **213**. The auxiliary substrate **213** is a flat rigid substrate, such as a glass substrate. Polymer **214** such as 3M LC5200/5320 is coated on the auxiliary substrate **213**. The polymer can be cured through UV and can be de-bonded through red laser.

In FIG. 4K, the ACF **203** is processed through the auxiliary substrate **213**. For example, the processing condition is that the temperature is between 150° C. and 200° C., the applied pressure is between 1 MPa and 4 MPa, the time period of applying pressure is between 10 second and 30 second. Through these processes, the ACF **203** interconnects the micro-LEDs with corresponding pad in the vertical direction.

Then, the auxiliary substrate **213** is de-bonded (through the polymer **214**).

In FIG. 4L, the normal subsequent processes are performed: etching the polymer **214**, to expose the epitaxial layers of the micro-LEDs; forming N-metal electrodes **215** (for example, ITO electrodes) on the epitaxial layers of the micro-LEDs; and performing encapsulation **216** on the N-metal electrodes (for example, PET lamination).

FIG. 5 shows a flow chart of still another illustrative embodiment of the method for transferring a micro-LED according to the present invention.

As shown in FIG. 5, at step **S3100**, at least one micro-LED is transferred from an original substrate to a support body. For example, the original substrate is laser-transparent.

In an example, this step can comprises: mounting the original substrate onto the support body, wherein the micro-LEDs are formed on the original substrate, the support body has light-release adhesive on its surface, and the micro-LEDs are adhered to the support body via the light-release adhesive; irradiating the original substrate with laser from the original substrate side, for lifting-off the at least one micro-LED from the original substrate, and irradiating light from the support body side, to release un-lifted-off micro-LEDs. In this example, the support body is transparent.

For example, the light-release adhesive can be a UV tape. For example, the support body is stiff. The displacement of micro-LEDs during transfer will have affect on the quality of the final product. The inventors of this application have found that this displacement can be reduced by using a stiff support body. This point has not been noticed by a person skilled in the art. For example, the material of the support body can be PET.

Generally, it is difficult to form red micro-LEDs on a laser-transparent substrate such as a sapphire substrate. Accordingly, in an example, the red micro-LEDs are formed

in advance and then are transferred to an original substrate, for being finally transferred to a receiving substrate. For example, in this embodiment, red micro-LEDs can be formed on a growth substrate. Then, the red micro-LEDs are transferred to an intermediate substrate. After that, the red micro-LEDs are transferred from the intermediate substrate to the original substrate.

At step S3200, the at least one micro-LED are transferred from the support body to a backup substrate.

For example, the backup substrate has elastomer or polymer on its surface. For example, the at least one micro-LED are bonded to the backup substrate through the elastomer or polymer.

In an example, this step can further comprises: bonding the support body with the at least one micro-LED to the backup substrate, and irradiating light from the support body side, to release the at least one micro-LED.

At step S3300, the at least one micro-LED are transferred from the backup substrate to a receiving substrate.

In an example, the step can further comprise: aligning the at least one micro-LED with the pads on the receiving substrate; and lifting-off the at least one micro-LED via the elastomer or polymer.

For example, the above transfer steps can be performed with respect to red micro-LEDs, blue micro-LEDs and green micro-LEDs, respectively. They will not be repeatedly described here.

After the above processes, normal subsequent processes can be done on the micro-LEDs. For example, the subsequent processes include: coating polymer on the receiving substrate with micro-LEDs; curing the polymer; etching the polymer, to expose the epitaxial layers of the micro-LEDs; forming N-metal electrodes on the epitaxial layers of the micro-LEDs; and performing encapsulation on the N-metal electrodes.

The inventors of this invention have found that during the transfer of micro-LEDs, usually, only part of the micro-LEDs on the original substrate are transferred. If the micro-LEDs are directly transferred to a receiving substrate, the remaining micro-LEDs on the original substrate are often contaminated. In this embodiment, this contamination can be reduced through the transfer via an intermediate support body.

In another embodiment, the present invention further provides a method for manufacturing a micro-LED device. The manufacturing method comprises transferring micro-LEDs to a receiving substrate by using the method for transferring micro-LEDs according to this embodiment. For example, the receiving substrate is a display screen or display substrate. The micro-LED device is a display device, for example.

In another embodiment, the present invention further provides a micro-LED device, such as a display device. The micro-LED device can be manufactured by using the method for manufacturing a micro-LED device according to said embodiment.

In another embodiment, the present invention further provides an electronic apparatus. The electronic apparatus contains a micro-LED device according to the embodiment. For example, the electronic apparatus can be a mobile phone, a pad and so on.

Generally, red micro-LEDs cannot be directly formed on a laser-transparent original substrate such as sapphire substrate. Thus, it is required that red micro-LEDs are formed on an additional substrate in advance, and then are trans-

ferred to a sapphire substrate. FIG. 6A to 6F shows an example for transferring red micro-LEDs according to the present invention.

As shown in FIG. 6A, red micro-LEDs 302 are formed on a growth substrate 301 such as GaAs substrate.

As shown in FIG. 6B, the red micro-LEDs 302 are bonded with intermediate substrate 304 such as silicon substrate, through temporary bonding polymer 303. The polymer 303 is a thermal release tape (TRT), for example.

As shown in FIG. 6C, the growth substrate 301 is removed by a wet etching method, for example.

As shown in FIG. 6D, a light resist 305 is coated on an original substrate 306 such as sapphire substrate. The original substrate 306 and the red micro-LEDs 302 are bonded through the resist 305. The resist 305 can endure the temperature above 200° C.; generally above 250° C.

As shown in FIG. 6E, the polymer 303 is processed under a temperature less than 200° C., to remove the intermediate substrate 304.

As shown in FIG. 6F, an O₂ plasma etching is performed on the resist 305, to isolate the respective red micro-LEDs 302.

FIG. 7A to 7L shows still another example for transferring a micro-LED according to the present invention.

As shown in FIG. 7A, the original substrate 406 has resist 405 and red micro-LEDs 402 thereon. The red micro-LEDs 402 are mounted onto a UV tape 411. The UV tape 411 is located on a stiff PET support body 402. The red micro-LEDs are selectively lifted-off through laser 413.

As shown in FIG. 7B, an ultraviolet is irradiated from the support body 412 side, to release un-lifted-off red micro-LEDs.

The lifted-off red micro-LEDs 402r are easily separated from the original substrate 406. As shown in FIG. 7C, the lifted-off red micro-LEDs 402r are adhered on the UV tape 411, while other red micro-LEDs remain on the original substrate 406.

As shown in FIG. 7D, the backup substrate 415 such as glass substrate has elastomer/polymer 416 thereon. For example, the elastomer/polymer 416 is coated on the backup substrate 415 through spin coating. For example, the elastomer/polymer 416 is PDMS or 3M LC 5320, and can be cured through ultraviolet, for example.

As shown in FIG. 7E, the support body is fully irradiated with ultraviolet, to release the red micro-LEDs and elastomer/polymer 416.

After that, for example, if the micro-LEDs do not have bumps thereon, the micro-LEDs on the backup substrate 415 can be screen-printed using silver paste.

As shown in 7F, the red micro-LEDs on the backup substrate 415 are aligned with the pads 419 on the receiving substrate 417. For example, the receiving substrate is a display substrate, and includes signal leads 418. For example, the red micro-LEDs are bonded to the pads 419 through reflow. The temperature of reflow can be more than 260° C. Then, the backup substrate 415 is separated from the receiving substrate 417 through laser lift-off.

FIG. 7G shows separated receiving substrate 417. The receiving substrate 417 has pads 419 and red micro-LEDs 402r thereon.

FIG. 7H shows a schematic diagram of transferring red micro-LEDs 422g from a backup substrate 420 to the receiving substrate 417. The backup substrate 420 has elastomer/polymer 421.

FIG. 7I shows the separated receiving substrate 417. The receiving substrate 417 has pads 419, red micro-LEDs 402r and green micro-LEDs 402r thereon.

FIG. 7J shows a schematic diagram of transferring blue micro-LEDs **425b** from a backup substrate **423** to the receiving substrate **417**. The backup substrate **423** has elastomer/polymer **424**.

FIG. 7K shows the separated receiving substrate **417**. The receiving substrate **417** has pads **419**, red micro-LEDs **402r**, green micro-LEDs **402g** and blue micro-LEDs **425b** thereon.

In FIG. 7L, the normal subsequent processes are performed on the transferred micro-LEDs: coating polymer **426** on the receiving substrate with micro-LEDs; curing the polymer **426**; etching the polymer, to expose the epitaxial layers of the micro-LEDs; forming N-metal electrodes **427** on the epitaxial layers of the micro-LEDs; and performing encapsulation (not shown) on the N-metal electrodes.

The solution of the present invention can use both vertical micro-LEDs and lateral micro-LEDs (flip-chip micro-LEDs). The micro-LEDs of vertical structure shown in the previous figures are illustrative and do not limit the scope of the present invention. FIG. 8 shows an example of lateral micro-LEDs.

In the example of FIG. 8, the micro-LEDs are lateral micro-LEDs. In the lateral micro-LEDs, the P electrodes and the N electrodes thereof are located on the same side. FIG. 8 shows a red lateral micro-LED **505**, a green lateral micro-LED **506** and a blue lateral micro-LED **507**. The red lateral micro-LED **505** contains a P electrode **505p** (positive electrode) and an N electrode **505n** (negative electrode). The green lateral micro-LED **506** contains a P electrode **506p** and an N electrode **506n**. The blue lateral micro-LED **507** contains a P electrode **507p** and an N electrode **507n**.

Lead structures (including pads) **515p**, **515n**, **516p**, **516n**, **517p**, **517n** are provided in the substrate **504**. The lead structures **515p**, **516p**, **517p** are for connection with positive electrodes. The lead structures **515n**, **516n**, **517n** are for connection with negative electrodes.

In the example of FIG. 8, the electrodes **505p**, **505n**, **506p**, **506n**, **507p**, **507n** are connected to the lead structures **515p**, **515n**, **516p**, **516n**, **517p**, **517n** via an anisotropic conductive layer **503**.

Polymer **502** can be coated between the lateral micro-LEDs. A transparent cover **501** can be provided over the lateral micro-LEDs.

FIG. 9 shows another example of lateral micro-LEDs. The difference between the example of FIG. 9 and that of FIG. 8 lies in that in FIG. 9, the lateral micro-LEDs are connected to the substrate via solder rather than an anisotropic conductive layer.

FIG. 9 shows a red lateral micro-LED **605**, a green lateral micro-LED **606** and a blue lateral micro-LED **607**. The red lateral micro-LED **605** contains a P electrode **605p** and an N electrode **605n**. The green lateral micro-LED **606** contains a P electrode **606p** and an N electrode **606n**. The blue lateral micro-LED **607** contains a P electrode **607p** and an N electrode **607n**.

Lead structures (including pads) **615p**, **615n**, **616p**, **616n**, **617p**, **617n** are provided in the substrate **604**. The lead structures **615p**, **616p**, **617p** are for connection with positive electrodes. The lead structures **615n**, **616n**, **617n** are for connection with negative electrodes.

In the example of FIG. 9, the electrodes **605p**, **605n**, **606p**, **606n**, **607p**, **607n** include solder bumps **602**, for example. The solder bumps **602** are coated with flux, for example. The electrodes **605p**, **605n**, **606p**, **606n**, **607p**, **607n** are bonded to the lead structures **615p**, **615n**, **616p**, **616n**, **617p**, **617n**, for example, through reflow-soldering, respectively.

For example, polymer **603** can be filled between the lateral micro-LEDs and the substrate **604**. A transparent cover **601**

can be provided over the lateral micro-LEDs. These processes are well-known in the art and thus are not described in detail here.

Therefore, for example, the present invention can further include the specific application of lateral micro-LEDs. More specifically, the present invention further provides a method for transferring micro-LED. The method comprises: forming micro-LEDs on a laser-transparent original substrate, wherein the micro-LEDs are lateral micro-LEDs whose P electrodes and N electrodes are located on one side; bringing the P electrodes and N electrodes of the lateral micro-LEDs into contact with pads preset on a receiving substrate; and irradiating the original substrate with laser from the original substrate side to lift-off the lateral micro-LEDs from the original substrate.

A technical effect of using lateral micro-LEDs lies in that the processing for N metal electrode after the micro-LED transfer can be omitted. Furthermore, the wafer-level color-binning/testing can be simplified because the P electrodes and N electrodes already exist when a test at wafer-level is performed.

Furthermore, for example, in this method, an anisotropic conductive layer can be provided on a receiving substrate so as to bring the P electrodes and N electrodes of the lateral micro-LEDs into contact with the pads through the anisotropic conductive layer. Then, after lifting-off the lateral micro-LEDs from the original substrate, the anisotropic conductive layer is processed to electrically connect the P electrodes and N electrodes of the lateral micro-LEDs with the pads on the receiving substrate.

For example, the anisotropic conductive layer can be at least one of an anisotropic conductive film, an anisotropic conductive paste and an anisotropic conductive tape.

In addition to bringing the P electrodes and N electrodes of the lateral micro-LEDs into contact with pads preset on a receiving substrate by the stickiness of an anisotropic conductive layer or by the surface tension of liquid (such as flux), the present invention can further realize the contact by actions of gravity, electrostatic force and/or electromagnetic force.

For example, when the original substrate is irradiated with laser from the original substrate side, the lateral micro-LEDs are separated from the original substrate and the lateral micro-LEDs are dropped off onto the receiving substrate because of gravity.

For example, electrostatic force can be applied by applying voltage to the pads, so that the lateral micro-LEDs are dropped off onto the receiving substrate after being lifted-off from the original substrate because of the electrostatic force.

For example, in case that the lateral micro-LEDs contains magnetic substance such as Ni, a magnetic field can be provided, so that the lateral micro-LEDs are dropped off onto the receiving substrate after being lifted-off from the original substrate because of the electromagnetic force.

Similarly, the transfer method in the example of using lateral micro-LEDs can be applied to a method for manufacturing a micro-LED device for transferring the lateral micro-LEDs onto a receiving substrate. For example, the receiving substrate is a display screen or display substrate. The micro-LED device is a display device, for example.

For example, a micro-LED device, such as a display device, can be manufactured by using the manufacturing method. The micro-LED device adopts lateral micro-LEDs.

For example, the present invention further provides an electronic apparatus. The electronic apparatus contains the micro-LED device. For example, the electronic apparatus can be a mobile phone, a pad and so on.

FIG. 10 shows a flow chart of a method for transferring micro-LEDs by means of a contactless action according to the present invention.

As shown in FIG. 10, in the method for transferring micro-LEDs, at step S4100, micro-LEDs are formed on a laser-transparent original substrate.

The micro-LEDs can be lateral micro-LEDs or can be micro-LEDs of vertical structure. In a lateral micro-LED, the P electrodes and N electrodes thereof are located on one same side. In a micro-LED of vertical structure, the P electrodes and N electrodes thereof are located on opposite sides.

At step S4200, the original substrate is irradiated with laser from the original substrate side to lift-off the micro-LEDs from the original substrate.

At step S4300, the micro-LEDs are brought into contact with pads preset on a receiving substrate through an action of contactless action.

The contactless action means that the action per se can be applied without the direct contact of objects. For example, the contactless action can be applied by means of a field. This is different from the action applied through the stickiness of an anisotropic conductive layer or by the surface tension of liquid (such as flux). It should be understood that although the contactless action per se can be applied without the direct contact of objects, the direct contact of objects can be kept through the contactless action. For example, several example of the contactless action are given as below.

For example, the contactless action is gravity. The micro-LEDs are placed over the receiving substrate. When the lift-off is performed, the micro-LEDs are dropped off on the receiving substrate and are left on the receiving substrate.

For example, the contactless action is electrostatic force. The electrostatic force can be applied by applying voltage to the pads.

For example, the contactless action is electromagnetic force. In case that the micro-LEDs contains magnetic substance, a magnetic field can be provided by means of a magnet such as permanent magnet, so that the micro-LEDs are dropped off and are left onto the receiving substrate after being lifted-off from the original substrate because of the electromagnetic force, thereby contacting with the pads directly or indirectly.

In this embodiment, the micro-LEDs are attached onto the receiving substrate via a contactless manner, which is not conceived by a person skilled in the art.

For example, the electrodes of the micro-LEDs include solder bumps. The solder bumps are bonded with the pads, for example, through reflow-soldering and so on.

The order of steps in FIG. 10 will not constitute any limitation of the present invention. For example, although the step S4200 are shown in front of the step S4030, the action of gravity, the action of electrostatic force or the action of electromagnetic force can be applied before the step S4200 or at the time when performing the step S4200. In another word, for example, the step S4300 can be performed before the step S4200 or simultaneously with the step S4200.

Similarly, the transfer method can be applied to a method for manufacturing a micro-LED device for transferring the micro-LEDs onto a receiving substrate. For example, the receiving substrate is a display screen or display substrate. The micro-LED device is a display device, for example.

For example, a micro-LED device, such as a display device, can be manufactured by using the manufacturing method.

For example, the present invention further provides an electronic apparatus. The electronic apparatus contains the

micro-LED device. For example, the electronic apparatus can be a mobile phone, a pad and so on.

Although some specific embodiments of the present invention have been demonstrated in detail with examples, it should be understood by a person skilled in the art that the above examples are only intended to be illustrative but not to limit the scope of the present invention. It should be understood by a person skilled in the art that the above embodiments can be modified without departing from the scope and spirit of the present invention. The scope of the present invention is defined by the attached claims.

What is claimed is:

1. A method for transferring micro-LED, comprising: forming micro-LEDs on a laser-transparent original substrate, wherein the micro-LEDs are lateral micro-LEDs whose P electrodes and N electrodes are located on one side; bringing the P electrodes and the N electrodes of the lateral micro-LEDs into contact with pads preset on a receiving substrate; and irradiating the original substrate with laser from an original substrate side to lift-off the lateral micro-LEDs from the original substrate; wherein the lateral micro-LEDs contain magnetic substance, and the P electrodes and the N electrodes of the lateral micro-LEDs are brought into contact with the pads preset on the receiving substrate by means of an action of electromagnetic force.
2. The method according to claim 1, further comprising: providing an anisotropic conductive layer on the receiving substrate; wherein the P electrodes and the N electrodes of the lateral micro-LEDs are brought into contact with the pads preset on the receiving substrate via the anisotropic conductive layer; wherein the method further comprises: processing the anisotropic conductive layer, to electrically connect the P electrodes and the N electrodes of the lateral micro-LEDs with the pads on the receiving substrate.
3. The method according to claim 2, wherein the anisotropic conductive layer is at least one of an anisotropic conductive film, an anisotropic conductive paste and an anisotropic conductive tape.
4. The method according to claim 1, wherein the P electrodes and the N electrodes of the lateral micro-LEDs are brought into contact with the pads preset on the receiving substrate by means of an action of gravity.
5. The method according to claim 1, wherein the P electrodes and the N electrodes of the lateral micro-LEDs are brought into contact with the pads preset on the receiving substrate by means of an action of electrostatic force.
6. The method according to claim 5, wherein the electrostatic force is applied by applying voltage to the pads.
7. The method according to claim 1, wherein the P electrodes and the N electrodes of the lateral micro-LEDs include solder bumps, and the method further comprises: bonding the solder bumps with the pads.
8. A method for manufacturing a micro-LED device, comprising transferring lateral micro-LEDs to a receiving substrate by using the method according to claim 1.
9. A micro-LED device, which is manufactured by using the method according to claim 8.
10. An electronic apparatus, containing a micro-LED device according to claim 9.

专利名称(译)	微LED的转移方法，制造方法，装置和电子设备		
公开(公告)号	US10141287	公开(公告)日	2018-11-27
申请号	US15/531194	申请日	2015-07-14
[标]申请(专利权)人(译)	歌尔声学股份有限公司		
申请(专利权)人(译)	歌尔声学，INC.		
当前申请(专利权)人(译)	歌尔声学，INC.		
[标]发明人	ZOU QUANBO WANG ZHE		
发明人	ZOU, QUANBO WANG, ZHE		
IPC分类号	H01L25/075 H01L33/00 H01L33/52 H01L33/62 H01L33/20		
CPC分类号	H01L25/0753 H01L33/0079 H01L33/0095 H01L33/52 H01L33/62 H01L2933/0066 H01L33/20 H01L2224/16225 H01L2224/83192 H01L2933/005 H01L33/0093		
代理人(译)	HULTQUIST，史蒂芬J.		
其他公开文献	US20170330867A1		
外部链接	Espacenet		

摘要(译)

本发明公开了一种微LED的转移方法，制造方法，装置和电子设备。转移微型LED的方法包括：在激光透明的原始基板上形成微型LED，其中微型LED是横向微型LED，其P电极和N电极位于一侧；使横向微型LED的P电极和N电极与预设在接受基板上的焊盘接触；用来自原始基板侧的激光照射原始基板，以从原始基板上剥离横向微型LED。使用横向微型LED的技术效果在于可以省略微型LED转移后的N金属电极的处理。

