



US007918806B2

(12) **United States Patent**
Griffin et al.

(10) **Patent No.:** **US 7,918,806 B2**
(45) **Date of Patent:** ***Apr. 5, 2011**

(54) **GUIDE WIRE WITH ADJUSTABLE FLEXIBILITY**

(75) Inventors: **Stephen Griffin**, Sunnyvale, CA (US);
Gregory E. Mirigian, Dublin, CA (US)

(73) Assignee: **Boston Scientific Scimed, Inc.**, Maple Grove, MN (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 442 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **11/352,753**

(22) Filed: **Feb. 13, 2006**

(65) **Prior Publication Data**

US 2006/0127561 A1 Jun. 15, 2006

Related U.S. Application Data

(63) Continuation of application No. 10/025,428, filed on Dec. 18, 2001, now Pat. No. 7,018,346.

(51) **Int. Cl.**
A61M 25/00 (2006.01)

(52) **U.S. Cl.** **600/585**

(58) **Field of Classification Search** 600/433-435, 600/585; 604/164.13, 170.01, 171; 606/28
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,416,531 A 12/1968 Edwards
3,485,234 A 12/1969 Stevens
3,612,038 A 10/1971 Halligan
3,612,058 A 10/1971 Ackerman

3,725,116 A 4/1973 Parker et al.
4,210,478 A 7/1980 Shoney
4,292,270 A 9/1981 Hannah et al.
4,341,218 A 7/1982 U
4,359,453 A 11/1982 Gordon
4,369,206 A 1/1983 Mayer et al.
4,385,635 A 5/1983 Ruiz
4,419,095 A 12/1983 Nebergall et al.
4,427,000 A 1/1984 Ueda
(Continued)

FOREIGN PATENT DOCUMENTS

EP 0 277 366 8/1988
(Continued)

OTHER PUBLICATIONS

Gleich, Bernhard, "Catheter Temperature Measurement with Ferromagnets," *Research Disclosure*, Feb. 2001, p. 189.

(Continued)

Primary Examiner — Max Hindenburg


Assistant Examiner — Jonathan M Foreman

(74) *Attorney, Agent, or Firm* — Seager, Tuft & Wickhem, LLC

(57) **ABSTRACT**

A guide wire with a distal portion having adjustable flexibility. The guide wire may include a distal polymeric member and a heat source. The heat source may be activated to cause the polymeric member to increase in temperature and increase in flexibility. The increase in flexibility of the distal portion of the guide wire enhances the ability of the guide wire to navigate tortuous vasculature to a target site. After the guide wire has been navigated to the target site, the heat source may be deactivated to cause the polymeric member to decrease in temperature and increase in stiffness. The increase in stiffness of the distal portion of the guide wire enhances support provided for devices (e.g., catheters) advanced thereon.

11 Claims, 1 Drawing Sheet



U.S. PATENT DOCUMENTS			
4,516,970 A	5/1985	Kaufman et al.	5,308,342 A
4,516,972 A	5/1985	Samson	5,318,999 A
4,531,943 A	7/1985	Van Tassel et al.	5,334,168 A
4,563,181 A	1/1986	Wijayarathna et al.	5,335,305 A
4,588,399 A	5/1986	Nebergall et al.	5,344,444 A
4,590,922 A	5/1986	Gordon	5,349,946 A
4,622,953 A	11/1986	Gordon	5,349,964 A
4,627,436 A	12/1986	Leckrone	5,358,493 A
4,636,346 A	1/1987	Gold et al.	5,368,591 A
4,643,186 A	2/1987	Rosen et al.	5,370,109 A
4,654,024 A	3/1987	Crittenden et al.	5,423,773 A
4,655,771 A	4/1987	Wallsten	5,423,774 A
4,672,962 A	6/1987	Hershenson	5,433,200 A
4,685,458 A	8/1987	Leckrone	5,441,489 A
4,690,175 A	9/1987	Ouchi et al.	5,443,495 A
4,705,511 A	11/1987	Kocak	5,445,624 A
4,728,322 A	3/1988	Walker et al.	5,449,369 A
4,735,620 A	4/1988	Ruiz	5,449,703 A
4,735,796 A	4/1988	Gordon	5,464,419 A
4,740,674 A *	4/1988	Tsutsumi 219/523	5,497,786 A
4,747,405 A	5/1988	Leckrone	5,502,087 A
4,748,979 A	6/1988	Hershenson	5,509,910 A
4,753,223 A	6/1988	Bremer	5,511,547 A
4,767,611 A	8/1988	Gordon	5,514,108 A
4,790,311 A	12/1988	Ruiz	5,529,653 A
4,807,620 A	2/1989	Strul et al.	5,531,685 A
4,817,613 A	4/1989	Jaraczewski et al.	5,531,715 A
4,838,859 A	6/1989	Strassmann	5,538,512 A
4,838,879 A	6/1989	Tanabe et al.	5,545,151 A
4,840,622 A	6/1989	Hardy	5,569,218 A
4,842,590 A	6/1989	Tanabe et al.	5,578,008 A
4,863,442 A	9/1989	DeMello et al.	5,591,199 A
4,869,248 A	9/1989	Narula	5,599,319 A
4,895,168 A *	1/1990	Machek 600/585	5,603,705 A
4,898,591 A	2/1990	Jang et al.	5,626,136 A
4,899,787 A	2/1990	Ouchi et al.	5,658,263 A
4,923,437 A	5/1990	Gordon	5,662,621 A
4,930,494 A	6/1990	Takehana et al.	5,662,622 A
4,950,258 A	8/1990	Kawai et al.	5,665,063 A
4,981,478 A	1/1991	Evard et al.	5,674,208 A
4,984,581 A	1/1991	Stice	5,676,659 A
5,009,655 A	4/1991	Daignault, Jr. et al.	5,711,909 A
5,017,259 A	5/1991	Kohsai	5,766,204 A
5,019,040 A	5/1991	Itaoka et al.	5,769,796 A
5,025,799 A	6/1991	Wilson	5,772,628 A
5,041,089 A	8/1991	Mueller et al.	5,779,673 A
5,047,025 A	9/1991	Taylor et al.	5,792,401 A
5,055,101 A	10/1991	McCoy	5,800,500 A
5,057,092 A	10/1991	Webster, Jr.	5,810,867 A
5,069,674 A	12/1991	Fearnott et al.	5,810,874 A
5,078,702 A	1/1992	Pomeranz	5,830,224 A
5,087,256 A	2/1992	Taylor et al.	5,836,925 A
5,090,956 A	2/1992	McCoy	5,891,082 A
5,093,385 A	3/1992	Ali	5,891,094 A
5,098,429 A	3/1992	Sterzer	5,897,537 A
5,116,317 A	5/1992	Carson et al.	5,911,715 A
5,143,085 A	9/1992	Wilson	5,911,737 A
5,156,596 A	10/1992	Balbierz et al.	5,938,623 A
5,160,559 A	11/1992	Scovil et al.	5,951,495 A
5,163,431 A	11/1992	Griep	5,954,651 A
5,176,660 A	1/1993	Truckai	5,957,966 A
5,180,376 A	1/1993	Fischell	5,971,979 A
5,190,520 A	3/1993	Fenton, Jr. et al.	5,997,526 A
5,190,540 A	3/1993	Lee	5,997,570 A
5,203,772 A	4/1993	Hammerslag et al.	6,006,756 A
5,211,183 A	5/1993	Wilson	6,017,323 A
5,217,440 A	6/1993	Frassica	6,017,335 A
5,221,270 A	6/1993	Parker	6,027,450 A
5,221,372 A	6/1993	Olson	6,030,405 A
5,222,949 A	6/1993	Kaldany	6,042,578 A
5,234,416 A	8/1993	Macaulay et al.	6,056,844 A
5,249,585 A	10/1993	Turner et al.	6,059,815 A
5,254,107 A	10/1993	Soltész	6,072,154 A
5,257,635 A	11/1993	Langberg	6,076,609 A
5,279,596 A	1/1994	Castaneda et al.	6,086,599 A
5,290,230 A	3/1994	Ainsworth et al.	6,090,099 A
5,298,532 A	3/1994	Ali	6,102,917 A
5,306,252 A	4/1994	Yutori et al.	6,102,933 A
			6,123,718 A
			5/1994 Sepetka et al.
			6/1994 Mitra et al.
			8/1994 Hemmer
			8/1994 Kosa et al.
			9/1994 Glastra
			9/1994 McComb
			9/1994 Imran et al.
			10/1994 Schweich, Jr. et al.
			11/1994 Lennox et al.
			12/1994 Cuny
			6/1995 Jimenez
			6/1995 Fischell et al.
			7/1995 Fleischhacker, Jr.
			8/1995 Utsumi et al.
			8/1995 Buscemi et al.
			8/1995 Jimenez
			9/1995 Imran
			9/1995 Mitra et al.
			11/1995 Glastra
			3/1996 Urick
			3/1996 Tateosian et al.
			4/1996 Lunn
			4/1996 Markle et al.
			5/1996 Stevens
			6/1996 Glastra
			7/1996 Hemmer et al.
			7/1996 Engelson et al.
			7/1996 Zenzon et al.
			8/1996 O'Connor et al.
			10/1996 Berg
			11/1996 Hara
			1/1997 Porter et al.
			2/1997 Stevens
			2/1997 Berg
			5/1997 Webster, Jr.
			8/1997 Dang et al.
			9/1997 Lafontaine
			9/1997 Gore et al.
			9/1997 Roth et al.
			10/1997 Berg et al.
			10/1997 McGurk
			1/1998 Gore et al.
			6/1998 Porter et al.
			6/1998 Palermo et al.
			6/1998 Bacich et al.
			7/1998 Roth et al.
			8/1998 Burnham
			9/1998 Spelman et al.
			9/1998 Zarbatany et al.
			9/1998 Lefebvre
			11/1998 Cohn et al.
			11/1998 Soltész
			4/1999 Leone et al.
			4/1999 Masterson et al.
			4/1999 Berg et al.
			6/1999 Berg et al.
			6/1999 Lee et al.
			8/1999 Quiachon et al.
			9/1999 Berg et al.
			9/1999 Berg et al.
			9/1999 Schroepfel et al.
			10/1999 Joye et al.
			12/1999 Giba et al.
			12/1999 Ligtienberg et al.
			12/1999 Shaddock
			1/2000 Chee
			1/2000 Burnham
			2/2000 Brown et al.
			2/2000 Zarbatany et al.
			3/2000 Dinh et al.
			5/2000 Guiles et al.
			5/2000 Lee et al.
			6/2000 Maynard
			6/2000 Job
			7/2000 Lee et al.
			7/2000 Samson et al.
			8/2000 Maitland et al.
			8/2000 Lee et al.
			9/2000 Tu et al.

6,165,166 A 12/2000 Samuelson et al.
 6,179,824 B1 1/2001 Eggers et al.
 6,183,443 B1 2/2001 Kratoska et al.
 6,197,844 B1 3/2001 Hamrock et al.
 6,210,393 B1 4/2001 Briskin
 6,212,422 B1 4/2001 Berg et al.
 6,224,610 B1 5/2001 Ferrera
 6,240,231 B1 5/2001 Ferrera et al.
 6,258,195 B1 7/2001 Holman et al.
 6,272,371 B1 8/2001 Shlomo
 6,287,320 B1 9/2001 Slepian
 6,290,692 B1 9/2001 Klima et al.
 6,296,622 B1 10/2001 Kurz et al.
 6,323,251 B1 11/2001 Perez et al.
 6,355,029 B1 3/2002 Joye et al.
 6,387,052 B1 5/2002 Quinn et al.
 6,388,043 B1 5/2002 Langer et al.
 6,428,534 B1 8/2002 Joye et al.
 6,428,563 B1 8/2002 Keller
 6,468,297 B1 10/2002 Williams et al.
 6,485,512 B1 11/2002 Cheng
 6,520,952 B1 2/2003 Jimenez
 6,533,752 B1 3/2003 Waram et al.
 6,555,288 B1 4/2003 Xu et al.
 6,562,021 B1 5/2003 Derbin et al.
 6,579,913 B2 6/2003 Klinkenberg et al.
 6,598,280 B1 7/2003 Giba et al.
 6,720,402 B2 4/2004 Langer et al.
 6,740,094 B2 5/2004 Maitland et al.
 6,740,107 B2 5/2004 Loeb et al.
 7,018,346 B2* 3/2006 Griffin et al. 600/585
 7,351,199 B2 4/2008 Nash
 2001/0039412 A1 11/2001 Fariabi
 2002/0026182 A1 2/2002 Joye et al.
 2002/0095169 A1 7/2002 Maitland et al.
 2002/0165520 A1 11/2002 Forman
 2003/0069522 A1 4/2003 Jacobsen et al.
 2003/0114914 A1 6/2003 Cheng

2003/0125710 A1 7/2003 Pepin
 2004/0054301 A1 3/2004 Cassell
 2004/0104512 A1 6/2004 Ejdenschink
 2008/0009831 A1 1/2008 Griffin

FOREIGN PATENT DOCUMENTS

EP	0 382 974	8/1990
EP	0 417 865	3/1991
EP	0 420 993	4/1991
EP	0 473 045	3/1992
EP	0 180 348	5/1992
EP	0 555 088	8/1993
JP	4-40652 U	4/1992
JP	5-84303 A	4/1993
JP	10-156942 A	6/1998
WO	WO 86/03980	7/1986
WO	WO 92/15356	9/1992
WO	WO 93/15785	8/1993
WO	WO 95/10321	4/1995
WO	WO 95/10321	4/1995
WO	WO 95/29722	11/1995
WO	WO 96/20750	7/1996
WO	WO 97/14466	4/1997
WO	WO 00/03756	1/2000
WO	WO 02/078777	10/2002

OTHER PUBLICATIONS

Kolobow et al., "A New Thin-Walled Nonkinking Catheter for Peripheral Vascular Connulation," *Surgery*, vol. 68, No. 4, Oct. 1970, pp. 625-626.

Suwanwatana, W., Research Poster—University of Delaware "Inductions Heating of Thin Films Containing Ferromagnetic Particles", www.ccm.udel.edu/publications/AR/posters/PS/Suwanwatana, Mar. 18, 2002, 2 pages.

* cited by examiner

Fig. 1





Fig. 2



1

GUIDE WIRE WITH ADJUSTABLE FLEXIBILITY

CROSS REFERENCE TO CO-PENDING APPLICATIONS

This application is a continuation of U.S. patent application Ser. No. 10/025,428, filed Dec. 18, 2001 now U.S. Pat. No. 7,018,346.

FIELD OF THE INVENTION

The present invention generally relates to intravascular guide wires. In particular, the present invention relates to intravascular guide wires having adjustable flexibility.

BACKGROUND OF THE INVENTION

Intravascular guide wires are often used to facilitate the delivery of therapeutic and diagnostic devices to remote vascular sites in the human body. In particular, intravascular guide wires are used to navigate through a patient's vasculature from a convenient location outside the patient's body, to a target site inside the patient's body requiring diagnosis and/or therapy. Once access to the target site has been provided by the guide wire, a therapeutic or diagnostic device (e.g., catheter) may then be advanced over the guide wire to the target site, and the desired therapeutic or diagnostic steps may be performed.

To facilitate navigation in tortuous vasculature, it is desirable that the guide wire have a relatively flexible distal end. To provide good support for devices advanced over the guide wire, it is desirable that the guide wire have a relatively stiff distal end. Conventional guide wires typically address these competing needs by establishing a compromise in flexibility and stiffness. However, it would be desirable to have a guide wire that does not compromise these competing needs.

SUMMARY OF THE INVENTION

To address these needs, the present invention provides, in one exemplary embodiment, a guide wire that has a distal portion with adjustable flexibility. In one example, the guide wire includes a distal polymeric member and a heat source. The heat source may be activated by a power supply, which causes the polymeric member to increase in temperature, to thereby increase the flexibility of the distal portion of the guide wire. The polymeric member may comprise a shape memory polymer having a glass transition temperature, wherein the increase in temperature is across the glass transition temperature.

The increase in flexibility of the distal portion of the guide wire enhances the ability of the guide wire to navigate vasculature of varying degrees of tortuosity. After the guide wire has been navigated to the target site, the heat source may be deactivated, which causes the polymeric member to decrease in temperature, to thereby increase the stiffness of the distal portion of the guide wire and provide enhanced support for devices advanced thereon.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a plan view of a guide wire system, including a guide wire, a controller/power source and a coupling/lead therebetween, in accordance with an exemplary embodiment of the present invention; and

2

FIG. 2 is a longitudinal cross-sectional view taken along line 2-2 in FIG. 1, illustrating in detail the distal portion of the guide wire shown in FIG. 1.

DETAILED DESCRIPTION

The following description should be read with reference to the drawings wherein like reference numerals indicate like elements throughout the several views. The detailed description and drawings illustrate embodiments by way of example, not limitation.

Refer now to FIG. 1 which illustrates a guide wire system in accordance with an exemplary embodiment of the present invention. The guide wire system includes a guide wire 10 connected to a controller and power source 50 by a coupling 40 and lead 60.

Guide wire 10 includes an elongate shaft 12 having a proximal portion 14 and a distal portion 16. Distal portion 16 includes a soft atraumatic tip 18. The proximal portion 14 of the shaft 12 is relatively stiff to provide pushability and torquability, and the distal portion 16 has adjustable flexibility to provide trackability in navigating tortuous vasculature and support for devices advanced thereover.

Except as described herein and implicit in the drawings, the guide wire 10 may have conventional dimensions and may be formed of conventional materials using conventional techniques known for intravascular guide wires used to navigate the human vasculature to remote locations including, but not limited to, the neurovasculature, the coronary vasculature, and the peripheral vasculature.

As will be discussed in more detail with reference to FIG. 2, the distal portion 16 of the guide wire 10 includes a heat source that is thermally connected to a polymeric member that increases in flexibility when heated, and increases in stiffness (e.g., returns to its nominal flexibility or stiffness at body temperature) when cooled. Thus, by activating or deactivating the heat source, the flexibility of the polymeric member, and thus the flexibility of the distal portion 16, may be adjusted. For example, the flexibility of the distal portion 16 may be increased by activating the heat source, which enhances the ability of the guide wire 10 to navigate tortuous vasculature to a target site. After the guide wire 10 has been navigated to the desired target site, the heat source may be deactivated to cause the distal portion 16 to increase in stiffness, which enhances guide wire 10 support provided for devices (e.g., catheters) advanced thereon.

To control activation and deactivation of the heat source, a controller/power supply 50 is connected by lead 60 to a coupling 40 which is releasably and rotatably connected to the proximal portion 14 of the guide wire shaft 12. Controller/power supply 50 may comprise a conventional power supply with conventional control circuitry to provide a constant or modulated AC or DC signal. The signal is transmitted by lead 60, which may comprise two (or more) conductors. The conductors in the lead 60 may be connected to leads in the shaft 12 of the guide wire by coupling 40. Coupling 40 may be removable to permit devices such as catheters to be advanced over the proximal end of the guide wire 10. Coupling 40 may also be rotatable to permit the guide wire to be rotated and steered during intravascular navigation.

Refer now to FIG. 2 which illustrates in detail certain aspects of the distal portion 16 of the guide wire 10, which may be in common with certain aspects of the proximal portion 14. As seen in FIG. 2, the shaft 12 includes a hypotube 22 which may comprise, for example, stainless steel or a super elastic metal such as a nickel titanium alloy, Nitinol, MP35N, Inconel, etc. The hypotube 22 may extend from the

3

proximal end of the guide wire shaft 12, and may include an outer sleeve 24 comprising a polymer such as polyurethane. A tapered core wire 26 may extend through the lumen in the hypotube 22, and may comprise stainless steel or a super elastic metal such as a nickel titanium alloy, Nitinol, MP35N, Inconel, etc. The distal end of the hypotube 22 in the region of the distal tip 18 may be helically slotted 28 to enhance flexibility. The distal end of the core wire 26 may be welded to the distal end of the slotted portion 28 of the hypotube 22 to form an atraumatic weld ball 30.

As mentioned previously, the distal portion 16 of the guide wire shaft 12 includes a heat source. In this particular example, the heat source comprises a resistive element 32. Resistive element 32 may comprise a tungsten or steel alloy that may be formed into a coil and heated by electro-resistive heating. Heater coil 32 may be disposed between adjacent turns in the slotted portion 28 of the hypotube 22. The resistive heater coil 32 is connected to insulated leads 34 which may be disposed in the lumen of the hypotube 22 around the core wire 26. Leads 34 are connected to coupling 40, which in turn is connected to controller/power supply 50 via lead 60.

A polymeric outer tube 36 may be disposed about the resistive heater coil 32, and a polymeric inner tube 38 may be provided to support the heater coil 32. The polymeric outer tube 36 and/or the polymeric inner tube 38 may be formed of a polymer that changes in stiffness when heated. For example, the polymeric outer tube 36 and/or the polymeric inner tube 38 may be formed of a polymer that is relatively stiff at temperatures at or below body temperature (37° C. or less) and relatively flexible at temperatures above body temperature. For example, a polymer may be selected with a glass transition temperature (T_g) that is above body temperature, such that heating the polymer above T_g results in the distal portion 16 of the guide wire 10 becoming relatively more flexible, and cooling the polymer below T_g , even when the guide wire 10 is disposed in the patient's body, results in the distal portion 16 of the guide wire 10 becoming relatively more stiff. In a preferred embodiment, the polymeric outer tube 36 and/or the polymeric inner tube 38 may be formed of a shape memory polymer (SMP) such as a shape memory polyurethane available from Mitsubishi. Other examples of suitable SMPs include polynorbornenes, polycaprolactones and copolymers thereof available from Pnemoscience. Some SMPs, such as polynorbornene, may change flexibility without changing temperature across T_g . Such SMPs may be above T_g at room temperature or body temperature, and may exhibit SMP characteristics at or near the melt temperature (T_m).

It should be understood that this disclosure is, in many respects, only illustrative. Changes may be made in details, particularly in matters of shape, size, arrangement of parts and order of steps without departing from the scope of the invention. The invention's scope is, of course, defined in the language in which the appended claims are expressed.

What is claimed is:

1. A method for manufacturing a guidewire, the method comprising:

providing a tubular shaft having an inner surface, an outer surface, and a helically slotted portion;

disposing a heat source on the shaft, wherein the heat source includes a coil at least partially disposed in the helically slotted portion;

attaching a polymeric member to the outer surface of the shaft about the heat source, the polymeric member being in thermal communication with the heat source and hav-

4

ing a first flexibility at a first temperature and a second flexibility at a second temperature; and

attaching a second polymeric member to the inner surface.

2. The method of claim 1, wherein the heat source includes an outer surface and wherein at least a portion of the polymeric member is attached to the outer surface of the heat source.

3. The method of claim 1, wherein the polymeric member includes a shape memory polymer.

4. The method of claim 1, wherein the heat source includes a resistive heating element.

5. A guidewire manufactured by the method of claim 1.

6. A method for manufacturing a guidewire, the method comprising:

providing a shaft having an outer surface;

wherein the shaft includes a hypotube having a lumen therethrough and a core wire disposed within the lumen; attaching the distal end of the core wire to the distal end of the hypotube;

disposing a heat source on the shaft, wherein the heat source includes a coil;

wherein at least a portion of the heat source is in contact with at least a portion of the shaft;

wherein the hypotube includes a helically slotted portion and wherein at least a portion of the coil is disposed in the helically slotted portion; and

attaching a polymeric member to the outer surface of the shaft about the heat source, the polymeric member being in thermal communication with the heat source and having a first flexibility at a first temperature and a second flexibility at a second temperature.

7. The method of claim 6, wherein the heat source includes an outer surface and wherein at least a portion of the polymeric member is attached to the outer surface of the heat source.

8. The method of claim 6, wherein the polymeric member includes a shape memory polymer.

9. A guidewire manufactured by the method of claim 6.

10. A method for manufacturing a guidewire, the method comprising:

providing a tubular shaft having an outer surface, a lumen extending through the shaft from a proximal end to a distal end thereof, the lumen defining an inner surface, and a helically slotted portion formed in the distal end; disposing a heater coil between adjacent turns in the helically slotted portion;

wherein at least a portion of the heater coil is in contact with at least a portion of the shaft, and wherein the heater coil is connected to insulated leads disposed within the lumen;

disposing a core wire within the lumen;

attaching the distal end of the core wire to the distal end of the shaft; and

coupling a polymeric member to the outer surface of the shaft about the heat source, the polymeric member being in thermal communication with the heater coil and having a first flexibility at a first temperature and a second flexibility at a second temperature;

coupling a second polymeric member to the inner surface of the shaft, the second polymeric member being in thermal communication with the heater coil;

wherein the second polymeric member supports the heater coil.

11. A guidewire manufactured by the method of claim 10.

* * * * *

专利名称(译)	导丝具有可调节的灵活性		
公开(公告)号	US7918806	公开(公告)日	2011-04-05
申请号	US11/352753	申请日	2006-02-13
[标]申请(专利权)人(译)	GRIFFIN STEPHEN MIRIGIAN GREGORYê		
申请(专利权)人(译)	GRIFFIN STEPHEN MIRIGIAN GREGORYê		
当前申请(专利权)人(译)	BOSTON SCIENTIFIC SCIMED , INC.		
[标]发明人	GRIFFIN STEPHEN MIRIGIAN GREGORY E		
发明人	GRIFFIN, STEPHEN MIRIGIAN, GREGORY E.		
IPC分类号	A61M25/00 A61M25/01 A61B5/00		
CPC分类号	A61M25/09 A61M2025/09175 A61M2025/0915		
其他公开文献	US20060127561A1		
外部链接	Espacenet USPTO		

摘要(译)

一种导丝，其远端部分具有可调节的柔韧性。导丝可包括远端聚合物构件和热源。可以激活热源以使聚合物构件的温度升高并增加柔韧性。导丝远端部分的柔韧性的增加增强了导丝将曲折脉管系统导向目标部位的能力。在导丝已经导航到目标位置之后，可以停用热源以使聚合物构件的温度降低并且增加刚度。导丝远端部分的刚度的增加增强了对在其上前进的装置（例如，导管）提供的支撑。

