



US008100924B2

(12) **United States Patent**
Browning

(10) **Patent No.:** **US 8,100,924 B2**
(45) **Date of Patent:** ***Jan. 24, 2012**

- (54) **SURGICAL IMPLANT**
- (75) Inventor: **James Browning**, Glasgow (GB)
- (73) Assignee: **Coloplast A/S**, Humlebaek (DK)
- (*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 221 days.

This patent is subject to a terminal disclaimer.

3,916,899 A	11/1975	Theeuwes et al.
3,993,058 A	11/1976	Hoff
4,233,968 A	11/1980	Shaw
4,444,933 A	4/1984	Columbus et al.
4,452,245 A	6/1984	Usher
4,633,873 A	1/1987	Dumican et al.
4,646,731 A	3/1987	Brower
4,655,221 A	4/1987	Devereux
4,769,038 A	9/1988	Bendavid et al.
4,857,041 A	8/1989	Annis et al.
4,873,976 A	10/1989	Schreiber

(Continued)

(21) Appl. No.: **12/551,676**

FOREIGN PATENT DOCUMENTS

(22) Filed: **Sep. 1, 2009**

DE 10019604 10/2001

(Continued)

(65) **Prior Publication Data**

US 2010/0222794 A1 Sep. 2, 2010

OTHER PUBLICATIONS

U.S. Appl. No. 60/279,794, filed Mar. 29, 2001, Klutke et al.

(Continued)

Related U.S. Application Data

(63) Continuation of application No. 10/473,825, filed as application No. PCT/GB02/01234 on Apr. 2, 2002, now Pat. No. 7,594,921.

Primary Examiner — Julian Woo

(30) **Foreign Application Priority Data**

Mar. 30, 2001 (GB) 0108088.6

(74) *Attorney, Agent, or Firm* — Coloplast Corp.; Daniel G. Chapik; Nichols R. Baumann

(51) **Int. Cl.**

A61B 17/08 (2006.01)
A61F 2/02 (2006.01)

(57) **ABSTRACT**

(52) **U.S. Cl.** **606/151**; 623/23.72

(58) **Field of Classification Search** 606/151;
128/898; 623/23.72–23.74; 424/422–424;
600/29, 30, 37

See application file for complete search history.


A surgical implant suitable for treatment of hernias is provided. The implant comprises a mesh having a residual maximum mass density of 50 g/m². The mesh comprises strands forming spaces and the strands comprise filaments forming pores. The spaces and pores are sized to minimise foreign body mass for implantation and to encourage integration of the implant. The mesh may be delivered using Dual Phase Technology™ for ease of handling, cutting and placement. The Dual Phase Technology™ may include encapsulation or coating with hydrogel.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,054,406 A	9/1962	Usher
3,888,975 A	6/1975	Ramwell
3,911,911 A	10/1975	Scommegna
3,913,573 A	10/1975	Gutnick

15 Claims, 10 Drawing Sheets



U.S. PATENT DOCUMENTS				
4,938,760	A	7/1990	Burton et al.	6,599,323 B2 7/2003 Melican et al.
5,013,292	A	5/1991	Lemay	6,638,210 B2 10/2003 Berger
5,112,344	A	5/1992	Petros	6,638,211 B2 10/2003 Suslian et al.
5,149,329	A	9/1992	Richardson	6,638,284 B1 10/2003 Rousseau et al.
5,259,835	A	11/1993	Clark et al.	6,641,524 B2 11/2003 Kovac
5,342,376	A	8/1994	Ruff	6,652,450 B2 11/2003 Neisz et al.
5,362,294	A	11/1994	Seitzinger	6,652,595 B1 11/2003 Nicoloa
5,386,836	A	2/1995	Biswas	6,666,817 B2 12/2003 Li
5,434,146	A	7/1995	Labrie et al.	6,669,706 B2 12/2003 Schmitt et al.
5,439,467	A	8/1995	Benderev et al.	6,669,735 B1 12/2003 Pelissier
5,456,711	A	10/1995	Hudson et al.	6,673,010 B2 1/2004 Skiba et al.
5,486,197	A	1/1996	Le et al.	6,679,896 B2 1/2004 Gellman et al.
5,507,754	A	4/1996	Green et al.	6,689,047 B2 2/2004 Gellman
5,522,896	A	6/1996	Prescott et al.	6,691,711 B2 2/2004 Raz et al.
5,562,689	A	10/1996	Green et al.	6,695,855 B1 2/2004 Gaston
5,569,273	A	10/1996	Titone et al.	6,702,827 B1 3/2004 Lund et al.
5,611,515	A	3/1997	Benderev et al.	6,737,371 B1 5/2004 Planck et al.
5,647,836	A	7/1997	Blake, III et al.	6,783,554 B2 8/2004 Amara et al.
5,695,525	A	12/1997	Mulhauser et al.	6,830,052 B2 12/2004 Carter et al.
5,697,931	A	12/1997	Thompson	6,911,003 B2 6/2005 Anderson et al.
5,697,978	A	12/1997	Sgro	6,953,428 B2 10/2005 Gellman et al.
5,749,884	A	5/1998	Benderev et al.	6,960,160 B2 11/2005 Browning
5,766,221	A	6/1998	Benderev et al.	7,025,063 B2 4/2006 Snitkin et al.
5,816,258	A	10/1998	Jervis	7,087,065 B2 8/2006 Ulmsten et al.
5,840,011	A	11/1998	Landgrebe et al.	7,112,210 B2 9/2006 Ulmsten et al.
5,851,229	A	12/1998	Lentz et al.	7,131,943 B2 11/2006 Kammerer
5,899,909	A	5/1999	Claren et al.	7,131,944 B2 11/2006 Jacquetin
5,904,692	A	5/1999	Steckel et al.	7,156,858 B2 1/2007 Schuldt-Hempe et al.
5,922,026	A	7/1999	Chin	7,404,819 B1 7/2008 Darios et al.
5,934,283	A	8/1999	Willem et al.	7,594,921 B2* 9/2009 Browning 606/151
5,954,057	A	9/1999	Li	2001/0000533 A1 4/2001 Kovac
5,997,554	A	12/1999	Thompson	2001/0018549 A1 8/2001 Scetbon
6,010,447	A	1/2000	Kardjian	2001/0049538 A1 12/2001 Trabucco
6,039,686	A	3/2000	Kovac	2001/0051815 A1 12/2001 Esplin
6,042,534	A	3/2000	Gellman	2001/0053916 A1 12/2001 Rioux
6,042,536	A	3/2000	Tihon et al.	2002/0005204 A1 1/2002 Benderev et al.
6,042,583	A	3/2000	Thompson et al.	2002/0042658 A1 4/2002 Tyagi
6,048,306	A	4/2000	Spielberg	2002/0049503 A1 4/2002 Milbocker
6,048,351	A	4/2000	Gordon et al.	2002/0052612 A1 5/2002 Schmitt
6,050,937	A	4/2000	Benderev	2002/0052654 A1 5/2002 Darois et al.
6,053,935	A	4/2000	Brenneman et al.	2002/0077526 A1 6/2002 Kammerer et al.
6,056,688	A	5/2000	Benderev et al.	2002/0083949 A1 7/2002 James
6,068,591	A	5/2000	Bruckner et al.	2002/0099260 A1 7/2002 Suslian et al.
6,077,216	A	6/2000	Benderev et al.	2002/0128670 A1 9/2002 Ulmsten et al.
6,090,116	A	7/2000	D'Aversa et al.	2002/0138025 A1 9/2002 Gellman et al.
6,110,101	A	8/2000	Tihon et al.	2002/0161382 A1 10/2002 Neisz et al.
6,117,067	A	9/2000	Gil-Vernet	2003/0023137 A1 1/2003 Gellman
6,159,207	A	12/2000	Yoon	2003/0191360 A1 10/2003 Browning
6,162,962	A	12/2000	Hinsch et al.	2003/0199732 A1 10/2003 Suslian et al.
6,190,401	B1	2/2001	Green et al.	2004/0029478 A1 2/2004 Planck et al.
6,197,036	B1	3/2001	Tripp et al.	2004/0034373 A1 2/2004 Schuldt-Hempe et al.
6,200,330	B1	3/2001	Benderev et al.	2004/0039453 A1 2/2004 Anderson et al.
6,221,005	B1	4/2001	Bruckner et al.	2004/0172048 A1 9/2004 Browning
6,231,496	B1	5/2001	Wilk et al.	2004/0231678 A1 11/2004 Fierro
6,245,082	B1	6/2001	Gellman et al.	2004/0249373 A1 12/2004 Gronemeyer et al.
6,264,676	B1	7/2001	Gellman et al.	2004/0249397 A1 12/2004 Delorme et al.
6,267,772	B1	7/2001	Mulhauser et al.	2004/0249473 A1 12/2004 Delorme et al.
6,273,852	B1	8/2001	Lehe et al.	2005/0000524 A1 1/2005 Cancel et al.
6,287,316	B1	9/2001	Agarwal et al.	2005/0004576 A1 1/2005 Benderev
6,306,079	B1	10/2001	Trabucco	2005/0277806 A1 12/2005 Cristalli
6,328,686	B1	12/2001	Kovac	2005/0278037 A1 12/2005 Delorme et al.
6,334,446	B1	1/2002	Beyar	2006/0025649 A1 2/2006 Smith et al.
6,355,065	B1	3/2002	Gabbay	2006/0025783 A1 2/2006 Smith et al.
6,387,041	B1	5/2002	Harari et al.	2006/0041185 A1 2/2006 Browning
6,406,423	B1	6/2002	Scetbon	2006/0058578 A1 3/2006 Browning
6,408,656	B1	6/2002	Ory et al.	2006/0205995 A1 9/2006 Browning
6,418,930	B1	7/2002	Fowler	2007/0020311 A1 1/2007 Browning
6,475,139	B1	11/2002	Miller	2007/0032881 A1 2/2007 Browning
6,478,727	B2	11/2002	Scetbon	2008/0021263 A1 1/2008 Escude et al.
6,478,791	B1	11/2002	Carter et al.	2008/0196729 A1 8/2008 Browning
6,491,703	B1	12/2002	Ulmsten	2008/0200751 A1 8/2008 Browning
6,527,802	B1	3/2003	Mayer	2009/0123522 A1 5/2009 Browning
6,544,273	B1	4/2003	Harari et al.	
6,575,897	B1	6/2003	Ory et al.	
6,592,515	B2	7/2003	Thierfelder et al.	
6,596,001	B2	7/2003	Stormby et al.	
6,599,235	B2	7/2003	Kovac	
6,599,318	B1	7/2003	Gabbay	

FOREIGN PATENT DOCUMENTS

EP	0 009 072	4/1980
EP	0 024 780	3/1981
EP	0 024 781	3/1981
EP	0 139 286	5/1985
EP	0 248 544	12/1987

EP	0 557 964	9/1993
EP	0 632 999	1/1995
EP	0 706 778	4/1996
EP	0 719 527	7/1996
EP	0 797 962	10/1997
EP	1 060 714	12/2000
EP	1353598	8/2002
EP	1 274 370	9/2006
FR	2 712 177	5/1995
FR	2 732 582	10/1996
FR	2 735 015	12/1996
FR	2 787 990	7/2000
WO	WO 91/00714	1/1991
WO	WO 95/33454	12/1995
WO	WO 96/03091	2/1996
WO	WO 96/06567	3/1996
WO	WO 97/13465	4/1997
WO	WO 97/22310	6/1997
WO	WO 98/35632	8/1998
WO	WO 98/57590	12/1998
WO	WO 99/16381	4/1999
WO	WO 99/59477	11/1999
WO	WO 00/07520	2/2000
WO	WO 00/15141	3/2000
WO	WO 00/38784	7/2000
WO	WO 00/74633	12/2000
WO	WO 01/45589	6/2001
WO	WO 01/80773	11/2001
WO	WO 02/30293	4/2002
WO	WO 02/060371	8/2002
WO	WO 02/065944	8/2002
WO	WO 02/078568	10/2002
WO	WO 02/078571	10/2002
WO	WO 02/098340	12/2002
WO	WO 03/002027	1/2003
WO	WO 03/013392	2/2003
WO	WO 03/022260	3/2003
WO	WO 03/057074	7/2003
WO	WO 03/086205	10/2003
WO	WO 03/092546	11/2003
WO	WO 03/094781	11/2003
WO	WO 2004/004600	1/2004
WO	WO 2004/012626	2/2004
WO	WO 2004/002370	11/2004
WO	WO 2004/098461	11/2004
WO	WO 2005/018494	3/2005
WO	WO 2006/015031	2/2006
WO	WO 2006/015042	2/2006
WO	2007/059199	5/2007
WO	2007/149555	12/2007
WO	WO 2008/007086	1/2008

OTHER PUBLICATIONS

- U.S. Appl. No. 60/302,929, filed Jul. 3, 2001, Lund et al.
U.S. Appl. No. 60/307,836, filed Jul. 25, 2001, Neisz et al.
U.S. Appl. No. 60/322,309, filed Sep. 14, 2001, Anderson et al.
DeBord, James R., (1998), "The Historical Development of Prosthetics in Hernia Surgery," Surgical Clinics of North America, 78(6): 973-1006.
Klinge, U. et al., (1996), "Pathophysiology of the abdominal wall," Der Chirurg, 67:229-233. (In German, Abstract in English).
Klinge, U. et al., (1998), "Modified Mesh for Hernia Repair that is Adapted to the Physiology of the Abdominal Wall," Eur J Surg, 164:951-960.
Klinge, U. et al., (1999), "Influence of polyglactin-coating on functional and morphological parameters of polypropylene-mesh modifications for abnormal wall repair," Biomaterials, 20:613-623.
Klinge et al., (2002), "Functional and Morphological Evaluation of a Low-Weight, Monofilament Polypropylene Mesh for Hernia Repair," Journal of Biomedical Materials Research, 63(2):129-137.
Klosterhalfen, B. et al., (1997), "Morphological correlation of the functional mechanics of the abdominal wall after mesh implantation," Langenbecks Arch Chir, 382:87-94. (In German, Abstract in English).
Klosterhalfen, B. et al., (1998), "Functional and morphological evaluation of different polypropylene-mesh modifications for abdominal wall repair," Biomaterials 19:2235-2246.
Lipton, S. and Estrin, J., (1994), "A Biomechanical Study of the Aponeurotic Iguinal Hernia Repair," Journal of the American College of Surgeons, vol. 178, pp. 595-599.
Nicita, Giulio, (1998), "A New Operation for Genitourinary Prolapse," The Journal of Urology, 160:741-745.
Schumpelick, V. et al., (1999), "Minimized polypropylene mesh for preperitoneal net plasty (PNP) of incisional hernias," Chirurg 70:422-430. (In German, Abstract in English).
Sand et al "Prospective randomized trial of polyglactin 910 mesh to prevent recurrence of cystoceles and rectoceles" American Journal of Obstetrics & Gynecology vol. 184, Issue 7, pp. 1357-1364, Jun. 2001.
Parker, MC and Phillips, RK, "Repair of rectocele using Marlex mesh", Ann R Coll Surg Engl (May 1993) 75(3): 193-194.
Canepa, G, et al, "Horseshoe-shaped Marlex mesh for the treatment of pelvic floor prolapse", European Urology (Jan. 2001) 39(Suppl 2): 23-27.
Migliari, R, et al, "Tension-Free Vaginal Mesh Repair for Anterior Vaginal Wall Prolapse", European Urology (2000) 38 (2): 151-155.
Schettini, M. et al, "Abdominal sacral colpopexy with prolene mesh", Int Urogynecol J Pelvic Floor Dysfunct (1999) 10(5): 259-299.

* cited by examiner




Fig. 1




Fig. 2




Fig. 3





Fig. 4



SECTION A-A

Fig. 5






Fig. 6






Fig. 8a




Fig. 8b




Fig. 8c




Fig. 8d




Fig. 9a




Fig. 9b




Fig. 9c




Fig. 9d




Fig. 10




Fig. 11




Fig. 12




Fig. 13

SURGICAL IMPLANT

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of U.S. patent application Ser. No. 10/473,825 that has issued as U.S. Pat. No. 7,594,921 and was filed on Sep. 30, 2003 in the U.S. and completed the requirements under 35 U.S.C. 371 on Apr. 26, 2004, which is the U.S. national phase of International Patent Application No. PCT/GB02/01234, filed Apr. 2, 2002, which claims priority to and the benefit of Great Britain patent Application No. 0108088.6, filed Mar. 30, 2001, the contents of each application being incorporated by reference herein.

The present invention relates to the treatment of a hernia such as a uterovaginal prolapse and, in particular, to a surgical implant for use in such treatment and to a related surgical procedure and device.

A hernia is basically a defect resulting in the protrusion of part of an organ through the wall of a bodily cavity within which it is normally contained. For example, a fairly common and well known type of hernia is a defect in the lower abdominal wall resulting in a sac which may contain a portion of the intestine protruding through the abdominal wall. This is referred to as an inguinal hernia. Similarly, a defect in the abdominal wall after surgery is referred to as an incisional hernia. Another type of hernia is a defect in the pelvic floor or other supporting structures resulting in a portion of the uterus, bladder, bowel or other surrounding tissue protruding through, e.g., the vaginal wall. This is usually referred to as uterovaginal prolapse.

A common way of treating hernias is to repair the defect by sutures, whether or not the hernial sac is also sutured or repaired, in order that the protruding organ is contained in its normal position. As the defect generally comprises a weakening and attenuation leading to parting of tissues in a fascial wall, it is usually necessary to apply tension to the sutures in order to close the parted tissues. Thus, the fascial wall is generally pinched or tensioned around the area of the defect in order to close the parted tissues.

This treatment is generally effective, but does have some inherent problems. In particular, the pinching or tensioning of tissue around the defect can lead to discomfort and/or recurrence of the hernia. Additionally, in the case of uterovaginal prolapse, such pinching or tensioning of the vaginal wall almost inevitably results in anatomical distortion (such as narrowing of the vaginal cavity) with consequential pain and quality of life implications for the patient and relatively high recurrence and/or complication rates.

In order to address these problems, in the case of inguinal hernia repair, it has been suggested to make use of a surgical implant to overlay or close the weakened and parted tissues without the need to pinch or tension the surrounding tissue of the fascia. Such surgical implants generally comprise meshes and are now widely used in inguinal hernia repair. Meshes may be applied subcutaneously (i.e. under the skin), internally or externally of the abdominal wall and may be either absorbable or non-absorbable depending on the nature and severity of the particular defect being treated. Meshes may be applied in combination with sutures to hold the mesh in place or, alternatively, with sutures that close the parted tissues as in a "non-mesh" technique. Meshes are usually applied in open surgical procedures, although they may sometimes be applied in laparoscopic surgical procedures.

A typical mesh for an inguinal hernia repair comprises woven or knitted polypropylene such as Marlex® or Prolene®. Such meshes have a number of desirable properties

that make them effective for use in hernia repair. For example, they are made of materials that are suitably inert so as to be less likely to cause adverse reactions when implanted in the body. Furthermore, they are mechanically strong, cheap, easily sterilisable and easy to work with.

However, conventional meshes have a number of inherent problems. For example, fistula or sinus (i.e. abnormal passages between internal organs or between an internal organ and the body surface) can develop as a result of a mesh being implanted and left inside the body. More generally, the placement of a foreign body subcutaneously can also lead to inflammation or infection. Similarly, edge extrusion (i.e. the erosion of body tissue around the edge of the mesh) can occur. Nevertheless, overall, the use of meshes is generally considered to be beneficial in the treatment of incisional and inguinal hernias.

It has also been suggested to use meshes in the treatment of uterovaginal prolapse. Meshes that have been proposed for use in the repair of uterovaginal prolapse are similar to those that are used for the repair of inguinal hernia and such like. However, there is concern that the above mentioned problems with the use of meshes are greater when a mesh is placed in the vaginal wall as this tissue is generally thin only just below the surface and therefore more prone to adverse reactions. Furthermore, the placement of a foreign body close to the rectum and urinary tract may increase the risk of infection, inflammation, erosion, fistula or translocation. Thus, it is a relatively widespread view that the use of meshes in the treatment of vaginal prolapse is less desirable than in the treatment of other hernias.

Nevertheless, as the use of meshes to treat uterovaginal prolapse can avoid anatomical distortion and the above mentioned problems related to this, the Applicant considers there are significant benefits in the use of meshes in the treatment of uterovaginal prolapse should it be possible to mitigate the problems associated with mesh treatment.

The applicant has recognised that there are a number of specific features of conventional meshes that exacerbate the problems of fistula, sinus, edge extrusion, infection etc., particularly when these meshes are implanted in the vaginal wall. The Applicant has therefore realised that it is possible to provide a surgical implant that has the benefits of mesh treatment, i.e. the avoidance of anatomical distortion and its related problems, and also minimises the above mentioned problems.

One specific problem with conventional meshes that the Applicant has recognised is that they have jagged or rough edges. The rough edges arise as conventional meshes are generally formed from sheets of multiple woven or intersecting fibres or strands. When the meshes are cut to size in manufacture or prior to fitting, the stray ends of the fibres or strands are left extending from the edge of the mesh, particularly where the edge is curved. In other words, the perimeter of the mesh comprises the spaced ends of the fibres or strands and is not smooth. It is thought that the jagged rough nature of the edges of the implant increases the likelihood of extrusion of the edge of the mesh in situ.

Conventional meshes are generally unnecessarily strong and substantial for use in the vaginal wall and of significant mass. This results in an unnecessary excess of foreign body material in the vaginal wall, increasing the risks associated with the placement of foreign bodies inside the human body, such as the risk of infection. Likewise, the bulk of such meshes can undesirably result in discomfort for the patient as the mesh can often be felt when in position. This is of particular concern when a mesh is placed in sensitive vaginal tissues or near to bowel or bladder.

A further disadvantage of the meshes presently used to treat hernias relates to pore size. The pore size of meshes in use is unphysiological and does not encourage acceptance of the implant in the body.

It is a aim of the present invention to overcome problems associated with existing meshes used to treat hernias.

According to the present invention there is provided a surgical implant suitable for treatment of hernias, the implant comprising a mesh having a residual maximum mass density of 50 g/m².

Preferably the maximum mass density is less than 30 g/m². More preferably the maximum mass density is less than 25 g/m².

By minimising mass density of a mesh for use in treating hernias the advantages of using a mesh are still apparent whereas the disadvantages are lessened in that jagged and rough edges are minimised as is the risk of infection. The residual mass density is the mass density of the mesh after implantation.

Preferably the surgical implant mesh comprises strands and includes major spaces and pores.

The strands of the mesh may be formed by at least two filaments, the major spaces formed between the strands providing the surgical implant with the necessary strength, the filaments arranged such that pores are formed in the strands of the mesh.

Alternatively the strands may be foamed by monofilaments which form loops which give rise to the pores.

Preferably strands are spaced by wider distance than the fibres or filaments of conventional meshes used in hernia repair.

Preferably the strands are spaced apart to form major spaces of between 1 to 10 mm.

More preferably the strands are spaced apart to form major spaces of between 2 to 8 mm.

The use of mesh having strands spaced between 1 to 10 mm apart has the advantage of reducing the foreign body mass that is implanted in the human body. Only sufficient tensile strength to securely support the defect and tissue being repaired is provided by the mesh.

It is desirable that the mesh of the present invention has a mass of between one tenth (1/10th) and one hundredth (1/100th) that of a conventional, e.g. Prolene®, mesh of the same surface area. The mesh of the invention therefore avoids the unnecessary bulk of conventional meshes.

More specifically it is preferred that the mass density is less than 50 g/m², more preferably less than 30 g/m² and most preferably less than 20 g/m². It is also preferred that the strands of the mesh of the present invention are narrower than those of meshes of the prior art.

Preferably the strands have a diameter of less than 600 µm.

In one embodiment the strands are arranged to form a diamond net mesh.

In an alternative embodiment the strands are arranged to form a hexagonal net mesh.

The strands and filaments are preferably warp knit.

In an alternative embodiment the strands are arranged to form a net mesh with suitable tensile strength and elasticity.

Preferably the strands are arranged to form a net mesh which has isotropic or near isotropic tensile strength and elasticity.

Preferably the filaments have a diameter of between 0.02 to 0.15 mm.

More preferably the filament of the mesh is of a diameter 0.08 to 0.1 mm.

This likewise has the advantage of reducing the overall bulk of the implant, and hence the amount of material retained in the human body.

Particular meshes which are embodiments of the present invention include warp knit diamond or hexagon net diamond net meshes. Four particular embodiments are set out below.

In two particular embodiments wherein the filaments are formed from polypropylene having a diameter of 0.07-0.08 mm wherein the strands are spaced to form spaces of either 2 mm or 5 mm.

Alternatively, filaments are formed from polyester having a diameter of 0.09 mm wherein the strands are spaced to form spaces of 5 mm.

Alternatively, filaments are formed from polyester having a diameter of 0.05-0.07 mm wherein the strands are spaced to form spaces of 2 mm.

As the surgical implant is comprised of narrow members arranged to be spaced by relatively wide gaps, major spaces, tissue may be slow to grow into the mesh. It is desirable for the mesh to have means for promoting tissue ingrowth. More specifically, it is desirable to provide pores in the strands of the mesh to aid tissue ingrowth and to which tissue may more easily adhere.

Preferably two filaments are interwoven/knitted to produce strands of the mesh comprising pores.

Alternatively at least three filaments are interwoven/knitted to produce strands of the mesh comprising pores.

For manufacturing reasons it is preferred that two filaments are used to form the pores in the strands of the mesh which aid tissue ingrowth, however if the one filament could be suitably knotted or twisted to form pores of suitable dimensions it is clear that this could be used to similar effect to form the strands of the mesh.

Preferably the pores in the strands are of between 50 to 200 µm in diameter.

More preferably the pores are of between 50 to 75 µm in diameter.

This is important in enabling efficient fibroblast through-growth and ordered collagen laydown in order to provide optimal integration into the body. This is discussed in detail in copending Patent Application No PCT/GB01/04554.

Rings or loops of material comprising pores of between 50 to 200 µm may be adhered to or formed on the strands of the mesh to provide pores.

As mentioned above, reducing the mass of the mesh has distinct advantages in relation to the suitability of the mesh for implantation in the body, i.e. the reduction of foreign body mass and improving the comfort of the patient. However, the handling characteristics of such a mesh, e.g. the ease with which a surgeon can manipulate and place the surgical implant in its desired location in the body, can be poor in some circumstances. More specifically, a mesh having narrow members or strands that are widely spaced will inevitably be somewhat flimsy and lacking in rigidity compared to conventional meshes.

Ideally the implant should be formed from materials or uses technologies which provide the implant with Dual Phase Technology™, such that it has suitable surgical handling characteristics and is also of minimal mass and suited for implantation in the body. The implant may be formed from a range of materials to provide it with Dual Phase Technology™.

The term Dual Phase Technology™ refers to a means to provide temporary substance to the mesh. Depending on the type of Dual Phase Technology™ employed the benefits imported, in addition to allowing minimal residual mesh mass may include assisting the mesh to be handled and cut, mini-

mising the effect of rough edges, assisting placing the mesh in position and providing tackiness to assist in holding the mesh in position on implantation, thus minimising or negating the need for any additional fixation by suturing or adhesion.

In a preferred embodiment of the invention having improved handling characteristics, the implant therefore has an absorbable coating.

Preferably this coating encapsulates the mesh of the surgical implant.

Alternatively this coating is applied to at least one face of the mesh.

The coating, covering or layer of absorbable material stiffens and adds bulk to the mesh such that it is easier to handle.

As the coating, covering or layer is absorbable, it is absorbed by the body after implantation and does not contribute to the foreign body mass retained in the body. Thus, the advantages of a surgical implant having minimal mass are retained.

Preferably the coating, covering a layer absorbs within 48 hours following implantation.

The coating, covering or layer may comprise any suitable soluble and biocompatible material.

Suitable hydrogel materials can be obtained from First Water in the UK. A typical hydrogel being developed for use in this application is known as FIRST PHASE™ or PHASE 1™.

The absorbable material may be a soluble hydrogel such as gelatin,

Alternatively the absorbable material is a starch or cellulose based hydrogel.

In a further alternative the absorbable material is an alginate.

In a further alternative the absorbable material may contain hyaluronic acid.

The coating, covering or layer may have any thickness or bulk that provides the surgical implant with suitable handling characteristics.

Preferably, the coating is a sheet with a thickness greater than that of the mesh.

Suitable handling characteristics may also be provided to the mesh by a range of other methods. The surgical implant may comprise a mesh and a backing strip the backing strip releasably attachable to the mesh.

The backing strip may be formed from a range of materials including plastics.

The surgical implant may be releasably attachable to the backing strip by adhesive.

The releasable attachment of a backing strip to the mesh provides a more substantial and less flexible surgical implant that is more easily handled by a surgeon. Following suitable placement of the surgical implant the backing strip can be removed from the surgical implant, the surgical implant being retained in the body and the backing material being removed by the surgeon. The surgical implant can therefore benefit from reduced mass while still providing characteristics required for surgical handling.

In a further alternative the strands of the mesh of the surgical implant are comprised of bicomponent microfibres.

Preferably the bicomponent microfibres comprise a core material and surface material.

The composite or biocomponent fibres preferably comprise a nonabsorbable or long lasting absorbable core and a shorter lasting absorbable surface material.

Whereas any licensed materials may be used, suitable materials presently available include polypropylene for the core and polylactic acid or polyglycolic acid for the surface materials.

Alternatively the bicomponent microfibres comprise an material which is rapidly absorbed by the body and a material which is not absorbed for a suitable longer period of time.

Preferably the surface material is capable of being absorbed by the body in a period of less than 48 hours.

Preferably the core material is capable of remaining in the body for a period of time sufficient to enable tissue ingrowth.

The surface material of the bicomponent microfibres or a portion of the composite polymers present during the insertion and placement of the surgical implant provides the surgical implant with characteristics required for surgical handling.

Following a period of insertion in the body, the surface material of the bicomponent microfibre is absorbed by the body leaving behind the reduced foreign mass of the core material of the strands of the mesh.

It is preferred that the surface material of the bicomponent microfibre is absorbed by the body within a number of hours such that only a core portion is left in the body for an extended length of time. Typically materials presently available which could be used to form the microfibres are absorbed by the body over a period of days or weeks.

The filaments of the mesh comprise a plastics or synthetic material.

Preferably the filaments of the mesh comprise of polypropylene or polyester.

Alternatively the filaments of the mesh comprise an absorbable material.

It can be appreciated that filaments which comprise in part of absorbable material would allow better surgical handling, but would enable the implant to also have minimal mass following implantation in the body.

Preferably the surgical implant comprises material that has memory.

Preferably the surgical implant has memory which urges the surgical implant to adopts a flat conformation.

Preferably the implant has a generally curved perimeter, i.e. to have few or no corners or apexes, as sharp corners increase the likelihood of edge erosion and infection. The specific shape will, however, vary according to the use to which the implant is to be put.

Due to the variety of sizes of such defects, and of the various fascia that may need repair by the implant, the implant may have any suitable size,

Preferably the surgical implant is of width between 1 cm to 10 cm and of length between 1 cm to 10 cm.

It may be desirable to provide a variety of implants having different sizes in order that a surgeon can select an implant of suitable size to treat a particular patient. This allows implants to be completely formed before delivery, ensuring, for example, that the smooth edge is properly formed under the control of the manufacturer. The surgeon would have a variety of differently sized (and/or shaped) implants to hand and select the appropriate implant to use after assessment of the patient.

Typically an anterior uterovaginal prolapse is ellipse shaped or a truncated ellipse whereas a posterior prolapse is circular or ovoid in shape.

Accordingly the implant shape may be any one of elliptical or tuncated ellipse, round, circular, oval, ovoid or some similar shape to be used depending on the hernia or polapse to be treated.

Different shapes are suitable for repairing different defects in fascial tissue and thus by providing a surgical implant which can be cut to a range of shapes a wide range of defects in fascial tissue can be treated.

Preferably the mesh can be cut to any desired size. The cutting may be carried out by a surgeon or nurse under sterile conditions such that the surgeon need not have many differently sized implants to hand, but can simply cut a mesh to the desired size of the implant after assessment of the patient. In other words, the implant may be supplied in a large size and be capable of being cut to a smaller size, as desired.

In this regard, whilst the surgical implant of the invention is particularly useful for the repair of uterovaginal prolapse, it may be used in a variety of surgical procedures including the repair of hernias.

Preferably the surgical implant is suitable for use in the treatment of hernias including incisional and inguinal hernias and/or for the treatment of uterovaginal prolapse.

More broadly, the Applicant has therefore recognised that the implant can have any shape that conforms with an anatomical surface of the human or animal body that may be subject to a defect to be repaired by the implant.

As discussed a disadvantage of the meshes used in hernia repair is that they have jagged or rough edges. Due to the wide spacing between strands of the mesh described above and the small diameter of the filaments, the edge problems are mitigated to an extent by the present invention.

To further reduce edge problems it would be preferable if a mesh had a circumferential member which extends, in use, along at least part of the perimeter of the implant to provide a substantially smooth edge.

In other words, the mesh has at least one circumferential member (i.e. fibre, strand or such like) that extends around at least part of its circumference.

Preferably at least part of the perimeter of the implant is defined by the circumferential member,

Alternatively at least part of the perimeter of the implant is defined by more than one circumferential member, at the edge of the mesh.

The edge of the mesh, and hence the perimeter of the implant, can therefore be generally smooth and this has significant advantages over conventional surgical meshes. Specifically, the Applicant has recognised that an implant having a smooth edge is less likely to cause edge extrusion or erosion.

Any amount of the perimeter of the implant may be defined by the circumferential member(s).

However, in order to maximise the benefits of the implant of the invention, it is preferable that at least 50% of the perimeter of the implant is defined by the circumferential member(s).

More preferably at least 80% of the perimeter of the implant is defined by the circumferential member(s).

Most preferably 100% of the perimeter of the implant is defined by the circumferential member(s).

The majority or the whole of the perimeter of the mesh being smooth minimises the risk of a rough edge causing edge erosion or infection.

The circumferential member(s) may be arranged in one of a variety of ways to provide the smooth edge or perimeter.

Preferably the circumferential members are arranged such that they each follow the edge of a desired shape of the surgical implant, the perimeter of the implant formed from a few members as possible.

This simplifies the construction of the mesh, which is desirable not only for manufacture, but also because simpler structures are less likely to have defects which might be problematic after implantation.

Preferably the perimeter of the mesh is defined, in use, by one circumferential member.

Preferably the mesh has a plurality of circumferential members arranged at different radial locations.

In order to provide an implant of given dimensions, the periphery of the mesh outward of the desired circumferential member is cut away such that one or more selected circumferential members form the perimeter of the implant as desired.

More preferably, the circumferential members are arranged concentrically.

A concentric arrangement of a plurality of circumferential members conveniently allows maintenance of the shape of the implant for different sizes of implant and provides the mesh with an even structure.

The remainder of the structure of the mesh may take a variety of forms.

The circumferential members can be arranged to join with one another in order to form an integral mesh.

Alternatively the mesh may additionally comprise transverse members which extend across the circumferential members joining the circumferential members.

The transverse members may extend radially from a central point to the perimeter of the implant.

Alternatively, the transverse members may extend toward the perimeter of the implant.

Preferably the transverse members are arranged to provide substantially even structural strength and rigidity to the implant.

It may be desirable to secure the mesh in place once it has been suitably located in the patient.

Preferably the mesh can be sutured to strong lateral tissue.

Alternatively, the mesh may be glued in place using a biocompatible glue.

This is advantageous, as it is fairly quick to apply glue to the area around the surgical implant.

Preferably the mesh comprises at least one capsule containing biocompatible glue for securing the implant in place.

Preferably 4 capsules containing glue are provided around the perimeter of the surgical implant.

Preferably the capsules comprise hollow thin walled spheres of around 3 to 5 mm diameter including gelatin.

Preferably the glue is a cyanoacrylate glue.

Conventionally, open procedures have been preferred for the treatment of hernias with meshes, as relatively broad access is required to the site of the defect to suitably implant and secure a mesh by sutures or such like.

However, it is desirable to treat hernias, as when carrying out any surgery, with as little trauma to the patient as possible. Thus, the use of minimally invasive techniques has been suggested for the treatment of hernias. However, such surgical techniques have not been considered to be useful in the treatment of uterovaginal prolapse with a mesh, as it has not been considered practical to position a mesh subcutaneously in the vaginal wall due to the difficulty in gaining direct access to this area.

According to another aspect of the present invention, there is provided a minimally invasive method of treating uterovaginal prolapse, the method comprising the steps;

making an incision in the vaginal wall close to the opening of the vaginal cavity and,

making a subcutaneous cut, through the incision, over and surrounding the area of the prolapse, which cut is substantially parallel to the vaginal wall; and

inserting a mesh according to the present invention, through the incision, into the space defined by the cut.

Thus, a mesh or the surgical implant such as that according to the invention can be inserted through a small incision (e.g. around 1 cm to 2 cm in length) at or in the region of the periphery or opening of the vaginal cavity. An incision in this position is easier for a surgeon to access than an incision

deeper in the vaginal cavity, yet the Applicant has realised that it is also convenient to treat vaginal prolapse by implanting a mesh in a surgical procedure carried out entirely through such an incision.

Preferably, the incision is at the anterior or posterior extremity of the prolapse sac of the vaginal cavity.

This is desirable as prolapse most often occurs in the anterior or posterior vaginal wall, so positioning the incision in such a location allows the most convenient access to these parts of the vaginal wall.

The provision of suitable handling characteristics for the mesh is particularly advantageous when the mesh is intended to be used in a conventional open surgical procedure, as the surgeon needs to handle the implant directly in order to place it in its desired location.

However, the suitable placement particularly in the treatment of uterovaginal prolapse, by minimally invasive techniques require the mesh to be as flexible as possible and therefore to have no absorbable coating or encasement.

A flexible, less bulky mesh may be more easily handled by tools that may be used to carry out the procedure.

Tools that may be used to carry out this procedure have a number of specific needs that need to be met that are not presently met by conventional minimally invasive surgical tools.

These specific needs can best be understood by considering the steps of the surgical procedure of the invention in turn.

The incision is made in the vaginal wall at the opening of the vaginal cavity. This can be carried out using a conventional implement such as a scalpel. It is preferable that the incision is as small as possible as this reduces trauma to the patient.

A cut is then made in the vaginal wall over the defect causing the prolapse or hernia. For example, scissors or another specialised cutting tool can be inserted through the incision and manipulated to provide a cut over the defect. The cut is below the surface of the skin and may provide a space between an upper (or outer) layer and a lower (or inner) layer of the vaginal wall, or between the skin and the vaginal wall, in the region of the defect, into which cavity the mesh can be inserted.

Next, the mesh is placed in the space defined by the cut. It is preferred that the mesh of the invention is supplied rolled up in order that it can be inserted through a small incision and unfurled in situ, i.e. in its intended position. Thus, it may be possible for the surgeon to insert the mesh through the incision by hand. However, this is likely to result in the incision needing to be large enough for the surgeon to insert a finger to manipulate the mesh in the space. This may cause unnecessary trauma to the patient and can be difficult for a surgeon to carry out.

According to another aspect of the present invention, there is provided a surgical tool for delivering a mesh subcutaneously through an incision, the tool being adapted to radially confine the mesh during delivery and being operable to release the mesh in its intended position.

Such a tool for placement of a mesh or the surgical implant of the present invention can insert and position the mesh or surgical implant in a convenient and controlled manner through a small incision. Furthermore, the incision through which the mesh is inserted need only be as large as the diameter of the tool, or the tool when carrying the mesh, which can be significantly smaller than where a surgeon's finger must be able to fit through the incision.

Preferably the tool comprises a housing and unfurling means the housing and unfurling means insertable through an incision in the patient, the housing and unfurling means

adapted to accommodate a rolled up mesh and separable to release the mesh the unfurling means capable of unfurling the rolled up mesh without any significant movement around the area of the incision

Preferably, the tool comprises two or more parts, the parts movable such that in a first position they house the mesh or surgical implant and, in a second position the mesh or surgical implant is released. More preferably the tool comprises two semi-circular channels, an inner channel having an external diameter suitable for fitting inside an outer channel.

The channels may be rotatable about a common axis such that in a first position the open faces of the channels face one another to form a closed housing and in a second position the inner channel sits inside the other channel to release the mesh.

Alternative the tool comprises a shaft and releasable securing means, the shaft adapted such that the mesh can be rolled around the shaft and releasable securing means to secure the rolled mesh in place.

In use, the tool is inserted through the incision with the mesh rolled around the outside of the shaft. Once the tool has been inserted, the mesh is released by turning the shaft to unroll the mesh at the same time as moving the shaft across the space in which the mesh is being placed.

A needle may be used to secure the free, outer end of the mesh whilst it is unfurled. The needle may be inserted through the vaginal wall to pin the mesh in place. Similarly, where the mesh is released from within a housing, needles may be used to ease the mesh out of the open housing.

In an alternate embodiment, the tool comprises two or more arms, each of which is releasably attached at one end to an edge of the surgical implant. The arms may be movable from a first position in which they radially confine the mesh to a second position to unfurl the mesh in its intended position.

In one example, the arms are pivotally interconnected such that they can be manipulated to move the ends of the arms from the first position to the second position.

In another example the arms may be arranged to extend radially outward from a housing to move from the first position to the second position. The extendable arms may comprise wires arranged to be extendable and retractable from and into the housing by operation at an end of the housing.

In another example, the arms may be resilient or sprung elements that can be released from the first position and move into the second position to which they are biased, i.e. to unfurl the mesh.

As can be appreciated, all of the above, embodiments of the tool are able to unfurl the mesh without any significant movement around area of the incision. For example, the pivot can be arranged to coincide with the incision, the tool rolled around an arc centred at the incision or the arms operated or housing opened forward of the incision. Thus, the incision can be small as no lateral movement is required at the area of the incision.

Embodiments of the present invention will now be described, by way of example only, with reference to the accompanying drawings, in which:

FIG. 1 is an illustration of a hernia;

FIG. 2 is an illustration of the hernia of FIG. 1 when intra-abdominal pressure is raised;

FIG. 3 is an illustration of the hernia of FIG. 1 after repair in accordance with the prior art;

FIG. 4 is an illustration of the hernia of FIG. 1 after an alternate repair in accordance with the prior art;

FIG. 5 is a schematic illustration of the female human vaginal area;

FIG. 6 is a cross-sectional view of the female human vaginal area along the line A-A of FIG. 5;

FIGS. 7a and 7b illustrate surgical implants according to the invention having a first shape;

FIGS. 8a, 8b, 8c and 8d illustrate surgical implants according to the invention having a second shape;

FIGS. 9a, 9b 9c and 9d illustrate surgical implants according to the invention having a third shape;

FIG. 10 illustrates a first surgical tool according to the invention in cross-section;

FIG. 11 illustrates a second surgical tool according to the invention;

FIG. 12 illustrates a third surgical tool according to the invention; and

FIG. 13 illustrates a fourth surgical tool according to the invention.

Referring to FIGS. 1 and 2, a hernia, vaginal prolapse or such like occurs when a fascial wall 1 ruptures, forming a defect 2, i.e. a weakening or, in this case, parting of the fascial wall 1. An organ 3, contained by the fascial wall 1 is then able to protrude through the defect 2. Such protrusion is illustrated in FIG. 2 and occurs particularly when pressure within the cavity defined by the fascial wall 1 is raised. For example, in the case of an inguinal hernia, when a patient coughs, intra-abdominal pressure is raised and the intestines may be pushed through the defect 2 in the abdominal wall.

Whilst the organ 3 that may protrude through the defect 2 is usually still contained by some other membrane 4, the hernia, prolapse or such like is inevitably painful and liable to infection or other complications. An effective and desirable treatment is therefore to close the defect 2 and contain the organ 3 in its normal position.

Referring to FIG. 3, hernias, vaginal prolapse and such like are conventionally repaired by providing sutures 5 across the defect 2 to join the tissues of the fascial wall 1. In addition, it may be firstly necessary to plicate (i.e. fold or reduce) the membrane 4 as this may have stretched due to distention of the organ 3. Plication of the membrane 4 corrects the stretching and helps to relieve pressure on the area of the defect 2 during healing as the membrane 4 can act to contain the organ 3 to some extent. Plication is generally achieved by applying sutures 6 to the membrane 4.

Referring to FIG. 4, it is also a known method of treating hernias to provide, additionally or alternatively to sutures, a mesh 7 across the defect 4. This allows for the defect 2 to be repaired without the parted tissues of the fascial wall 1 necessarily being brought together and for the defect to heal without the fascial wall 1 being pinched or tensioned to correct the defect 2.

FIG. 5 schematically illustrates (a sagittal view of) the female human vaginal area. The vagina 8 is illustrated with its anterior portion (front) at the top of the diagram and the posterior portion (rear) at the bottom of the diagram. The opening of the urethra, or urethral meatus, 9 is at the forward or anterior end of the vagina 8. The central portion of the vagina 8 forms the vaginal cavity which terminates at the cervix 10. Spaced from the rearward or posterior end of the vagina 8 is the anus 11. Four areas A to D of the vaginal wall 12 are outlined in FIG. 5. These areas A to D are those areas of the vaginal wall 12 in which vaginal prolapse often occurs.

Referring to FIG. 6, which is a cross sectional view along the line A-A in FIG. 5, it can be more clearly seen that the wall 12 of the vagina 8 is bounded by the bladder 13 and urethra 14, the uterus 15, the small bowel 16 and rectum 17. The small bowel 16 and rectum 17 are separated by the "Pouch of Douglas" PoD.

Area A is the lower one third of the anterior vaginal wall 12 (i.e. the one third nearest the entrance to the vaginal cavity) adjacent the bladder 13 and urethra 14. Prolapse in this area is

referred to as anterior or, more specifically, urethrocoele prolapse. Area B is the upper two thirds of the anterior vaginal wall 12. Prolapse in this area is referred to as anterior or, more specifically; cystocele prolapse. The central area of the vaginal wall 12 in which the cervix 10 is located is adjacent the uterus 15 and prolapse in this area is referred to as central, uterine or vault prolapse. Area C is the upper one third of the posterior vaginal wall 12. This area of the vaginal wall 12 is adjacent the small bowel 16 and prolapse in this area is referred to as posterior or enterocele prolapse. Finally, area D is the lower two thirds of the posterior vaginal wall and is adjacent the rectum 17. Prolapse in this area is generally referred to as posterior or rectocele prolapse.

Conventionally, any of the above types of hernia have been treated by providing sutures in the area of the prolapse. For example, the extent of the defect causing the prolapse is first identified by the surgeon. Lateral sutures, i.e. sutures from one side to the other of the vaginal wall 12 as seen in FIG. 5 or right to left rather than anterior to posterior, are provided across the area of the defect. This joins the parted tissues of the vaginal wall and repairs the defect. The organ protruding through the vaginal wall is therefore contained. Disadvantages of this technique include anatomical distortion of the vagina due to tensioning of the wall by the sutures to repair the defect.

A surgical implant for use in the repair of vaginal prolapse in accordance with an embodiment of the present invention comprises a mesh 20. The mesh is comprised of strands 22. The strands being less than 600 μm and approximately 150 to 600 μm in diameter. The strands are arranged such that they form a regular network and are spaced apart from each other such that for a diamond net a space of between 2 mm to 5 mm exists between the points where the strands of the mesh interact with each other (a). In a hexagonal net arrangement the space is between 2 mm to 5 mm between opposite diagonal points where the strands of the mesh interact (b).

It is preferable to space the strands as far as part as possible to allow blood to pass through the implant and reduce the mass of the implant, while providing the mesh with sufficient tensile strength and elasticity to be effective. It can therefore be appreciated that considerable variability in the maximum spacing between the strands can be achieved depending of the material from with the strands are comprised and the net pattern in which the strands are arranged.

In the embodiment shown in FIG. 7a the strands are arranged in a diamond net pattern 24, however any pattern which provides suitable tensile strength an elasticity may be used.

For example a hexagonal net pattern may be used as shown in FIG. 7b.

Ideally in order to reduce the overall mass of the implant the strands 22 should have as narrow a diameter as possible while still providing the mesh 20 with suitable tensile strength and elasticity.

The strands 22 of the mesh 20 are comprised of at least two filaments 26 arranged to interact such that pores 28 are formed between the filaments 26.

The pores 28 formed between the filaments 26 are around 50 to 200 μm , such a spacing allowing fibroblast through growth to occur. This fibroblast through growth secures the implant 20 in place within the body. Additionally and importantly the suitably sized pores allow the implant 20 to act as a scaffold to encourage the lay down of new tissue. The lay down of new tissue promotes the healing of the hernia.

The filaments **26** may be formed from any biocompatible material. In this embodiment the filaments **26** are formed from polyester, wherein each polyester filament **26** is around 0.09 mm in diameter.

In the embodiment shown the filaments **26** of the strands **24** are knitted together using warp knit to reduce the possibility of fraying of the filaments **26** and strands **24**.

Alternative suitable materials of which the filaments may be formed include polypropylene.

Suitable materials from which the mesh can be made: provide sufficient tensile strength to support a fascial wall during repair of a defect in the fascial wall causing a hernia; are sufficiently inert to avoid foreign body reactions when retained in the human body for long periods of time; can be easily sterilised to prevent the introduction of infection when the mesh is implanted in the human body; and have suitably easy handling characteristics for placement in the desired location in the body.

The fine warp knit of the filaments **26** provides a surgical implant which is flexible in handling, which can be easily cut into different shapes and dimensions. As the strands **24** are formed using warp knit the possibility of fraying of the edge of the surgical implant **20** following production or cutting of the surgical implant **20** is reduced.

Other methods of reducing fraying of the filaments **24**, not arranged to form the strands using warp knit, following cutting or production of the implant are heat treatment, laser treatment or the like to seal the edges of the surgical implant.

The mesh **20** may be supplied in any shape or size and cut to the appropriate dimensions as required by the surgeon.

It can be appreciated that cutting of the mesh will produce an unfinished edge **30**. Due to the sparse nature of the strands that form the mesh and their narrow diameter this unfinished edge does not suffer from the same problems as edges of meshes of the prior art.

In other words the edge produced is not rough and jagged such that it increases the likelihood of extrusion of the edge of the mesh in situ or the chance of infection.

As discussed an advantage of the mesh of the present invention is that it allows the production of a mesh suitable for use in hernia repair which allows substantially less foreign material to be left into the body.

However, the mesh being flexible and insubstantial is less suitable for allowing easy handling of the mesh directly by a surgeon. Referring to FIGS. **8a** and **8b** the mesh described above may be treatable using an absorbable coating **32**.

The absorbable coating **32** comprises a layer of absorbable material having a thickness greater than that of the strands **22** of the mesh **20**. For example, the thickness of the layer of absorbable material may be around 1 to 2 mm. The strands **22** of the mesh **20** may be entirely embedded in the absorbable coating **32** such that the outer surface of the mesh **20** is covered entirely of the absorbable coating **32**.

In effect the entire surgical implant is encased in the absorbable coating as shown in FIG. **8b**.

Thus, the surgical implant has no gaps or holes on its surface. This has the advantage of reducing the likelihood of bacteria becoming lodged on the strands **22** of the mesh **20** before implantation of the mesh **20**. Furthermore, the absorbable coating **32** makes the mesh **20** more substantial and less flexible such that it is more easily handled by a surgeon. This is particularly useful when it is desired to place the mesh in a desired location in a conventional, open surgical procedure.

In an alternative embodiment shown in FIG. **8a** the absorbable coating **32** comprises a layer of absorbable material applied to one face **34** of the mesh **20**, such that the mesh has a first face **34** on which the absorbable material has been

applied and a second face **36** on which the absorbable material has not been applied such that the first and second faces **34** and **36** each have different characteristics.

It can also be envisaged that the surgical implant is provided with improved surgical handling qualities by a range of other methods. Such methods including, the releasable attachment of the mesh **20** to a backing strip **40**. This embodiment is shown in FIG. **8c**.

The backing strip may be formed from plastics material and is adhered to the surgical implant using releasable adhesive.

In a similar fashion to the absorbable coating the backing strip **40** causes the mesh **20** to be more substantial and less flexible such that it is more easily handled by a surgeon. Following the suitable placement of the mesh **20** the backing strip **40** can be removed from the mesh **20**, the mesh **20** being retained in the body and the backing material **40** being removed by the surgeon. Application of the backing strip **40** to the mesh **20** means the mesh **20** benefits from reduced mass but that the mesh **20** and backing strip **40** together give characteristics required for surgical handling.

In a further embodiment the filaments of the mesh may be comprised from bicomponent microfibres **50** or composite polymers **60**. These technologies provide the implant with dual phase technology.

As shown in FIG. **8d** the bicomponent microfibres **50** comprise a core **52** (cutaway section shows core region) and surface material **54**. The surface material **54** is designed such that it is absorbed by the body in a matter of hours, while the core material **52** remains in the body for a longer period to enable tissue ingrowth.

Suitable bicomponent microfibres **50** include a polypropylene non absorbable portion and a polylactic acid absorbable portion.

The surface material **54** is present during the surgical procedure when the mesh **20** is being inserted and located in the patient, and provides the mesh with characteristics desirable for surgical handling. Following a period of insertion in the body, typically a few hours, the surface material **54** is absorbed into the body leaving only the core material **52** of the filaments **26** in the body. The core material of the filament having reduced foreign mass in comparison to meshes of the prior art or the mesh **20** when it also includes the surface material **54**.

As shown in FIG. **8e** the mesh of the surgical implant may be formed composite polymers **60**. As described for the bicomponent microfibres **50**, composite polymers **60** provide the surgical implant with dual phase technology. A first face **62** of the mesh **20** thus having particular characteristics such as flexibility and elasticity, while a second face **64** of the mesh **20** provides the mesh **20** with characteristics which improved the surgical handling of the mesh **20** such as strength and robustness. The cutting of the mesh described causes an unfinished edge of the mesh to be produced. This unfinished mesh not being as likely to cause the same problems as the rough and jagged edges of the implants of the prior art, due to the fewer strands, smaller diameter filaments and treatment of the mesh with absorbable coating which protects the tissue from the mesh during the surgical procedure when damage is most likely to occur.

Referring to **9a**, a further embodiment of the mesh may comprise strands as discussed and more specifically, perimeter strands. Typically the mesh is circular or the like in shape and thus this perimeter strand can be generally referred to as a circumferential strand **70**.

In the example shown in FIG. **9a** one strand runs around the circumference of the oval shape of the mesh **20**. In another

embodiment, several circumferential strands **70** may be present, each circumferential strand **70** may extend over one side of the oval mesh **20**, i.e. around half the circumference of the mesh.

As shown in FIG. **9b** the circumferential strands **70** are arranged concentrically and each extends around the mesh **20** at a different radial location.

An outer circumferential strand **70** extending around the perimeter of the mesh **20**, and further circumferential strands **72** and **74** are arranged inwardly of the outer circumferential strand forming a perimeter spaced by a distance (a). The distance a between adjacent circumferential members **70**, **72** and **74**, can vary and in this example is 20 mm.

Transverse strands **76** extend from the centre of the oval mesh **20** to points on the perimeter of the mesh **78**. In this example, four transverse strands **76** are provided across the diameter of the mesh **20**, dividing the mesh **18** into eight angularly equal portions.

The mesh **20** of this embodiment may be formed from materials as previously described. Depending on the material chosen the mesh may be woven, knitted or extruded as one piece, or individual or groups of strands can be extruded separately and joined to one another.

Such a construction as described above provides a mesh **20** with sufficient tensile strength to repair defects causing vaginal prolapse whilst having minimal bulk. Similarly, such a construction provides a suitably flexible yet resilient mesh for handling using the surgical tools described below. Referring to FIGS. **9c** and **9d**, meshes **80**, **82** of in the shape of the outline having angled sides respectively, rather than oval, are illustrated.

These meshes have a similar structure to that described with reference to FIGS. **9a** and **b**. However, the mesh has a perimeter member **80** having angled sides. Further it may have transverse members arranged only to extend towards the perimeter of the mesh, rather than all being across the diameter of the mesh. This provides a more uniform structure. More specifically, referring to FIG. **9d** the mesh has a transverse member **84** extending along its axis of symmetry, a transverse member **86** bisecting the axis of symmetry, and four further transverse members **88** extending from the axis of symmetry to the perimeter of the mesh **90**.

In addition to the pores provided by the combination of filaments **26** which form the strands **22**, pores can be provided by rings of polypropylene positioned at the intersection of the circumferential and transverse members.

Alternatively the pores may be formed by the spacing of the transverse members, such that pores of a size 50-200 μm suitable for enabling tissue ingrowth exist between the transverse members.

To secure the mesh to a suitable location in the body a number of methods can be used. The tackiness of the absorbable coating may hold the mesh suitably until it is secured by tissue ingrowth.

Alternatively the surgical implant can have capsules **100** (not shown) of biocompatible glue for securing the mesh **20** in place. In this example, six capsules **100** comprising spheres having a diameter of 4 mm and made from a rapidly absorbable material are provided around the perimeter of the mesh **20**. On placement in the body, the capsules **100** dissolve and release a biocompatible glue contained within to secure the mesh **20** in place.

Referring to FIG. **10**, a tool **200** for inserting one of the meshes described (usually without an absorbable coating **32**) comprises two channels **202**, **204**. The channels **202**, **204** are semi-circular in cross-section and the channel **202** has a diameter slightly smaller than the diameter of channel **204**.

The channels are interconnected such that the channel **202** can be rotated inside the channel **204**. In use, the mesh **20** is rolled up and placed in the space formed by the channels **202,204** in a first position in which the open sides of the channels face one another to form a housing or tube. After insertion into the desired location, channel **204** is rotated inside the channel **202** to release the mesh **20**.

Referring to FIG. **11**, an alternative tool **210** for inserting one of the meshes described comprises an elongate housing **212** around which the mesh is rolled and secured. The tool **210** has means for trapping an edge of the mesh **20** to secure it on the housing of the tool **212**, such as a groove **214**. In use, once the mesh **20** has been rolled around the housing of the tool **210** it may be secured by a removable clip or other such retaining means (not shown). After insertion of the tool **210** into the desired location, the mesh **20** is released and the tool **210** is rotated to unfurl the mesh **20**.

Referring to FIG. **12**, another alternative tool **220** for inserting one of the meshes described above in the body comprises two arms **222** pivotally interconnected by a pivot **224**. One end of each arm **226** has means for being releasably attached to the mesh **20**. The other end of each arm **228** is operable to move the ends that may be attached to the mesh **20** toward or away from one another by rotation around the pivot **224**. When the ends of the arms **226,228** to which the mesh **20** can be attached are moved to a position in which they are close to one another, the tool **220** is substantially elongate. Furthermore, the mesh **20** is radially confined by the arms. Once the mesh **20** has been inserted into position, the arms **226,228** can be manipulated to move the ends to which the mesh **20** can be attached apart to unfurl the mesh **20** in its intended position.

Referring to FIG. **13**, another tool **230** for inserting one of the meshes described above in its desired location comprises an elongate housing **232** having a number of pairs of holes **234** spaced along its length (in this example three pairs) at the distal end of the tool **230**. The housing **232** is hollow and contains a number (in this case three) of pairs of wires **236**, made from polypropylene for example, which extend along the length of the housing **232** and out through the pairs of holes **234**. The wires **236** also protrude from the proximal end of the housing such that they can be pushed and pulled in and out of the housing **232**. The ends of the wires **236** that protrude from the holes **234** have means for releasably attaching to points near the perimeter of the mesh **20**.

In use, the wires **236** are attached to the mesh **20** and retracted by pulling them back through the housing **30** such that the mesh **20** is radially confined close to the housing **232**. Once the tool **230** has been inserted into the intended position, the wires **236** are pushed into the housing **232** and consequently out through the holes **234** to urge the mesh **20** away from the housing **232**. Thus, the mesh **20** can be unfurled in its desired location in the body.

Referring once again to FIG. **5** in order to repair a urethrocoele prolapse i.e. a defect in the area A of FIG. **5**, the surgeon first locates the defect by examining the patient in the conventional manner. The extent of the defect can then be ascertained and, if necessary, a suitable template used to estimate the shape and dimensions of a preferred surgical implant to repair the defect. A suitably shaped surgical implant can then be selected.

The meshes described above are, in this example, supplied in a single size. After examination of the patient and estimation of the desired dimensions of the preferred mesh, the surgeon cuts the mesh to the preferred size.

Where the mesh comprises a circumferential member **70** the cut made in the mesh is through the transverse members

76 just outward of the circumferential member 70 corresponding most closely with the preferred size of mesh. Thus, regardless of the size to which the mesh is to be cut, a circumferential member 70 defines the perimeter of the mesh, and the perimeter of the mesh is substantially smooth. This desirably reduces the likelihood of infection or edge erosion once the mesh is inserted in the body.

The surgeon then attaches the mesh to or inserts the mesh with one of the insertion tools described herein. For example, the mesh is rolled up and placed within the insertion tool 200 illustrated in FIG. 10, wrapped around the insertion tool 210 illustrated in FIG. 11, attached to the ends of the arms 222 of the insertion tool 220 illustrated in FIG. 12 or attached to the ends of the wires 236 of the insertion tool 230 illustrated in FIG. 13.

An incision 9 is then made in the vaginal wall 12 at the forward most portion of the vaginal wall 12 adjacent the opening of the vaginal cavity. A cutting implement (not illustrated), such as scissors or a specialised cutting tool, is/are then inserted through the incision 9 into the area A, i.e. the lower portion of the anterior vaginal wall 12. Using the cutting implement, a cut is made in the area A parallel with the surface of the vaginal wall 12. In other words, a space is opened up in the vaginal wall 12 over the area of the defect in the vaginal wall 12. The cutting implement is then withdrawn and the mesh 20 is inserted in the space defined by the cut.

Where the insertion tool 200 illustrated in FIG. 10 is used, the tool 200 is inserted into the area A and the channel 202 rotated to a position within the channel 204 to release the mesh 20. The insertion tool 200 can then be retracted and the mesh unfurls due to its inherent resilience or flat memory. Should it be required to help the mesh 20 to unfurl, or slightly re-position the mesh 20 defect 2, an elongate tool (not shown) may be inserted through the incision 9 or needles may be introduced directly through the vaginal wall 12 to manipulate the mesh 20. This procedure can be viewed laproscopically through the incision 9 if desired.

Where the insertion tool 210 illustrated in FIG. 11 is used, it is desirable for the insertion tool 210 to be inserted to one side of the space defined by the cut. The mesh 20 is then released and a needle inserted through the vaginal wall to hold the released edge of the mesh 20 in position. The tool 210 is then rolled across the space defined by the cut in an arc having a centre of rotation around the incision 9. Thus, the mesh 20 is unfurled, but no significant movement is required around the incision 9.

Where the insertion tool 220 illustrated in FIG. 12 is used, the insertion tool 220 is simply inserted through the incision 9 and opened to expand the mesh 20 into its desired location. The mesh 20 is released from the insertion tool 220 which can then be closed and withdrawn through the incision 9.

Finally, where the insertion tool 250 illustrated in FIG. 13 is used, the mesh 20 is retracted by withdrawing the wires 236 through their holes 234 and the mesh is inserted through the incision 9. Once the insertion tool 230 has been inserted into its desired location, the wires 236 are urged forward and out through the holes 234 to expand the mesh in its intended position. The wires 236 can then be released from the mesh 20, withdrawn into the housing 232 and the tool 230 withdrawn through the incision 9.

Once the mesh 20 is in place, the incision may be closed.

However, it can be desirable to secure the 20 in place, rather than rely on the mesh 20 remaining in its desired location of its own accord. In one example, sutures are therefore be placed either laproscopically through the incision 9 or directly through the vaginal wall 12 to hold the mesh 20 in place. In another example, glue capsules provided on the

mesh 20 dissolve to secure the mesh 20 to the tissue surrounding the space defined by the cut, or such capsules may be punctured by needles inserted directly through the vaginal wall 12.

The surgical implant described herein is advantageous over the meshes of the prior art in several ways.

In particular the mesh, of the present invention includes smoother edges, the polyester material of the present invention being softer than polypropylene. Further, the filaments of the present invention are narrower in diameter enabling them to be more pliable than the strands of the meshes of the prior art. This causes the edge or edges of the mesh of the present invention to have fewer jagged edges and thus be smoother than the edges of meshes or the prior art.

In addition encasement of the mesh in an absorbable coating further protects the tissue both during placement and for a period of time after placement of the surgical implant.

Dual Phase Technology™ such as encasement in an absorbable coating or as otherwise discussed herein provides the implant with good handling characteristics, further it enables the implant to be more easily cut. As described above an absorbable coating may protect the tissues around where the implant is to be located both during placement and for a period of time following placement of the implant in the tissue.

Dual Phase Technology™ may also provide the implant with memory. This memory may allow the implant to be more easily placed flat on the tissue. Further the dual phase technology such as an absorbable coating may provide the implant with mild adhesive properties or tackiness which would aid both the locating and securing of the implant in the tissue.

The surgical implant described herein thus allows tension free repair of hernias, particular vaginal prolapse, with minimum pain. This allows the procedure to be performed under local anaesthetic in an out patient or office setting.

Whilst the above embodiments of the invention have been described with reference to vaginal prolapse, the mesh and surgical tools may equally be used to repair any bodily hernia. Furthermore, whilst the above procedure has been described in relation to a urethrocoele prolapse, prolapse in other parts of the vaginal wall 12 can be treated through incisions elsewhere in the vaginal wall, or other bodily hernias through suitable incisions in the appropriate tissue.

The invention claimed is:

1. A method of providing support to a prolapsed area of a patient, the method comprising the steps of:
 - making an incision to access a prolapse selected from the group consisting of urethrocoele prolapse, cystocele prolapse, vault prolapse, uterine prolapse, enterocele prolapse, and rectocele prolapse;
 - forming a space in tissues;
 - inserting through the incision into the space in the tissues an implant comprising a mesh having a mass density of 20 g/m² or less; and
 - implanting the mesh in the area of the prolapse to provide support to a vaginal wall of the patient.
2. The method of claim 1, comprising implanting the implant in a minimally invasive surgical procedure.
3. The method of claim 1, comprising implanting the implant in a laparoscopic surgical procedure.
4. The method of claim 1, wherein implanting the mesh comprises implanting a mesh providing major spaces formed in the mesh that are configured to allow blood to pass through the implant.

19

5. The method of claim 1, wherein implanting the implant comprises implanting mesh providing pore spaces formed in the mesh that are configured to allow fibroblast growth through the mesh.

6. The method of claim 1, wherein the mesh includes biocompatible polypropylene filaments.

7. The method of claim 1, wherein the mesh includes strands and the strands are spaced apart to form major spaces of about 1 mm to about 10 mm.

8. The method of claim 7, wherein the strands are legs than about 600 μm in diameter.

9. The method of claim 7, wherein the strands are formed by monofilaments having diameters between about 0.02 mm to 0.15 mm.

20

10. The method of claim 7, wherein pores are formed within the strands, and wherein the pores are between about 50 μm and about 200 μm in diameter.

11. The method of claim 7, wherein the strands are knitted to form a warp knitted mesh.

12. The method of claim 1, wherein the mesh has isotropic or near isotropic tensile strength.

13. The method of claim 1, wherein the mesh has a diamond net pattern.

14. The method of claim 1, wherein the implant is about 1-10 cm wide.

15. The method of claim 1, wherein implanting the mesh comprises securing a portion of the mesh to the vaginal wall of the patient.

* * * * *

专利名称(译)	外科植入物		
公开(公告)号	US8100924	公开(公告)日	2012-01-24
申请号	US12/551676	申请日	2009-09-01
[标]申请(专利权)人(译)	MPATHY医疗器械		
申请(专利权)人(译)	MPATHY医疗器械有限公司		
当前申请(专利权)人(译)	COLOPLAST A / S		
[标]发明人	BROWNING JAMES		
发明人	BROWNING, JAMES		
IPC分类号	A61B17/08 A61F2/02 A61F2/00		
CPC分类号	A61F2/0063 A61F2/0036 A61F2002/0068 A61F2250/0071 A61F2002/0072 A61F2002/0081 A61F2002/0086		
优先权	2001008088 2001-03-30 GB PCT/GB2002/001234 2002-04-02 WO		
其他公开文献	US20100222794A1		
外部链接	Espacenet USPTO		

摘要(译)

提供了一种适用于治疗疝气的外科植入物。植入物包括具有50g / m²的残余最大质量密度的网。网状物包括形成空间的股线，股线包括形成孔的细丝。空间和孔的尺寸设计成使植入物的异物量最小化并促进植入物的整合。可以使用Dual Phase Technology TM来递送网状物，以便于处理，切割和放置。Dual Phase Technology TM可包括用水凝胶包封或涂覆。

